



- (51) **International Patent Classification:**
D21H 11/16 (2006.01) *D21H 15/00* (2006.01)
D21H 11/18 (2006.01)
- (21) **International Application Number:** PCT/IB2017/050913
- (22) **International Filing Date:** 17 February 2017 (17.02.2017)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
62/297,279 19 February 2016 (19.02.2016) US
- (71) **Applicant:** STORA ENSO OYJ [FI/FI]; P.O. Box 309, 00101 Helsinki (FI).
- (72) **Inventors:** HEISKANEN, Isto; Kanava-aukio 10 as 13-14, 55100 Imatra (FI). SAUKKONEN, Esa; Poronkatu 17 B2, 53850 Lappeenranta (FI).
- (74) **Agent:** KLING, Susanna; Stora Enso AB, Group IP, Box 9090, 65009 Karlstad (SE).
- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2017/141205 A1

(54) **Title:** SHEET HAVING IMPROVED DEAD-FOLD PROPERTIES

(57) **Abstract:** A sheet having dead-fold properties, wherein said sheet comprises cellulose fibers whereof at least 75%, preferably at least 90%, or more preferably at least 95% of said cellulose fibers have a fiber length of less than 1 mm, and wherein the tensile strength ratio (MD/CD) of the film is above 1.4, preferably higher than 1.6 and most preferably higher than 1.8.

SHEET HAVING IMPROVED DEAD-FOLD PROPERTIES

Technical field

The present invention relates to a thin sheet having improved dead-fold properties. The sheet may be translucent or transparent.

5

Background

At the moment, there are several applications (mostly packaging related) where packaging films needs to be converted. In many cases, these folded packaging needs to be stable and not allowed to bounce back to its original shape. This type of fold and behavior is called dead-fold. Such dead-fold behavior is required in many applications including innerliner in cigarette packages, candy twist wraps, flexible walled containers, food wraps etc.

Further, polymer films typically do not have good dead-fold properties and several attempts as described in for instance U.S pat. no. 4,786,533; EP0148567; US.Pat.no. 4,965,135 have been made to improve the dead-fold properties of these films.

For instance, for candy wraps this “dead fold” is produced by optimizing the fiber orientation in the machine direction. However, such a solution has not given a satisfying result and oftentimes dead-fold has only been achieved in one direction.

There are also other techniques to achieve or control dead-fold. For instance, for many inner liners dead fold is achieved through a metallization process, where coated paper is metallized in vacuum conditions. This is a solution that gives relatively good dead fold behavior in both directions. The technique does have some drawbacks in that in certain cases some of the metallization is not adhered perfectly to the coated paper, meaning that some metal might migrate. Due to customers’ increasing awareness of the potential negative effects of using aluminum in food packages, environmental reasons such as CO₂ footprint or recyclability, this solution is currently not growing.

Further in many cases metallized paper has been replaced with plastic

30

solutions. Another problem with metallization is cost because it is a slow process and requires often special paper grades. In the published patent application WO2015032432A1, a thin (25.5-34 g/m²) food wrap paper is disclosed with improved dead-fold stiffness, but the solution is based on a
5 surface treatment.

Consequently, there is a need to find more sustainable solutions compared to the conventional techniques. There is thus a need to find a translucent/transparent thin film or paper with high dead-fold properties, which can be manufactured in a paper machine.

10

Summary

It is an object of the present disclosure, to provide an improved dead-folded sheet, such as for instance a thin sheet of paper/film, which may be translucent or transparent.

15

The invention is defined by the appended independent claims. Embodiments are set forth in the appended dependent claims and in the following description.

20

According to a first aspect there is provided a sheet having dead-fold properties, wherein said sheet comprises cellulose fibers whereof at least 75%, preferably at least 90%, or more preferably at least 95% of said cellulose fibers have a fiber length of less than 1 mm, and wherein the tensile strength ratio (MD/CD) of the film is above 1.4, preferably higher than 1.6 and most preferably higher than 1.8.

25

The tensile strength ratio defines the fiber orientation of the sheet, and in this way, a sheet with high dead-fold stiffness in both directions of the sheet is provided. The sheet can be made with high dead-fold stiffness or dead-fold behavior without any surface treatment process such as surface sizing, impregnation or metallization or lamination. Through this sheet it is also possible to improve dead-fold properties of plastic films, when used as
30 multilayer structure with the sheet.

The sheet may be any one of thin paper substrates, films, nano-papers or similar substrates.

The remaining 0-25% of the cellulose fibers may comprise cellulose fibers having a length of > 1 mm, and wherein said longer cellulose fibers have a length of at least 2 mm, or at least 2.5 mm, or at least 3 mm.

The cellulose fibers having a length of < 1 mm may be obtained
5 through any one of a cutting and fibrillation technique or a combination thereof.

The moisture content of the sheet may be below 8 weight-%, preferably below 6 weight-%, and most preferably below 4 weight-%.

The lower the end moisture, i.e. the moisture in the end product, the
10 better dead-fold properties may be obtained.

The cellulose fibers having a fiber length of less than 1 mm may be nanofibrillated polysaccharide, wherein said nanofibrillated polysaccharide is any one of microfibrillated cellulose and nanocrystalline cellulose.

The sheet may further comprise fillers, in an amount of more than 3
15 weight-% of the weight of the sheet, preferably of more than 7 weight-% and said filler may be any one of precipitated calcium carbonate(PCC), ground calcium carbonate (GCC), kaolin, bentonite and talc or a combination or mixture thereof.

The sheet may further comprise a colorant.

20 The sheet may have a basis weight of less than 50 g/m², or preferably less than 25 g/m².

Said cellulose fibers having a length of < 1 mm may be highly refined cellulose fibers having a Schopper-Riegler (SR) value of above 70, more preferably above 90 or even above 92.

25 The sheet may be transparent or translucent.

According to a second aspect there is provided a method of manufacturing a sheet having dead-fold properties according to the first aspect, wherein said sheet comprises cellulose fibers whereof at least 75%, or preferably at least 90%, or even more preferred at least 95% of said cellulose fibers have a fiber
30 length of less than 1 mm, and wherein the tensile strength ratio (MD/CD) of the film is above 1.4, preferably higher than 1.6 and most preferably higher than 1.8, wherein said cellulose fibers having a fiber length of less than 1 mm have a Schopper-Riegler (SR) value of more than 70 in a paper making machine, wherein said method comprises the steps of; providing a

suspension comprising a mixture of cellulose fibers having a length of less than 1 mm and cellulose fibers having a length of more than 2 mm, forming a web or film of said solution, drying or dewatering said formed film or web, thereby forming said sheet having dead-fold properties.

5 The step of forming a web may be any one of providing said suspension to a wire of said paper making machine, and providing said suspension to a substrate in a cast coating operation.

The sheet may have a moisture content of less than 10%, preferably less than 8 %, or even more preferred of less than 4 % after the drying or
10 dewatering step.

The sheet may have a basis weight of less than 50 g/m², or preferably less than 25 g/m².

The method may further comprise the step of: calendaring said formed film or web, and wherein the step of calendaring is performed prior to, after or
15 simultaneously with the drying step.

According to the second aspect the method may comprise obtaining a desired fiber orientation of said sheet through any one of adjusting a jet to wire ratio, adjusting laminar shear on the wire, adjusting the wet web and/or dry web tension, creating turbulence by pulsation when forming said web or
20 film, and adjusting fiber composition of the suspension comprising cellulose fibers, or a combination thereof.

According to a third aspect there is provided a sheet having dead-fold properties obtained by the method according to the second aspect.

According to a fourth aspect there is provided a laminate comprising
25 the sheet according to the first aspect or the third aspect and at least one second layer, wherein said second layer may comprise any one of a polymer, wax and mineral.

The polymer may for instance be polyethylene (PE). According to one alternative the sheet may be cast coated directly onto a polymer layer (e.g.
30 PE) forming said laminate. Alternatively, the additional layer may be coated or laminated onto the first sheet.

According to a fifth aspect there is provided the use of a sheet according to the first or third aspect as inner liner of cigarette packaging, as candy wrap paper or as food wrap paper.

According to a sixth aspect there is provided an inner liner for a cigarette packaging which inner liner comprises the sheet according to the first or third aspect.

According to a seventh aspect there is provided an inner liner for a cigarette packaging, which inner liner is composed of the sheet according to the first and third aspect.

According to an eighth aspect there is provided a candy- or food wrap comprising or consisting of the sheet according to the first and third aspect or a laminate according to the fourth aspect.

According to a ninth aspect there is provided the use of a sheet according to the first or third aspect, or a laminate according to the fourth aspect as a blank for dead-folding applications. Such dead-fold application may include not only packaging and food applications, but also application in electronics, for screens etc.

15

Description of Embodiments

According to the invention a sheet having dead-fold properties is formed from a suspension comprising cellulose fibers. The sheet is mainly based on highly refined fibers having an Schopper Riegler (SR) value of > 70 or more preferably > 90 , and most preferably > 92 , wherein these fibers have a length of less than 1 mm. The sheet comprises at least 75 weight-% based on the total amount of fibers in the sheet of these cellulose fibers having a length of less than 1 mm. Preferably the amount of these fibers having a length of less than 1 mm is more than 80 weight-%, or more than 90 weight-%, or even more preferred more than 95 weight-%.

These cellulose fibers having a length of less than 1 mm, may be a nanofibrillated polysaccharide or nanocellulose, wherein said nanofibrillated polysaccharide or nanocellulose is any one of microfibrillated cellulose and nanocrystalline cellulose.

It has surprisingly been found that paper/film based on these highly refined and short fibers (SR > 70 or more preferably > 90 , most preferably > 92), has a tensile strength ratio (MD/CD) of more than 1.4, preferably more than 1.6

and most preferably more than 1.8 has improved dead-fold properties. The sheet may be translucent/or transparent. This means that the sheet can be made with high dead-fold stiffness or dead-fold behavior without any surface treatment process such as surface sizing, impregnation or metallization or
5 lamination.

The term "sheet" is meant to include thin paper substrates, films, nano-papers or similar substrates. By the term "sheet" is thus meant a web formed or cast coated article, such as e.g. film.

The sheet may be made in a paper making machine, such as a Fourdrinier
10 machine. The sheet may thus be made by use of wet-laid technologies, such as by using a wire or permeable carrier substrate. Alternatively, the sheet may be made by cast coating techniques, e.g. by coating a carrier substrate and thereafter removing the formed sheet/film from the carrier substrate.

The thin paper or film produced according to the invention shows further
15 features such as grease proof properties (without wax or plastic coating), gas or aroma barriers, mineral oil barriers, printable, anti-counterfeit (e.g. markers or laser marking), semi-transparent or optical effects, optical barrier e.g. UV barrier, etc.

The oxygen transmission rate (OTR) value of the sheet may preferably be
20 less than 1000 cc/m²*day at 23°C and 50 % relative humidity (RH), and more preferred less than 750 cc/m²*day at 23°C and 50 % RH, and even more preferred less than 100 cc/m²*day at 23°C and 50 % RH. One characteristic of the sheet is that it comprises low amounts of long fibers. Lower amount of coarse fibers improves dead-fold, and the amount of long or coarse fibers
25 should preferably be less than 25%, more preferably less than 15%, most preferably less than 10%. The amount of long fibers is e.g. identified by fractionation using a DDJ apparatus or e.g. by sedimentation methods. A coarse indication can also be obtained by simply calculating fibers by using a
microscope, or optical fiber analyzer.

30 By long fiber is meant e.g. Kraft fiber of hardwood or softwood, (synthetic fiber), bagasse, dissolving pulp, or including all pulps typically longer than 1 mm and having a fiber diameter > 20 μm.

The long fibers may further have a length of at least 2 mm, or at least 2.5 mm or even at least 3 mm.

The long fibers may be from softwood source, e.g. pine or spruce. The long fibers may also contribute to an improved tear strength of the sheet,
5 compared to shorter fibers. Alternatively, the long fibers may be made of hardwood, such as birch.

The orientation of the fibers in the sheet, and/or the (micro)fiber, is characterized by the sheet having a tensile strength ratio (MD/CD) of more than 1.4, preferably more than 1.6 and most preferably more than 1.8. The
10 tensile strength ratio is measured by conventional standard methods as described in EN ISO 5270, EN ISO 1924, SCAN-P 67.

The sheet preferably has a low grammage or basis weight. The basis weight is preferably below 50 g/m², and most preferably below 25 g/m².

According to one alternative the sheet may be calendered, which improves
15 dead-fold even further.

According to one alternative the sheet may comprise a colorant. The colorant may be a dye or a pigment based colorant. Said colorant may optionally be added in the wet end of the paper making process, or alternatively included during manufacturing of microfibrillated cellulose (MFC) manufacturing. The
20 colorant can also be a fluorescent or other types of "non-visible" colorants.

The total amount of cellulose fibers in the sheet may be at least 80 weight % based on the total weight of the sheet. The remaining 0-20% may comprise any conventional papermaking additives and chemicals.

A typical furnish composition used to make the sheet may include 95% MFC
25 (SR > 90), 5% kraft fiber, + process additives such as retention aids.

Alternatively, the furnish comprises 100% MFC + process additives, fillers or other performance chemicals.

Preferably the end product sheet has a moisture content of below 8% and most preferably below 4%.

30 Higher filler content improves the dead-fold. Preferably higher than 3% and most preferably higher than 7%

The sheet may be made from highly refined fibers or MFC having a Schopper-Riegler (SR) value of above 70, more preferably above 90 or even above 92. Said SR value defines the SR value measured for the pulp without

added chemicals. The final furnish, comprising further additives, may show a different SR value. The fibrillation of fibers can be measured by determining Schopper Riegler (SR) value or Canadian standard freeness (CSF). Standard methods for measuring SR value is ISO 5267-1:1999, SS-EN ISO 5267-
5 1:2000 and CSF values ISO 5267-2:2001.

The sheet is preferably a two-sidedness sheet, meaning that the top and back side properties differs e.g. with regard to concentration of short fibers or surface roughness. This has shown to have beneficial effects on the dead-fold properties. This is a feature of at least papers formed on a Fourdrinier
10 type machines where the two-sidedness is achieved automatically.

The preferred fiber orientation (i.e. the preferred tensile strength ratio) may be obtained by for instance adjusting jet to wire ratio. The adjustment of the jet-to-wire speed ratio permits to change the strength properties of the paper. The jet (speed of head box flow) to wire (speed of wire) ratio, will depend on
15 several different factors, such as the machine type, head box type, fibers used, the consistency of the fiber solution, the wire shaking and the average speed of the wire. In cast coating the speed of belt or web onto which casting is done will be one determining factor.

Another way of obtaining the preferred fiber orientation is by providing a
20 laminar shear on the wire. This may be performed by e.g. wire shaking on Fourdrinier type paper machine.

Yet another way of obtaining the preferred fiber orientation may be by adjusting and controlling the wet web tension and/or the dry web tension. The preferred fiber orientation may also be obtained by adjusting the fiber
25 composition. Adjusting the fiber composition of the furnish will affect the hydrodynamic properties and friction.

The fiber composition may be analyzed e.g. with on-line fiber analyzers, which are based on optics.

The desired fiber orientation may also be obtained by adjusting the flow
30 behavior e. g. creating turbulence by pulsation, may cause less orientation effects etc. This may be performed when forming the paper web from the head-box to the wire.

It is also possible to combine different techniques to obtain the desired fiber orientation, and thus the desired tensile strength ratio (MD/CD) of the sheet.

The fiber orientation in the sheet may be measured and characterized by different techniques.

One way is by measuring the orientation of edges of fiber segments (Erkkilä, A-L., Pakarinen, P., Odell, M., Pulp Pap. Can. 99(1):81 (1998). Other
5 techniques include image analyses of e.g. dyed or tracer fibers. The MD/CD ratio R of tensile strength and the MD/CD ratio R of elastic modulus may also be measured.

The dielectric permittivity, ultrasound or microwave transmittance to determine elastic modulus and then further the fiber orientation in the sheet.
10 It is also possible to use optical measurements, such as light diffraction to determine the fiber orientation.

Without bound to any theory, be believe that this “dead fold” phenomenon is related to the properties of individual fibers. As fibers form thigh structure with orientated micro fibrils, they are able to resist bending force very well and
15 bounce back after bending. If this this fiber structure is destroyed into individual microfibers, and then a film/paper is formed from this material, then the formed film has lost is “spring back” after folding.

Wax pouch structures additionally have stiffness and dead-fold characteristics that enable the formed, empty pouch to stay open and hold its shape as the
20 pouch is transported to filler units over long distances.

Dead-fold refers to a measure of the ability of the packaging material to retain a fold or crease. A simple test for dead-fold property may involve stamping a 180° fold in the packaging material at ambient temperature and then measuring the angle to which the fold opens thereafter. The lower or smaller
25 recovery angles are desirable because this indicates greater dead fold retention.

In the context of this application and the attached patent claims, by the term “fiber length” is meant the arithmetic average length of fiber; which can be measured e.g. according to TAPPI standard (Kajaani FS5 Optical
30 fiberanalyser, Metso Automation).

According to one alternative the sheet may form a laminate with at least one second layer. According to one alternative the sheet may be provided with the second layer being any one of a polymer layer, such a polyethylene (PE) coating layer or a wax layer. The polymer or wax layer may be provided onto

the film or substrate by any conventional means such as roll coating, spray coating, lamination and extrusion. This may be done in a separate converting step, on-line or off-line. The sheet may also be cast coated directly onto a plastic substrate, where the substrate then forms the second layer.

- 5 The thickness of the wax or polymer layer may be in the range of 5 to 30 μm , preferably around 20 μm .

By providing the above mentioned sheet with, for instance, a PE coating layer it is possible to achieve an OTR value of the laminated sheet of less than 100 $\text{cc/m}^2\cdot\text{day}$ determined at 23°C and 50 % RH.

10

Trials

- A Kraft pulp fiber was refined until Schopper Riegler value was >96 (94-100). A wet laid technique or papermaking method similar to Fourdrinier was used to form a web thereof having a grammage of ca 30 g/m^2 . Different amount of
15 hardwood pulp (birch, low SR value, below 25) was used as a long fiber fraction in the furnish. In addition to the fiber furnish, process chemical such as cationic starch (4 kg/tn), hydrophobic sizing chemicals were used (1.5 kg/tn).

- 20 The wet web was run through a press section and then dried until a moisture content of ca 6 weight-%.

A polyethylene coating layer was extruded onto the films or substrates in a separate converting step. The thickness of PE layer is about 20 μm .

25

Dead-fold measurements were made on samples (non PE coated) ($W = 55$ mm, $L = 155$ mm) by folding at distance 55 mm from edge for the side to be investigated.

- 30 Below the sample, a suction board was placed to supports the substrate during folding. The sample was folded 180 degrees on to top-side or bottom-side and then a 0.957 kg weight or 5.5 kg weight was added onto the folded sample for 5 seconds.

The angle was then measured after 1 hour. The MFC film materials described herein do not significantly straighten (e.g., to not more than about 150 degrees in maximum with 0.957 kg weight, and not more than about 170 degrees in maximum with 5.5 kg weight) after being folded.

5

Table. 1 Results of dead-fold trials

Recipe	Ref	1	2	3	Commercial cigarette inner liner	Copy paper, 80 gsm
Nanocellulose, SR 96	100%	85%	70%	50%		
Kraft Pulp, birch		15%	30%	50%		
Starch	4 kg/tn	4 kg/tn	4 kg/tn	4 kg/tn		
Hydrophobic sizing chemical	1.5 kg/tn	1.5 kg/tn	1.5 kg/tn	1.5 kg/tn		
Physical properties						
Grammage, g/m ²	29,7	31,1	30,8	30,2		
Moisture content, wt%	6,80	6,22	6,86	6,81		
Opacity C/2° +UV, Top side, %	26,6	27,7	30,8	37,7		
Opacity C/2° +UV, Bottom side, %	26,9	27,8	31,1	38,4		
Film properties						
OTR 23°C/ 50 % RH	30,4	6604	no O2 barrier	no O2 barrier		
OTR after PE Coating, 23°C/ 50 % RH	1,65	3	90,85	525		

Dead-fold, angle MD (Top- side/back-side), 0.957 kg weight, recovery angle	21/17	20/12	17/12	24/23		
Dead-fold, angle CD (Top- side/back-side), 0.957 kg weight, recovery angle	12/18	10/4	8/16	10/20		
Dead-fold, angle MD (Top- side/back-side), 5.5 kg weight, recovery angle	4/0	5/6	3/3	5/7	-/33	43/47
Dead-fold, angle CD (Top- side/back-side), 5.5 kg weight, recovery angle	2/2	2/6	2/2	6/12		22/16

In another trial, an MFC film of around 40 gsm was produced by cast coating from a suspension comprising MFC and 30% sorbitol. This film showed a recovery angle of 0 degrees.

CLAIMS

1. A sheet having dead-fold properties, wherein said sheet comprises cellulose fibers whereof at least 75%, preferably at least 90%, or more
5 preferably at least 95% of said cellulose fibers have a fiber length of less than 1 mm, and wherein the tensile strength ratio (MD/CD) of the film is above 1.4, preferably higher than 1.6 and most preferably higher than 1.8.
2. The sheet according to claim 1, wherein the sheet is any one of thin
10 paper substrates, films, nano-papers or similar substrates.
3. The sheet according to any one of the preceding claims, wherein the remaining 0-25% of the cellulose fibers in the sheet comprise cellulose fibers having a length of > 1 mm, and of at least 2 mm, or at least 2.5 mm, or
15 at least 3 mm.
4. The sheet according to any one of the preceding claims, wherein the cellulose fibers having a length of < 1 mm are obtained through any one of a cutting and fibrillation technique or a combination thereof.
20
5. The sheet according to any one of the preceding claims, wherein the moisture content of the sheet is below 8 weight-%, preferably below 6 weight-%, and most preferably below 4 weight-%.
- 25 6. The sheet according to anyone of the above claims, wherein the cellulose fibers having a fiber length of less than 1 mm is a nanofibrillated polysaccharide, wherein said nanofibrillated polysaccharide is any one of microfibrillated cellulose and nanocrystalline cellulose.
- 30 7. The sheet according to anyone of the above claims, wherein the

sheet further comprises fillers, in an amount of more than 3 wt-% of the total weight of the sheet, preferably of more than 7 wt-% of the total weight of the sheet.

5 8. The sheet according to claim 6, wherein said filler is any one of precipitated calcium carbonate (PCC), ground calcium carbonate (GCC), kaolin, bentonite and talc or a combination or mixture thereof.

9. The sheet according to anyone of the above claims, wherein the
10 sheet further comprises a colorant.

10. The sheet according to anyone of the above claims, wherein the sheet has a basis weight of less than 50 g/m², or preferably less than 25 g/m².

15 11. The sheet according to anyone of the above claims, wherein said cellulose fibers having a length of < 1 mm are highly refined cellulose fibers having a Schopper-Riegler (SR) value of above 70, more preferably above 90 or even above 92.

20 12. The sheet according to anyone of the above claims, wherein the sheet is transparent or translucent.

13. A method of manufacturing a sheet having dead-fold properties according to claims 1 to 11, wherein said sheet comprises cellulose fibers
25 whereof at least 75%, or preferably at least 90%, or even more preferred at least 95% of said cellulose fibers have a fiber length of less than 1 mm, and wherein the tensile strength ratio (MD/CD) of the film is above 1.4, preferably higher than 1.6 and most preferably higher than 1.8, wherein said cellulose fibers having a fiber length of less than 1 mm have a Schopper-Riegler (SR)

value of more than 70 in a paper making machine, wherein said method comprises the steps of:

- 5 providing a suspension comprising a mixture of cellulose fibers having a length of less than 1 mm and cellulose fibers having a length of more than 2 mm,
forming a web or film of said suspension;
drying or dewatering said formed film or web, thereby forming said sheet having dead-fold properties.

10 14. The method according to claim 13, wherein the step of forming a web is any one of providing said suspension to a wire of said paper making machine, and providing said suspension to a substrate in a cast coating operation.

15 15. The method according to claim 13 or 14, wherein said sheet has a moisture content of less than 10%, preferably less than 8 %, or even more preferred of less than 4 % after the drying or dewatering step.

20 16. The method according to any one of claims 13 to 15, wherein the sheet has a basis weight of less than 50 g/m², or preferably less than 25 g/m².

25 17. The method according to any one of claims 13 to 16 , wherein said method further comprises the step of:
calendering said formed film or web, and wherein the step of calendaring is performed prior to, after or simultaneously with the drying step.

30 18. The method according to any one of claims 13 to 17, wherein the method comprises obtaining a desired fiber orientation of said sheet through any one of adjusting a jet to wire ratio, adjusting laminar shear on the wire, adjusting the wet web and/or dry web tension, creating turbulence by

pulsation when forming said web or film, and adjusting fiber composition of the suspension comprising cellulose fibers, or a combination thereof.

19. A sheet having dead-fold properties obtained by the method
5 according to any one of claim 13 to 18.

20. A laminate comprising the sheet according to any one of claims 1
2, or 19, and at least one second layer, wherein said second layer may
comprise any one of a polymer, wax and mineral.
10

21. Use of a sheet according to anyone of claims 1 – 12, or claim 19 as
inner liner of cigarette packaging, as candy wrap paper or as food wrap
paper.

22. An inner liner for a cigarette packaging which inner liner comprises
15 the sheet according to anyone of claims 1 – 12 or claim 19, or a laminate
according to claim 20.

23. An inner liner for a cigarette packaging, which inner liner is
20 composed of the sheet according to anyone of claims 1 – 12 or claim 19, or a
laminate according to claim 20.

24. A candy- or food wrap comprising or consisting of the sheet
according to anyone of the claims 1 – 12 or claim 19, or a laminate according
25 to claim 20.

25. Use of a sheet according to any one of claims 1 to 12 or claim 19 or
a laminate according to claim 20, as a blank for dead-folding applications.

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2017/050913

A. CLASSIFICATION OF SUBJECT MATTER
INV. D21H11/16 D21H11/18 D21H15/00
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
D21H
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 965 135 A (IM JANG-HI [US] ET AL) 23 October 1990 (1990-10-23) cited in the application the whole document	1,13, 19-25
A	WO 2015/032432 A1 (MONDI AG [AT]) 12 March 2015 (2015-03-12) cited in the application the whole document	1,13, 19-25
A	EP 0 148 567 A1 (MOBIL OIL CORP [US]) 17 July 1985 (1985-07-17) cited in the application the whole document	1,13, 19-25
A	WO 2013/160553 A1 (STORA ENSO OYJ [FI]) 31 October 2013 (2013-10-31) the whole document	1-25
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---	---

Date of the actual completion of the international search 6 April 2017	Date of mailing of the international search report 18/04/2017
---	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Naeslund, Per
--	---

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2017/050913

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2014/147295 A1 (AHLSTROEM OY [FI]) 25 September 2014 (2014-09-25) abstract	1-25

A	WO 2014/071523 A1 (FPINNOVATIONS [CA]) 15 May 2014 (2014-05-15) abstract	1-25

A	WO 2014/091413 A1 (STORA ENSO OYJ [FI]) 19 June 2014 (2014-06-19) abstract	1-25

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/IB2017/050913

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4965135	A	23-10-1990	NONE
WO 2015032432	A1	12-03-2015	CN 105518214 A EP 3041990 A1 US 2016194831 A1 WO 2015032432 A1
EP 0148567	A1	17-07-1985	CA 1256230 A DE 3476670 D1 EP 0148567 A1 JP S60133040 A
WO 2013160553	A1	31-10-2013	CA 2871554 A1 CN 104302834 A EP 2841649 A1 FI 124235 B JP 2015514884 A RU 2014146502 A TW 201404972 A US 2015114581 A1 UY 34768 A WO 2013160553 A1
WO 2014147295	A1	25-09-2014	CA 2900723 A1 DK 2956582 T3 EP 2956582 A1 ES 2593680 T3 FR 3003581 A1 US 2016016717 A1 WO 2014147295 A1
WO 2014071523	A1	15-05-2014	AU 2013344245 A1 CA 2889991 A1 CN 104838050 A EP 2917390 A1 JP 2016503465 A KR 20150082523 A RU 2015121724 A US 2015275433 A1 WO 2014071523 A1
WO 2014091413	A1	19-06-2014	CN 104995353 A EP 2931971 A1 SE 1251427 A1 US 2015315747 A1 WO 2014091413 A1