

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 January 2004 (29.01.2004)

PCT

(10) International Publication Number
WO 2004/009694 A1

(51) International Patent Classification⁷: **C08K 5/3492**,
5/3437, 5/3435

(21) International Application Number:
PCT/US2003/022672

(22) International Filing Date: 22 July 2003 (22.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/397,026 22 July 2002 (22.07.2002) US
10/370,488 24 February 2003 (24.02.2003) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant: **GENERAL CABLE TECHNOLOGIES CORPORATION** [US/US]; 4 Tesseneer Drive, Highland Heights, KY 41076 (US).

(72) Inventor: **EASTER, Mark**; 4020 North Pennsylvania, Indianapolis, IN 46205 (US).

(74) Agents: **GREENBAUM, Michael, C.** et al.; Blank Rome LLP, 600 New Hampshire Avenue, NW, Suite 1100, Washington, DC 20037 (US).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: IMPROVED INSULATION COMPOSITIONS CONTAINING METALLOCENE POLYMERS

(57) Abstract: Novel antioxidant systems for metallocene based filled cable insulation are disclosed. These antioxidant systems provide excellent protection against thermal degradation, better cure state and reduced dissipation factor after prolonged heat exposure. The antioxidants consist of mixtures of hindered amine light stabilizers or sterically hindered amine light stabilizers and amine antioxidants.

WO 2004/009694 A1

IMPROVED INSULATION COMPOSITIONS CONTAINING METALLOCENE POLYMERS

FIELD OF THE INVENTION

5 The invention relates to insulation compositions for electric power cables having a base polymer comprising at least one metallocene polymer, a filler; and an additive comprising a blend of an amine antioxidant, and a hindered amine light stabilizer, or a sterically hindered amine light stabilizer, or 2,5-Di(tert-amyl)hydroquinone (TAHQ) or mixtures of said stabilizers and TAHQ.

10 BACKGROUND OF THE INVENTION

Typical power cables generally have one or more conductors in a core that is surrounded by several layers that can include: a first polymeric semiconducting shield layer, a polymeric insulating layer, a second polymeric semiconducting shield layer, a metallic tape shield and a polymeric jacket.

15 Polymeric materials have been utilized in the past as electrical insulating and semiconducting shield materials for power cables. In services or products requiring long-term performance of an electrical cable, such polymeric materials, in addition to having suitable dielectric properties, must be durable. For example, polymeric insulation utilized in building wire, electrical motor or machinery power wires, or underground power transmitting cables,
20 must be durable for safety and economic necessities and practicalities.

One major type of failure that polymeric power cable insulation can undergo is the phenomenon known as treeing. Treeing generally progresses through a dielectric section under electrical stress so that, if visible, its path looks something like a tree. Treeing may occur and progress slowly by periodic partial discharge. It may also occur slowly in the
25 presence of moisture without any partial discharge, or it may occur rapidly as the result of an

impulse voltage. Trees may form at the site of a high electrical stress such as contaminants or voids in the body of the insulation-semiconductive screen interface. In solid organic dielectrics, treeing is the most likely mechanism of electrical failures, which do not occur catastrophically, but rather appear to be the result of a more lengthy process. In the past, extending the service life of polymeric insulation has been achieved by modifying the polymeric materials by blending, grafting, or copolymerization of silane-based molecules or other additives so that either trees are initiated only at higher voltages than usual or grow more slowly once initiated.

There are two kinds of treeing known as electrical treeing and water treeing. Electrical treeing results from internal electrical discharges that decompose the dielectric. High voltage impulses can produce electrical trees. The damage which results from the application of moderate alternating current voltages to the electrode/insulation interfaces, which can contain imperfections, is commercially significant. In this case, very high, localized stress gradients can exist and with sufficient time can lead to initiation and growth of trees. An example of this is a high voltage power cable or connector with a rough interface between the conductor or conductor shield and the primary insulator. The failure mechanism involves actual breakdown of the modular structure of the dielectric material, perhaps by electron bombardment. In the past much of the art has been concerned with the inhibition of electrical trees.

In contrast to electrical treeing, which results from internal electrical discharges that decompose the dielectric, water treeing is the deterioration of a solid dielectric material, which is simultaneously exposed to liquid or vapor and an electric field. Buried power cables are especially vulnerable to electrical treeing. Water trees initiate from sites of high electrical stress such as rough interfaces, protruding conductive points, voids, or imbedded contaminants, but at a lower voltages than that required for electrical trees. In contrast to

electrical trees, water trees have the following distinguishing characteristics; (a) the presence of water is essential for their growth; (b) no partial discharge is normally detected during their growth; (c) they can grow for years before reaching a size that may contribute to a breakdown; (d) although slow growing, they are initiated and grow in much lower electrical fields than those required for the development of electrical trees.

Electrical insulation applications are generally divided into low voltage insulation (less than 1 K volts), medium voltage insulation (ranging from 1 K volts to 35 K volts), and high voltage insulation (above 35 K volts). In low to medium voltage applications, for example, electrical cables and applications in the automotive industry, electrical treeing is generally not a pervasive problem and is far less common than water treeing, which frequently is a problem. For medium-voltage applications, the most common polymeric insulators are made from either polyethylene homopolymers or ethylene-propylene elastomers, otherwise known as ethylene-propylene-rubber (EPR) or ethylene-propylene-diene ter-polymer (EPDM) .

Polyethylene is generally used neat (without a filler) as an electrical insulation material. Polyethylenes have very good dielectric properties, especially dielectric constants and power factors. The dielectric constant of polyethylene is in the range of about 2.2 to 2.3. The power factor, which is a function of electrical energy dissipated and lost should be as low as possible, is around 0.0002 at room temperature, a very desirable value. The mechanical properties of polyethylene are also adequate for utilization in many applications as medium-voltage insulation. They are prone to deformation at high temperatures. However, polyethylene homopolymers are very prone to water treeing, especially toward the upper end of the medium-voltage range.

There have been attempts to make polyethylene-based polymers that would have long-term electrical stability. For example, when dicumyl peroxide is used as a crosslinking agent for polyethylene, the peroxide residue functions as a tree inhibitor for some time after curing. However, these residues are eventually lost at most temperatures where electrical power cable are used. U.S. Pat. No. 4,144,202 issued Mar. 13, 1979 to Ashcraft, et al. discloses the incorporation into polyethylenes of at least one epoxy containing organo-silane as a treeing inhibitor. However, a need still exists for a polymeric insulator having improved treeing resistance over such silane containing polyethylenes.

Unlike polyethylene, which can be utilized neat, the other common medium-voltage insulator, EPR, typically contains a high level of filler in order to resist treeing. When utilized as a medium-voltage insulator, EPR will generally contain about 20 to about 50 weight percent filler, most likely, calcined clay, and preferably crosslinked with peroxides. The presence of the filler gives EPR a high resistance against the propagation of trees. EPR also has mechanical properties Superior to polyethylene at elevated temperatures.

Unfortunately, while the fillers utilized in EPR may help prevent treeing, they will generally have poor dielectric properties, i.e. a poor dielectric constant and a poor power factor. The dielectric constant of filled EPR is in the range of about 2.3 to about 2.8. Its power factor is on the order of about 0.002 to about 0.005 at room temperature, which is about an order of magnitude worse than polyethylene.

Thus, both polyethylenes and EPR have serious limitations. Polyethylene although has good electric properties, it has poor water tree resistance. While filled EPR has good treeing resistance and good mechanical properties, it has poorer dielectric properties.

Power factor increases with temperature. In addition it may continue to increase with time at high temperatures. Underwriters Labs MV105 rated cables must be able to survive 21 days at an emergency circuit overload temperature of 140 C. Filled EPR insulations are

usually used in these applications.

Another class of polymers exists today and are described in EP-A-0 341 644 published Nov. 15, 1989. This reference describes linear polyethylenes produced by a traditional Ziegler-Natta catalyst systems. They generally have a broad molecular weight distribution similar to linear low-density polyethylene and at low enough densities can show better tree retardancy. However, these linear-type polymers in the wire and cable industry have poor melt temperature characteristics and poor processibility. In order to achieve a good mix in an extruder, linear polymers must be processed at a temperature at which traditionally used peroxides prematurely crosslink the polymers, a phenomenon commonly referred to as scorch. If the processing temperature is held low enough to avoid scorch, incomplete melting occurs because of the higher melting species in linear polymers having a broad molecular weight distribution. This phenomenon results in poor mixing, surging extruder pressures, and other poor results.

Newer metallocene polyethylene co-polymers are more flexible and have been proposed for use as cable insulation but they too have generally poorer thermal stability, and may deform when exposed to high heat. They also suffer from higher electrical loss with AC current which may be measured in the form of a dissipation factor called tan delta.

1,2-dihydro-2,2,4 trimethylquinolines or "TMQ"s are the universally preferred antioxidants for filled LV, MV or HV cable insulations because of their good thermal degradation protection, low interference with the peroxide cure systems widely used and low cost. TMQs are not used in polyethylene insulation because of their staining nature.

Hindered amine light stabilizers or "HAL"s are primarily used in clear plastic film, sheets or coatings to prevent degradation by light. HALs are used in unfilled polyethylene insulations. They are thought to prevent degradation caused by light emitted by tiny

electrical discharges. US Patent No. 5,719,218 discloses an optically transparent polyethylene insulation formulation with a HALs where it is stated that the HALs are useful for the prevention of degradation of the insulation by water trees.

EPDM type insulations have excellent resistance to water trees and have been used for over 30 years in AC cable insulations exposed to wet environments. They are also proven to perform in high temperature service in urban power networks. Filled insulations are opaque so they do not suffer from degradation caused by light emitted by tiny electrical discharges.

Metallocene polymers have shown much higher resistance to water trees than polyethylene but are not widely used as medium or high voltage AC cable insulation due to their higher AC loss and generally poorer thermal degradation resistance and higher cost than polyethylene. Metallocene polymers do have good acceptance of fillers and can be used for flexible, low temperature, low voltage or DC insulations

Therefore, a need exists in the electrical cable industry for an additive system that improves the performance of metallocene polymers as a filled insulation composition

SUMMARY OF THE INVENTION

The invention provides an additive system that improves the performance of metallocene polymers as a filled insulation composition.

Specifically, the invention provides an insulation composition for electric cable comprising; (a) a base polymer comprising at least one metallocene polymer; (b) a filler; and (c) an additive comprising a blend of; (i) an amine antioxidant, and (ii) a hindered amine light

stabilizer, or a sterically hindered amine light stabilizer, or 2,5-Di(tert-amyl)hydroquinone (TAHQ) or mixtures of said stabilizers and TAHQ.

In another embodiment of the invention, the insulation composition base polymer further comprises at least one non-metallocene polymer and can have

5

In other embodiments of the invention, the base polymer may comprise 20% to 99% by weight metallocene polymer and 1% to 80% by weight non-metallocene polymer, the additive may be from about 0.5% to about 2.5% by weight of said composition.

10 DETAILED DESCRIPTION OF THE INVENTION

The invention particularly relates to polymeric products utilizing polyolefins, which products have a unique combination of good mechanical properties, good dielectric properties, and good water treeing resistance, as well as lower melt temperature for processability with peroxide-containing compounds. The products are therefore extremely
15 useful as insulation compositions for electric power cables.

The polymers utilized in the jacketing (protective), insulating, conducting or semiconducting layers of the inventive cables of the invention may be made by any suitable process which allows for the yield of the desired polymer with the desired physical strength properties, electrical properties, tree retardancy, and melt temperature for processability.

20 The base polymer in accordance with the invention comprises at least one metallocene polymer, and also may include, if desired non-metallocene polymers

Metallocene polymers are produced using a class of highly active olefin catalysts known as metallocenes, which for the purposes of this application are generally defined to

contain one or more cyclopentadienyl moiety. The manufacture of metallocene polymers is described in U.S. Patent No. 6,270,856 to Hendewerk, et al, the disclosure of which is incorporated by reference in its entirety.

Metallocenes are well known especially in the preparation of polyethylene and
5 copolyethylene-alpha-olefins. These catalysts, particularly those based on group IV transition metals, zirconium, titanium and hafnium, show extremely high activity in ethylene polymerization. Various forms of the catalyst system of the metallocene type may be used for polymerization to prepare the polymers used in this invention, including but not limited to those of the homogeneous, supported catalyst type, wherein the catalyst and cocatalyst are
10 together supported or reacted together onto an inert support for polymerization by a gas phase process, high pressure process, or a slurry, solution polymerization process. The metallocene catalysts are also highly flexible in that, by manipulation of the catalyst composition and reaction conditions, they can be made to provide polyolefins with controllable molecular weights from as low as about 200 (useful in applications such as lube-oil additives) to about 1
15 million or higher, as for example in ultra-high molecular weight linear polyethylene. At the same time, the MWD of the polymers can be controlled from extremely narrow (as in a polydispersity of about 2), to broad (as in a polydispersity of about 8).

Exemplary of the development of these metallocene catalysts for the polymerization
20 of ethylene are U.S. Pat. No. 4,937,299 and EP-A-0 129 368 to Ewen, et al., U.S. Pat. No. 4,808,561 to Welborn, Jr., and U.S. Pat. No. 4,814,310 to Chang, all hereby are fully incorporated by reference. Among other things, Ewen, et al. teaches that the structure of the metallocene catalyst includes an alumoxane, formed when water reacts with trialkyl aluminum. The alumoxane complexes with the metallocene compound to form the catalyst.
25 Welborn, Jr. teaches a method of polymerization of ethylene with alpha-olefins and/or

diolefins. Chang teaches a method of making a metallocene alumoxane catalyst system utilizing the absorbed water in a silica gel catalyst support. Specific methods for making ethylene/alpha-olefin copolymers, and ethylene/alpha-olefin/diene terpolymers are taught in U.S. Pat. Nos. 4,871,705 (issued Oct. 3, 1989) and 5,001,205 (issued Mar. 19, 1991) to Hoel,
5 et al., and in EP-A-0 347 129 published Apr. 8, 1992, respectively, all of which are hereby fully incorporated by reference.

Other cocatalysts may be used with metallocenes, such as trialkylaluminum compounds or ionizing ionic activators, such as tri(n-butyl)ammonium
10 tetra(pentafluorophenyl) boron, which ionize the neutral metallocene compound. Such ionizing compounds may contain an active proton or some other cation such as carbonium, which ionizing the metallocene on contact, forms a metallocene cation associated with (but not coordinated or only loosely coordinated with) the remaining ion of the ionizing ionic compound. Such compounds are described in EP-A-0 277 003 and EP-A-0 277 004, both
15 published Aug. 3, 1988, and are herein fully incorporated by reference. Also, the polymers useful in this invention can be a metallocene catalyst component that is a monocyclopentadienyl compound, which is activated by either an alumoxane or an ionic activator to form an active polymerization catalyst system. Catalyst systems of this type are shown by PCT International Publication WO92/00333, published Jan. 9, 1992, U.S. Pat. Nos.
20 5,096,867 and 5,055,438, EP-A-0 420 436 and WO91/04257 all of which are fully incorporated herein by reference. The catalyst systems described above may be optionally prepolymerized or used in conjunction with an additive component to enhance catalytic productivity.

25 As previously stated metallocene catalysts are particularly attractive in making

tailored ultra-uniform and super-random specialty copolymers. For example, if a lower density copolymer is being made with a metallocene catalyst such as very low density polyethylene, (VLDPE), an ultra-uniform and super random copolymerization will occur, as contrasted to the polymer produced by copolymerization using a conventional Ziegler-Natta catalyst. In view of the ongoing need for electrical cables having improved mechanical and dielectric properties and improved water treeing resistance, as well as the need to process these materials at temperatures low enough to allow scorch free processing, it would be desirable to provide products utilizing the high quality characteristics of polyolefins prepared with metallocene catalysts.

The base polymer utilized in the insulation composition for electric cable in accordance with the invention may also be selected from the group of polymers consisting of ethylene polymerized with at least one comonomer selected from the group consisting of C₃ to C₂₀ alpha-olefins and C₃ to C₂₀ polyenes. Generally, the alpha-olefins suitable for use in the invention contain in the range of about 3 to about 20 carbon atoms. Preferably, the alpha-olefins contain in the range of about 3 to about 16 carbon atoms, most preferably in the range of about 3 to about 8 carbon atoms. Illustrative non-limiting examples of such alpha-olefins are propylene, 1-butene, 1-pentene, 1-hexene, 1-octene and 1-dodecene. Preferably, the polymers utilized in the cables of the invention are either ethylene/alpha-olefin copolymers or ethylene/alpha-olefin/diene terpolymers. The polyene utilized in the invention generally has about 3 to about 20 carbon atoms. Preferably, the polyene has in the range of about 4 to about 20 carbon atoms, most preferably in the range of about 4 to about 15 carbon atoms. Preferably, the polyene is a diene, which can be a straight chain, branched chain, or cyclic hydrocarbon diene. Most preferably, the diene is a non conjugated diene. Examples of suitable dienes are straight chain acyclic dienes such as: 1,3-butadiene, 1,4-hexadiene and

1,6-octadiene; branched chain acyclic dienes such as: 5-methyl-1,4-hexadiene, 3,7-dimethyl-1,6-octadiene, 3,7 -dimethyl-1,7-octadiene and mixed isomers of dihydro myricene and dihydroocinene; single ring alicyclic dienes such as: 1,3-cyclopentadiene, 1,4-cyclohexadiene, 1,5-cyclooctadiene and 1,5-cyclododecadiene; and multi-ring alicyclic fused and bridged ring dienes such as: tetrahydroindene, methyl tetrahydroindene, dicyclopentadiene, bicyclo-(2,2,1)-hepta-2-5-diene; alkenyl, alkylidene, cycloalkenyl and cycloalkylidene norbornenes such as 5-methylene-2-norbornene (MNB), 5-propenyl-2-norbornene, 5-isopropylidene-2-norbornene, 5-(4-cyclopentenyl)-2-norbornene, 5-cyclohexylidene-2-norbornene, 5-vinyl-2-norbornene and norbornene. Of the dienes typically used to prepare EPR's, the particularly preferred dienes are 1,4-hexadiene, 5-ethylidene-2-norbornene, 5-vinylidene-2-norbornene, 5-methylene-2-norbornene and dicyclopentadiene. The especially preferred dienes are 5-ethylidene-2-norbornene and 1,4-hexadiene.

In preferred embodiments of the invention, the base polymer comprises metallocene EP which is an EPR or EPDM polymer prepared with metallocene catalysts.

As an additional polymer in the base polymer composition, a non-metallocene base polymer may be used having the structural formula of any of the polyolefins or polyolefin copolymers described above. Ethylene-propylene rubber (EPR), polyethylene, polypropylene or ethylene vinyl acetates having a range of vinyl acetate content of from about 20% to about 40% may all be used in combination with the metallocene polymers in the base polymer.

In embodiments of the invention, the insulation composition base polymer comprises 20% to 99% by weight metallocene polymer and 1% to 80% by weight non-metallocene polymer. The additive is present in amounts from about 0.5% to about 2.5% by weight of said composition, preferably from about 1.0% to about 1.5% by weight of said composition. In preferred embodiments, the additive has a weight/weight ratio of HALS/TMQ of from

about 90/10 to about 10/90, more preferably a weight/weight ratio of HALS/TMQ of from about 75/25 to about 25/75.

As described above, the additive in accordance with the invention comprises a blend of; (i) an amine antioxidant, and (ii) a hindered amine light stabilizer, or a sterically hindered amine light stabilizer, or 2,5-Di(tert-amyl)hydroquinone (TAHQ) or mixtures of said stabilizers and TAHQ.

Any suitable hindered amine light stabilizers may be used in accordance with the invention. Chimassorb 944 LD is preferred.

Any suitable sterically hindered amine light stabilizers may be used in accordance with the invention are. Tinuvin 622 LD is preferred.

The insulating composition the invention is filled. An illustrative example of a suitable filler is clay, talc (aluminum silicate or magnesium silicate), magnesium aluminum silicate, magnesium calcium silicate, calcium carbonate, magnesium calcium carbonate, silica, ATH, magnesium hydroxide, sodium borate, calcium borate, kaolin clay, glass fibers, glass particles, or mixtures thereof. In accordance with the invention, the weight percent range for fillers is from about 10 percent to about 60 percent, preferably from about 20 to about 50 weight percent filler.

Other additives commonly employed in the polyolefin compositions utilized in the invention can include, for example, crosslinking agents, antioxidants, processing aids, pigments, dyes, colorants, metal deactivators, oil extenders, stabilizers, and lubricants.

All of the components of the compositions utilized in the invention are usually blended or compounded together prior to their introduction into an extrusion device from which they are to be extruded onto an electrical conductor. The polymer and the other additives and fillers may be blended together by any of the techniques used in the art to blend and compound such mixtures to homogeneous masses. For instance, the components may be

fluxed on a variety of apparatus including multi-roll mills, screw mills, continuous mixers, compounding extruders and Banbury mixers.

After the various components of the composition are uniformly admixed and blended together, they are further processed to fabricate the cables of the invention. Prior art methods for fabricating polymer insulated cable and wire are well known, and fabrication of the cable of the invention may generally be accomplished any of the various extrusion methods.

In a typical extrusion method, an optionally heated conducting core to be coated is pulled through a heated extrusion die, generally a cross-head die, in which a layer of melted polymer is applied to the conducting core. Upon exiting the die, the conducting core with the applied polymer layer is passed through a heated vulcanizing section, or continuous vulcanizing section and then a cooling section, generally an elongated cooling bath, to cool. Multiple polymer layers may be applied by consecutive extrusion steps in which an additional layer is added in each step, or with the proper type of die, multiple polymer layers may be applied simultaneously.

The conductor of the invention may generally comprise any suitable electrically conducting material, although generally electrically conducting metals are utilized. Preferably, the metals utilized are copper or aluminum. In power transmission, aluminum conductor/steel reinforcement (ACSR) cable, aluminum conductor/aluminum reinforcement (ACAR) cable, or aluminum cable is generally preferred.

EXAMPLES

The samples in the tables were mixed in a 3.17 liter banbury at 70-75 RPM. Batch size was 2300g - 2500g. Half of the polymer was added first. After the polymer fluxed, the clays, antioxidants, pigments, etc. were added. The remaining polymer(s) were added next.

After material fluxed the wax was added. The material was removed from the banbury when the temperature reaches 275°F. Total mix time was 4-8 minutes.

For the 2nd pass Banbury was at 50-60 RPM. Half of the material from 1st pass was added, after it fluxed the peroxide was added. Then the rest of the material was added. The material was removed from the banbury when the temperature reached 230°F. Total mix time was 1.5-5 minutes.

Samples were pressed to 45 mill cured slab at 350 degrees F for 20 minutes.

Samples were tested for Dissipation factor with a Tettex 2818 dissipation factor test set connected to a Tettex 2914 precision solids dielectric cell as follows

1. Degas Slabs overnight in Vacuum Oven @ 70°C
2. Measure Unaged SIC/TD @ 130°C
3. Age slabs 14 days @ 140°C
4. Measure Aged SIC/TD @ 130°C

Tensile properties were tested according to ASTM D412

Mh was tested on an Alfa Technologies MDR 2000 with ½ degree arc and scorch was tested on an Alfa Technologies Mooney 2000.

The following materials were used:

Antioxidants and HALS

5 Agerite TMQ/, Polymerized 1,2-dihydro-2,2,4-trimethylquinoline, Antioxidant, R.T. Vanderbilt Company, Inc., Norwalk, CT

10 Santovar TAHQ, 2,5-Di(tert-amyl)hydroquinone, A, Flexsys Amerikca L.P., Akron, OH

Chimassorb 81, 2-Hydroxy-4-n-octoxybenzophenone, Hindered Amine Light Stabilizer, Ciba Specialty Chemicals Corp., Tarrytown, NY

15 Chimassorb 944 LD, Poly[[6-[(1,1,3,3-tetramethylbutyl)amino]-1,3,5-triazine-2,4-diyl] Light Stabilizer, Ciba Specialty Chemicals Corp., Tarrytown, NY

20 Tinuvin 622 LD, Dimethyl succinate polymer w/ 4-hydroxy-2,2,6,6,-tertramethyl-1-piperidineethanol, Stearically Hindered Amine Light Stabilizer, Ciba Specialty Chemicals Corp., Tarrytown, NY

Tinuvin 783 FDL, 50% by wt Tinuvin 622 and 50% by wt Chimassorb 944, Light Stabilizer, Ciba Specialty Chemicals Corp., Tarrytown, NY

25 Irganox 1035, Thiodiethylene bis(3,5-di-(tert)-butyl-4-hydroxyhydrocinnamate, Antioxidant, Ciba Specialty Chemicals Corp., Tarrytown, NY

Naugard 76, Octadecyl,3,5,-di-tert-butyl-4-hydroxyhydrocinnamate, Antioxidant, Uniroyal Chemical Company, Inc., Middlebury, CT

30 Vanox AM, 2-Propanone, Antioxidant, R.T. Vanderbilt Company, Inc., Norwalk, CT

Vanox DSTDP, Distearyl thiodipropionate, Secondary Antioxidant, R.T. Vanderbilt Company, Inc., Norwalk, CT

35 Vanox ZMTI, 2H-Benzimidazole-2-thione,1,3-dihydro-4(or 5)-methyl-, Antioxidant, R.T. Vanderbilt Company, Inc., Norwalk, CT

Polymers

40 Vistalon , Ethylene Propylene Diene Rubber, Polymer, .86 g/ml, ExxonMobil Chemical Company, Houston, TX

Engage 8200, Copolymer of Ethylene and Octene-1, Polymer, .87 g/ml, Dupont Dow Elastomers L. L. C., Wilmington, DE

Exact 4006, Ethylene-Olefin Copolymer, Polymer, .9 g/ml, ExxonMobil Chemical Company, Houston, TX

45 LDPE, Low-density Polyethylene, Polymer, .92 g/ml, Equistar Chemicals, LP, Houston , TX

Filler

Polyfil, Chemically Treated Anhydrous Aluminum Silicate, Filler, Huber Engineered Materials, Macon, GA

5 Minor Ingredients

Red Lead, Lead(II,IV)-oxide, Activator, Hammond Lead Products, Hammond, Indiana

Recco 140, Paraffin Wax, Processing Aid, R.E. Carroll Inc., Trenton, New Jersey

10

(Silane) A172 - 50G, 50% Vinyl - tris (2 - methoxyethoxy) silane in a 50% elastomeric (EPDM), Coupling Agent, UA Rubber Speciality Chemical Sdn. Bhd., Bukit Mertajam. Malaysia

15

Zinc Oxide, Activator, U.S. Zinc Corp., Chicago, IL

DI-Cup, Dicumyl Peroxide, Cross-Linker, Hercules Incorporated, Wilmington, DE

ANTIOXIDANT STUDY

5

COMPARATIVE EXAMPLES

	A	B	C	D	E	F
Vistalon EPDM	51					
Engage 8200		51	51	51	51	51
Exact 4006						
LPDE	10	10	10	10	10	10
A172 treated clay filler	28.9	28.9	28.9	28.9	28.9	28.9
Paraffin Wax	2.8	2.8	2.8	2.8	2.8	2.8
red lead	3	3	3	3	3	3
(A172) silane	0.5	0.5	0.5	0.5	0.5	0.5
Zinc oxide	2.8	2.8	2.8	2.8	2.8	2.8
Agerite TMQ	1	1	0.75			
DSTDP			.25		.25	
naugard 76				1		
vanox ZMTI						
Irganox 1035					0.75	
Chimassorb 944						
Tinuvin 783FDL						
Tinuvin 622LD						
Vanox ZMTI						0.25
Santovar TAHQ						
Vanox AM						0.75
Dicup	1.5	1.5	1.5	1.5	1.5	1.5
TOTAL	101.5	101.5	101.5	101.5	101.5	101.5

Tan Delta at 130 C %	1.3	3.6	3.6	NA	NA	3.8
----------------------	-----	-----	-----	----	----	-----

Tan Delta 130C %						
aged 14d 140C	1.2	10	11.3			12

Tan Delta 130C %						
aged 21d 140C	1.1	8.7	10.5			12.4

MDR reports min. to min.		6 Min @ 400°F				
MH	14.6	6.6	6.54	10.35	10.2	7.65
ML	0.83	0.22	0.21	0.23	0.23	0.2
MOONEY SCORCH 130°C/30 min						
SCORCH TIME @ Ts 5	30	30	30	30	30	40
INITIAL						
TENSILE (PSI)	1791	1812	1760	1903	1909	1850
% ELONGATION	315	471	525	490	477	515
AGED 21 Days 140°C						
% TENS RETAINED	91	91	92	0	4	88
% ELONG RETAINED	92	105	98	0	1	94
AGED 21 Days 150°C						
% TENS RETAINED	67	32	71	0	0	58
% ELONG RETAINED	70	7	67	0	0	41

ANTIOXIDANT STUDY

Invention Examples 1-8 According to Invention and
Comparative Example G

	1	2	3	4	5	G	6	7	8
Vistalon EPDM									
Engage 8200	51	51	51	51	51				
Exact 4006						51	51	51	51
LPDE	10	10	10	10	10	10	10	10	10
A172 treated clay filler	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9
Paraffin Wax	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8
red lead	3	3	3	3	3	3	3	3	3
(A172) silane	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Zinc oxide	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8
Agerite TMQ		0.5	0.5	0.75	0.75	1	0.75		0.7
DSTDP									
naugard 76									
vanox ZMTI									
Irganox 1035									
Chimassorb 944	1			0.25				1	0.3

Tinuvin 783FDL			0.5						
Tinuvin 622LD		0.5							
Vanox ZMTI									
Santovar TAHQ					0.25		0.25		
Vanox AM									
Dicup	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
TOTAL	101.5	101.5	101.5	101.5	101.5	101.5	101.5	101.5	101.5

Tan Delta at 130 C %	2.5	1.9	2.27	3.7	3	1.25	1.34	1.29	1.3
----------------------	-----	-----	------	-----	---	------	------	------	-----

Tan Delta 130C %									
aged 14d 140C	4.7	4.6	6.9	9.36	10.5	1.3	0.93	0.92	0.92
Tan Delta 130C %									
aged 21d 140C	5.1	5.5	6.6	9.5	12.9	1.3	0.9	0.85	0.84

MDR reports min. to min.

MH	6.77	9.57	8.85	6.64	7.05	10.7	11.26	12.8	11
ML	0.24	0.3	0.27	0.2	0.17	0.13	0.11	0.16	0.14

MOONEY SCORCH
130°C/30 min

SCORCH TIME @ Ts 5	20.4	28.8	25	30	40	28.5	30	22	30
--------------------	------	------	----	----	----	------	----	----	----

INITIAL

TENSILE (PSI)	1807	1883	1876	1747	1834	1995	1987	2121	2005
% ELONGATION	555	492	493	510	521	332	471	532	501

AGED 21 Days
140°C

% TENS RETAINED	88	93	94	94	96	89	92	77	92
% ELONG RETAINED	81	103	98	99	99	97	96	72	99

AGED 21 Days
150°C

% TENS RETAINED	53	84	79	81	76	70.9	38.7	43	68
% ELONG RETAINED	40	79	86	85	83	70	14	32	93

The antioxidant systems of the invention provide good protection against thermal degradation, better cure state and reduced dissipation factor after prolonged heat exposure in
5 filled metallocene AC insulations.

Lettered examples are comparative examples and numbered examples are examples in accordance with the invention.

10 Example A shows the good thermal and electrical properties of a traditional Zeigler-Natta EPR rubber formulation. Example B shows the poor performance of a metallocene polymer in the same formulation. Examples C – F show poor performance with other known antioxidant systems. Embodiments of the invention 1 – 3 show the greatly improved thermal properties and dramatically improved dissipation factor after aging. Embodiments 4 and 5 do
15 not show improved electrical properties but do show the greatly improved thermal properties. In fact, Embodiments 2 – 5 show superior thermal properties to Example A. Embodiments 2,3 and 5 show increased state of cure as compared to Example B

Dissipation factors are general higher here because the Engage 8200 was not electrical grade

Example G shows a different metallocene polymer that has better thermal and
20 electrical properties but still shows electrical improvement with the antioxidant systems of the invention. Embodiment 8 shows improved thermal properties at 150 C and Embodiments 6,7, and 8 show higher cure state

While the present invention has been described and illustrated by reference to particular embodiments thereof, it will be appreciated by those of ordinary skill in the art that
25 the invention lends itself to variations not necessarily illustrated herein.

For this reason, then, reference should be made solely to the appended claims for the purposes of determining the true scope of this invention.

What is claimed is:

1. An insulation composition for electric cable comprising:

(a) a base polymer comprising at least one metallocene polymer;

(b) a filler; and

5 (c) an additive comprising a blend of;

(i) an amine antioxidant, and

(ii) a hindered amine light stabilizer, or

a sterically hindered amine light stabilizer, or

2,5-Di(tert-amyl)hydroquinone (TAHQ) or mixtures of

10 said stabilizers and TAHQ.

2. An insulation composition according to claim 1 wherein said base polymer further comprises at least one non-metallocene polymer.

15 3. An insulation composition according to claim 2 wherein said base polymer comprises 20% to 99% by weight metallocene polymer and 1% to 80% by weight non-metallocene polymer.

4. An insulation composition according to claim 1 wherein said at least one
20 metallocene polymer is metallocene EP.

5. An insulation composition according to claim 1 wherein said additive is from about 0.5% to about 2.5% by weight of said composition.

6. An insulation composition according to claim 1 wherein said additive is from about 1.0% to about 1.5% by weight of said composition.

7. An insulation composition according to claim 1 wherein said additive has a
5 weight/weight ratio of HALS/TMQ of from about 90/10 to about 10/90.

8. An insulation composition according to claim 1 wherein said additive has a weight/weight ratio of HALS/TMQ of from about 75/25 to about 25/75.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/22672

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : C08K 5/3492, 5/3437, 5/3435

US CL : 524/87, 99, 100, 252, 254, 255, 257, 258

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/87, 99, 100, 252, 254, 255, 257, 258

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
Please See Continuation Sheet**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6,455,616 B1 (COGEN) 24 September 2002 (24.09.2002)	1-8
X	US 2002/0169238 A1 (CARONIA et al.) 14 November 2002 (14.11.2002)	1-8
A	US 5,731,082 A (GROSS et al.) 24 March 1998 (24.03.1998)	
A	US 5,246,783 A (SPENADEL et al.) 21 September 1993 (21.09.1993)	
A	US 4,870,121 A (BAMJI et al.) 26 September 1989 (26.09.1989)	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T"

later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X"

document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y"

document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&"

document member of the same patent family

Date of the actual completion of the international search

18 November 2003 (18.11.2003)

Date of mailing of the international search report

09 DEC 2003

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US
Commissioner for Patents
P.O. Box 1450
Alexandria, Virginia 22313-1450

Facsimile No. (703)305-3230

Authorized officer

Matthew A. Thexton

Telephone No. 703-308-0661

INTERNATIONAL SEARCH REPORT

PCT/US03/22672

Continuation of B. FIELDS SEARCHED Item 3:

EAST: above US subclasses and metallocene and (antioxidant or anti adj oxidant)

EAST: EPO, JPO DERWENT: ethylene and metallocene and (antioxidant or anti adj oxidant)

EAST: treeing and metallocene