



(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(22) Date de dépôt/Filing Date: 2021/08/20

(41) Mise à la disp. pub./Open to Public Insp.: 2022/08/25

(30) Priorité/Priority: 2021/02/25 (CA3,110,357)

(51) Cl.Int./Int.Cl. *D21C 3/04* (2006.01),
C01B 17/69 (2006.01), *C08H 7/00* (2011.01),
C08H 8/00 (2010.01), *C08J 11/10* (2006.01),
C09K 3/00 (2006.01)

(71) Demandeur/Applicant:
SIXRING INC., CA

(72) Inventeurs/Inventors:
PURDY, CLAY, CA;
WEISSENBERGER, MARKUS, CA;
PAGELS, MARKUS, CA;
WYNNYK, KYLE G., CA

(74) Agent: BURNET, DUCKWORTH & PALMER LLP

(54) Titre : ACIDE SULFURIQUE MODIFIE ET UTILISATIONS CONNEXES

(54) Title: MODIFIED SULFURIC ACID AND USES THEREOF

(57) Abrégé/Abstract:

An aqueous composition comprising: sulfuric acid; a heterocyclic compound; and a peroxide. Said composition being capable of delignifying biomass under milder conditions than conditions under which kraft pulping takes place.

ABSTRACT

An aqueous composition comprising: sulfuric acid; a heterocyclic compound; and a peroxide. Said composition being capable of delignifying biomass under milder conditions than conditions under which kraft pulping takes place.

MODIFIED SULFURIC ACID AND USES THEREOF

FIELD OF THE INVENTION

The present invention is directed to a method and composition useful in decomposing organic material by oxidation such as, but not limited to, the delignification of wood or plant substance, as an example and more specifically, to a method and composition for performing such under more optimal conditions than those under which the kraft process is currently conducted.

BACKGROUND OF THE INVENTION

The first step in paper production and most energy-intensive one is the production of pulp. Notwithstanding water, wood and other plant materials used to make pulp contain three main components: cellulose fibres; lignin; and hemicelluloses. Pulping has a primary goal to separate the fibres from the lignin. Lignin is a three-dimensional polymer which figuratively acts as a mortar to hold all the fibres together within the plant. Its presence in finished pulp is undesirable and adds nothing to the finished product. Pulping wood refers to breaking down the bulk structure of the fibre source, be it chips, stems or other plant parts, into the constituent fibres. The cellulose fibres are the most desired component when papermaking is involved. Hemicelluloses are shorter branched polysaccharide polymers consisting of various sugar monosaccharides which form a random amorphous polymeric structure. The presence of hemicellulose in finished pulp is also regarded as bringing no value to a paper product. This is also true for biomass conversion. The challenges are similar. Only the desired outcome is different. Biomass conversion would have the further breakdown to monosaccharides as a desired outcome while a pulp & paper process normally stops right after lignin dissolution.

There are two main approaches to preparing wood pulp or woody biomass: mechanical treatment and chemical treatment. Mechanical treatment or pulping generally consists of mechanically tearing the wood chips apart and, thus, tearing cellulose fibres apart in an effort to separate them from each other. The shortcomings of this approach include: broken cellulose fibres, thus shorter fibres and lignin being left on the cellulose fibres thus being inefficient or non-optimal. This process also consumes large amounts of energy and is capital intensive. There are several approaches included in chemical pulping. These are generally aimed at the degradation the lignin and hemicellulose into small, water-soluble molecules. These now degraded components can be separated from the cellulose fibres by washing the latter without depolymerizing the cellulose fibres. The chemical process is currently energy intensive as well as high amounts of heat and / or higher pressures are typically required; in many cases, agitation or mechanical intervention are also required, further adding inefficiencies and costs to the process.

There exist pulping or treatment methods which combine, to a various extent, the chemical aspects of pulping with the mechanical aspects of pulping. To name a few of the widely employed pulping methods referred to above, one must include thermomechanical pulping (also commonly referred to as TMP), and chemi-thermomechanical pulping (CTMP). Through a selection of the advantages provided by each general pulping method, the treatments are designed to reduce the amount of energy required by the mechanical aspect of the pulping treatment. This can also directly impact the strength or tensile strength degradation of the fibres subjected to these combination pulping approaches. Generally, these approaches involve a shortened chemical treatment (compared to conventional exclusive chemical pulping) which is then typically followed by mechanical treatment to separate the fibres.

The most common process to make pulp for paper production is the kraft process. In the kraft process, wood chips are converted to wood pulp which is almost entirely pure cellulose fibres. The multi-step kraft process consists of a first step where wood chips are impregnated / treated with a chemical solution. This is done by soaking the wood chips and then pre-heating them with steam. This step swells the wood chips and expels the air present in them and replaces the air with the liquid. This produces black liquor a resultant by-product from the kraft process. It contains water, lignin residues, hemicellulose and inorganic chemicals. White liquor is a strong alkaline solution comprising sodium hydroxide and sodium sulfide. Once the wood chips have been soaked in the various chemical solutions, they undergo cooking. To achieve delignification in the wood chips, the cooking is carried out for several hours at temperatures reaching up to 176°C. At these temperatures, the lignin degrades to yield water soluble fragments. The remaining cellulosic fibres are collected and washed after the cooking step.

US patent number 5,080,756 teaches an improved kraft pulping process and is characterized by the addition of a spent concentrated sulfuric acid composition containing organic matter to a kraft recovery system to provide a mixture enriched in its total sulfur content that is subjected to dehydration, pyrolysis and reduction in a recovery furnace. The organic matter of the sulfuric acid composition is particularly beneficial as a source of thermal energy that enables high heat levels to be easily maintained to facilitate the oxidation and reduction reactions that take place in the furnace, thus resulting in the formation of sulfide used for the preparation of cooking liquor suitable for pulping.

Caro's acid, also known as peroxymonosulfuric acid (H_2SO_5), is one of the strongest oxidants known. There are several known reactions for the preparation of Caro's acid but one of the most straightforward involves the reaction between sulfuric acid (H_2SO_4) and hydrogen peroxide (H_2O_2).

Preparing Caro's acid in this method allows one yield in a further reaction potassium monopersulfate (PMPS) which is a valuable bleaching agent and oxidizer. While Caro's acid has several known useful applications, one noteworthy is its use in the delignification of wood.

Biofuel production is another potential application for the kraft process. One of the current drawbacks of biofuel production is that it requires the use of food grade plant parts (such as seeds) in order to transform polysaccharides into fuel in a reasonably efficient process. The carbohydrates could be obtained from cellulosic fibres, by using non-food grade biomass in the kraft process; however, the energy intensive nature of the kraft process for delignification makes this a less commercially viable option. In order to build a plant based chemical resource cycle there is a great need for energy efficient processes which can utilize plant-based feedstocks that don't compete with human food production.

While the kraft pulping process is the most widely used chemical pulping process in the world, it is extremely energy intensive and has other drawbacks, for example, substantial odours emitted around pulp producing plants or general emissions that are now being highly regulated in many pulp and paper producing jurisdictions. In light of the current environmental challenges, economic challenges and climatic changes, along with emission fees being implemented, it is highly desirable to optimize the current pulping processes. In order to provide at least linear quality fibres without the current substantial detriment to the environment during the production thereof. Accordingly, there still exists a need for a composition capable of performing delignification on wood substance under reduced temperatures and pressures versus what is currently in use without requiring any additional capital expenditures.

SUMMARY OF THE INVENTION

The inventors have developed novel compositions which are capable of being used to delignify biomass under room temperature conditions (i.e. 20-25°C). While such compositions can also be used for other applications, it is noteworthy to point out that despite the fact that they contain sulfuric acid and peroxide, they present better handling qualities than conventional compositions comprising sulfuric acid and a peroxide component.

According to an aspect of the present invention, there is provided an aqueous acidic composition comprising:

- sulfuric acid;
- a heterocyclic compound; and

- a peroxide.

According to an aspect of the present invention, there is provided an aqueous acidic composition comprising:

- sulfuric acid;
- a heterocyclic compound; and

wherein sulfuric acid and said a heterocyclic compound; are present in a molar ratio of no less than 1:1.

Preferably, the sulfuric acid and said heterocyclic compound are present in a molar ratio ranging from 28:1 to 2:1. More preferably, the sulfuric acid and heterocyclic compound are present in a molar ratio ranging from 24:1 to 3:1. Preferably, the sulfuric acid and heterocyclic compound are present in a molar ratio ranging from 20:1 to 4:1. More preferably, the sulfuric acid and heterocyclic compound are present in a molar ratio ranging from 16:1 to 5:1. According to a preferred embodiment of the present invention, the sulfuric acid and heterocyclic compound are present in a molar ratio ranging from 12:1 to 6:1.

Also preferably, said heterocyclic compound has a molecular weight below 300 g/mol. Also preferably, said heterocyclic compound has a molecular weight below 150 g/mol. More preferably, said heterocyclic compound is a secondary amine. According to a preferred embodiment of the present invention, said heterocyclic compound is selected from the group consisting of: imidazole; triazole; and N-methylimidazole.

According to an aspect of the present invention, there is provided an aqueous composition for use in the delignification of biomass such as wood, wherein said composition comprises:

- sulfuric acid;
- a heterocyclic compound; and
- a peroxide.

wherein the sulfuric acid and the heterocyclic compound are present in a mole ratio ranging from 2:1 to 28:1.

According to an aspect of the present invention, there is provided an aqueous composition for use in the breaking down of cellulose from biomass (*i.e.* a plant source), wherein said composition comprises:

- sulfuric acid in a 20 – 70 wt% of the total weight of the composition;
- a heterocyclic compound; and
- a peroxide;

wherein the sulfuric acid and the heterocyclic compound are present in a mole ratio ranging from 2:1 to 30:1.

Preferably, the peroxide is hydrogen peroxide.

According to an aspect of the present invention, there is provided a method of delignification of biomass / plant material, said method comprising:

- providing said plant material comprising cellulose fibres and lignin;
- exposing said plant material requiring to a composition comprising:
 - o sulfuric acid in a 20 – 80 wt% of the total weight of the composition; and
 - o the heterocyclic compound;

for a period of time sufficient to remove substantially all of the lignin present on said plant material. Preferably, the composition further comprises a peroxide. Preferably, the composition comprises sulfuric acid ranging from 20 – 70 wt% of the total weight of the composition. More preferably, the composition comprises sulfuric acid ranging from 30 – 70 wt% of the total weight of the composition.

Preferably, said heterocyclic compound has a molecular weight below 300 g/mol. More preferably, said heterocyclic compound has a molecular weight below 150 g/mol. According to a preferred embodiment of the present invention, the composition has a pH less than 1. According to another preferred embodiment of the present invention, the composition has a pH less than 0.5.

According to an aspect of the present invention, there is provided a one-pot process to separate lignin from a lignocellulosic feedstock, said process comprising the steps of:

- providing a vessel;
- providing said lignocellulosic feedstock;
- providing a composition comprising;
 - an acid;
 - a modifying agent comprising a heterocyclic compound; and
 - a peroxide;
- exposing said lignocellulosic feedstock to said composition in said vessel for a period of time sufficient to remove at least 80% of the lignin present said lignocellulosic feedstock;
- optionally, separating and removing a liquid phase comprising dissolved lignin fragments from a solid phase comprising cellulose fibres.

According to a preferred embodiment of the present invention, the a composition consists of;

- an acid;
- a modifying agent comprising a heterocyclic compound; and
- a peroxide.

The inventors have discovered that delignification of biomass such as wood material / woody pulp (for example, but not limited to wood chips) can occur at substantially lower temperatures than those used during conventional kraft pulping process. In fact, experiments conducted at room temperature with preferred compositions according to the present invention were shown to degrade the lignin present in wood chips to free up cellulose fibres. According to a preferred embodiment of a method according to the present invention, a wood sample was dissolved at 30°C upon exposure to a composition according to a preferred embodiment of the present invention. According to a preferred embodiment of the present invention, one could substantially reduce the energy input costs involved in current pulp delignification by applying a method involving a preferred composition of the present invention.

DESCRIPTION OF THE INVENTION

The experiments carried out using an aqueous acidic composition according to a preferred embodiment of the present invention as shown that wood chips can undergo delignification under controlled reaction conditions and eliminate or at least minimize the degradation of the cellulose. Degradation is understood to mean a darkening of cellulose, which is symbolic of an uncontrolled acid attack on the cellulose and staining thereof.

The heterocyclic compound together in the presence of sulfuric acid and the peroxide component, seems to generate a coordination of the compounds which acts as a modified sulfuric acid. In that respect, it is believed that the presence of the heterocyclic compound forms an adduct with the sulfuric acid to generate a modified sulfuric acid. The strength of the modified acid is dictated by the moles of sulfuric acid to the moles of the heterocyclic compound. Hence, a composition comprising a molar ratio of 6:1 of sulfuric acid: the heterocyclic compound would be much less reactive than a composition of the same components in a 28:1 molar ratio.

When performing delignification of wood using a composition according to a preferred embodiment of the present invention, the process can be carried out at substantially lower temperatures than temperatures used in the conventional kraft pulping process. The advantages are substantial, here are a few: the kraft pulping process requires temperatures in the vicinity of 176 – 180°C in order to perform the

delignification process, a preferred embodiment of the process according to the present invention can delignify wood at far lower temperatures, even as low as 20°C. According to a preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 0°C. According to a preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 10°C. According to a preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 30°C. According to another preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 40°C. According to yet another preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 50°C. According to yet another preferred embodiment of the present invention, the delignification of wood can be performed at temperatures as low as 60°C. Other advantages include: a lower input of energy; reduction of emissions and reduced capital expenditures; reduced maintenance; lower shut down / turn around costs; also there are health, safety and environment ("HSE") advantages compared to conventional kraft pulping compositions.

In each one of the above preferred embodiments, the temperature at which the processes are carried out are substantially lower than the current energy-intensive kraft process.

Moreover, the kraft process uses high pressures to perform the delignification of wood which is initially capital intensive, dangerous, expensive to maintain and has high associated turn-around costs. According to a preferred embodiment of the present invention, the delignification of wood can be performed at atmospheric pressure. This, in turn, circumvents the need for highly specialized and expensive industrial equipment such as pressure vessels / digestors. It also allows the implementation of delignification units in many of parts of the world where the implementation of a kraft plant would previously be impracticable due to a variety of reasons.

Some of the advantages of a process according to a preferred embodiment of the present invention, over a conventional kraft process are substantial as the heat / energy requirement for the latter is not only a great source of pollution but is in large part the reason the resulting pulp product is so expensive and has high initial capital requirements. The energy savings in the implementation of a process according to a preferred embodiment of the present invention would be reflected in a lower priced pulp and environmental benefits which would have both an immediate impact and a long-lasting multi-generational benefit for all.

Further cost savings in the full or partial implementation of a process according to a preferred embodiment of the present invention, can be found in the absence or minimization of restrictive regulations for the operation of a high temperature and high-pressure pulp digestors.

In the preparation of blends it has been found that modifying agents comprising an aromatic and/or conjugated amine, such as imidazole, n-methylimidazole and triazole, are significantly less exothermic than modifying agents comprising an aliphatic amine. This makes the overall preparation of these systems easier and safer. Hence, it makes desirable and attractive for operators when considering the large volumes of acidic compositions they handle especially, but not to be limited to the pulping industry.

Preparation of a composition according to a preferred embodiment of the present invention

A composition according to a preferred embodiment of the present invention was prepared by admixing sulfuric acid (92-98%) with imidazole (Sigma Aldrich, ACS reagent, $\geq 99\%$, flakes) in a glass jar on a magnetic stir plate, and hydrogen peroxide was subsequently added and mixed in to generate a modified sulfuric acid-peroxide composition.

For the $\text{H}_2\text{SO}_4\text{:H}_2\text{O}_2\text{:N-methylimidazole}$ blend with a 5:5:1 molar ratio. 52.9g of concentrated sulfuric acid (93%) was mixed with 8.2g N-methylimidazole. Then, 58.8g of a hydrogen peroxide solution in water (29%) was slowly added to the acid. As the mixing releases a large amount of heat the beaker was placed in an ice bath. The pH of the resulting composition was less than 0.5.

Delignification experiments

After mixing, the resulting composition is split into 4 equal parts. One part was exposed to 1.5g of wood shavings, another part was exposed to commercially available lignin and another part was exposed to commercially available cellulose respectively and stirred at ambient conditions for 3 hours. The fourth part of the blend is kept as a blend reference sample.

Control tests were run for the respective mixtures with just kraft lignin or just cellulose added instead of biomass.

Commercially available lignin (Sigma-Aldrich; Lignin, kraft; Prod# 471003) was used as a control in the testing.

Commercially available cellulose (Sigma-Aldrich; Cellulose, fibres (medium); Prod# C6288) was also used as a control in the testing.

The solid phase of each blend was filtered off after 3h of reaction time, rinsed with water and dried in an oven at 45°C to constant weight. An effective blend should dissolve all lignin and leave the cellulose as intact as possible. The results of the experiments conducted with several compositions are reported in Table 1 below.

Table 1 - Recovery of solids (% of initial mass) after 3h reaction time

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)	Comment
5:5:1	H ₂ SO ₄ : H ₂ O ₂ : n-methylimidazole	46.51%	10.08%	96.80%	
10:10:1	H ₂ SO ₄ : H ₂ O ₂ : n-methylimidazole	46.8%	0%	91.2%	
30:30:1	H ₂ SO ₄ : H ₂ O ₂ : n-methylimidazole	44.19%	0.00%	100.00%	
30:10:3	H ₂ SO ₄ : H ₂ O ₂ : n-methylimidazole	0.00%	0.00%	0.00%	reaction ran away after 10 minutes consuming wood, lignin, cellulose
10:10:1	H ₂ SO ₄ : H ₂ O ₂ : Triazole	48.96%	19.53%	86.09%	
30:10:3	H ₂ SO ₄ : H ₂ O ₂ : Triazole	2.61%	0.00%	37.80%	reaction ran away
10:10:1	H ₂ SO ₄ : H ₂ O ₂ : Imidazole	46.00%	5.00%	100.00%	
30:10:3	H ₂ SO ₄ : H ₂ O ₂ : Imidazole	4.00%	0.00%	7.00%	reaction ran away

The blend with a ratio of 10:10:1 of sulfuric acid (96% conc. used) to hydrogen peroxide (as 30% solution) to imidazole results in a mass recovery of 46% from wood and 100% from the cellulose control. However, some of the lignin from the lignin control could be recovered, which is an indication that the composition, while good, was not completely optimized for complete lignin removal. Alternatively, it is possible that a longer residence time would have permitted complete delignification. Regardless of the reason, it is felt that such performance can be readily used for the production of commercially useful and valuable pulp.

The above experiment is a clear indication that a preferred composition according to the present invention not only provides an adequate dissolving acid to delignify plant material but is also valuable in controlling the ultimate degradation of cellulosic material into carbon black residue resulting in higher yields potentially for the operators thus increasing profitability while reducing emissions and the risk to the employees, contractors and public.

Additional testing was carried out to confirm the above initial results and to explore the feasibility of using other ratios or other compounds with similar chemical features or characteristics as modifying agent. According to a preferred embodiment of the present invention, the modifying agent is selected in the group consisting of: imidazole; N-methylimidazole; triazole; pyrrole; pyrazine; benzotriazole; and quinoline and combinations thereof. According to a most preferred embodiment of the present invention, the modifying agent is imidazole and N-methylimidazole. Even more preferable, the modifying agent is N-methylimidazole. The results of the experiments are set out below in Tables 2 to 5.

Table 2 - Recovery of solids (% of initial mass) after 3h reaction time using imidazole as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :Imidazole	40.01%	0%	95.37%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :Imidazole	46.0%	5.0%	100%
20:20:1	H ₂ SO ₄ :H ₂ O ₂ :Imidazole	49.1%	0%	47.1%
30:10:3	H ₂ SO ₄ :H ₂ O ₂ :Imidazole	4.0%	0%	7.0%

Table 3 - Recovery of solids (% of initial mass) after 3h reaction time using N-methylimidazole as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
5:5:1	H ₂ SO ₄ :H ₂ O ₂ :N-methylimidazole	46.5%	10.1%	96.8%
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :N-methylimidazole	46.8%	0%	91.2%
30:30:1	H ₂ SO ₄ :H ₂ O ₂ :N-methylimidazole	44.2%	0%	100%

Table 4 - Recovery of solids (% of initial mass) after 3h reaction time using benzotriazole as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :Benzotriazole	52.4%	0%	94.3%

Table 5 - Recovery of solids (% of initial mass) after 3h reaction time using quinoline as modifying agent

Molar Ratio	Chemical	Wood Yield (%)	Lignin Yield (%)	Cellulose Yield (%)
10:10:1	H ₂ SO ₄ :H ₂ O ₂ :Quinoline	61.55%	0%	99.8%

Other experiments were attempted using indole as modifying agent, however the acid-peroxide composition became unstable after the addition of indole. This was an indication that, in this particular application, indole would not be a desirable compound to use.

A method to yield glucose from wood pulp would represent a significant advancement to the current process where the conversion of such is chemical and energy intensive, costly, emissions intensive and dangerous all while not resulting in highly efficient results, especially in large-scale operations. It is desirable to employ a composition which may delignify wood but also allows the operator some control in order to preserve the cellulose rather than degrading it to carbon black resulting in higher efficiencies and yields along with increased safety and reduced overall costs.

According to a preferred embodiment of the method of the present invention, the separation of lignin can be effected and the resulting cellulose fibres can be further processed to yield glucose monomers. Glucose chemistry has a multitude of uses including as a starting block in the preparation of widely used chemicals including but not limited to diacetone, dithioacetal, glucoside, glucal and hydroxyglucal to name but a few.

According to another preferred embodiment of the present invention, the composition can be used to decompose organic material by oxidation such as those used in water treatment, water purification and/or water desalination. An example of this is the removal (*i.e.* destruction) of algae on filtration membranes. As such membranes can be quite expensive, it is imperative that they be used for as long as possible. However, given the difficulty to remove organic matter which accumulates on it over time, new approaches are necessary to do so efficiently and with as little damage to the membrane as possible. Mineral acids are too strong and, while they will remove the organic matter, will damage the filtration membranes. A preferred composition of the present invention remedies this issue as it is less aggressive than the mineral acids and, as such, will remove the organic contaminants in a much milder approach, therefore sparing the membrane.

While the foregoing invention has been described in some detail for purposes of clarity and understanding, it will be appreciated by those skilled in the relevant arts, once they have been made familiar with this disclosure that various changes in form and detail can be made without departing from the true scope of the invention in the appended claims.

CLAIMS

1. An aqueous acidic composition comprising:
 - sulfuric acid;
 - a heterocyclic compound and
 - a peroxide.
2. An aqueous acidic composition comprising:
 - sulfuric acid;
 - a heterocyclic compound; andwherein sulfuric acid and said heterocyclic compound are present in a molar ratio of no less than 1:1.
3. The composition according to claim 1 or 2, wherein sulfuric acid, said heterocyclic compound are present in a molar ratio ranging from 28:1 to 2:1.
4. The composition according to any one of claims 1 to 3, wherein sulfuric acid, said heterocyclic compound are present in a molar ratio ranging from 20:1 to 5:1.
5. The composition according to any one of claims 1 to 4, wherein sulfuric acid, said heterocyclic compound are present in a molar ratio of approximately 10:1.
6. The composition according to any one of claims 1 to 5 where said heterocyclic compound has a molecular weight below 300 g/mol.
7. The composition according to any one of claims 1 to 6 where said heterocyclic compound is a secondary amine.
8. The composition according to any one of claims 1 to 7 where said heterocyclic compound is selected from the group consisting of: imidazole; N-alkylimidazole ;N-methylimidazole; triazole; pyrrole; pyrazine; benzotriazole; and quinoline and combinations thereof.
9. The composition according to any one of claims 1 to 8 where said heterocyclic compound is selected from the group consisting of: imidazole and N-methylimidazole.

10. The composition according to any one of claims 1 to 9 where said heterocyclic compound is imidazole.
11. The composition according to any one of claims 1 to 10, where the peroxide is hydrogen peroxide.
12. Method of delignification of plant material, said method comprising:
- providing said plant material comprising cellulose fibres and lignin;
 - exposing said plant material requiring to a composition comprising:
 - o sulfuric acid present in amount ranging from 20 to 80 wt% of the total weight of the composition; and
 - o a heterocyclic compound;
- for a period of time sufficient to remove substantially all of the lignin present on said plant material.
13. Method according to claim 15 where said heterocyclic compound has a molecular weight below 300 g/mol.
14. Method according to any one of claims 15 to 16 where said composition further comprises a peroxide.
15. Method according to any one of claims 15 to 17 where said heterocyclic compound is selected from the group consisting of: imidazole; N-alkylimidazole; N-methylimidazole; triazole; pyrrole; pyrazine; benzotriazole; and quinoline and combinations thereof.
16. Method according to any one of claims 15 to 17 where said heterocyclic compound is selected from the group consisting of: imidazole and N-methylimidazole.
17. Method according to any one of claims 15 to 18 where said heterocyclic compound is imidazole.
18. A one-pot process to separate lignin from a lignocellulosic feedstock, said process comprising the steps of:
- providing a vessel;
 - providing said lignocellulosic feedstock;
 - providing a composition comprising:
 - an acid;
 - a modifying agent comprising a heterocyclic compound; and
 - a peroxide;

- exposing said lignocellulosic feedstock to said composition in said vessel for a period of time sufficient to remove at least 80% of the lignin present said lignocellulosic feedstock;
 - optionally, separating and removing a liquid phase comprising dissolved lignin fragments from a solid phase comprising cellulose fibres.
19. The process according to claim 18, wherein said acid is sulfuric acid.
20. The process according to claim 18 or 19 wherein said peroxide is hydrogen peroxide.
21. The process according to any one of claims 18 to 20, wherein the period of time is sufficient to remove at least 90% of the lignin present on said plant material.
22. The process according to any one of claims 18 to 21, wherein the period of time is sufficient to remove at least 95% of the lignin present on said plant material.
23. The process according to any one of claims 19 to 22, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 50°C.
24. The process according to any one of claims 18 to 23, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 40°C.
25. The process according to any one of claims 18 to 24, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 30°C.
26. The process according to any one of claims 18 to 25, wherein the temperature of the composition prior to the step of exposing it to the lignocellulosic feedstock is below 25°C.
27. The process according to any one of claims 18 to 26, wherein said method is carried out at ambient temperature.
28. The process according to any one of claims 18 to 27, wherein said method is carried out at ambient pressure.
29. An aqueous composition for use in the delignification of wood, wherein said composition comprises:
- sulfuric acid;
 - heterocyclic compound; and

- a peroxide;

wherein the sulfuric acid and the heterocyclic compound are present in a mole ratio ranging from 2:1 to 28:1.

30. An aqueous composition for use in the processing and depolymerisation of cellulose from a plant source, wherein said composition comprises:

- sulfuric acid present in amount ranging from 20 to 80 wt% of the total weight of the composition;
- a heterocyclic compound; and
- a peroxide;

wherein the sulfuric acid and the heterocyclic compound are present in a mole ratio ranging from 2:1 to 28:1.