

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

29 March 2018 (29.03.2018)



(10) International Publication Number

WO 2018/055010 A1

(51) International Patent Classification:

C08K 5/00 (2006.01)

C08K 5/3435 (2006.01)

C08K 5/08 (2006.01)

G02B 1/04 (2006.01)

C08K 5/17 (2006.01)

G02C 7/02 (2006.01)

Published:

— with international search report (Art. 21(3))

(21) International Application Number:

PCT/EP2017/073838

(22) International Filing Date:

20 September 2017 (20.09.2017)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

16306204.5

20 September 2016 (20.09.2016) EP

(71) Applicant: ESSILOR INTERNATIONAL [FR/FR]; 147

Rue de Paris, 94220 Charenton-Le-Pont (FR).

(72) Inventors: CHIU, Hao Wen; C/O Essilor of America,

13555 North Stemmons Freeway, Dallas, Texas 75234

(US). FRENCH, Elliot; C/O Essilor of America, 13555

North Stemmons, DALLAS, Texas 75234 (US). JAL-

LOULI, Aref; C/O Essilor of America, 13555 North Stem-

mons Freeway, Dallas, Texas 75234 (US). SHAN, Haifeng;

C/O Essilor of America, 13555 North Stemmons Freeway,

Dallas, Texas 75234 (US).

(74) Agent: CHAUVIN, Vincent et al.; JACOBACCI

CORALIS HARLE, 32 rue de l'Arcade, 75008 PARIS (FR).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,

DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,

HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,

KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,

MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,

OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,

SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,

TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH,

GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,

UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,

TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,

EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,

MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,

TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,

KM, ML, MR, NE, SN, TD, TG).

(54) Title: POLYCARBONATE RESIN COMPOSITIONS WITH CONSISTENT COLOR AND STABLE BLUE-CUT PERFORMANCE

(57) Abstract: Embodiments of the disclosure relate to a series of PC resin additives for maintaining the color stability and blue-cut performance during injection molding. The additives may be used to adapt a PC resin customarily used for sun protection lenses for clear lens applications.



WO 2018/055010 A1

Polycarbonate resin compositions with consistent color and stable blue-cut performance**FIELD OF THE INVENTION**

The invention relates to the field of ophthalmic lenses, including polarized ophthalmic lenses for spectacles and sunglasses.

5

BACKGROUND

Lenses made of commercially-available polycarbonate (PC) resins customarily used for sunglass and sunvisor markets have been historically shown to exhibit significantly higher blue-cut performance than those made of clear, ophthalmic-grade PC resins. These PC resins are targeted towards solar lens applications in which the lenses are significantly tinted. When employing these resins in clear, ophthalmic lens applications, a slight yellow tint is apparent. The yellow tint is due in part to the inclusion of UV absorbers that filter blue light.

Injection molded sunglasses lenses using the above-mentioned PC resins include tinting that masks color variations caused by the injection molding process. Because color variations are generally imperceptible in heavily tinted lenses, there is not a need for manufacturers to incorporate additives that minimize color variation. When these PC resins are used to produce clear or lightly-tinted ophthalmic lenses by injection molding, color variation becomes apparent. Lenses using the above-mentioned PC resins may gradually change color appearance during service resulting from photo-degradation of the PC resin and added colorants. This change in lens color has been shown to affect blue-cut performance.

Photo-degradation and color variation may be reduced or prevented by the inclusion of additives that provide proper protection. There is a need in the industry for clear, ophthalmic grade lenses that provide protection from blue light. Because color variation is more apparent in clear lenses, it is important to incorporate an additive package that minimizes color variation during lens production and provides long-term light protection to the lens components.

25

SUMMARY

It is an object of the disclosure to provide a polycarbonate resin for use in clear lenses that offers blue-light blocking functionality, or blue-cut performance, that is comparable to sunglass lenses. The inclusion of blue-cut functionality in clear lenses will help protect prescription eyeglass wearers from phototoxic blue light. In some embodiments, the polycarbonate resin comprises a UV absorber. In order to offset the yellow tint imparted by a UV absorber, a colorant may be added to the polycarbonate resin.

The polycarbonate resin may include other additives, such as antioxidants and light stabilizers in order to produce lenses with consistent color. Hence, it is one object of the disclosure to provide

an additive package to be incorporated into base PC resins with 400nm UV cut-offs to protect the resin during processing and minimize color variation of the resulting lenses. It is another object of the disclosure for the proposed additive package to further protect the lenses from color changes due to photo-degradation. The presently-disclosed additives and resin formulations provide for the production of clear lenses with consistent color and constant blue-cut performance during service.

A high blue-cut performance polycarbonate resin composition for use in clear lenses is provided herein. In some embodiments, a clear lens is a tinted or untinted lens with a luminous transmittance of light within the visible spectral range ranging from 80% or greater to 100%. In some embodiments, the polycarbonate resin composition comprises a polycarbonate polymer, a UV absorber, a colorant additive, and a light stabilizer. In some aspects, the polycarbonate polymer is a base resin. In other embodiments, a base resin comprises a polycarbonate polymer and a UV absorber. In some aspects, the base resin blocks greater than 99% of light with a wavelength less than 400 nm at each wavelength in the wavelength range of 315-400 nm, and partially blocks blue light in the 400-500nm range. In some aspects, the resin composition blocks greater than 99% of light with a wavelength less than 400 nm at each wavelength in the wavelength range of 315-400 nm, and partially blocks blue light in the 400-500 nm range. In some embodiments, the polycarbonate polymer has a weight average molecular weight ranging from about 20,000 to about 40,000 g/mol.

UV absorbers are frequently incorporated in optical articles in order to reduce or prevent UV light from reaching the retina (in particular in ophthalmic lens materials). In addition, UV absorbers protect the substrate material from UV light, thus preventing it from weathering and becoming brittle and/or yellow. In some aspects, the UV absorber preferably has the ability to at least partially block light having a wavelength shorter than 400 nm, preferably UV wavelengths below 385 or 390 nm, but also has an absorption spectrum extending to the visible blue light range (400 - 500 nm). Most preferred ultraviolet absorbers have a maximum absorption peak in a range from 350 nm to 370 nm and/or do not absorb light in the 465-495 nm range, preferably the 450-550 nm range.

In some aspects, the polycarbonate resin UV absorber is a benzotriazole absorber. Suitable UV absorbers include without limitation 2-(2-hydroxyphenyl)-benzotriazoles such as 2-(2-hydroxy-3-t-butyl-5-methylphenyl) chlorobenzotriazole, 2-(2'-hydroxy-5'-t-octylphenyl) benzotriazole, 2-(3'-methallyl-2'-hydroxy-5'-methyl phenyl) benzotriazole or other allyl hydroxymethylphenyl benzotriazoles, 2-(3,5-di-t-amyl-2-hydroxyphenyl) benzotriazole, and the 2-hydroxy-5-acryloxyphenyl-2H-benzotriazoles disclosed in U.S. Pat. No. 4,528,311 and also Tinuvin®CarboProtect® from BASF. Preferred absorbers are of the benzotriazole family.

Commercially available products include Tinuvin 326 from BASF, Seeseorb 703 from Cipro, Viosorb 550 from Kyodo Chemicals, and Kemisorb 73 from Chemipro, Tinuvin®CarboProtect®. In specific aspects, the UV absorber is 2-(5-chloro-2H-benzotriazole-2-yl)-6-(1,1-dimethylethyl)-4-methyl phenol. In some embodiments, the polycarbonate resin comprises 0.05 to 1% by weight of a UV absorber.

In some aspects, the polycarbonate resin comprises a colorant additive. Suitable colorant additives can be selected from azo dyes, polymethyne dyes, arylmethyne dyes, polyene dyes, anthracenedione dyes, pyrazolone dyes, anthraquinone dyes, auinophtalone dyes, and carbonyl dyes. In some aspects, the polycarbonate resin colorant additive is a blue dye, violet dye, red dye, or any combination thereof. In some embodiments, the blue dye is an anthraquinone dye. In further aspects, the blue dye is 1,4-di(2,6-dibromo-4-methylphenylamino) anthracene-9,10-dione.

In some aspects, a resin composition comprises at least one hindered amine light stabilizer, and/or at least one antioxidant, more preferably at least one hindered amine light stabilizer and at least one antioxidant. This combination of free radical scavengers offers the best protection from thermal and photo degradation to optical filtering means. Protection of optical filtering means from photo-degradation can also be reinforced by the presence on the optical article of an antireflection coating containing at least one mineral/dielectric layer.

In some embodiments, the polycarbonate resin further comprises an antioxidant or heat-stabilizer. Preferred antioxidants are sterically hindered phenols, benzenepropanoic acid esters, thioethers or phosphites. In further embodiments, the antioxidant is a benzenepropanoic acid ester. In specific embodiments, the antioxidant is the benzenepropanoic acid ester, 3(1,1-dimethylethyl)-4-hydroxy-5-methyl-1,1'-[1,2-ethanediylbis(oxy-2,1-ethanediyl)] ester. In some embodiments, 0.05 to 1% by weight of an antioxidant is added to a polycarbonate resin.

In some aspects, the polycarbonate resin may further comprise a light stabilizer. In some embodiments, the light stabilizer is a hindered amine light stabilizer. In further aspects, the hindered amine light stabilizer is bis(1,2,2,6,6-pentamethyl-4-piperidiny)-[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]butylmalonate. In some embodiments, 0.05 to 1% by weight of a light stabilizer is added to a polycarbonate resin. In additional aspects, the resin may further comprise a selective blue blocking filter, also referred to herein as a selective filter.

In further embodiments, the presently disclosed resin is used to produce a clear lens with a D65 transmittance of greater than 85% for a 1.1 mm thick lens. In some embodiments, lenses comprising the presently disclosed resin composition have a BVC(B') value of $\geq 15\%$, preferably of $\geq 18\%$, more preferably of $\geq 20\%$. In additional embodiments, the clear lens may further

comprise at least one wafer overmold for increasing at least one of blue-cut performance, color balance, and lens clarity.

In a further embodiment, a method for producing clear lenses with improved optical characteristics and/or degradation resistance from a base resin is disclosed. In some
5 embodiments, a base resin is a commercially available blue-cut performance resin, which includes a UV absorber. In some embodiments, the base resin is Teijin Panlite L-1250VX PC resin, Bayer Makrolon LQ3187, or Sabic Lexan OQ4120, OQ4320, OQ4320R, OQ4620, or OQ4620R. In some aspects, a base resin comprises a polycarbonate polymer and a UV absorber. Base resins are typically used for sunglass and sunvisor markets and may include a UV blocker
10 in the resin composition. In some aspects, a method for producing clear lenses with improved optical characteristics and/or degradation resistance comprises the step of obtaining a base resin and adding one or more additives selected from the group consisting of a colorant additive, an antioxidant, a light stabilizer, and a selective blue blocking filter. In some aspects, an additional or supplementary UV blocker is added to the base resin. In some embodiments, the base resin
15 blocks greater than 99% of light with a wavelength less than 400 nm at each wavelength in the wavelength range of 315-400 nm.

In some embodiments, a benzotriazole UV absorber is added to a base resin. Suitable UV absorbers include without limitation 2-(2-hydroxyphenyl)-benzotriazoles such as 2-(2-hydroxy-3-t-butyl-5-methylphenyl) chlorobenzotriazole, 2-(2'-hydroxy-5'-t-octylphenyl) benzotriazole, 2-
20 (3'-methallyl-2'-hydroxy-5'-methyl phenyl) benzotriazole or other allyl hydroxymethylphenyl benzotriazoles, 2-(3,5-di-t-amyl-2-hydroxyphenyl) benzotriazole, and the 2-hydroxy-5-acryloxyphenyl-2H-benzotriazoles disclosed in U.S. Pat. No. 4,528,311 and also Tinuvin®CarboProtect® from BASF. Preferred absorbers are of the benzotriazole family. Commercially available products include Tinuvin 326 from BASF, Seeseorb 703 from Cipro,
25 Viosorb 550 from Kyodo Chemicals, and Kemisorb 73 from Chemipro, Tinuvin®CarboProtect®. In specific aspects, the UV absorber is 2-(5-chloro-2H-benzotriazole-2-yl)-6-(1,1-dimethylethyl)-4-methyl phenol. In some embodiments, 0.05 to 1% by weight of a UV absorber is added to a base resin.

In some aspects, a at least one colorant additive is added to a base resin. Suitable colorant
30 additives can be selected from azo dyes, polymethyne dyes, arylmethyne dyes, polyene dyes, anthracinedione dyes, pyrazolone dyes, anthraquinone dyes, auinophtalone dyes, and carbonyl dyes. In some aspects, a blue dye colorant additive is added to a base resin. In some aspects, the polycarbonate resin colorant additive is a blue dye, violet dye, red dye, or any combination thereof. In some embodiments, the blue dye is an anthraquinone dye. In further aspects, the blue
35 dye is 1,4-di(2,6-dibromo-4-methylphenylamino) anthracene-9,10-dione. In some embodiments,

0.1 to 20 ppm of a dye is added to a base resin. In preferred embodiments, 5 to 10 ppm of a dye is added to a base resin.

In some embodiments, an antioxidant or heat-stabilizer is added to a base resin. Preferred antioxidants are benzenepropanoic acid esters, sterically hindered phenols, thioethers or phosphites. In further embodiments, the antioxidant is a benzenepropanoic acid ester. In specific
5 embodiments, the antioxidant is the benzenepropanoic acid ester 3(1,1-dimethylethyl)-4-hydroxy-5-methyl-1,1'-[1,2-ethanediylbis(oxy-2,1-ethanediyl)] ester. In some embodiments, 0.05 to 1% by weight of an antioxidant is added to a base resin.

In some aspects, a light stabilizer is added to a base resin. In some embodiments, the light
10 stabilizer is a hindered amine light stabilizer. Preferred hindered amine light stabilizers are derivatives of piperidine, such as derivatives of 2,2,6,6-tetramethyl piperidine. In further aspects, the hindered amine light stabilizer is bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl] butylmalonate. In some embodiments, 0.05 to 1% by weight of a light stabilizer is added to a base resin.

In some aspects, the resin composition further comprises at least one selective filter. A selective
15 filter selectively inhibits/blocks transmission of light in a selected wavelength range chosen within the 400-500 nm range, preferably in the 400-460 nm range. In some aspects, a selective filter has little or no effect on transmission of wavelengths outside the selected wavelength range, unless specifically configured to do so. The bandwidth of the selected range can
20 preferably range from 10 to 70 nm, preferably from 10 to 60 nm more preferably 20 to 50 nm. In some embodiments the selective filter preferably blocks or cuts at least 5 % of the light in the selected wavelength range, preferably at least 8 %, more preferably at least 12 %. The phrase "blocking X %" of incident light in a specified wavelength range does not necessarily mean that some wavelengths within the range are totally blocked, although this is possible. Rather,
25 "blocking X %" of incident light in a specified wavelength range means that an average of X % of said light within the range is not transmitted. As used herein, the light blocked in this way is light arriving on the main face of the optical article onto which the layer comprising the at least one optical filtering means is deposited, generally the front main face.

In some aspects, the selective filter is a notch filter. Preferably, the selective filter is an
30 absorbing dye at least partially absorbing light in the 400-500 nm wavelength range, preferably in the 400-460 nm wavelength range. The chemical nature of the absorbing dye that may act as filter for at least partially inhibiting light having the selected wavelength range is not particularly limited as far as the absorbing dye acts as a selective filter. Blue light blocking dyes, typically yellow dyes, are preferably selected to have little or no absorbance in other parts of the visible
35 spectrum to minimize the appearance of other colors.

Porphyrins are well-known macrocycle compounds composed of four modified pyrrole subunits interconnected at their carbon atoms via methine bridges. The parent porphyrin is porphine and substituted porphines are called porphyrins. Porphyrins are the conjugate acids of ligands that bind metals to form (coordination) complexes.

5 Certain porphyrins or porphyrin complexes or derivatives are interesting in that they provide selective absorption filters having a bandwidth in some cases of for example 20 nm in the selected blue range of wavelengths. The selectivity property is in part provided by the symmetry of the molecules. Such selectivity helps to limit the distortion of the visual perception of color, to limit the detrimental effects of light filtering to scotopic vision and to limit the impact on
10 circadian rhythm.

For example, the one or more porphyrins or porphyrin complexes or derivatives are selected from the group consisting of Chlorophyll a; Chlorophyll b; 5,10, 15,20-tetrakis(4-sulfonatophenyl) porphyrin sodium salt complex; 5,10,15,20-tetrakis(N-alkyl-4-pyridyl) porphyrin complex; 5,10,15,20-tetrakis(N-alkyl-3-pyridyl) porphyrin complex, and 5,10,15,20-
15 tetrakis(N-alkyl-2-pyridyl) porphyrin complex, the alkyl being preferably an alkyl chain, linear or branched, comprising 1 to 4 carbon atoms per chain. For example the alkyl may be selected from the group consisting of methyl, ethyl, butyl and propyl.

The complex usually is a metal complex, the metal being selected from the group consisting of Cu cation, Cr(III), Ag(II), In(III), Mn(III), Sn(IV), Fe (III), Co (II), Mg(II) and Zn(II). Cr(III),
20 Ag(II), In(III), Mn(III), Sn(IV), Fe (III), Co (II) and Zn(II) demonstrate absorption in water in the range of 425nm to 448nm with sharp absorption peaks. Moreover, the complexes they provide are stable and not acid sensitive. Cr(III), Ag(II), In(III), Sn(IV), Fe (III), in particular, do not exhibit fluorescence at room temperature.

In some embodiments, a base resin is used to produce lenses with a BVC(B') value of $\geq 20\%$. In
25 further embodiments, a base resin is used to produce a clear lens with a D65 transmittance of greater than 85% for a 1.1 mm lens. In some embodiments, a resin composition is used to produce lenses with a BVC(B') value of $\geq 20\%$. In further embodiments, a resin composition is used to produce a clear lens with a D65 transmittance of greater than 85% for a 1.1 mm lens. In additional embodiments, the clear lens may further comprise at least one wafer overmold for
30 increasing at least one of blue-cut performance, color balance, and lens clarity.

Any embodiment of any of the disclosed compositions and/or methods can consist of or consist essentially of—rather than comprise/include/contain/have—any of the described elements and/or features and/or steps. Thus, in any of the claims, the term “consisting of” or “consisting essentially of” can be substituted for any of the open-ended linking verbs recited above, in order

to change the scope of a given claim from what it would otherwise be using the open-ended linking verb.

The term “substantially” and its variations are defined as being largely but not necessarily wholly what is specified as understood by one of ordinary skill in the art, and in one non-limiting embodiment substantially refers to ranges within 10%, within 5%, within 1%, or within 0.5%.

“Analogue” and “analog,” when referring to a compound, refers to a modified compound wherein one or more atoms have been substituted by other atoms, or wherein one or more atoms have been deleted from the compound, or wherein one or more atoms have been added to the compound, or any combination of such modifications. Such addition, deletion or substitution of atoms can take place at any point, or multiple points, along the primary structure comprising the compound.

“Derivative,” in relation to a parent compound, refers to a chemically modified parent compound or an analogue thereof, wherein at least one substituent is not present in the parent compound or an analogue thereof. One such non-limiting example is a parent compound which has been covalently modified. Typical modifications are amides, carbohydrates, alkyl groups, acyl groups, esters, pegylations and the like.

The term “about” or “approximately” or “substantially unchanged” are defined as being close to as understood by one of ordinary skill in the art, and in one non-limiting embodiment the terms are defined to be within 10%, preferably within 5%, more preferably within 1%, and most preferably within 0.5%.

The use of the word “a” or “an” when used in conjunction with the term “comprising” in the claims and/or the specification may mean “one,” but it is also consistent with the meaning of “one or more,” “at least one,” and “one or more than one.”

As used in this specification and claim(s), the words “comprising” (and any form of comprising, such as “comprise” and “comprises”), “having” (and any form of having, such as “have” and “has”), “including” (and any form of including, such as “includes” and “include”) or “containing” (and any form of containing, such as “contains” and “contain”) are inclusive or open-ended and do not exclude additional, unrecited elements or method steps.

The compositions and methods for their use can “comprise,” “consist essentially of,” or “consist of” any of the ingredients or steps disclosed throughout the specification. With respect to the transitional phrase “consisting essentially of,” in one non-limiting aspect, a basic and novel characteristic of the compositions and methods disclosed in this specification includes the compositions’ abilities to block or reduce passage of blue light through an optical article.

Other objects, features and advantages of the present invention will become apparent from the following detailed description. It should be understood, however, that the detailed description

and the examples, while indicating specific embodiments of the invention, are given by way of illustration only. Additionally, it is contemplated that changes and modifications within the spirit and scope of the invention will become apparent to those skilled in the art from this detailed description.

5

BRIEF DESCRIPTION OF THE FIGURES

FIG. 1 is a graph depicting yellowness index (YI) and BVC(B') of a series of lenses formed by injection molding of a commercially available polycarbonate resin. The upward drifting of YI and evolution of BVC(B') demonstrate the insufficiency of commercial PC resins of 400 nm UV cut-off in maintaining the color stability and blue-cut performance during injection molding.

FIG. 2 is a graph depicting the transmission spectrum of one embodiment of a blue-cut polycarbonate resin lens.

DETAILED DESCRIPTION

Various features and advantageous details are explained more fully with reference to the non-limiting embodiments that are illustrated in the accompanying drawings and detailed in the following description. It should be understood, however, that the detailed description and the specific examples, while indicating embodiments, are given by way of illustration only, and not by way of limitation. Various substitutions, modifications, additions, and/or rearrangements will be apparent to those of ordinary skill in the art from this disclosure.

In the following description, numerous specific details are provided to provide a thorough understanding of the disclosed embodiments. One of ordinary skill in the relevant art will recognize, however, that the invention may be practiced without one or more of the specific details, or with other methods, components, materials, and so forth. In other instances, well-known structures, materials, or operations are not shown or described in detail to avoid obscuring aspects of the invention.

Disclosed herein is a method for improving the color stability of existing polycarbonate resins during processing and that of the lenses made therefrom. More specifically, a combination of various additives including UV blockers, antioxidants, light stabilizers, for example, hindered amine light stabilizers, and colorants may be added to a polycarbonate base resin before being formed into optical lenses. The resulting lenses exhibit consistent color and notable blue-cut performance. The modified resin formulations may be used to produce clear lenses help protect prescription eyeglass wearers from phototoxic blue light.

Blue-cut of a lens is typically defined by:

Blue light cut (%) = 100 - T_{sb}

$$T_{sb} = \frac{\int_{380\text{ nm}}^{500\text{ nm}} T(\lambda) \cdot E_{s\lambda}(\lambda) \cdot B(\lambda) \cdot d\lambda}{\int_{380\text{ nm}}^{500\text{ nm}} E_{s\lambda}(\lambda) \cdot B(\lambda) \cdot d\lambda}$$

where

$T(\lambda)$: Transmittance (%) with 5 nm pitch

$E_{s\lambda}(\lambda)$: Solar spectral irradiation (ISO 8980-3: Annex B)

$B(\lambda)$: Blue light hazard function (ISO 8980-3: Annex B)

5

The experiments and observations disclosed herein espouse a blue-cut performance measure characterized by:

$$BVC(B') = 100\% - \frac{\int_{400\text{ nm}}^{455\text{ nm}} B'(\lambda) \cdot T(\lambda) \cdot d\lambda}{\int_{400\text{ nm}}^{455\text{ nm}} B'(\lambda) \cdot d\lambda}$$

or

$$BVC(B) = 100\% - \frac{\int_{400\text{ nm}}^{455\text{ nm}} B(\lambda) \cdot T(\lambda) \cdot d\lambda}{\int_{400\text{ nm}}^{455\text{ nm}} B(\lambda) \cdot d\lambda}$$

where

10

$T(\lambda)$: Transmittance (%) with 10 nm pitch

$B'(\lambda)$: Blue light hazard function (Arnault et al., PlosOne, 2013)

$B(\lambda)$: Blue light hazard function (ISO 8980-3: Annex B)

The blue-cut performance of a lens is a function of the transmittance $T(\lambda)$, which is directly linked to its color appearance corresponding to a specific transmission spectrum. Hence, it is important for a lens to have consistent and stable color to achieve constant blue-cut performance. During lens injection molding processes, insufficient protection from heat and oxidation may cause a lens color to vary. A typical indicator of lens color variation is the continuous evolution of the yellowness index (YI) from lens to lens (**FIG. 1**). Lens color could also change due to photo-degradation of the base PC resin and the constituent additives and colorants. The increase of YI during the production of successive lenses indicates that heat and/or oxidation are adversely affecting lens quality.

In order to enhance protection of commercial PC resins of 400nm UV cut-off from degradation/oxidation due to high heat, an antioxidant or heat stabilizer such as a benzenepropanoic acid may be added to a base PC resin. 3(1,1-dimethylethyl)-4-hydroxy-5-methyl-1,1'-[1,2-ethanediylbis(oxy-2,1-e-thanediyl)] ester is a commercially available benzenepropanoic acid sold under the name Irganox® 245 sold by Ciba part of BASF. In some embodiments, 0.05 to 1% by weight of a benzenepropanoic acid is added. In order to reduce or prevent photo-degradation of the resulting lenses, a light stabilizer may be added to a base PC resin. In some embodiments, the light stabilizer bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-[[3,5-

bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]butylmalonate may be added to a base PC resin. This compound is commercially available as Tinuvin® 144, and is sold by Ciba part of BASF. In some aspects, 0.05 to 1% by weight of a light stabilizer is added to the resin

5 Experimental section

Injection Molding of a commercial PC resin

Injection molding of 1.50B SFSV lenses with Teijin Panlite L-1250VX PC resin having 400nm UV-cut was carried out using a Nissei FN4000 injection molding machine with the following
10 process parameters:

Melt temperature: 515 F

Mold temperature: 270 F

Screw speed: 15 rpm

Injection speed: 6%

15 Packing pressure: 1220 psi

Packing time: 10 s

Cooling time: 250 s

The graph depicted in **FIG. 1** illustrates the YI and BVC(B') data of the resulting comparative lenses. As seen in **FIG. 1**, the upward drift of YI and the evolution of BVC(B') are apparent,
20 which demonstrate clearly the insufficiency of commercial PC resins of 400nm UV cut-off in maintaining the color stability and blue-cut performance during injection molding.

According to the invention, a combination of various additives including UV blockers, antioxidants, light stabilizers, for example, hindered amine light stabilizers, and colorants may be
25 added to the above polycarbonate base resin before being formed into optical lenses to maintaining the color stability and blue-cut performance during injection molding and produce clear blue-cut performance lenses with stable color.

The claims are not to be interpreted as including means-plus- or step-plus-function limitations, unless such a limitation is explicitly recited in a given claim using the phrase(s) “means for” or
30 “step for,” respectively.

CLAIMS

1. A high blue-cut performance polycarbonate resin composition for use in clear lenses comprising;
a polycarbonate polymer;
a UV absorber;
5 a colorant additive;
an antioxidant; and
a hindered amine light stabilizer;
wherein the resin blocks >99% of light with a wavelength less than 400 nm at each wavelength in the wavelength range of 315-400 nm, and partially blocks blue light in the 400-500 nm range.
- 10 2. The polycarbonate resin composition of claim 1, wherein a weight average molecular weight of the polycarbonate polymer ranges from about 20,000 to about 40,000 g/mol.
3. The polycarbonate resin composition of claim 1 or 2, wherein the UV absorber is a benzotriazole absorber.
4. The polycarbonate resin composition of claim 3, wherein the UV absorber is 2-(5-chloro-2H-
15 benzotriazole-2-yl)-6-(1,1-dimethylethyl)-4-methyl phenol.
5. The polycarbonate resin composition of any of claims 1 to 4, wherein the colorant additive is a blue dye, a violet dye, a red dye, or any combination thereof.
6. The polycarbonate resin composition of claim 5, wherein the colorant additive is 1,4-di(2,6-dibromo-4-methylphenylamino) anthracene-9,10-dione.
- 20 7. The polycarbonate resin composition of any of claims 1 to 6, wherein the antioxidant is a benzenepropanoic acid ester.
8. The polycarbonate resin composition of claim 7, wherein the antioxidant is benzenepropanoic acid, 3(1,1-dimethylethyl)-4-hydroxy-5-methyl-1,1'-[1,2-ethanediylbis(oxy-2,1-ethanediyl)] ester.
9. The polycarbonate resin composition of any of claims 1 to 8, wherein the hindered amine light
25 stabilizer is bis(1,2,2,6,6-pentamethyl-4-piperidinyl)-[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]butylmalonate.
10. The polycarbonate resin composition of any of claims 1 to 9, wherein the resin further comprises a selective blue blocking filter.

11. The polycarbonate resin composition of claim 10, wherein the selective blue blocking filter at least partially blocks blue light in a wavelength range chosen within the 400-460 nm range.

12. Use of the polycarbonate resin composition of claim 1 in a clear lens, wherein a D65 transmittance of a 1.1 mm thick lens is greater than 85%.

5 13. Use of the clear lens of claim 12, wherein the lens comprises a BVC(B') value of $\geq 20\%$.

14. Use of the clear lens of claim 13, wherein the lens further comprises a wafer overmold for increasing at least one of blue-cut performance, color balance, and lens clarity.

1/2




FIGURE 1




FIGURE 2

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2017/073838

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08K5/00 C08K5/08 C08K5/17 C08K5/3435 G02B1/04
G02C7/02

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08K G02B G02C C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 197 508 A1 (MOBAY CORP [US]) 15 October 1986 (1986-10-15)	1-4
Y	page 1, line 3 - line 11 page 3, line 4 - line 6 page 8, line 32 - page 9, line 2 examples 6,15 claim 9	1-14
Y	----- US 5 869 554 A (PICKETT JAMES EDWARD [US] ET AL) 9 February 1999 (1999-02-09) column 1, line 50 - line 52 example 1 claim 1	1-14
Y	----- US 5 949 518 A (BELMARES HECTOR [US] ET AL) 7 September 1999 (1999-09-07) figure 1 claims 1,2,5,7 ----- -/-	1-14



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

25 October 2017

Date of mailing of the international search report

09/11/2017

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Kaul-Buchberger, Eva

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2017/073838

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 1 580 591 A1 (INTERCAST EUROP SPA [IT]) 28 September 2005 (2005-09-28) example 2 -----	1-14
Y	US 2009/029172 A1 (ISOZAKI TOSHIO [JP]) 29 January 2009 (2009-01-29) paragraph [0041] -----	1-14
A	EP 1 454 961 A2 (DEGUSSA [DE]) 8 September 2004 (2004-09-08) paragraph [0025] -----	1-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2017/073838

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0197508	A1	15-10-1986	CA 1289290 C 17-09-1991
		DE 3661021 D1 01-12-1988	
		EP 0197508 A1 15-10-1986	
US 5869554	A	09-02-1999	CN 1210120 A 10-03-1999
		DE 69824504 D1 22-07-2004	
		DE 69824504 T2 23-06-2005	
		EP 0900823 A2 10-03-1999	
		JP H11152404 A 08-06-1999	
		SG 67540 A1 21-09-1999	
		US 5869554 A 09-02-1999	
US 5949518	A	07-09-1999	AU 715653 B2 10-02-2000
		EP 0880715 A1 02-12-1998	
		US 5949518 A 07-09-1999	
		WO 9730362 A1 21-08-1997	
EP 1580591	A1	28-09-2005	EP 1580591 A1 28-09-2005
		US 2006033851 A1 16-02-2006	
		US 2006114573 A1 01-06-2006	
US 2009029172	A1	29-01-2009	CN 101120052 A 06-02-2008
		DE 112006000365 T5 17-01-2008	
		JP 5166862 B2 21-03-2013	
		JP WO2006087880 A1 03-07-2008	
		TW I385212 B 11-02-2013	
		US 2009029172 A1 29-01-2009	
		WO 2006087880 A1 24-08-2006	
EP 1454961	A2	08-09-2004	AU 2004200718 A1 09-09-2004
		CA 2458294 A1 25-08-2004	
		CN 1534064 A 06-10-2004	
		DE 10308226 A1 23-09-2004	
		EP 1454961 A2 08-09-2004	
		HK 1070087 A1 06-02-2009	
		JP 2004256812 A 16-09-2004	
		KR 20040076630 A 01-09-2004	
		TW I301141 B 21-09-2008	
		US 2004166342 A1 26-08-2004	