
X555

A. H. Allen,

Bench Plane.

Patented Dec. 10, 1872.



5608

Amos D. Allen of Connecticut

May 10, 1804

Letters Patent May 10, 1804

The schedule referred to in these Letters Patent and making part of the same, containing a Description in the words of the said Amos D. Allen himself of his composition of matter for Pebbles he made or drawn as

Take Linseed oil prepared by boiling it about two ounces to a pound of linseed oil, half an ounce of Venice Turpentine, & about two ounces of gum copal made fine, half an ounce of Venice Turpentine, & about two ounces of the above prepared linseed oil quite hot. Then grind with the above mixture about a pound of lead, which will complete the composition into a hard durable body. It must be applied to the wood or other substance immediately or it will grow so stiff as to be impossible to spread it with a brush. When the wood (etc.) has received a sufficient coat of the above, & has become hard by being exposed to the sun it is polished by pumice & rotten stone made fine and used in water with a piece of linen. Dilute the composition if necessary with spirit of turpentine

Witnesses

Josiah Hewitt

Lucretia Hewitt

Amos D. Allen

220 words]