



Office de la Propriété

Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2278130 C 2008/04/22

(11)(21) **2 278 130**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 1998/02/05
(87) Date publication PCT/PCT Publication Date: 1998/08/13
(45) Date de délivrance/Issue Date: 2008/04/22
(85) Entrée phase nationale/National Entry: 1999/07/15
(86) N° demande PCT/PCT Application No.: US 1998/002246
(87) N° publication PCT/PCT Publication No.: 1998/034964
(30) Priorité/Priority: 1997/02/07 (US08/798,412)

(51) Cl.Int./Int.Cl. *C07F 9/00*(2006.01),
C07F 5/00(2006.01), *C08F 10/00*(2006.01),
C08F 4/622(2006.01), *C08F 4/68*(2006.01),
C08F 4/639(2006.01), *C08F 210/16*(2006.01)

(72) Inventeurs/Inventors:
MURPHY, VINCENT JOHN, US;
TURNER, HOWARD W., US

(73) Propriétaire/Owner:
EXXONMOBIL CHEMICAL PATENTS INC., US

(74) Agent: BORDEN LADNER GERVAIS LLP

(54) Titre : COMPOSES DE METAUX DE TRANSITION DU GROUPE 5

(54) Title: GROUP 5 TRANSITION METAL COMPOUNDS

(57) Abrégé/Abstract:

The invention addresses Group 5 metal compounds suitable as polymerization catalysts characterized by comprising one Group 15 element polyanionic ancillary ligand and three single or multidentate univalent ligands comprising Group 14-16 elements bound to the Group 5 metal, but excluding cyclopentadienyl ligands. The invention Group 5 metal compounds can be generically represented by the chemical symbols: (1) $[RJ]MR'_3$, and (2) $[(RJ)Y_n(X)]MR'_2$, where M is a Group 5 transition metal, preferably vanadium; J is a Group 15 heteroatom ligand covalently bound to M, preferably nitrogen; R is a substituted or unsubstituted aryl, hydrocarbyl or organometalloid group covalently bound to J; each R' is, independently, a uninegative ligand, e.g., substituted or unsubstituted aryl, substituted or unsubstituted linear or cyclic hydrocarbyl, silyl, hydride or substituted or unsubstituted organometalloid group; X is a univalent single or multidentate ancillary ligand comprising at least one Group 14-16 element covalently bound to M; and, Y is an optional covalent bridging group linking R and X, comprising at least one Group 14-16 element, n - 1 when X is covalently linked to R and n-0 when X is not covalently linked to R. Catalyst activation can be accomplished with standard metallocene catalyst activators. Olefin polymerization is exemplified.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 10/00, 4/68, C07F 9/00		A1	(11) International Publication Number: WO 98/34964 (43) International Publication Date: 13 August 1998 (13.08.98)
(21) International Application Number: PCT/US98/02246 (22) International Filing Date: 5 February 1998 (05.02.98)		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>With amended claims.</i>	
(30) Priority Data: 08/798,412 7 February 1997 (07.02.97) US		Date of publication of the amended claims: 8 October 1998 (08.10.98)	
(71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US).			
(72) Inventors: MURPHY, Vincent, John; Apartment No. 11F, 20800 Homestead Road, Cupertino, CA 95014 (US). TURNER, Howard, W.; 21583 LaPlaya Court, Cupertino, CA 95014 (US).			
(74) Agents: MULLER, William, G. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).			

(54) Title: GROUP 5 TRANSITION METAL COMPOUNDS

(57) Abstract

The invention addresses Group 5 metal compounds suitable as polymerization catalysts characterized by comprising one Group 15 element polyanionic ancillary ligand and three single or multidentate univalent ligands comprising Group 14-16 elements bound to the Group 5 metal, but excluding cyclopentadienyl ligands. The invention Group 5 metal compounds can be generically represented by the chemical symbols: (1) [RJ]MR'3, and (2) [(RJ)Yn(X)]MR'2, where M is a Group 5 transition metal, preferably vanadium; J is a Group 15 heteroatom ligand covalently bound to M, preferably nitrogen; R is a substituted or unsubstituted aryl, hydrocarbyl or organometalloyd group covalently bound to J; each R' is, independently, a uninegative ligand, e.g., substituted or unsubstituted aryl, substituted or unsubstituted linear or cyclic hydrocarbyl, silyl, hydride or substituted or unsubstituted organometalloyd group; X is a univalent single or multidentate ancillary ligand comprising at least one Group 14-16 element covalently bound to M; and, Y is an optional covalent bridging group linking R and X, comprising at least one Group 14-16 element, n = 1 when X is covalently linked to R and n=0 when X is not covalently linked to R. Catalyst activation can be accomplished with standard metallocene catalyst activators. Olefin polymerization is exemplified.

-1-

TITLE: GROUP 5 TRANSITION METAL COMPOUNDS

5

TECHNICAL FIELD

10 This invention relates to organometallic compounds comprising a Group 15 polyanionic ancillary ligand covalently bound to a Group 5 metal center, particularly those suitable for catalysis of olefin polymerization.

BACKGROUND OF THE INVENTION

15 Coordination polymerization of olefinically unsaturated monomers is well known and has led to the great proliferation of thermoplastic compositions of matter from olefins, such as polyethylene, polypropylene, and ethylene propylene rubber. Early pioneers utilized the early transition metal compounds, particularly those of the Group 4 metals, with such activators as aluminum alkyl compounds. Later developments extended this work to bulky ancillary ligand-containing (e.g., η -cyclopentadienyl) transition metal compounds ("metallocenes") with activators such as alkyl 20 alumoxanes. Representative work addressing polymer molecular weight effects of substituted mono and bis metallocene compounds is described in EP-A 0 129 368 and its counterpart U.S. patent 5,324,800. Hetero-atom containing monocyclopentadienyl metallocene compounds are 25 described in U.S. patent 5,057,475 and silicon bridged biscyclopentadienyl metallocene catalysts are described 30

in U.S. patent 5,017,714. Recent developments have shown the effectiveness of ionic catalysts comprised of activated metallocene cations stabilized by compatible noncoordinating anions, see for example U.S. patents 5,278,119 and 5,384,299 and WO 92/00333.

Transition metal polymerization catalyst systems from Group 5-10 metals wherein the active transition metal center is in a high oxidation state and stabilized by low coordination number polyanionic ancillary ligand systems are described in US patent 5,502,124 and its divisional US patent 5,504,049. Suitable low coordination number polyanionic ancillary ligands include both bulky imides and carbolides. Such are said to be suitable alone or in combination with conventional monoanionic ancillary ligands, such as cyclopentadienyl derivatives. Examples 2 and 8 illustrate Group 5 metal catalyst compounds comprising, respectively, (cyclopentadienyl)vanadium(*p*-tolylimido) dichloride and (cyclopentadienyl)niobium(2,6-diisopropyl-phenylimido) di-methyl. Olefin polymerization catalysts from Group 5 or 6 metal imido complexes are also described in EP 0 641 804. The Group 5 metal complexes include one imido ligand and a monoanionic organic group containing a cyclopentadienyl nucleus. Example 1 illustrates the preparation of (cyclopentadienyl)vanadium (*p*-tolylimido) dichloride and the Tables on pages 7-9 illustrate polymerization using it.

Effective olefin polymerization catalysts based upon vanadium alkyl complexes in which the metal center is stabilized in its highest oxidation state are elusive since there are no well established procedures for the synthesis of such compounds. Difficulties associated with the synthesis of vanadium alkyls in which the metal center is stabilized in its highest oxidation state are well documented. See for example, Buijink, J. J. Organomet. Chem. 1995, 497, 161-170, Devore, D. D. J. Am. Chem. Soc., 1987, 109, 7408-7416.

15

It would therefore be desirable to provide vanadium alkyl complexes in which the vanadium metal center is stabilized in its highest oxidation state by (a) a low coordination number polyanionic ligand and (b) and suitable additional ancillary ligands.

INVENTION DISCLOSURE

This invention is directed to Group 5 metal compounds, preferably vanadium, suitable for activation as polymerization catalysts and characterized by comprising one polyanionic ancillary ligand and three single or multidentate uninegative ligands, excluding cyclopentadienyl ligands. The polyanionic ancillary ligand will comprise a Group 15 element covalently bound

to the Group 5 metal and the uninegative ligands will comprise Group 14 - 16 elements as single or multidentate ligands bound to the Group 5 metal. The invention includes a polymerization process characterized by comprising contacting one or more monomers polymerizable by coordination or carbocationic polymerization under suitable polymerization conditions with these catalyst compositions.

10

BEST MODE AND EXAMPLES OF THE INVENTION

The invention Group 5 metal compounds described above can be generically represented by the following symbols:

15

(1) $[RJ]MR'_3$, and

(2) $[(RJ)Y_n(X)]MR'_2$


20

where M is a Group 5 metal; J is a Group 15 heteroatom ligand covalently bound to M; R is a substituted or unsubstituted aryl, hydrocarbyl or organometalloid group covalently bound to J, preferably substituted or unsubstituted aryl or alicyclic hydrocarbyl; each R' is, independently, a uninegative ligand, e.g., substituted or unsubstituted aryl, substituted or unsubstituted linear or cyclic hydrocarbyl, silyl, hydride or substituted or unsubstituted organometalloid group, additionally any two R' maybe joined to form a metallocycle; X is a univalent single or multidentate ancillary ligand comprising at

least one Group 14 - 16 element covalently bound to M; and, Y is an optional covalent bridging group linking R and X, comprising at least one Group 14 - 16 element, n = 1 when X is covalently linked to R and n=0 when X is not covalently linked to R. The term "substituted" means that one or more hydrogen atoms on the hydrocarbyl, aryl or organometalloid group is replaced by a C₁-C₂₀ hydrocarbyl radical or any of an aryl radical, a halide radical, a phosphido radical, an alkoxide or aryloxide radical (preferably having from one twenty carbon atoms), or any other radical containing a Lewis acidic or basic functionality.


In an embodiment, the univalent ligands comprise one ligand comprising a Group 15-16 element and two ligands comprising Group 14 elements, the elements bound to the Group 5 metal.

The Group 5 metal compounds of the invention having one polyanionic ancillary ligand and three univalent single or multidentate ligands can be represented by the figures below:



wherein each of the labeled substituents are as defined above. Suitable single dentate ligands X include those in the group consisting of aryloxides or alkoxides [-OR¹], siloxides [-OSiR¹₃], thiols [-SR¹], amides [-NR¹₂], and phosphides [-PR¹₂], where R¹ can be any member within the group defined above for R'. Suitable multidentate ligands are represented by the bidentate carboxylates


[-O₂CR¹], carboxythiolates [-S₂CR¹], triflates [-O₃SR¹], acetylacetates [η^2 -R¹COCR¹COR¹], amidates [η^2 -R¹NCR¹NR¹], Group 15 or 16 *ortho*-substituted pyridines (illustration (a)), Group 15 or 16 substituted hydrocarbyls (illustration (b)), Group 15 or 16 substituted aryls (illustration (c)),



where x=0-6, each x is selected independently, and E is independently a Group 15 element (in which case z may be 1 or 2) or a Group 16 element (in which case z may be 0 or 1).


In addition, multidentate ligands such as shown in illustration (d) may be used

(d)




5

Representative (1) and (2) compounds include the following.



10

Representative (2) compounds include the following.



5

wherein E is either a Group 15 element (in which case $z=1$) or a Group 16 element (in which case $z=0$); x, R' is defined as above.

10

The catalyst compounds of the invention may be prepared in high yields using the following techniques. For vanadium, for example, the synthesis can begin with a reaction between vanadium oxytrichloride and a suitable organic molecule such as an isocyanate, an amine, or an alkali metal salt of an amine (See Scheme 1).


15

Scheme 1



5 Further chemical modifications can be made through ligand exchange reactions such as metathesis. (See Scheme 2).

Scheme 2



For instance, treatment of an arylimido-group (V) trialkyl complex with one equivalent of a protic reagent such as an amine or an alcohol, leads to elimination of 15 one equivalent of alkane along with ligation of an amido group to form compounds of the invention. Alternatively the compounds of the invention may be prepared by initial substitution of a single chloride ligand from an arylimido-group (V) metal trichloride by reaction with, 20 for example, an alkali metal salt of a alcohol, leading to the formation of an arylimido-group (V) metal (alkoxy) dichloride. Alkylation of the arylimido-group (V) (alkoxy) dichloride leads to formation of the compounds of the invention. A previous attempt to prepare 25 compounds of these types has involved direct addition of alkylating agents to (tolylimido)vanadium (V)

-10-

trichloride. This reaction led to the formation of (tolylimido)vanadium (V) (*bis*-methyltrimethylsilyl) chloride, see for example: Devore, D. D., *J. Am. Chem. Soc.*, 1987, 109, 7408-7416. The methods described above for the preparation of the compounds of the invention offer greater versatility and control for steric and electronic variations around the metal center.


In addition, the use of (a) a low coordination number polyanionic ligand and (b) and an additional ancillary ligand which can donate lone pair π -electrons to the vanadium metal center (see representative examples of formula (2)) leads to enhanced stability thereby enabling the formation of vanadium alkyl complexes in which the vanadium metal center is stabilized in its highest oxidation state. This unexpected finding is corroborated by (1) the paucity of vanadium alkyl complexes in which the vanadium metal center is stabilized in its highest oxidation state and (2) reports confirming the instability of vanadium (V) alkyl complexes which do not possess the ancillary ligand arrangements of the compounds of the invention. For example, tert-butylimido-cyclopentadienyl vanadium dimethyl is reported to be thermally unstable, decomposing within minutes at room temperature. See Preuss, F. Z. Naturforsch 1990, 45b, 191-198.

Further details may be found in *Progress in Inorganic Chemistry*, Volume 42, 1994, 239-482.

The Group 5 metal compounds according to the invention may be activated for polymerization catalysis in any manner sufficient to allow coordination or cationic polymerization. This can be achieved for 5 coordination polymerization when one ligand can be abstracted and another will either allow insertion of the unsaturated monomers or will be similarly abstractable for replacement with an that allows insertion of the unsaturated monomer, e.g., alkyl, silyl, or hydride. The 10 traditional activators of coordination polymerization art are suitable, those typically include Lewis acids such as Ziegler organometallic cocatalysts and alumoxane compounds, and ionizing, anion precursor compounds that abstract one so as to ionize the Group 5 metal center 15 into a cation and provide a counter-balancing noncoordinating anion.

The Ziegler cocatalyst will typically be a organometallic compound of a metal of Groups 1, 2, 12 or 20 13 of the Periodic table of elements. Preferred are organoaluminum compounds selected from the group consisting of aluminum alkyl, aluminum alkyl halide and aluminum halide. These can be represented by the formulae:

25



wherein R^2 is independently a hydride or C_1 to C_{10} hydrocarbyl radicals including aliphatic, alicyclic or

aromatic hydrocarbon radicals, X' is a halogen and s is an integer from 0 to 3; and,

5 $\text{Al}_2\text{R}^2\text{X}'_3$, which are hydrocarbylaluminum sesqui-halides.

10 Examples include triethylaluminum, triisobutylaluminum, diethyl aluminumchloride, $\text{Al}_2\text{Et}_3\text{Cl}_3$, and $\text{Al}_2(\text{i-Bu})_3\text{Cl}_3$.

15

Alkylalumoxanes and modified alkylalumoxanes are suitable as catalyst activators, particularly for the invention metal compounds comprising halide ligands. The alumoxane component useful as catalyst activator typically is an oligomeric aluminum compound represented by the general formula $(\text{R}''-\text{Al}-\text{O})_n$, which is a cyclic compound, or $\text{R}''(\text{R}''-\text{Al}-\text{O})_n\text{AlR}''_2$, which is a linear compound. In the general alumoxane formula R'' is independently a C_1 to C_{10} alkyl radical, for example, methyl, ethyl, propyl, butyl or pentyl and "n" is an integer from 1 to about 50. Most preferably, R'' is methyl and "n" is at least 4. Alumoxanes can be prepared by various procedures known in the art. For example, an aluminum alkyl may be treated with water dissolved in an inert organic solvent, or it may be contacted with a hydrated salt, such as hydrated copper sulfate suspended in an inert organic solvent, to yield an alumoxane. Generally, however prepared, the reaction of an aluminum alkyl with a limited amount of water yields a mixture of the linear and cyclic species of the alumoxane.

Methylalumoxane and modified methylalumoxanes are preferred. For further descriptions see, U.S. patents No. 4,665,208, 4,952,540, 5,041,584, 5,091,352, 5,206,199, 5,204,419, 4,874,734, 4,924,018, 4,908,463, 5 4,968,827, 5,329,032, 5,248,801, 5,235,081, 5,157,137, 5,103,031 and EP 0 561 476 A1, EP 0 279 586 B1, EP 0 516 476 A, EP 0 594 218 A1 and WO 94/10180.

10

When the activator is an alumoxane, the preferred transition metal compound to activator molar ratio is from 1:2000 to 10:1, more preferably from about 1:500 to 15 10:1, even more preferably from about 1:250 to 1:1 and most preferably from about 1:100 to 1:1.

The term "noncoordinating anion" is recognized to mean an anion which either does not coordinate to the metal cation or which is only weakly coordinated to it 20 thereby remaining sufficiently labile to be displaced by a neutral Lewis base, such as an olefinically or acetylenically unsaturated monomer.

Descriptions of ionic catalysts, those comprising a 25 transition metal cation and a noncoordinating anion, suitable for coordination polymerization appear in the early work in U.S. patents 5,064,802, 5,132,380, 5,198,401, 5,278,119, 5,321,106, 5,347,024, 5,408,017, 5,599,671, and international publications WO 92/00333 and 30 WO 93/14132. These teach a preferred method of

WO 98/34964

PCT/US98/02246

-14-

preparation wherein metallocenes are protonated by noncoordinating anion precursors such that an alkyl/hydride group is abstracted by protonation from a transition metal to make it both cationic and charge-balanced by the noncoordinating anion. Since the abstraction and insertion ligands of such metallocenes also may be ligands of the Group 5 metal compounds of the invention, similar methods of preparation as active polymerization catalyst components may be followed.

10

The use of ionizing ionic compounds not containing an active proton but capable of producing both the active Group 5 metal cation and an noncoordinating anion is also useful. See, EP-A-0 426 637, EP-A-0 573 403 and U.S. patent 5,387,568 for instructive ionic compounds. Reactive cations of the ionizing ionic compounds, other than the Bronsted acids, include ferrocenium, silver, tropylium, triphenylcarbenium and triethylsilylium, or alkali metal or alkaline earth metal cations such as sodium, magnesium or lithium cations. A further class of noncoordinating anion precursors suitable in accordance with this invention are hydrated salts comprising the alkali metal or alkaline earth metal cations and a non-coordinating anion as described above. The hydrated salts can be prepared by reaction of the metal cation-noncoordinating anion salt with water, for example, by hydrolysis of the commercially available or readily synthesized $\text{LiB}(\text{pfp})_4$ which yields $[\text{Li} \bullet \text{xH}_2\text{O}] [\text{B}(\text{pfp})_4]$, where (pfp) is pentafluorophenyl or perfluorophenyl.

20
25
30

-15-

Any metal or metalloid capable of forming a coordination complex which is resistant to degradation by water (or other Bronsted or Lewis Acids) may be used or contained in the noncoordinating anion. Suitable metals 5 include, but are not limited to, aluminum, gold, platinum and the like. Suitable metalloids include, but are not limited to, boron, phosphorus, silicon and the like.

10

An additional method of making the active polymerization catalysts of this invention uses ionizing 15 anion pre-cursors which are initially neutral Lewis acids but form a Group 5 metal cation and the noncoordinating anion upon ionizing reaction with the invention compounds, for example tris(pentafluorophenyl) boron acts to abstract a hydrocarbyl, hydride or silyl ligand to 20 yield a Group 5 metal cation and stabilizing noncoordinating anion, see EP-A-0 427 697 and EP-A-0 520 732 for illustration utilizing Group 4 metallocene compounds. See also the methods and compounds of EP-A-0 495 375.

25

When the cation portion of an ionic noncoordinating 30 anion precursor is a Bronsted acid such as protons or

protonated Lewis bases (excluding water), or a reducible Lewis acid such as ferrocenium or silver cations, or alkaline metal or alkaline earth metal cations such as those of sodium, magnesium or lithium cations, the transition metal to activator molar ratio may be any ratio, but preferably from about 10:1 to 1:10, more preferably from about 5:1 to 1:5, even more preferably from about 2:1 to 1:2 and most preferably from about 1.2:1 to 1:1.2 with the ratio of about 1:1 being the most preferred.

Thus suitable active catalyst complexes for coordination polymerization can be prepared by activation with the traditional metallocene activators, typically the alkylaluminum halides, alkylalumoxanes and ionizing boron or aluminum compounds known in the art. The active catalysts thus are catalytically active components comprising complexes derived from the Group 5 metal compounds containing the ancillary ligands according to the invention, and aluminum alkyls, alumoxanes or noncoordinating anions. The carbocationic catalyst complexes according to the invention will be those prepared with the ionizing noncoordinating anion precursor compounds.

25

The catalyst complexes of the invention are useful in polymerization of unsaturated monomers conventionally known to be polymerizable under either coordination polymerization conditions or cationic polymerization conditions using metallocenes. Such conditions are well

known and include solution polymerization, slurry polymerization, and low, medium and high pressure gas-phase polymerization. The catalyst of the invention may be supported and as such will be particularly useful in the known operating modes employing fixed-bed, moving-bed, fluid-bed, or slurry processes conducted in single, 5 series or parallel reactors.

When using the catalysts of the invention, 10 particularly when immobilized on a support, the total catalyst system will generally additionally comprise one or more scavenging compounds. The term "scavenging compounds" as used in this application and its claims is meant to include those compounds effective for removing 15 polar impurities from the reaction environment. Impurities can be inadvertently introduced with any of the polymerization reaction components, particularly with solvent, monomer and catalyst feed, and adversely affect catalyst activity and stability. It can result in 20 decreasing or even elimination of catalytic activity, particularly when ionizing anion pre-cursors activate the catalyst system. The polar impurities, or catalyst poisons include water, oxygen, metal impurities, etc. Preferably steps are taken before provision of such into 25 the reaction vessel, for example by chemical treatment or careful separation techniques after or during the synthesis or preparation of the various components, but some minor amounts of scavenging compound will still normally be used in the polymerization process itself.

WO 98/34964

PCT/US98/02246

-18-

Typically the scavenging compound will be an organometallic compound such as the Group-13 organometallic compounds of U.S. patents 5,153,157, 5,241,025 and WO-A-91/09882, WO-A-94/03506, WO-A-93/14132, and that of WO 95/07941. Exemplary compounds include triethyl aluminum, triethyl borane, triisobutyl aluminum, methylalumoxane, isobutyl aluminumoxane, and tri-n-octylaluminum. Those scavenging compounds having bulky or C₆-C₂₀ linear hydrocarbyl substituents covalently bound to the metal or metalloid center being preferred to minimize adverse interaction with the active catalyst. Examples include triethylaluminum, but more preferably, bulky compounds such as triisobutylaluminum, trisoprenylaluminum, and long-chain linear alkyl-substituted aluminum compounds, such as tri-n-hexylaluminum, tri-n-octylaluminum, or tri-n-dodecylaluminum. When alumoxane is used as activator, any excess over the amount needed to activate the catalysts present will act as scavenger compounds and additional scavenging compounds may not be necessary. Alumoxanes also may be used in scavenging amounts with other means of activation, e.g., methylalumoxane and trisobutyl-aluminoxane. The amount of scavenging agent to be used with Group 5 catalyst compounds of the inventions is minimized during polymerization reactions to that amount effective to enhance activity and avoided altogether if the feeds can be sufficiently free of adventitious impurities.

The catalyst according to the invention may be supported for use in gas phase, bulk, slurry polymerization processes, or otherwise as needed. Numerous methods of support are known in the art for copolymerization processes for olefins, particularly for catalysts activated by alumoxanes, any is suitable for the invention process in its broadest scope. See, for example, U.S. patents 5,057,475 and 5,227,440. An example of supported ionic catalysts appears in WO 94/03056. A particularly effective method is that described in U.S. Patent No. 5,643,847 and WO 96/04319. A bulk, or slurry, process utilizing supported, invention Group 5 metal compounds activated with alumoxane co-catalysts can be utilized as described for ethylene-propylene rubber in U.S. patents 5,001,205 and 5,229,478, these processes will additionally be suitable with the catalyst systems of this application. Both inorganic oxide and polymeric supports may be utilized in accordance with the knowledge in the field. See U.S. patents 5,422,325, 5,427,991, 5,498,582, 5,466,649, and international publications WO 93/11172 and WO 94/07928.

In an embodiment, the catalyst is supported on a solid porous support.

In preferred embodiments of the process for this invention, the catalyst system is employed in liquid phase (solution, slurry, suspension, bulk phase or combinations thereof), in high pressure liquid or

-20-

supercritical fluid phase, or in gas phase. Each of these processes may be employed in singular, parallel or series reactors. The liquid processes comprise contacting olefin monomers with the above described catalyst system in a suitable diluent or solvent and allowing said monomers to react for a sufficient time to produce the invention copolymers. Hydrocarbyl solvents are suitable, both aliphatic and aromatic, hexane and toluene are preferred. Halocarbon solvents, e.g., methylene chloride will additionally be suitable. Bulk and slurry processes are typically done by contacting the catalysts with a slurry of liquid monomer, the catalyst system being supported. Gas phase processes typically use a supported catalyst and are conducted in any manner known to be suitable for ethylene homopolymers or copolymers prepared by coordination polymerization. Illustrative examples may be found in U.S. patents 4,543,399, 4,588,790, 5,028,670, 5,382,638, 5352,749, 5,436,304, 5,453,471, and 5,463,999, and WO 95/07942.

20

The use of alkyl halide promoters, such as hexachlorocyclopentadiene, ethyltrichloroacetate or benzoyl chloride with Ziegler vanadium catalysts to enhance performance (i.e., increase yields of polyethylene) is well known and may be used with the catalysts of this invention. See, for example, U.S. patents 4,232,140, 4,508,842, and EP-0 44 119 and EP-0 196 830.

Generally speaking the polymerization reaction
5 temperature can vary from about -50°C to about 250°C. Preferably the reaction temperature conditions will be from -20°C to 220°, more preferably below 200°C. The pressure can vary from about 1 mm Hg to 2500 bar, preferably from 0.1 bar to 1600 bar, most preferably from
10 1.0 to 500 bar. Where lower molecular weight copolymers, e.g., Mn < 10,000, are sought it will be suitable to conduct the reaction processes at temperatures above about 0°C and pressures under 500 bar. The multiboron activators of U.S. patent 5,278,119 can additionally be
15 employed to facilitate the preparation of the low molecular weight copolymers of the invention.

Linear polyethylene, including high and ultra-high molecular weight polyethylenes, including both homo- and
20 copolymers with other alpha-olefin monomers, alpha-olefinic and/or non-conjugated diolefins, for example, C₃-C₂₀ olefins, diolefins or cyclic olefins, are produced by adding ethylene, and optionally one or more of the other monomers, to a reaction vessel under low pressure
25 (typically < 50 bar), at a typical temperature of 20-250 °C with the invention catalyst that has been slurried with a solvent, such as heptane or toluene. Heat of polymerization is typically removed by cooling. Gas phase polymerization can be conducted, for example, in a
30 continuous fluid bed gas-phase reactor operated at 2000-

3000 kPa and 60-160 °C, using hydrogen as a reaction modifier (100-200 ppm), C₄-C₈ comonomer feedstream (0.5-1.2 mol%), and C₂ feedstream (25-35 mol%). See, U.S. patents 4,543,399, 4,588,790; 5,028,670 and 5,405,922 and 5,462,999.

Ethylene- α -olefin (including ethylene-cyclic olefin and ethylene- α -olefin-diolefin) elastomers of high molecular weight and low crystallinity can be prepared utilizing the catalysts of the invention under traditional solution polymerization processes or by introducing ethylene gas into a slurry utilizing the α -olefin or cyclic olefin or mixture thereof with other monomers, polymerizable and not, as a polymerization diluent in which the invention catalyst is suspended. Typical ethylene pressures will be between 10 and 1000 psig (69-6895 kPa) and the polymerization diluent temperature will typically be between -10-160 °C. The process can be carried out in a stirred tank reactor, or more than one operated in series or parallel. See the general disclosure of U.S. patent 5,001,205 for general process conditions. See also, U.S. patent no. 5,696,213 and 5,625,016.

-23-

Pre-polymerization of the supported catalyst of the invention may also be used for further control of polymer particle morphology in typical slurry or gas phase reaction processes in accordance with conventional teachings. For example such can be accomplished by pre-polymerizing a C₂-C₆ alpha-olefin for a limited time, for example, ethylene is contacted with the supported catalyst at a temperature of -15 to 30 °C. and ethylene pressure of up to about 250 psig (1724 kPa) for 75 min. to obtain a polymeric coating on the support of polyethylene of 30,000-150,000 molecular weight. The pre-polymerized catalyst is then available for use in the polymerization processes referred to above. The use of polymeric resins as a support coating may additionally be utilized, typically by suspending a solid support in dissolved resin of such material as polystyrene with subsequent separation and drying.

20

Other olefinically unsaturated monomers besides those specifically described above may be polymerized using the catalysts according to the invention either by coordination or carbocationic polymerization, for example, styrene, alkyl-substituted styrene, ethylidene norbornene, norbornadiene, dicyclopentadiene, and other olefinically-unsaturated monomers, including other cyclic olefins, such as cyclopentene, norbornene, alkyl-substituted norbornenes, and including isobutylene,

isoprene, butadiene, vinyl ethers, vinyl carbazoles, etc. Additionally, alpha-olefinic macromonomers of up to 100 mer units, or more, may also be incorporated by copolymerization.

In an embodiment, the monomers are selected from the group consisting of ethylene, alpha-olefins, cyclic olefins, non-conjugated diolefins, acetylenically unsaturated monomers, olefinically unsaturated aromatic monomers, and $C_{20}-C_{100}$ macromers. In another embodiment, the monomers comprise ethylene and at least one cyclic olefin.

Lubricating oil additive compositions can be prepared advantageously when low molecular weight alpha-olefin copolymers having vinyl or vinylidene terminal unsaturation are prepared with the catalysts of the invention. See the disclosures of U.S. patent 5,498,809 and international patent applications WO 93/24359, WO 94/19436 and WO 94/13715 for further information as to low molecular weight alpha-olefin polymers.

In a similar manner, but utilizing higher molecular weight ($10,000 < M_n < 300,000$) alpha-olefin/diolefin copolymer having a crystallinity low enough to permit of oil solubility (e.g., < 40% crystallinity), as in U.S. patent no. 5,696,213 and 5,625,016, multifunctional viscosity modifying lubricating oil additives can be produced. See the descriptions of lubricating oil modifiers and lubricating oil compositions in U.S. patent nos. 4,749,505, 4,772,406 and WO-A-93/12148.

Carbocationic polymerization can be effected by use of the catalysts of the invention when converted to active cationic species by activating ionization. Such polymerization techniques are well known in the art, see

5 Kennedy, J. P., Carbocationic Polymerization of Olefins : A Critical Inventory (John Wiley & Sons, 1975). See also, Baird, Michael C., et al, $\eta^5\text{-C}_5\text{Me}_5\text{TiMe}_3\text{B}(\text{C}_6\text{F}_5)_3$: A **Carbocationic Olefin Polymerization Initiator Masquerading as a Ziegler-Natta Catalyst**, *J. Am. Chem. Soc.* **1994**, *116*, 6435-6436, for conditions under which the first row metal Ti in stable metallocene cationic form was used for carbocationic polymerization.

15

The catalyst compositions of the invention can be used as described above individually for coordination or carbocationic polymerization or can be mixed to prepare polymer blends with other known olefin polymerization catalyst compounds. By selection of monomers, blends of coordination catalyst compounds or blends of carbocationic catalyst compounds, or any together, polymer blends can be prepared under polymerization conditions analogous to those using individual catalyst compositions. Polymers having increased MWD for improved processing and other traditional benefits available from polymers made with mixed catalyst systems can thus be achieved.

The following examples are presented to illustrate the foregoing discussion. All parts, proportions and percentages are by weight unless otherwise indicated. Ambient temperatures were used for the polymerization 5 examples unless otherwise noted. Although the examples may be directed to certain embodiments of the present invention, they are not to be viewed as limiting the invention in any specific respect. In these examples certain abbreviations are used to facilitate the 10 description. These include standard chemical abbreviations for the elements and certain commonly accepted abbreviations, such as : Me = methyl, Et = ethyl, Prⁱ = isopropyl, Bu = butyl, Ph = phenyl, and THF = tetrahydrofuran.

15

Example 1 - Catalyst Preparation

(a) Preparation of (2,6-Prⁱ₂C₆H₃N)VC₁₃•THF

20 A solution of 25 g of VOCl₃ (0.14 mol) and 25 g 2,6-diisopropylphenylisocyanate (0.12 mol) in 100 ml. octane were refluxed together for 24 hours. Subsequent solvent removal under reduced pressure yielded a dark green oily solid. This solid was extracted with 50 mL of 25 pentane, filtered and treated with approximately 20 mL of THF to produce a sandy colored precipitate. Collection by filtration yielded 33.6 g of (2,6-Prⁱ₂C₆H₃N)VC₁₃•THF. A further 6.0 g was obtained by a second extraction of the remaining green oily solid, subsequent treatment with

WO 98/34964

PCT/US98/02246

-20-

supercritical fluid phase, or in gas phase. Each of these processes may be employed in singular, parallel or series reactors. The liquid processes comprise contacting olefin monomers with the above described catalyst system in a suitable diluent or solvent and allowing said monomers to react for a sufficient time to produce the invention copolymers. Hydrocarbyl solvents are suitable, both aliphatic and aromatic, hexane and toluene are preferred. Halocarbon solvents, e.g., 5 methylene chloride will additionally be suitable. Bulk and slurry processes are typically done by contacting the catalysts with a slurry of liquid monomer, the catalyst system being supported. Gas phase processes typically use a supported catalyst and are conducted in any manner known to be suitable for ethylene homopolymers or 10 copolymers prepared by coordination polymerization. Illustrative examples may be found in U.S. patents 15 4,543,399, 4,588,790, 5,028,670, 5,382,638, 5352,749, 5,436,304, 5,453,471, and 5,463,999, and WO 95/07942. 20 Each is incorporated by reference for purposes of U.S. patent practice.

The use of alkyl halide promoters, such as hexachlorocyclopentadiene, ethyltrichloroacetate or 25 benzoyl chloride with Ziegler vanadium catalysts to enhance performance (i.e., increase yields of polyethylene) is well known and may be used with the catalysts of this invention. See, for example, U.S. patents 4,232,140, 4,508,842, and EP-0 44 119 and EP-0

THF and isolation by filtration. Total yield 39.6 g (0.10 Mol), 69% based on vanadium.

(b) Preparation of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$

5

A solution of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{VCl}_3\text{-THF}$ (20 g, 0.049 mol) in 50 mL hexane was cooled to -30 °C. A solution of $\text{C}_6\text{H}_5\text{CH}_2\text{MgCl}$ (148 mL, 1M solution in diethylether, 0.148 mol) was added dropwise over a period of 15 minutes leading to a change in the color of the solution from green to red. The resultant red solution was allowed to warm up to room temperature whereupon it was filtered and the solvent removed under a stream of nitrogen. Recrystallization of the resultant crude oily solid from hexane yielded $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$ as a dark red crystalline solid (16 g, 0.032 mol, 65%).

(c) Preparation of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{OC}(\text{CF}_3)_3)_2(\text{CH}_2\text{C}_6\text{H}_5)_2$

20

A solution of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$ (0.53 g, 1.0 mmol) in 20 mL hexane was treated with $(\text{CF}_3)_3\text{COH}$ (138 μL , 1.0 mmol) and stirred overnight. Solvent removal under a stream of nitrogen left an oily brown solid. Recrystallization from a hexane solution at -30 °C produced large dark brown crystals of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{OC}(\text{CF}_3)_3)_2(\text{CH}_2\text{C}_6\text{H}_5)_2$ in 60% yield (0.40 g, 0.6 mmol).

(d) Preparation of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{NPhMe})(\text{CH}_2\text{C}_6\text{H}_5)_2$

A solution of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$ (0.3 g, 0.6 mmol) in 20 mL hexane was treated with N-methylaniline (65 μL , 0.6 mmol) and stirred for 48 hours. Solvent removal under a stream of nitrogen left an oily brown solid. Recrystallization from a hexane solution at -30°C produced red crystals of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{NPhMe})(\text{CH}_2\text{C}_6\text{H}_5)_2$ in 55% yield (0.17 g, 0.33 mmol).

(e) Preparation of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{OC}_6\text{H}_3\text{-2,6-Pr}^i_2)(\text{CH}_2\text{C}_6\text{H}_5)_2$

A solution of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$ (1.2g, 2.4 mmol) in 20 mL dichloromethane was treated with 2,6-Prⁱ₂C₆H₃OH (450 μL , 2.4 mmol) and stirred for 48 hours. Solvent removal under a stream of nitrogen left an oily red-brown solid. Recrystallization from a hexane solution at -30°C produced dark red crystals of $(2,6\text{-Pr}^i_2\text{C}_6\text{H}_3\text{N})\text{V}(\text{OC}_6\text{H}_3\text{-2,6-Pr}^i_2)(\text{CH}_2\text{C}_6\text{H}_5)_2$ in 75% yield (1.05 g, 1.8 mmol).

(f) Preparation of $(2,6\text{-Me}_2\text{-C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$

A solution of $(2,6\text{-Me}_2\text{-C}_6\text{H}_3\text{N})\text{VCl}_3\text{-THF}$ (0.50 g, 1.4 mmol) in 20 mL of hexane was cooled to -30°C . A solution of C₆H₅CH₂MgCl (4.3 mL, 1M solution in diethylether, 4.3

mmol) was added dropwise over a period of 15 mins leading to a change in the color of the solution from green to red. The resultant red solution was allowed to warm up to room temperature whereupon it was filtered and the solvent removed under a stream of nitrogen. Recrystallization of the resultant crude oily solid from hexane yielded $(2,6\text{-Me}_2\text{-C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$ as a dark red crystalline solid (0.25 g, 0.6 mmol, 40%).

10

Example 2 - Polymerization Examples

(a) A catalyst solution containing 10 mg $(2,6\text{-Pr}^i_2\text{-C}_6\text{H}_3\text{N})\text{V}(\text{CH}_2\text{C}_6\text{H}_5)_3$ and 10 mg $\text{B}(\text{C}_6\text{F}_5)_3$ was prepared in 3 mL of toluene. The catalyst solution, along with 400 mL of hexane, and 45 mL 1-hexene was added to a 1 liter stainless-steel autoclave which had been previously purged with nitrogen. The autoclave was pressurized with ethylene at 150 psi and the mixture was stirred at 30°C for 1 hour whereupon the autoclave was vented. 4.6 g of polymer was produced using this procedure.

(b) A catalyst solution containing 50 mg $(2,6\text{-Pr}^i_2\text{-C}_6\text{H}_3\text{N})\text{V}(\text{NPhMe})(\text{CH}_2\text{C}_6\text{H}_5)_2$ and 80 mg $[\text{PhNHMe}_2][\text{B}(\text{C}_6\text{F}_5)_4]$ was prepared in 5 mL of toluene in a serum capped bottle. Ethylene was bubbled through the solution for 10 minutes causing the precipitation of polymer. The bottle was opened and the contents diluted with water. The solid polymer was washed with acetone and dried. The yield of polyethylene was 1g.

(c) A catalyst solution containing 10 mg (2,6-Prⁱ₂-C₆H₃N)V(OC(CF₃)₃)(CH₂C₆H₅)₂ in 5 mL of toluene was treated with 5 mL of a solution containing 10 wt% methylalumoxane. The catalyst solution, along with 400 mL of hexane and 45mL 1-hexene was added to a 1 liter stainless-steel autoclave which had been previously purged with nitrogen. The autoclave was pressurized with ethylene at 100 psi and the mixture was stirred at 25°C for 1 hour whereupon the autoclave was vented. 7.5 g of polymer was produced from this procedure.

(d) A catalyst solution containing 50 mg (2,6-Prⁱ₂-C₆H₃N)V(OC₆H₃-2,6-Prⁱ₂)(CH₂C₆H₅)₂ and 78 mg [Ph₃C][B(C₆F₅)₄] was prepared in 5 mL of toluene. The catalyst solution, along with 400 mL of hexane and 45 mL 1-hexene was added to a 1 liter stainless-steel autoclave which had been previously purged with nitrogen. The autoclave was pressurized with ethylene at 150 psi and the mixture was stirred at 30°C for 1 hour whereupon the autoclave was vented. 1 g of polymer was produced from this procedure.

(e) In this example a mixture of 20 mg (2,6-Me₂-C₆H₃N)V(CH₂C₆H₅)₃ and 25 mg [PhNHMe₂][B(C₆F₅)₄] was prepared in 5 mL of toluene. 10 mL 1-hexene was then added to the resultant mixture. After 1 hour the solvent was removed under a stream of nitrogen and the solid polymer was washed with acetone and dried. The yield of polyhexene was 1 g.

CLAIMS:

1. An olefin polymerization catalyst composition comprising the reaction product of 1) a Group 5 metal compound stabilized in its highest metal oxidation state comprising one Group 15 element polyanionic ligand and three single or multidentate univalent ligands comprising Group 14-16 elements bound to the Group 5 metal, but excluding cyclopentadienyl ligands, wherein at least one of said univalent ligands comprises a Group 14 element bound to the Group 5 metal, and 2) a catalyst activator compound.
- 15 2. The catalyst composition of claim 1 wherein said univalent ligands comprise one ligand comprising a Group 15-16 element and two ligands comprising Group 14 elements, said elements bound to the Group 5 metal.
- 20 3. The catalyst composition of claim 1 wherein said Group 5 metal compounds are represented by the symbols :
 - 25 (1) $[(RJ)MR']_n$, and
 - (2) $[(RJ)Y_n(X)]MR'$,where M is a Group 5 transition metal; J is a Group 15 heteroatom ligand covalently bound to M; R is a substituted or unsubstituted aryl, hydrocarbyl or organometalloid group covalently bound to J; each

-32-

R' is, independently, a uninegative ligand which is substituted or unsubstituted aryl, substituted or unsubstituted linear or cyclic hydrocarbyl, silyl, hydride or substituted or unsubstituted organometalloid group; X is a univalent single or multidentate ligand comprising at least one Group 14 - 16 element covalently bound to M; and, Y is an optional covalent bridging group linking R and X, comprising at least one Group 14 - 16 element, n = 1 when X is covalently linked to R and n=0 when X is not covalently linked to R.

10


15

4. The catalyst composition of claim 1 wherein said Group 5 metal is vanadium.



5. The catalyst composition of claim 3 wherein said Group 5 metal is vanadium.

20

6. The catalyst composition of claim 4 wherein compound 1) is:



25



30

7. The catalyst composition of claim 1 wherein said catalyst activator compound is an alkylalumoxane or an aluminum alkyl.

-33-


8. The catalyst composition of claim 1 wherein said catalyst activator compound is an ionizing noncoordinating anion precursor compound.
- 5
9. A polymerization process characterized by comprising contacting one or more monomers polymerizable by coordination polymerization under suitable coordination polymerization conditions
- 10 with a catalyst composition according to claim 1.
10. The process of Claim 9 wherein said one or more monomers comprise at least one member which is ethylene, α -olefins, cyclic olefins, non-
15 conjugated diolefins, acetylenically unsaturated monomers, olefinically unsaturated aromatic monomers, or C_{20} - C_{100} macromonomers.
11. The process of Claim 10 wherein said one or more
20 monomers comprise at least one member which is ethylene or C_2 - C_{20} α -olefins.
12. The process of Claim 10 wherein said one or more monomers comprise ethylene and at least one
25 cyclic olefin.
13. The process of Claim 10 wherein said catalyst compound additionally comprises a solid porous support.
- 30 14. A polymerization process characterized by comprising contacting one or more monomers

polymerizable by coordination polymerization under suitable polymerization conditions with a catalyst composition according to claim 8.

5 15. A polymerization process characterized by comprising contacting one or more monomers polymerizable by carbocationic polymerization under suitable carbocationic polymerization conditions with a catalyst composition according to claim 8.

10

16. Organometallic compounds represented by the following expression:



15

where M is a Group 5 metal; J is a Group 15 heteroatom ligand covalently bound to M; R is a substituted or unsubstituted aryl or alicyclic hydrocarbyl group covalently bound to J; each R' is, independently, a uninegative ligand which is substituted or unsubstituted aryl, substituted or unsubstituted linear or cyclic hydrocarbyl, silyl, hydride or substituted or unsubstituted organometalloid group; X is a univalent single or multidentate ligand comprising at least one Group 14 - 16 element covalently bound to M; and, Y is an optional covalent bridging group linking R and X, comprising at least one Group 14 - 16 element, n = 1 when X is covalently linked to R and n=0 when X is not covalently linked to R.

20

25

30