



(86) Date de dépôt PCT/PCT Filing Date: 2016/02/01
(87) Date publication PCT/PCT Publication Date: 2016/09/09
(85) Entrée phase nationale/National Entry: 2017/08/08
(86) N° demande PCT/PCT Application No.: EP 2016/052045
(87) N° publication PCT/PCT Publication No.: 2016/139020
(30) Priorité/Priority: 2015/03/05 (EP15157697.2)

(51) Cl.Int./Int.Cl. *C22B 5/00* (2006.01),
C22B 3/44 (2006.01), *C22B 11/00* (2006.01)
(71) Demandeur/Applicant:
HERAEUS DEUTSCHLAND GMBH & CO. KG, DE
(72) Inventeurs/Inventors:
STETTNER, MARTIN, DE;
THIEL, VASCO, DE;
FUCHS ALAMEDA, STEFANIE, DE;
VOSS, STEFFEN, DE
(74) Agent: MACRAE & CO.

(54) Titre : METHODE DE PRODUCTION DE RHODIUM ELEMENTAIRE
(54) Title: METHOD FOR PRODUCING ELEMENTAL RHODIUM

(57) **Abrégé/Abstract:**

Disclosed is a method for synthesizing elemental rhodium, comprising the steps of: (1) providing an aqueous suspension of diethylenetriammonium hexahalorhodate adjusted to a pH between -1 and +2 using hydrohalic acid; (2) adding enough reducing agent to the suspension provided in step (1) for all of the diethylenetriammonium hexahalorhodate to be converted, and letting the reaction continue until the formation of elemental rhodium has been completed; and (3) separating the elemental rhodium formed in step (2) from the aqueous hydrohalic acid composition formed in step (2); halogen being bromine and/or chlorine.



(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges

Eigentum

Internationales Büro

(43) Internationales

Veröffentlichungsdatum

9. September 2016 (09.09.2016)



(10) Internationale Veröffentlichungsnummer

WO 2016/139020 A1

(51) Internationale Patentklassifikation:
C22B 11/00 (2006.01)

(21) Internationales Aktenzeichen: PCT/EP2016/052045

(22) Internationales Anmeldedatum:
1. Februar 2016 (01.02.2016)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
15157697.2 5. März 2015 (05.03.2015) EP

(71) Anmelder: HERAEUS DEUTSCHLAND GMBH &
CO. KG [DE/DE]; Heraeusstr. 12-14, 63450 Hanau (DE).

(72) Erfinder: STETTNER, Martin; Bornfeldstraße 14, 63674
Altenstadt (DE). THIEL, Vasco; Wasserloser Str. 34,
63755 Alzenau (DE). FUCHS ALAMEDA, Stefanie;
Biebertalstr. 28, 63599 Biebergemünd (DE). VOSS,
Steffen; Dolmenring 14, 63694 Limeshain (DE).

(74) Anwalt: HERAEUS IP; Heraeus Holding GmbH,
Heraeusstr. 12-14, 63450 Hanau (DE).

(81) Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare nationale Schutzrechtsart): AE, AG, AL,

AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW,
BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK,
DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM,
GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP,
KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,
ZW.

(84) Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare regionale Schutzrechtsart): ARIPO (BW,
GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST,
SZ, TZ, UG, ZM, ZW), eurasisches (AM, AZ, BY, KG,
KZ, RU, TJ, TM), europäisches (AL, AT, BE, BG, CH,
CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE,
IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO,
RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Veröffentlicht:

— mit internationalem Recherchenbericht (Artikel 21 Absatz
3)

(54) Title: METHOD FOR SYNTHESIZING ELEMENTAL RHODIUM

(54) Bezeichnung : VERFAHREN ZUR HERSTELLUNG VON ELEMENTAREM RHODIUM

(57) Abstract: Disclosed is a method for synthesizing elemental rhodium, comprising the steps of: (1) providing an aqueous suspension of diethylenetriammonium hexahalorhodate adjusted to a pH between -1 and +2 using hydrohalic acid; (2) adding enough reducing agent to the suspension provided in step (1) for all of the diethylenetriammonium hexahalorhodate to be converted, and letting the reaction continue until the formation of elemental rhodium has been completed; and (3) separating the elemental rhodium formed in step (2) from the aqueous hydrohalic acid composition formed in step (2); halogen being bromine and/or chlorine.

(57) Zusammenfassung: Verfahren zur Herstellung von elementarem Rhodium, umfassend die Schritte: (1) Bereitstellen einer mit Halogenwasserstoffsäure auf einen pH-Wert von -1 +2 eingestellten wässrigen Suspension von Diethylentriammoniumhexahalogenorhodat, (2) Zugabe einer zur vollständigen Umsetzung des Diethylentriammoniumhexahalogenorhodats hinreichenden Menge an Reduktionsmittel zur in Schritt (1) bereitgestellten Suspension und Reagierenlassen bis zum Ende der Bildung elementaren Rhodiums, und (3) Abtrennen des in Schritt (2) gebildeten elementaren Rhodiums aus der in Schritt (2) gebildeten halogenwasserstoffsäuren wässrigen Zusammensetzung, wobei Halogen Brom und/oder Chlor bedeutet.



WO 2016/139020 A1

METHOD FOR PRODUCING ELEMENTAL RHODIUM

The present invention relates to a method for producing elemental rhodium from diethylene triammonium hexahalogenorhodate.

- 5 It is known to separate rhodium or Rh^{3+} from other precious metals in the process of precious metals refining as a poorly soluble salt of aliphatic polyamine and trihydrogen hexahalogenorhodic acid. A known representative of said salts is the complex salt of diethylene triamine (DETA) and trihydrogen hexachlororhodic acid, i.e. the triethylene triammonium hexachlororhodate represented by formula, $\text{H}_3(\text{DETA})\text{RhCl}_6$ or
- 10 $(\text{H}_3\text{NC}_2\text{H}_4\text{NH}_2\text{C}_2\text{H}_4\text{NH}_3)(\text{RhCl}_6)$. It is also known to boil said salts of aliphatic polyamine and trihydrogen hexachlororhodic acid in aqua regia for further processing. In this process, the organic components are decomposed through oxidation and ultimately an acidic aqueous solution of H_3RhCl_6 is formed that can be subjected to further refining. According to another known alternative, the salts of aliphatic polyamine and trihydrogen
- 15 hexahalogenorhodic acid are calcined in an oxygen-containing atmosphere and the rhodium-containing oxidic residue is subjected to further refining.

The present invention consists of a method for producing elemental rhodium, comprising the steps of:

- 20 (1) providing an aqueous suspension of diethylene triammonium hexahalogenorhodate adjusted with hydrohalic acid to a pH value of -1 to +2;
- (2) adding a sufficient quantity of reducing agent for complete conversion of the diethylene triammonium hexahalogenorhodate to the suspension provided in step (1) and allowing the reaction to proceed until the formation of elemental
- 25 rhodium is completed; and
- (3) separating the elemental rhodium formed in step (2) from the hydrohalic aqueous composition formed in step (2);

whereby halogen shall be understood to be bromine and/or chlorine, preferably chlorine.

The terms and/or abbreviations, “halogen” or “hal”, used in the description and in the claims

represent bromine and/or chlorine, preferably chlorine.

5 The terms and/or abbreviations, “hydrohalic acid” or “hydrohalic”, used in the description and in the claims

represent hydrobromic acid and/or hydrochloric acid , preferably hydrochloric acid, and/or hydrobromic and/or hydrochloric, preferably hydrochloric.

10 An aqueous suspension of diethylene triammonium hexahalogenorhodate, adjusted with hydrohalic acid to a pH in the range of -1 to +2, preferably of -0.5 to +0.5, is provided in step (1) of the method according to the invention. The determination of the pH value is not associated with any special requirements and can be done with a common pH meter.

15

Typically, the diethylene triammonium hexahalogenorhodate originates from the precious metals refining known to a person skilled in the art or, to be more precise, from the rhodium separation step in the scope of precious metals refining. Due to its poor solubility in water and/or hydrohalic aqueous milieu, the diethylene triammonium

20 hexahalogenorhodate can be isolated therein in the rhodium separation step.

A preferred example is the above-mentioned diethylene triammonium hexahalogenorhodate.

25 The procedure applied in this context can be such that the diethylene triammonium hexahalogenorhodate is suspended in water and hydrohalic acid is added until the pH value of the aqueous suspension is adjusted to within the range of -1 to +2.

Alternatively, the diethylene triammonium hexahalogenorhodate can just as well be added to and suspended in a hydrohalic acid having a pH in the range of -1 to +2.

30

The fraction of the diethylene triammonium hexahalogenorhodate in the aqueous suspension provided in step (1) is, for example, in the range of 5 to 40 % by weight, expediently 10 to 30 % by weight, relative to the total suspension.

5 In step (2) of the method according to the invention, a sufficient quantity of reducing agent for complete conversion of the diethylene triammonium hexahalogenorhodate is added to the suspension provided in step (1) and the reaction is allowed to proceed until the formation of elemental rhodium is completed. The term, "suspension", shall be understood to mean that the diethylene triammonium hexahalogenorhodate is present
10 in suspension due to its poor solubility, i.e. the aqueous suspension therefore being agitated, for example being stirred.

It is feasible to use one or multiple reducing agent(s) in combination. In the latter case, the reducing agents can be added separately, i.e. one after the other, or at the same
15 time or overlapping in time.


Various oxidisable substances such as, for example, hydrazine, hydrazine hydrate, Sn(II) compounds, such as SnCl_2 , non-precious metals, such as zinc, iron, aluminium, tin, are suitable reducing agents.

20 It is preferred to use iron as reducing agent, particularly in the form of iron powder.

The addition of the reducing agent can be based on exact stoichiometric considerations or an excess as compared to theory, possibly needed for practical reasons, can be
25 added, if applicable. It is preferred to add aliquots of the reducing agent or reducing agents to the agitated, for example stirred, suspension and to monitor the progress of the reaction by means of a disappearance and/or dissolution of the diethylene triammonium hexahalogenorhodate and the concurrent formation of elemental rhodium. The progress of the reaction can also be monitored analytically, for example
30 supplementary to visual monitoring, for example by determination of the Rh^{3+} content in the aqueous phase of the reaction material or by measuring the redox potential of the

aqueous phase of the reaction material. In this regard, a person skilled in the art will understand the term, "sufficient amount of reducing agent", not in a purely stoichiometric sense, but based on the existing practical situation.

- 5 It is being assumed that the reduction reaction that is ongoing in step (2) can be described as follows using diethylene triammonium hexahalogenorhodate and iron as reducing agent for exemplary purposes:



Possibly, hydrogen formed from the iron in the hydrohalic milieu of the reaction material may act as reducing agent as well; but this was not investigated in any more detail.

- 15 During step (2), the pH value of the aqueous phase of the reaction material is maintained in the range of -1 to +2, preferably of -0.5 to +0.5, for which purpose it may be necessary to add an appropriate amount of hydrohalic acid. The temperature of the reaction material during step (2) is, for example, in the range of 20 to 70°C, preferably 40 to 65°C. The duration of process step (2) is, for example, in the range of 2 to 4
- 20 hours, whereby it may be expedient to keep stirring after the final addition of reducing agent until the pH value is constant within the pH range of -1 to +2, preferably -0.5 to +0.5, for example for 0.5 to 2 hours at 20 to 70°C, preferably 40 to 65°C.

- 25 The elemental rhodium formed in step (2) is present in particulate form, in particular as spongy rhodium.

- After the completion of step (2), the elemental rhodium formed in step (3) is separated from the hydrohalic aqueous composition formed in step (2). Conventional solid-liquid separation procedures known to a person skilled in the art can be used in this context,
- 30 for example decanting, lifting, filtration or suitable combinations of said separation procedures.

The separated elemental rhodium can expediently be washed with water. Subsequently, the rhodium, which is obtained largely or completely free of accompanying organic substances in the method according to the invention, can be purified further. For example, a treatment with chlorine and hydrochloric acid while forming an aqueous acidic H_3RhCl_6 solution is feasible, which can then be purified further. Examples of suitable cleaning techniques include ion exchange, extraction, and electrolysis.

Ultimately, the substance, H_3RhCl_6 , is the same result as is obtained in the above-mentioned method of aqua regia boiling of a salt of aliphatic polyamine and trihydrogenhexachlororhodic acid.

The hydrohalic filtrate, which is obtained during the separation of elemental rhodium from the hydrohalic aqueous composition formed in step (2) and contains cations in the form of fully protonated diethylene triamine and halide anions, can also contain oxidised reducing agent and/or oxidation products thereof depending on the type of reducing agent used in step (2). If needed, said oxidised reducing agent or oxidation products of the reducing agent(s) can be removed from the filtrate, for example, through a suitable precipitation reaction; but there is no compelling necessity to do so. The hydrohalic filtrate can be used and/or reused in the scope of a further process step (4) of precious metals refining to precipitate Rh^{3+} as diethylene triammonium hexahalogenorhodate.

One advantage of the method according to the invention is that it does not involve the above-mentioned boiling of the salts of aliphatic polyamine and trihydrogen hexahalogenorhodic acid in aqua regia. Accordingly, the production and ensuing need to remove nitrous gases is avoided as well. As mentioned above, another advantage is that the aliphatic polyamide is re-obtained in solution in hydrohalic acid-protonated aqueous form and can be reused in precious metals refining for precipitation of Rh^{3+} as poorly soluble diethylene triammonium hexahalogenorhodate.

Examples

Example 1:

A total of 30 g solid diethylene triammonium hexachlororhodate were suspended in 150 ml of water, the suspension was heated to 60°C, and 10N hydrochloric acid was added to adjust the pH to 0.5. Then, 10 g iron powder was added in aliquots to the suspension while stirring and the sample was maintained at 60°C. The pH was checked during the addition of iron and maintained at pH 0 to -0.5 by adding 10N hydrochloric acid. Stirring at 60°C was continued for 2 more hours. The reaction material was separated by suction filtration into elemental rhodium, in the form of spongy rhodium, and an acidic aqueous filtrate containing dissolved diethylene triammoniumchloride. The spongy rhodium was washed with water and then subjected to further refining by means of chlorine and hydrochloric acid; the rhodium yield relative to the rhodium content of the diethylene triammonium hexachlororhodate educt was: >99%.

Example 2:

A total of 30 g solid diethylene triammonium hexachlororhodate were suspended in 200 ml of water, the suspension was heated to 60°C, and 10N hydrochloric acid was added to adjust the pH to 0.2. Then, 10 g iron powder was added in aliquots to the suspension while stirring and the sample was maintained at 60°C.

The pH was checked during the addition of iron and maintained at pH 0 to -0.5 by adding 10N hydrochloric acid. Stirring was continued for 2 more hours. The reaction material was separated by suction filtration into elemental rhodium, in the form of spongy rhodium, and an acidic aqueous filtrate containing dissolved diethylene triammoniumchloride. The spongy rhodium was washed with water and then subjected to further refining by means of chlorine and hydrochloric acid; the rhodium yield relative to the rhodium content of the diethylene triammonium hexachlororhodate educt was: >99%.

Claims

1. Method for producing elemental rhodium, comprising the steps of:
 - (1) providing an aqueous suspension of diethylene triammonium hexahalogenorhodate adjusted with hydrohalic acid to a pH value of -1 to +2;
 - (2) adding a sufficient quantity of reducing agent for complete conversion of the diethylene triammonium hexahalogenorhodate to the suspension provided in step (1) and allowing the reaction to proceed until the formation of elemental rhodium is completed; and
 - (3) separating the elemental rhodium formed in step (2) from the hydrohalic aqueous composition formed in step (2);
 whereby halogen is bromine and/or chlorine.
2. Method according to claim 1,

whereby the pH value of the aqueous suspension provided in step (1) is in the range of -0.5 to +0.5.
3. Method according to claim 1 or 2,

whereby the diethylene triammonium hexahalogenorhodate originates from the rhodium separation step of precious metals refining.
4. Method according to any one of the preceding claims,

whereby the diethylene triammonium hexahalogenorhodate is suspended in water and hydrohalic acid is added until the pH value of the aqueous suspension is adjusted to within the range of -1 to +2 or the diethylene triammonium hexahalogenorhodate is added to and suspended in a hydrohalic acid having a pH in the range of -1 to +2.
5. Method according to any one of the preceding claims,

whereby the fraction of the diethylene triammonium hexahalogenorhodate in the aqueous suspension provided in step (1) is in the range of 5 to 40 % by weight.

6. Method according to any one of the preceding claims,
whereby the aqueous suspension is being agitated during step (2).
7. Method according to any one of the preceding claims,
whereby one reducing agent or a combination of reducing agents is used and the
reducing agents, in the case of a combination of reducing agents, are one after the
other, at the same time or overlapping in time.
8. Method according to any one of the preceding claims,
Whereby the reducing agent(s) is/are selected from the group consisting of
hydrazine, hydrazine hydrate, Sn(II) compounds, zinc, iron, aluminium, and tin.
9. Method according to any one of the claims 1-7,
whereby iron powder is used as reducing agent.
10. Method according to any one of the preceding claims,
whereby the pH value is maintained in the range of -1 to +2 during step (2),
possibly by adding hydrohalic acid.
11. Method according to any one of the preceding claims,
whereby the temperature of the reaction material is maintained in the range of 20
to 70°C during step (2).
12. Method according to any one of the preceding claims,
whereby the hydrohalic filtrate obtained during the separation of the elemental
rhodium is used in a step (4) of precious metals refining to precipitate Rh^{3+} as
diethylene triammonium hexahalogenorhodate.

13. Method according to claim 12,
any reducing agent or oxidation products of the reducing agent(s) is/are removed
from the hydrohalic filtrate before using it in step (4).
14. Method according to any one of the preceding claims,
whereby the diethylene triammonium hexahalogenorhodate is diethylene
triammonium hexachlororhodate.