



(51) International Patent Classification:

H01L 21/3065 (2006.01) *H01L 21/67* (2006.01)
H01L 21/311 (2006.01)

(21) International Application Number:

PCT/US2017/055800

(22) International Filing Date:

09 October 2017 (09.10.2017)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/410,225 19 October 2016 (19.10.2016) US
15/726,120 05 October 2017 (05.10.2017) US

(71) Applicant: **LAM RESEARCH CORPORATION**
[US/US]; 4650 Cushing Parkway, M/S CA-1, Fremont, California 94538 (US).

(72) Inventors: **TAN, Zongkui**; 1855 Camargo Drive, San Jose, California 95132 (US). **XIANG, Hua**; 4057 San Giorgio Court, Pleasanton, California 94588 (US). **HU, Wenbing**; 350 E. Taylor Street Apt. 3215, San Jose, California 95112 (US). **XU, Qing**; 4615 Amiens Avenue, Fremont, California 94555 (US). **FU, Qian**; 5647 Stonecliff Vista Lane, Pleasanton, California 94566 (US).

(74) Agent: **LEE, Michael**; BEYER LAW GROUP LLP, P.O. Box 51887, Palo Alto, California 94303-1887 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,

KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) Title: SILICON OXIDE SILICON NITRIDE STACK ION-ASSISTED ETCH




FIG. 2

(57) Abstract: A method for ion-assisted etching a stack of alternating silicon oxide and silicon nitride layers in an etch chamber is provided. An etch gas comprising a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon is flowed into the etch chamber. The gas is formed into an in-situ plasma in the etch chamber. A bias of about 10 to about 100 volts is provided to accelerate helium ions to the stack and activate a surface of the stack to form an activated surface for ion-assisted etching, wherein the in-situ plasma etches the activated surface of the stack.

SILICON OXIDE SILICON NITRIDE STACK ION-ASSISTED ETCH**CROSS REFERENCE TO RELATED APPLICATION**

[0001] This application claims the benefit of priority of U.S. Provisional Application No. 62/410,225, filed October 19, 2016, and U.S. Application No. 5 15/726,120, filed October 5, 2017, which is incorporated herein by reference for all purposes.

BACKGROUND

[0002] The present disclosure relates to the formation of semiconductor devices. More specifically, the disclosure relates to the formation of stair-step semiconductor 10 devices.

[0003] During semiconductor wafer processing, stair-step features are sometimes required. For example, in 3D flash memory devices, multiple cells are stacked up together in chain format to save space and increase packing density. The stair-step structure allows electrical contact with every gate layer. Such stair-step structures 15 may be formed by a plurality of alternating layers of silicon oxide and silicon nitride, where such stacks are designated as ONON stacks. ONON stacks may also be used to form other semiconductor devices in addition to stair-step semiconductor devices.

SUMMARY

[0004] To achieve the foregoing and in accordance with the purpose of the 20 present disclosure, a method for ion-assisted etching a stack of alternating silicon oxide and silicon nitride layers in an etch chamber is provided. An etch gas comprising a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon is flowed into the etch chamber. The gas is formed into an *in-situ* plasma in the etch chamber. A bias of about 10 to about 100 volts is provided to accelerate helium ions 25 to the stack and to activate a surface of the stack to form an activated surface of the stack for ion-assisted etching, wherein the *in-situ* plasma etches the activated surface of the stack.

[0005] In another manifestation, a method for forming a stair-step structure in a stack in a plasma processing chamber is provided, wherein the stack has an organic 30 mask and wherein the stack comprises a plurality of bilayers of silicon oxide and silicon nitride, comprising a plurality of cycles, wherein each cycle comprises trimming the organic mask and ion-assisted etching at least one complete bilayer of

the stack. The ion-assisted etching comprises flowing an etch gas comprising a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon into an etch chamber, forming the etch gas into an *in-situ* plasma in the etch chamber, and providing bias of about 10 to about 100 volts to accelerate helium ions to the stack in the etch chamber and activate a surface of the stack to form an activated surface of the stack, wherein the *in-situ* plasma etches the activated surface of the stack.

[0006] These and other features of the present disclosure will be described in more detail below in the detailed description of the disclosure and in conjunction with the following figures.

10

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] The present disclosure is illustrated by way of example, and not by way of limitation, in the figures of the accompanying drawings and in which like reference numerals refer to similar elements and in which:

[0008] FIG. 1 is a high level flow chart of a process that may be used in an embodiment of the disclosure.

15

[0009] FIG. 2 is a more detailed flow chart of step 108 in FIG. 1 on using ion-assisted etch to form a stair-step structure.

[0010] FIGS. 3A-F are schematic cross-sectional views of a stack etched according to an embodiment of the disclosure.

[0011] FIG. 4 is a schematic view of a plasma processing chamber that may be used in practicing the disclosure.

20

[0012] FIG. 5 illustrates a computer system, which is suitable for implementing a controller used in embodiments of the present disclosure.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0013] The present disclosure will now be described in detail with reference to a few preferred embodiments thereof as illustrated in the accompanying drawings. In the following description, numerous specific details are set forth in order to provide a thorough understanding of the present disclosure. It will be apparent, however, to one skilled in the art, that the present disclosure may be practiced without some or all of these specific details. In other instances, well known process steps and/or structures have not been described in detail in order to not unnecessarily obscure the present disclosure.

30

[0014] To facilitate understanding, FIG. 1 is a high level flow chart of a process that may be used in an embodiment of the disclosure, which forms a stair-step structure in a stack. An organic mask is formed over a stack of alternating silicon oxide and silicon nitride (ONON) layers (step 104). A stair-step structure is formed with an ion-assisted etch (step 108). The organic mask is trimmed (step 112). If the etch of the stair-step is not complete (step 116), then the process goes to the ion-assisted etching stair-step formation step (step 108). Otherwise, the process is complete and other steps may be performed.

[0015] FIG. 2 is a more detailed flow chart of the step of forming a stair-step structure using an ion-assisted etch. An etch gas is flowed into a processing chamber (step 204), wherein the etch gas comprises a fluorine containing component, helium, and a hydrofluorocarbon or a fluorocarbon component. The etch gas is formed into a plasma inside the plasma chamber (step 208). A low bias of 10 to 100 volts is provided to cause ion bombardment from helium ions to activate a surface of the stack for ion-assisted etching, wherein the plasma etches the activated surface of the stack (step 212). The ion-assisted etch process is stopped (step 216).

Example

[0016] In an example of an implementation of the disclosure, a stair-step memory array is etched. In such a memory array, memory stacks are formed over a wafer. FIG. 3A is a cross sectional view of a stack 300 comprising a plurality of layers of memory stacks 304 formed over a wafer 308. In this embodiment, each memory stack of the plurality of memory stacks is formed by bilayers of a layer of silicon oxide (SiO₂) 316 on top of a layer of silicon nitride (SiN) 312 forming an ONON stack. An organic mask 320 is formed over the memory stacks 304 (step 104). The organic mask may be a photoresist mask that is formed using a spin on process and a photolithographic patterning. In the alternative, the organic mask may be a spun on or otherwise applied organic layer, without photolithographic patterning.

[0017] The stack 300 may be placed in a processing tool to perform subsequent steps. FIG. 4 illustrates a processing tool that may be used in an implementation of the disclosure. FIG. 4 is a schematic view of a plasma processing system 400, including a plasma processing tool 401. The plasma processing tool 401 is an inductively coupled plasma etching tool and includes a plasma reactor 402 having a

plasma processing chamber 404 therein. A transformer coupled power (TCP) controller 450 and a bias power controller 455, respectively, control a TCP power supply 451 and a bias power supply 456 influencing the plasma 424 created within plasma chamber 404.

5 **[0018]** The TCP power controller 450 sets a set point for TCP power supply 451 configured to supply a radio frequency signal at 13.56 MHz, tuned by a TCP match network 452, to a TCP coil 453 located near the plasma chamber 404. An RF transparent window 454 is provided to separate TCP coil 453 from plasma chamber 404, while allowing energy to pass from TCP coil 453 to plasma chamber 404.

10 **[0019]** The bias power controller 455 sets a set point for bias power supply 456 configured to supply an RF signal, tuned by bias match network 457, to a chuck electrode 408 located within the plasma chamber 404 creating a direct current (DC) bias above electrode 408 which is adapted to receive the stack 300.

15 **[0020]** A gas supply mechanism or gas source 410 includes a source or sources of gas or gases 416 attached via a gas manifold 417 to supply the proper chemistry required for the process to the interior of the plasma chamber 404. A gas exhaust mechanism 418 includes a pressure control valve 419 and exhaust pump 420 and removes particles from within the plasma chamber 404 and maintains a particular pressure within plasma chamber 404.

20 **[0021]** A temperature controller 480 controls the temperature of a cooling recirculation system provided within the chuck electrode 408 by controlling a cooling power supply 484. The plasma processing system also includes electronic control circuitry 470. The plasma processing system may also have an end point detector. An example of such an inductively coupled plasma processing chamber is the Kiyo
25 built by Lam Research Corporation of Fremont, CA, which is used to etch silicon, polysilicon and conductive layers, in addition to dielectric and organic materials. In other embodiments of the disclosure, a capacitively coupled system may be used.

30 **[0022]** FIG. 5 is a high level block diagram showing a computer system 500, which is suitable for implementing a control circuitry 470 used in embodiments of the present disclosure. The computer system may have many physical forms ranging from an integrated circuit, a printed circuit board, and a small handheld device up to a huge super computer. The computer system 500 includes one or more processors 502,

and further can include an electronic display device 504 (for displaying graphics, text, and other data), a main memory 506 (e.g., random access memory (RAM)), storage device 508 (e.g., hard disk drive), removable storage device 510 (e.g., optical disk drive), user interface devices 512 (e.g., keyboards, touch screens, keypads, mice or
5 other pointing devices, etc.), and a communication interface 514 (e.g., wireless network interface). The communication interface 514 allows software and data to be transferred between the computer system 500 and external devices via a link. The system may also include a communications infrastructure 516 (e.g., a communications bus, cross-over bar, or network) to which the aforementioned devices/modules are
10 connected.

[0023] Information transferred via communications interface 514 may be in the form of signals such as electronic, electromagnetic, optical, or other signals capable of being received by communications interface 514, via a communication link that carries signals and may be implemented using wire or cable, fiber optics, a phone line,
15 a cellular phone link, a radio frequency link, and/or other communication channels. With such a communications interface, it is contemplated that the one or more processors 502 might receive information from a network, or might output information to the network in the course of performing the above-described method steps. Furthermore, method embodiments of the present disclosure may execute
20 solely upon the processors or may execute over a network such as the Internet, in conjunction with remote processors that share a portion of the processing.

[0024] The term “non-transient computer readable medium” is used generally to refer to media such as main memory, secondary memory, removable storage, and storage devices, such as hard disks, flash memory, disk drive memory, CD-ROM and
25 other forms of persistent memory and shall not be construed to cover transitory subject matter, such as carrier waves or signals. Examples of computer code include machine code, such as produced by a compiler, and files containing higher level code that are executed by a computer using an interpreter. Computer readable media may also be computer code transmitted by a computer data signal embodied in a carrier
30 wave and representing a sequence of instructions that are executable by a processor.

[0025] In this example, a stair step is ion-assisted etched (step 108). An etch gas is flowed into a processing chamber (step 204), wherein the etch gas comprises a

fluorine containing component, helium, and a hydrofluorocarbon or a fluorocarbon component. In this example, the etch gas consists essentially of 50 sccm SF₆, 100 CHF₃, 700 sccm He. CHF₃ is the hydrofluorocarbon component. SF₆ is the fluorine containing component. The etch gas is formed into a plasma (step 208). Inductively
5 coupled RF power is provided at 13.56 MHz with a power of 2600 Watts. A low bias of 50 volts is provided to cause ion bombardment from helium ions (step 212) to activate a surface of the stack for ion-assisted etching, wherein the *in-situ* plasma etches the activated surface of the stack. The etch process is stopped after 25 seconds (step 216). The etch process may be stopped by stopping the flow of the etch gas. In
10 addition, the RF power may be stopped. If the RF power is used to provide trimming, then the RF power may continue. FIG. 3B is a cross-sectional view of the stack 300 after a stair-step has been ion-assisted etched in the stack. An exposed horizontal surface of the stack has been etched. In this example two bilayers of silicon oxide and silicon nitride are etched to form a first step 324.

15 **[0026]** The organic mask is trimmed (step 112). An example of a recipe for the trim of the organic mask provides a pressure between 30 to 400 mTorr. A trim gas is flowed from the gas source 416 to the plasma chamber 404 (step 504), where the trimming gas is 1000 sccm O₂, 40 sccm N₂, and 50 sccm NF₃. The trimming gas is formed into a plasma. In this example, 1800 watts TCP power is provided at 13.56
20 MHz. 0 volts of bias is provided. The plasma is maintained for 20 to 60 seconds, and then the trimming gas is stopped. FIG. 3C is a cross-sectional view of the stack 300, after the organic mask 320 is trimmed.

[0027] If the stair is not complete (step 116), another stair-step is ion-assisted etched using the organic mask as a mask (step 108). The same recipe as the previous
25 stair-step etch may be used. FIG. 3D is a cross-sectional view of the stack 300 after a stair-step has been etched. In this example two bilayers of silicon oxide and silicon nitride are etched to form a second step 328, while deepening the first step 324. The deepening of the first step 324 etches the first step, without using a mask and provides a vertical sidewall and a corner, without faceting.

30 **[0028]** The organic mask 320 is trimmed again (step 112). The same trim recipe may be used. FIG. 3E is a cross-sectional view of the stack 300 after the organic mask 320 is trimmed (step 112).

[0029] If the stair is not complete (step 116), another stair-step is ion-assisted etched using the organic mask as a mask (step 108). The same recipe as the previous stair-step etch may be used. FIG. 3F is a cross-sectional view of the stack 300 after a stair-step has been etched. In this example two bilayers of silicon oxide and silicon nitride are etched to form a third step 332, while deepening the second step 328 and the first step 324.

[0030] The process is continued until the stair is completed (step 116). The cycle is then stopped. Additional processes may be provided, such as removing the organic mask.

[0031] The completed stair provides an improved structure over stairs created using other processes in a manner that is faster than other processes. A feature about such a stair-step etch is that an unmasked region forming a step is etched. Other etch processes may depend on a chemical etching, which alternates between selectively etching silicon oxide with respect to silicon nitride and then selectively etching silicon nitride with respect to silicon oxide. Such an etch process would alternate etch gas chemistries and other parameters to alternate the selectivity. Such processes using alternating etches to selectively etch individual layers are slower than the above embodiment, which uses a single etch process to etch multiple individual layers with a single etch process. In addition, it is more difficult to control the vertical profile of such chemical etches, since a chemical etch would etch vertical surfaces in addition to horizontal surfaces. As a result, the resulting stair step structure would have a tapered profile. Such chemical etches of silicon oxide would use silicon nitride as a mask and etch stop. Such chemical etches of silicon nitride would use silicon oxide as a mask and etch stop. Other previous processes may rely on ion bombardment in order to etch silicon oxide and silicon nitride with a single etch process. Such ion bombardment tends to have some nonvertically directed ions. Such nonvertical ions cause sidewall loss. In addition, such bombardment may cause faceting of the corners of the stair steps. Such faceting will also cause a tapered profile. Previous processes may add temporary masks to protect the sidewalls or organic mask. The formation of such masks further increase processing time.

[0032] The above embodiment provides an ion-assisted etch. Helium ions with a low bias voltage of 10 to 100 volts provides ion assistance to the etch, while avoiding

ion bombardment damage caused by ion bombardment etching. Helium ions provide a low atomic weight to avoid ion bombardment damage. The bias voltage should be enough to activate the surface without any additional damage or faceting at the corners of the stairs. Preferably, the bias voltage allows the helium ions to activate the surface of the stack without etching the stack. Instead, the plasma chemically etches the activated surfaces of the stack. The flow rates of the fluorine containing component and the hydrofluorocarbon or hydrocarbon may be used as control parameters to provide the desired etch while providing sufficient passivation to prevent sidewall damage and faceting, while performing the ion-assisted etch. The ion-assist allows the etching of both the silicon oxide and silicon nitride, using a single etch process. The embodiment provides a stair-step structure with vertical sidewalls or sidewalls with a reduced slope. The above embodiment has been found to provide an etch process that is twice as fast as a baseline chemical etch process that alternates between selective etch chemistries. In addition, the above embodiment has been found to more selectively etch ONON layers with respect to the organic mask and help to improve the L/V ratio, which is the lateral organic mask trim to vertical organic mask height loss ratio. It was found that the above embodiment was able to etch in about 30 seconds 3 pairs of silicon oxide/silicon nitride bilayers with a total thickness of 170 nm, compared to a conventional chemical etch using two alternating etch recipes, which took about 60 seconds. Therefore, the above embodiment was about twice as fast as a previous etch process. The above embodiment was found to have a vertical profile of greater than 85°, whereas a conventional chemical etch using two alternating etch recipes had a vertical profile of less than 80°. In the specification and claims, a vertical profile is defined as having a profile of greater than 85° from the horizon. Since this embodiment provides an ion-assisted etch, only areas activated by ion-assist are chemically etched. As a result, sidewall etching is reduced without requiring a protective sidewall layer. Therefore, during the etch process the stair-step structure does not have a mask over some steps and sidewalls of the steps.

[0033] In addition, the above embodiment provides a single etch process with approximately a 1 to 1 selectivity between etching the silicon oxide and silicon nitride. This causes the silicon oxide to be etched about as fast as the silicon nitride.

In such a single step process for etching multiple layers of silicon oxide and silicon nitride, it is desirable to etch both the silicon oxide and silicon nitride at the same rate.

[0034] Preferably, the fluorine containing component is SF_6 or NF_3 , which acts as the main etchant for etching SiN. Preferably, the hydrofluorocarbon or fluorocarbon is CHF_3 or CF_4 , which acts as the main etchant for etching silicon oxide. It has been found that the correct balance of these two etchants combined with ion-assist can stop lateral chemical etching. With a large He dilution, the majority of ions are from He. Preferably, the flow rate of He is at least twice the flow rate of the remaining components of the etch gas, measured by volume flow rate (sccm). The flow rate of the remaining components of the etch gas equals the flow rate of the etch gas minus the flow rate of the helium. More preferably, the flow rate of He is at least four times the flow rate of the remaining components of the etch gas. Preferably, the low bias voltage is between 10 to 100 volts. More preferably, the low bias voltage is between 20 to 70 volts. Preferably, the etch is at a low pressure of between 5 to 20 mTorr, to reduce inter ions collisions, resulting in a higher percentage of vertical ions.

[0035] Preferably, the cycle is repeated at least 5 times, so that at least five stair-steps are provided. More preferably, at least 8 stair-steps may be provided. The stair-steps may be formed in one or more horizontal directions (X or Y) in other embodiments.

[0036] In other embodiments, other feature shapes may be etched into a plurality of silicon oxide and silicon nitride bilayers with a single ion-assisted etch process. The ion-assisted etch process would reduce corner faceting and sidewall etching on non-stair step structures, while increasing the etch rate of the bilayers.

[0037] In other embodiments, the first layer is a silicon nitride layer. In other embodiments, the last step is an etch step, wherein the organic layer is not subsequently trimmed after the last etch step. In some embodiments, the ion-assisted etch may be used to etch high aspect ratio features, such as contacts.

[0038] In some embodiments, the etch gas consists essentially of a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon. In other embodiment the etch gas comprises a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon with the addition of one or more of HBr, COS, Cl_2 , N_2 , Ar, H_2 , or SiCl_4 . For example, in one embodiment the etch gas consists essentially of a fluorine

component, helium, HBr, COS, and a fluorohydrocarbon or hydrocarbon. In another embodiment the etch gas consists essentially of a fluorine component, helium, HBr or COS, and a fluorohydrocarbon or hydrocarbon.

[0039] In an embodiment, the stack comprises at least two pairs of bilayers of
5 silicon oxide and silicon nitride. In another embodiment, the stack comprises at least 100 pairs of bilayers of silicon oxide and silicon nitride.

[0040] While this disclosure has been described in terms of several preferred
embodiments, there are alterations, permutations, and various substitute equivalents,
which fall within the scope of this disclosure. It should also be noted that there are
10 many alternative ways of implementing the methods and apparatuses of the present
disclosure. It is therefore intended that the following appended claims be interpreted
as including all such alterations, permutations, and various substitute equivalents as
fall within the true spirit and scope of the present disclosure.

CLAIMS

What is claimed is:

1. A method for ion-assisted etching a stack of alternating silicon oxide and silicon nitride layers in an etch chamber, comprising:
 - 5 flowing an etch gas comprising a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon into the etch chamber;
 - forming the etch gas into an *in-situ* plasma in the etch chamber; and
 - providing a bias of about 10 to about 100 volts to accelerate helium ions to the stack and activate a surface of the stack to form an activated surface for ion-assisted
 - 10 etching, wherein the *in-situ* plasma etches the activated surface of the stack.
2. The method, as recited in claim 1, wherein a flow rate of helium of the etch gas is at least twice a flow rate of remaining components of the etch gas.
3. The method, as recited in claim 1, wherein the stack comprises at least two pairs of bilayers of silicon oxide and silicon nitride.
- 15 4. The method, as recited in claim 1, wherein the stack comprises at least 100 pairs of bilayers of silicon oxide and silicon nitride.
5. The method, as recited in claim 1, wherein the forming the etch gas into an *in-situ* plasma comprises providing RF power to the etch chamber through inductive coupling.
- 20 6. The method, as recited in claim 1, wherein the stack is in a form of a stair-step structure, wherein the stair-step structure has a mask over part of the stack, wherein the mask does not cover some steps and sidewalls of the steps.
7. The method, as recited in claim 1, wherein the stack is disposed below an organic mask, and the method further comprising trimming the organic mask.
- 25 8. The method, as recited in claim 1, wherein the etch gas further comprises at least one of HBr, COS, Cl₂, N₂, Ar, H₂, or SiCl₄.
9. The method, as recited in claim 1, wherein the helium ions do not etch the stack and wherein the *in-situ* plasma chemically etches only the activated surface of the stack.
- 30 10. A method for forming a stair-step structure in a stack in a plasma processing chamber, wherein the stack has an organic mask and wherein the stack comprises a plurality of bilayers of silicon oxide and silicon nitride, comprising a plurality of

cycles, wherein each cycle comprises:

a) trimming the organic mask; and

b) ion-assisted etching at least one complete bilayer of the stack, wherein the ion-assisted etching comprises:

5 flowing an etch gas comprising a fluorine component, helium, and a fluorohydrocarbon or hydrocarbon into an etch chamber;

 forming the etch gas into an *in-situ* plasma in the etch chamber; and

 providing a bias of about 10 to about 100 volts to accelerate helium ions to the stack in the etch chamber and activate a surface of the stack to form an
10 activated surface of the stack, wherein the *in-situ* plasma etches the activated surface of the stack.

11. The method, as recited in claim 10, wherein the cycle of steps a-b is repeated at least 5 times.

12. The method, as recited in claim 10, wherein the organic mask is a photoresist
15 mask.



13. The method, as recited in claim 10, wherein steps a-b are performed in an inductively coupled plasma processing chamber.

14. The method, as recited in claim 10, wherein a flow rate of helium of the etch gas is at least twice a flow rate of remaining components of the etch gas.

20 15. The method, as recited in claim 10, wherein the helium ions do not etch the stack and wherein the *in-situ* plasma chemically etches only the activated surface of the stack.

16. The method, as recited in claim 10, wherein the etch gas further comprises at least one of HBr, COS, Cl₂, N₂, Ar, H₂, or SiCl₄.

25






FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E






FIG. 3F





INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2017/055800**A. CLASSIFICATION OF SUBJECT MATTER****H01L 21/3065(2006.01)i, H01L 21/311(2006.01)i, H01L 21/67(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

H01L 21/3065; H01L 21/311; H01L 27/115; H01L 21/308; H01L 21/02; H01L 21/8247; H01L 21/67

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & Keywords: silicon oxide, silicon nitride, fluorine, helium, etch, plasma, ion, stair-step structure, mask

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2014-0363980 A1 (TOKYO ELECTRON LIMITED) 11 December 2014 See paragraphs [0021]-[0108] and figures 1-11.	1-16
A	JP 07-335611 A (HITACHI LTD.) 22 December 1995 See paragraphs [0008]-[0011] and figures 1-2.	1-16
A	US 2016-0218015 A1 (CENTRAL GLASS COMPANY, LIMITED) 28 July 2016 See paragraphs [0049]-[0052] and figure 3.	1-16
A	JP 2015-133355 A (TOKYO ELECTRON LTD.) 23 July 2015 See paragraphs [0018]-[0063] and figures 1-3B.	1-16
A	KR 10-2012-0064820 A (SAMSUNG ELECTRONICS CO., LTD.) 20 June 2012 See paragraphs [0032]-[0050] and figures 1-7.	1-16

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

23 February 2018 (23.02.2018)

Date of mailing of the international search report

26 February 2018 (26.02.2018)

Name and mailing address of the ISA/KR

International Application Division

Korean Intellectual Property Office

189 Cheongsa-ro, Seo-gu, Daejeon, 35208, Republic of Korea



Facsimile No. +82-42-481-8578

Authorized officer

CHOI, Sang Won

Telephone No. +82-42-481-8291



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2017/055800

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2014-0363980 A1	11/12/2014	CN 104081502 A	01/10/2014
		CN 104081502 B	29/06/2016
		JP 2013-171890 A	02/09/2013
		JP 5912637 B2	27/04/2016
		KR 10-2014-0125370 A	28/10/2014
		TW 201351499 A	16/12/2013
		TW I563561 B	21/12/2016
		US 9202707 B2	01/12/2015
		WO 2013-121936 A1	22/08/2013
JP 07-335611 A	22/12/1995	JP 3011018 B2	21/02/2000
US 2016-0218015 A1	28/07/2016	JP 2016-139782 A	04/08/2016
		KR 10-1763782 B1	01/08/2017
		KR 10-2016-0091285 A	02/08/2016
		TW 201639033 A	01/11/2016
		US 9728422 B2	08/08/2017
JP 2015-133355 A	23/07/2015	JP 5970004 B2	17/08/2016
		KR 10-2015-0083426 A	17/07/2015
		US 2015-0194441 A1	09/07/2015
KR 10-2012-0064820 A	20/06/2012	KR 10-2012-0095571 A	29/08/2012
		US 2012-0149185 A1	14/06/2012
		US 8822287 B2	02/09/2014