




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H02G 15/18, 1/14, B29C 61/06	A1	(11) International Publication Number: WO 99/08355 (43) International Publication Date: 18 February 1999 (18.02.99)
<p>(21) International Application Number: PCT/US98/13959</p> <p>(22) International Filing Date: 6 July 1998 (06.07.98)</p> <p>(30) Priority Data: 08/909,951 12 August 1997 (12.08.97) US</p> <p>(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p> <p>(72) Inventors: SADLO, James, L.; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MELANCON, Gene, J.; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p> <p>(74) Agents: MCNUTT, Matthew, B. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p>		<p>(81) Designated States: BR, CA, CN, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>

(54) Title: SUPPORT CORE RIBBON FOR COLD-SHRINK TUBE

(57) Abstract

A core for an elastomeric tubing assembly is produced from a ribbon (30) helically wound on itself to form a cylindrical tube. The edges (32, 34) of the ribbon (30) are formed to interlock with each other and are contoured to facilitate ultrasonic welding of the edges (32, 34). A support member (50) is coextruded in the ribbon (30) to provide increased resistance to premature collapse of the tube.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Support Core Ribbon For Cold-Shrink Tube

Field of the Invention

This application is a continuation-in-part
5 application of U.S. Application 08/384,516, filed on
February 6, 1995, now issued United States Patent No.
5,670,223. This invention relates generally to
elastomeric sleeving supported by a removable core, and
particularly to construction of the core.

10

Background of the Invention

United States patent number 3,515,798, assigned to
the assignee of the present invention, describes an
elastomeric cover and removable core assembly which is
15 particularly useful in the electrical distribution
industry. However, the application of rubbery
insulating sleeves to electric wire or cable splice
areas is illustrative, and although the invention will
be described primarily in terms of devices and
20 procedures adapted particularly therefor, it is not to
be construed as limited thereto, being equally
applicable, for example, in the application of
corrosion-preventing protective sleeves to welded pipe
joints. The assembly is typically referred to as cold
25 shrink tubing to differentiate it from polymeric tubing
which may be shrunk by the application of heat.

Figure 1 illustrates a typical use for and
construction of a cold-shrink tube assembly and shows
two cable-ends 11 comprising a stranded conductor 12
30 and an insulating covering 13. The covering is cut
away at 14 and the conductors 12 joined together in
end-to-end configuration by suitable means which may

typically consist of a compressed or indented metal sleeve or a close-fitting metal tube with set-screw retainers. The joint or splice may be covered with insulating mastic or tape, here omitted for clarity of
5 illustration.

The cold-shrink tube assembly is slipped over one of the wire-ends prior to joining the two ends. After the splice is completed, the assembly is slid into position over the splice area and the support is
10 removed to permit the elastic cover to contract and form a tight fit. The process will be apparent from the illustration. The support comprises a unitary tubular core 15 helically grooved along its entire length, the continuous groove 16 permitting the core 15
15 to be pulled out into a continuous strip 17 which is removed through the bore, i.e., from between the core 15 and the cable 11. An elastic tube 18 in radially extended or stretched condition is supported on the core 15. As the strip 17 is progressively withdrawn,
20 the tube 18 contracts about the cable as at 19 to form a closely conforming and tightly retained protective covering. Contraction of the tube results in the application of a resultant force against the end of the core 15 and assists in the removal of the strip 17 as
25 the core 15 is unwound.

Although the construction described above has been used effectively for many years, considerable effort has been invested to reduce the amount of material used for the core 15 without compromising the strength of
30 the core 15, i. e., its ability to withstand the compressive forces imposed upon it by the elasticity of the tube 18.

One method of reducing the amount of material used in the core 15 has been to produce the core 15 from a continuous ribbon 20 such as that shown in Figures 2 and 3. The ribbon 20 includes edges 22 and 24 which
5 interlock, as shown in Figure 3, when the ribbon 20 is helically wound to form a tubular core. The interlocked edges 22 and 24 may be joined by such means as adhesives, heat welding or solvent welding, but the preferred method is ultrasonic welding. The
10 construction of Figures 2 and 3 was effective to reduce the amount of material used in the core 15 since the thickness of the core tube could be reduced as it was no longer necessary to cut a groove 16 in the material to form the helical line of weakening which allowed the
15 core 15 to be pulled as a strip 17 from the assembly. The joint between the edges 22 and 24 of the joined ribbon 20 formed the helical line of weakness around the core 15. Unfortunately, it was found that the extensive surface area of the contact between the two
20 edges 22 and 24 of the ribbon 20 resulted in bonds at the joint surface which were difficult to control, both in terms of location and strength. As a result, the core 15 was at times too weak to support the elastomeric sleeve 18 or too strong to allow easy
25 stripping of the core 15 from the sleeve 18.

The present invention modifies the shape of the ribbon edges 22 and 24 in order to achieve greater uniformity of bonding at the joint.

As less material is used in the support core, the
30 possibility of premature collapse increases, especially as the diameter of the core becomes larger. The support core must have strength sufficient to resist

collapsing under the compressive force of the tube for long periods of time and at elevated temperatures. The external pressure of the tube can cause collapsing of the support core, for instance, by buckling. This effect can be enhanced by the uneven thickness of the expanded tube which results in uneven pressure on the support core. Subject to this uneven pressure, the support core takes on an oval shape which is easier to collapse than a perfect circular cylinder. Ellipicity is the most important defect which determines premature collapse of circular supporting tubular cores. As the diameter of the support cores and expanded elastic tubings increases, the defects may become more pronounced and thus make premature collapse more common. Further, for given materials, the thickness of support cores required to support large diameter expanded elastic tubings is a fast function of the diameter of the core. Hence, there has been a natural limit to the size of tubings which can be reliably supported by collapsible support cores without the wall thickness of the core becoming unacceptably large.

The invention provides a ribbon with greater hoop strength by placing within the ribbon a support member formed of a material capable of withstanding high temperatures and increased pressure associated with large diameter support cores and stretched elastic tubings.

Summary of the Invention

The present invention produces cold-shrink tube assembly cores having more uniform and predictable characteristics than previous core constructions. The

core is manufactured from a ribbon adapted to be edge joined to itself to form a helically wound tube. The ribbon comprises a longitudinal body having first and second major surfaces and first and second edges. A
5 support member extends longitudinally through the body of the ribbon. The ribbon additionally comprises a first coupling projection extending from the first major surface toward the second major surface and terminating short of the second major surface, a second
10 coupling projection extending from the second major surface toward the first major surface and terminating short of the first major surface, recesses in the ribbon adjacent the first and the second coupling projections for accepting the projections and thus
15 permitting the first coupling projection of one ribbon section to engage the second coupling projection of another ribbon section with the major surfaces of the ribbon sections aligned to form a smooth surface of the tube, the coupling projections being formed such that
20 the first and the second coupling projections may engage each other along a continuous surface free of any surfaces which are perpendicular to said major surfaces.

The support member within the body of the ribbon
25 may be a coextruded polymer, such as ABS resin or modified PPO resin. The support member gives additional hoop strength to the ribbon such that the core is more resistant to premature collapse when subjected to high pressures associated with large
30 diameter stretched elastic tubes, or when stored in high temperature conditions.

The ribbon may further include perforations within the larger recess to alternatively or additionally increase the uniformity of the force necessary to separate the helical coils of the core when it is
5 desired to remove the core from the sleeve.

Brief Description of the Drawings

The present invention will be more particularly described with respect to the following drawings,
10 wherein like numbers refer to like parts in the several views, and wherein:

Figure 1 is plan view, with portions in cross-section, of a cable and protective sleeve assembly of the prior art;

15 Figure 2 is a cross-sectional view of a ribbon used to manufacture a tubular core according to the prior art;

Figure 3 is a cross-sectional view of the ribbon of Figure 2 wound in helical fashion and edge-joined to
20 manufacture a tubular core according to the prior art;

Figure 4 is a cross-sectional view of a ribbon used to manufacture a tubular core according to the present invention;

Figure 5 is a cross-sectional view of the ribbon
25 of Figure 4 wound in helical fashion and edge-joined to manufacture a tubular core according to the present invention.

Figure 6 is a cross-sectional view of the ribbon of Figure 4 showing a support member within the body of
30 the ribbon.

Description of the Preferred Embodiment

Figures 2 and 3 illustrate a ribbon 20 of the prior art from which a tubular core similar to the core 15 of Figure 1 may be wound. The ribbon 20 includes formed edges 22 and 24 which allow one edge 22 of one longitudinal portion of the ribbon 20 to interlock with the opposite edge 24 of another longitudinal portion of the ribbon 20 so that the ribbon 20 may be helically wound to form a cylindrical tube. This tube may be used as a core to support an elastomeric sleeve of rubber or other suitable material as shown in Figure 1.

As the ribbon 20 is helically wound, the edges are joined by a suitable method, such as by means of an adhesive, heat welding or solvent welding, but preferably ultrasonic welding, to provide sufficient strength in the finished core to support the sleeve in an expanded state. At the same time, it is desirable that the strength of the joint be sufficiently weaker than the strength of the ribbon 20 material so that the joint will separate predictably when it is desired to tear the core into a strip to effect its removal from the sleeve.

It has been found that the configuration of the edges 22 and 24 of the ribbon 20, and the resulting length of the line of contact between the mated edges, did not always allow the results of welding or bonding to be accurately predicted, either in the location of the weld along the line of contact between the halves or in the strength of the bond. In particular, it was found that the vertical surfaces associated with the construction of Figures 2 and 3 caused undesirable and unpredictable welding or bonding at these locations. This at times resulted in tearing of the material of

the ribbon 20 rather than separation at the joint, insufficient strength to support the elastomeric sleeve or undesirably high effort necessary to separate the core into a strip for removal.

5 Figures 4 and 5 illustrate a ribbon 30 designed to minimize the uncertainties associated with the ribbon 20 of Figures 2 and 3. The ribbon 30 is of any polymeric material suitable for ultrasonic welding or other bonding techniques and possessing sufficient
10 strength to support the sleeve. Suitable materials have been found to be polyolefins. The ribbon 30 includes asymmetrical edges 32 and 34 which are designed to provide greater control over bonding in general, and, in particular, ultrasonic welding of the
15 ribbon edges 32 and 34 to each other. Each edge 32 and 34 includes a coupling projection 36 and 38 extending from a major surface of the ribbon 30 to a point short of the opposite major surface of the ribbon 30. Each coupling projection 36 and 38 includes a contour which
20 results in surface contact around substantially the entirety of the projection 38 without any vertical mating surface between the projection 38 and the projection 36.

Each coupling projection 36 and 38 is received by a
25 recess 40 and 42 which are shaped to control contact between the mated edges of the ribbon 30. At least one of the recesses 42 is preferably oversized in relation to its respective coupling projection 36 so that an open area is produced adjacent the coupling projection
30 36 when the coupling projection 36 is inserted in the recess 42. In this manner, the extent of contact between the coupling projections 36 and 38 and the

recesses 40 and 42 is controlled, thus allowing further control over the bonding process used to join the ribbon edges 32 and 34.

As shown in Figures 4 and 5, the ribbon 30 may be formed with a continuous perforation 44 extending from the bottom of the larger recess 42 through the ribbon 30 to exit at the major surface of the ribbon 30. This perforation 44 may be used to control the force necessary to separate the core into a strip for removal. For example, the weld between the edges 32 and 34 of the ribbon 30 can be increased to a high strength level by appropriate selection of edge 32 and 34 contours, but the stripping force can be maintained at lower predetermined levels by proper selection of perforation size and the separation between adjacent perforations.

As shown in Figure 6, the body of ribbon 30 may be provided with a support member 50. Support member 50 extends longitudinally along the length of ribbon 30. Support member 50 preferably has greater strength and temperature resistance than the material forming the remainder of ribbon 30, such that the inclusion of support member 50 in ribbon 30 causes a support core formed from ribbon 30 to exhibit increased resistance to premature collapse when subjected to high pressures from large diameter stretched elastic tubes and when stored in high temperature conditions. Support member 50 is preferably a thermoplastic material, such as ABS resin (a terpolymer based on acrylonitrile, butadiene and styrene), while the remainder of ribbon 30 is formed of a thermoplastic material such as a polyolefin resin. Other suitable materials for support member 50

include, for example, a modified PPO (polyphenylene oxide) resin. Support member 50 is preferably coextruded with the body of ribbon 30. However, other methods of forming ribbon 30 with support member 50 as
5 shown in Figure 6 may be recognized by those skilled in the art, and are contemplated to be within the scope of the present invention.

The improved strength of a core formed from a ribbon 30 as depicted in Figure 6 can be seen from the
10 data in Table 1. The data in Table 1 was generated by forming cores from three types of ribbon: 1) polyolefin with no support member (POLY); 2) polyolefin coextruded with an ABS resin support member (CO-ABS); and 3) polyolefin coextruded with a modified PPO resin support
15 member (CO-PPO). The core internal diameter was measured and the core was placed on its side in a test fixture in a 70C oven. The sample was left in the oven for 10 minutes. Ten minutes into the test, weight was placed on top of the sample and the core inner diameter
20 measured. Additional weight was added and the inside diameter measured at ten minute intervals until the core had collapsed to an oval shape having an inside diameter $2/3$ of the original diameter, at which point core failure was deemed to have occurred. All core
25 samples had a wall thickness of 0.1 inch.

TABLE 1.

Core Material	Initial I.D. (mm)	Failure	
		time (min)	weight (lbs.)
POLY	46	30	5.39
POLY	68	40	8.08
CO-ABS	47	70	16.16
CO-ABS	61	40	8.08
CO-ABS	68	80	18.85
CO-ABS	68	60	13.47
CO-PPO	61	50	10.77
CO-PPO	69	50	10.77

As seen in Table 1, when comparing cores of similar initial diameters, those cores formed from a ribbon having a coextruded support member of either ABS or modified PPO performed significantly better than the cores formed from a ribbon lacking a support member. In particular, the cores having the support member took longer to fail and failed at higher weights than the cores without a support member.

Although the present invention has been described with respect to only a single embodiment of coupling projections, many modifications will be apparent to those skilled in the art. For example, both recesses 40 and 42 may be oversized with respect to the coupling projection 36 or 38 which is to be inserted therein. Also, although only a single projection and recess is shown at each edge of the ribbon, it is possible to have more than one projection on one or both edges, with recesses separating each projection. In this manner, any number of "fingers" could lock the edges of the ribbon together. Similarly, although support member 50 is shown as rectangular in shape, other

shapes and configurations of support member 50 would work equally well.

What is claimed is:

1. A ribbon adapted to be joined to itself to form a helically-wound tube, the ribbon comprising:

a longitudinal body having first and second major
5 surfaces and first and second edges;

a support member extending longitudinally through the body;

a first coupling projection extending from said first major surface toward said second major surface
10 and terminating short of said second major surface;

a second coupling projection extending from said second major surface toward said first major surface and terminating short of said first major surface;

recesses in said ribbon adjacent said first and
15 said second coupling projections for accepting said projections and thus permit said first coupling projection of one ribbon section to engage said second coupling projection of another ribbon section with the major surfaces of said ribbon sections aligned to form
20 a smooth surface on said tube;

said coupling projections being formed such that said first and said second coupling projections engage each other along a continuous surface free of any surfaces which are perpendicular to said major
25 surfaces, at least one of said recesses being larger than the coupling projection to be inserted therein so that an open area is provided adjacent said coupling projection when said coupling projection is inserted within said one recess.

30

2. The ribbon of claim 1, wherein the body and support member are formed of thermoplastic materials.

3. The ribbon of claim 2, wherein the body and support member are coextruded.
- 5 4. The ribbon of claim 3, wherein the body is formed of a polyolefin resin and the support member is formed of ABS resin.
5. A ribbon according to claim 1 further including
10 spaced perforations extending through said ribbon at said one recess.
6. An elastic sleeve assembly comprising an elastic sleeve member supported in highly stretched condition
15 on a hollow core formed of a ribbon adapted to be joined to itself to form a helically-wound tube, the ribbon comprising:
- a longitudinal body having first and second major surfaces and first and second edges;
 - 20 a support member extending longitudinally through the body;
 - a first coupling projection extending from said first major surface toward said second major surface and terminating short of said second major surface;
 - 25 a second coupling projection extending from said second major surface toward said first major surface and terminating short of said first major surface;
 - recesses in said ribbon adjacent said first and said second coupling projections for accepting said
30 projections and thus permit said first coupling projection of one ribbon section to engage said second coupling projection of another ribbon section with the

major surfaces of said ribbon sections aligned to form a smooth surface on said tube;

said coupling projections being formed such that said first and said second coupling projections may
5 engage each other along a substantially continuous surface free of any surface perpendicular to said major surfaces, at least one of said recesses being larger than the coupling projection to be inserted therein so that an open area is provided adjacent said coupling
10 projection when said coupling projection is inserted within said one recess.

7. The ribbon of claim 6, wherein the body and support member are formed of thermoplastic materials.
15

8. The ribbon of claim 7, wherein the body and support member are coextruded.

9. The ribbon of claim 8, wherein the body is formed
20 of a polyolefin resin and the support member is formed of ABS resin.

10. A ribbon according to claim 6 further including spaced perforations extending through said ribbon at
25 said one recess.

1/2




Fig. 1
(PRIOR ART)




Fig. 2
(PRIOR ART)




Fig. 3
(PRIOR ART)




Fig. 4




Fig. 5




Fig. 6

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/13959

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 H02G15/18 H02G1/14 B29C61/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 H02G B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 96 24977 A (MINNESOTA MINING AND MANUFACTURING COMPANY) 15 August 1996 see page 6, line 33 - page 7, line 14; figures 4,5 ---	1,5,6,10
Y	EP 0 735 639 A (PIRELLI CAVI) 2 October 1996 see claim 1; figure 1 ---	1,5,6,10
A	EP 0 619 636 A (SOCIETE INDUSTRIELLE DE LIAISONS ELECTRIQUES) 12 October 1994 see column 4, line 22 - line 30; figure 2 ---	1,6
A	WO 83 00779 A (MINNESOTA MINING AND MANUFACTURING COMPANY) 3 March 1983 see abstract; figures 1,2 --- -/--	1,6

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

° Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

28 September 1998

Date of mailing of the international search report

02/10/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lomme1, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/13959

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 3 808 352 A (JOHNSON) 30 April 1974 see page 3, line 40 - line 46 see column 4, line 48 - line 55; figures 1,2</p> <p style="text-align: center;">-----</p>	1,6

INTERNATIONAL SEARCH REPORT

Information on patent family members

In. tional Application No

PCT/US 98/13959

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9624977 A	15-08-1996	US 5670223 A AU 4689896 A CA 2211178 A EP 0808525 A	23-09-1997 27-08-1996 15-08-1996 26-11-1997
EP 735639 A	02-10-1996	IT MI950606 A AU 5032196 A CA 2172683 A CN 1142581 A JP 9028015 A NO 961215 A US 5800886 A ZA 9602387 A	27-09-1996 10-10-1996 28-09-1996 12-02-1997 28-01-1997 30-09-1996 01-09-1998 30-07-1996
EP 619636 A	12-10-1994	FR 2703817 A CA 2120640 A DE 69404196 D DE 69404196 T ES 2107145 T	14-10-1994 10-10-1994 21-08-1997 26-02-1998 16-11-1997
WO 8300779 A	03-03-1983	AU 8821382 A EP 0087435 A JP 58501303 T ZA 8205931 A	08-03-1983 07-09-1983 04-08-1983 29-06-1983
US 3808352 A	30-04-1974	CH 559981 A JP 49074394 A SE 393716 B ZA 7308273 A	14-03-1975 18-07-1974 16-05-1977 25-09-1974