



(86) Date de dépôt PCT/PCT Filing Date: 1995/03/23
 (87) Date publication PCT/PCT Publication Date: 1995/09/28
 (45) Date de délivrance/Issue Date: 2002/06/25
 (85) Entrée phase nationale/National Entry: 1996/09/20
 (86) N° demande PCT/PCT Application No.: SE 1995/000307
 (87) N° publication PCT/PCT Publication No.: 1995/025604
 (30) Priorité/Priority: 1994/03/23 (9400977-6) SE

(51) Cl.Int.⁶/Int.Cl.⁶ B08B 17/04
 (72) Inventeur/Inventor:
 Svensson, Sigfrid, BE
 (73) Propriétaire/Owner:
 POLYSACCHARIDE INDUSTRIES AB PSI, SE
 (74) Agent: SIM & MCBURNEY

(54) Titre : SYSTEME DE PROTECTION D'UNE SURFACE CONTRE LES SOUILLURES
 (54) Title: PROCESS FOR PROTECTING A SURFACE FROM NON-DESIRED CONTAMINATION

(57) **Abrégé/Abstract:**

A process for protecting a surface from non-desired contamination and for facilitating removal of said contamination from said surface, characterized by the steps: a) preparing a solution of polysaccharides containing at least two components, wherein one component is constituted by a first polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, directly forms a film, and wherein the second component is constituted by a second polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, forms a film via at least partial gel formation, or by interaction with said first polysaccharide, said films being redissolvable or swellable; b) applying the solution from step a) onto said surface before subjected to contamination; c) allowing the applied solution to dry so as to form a solid film on said surface via at least partial gel formation; d) treating the film-coated surface with a liquid capable of redissolving film or provided swelling thereof; and e) removing the non-desired contamination by complete or partial removal of the film from the surface.



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B05D 5/00, C08L 5/00, C09D 5/00	A1	(11) International Publication Number: WO 95/25604 (43) International Publication Date: 28 September 1995 (28.09.95)
(21) International Application Number: PCT/SE95/00307 (22) International Filing Date: 23 March 1995 (23.03.95) (30) Priority Data: 9400976-8 23 March 1994 (23.03.94) SE (71) Applicant (for all designated States except US): POLYSAC- CHARIDE INDUSTRIES AB PSI [SE/SE]; Annedalsvägen 39, S-161 71 Bromma (SE). (72) Inventor; and (75) Inventor/Applicant (for US only): SVENSSON, Sigfrid [SE/BE]; 467, avenue Molière, B-1060 Bryssel (BE). (74) Agent: AWAPATENT AB; P.O. Box 45086, S-104 30 Stockholm (SE).	(81) Designated States: AM, AT, AT (Utility model), AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i> <div style="text-align: center; font-size: 2em; font-weight: bold;">2186131</div>	
(54) Title: PROCESS FOR PROTECTING A SURFACE FROM NON-DESIRED CONTAMINATION		
(57) Abstract A process for protecting a surface from non-desired contamination and for facilitating removal of said contamination from said surface, characterized by the steps: a) preparing a solution of polysaccharides containing at least two components, wherein one component is constituted by a first polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, directly forms a film, and wherein the second component is constituted by a second polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, forms a film via at least partial gel formation, or by interaction with said first polysaccharide, said films being redissolvable or swellable; b) applying the solution from step a) onto said surface before subjected to contamination; c) allowing the applied solution to dry so as to form a solid film on said surface via at least partial gel formation; d) treating the film-coated surface with a liquid capable of redissolving film or provided swelling thereof; and e) removing the non-desired contamination by complete or partial removal of the film from the surface.		

PROCESS FOR PROTECTING A SURFACE FROM NON-DESIRED CONTAMINATION

The present invention relates to a process for protecting surfaces from non-desired contamination and for
5 facilitating removal of such contamination from the surfaces.

In EP B1 0 365 584 there is described a contamination removal process based on the use of a solution containing a polysaccharide and a solvent therefor for creating a
10 protective coating on a surface. After being subjected to contamination such protective surface can be easily freed from the contamination by treating the coated surface with a liquid which is capable of redissolving the protective coating or providing for swelling thereof. The invention
15 according to said patent specification constitutes an excellent solution to the contamination problem as reflected by contamination resulting from so called graffiti, traffic pollution etc.

The present invention constitutes a significant improvement of the techniques disclosed in EP B1 0 365 584,
20 and the purpose of the present invention is to provide for a polysaccharide film which has low solubility in water of room temperature.

A number of polysaccharides, for example carageenan
25 and agar, which are dissolved in water at an increased temperature form at certain minimum concentrations gels when such solution is cooled to a lower temperature. Continued evaporation of water results in the formation of a film which frequently is resistant to dissolution and can
30 be dissolved or made to swell only at an increased temperature.

The coating of surfaces with polysaccharide solutions at an increased temperature is difficult, and to apply a polysaccharide gel by spraying or the like results in inferior
35 adhesion to the substrate since the solvent is inextricably bound in the gel structure.

The problem to be solved by the instant invention can be said to reside in finding new techniques, whereby it is possible to make use of the advantages associated with gel formation as an intermediate stage while at the same time
5 providing for a concentration of polysaccharides in the solution resulting in a film of sufficient thickness. If a polysaccharide of the gelling type is used alone the concentration thereof in solution has to be very low in order to obtain a solution thereof that can be applied without
10 difficulty. If the concentration is increased to a level which will result in sufficient film thickness then gelling will occur and the application by spraying or the like will constitute a severe problem. The invention solves this problem in a satisfactory way and thereby consti-
15 tutes a significant advance in the art.

The present invention aims at solving the problem of obtaining a resistant coating or film constituted by polysaccharides while making use of the advantage of gel formation as an intermediary step in the process of obtaining
20 the film.

To this end the invention provides for a process for protecting a surface from non-desired contamination and for facilitating removal of said contamination from the surface, and said process involves the following steps:

25 a) preparing a solution of polysaccharides containing at least two components, wherein one component is constituted by a first polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, directly forms a film, and wherein the second component is
30 constituted by a second polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, forms a film via at least partial gel formation, or by interaction with said first polysaccharide, when precipitated from a solution by evaporation of the solvent
35 thereof, forms a film via at least partial gel formation, said films being redissolvable or swellable;

3

b) applying the solution from step a) onto said surface before subjected to contamination;

c) allowing the applied solution to dry so as to form a solid film on said surface via at least partial gel formation;

d) treating the film-coated surface with a liquid capable of redissolving film or providing swelling thereof; and

e) removing the non-desired contamination by complete or partial removal of the film from the surface.

The process as outlined above resides in principal in proceeding from a polysaccharide solution, to an intermediate gel and to a solid film. This can be accomplished in three different ways.

According to a first aspect of the invention the solution in step a) above is prepared by using as a second polysaccharide one which is capable of forming, when precipitated from a solution thereof by evaporation of the solvent thereof, a film via at least partial gel formation. In this aspect of the invention there may be used as a second polysaccharide one capable of gel formation, and the gel formation of said second polysaccharide is disturbed by the presence of a first polysaccharide which is non-gelling, so that a solution of the two can be obtained at a desirably high concentration without the formation of a gel at a useful temperature, such as room temperature. Upon evaporation of the solvent from such solution there will be formed a gel which is finally converted into a solid film.

According to a second aspect of the invention there is prepared in step a) above a solution, wherein said second polysaccharide is capable of interacting with said first polysaccharide to give the desired result. According to a third aspect of the invention there may be used an admixture of two polysaccharides, of which each alone will not form a gel when precipitated from a solution by evaporation of the solvent thereof, but which together by in-

teraction pass a gel stage at increased concentration and finally form a solid film.

The three different aspects of the invention described above make it possible to form a protective coating of surfaces, wherein the polysaccharide solution upon concentration passes through the gel stage before forming a solid film. The resulting film resists dissolution since treatment with the solvent, such as water, only results in swelling of the film to a gel unless the temperature is increased so that the gel will be dissolved.

In the process according to the present invention the concentration of polysaccharides in the solution prepared in step a) above preferably exceeds about 0.1% (w/v). It is also preferred that said amount is at most about 10% (w/v), particularly at most about 5% (w/v).

The proportions based on weight between said first and second polysaccharides may vary within very broad limits, such as from about 1000:1 to 1:1000 depending on the nature of the compounds.

Said first polysaccharide used in the process according to the invention and which is of the non-gelling type, is preferably selected from celluloses and derivatives thereof, starches and derivatives thereof, plant gums and microbial polysaccharides. Among plant gums there may be mentioned guar gum and Locust bean gum, and among microbial polysaccharides a useful example is dextran.

The second polysaccharide of the type that is gelling alone or gelling by interaction with the first polysaccharide, is preferably selected from microbial polysaccharides and algal polysaccharides, examples being xanthan and agar.

Particularly preferred combinations are plant gums and xanthan or agar. The concentration of the plant gum is preferably within the range about 1 to about 2% by weight, whereas the second polysaccharide is used in a lesser amount, such as from about 0.2 to about 1% by weight for xanthan and from about 0.005 to about 0.05% by weight for

agar.

In the combination plant gum and agar the proportion by weight between the two suitably lies within the range about 50:1 to about 300:1. In the combination Guar gum -
5 agar the proportion is preferably between from about 150:1 to about 250:1, whereas said proportion with Locust bean gum is preferably from about 50:1 to about 150:1.

Within the concept of this invention more than two polysaccharides may be used, such as two different non-
10 gelling polysaccharides in addition to one polysaccharide of the second type or vice versa, or both.

According to yet another aspect of the invention the solution under step a) above is preferably provided with a pH buffer for the purpose of counteracting changes in the
15 pH of the film formed independent of exterior influence. This is suitable particularly to withstand the influence of environmental conditions, such as acid rain, bird droppings, and other conditions involving acid or basic pH's.

The invention will in the following be further illustrated by non-limiting examples, wherein percentages are
20 given in weight by volume unless otherwise indicated. These examples illustrate the three main aspects of the present invention as outlined above.

25 EXAMPLE 1

20 parts by volume of a solution of dissolvable potato starch (Sigma) in water (2%) are admixed at 90°C with 1 part by volume of a 1% aqueous solution of agar (Sigma). The resulting mixture is cooled to room temperature resulting
30 in a solution of the two polysaccharides.

The resulting solution is applied to a solid substrate (concrete), and upon evaporation of the solvent (to approximately 20% of the original volume) a gel is formed which on further evaporation of solvent forms a solid
35 film. This film is fairly resistant to treatment with cold water (15°C) but a certain swelling of the surface layer of the film will be obtained. The film is well suited for

6

the protection of surfaces against graffiti type of contamination or air pollution, such contamination being easily removable by washing the film using water of increased temperature and/or pressurized water supplied through
5 a nozzle.

EXAMPLE 2

Example 1 is repeated but with the use of an aqueous solution containing 1.5% Locust bean gum and 0.01% agar.
10 Said solution is applied to a substrate (glass) and forms a solid film via the formation of a gel. To improve adhesion of the solution to the glass substrate the glass can be pretreated by the application of a primer, such as polymin.

15

EXAMPLE 3

A solution of a mixture of xanthan gum and Locust bean gum in the weight proportions 1:3 is prepared at a total concentration of polysaccharides of 0.3%. The
20 solution is sprayed onto an aluminum substrate in an amount of 0.1 l/m². After about 1 h at 20°C the applied solution has formed a gel, which after additional 2 h has been converted into a transparent solid film. The properties and behaviour of said film are similar to those
25 of the film of Example 1.

EXAMPLE 4

Example 1 is repeated but in this case there is added to the polysaccharide solution a Sørensen phosphate buffer
30 constituted by a mixture of disodium hydrogen phosphate and potassium dihydrogen phosphate resulting in a pH of the solution of about 7. The resulting film maintains a neutral pH under the influence of acid as well as basic environmental influence, such as acid rain and bird drop-
35 pings, respectively.

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

1. A process for protecting a surface from non-desired contamination and for facilitating removal of said contamination from said surface, comprising the steps:

a) preparing a solution of polysaccharides containing at least two components, wherein one component is constituted by a first polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, directly forms a film, and wherein the second component is constituted by a second polysaccharide which, when precipitated from a solution by evaporation of the solvent thereof, forms a film via at least partial gel formation, or by interaction with said first polysaccharide, when precipitated from a solution by evaporation of the solvent thereof, forms a film via at least partial gel formation, said films being redissolvable or swellable;

b) applying the solution from step a) onto said surface before subjected to contamination;

c) allowing the applied solution to dry so as to form a solid film on said surface via at least partial gel formation;

d) exposing the film-coated surface to non-desired contamination;

e) treating the film-coated surface with a liquid capable of redissolving film or providing swelling thereof; and

f) removing the non-desired contamination by complete or partial removal of the film from the surface.

2. A process according to claim 1, comprising preparing in step a) a solution, wherein said second

polysaccharide only by interaction with said first polysaccharide is capable of forming, when precipitated from a solution thereof by evaporation of the solvent thereof, a film via at least partial gel formation.

3. A process according to claim 1 or 2, comprising preparing in step a) a solution containing polysaccharides in an amount of at least 0.1% (w/v).

4. A process according to claim 3, wherein said amount is at most 10% (w/v).

5. A process according to claim 4, wherein said amount is at most 5% (w/v).

6. A process according to any one of claims 1 to 5, wherein said first polysaccharide is selected from cellulose and derivatives thereof, starch and derivatives thereof, plant gums, and microbial polysaccharides.

7. A process according to claim 6, wherein the first polysaccharide is dextran.

8. A process according to claim 1, wherein said second polysaccharide is an algal polysaccharide.

9. A process according to claim 8, wherein said second polysaccharide is agar.

10. A process according to claim 1 or 4, wherein said second polysaccharide is a microbial polysaccharide.

11. A process according to claim 10, wherein said second polysaccharide is xanthan.

12. A process according to any one of claim 1 to 11, wherein in step a) the solution is supplied with a pH buffer for the purpose of counteracting changes in the pH of the film formed independent of exterior influence.

13. A surface protected by the process according to any one of claims 1 to 12.