



- (51) International Patent Classification:  
G02F 1/15 (2006.01)
- (21) International Application Number:  
PCT/US20 12/0688 17
- (22) International Filing Date:  
10 December 2012 (10. 12.2012)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
61/569,716 12 December 2011 (12. 12.2011) US  
61/664,638 26 June 2012 (26.06.2012) US  
61/709,046 2 October 2012 (02. 10.2012) US
- (71) Applicant (for all designated States except US): **VIEW, INC.** [US/US]; 195 South Milpitas Boulevard, Milpitas, California 95035 (US).
- (72) Inventors; and
- (71) Applicants (for US only): **STRONG, Fabian** [US/US]; 566 School Street, Fremont, California 94536 (US). **BHATNAGAR, Yashraj** [US/US]; 1783 Wade Avenue, Santa Clara, California 95051 (US). **DIXIT, Abhishek Anant** [IN/US]; 6060 Fairmount Parkway, Pasadena,

Texas 77505 (US). **MARTIN, Todd** [US/US]; 1568 Thomas Court, Mountain View, California 94040 (US). **ROZBICKI, Robert T.** [US/US]; 3002 Oakleigh Manor Lane, Germantown, Tennessee 38138 (US).

(74) Agents: **MARTINEZ-LEMKE, Sheila** et al; Weaver Austin Villeneuve & Sampson LLP, P.O. Box 70250, Oakland, California 94612-0250 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,

[Continued on nextpage]

(54) Title: THIN-FILM DEVICES AND FABRICATION




Fig. 4B

(57) Abstract: Thin-film devices, for example electrochromic devices for windows, and methods of manufacturing are described. Particular focus is given to methods of patterning optical devices. Various edge deletion and isolation scribes are performed, for example, to ensure the optical device has appropriate isolation from any edge defects. Methods described herein apply to any thin-film device having one or more material layers sandwiched between two thin film electrical conductor layers. The described methods create novel optical device configurations.

WO 2013/090209 A1

TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— *with international search report (Art. 21(3))*

## THIN-FILM DEVICES AND FABRICATION

### CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims benefit of and priority to USSN 61/569,716, filed on  
5 December 12, 2011; USSN 61/664,638, filed on June 26, 2012 and USSN 61/709,046 filed  
on October 2, 2012, which are incorporated herein by reference in their entirety for all  
purposes.

### FIELD

[0002] Embodiments disclosed herein relate generally to optical devices, and more  
10 particularly to methods of fabricating optical devices.

### BACKGROUND

[0003] Electrochromism is a phenomenon in which a material exhibits a reversible  
electrochemically-mediated change in an optical property when placed in a different  
electronic state, typically by being subjected to a voltage change. The optical property is  
15 typically one or more of color, transmittance, absorbance, and reflectance. For example, one  
well known electrochromic material is tungsten oxide ( $WO_3$ ). Tungsten oxide is a  
cathodically coloring electrochromic material in which a coloration transition, bleached (non-  
colored) to blue, occurs by electrochemical reduction. When electrochemical oxidation takes  
place, tungsten oxide transitions from blue to a bleached state.

20 [0004] Electrochromic materials may be incorporated into, for example, windows for home,  
commercial and other uses. The color, transmittance, absorbance, and/or reflectance of such  
windows may be changed by inducing a change in the electrochromic material, that is,  
electrochromic windows are windows that can be darkened and lightened reversibly via  
application of an electric charge. A small voltage applied to an electrochromic device of the  
25 window will cause it to darken; reversing the voltage causes it to lighten. This capability  
allows control of the amount of light that passes through the windows, and presents an  
opportunity for electrochromic windows to be used as energy-saving devices.

[0005] While electrochromism was discovered in the 1960's, electrochromic devices, and  
particularly electrochromic windows, still unfortunately suffer various problems and have not  
30 begun to realize their full commercial potential despite many recent advancements in

electrochromic technology, apparatus, and related methods of making and/or using electrochromic devices.

### SUMMARY

5 [0006] Thin-film devices, for example, electrochromic devices for windows, and methods of manufacturing are described. Particular focus is given to methods of patterning and fabricating optical devices. Various edge deletion and isolation scribes are performed, for example, to ensure the optical device has appropriate isolation from any edge defects, but also to address unwanted coloration and charge buildup in areas of the device. Edge treatments are applied to one or more layers of optical devices during fabrication. Methods described herein apply to any thin-film device having one or more material layers 10 sandwiched between two thin-film electrical conductor layers. The described methods create novel optical device configurations.

[0007] One embodiment is an optical device including: (i) a first conductor layer on a substrate, the first conductor layer including an area less than that of the substrate, the first 15 conductor layer surrounded by a perimeter area of the substrate which is substantially free of the first conductor layer; (ii) one or more material layers including at least one optically switchable material, the one or more material layers configured to be within the perimeter area of the substrate and co-extensive with the first conductor layer but for at least one exposed area of the first conductor layer, the at least one exposed area of the first conductor 20 layer free of the one or more material layers; and (iii) a second conductor layer on the one or more material layers, the second conductor layer transparent and co-extensive with the one or more material layers, where the one or more material layers and the second conductor layer overhang the first conductor layer but for the at least one exposed area of the first conductor layer. The optical device may further include a vapor barrier layer coextensive with the 25 second conductor layer. The optical device may include a diffusion barrier between the first conductor layer and the substrate. In some embodiments, the optical device does not include an isolation scribe, i.e., there are no inactive portions of the device isolated by a scribe.

[0008] In certain embodiments, the at least one optically switchable material is an electrochromic material. The first and second conductor layers may both be transparent, but 30 at least one is transparent. In certain embodiments, the optical device is all solid-state and inorganic. The substrate may be float glass, tempered or not.

[0009] Certain embodiments include an insulated glass unit (IGU) which includes optical devices described herein. In certain embodiments, any exposed areas of the first conducting layer are configured to be within the primary seal of the IGU. In certain embodiments, any bus bars are also configured to be within the primary seal of the IGU. In certain

5   embodiments, any isolation or other scribes are also within the primary seal of the IGU. Optical devices described herein may be of any shape, e.g., regular polygon shaped such as rectangular, round or oval, triangular, trapezoidal, etc., or irregularly-shaped.

[0010] Some embodiments are methods of making optical devices as described herein. One embodiment is a method of fabricating an optical device including one or more material

10   layers sandwiched between a first and a second conducting layer, the method including: (i) receiving a substrate including the first conducting layer over its work surface (e.g., an underlying glass layer with or without a diffusion barrier); (ii) removing a first width of the first conducting layer from between about 10% and about 90% of the perimeter of the substrate; (iii) depositing the one or more material layers of the optical device and the second

15   conducting layer such that they cover the first conducting layer and, where possible (except where the portion the substrate where the first conducting layer was not removed), extend beyond the first conducting layer about its perimeter; (iv) removing a second width, narrower than the first width, of all the layers about substantially the entire perimeter of the substrate, where the depth of removal is at least sufficient to remove the first conducting layer; (v)

20   removing at least one portion of the second transparent conducting layer and the one or more layers of the optical device thereunder thereby revealing at least one exposed portion of the first conducting layer; and (vi) applying an electrical connection, e.g. a bus bar, to the at least one exposed portion of the first transparent conducting layer; where at least one of the first and second conducting layers is transparent.

[0011] In one embodiment, (ii) includes removing the first width of the first conducting layer from between about 50% and about 75% around the perimeter of the substrate. In one embodiment, the at least one exposed portion of the first conducting layer exposed is fabricated along the perimeter portion of the optical device proximate the side or sides of the substrate where the first conducting layer was not removed in (ii). Methods may further

30   include applying at least one additional electrical connection (e.g., a second bus bar) to the second conducting layer. Aspects of methods described herein may be performed in an all vacuum integrated deposition apparatus. Methods may further include fabricating an IGU using optical devices as described herein.

[0012] Certain embodiments include fabrication methods, and resulting devices, having particular edge treatments which create more robust and better performing devices. For example the edge of an electrochromic device layer or layers may be tapered in order to avoid stress and cracking in overlying layers of the device construct. In another example, lower conductor exposure for bus bar application is carried out to ensure good electrical contact and uniform coloration front in the electrochromic device. In certain embodiments, device edge treatments, isolation scribes and lower conductor layer exposures are performed using variable depth laser scribes.

[0013] These and other features and advantages will be described in further detail below, with reference to the associated drawings.

### BRIEF DESCRIPTION OF THE DRAWINGS

[0014] The following detailed description can be more fully understood when considered in conjunction with the drawings in which:

[0015] **Figures 1A, 1B, and 1C** are cross-section, end view, and top view drawings respectively of an electrochromic device fabricated on a glass substrate.

[0016] **Figure 1D** is a detailed portion of the cross-section shown in **Figure 1A**.

[0017] **Figure 2A** is a partial cross-section of an improved electrochromic device architecture on a substrate, according to disclosed embodiments.

[0018] **Figures 2B-2C** are cross-sectional and end view drawings respectively of an improved device architecture similar to that described in relation to **Figure 2A**.

[0019] **Figures 2D-E** are partial cross-sectional and top view drawings respectively of a device with an architecture similar to that described in relation to **Figures 2A-C**.

[0020] **Figure 3** is a partial cross-section showing an improved device architecture where the diffusion barrier is removed along with the lower conducting layer.

[0021] **Figure 4A** is a flowchart of a process flow describing aspects of a method of fabricating an electrochromic device, according to embodiments.

[0022] **Figure 4B** are top views depicting steps in the process flow described in relation to **Figure 4A**.

[0023] **Figure 4C** depicts cross-sections of the electrochromic lite described in relation to **Figure 4B**.

[0024] **Figure 4D** is a top view schematic depicting steps during fabrication on a round substrate.

5 [0025] **Figure 4E** is a top view schematic depicting steps during fabrication of an electrochromic device.

[0026] **Figure 4F** is a schematic drawing in the perspective view depicting fabrication of an IGU with an optical device.

10 [0027] **Figure 4G** is a schematic drawing of top views of devices similar to that described in relation to **Figure 4B**.

[0028] **Figures 4H** and **4I** are schematic drawings depicting steps of a process flow similar to that described in relation to **Figure 4A** and carried out on a large-area substrate as applied to coat then cut methods.

15 [0029] **Figure 4J** is a drawing depicting roll-to-roll processing forming laminates of electrochromic devices where the lamination uses a flexible mate lite.

[0030] **Figure 5A** is a flowchart of a process flow describing aspects of a method of fabricating an optical device having opposing bus bars on each of first and second conductor layers.

20 [0031] **Figure 5B** is a schematic of top-views depicting steps in the process flow described in relation to **Figure 5A**.

[0032] **Figure 5C** shows cross-sections of the electrochromic lite described in relation to **Figure 5B**.

[0033] **Figures 5D** and **5E** are top view schematics of electrochromic devices.

25 [0034] **Figures 5F** and **5G** are schematic drawings depicting steps in a process flow similar to that described in relation to **Figure 5A** and carried out on a large-area substrate as applied to coat then cut methods, according to embodiments.

[0035] **Figure 6A** is a schematic drawing depicting roll-to-roll fabrication of electrochromic devices on flexible substrates and optional lamination with rigid substrates.

[0036] **Figure 6B** is a schematic drawing depicting lamination of electrochromic devices on flexible glass substrates and lamination with flexible substrates.

[0037] **Figure 7** includes cross-sectional views of an electrochromic device similar to the device described in relation to **Figure 4C**, detailing problematic issues overcome by certain embodiments described herein.

[0038] **Figures 8A** and **8B** is a cross-sectional and top view respectively of an electrochromic device describing tapering the edge(s) of the lower conductor layer in order to avoid stress in subsequently deposited overlying layers.

[0039] **Figures 9A** and **9B** are drawings depicting problematic issues related to exposure of a lower conductor for bus bar application.

[0040] **Figures 10A** through **10F** are drawings depicting embodiments for improved bus bar pad exposure.

#### DETAILED DESCRIPTION

[0041] For the purposes of brevity, embodiments are described in terms of electrochromic devices; however, the scope of the disclosure is not so limited. One of ordinary skill in the art would appreciate that methods described can be used to fabricate virtually any thin-film device where one or more layers are sandwiched between two thin-film conductor layers. Certain embodiments are directed to optical devices, that is, thin-film devices having at least one transparent conductor layer. In the simplest form, an optical device includes a substrate and one or more material layers sandwiched between two conductor layers, one of which is transparent. In one embodiment, an optical device includes a transparent substrate and two transparent conductor layers. In another embodiment, an optical device includes a transparent substrate upon which is deposited a transparent conductor layer (the lower conductor layer) and the other (upper) conductor layer is not transparent. In another embodiment, the substrate is not transparent, and one or both of the conductor layers is transparent. Some examples of optical devices include electrochromic devices, flat panel displays, photovoltaic devices, suspended particle devices (SPD's), liquid crystal devices (LCD's), and the like. For context, a description of electrochromic devices is presented below. For convenience, all solid-state and inorganic electrochromic devices are described; however, embodiments are not limited in this way.



[0042] A particular example of an electrochromic lite is described with reference to **Figures 1A-1D**, in order to illustrate embodiments described herein. The electrochromic lite includes an electrochromic device fabricated on a substrate. **Figure 1A** is a cross-sectional representation (see cut X-X' of **Figure 1C**) of an electrochromic lite, **100**, which is fabricated starting with a glass sheet, **105**. **Figure 1B** shows an end view (see perspective Y-Y' of **Figure 1C**) of electrochromic lite **100**, and **Figure 1C** shows a top-down view of electrochromic lite **100**.

[0043] **Figure 1A** shows the electrochromic lite **100** after fabrication on glass sheet **105** and the edge has been deleted to produce area **140** around the perimeter of the lite. Edge deletion refers to removing one or more material layers from the device about some perimeter portion of the substrate. Typically, though not necessarily, edge deletion removes material down to and including the lower conductor layer (e.g., layer **115** in the example depicted in **Figures 1A-1D**), and may include removal of any diffusion barrier layer(s) down to the substrate itself. In **Figures 1A-1B**, the electrochromic lite **100** has also been laser scribed and bus bars have been attached. The glass lite, **105**, has a diffusion barrier, **110**, and a first transparent conducting oxide (TCO) **115** on the diffusion barrier.

[0044] In this example, the edge deletion process removes both TCO **115** and diffusion barrier **110**, but in other embodiments, only the TCO is removed, leaving the diffusion barrier intact. The TCO layer **115** is the first of two conductive layers used to form the electrodes of the electrochromic device fabricated on the glass sheet. In some examples, the glass sheet may be prefabricated with the diffusion barrier formed over underlying glass. Thus, the diffusion barrier is formed, and then the first TCO **115**, an EC stack **125** (e.g., stack having electrochromic, ion conductor, and counter electrode layers), and a second TCO, **130**, are formed. In other examples, the glass sheet may be prefabricated with both the diffusion barrier and the first TCO **115** formed over underlying glass.

[0045] In certain embodiments, one or more layers may be formed on a substrate (e.g., glass sheet) in an integrated deposition system where the substrate does not leave the integrated deposition system at any time during fabrication of the layer(s). In one embodiment, an electrochromic device including an EC stack and a second TCO may be fabricated in the integrated deposition system where the glass sheet does not leave the integrated deposition system at any time during fabrication of the layers. In one case, the first TCO layer may also be formed using the integrated deposition system where the glass sheet does not leave the integrated deposition system during deposition of the EC stack, and the TCO layer(s). In one

embodiment, all of the layers (e.g., diffusion barrier, first TCO, EC stack, and second TCO) are deposited in the integrated deposition system where the glass sheet does not leave the integrated deposition system during deposition. In this example, prior to deposition of EC stack **125**, an isolation trench, **120**, may be cut through first TCO **115** and diffusion barrier **110**. Trench **120** is made in contemplation of electrically isolating an area of first TCO **115** that will reside under bus bar 1 after fabrication is complete (see **Figure 1A**). Trench **120** is sometimes referred to as the "LI" scribe, because it is the first laser scribe in certain processes. This is done to avoid charge buildup and coloration of the EC device under the bus bar, which can be undesirable. This undesirable result is explained in more detail below and was the impetus for certain embodiments described herein. That is, certain embodiments are directed toward eliminating the need for isolation trenches, such as trench **120**, for example, to avoid charge buildup under a bus bar, but also to simplify fabrication of the device by reducing or even eliminating laser isolation scribe steps.

[0046] After formation of the EC device, edge deletion processes and additional laser scribing are performed. **Figures 1A** and **1B** depict areas **140** where the EC device has been removed, in this example, from a perimeter region surrounding laser scribe trenches, **150**, **155**, **160** and **165**. Laser scribes **150**, **160** and **165** are sometimes referred to as "L2" scribes, because they are the second scribes in certain processes. Laser scribe **155** is sometimes referred to as the "L3" scribe, because it is the third scribe in certain processes. The L3 scribe passes through second TCO, **130**, and in this example (but not necessarily) the EC stack **125**, but not the first TCO **115**. Laser scribe trenches **150**, **155**, **160**, and **165** are made to isolate portions of the EC device, **135**, **145**, **170**, and **175**, which were potentially damaged during edge deletion processes from the operable EC device. In one embodiment, laser scribe trenches **150**, **160**, and **165** pass through the first TCO to aid in isolation of the device (laser scribe trench **155** does not pass through the first TCO, otherwise it would cut off bus bar 2's electrical communication with the first TCO and thus the EC stack). In some embodiments, such as those depicted in **Figures 1A-1D**, laser scribe trenches **150**, **160**, and **165** may also pass through a diffusion barrier.

[0047] The laser or lasers used for the laser scribe processes are typically, but not necessarily, pulse-type lasers, for example, diode-pumped solid state lasers. For example, the laser scribe processes can be performed using a suitable laser. Some examples of suppliers that may provide suitable lasers include IPG Photonics Corp. (of Oxford, Massachusetts), Ekspla (of Vilnius, Lithuania), TRUMPF Inc. (Farmington, Connecticut), SPI Lasers LLC

(Santa Clara, California), Spectra-Physics Corp. (Santa Clara, California), nLIGHT Inc. (Vancouver, Washington), and Fianium Inc. (Eugene, Oregon). Certain scribing steps can also be performed mechanically, for example, by a diamond tipped scribe; however, certain embodiments describe depth control during scribes or other material removal processing, which is well controlled with lasers. For example, in one embodiment, edge deletion is performed to the depth of the first TCO, in another embodiment edge deletion is performed to the depth of a diffusion barrier (the first TCO is removed), in yet another embodiment edge deletion is performed to the depth of the substrate (all material layers removed down to the substrate). In certain embodiments, variable depth scribes are described.

10 [0048] After laser scribing is complete, bus bars are attached. Non-penetrating bus bar (1) is applied to the second TCO. Non-penetrating bus bar (2) is applied to an area where the device including an EC stack and a second TCO was not deposited (for example, from a mask protecting the first TCO from device deposition) or, in this example, where an edge deletion process (e.g. laser ablation using an apparatus e.g. having a XY or XYZ galvanometer) was used to remove material down to the first TCO. In this example, both bus bar 1 and bus bar 2 are non-penetrating bus bars. A penetrating bus bar is one that is typically pressed into (or soldered) and through one or more layers to make contact with a lower conductor, e.g. TCO located at the bottom of or below one or more layers of the EC stack). A non-penetrating bus bar is one that does not penetrate into the layers, but rather makes electrical and physical contact on the surface of a conductive layer, for example, a TCO. A typical example of a non-penetrating bus bar is a conductive ink, e.g. a silver-based ink, applied to the appropriate conductive surface.

25 [0049] The TCO layers can be electrically connected using a non-traditional bus bar, for example, a bus bar fabricated with screen and lithography patterning methods. In one embodiment, electrical communication is established with the device's transparent conducting layers via silk screening (or using another patterning method) a conductive ink followed by heat curing or sintering the ink. Advantages to using the above described device configuration include simpler manufacturing, for example, and less laser scribing than conventional techniques which use penetrating bus bars.

30 [0050] After the bus bars are fabricated or otherwise applied to one or more conductive layers, the electrochromic lite may be integrated into an insulated glass unit (IGU), which includes, for example, wiring for the bus bars and the like. In some embodiments, one or both of the bus bars are inside the finished IGU. In particular embodiments, both bus bars are

configured between the spacer and the glass of the IGU (commonly referred to as the primary seal of the IGU); that is, the bus bars are registered with the spacer used to separate the lites of an IGU. Area **140** is used, at least in part, to make the seal with one face of the spacer used to form the IGU. Thus, the wires or other connection to the bus bars runs between the spacer and the glass. As many spacers are made of metal, e.g., stainless steel, which is conductive, it is desirable to take steps to avoid short circuiting due to electrical communication between the bus bar and connector thereto and the metal spacer. Particular methods and apparatus for achieving this end are described in U.S. Patent Application, serial number 13/312,057, filed December 6, 2011, and titled "Improved Spacers for Insulated Glass Units," which is hereby incorporated by reference in its entirety. In certain embodiments described herein, methods and resulting IGUs include having the perimeter edge of the EC device, bus bars and any isolation scribes are all within the primary seal of the IGU.

**[0051]** **Figure 1D** depicts a portion of the cross section in **Figure 1A**, where a portion of the depiction is expanded to illustrate an issue for which certain embodiments disclosed herein may overcome. Prior to fabrication of EC stack **125** on TCO **115**, an isolation trench, **120**, is formed through TCO **115** and diffusion barrier **110** in order to isolate a portion of the **115/110** stack from a larger region. This isolation trench is intended to cut off electrical communication of the lower TCO **115**, which is ultimately in electrical communication with bus bar 2, with a section of TCO **115** that lies directly below bus bar 1, which lies on TCO **130** and supplies electrical energy thereto. For example, during coloration of the EC device, bus bar 1 and bus bar 2 are energized in order to apply a potential across the EC device; for example, TCO **115** has a negative charge and TCO **130** has a positive charge or visa versa.

**[0052]** Isolation trench **120** is desirable for a number of reasons. It is sometimes desirable not to have the EC device color under bus bar 1 since this area is not viewable to the end user (the window frame typically extends beyond the bus bars and the isolation trench and/or these features are under the spacer as described above). Also, sometimes area **140** includes the lower TCO and the diffusion barrier, and in these instances it is undesirable for the lower TCO to carry charge to the edge of the glass, as there may be shorting issues and unwanted charge loss in areas that are not seen by the end user. Also, because the portion of the EC device directly under the bus bar experiences the most charge flux, there is a predisposition for this region of the device to form defects, e.g., delamination, particle dislodging (pop-off defects), and the like, which can cause abnormal or no coloring regions that become visible in

the viewable region and/or negatively affect device performance. Isolation trench **120** was designed to address these issues. Despite these desired outcomes, it has been found that coloration below the first bus bar still occurs. This phenomenon is explained in relation to the expanded section of device **100** in the lower portion of **Figure ID**.

5 **[0053]** When EC stack **125** is deposited on first TCO **115**, the electrochromic materials, of which EC stack **125** is comprised, fill isolation trench **120**. Though the electrical path of first TCO **115** is cut off by trench **120**, the trench becomes filled with material that, although not as electrically conductive as the TCO, is able to carry charge and is permeable to ions. During operation of EC lite **100**, e.g. when first TCO **115** has a negative charge (as depicted  
10 in **Figure ID**), small amounts of charge pass across trench **120** and enter the isolated portion of first TCO **115**. This charge buildup may occur over several cycles of coloring and bleaching EC lite **100**. Once the isolated area of TCO **115** has charge built up, it allows coloration of the EC stack **125** under bus bar 1, in area **180**. Also, the charge in this portion of first TCO **115**, once built up, does not drain as efficiently as charge normally would in the  
15 remaining portion of TCO **115**, e.g., when an opposite charge is applied to bus bar 2. Another problem with isolation trench **120** is that the diffusion barrier may be compromised at the base of the trench. This can allow sodium ions to diffuse into the EC stack **125** from the glass substrate. These sodium ions can act as charge carriers and enhance charge buildup on the isolated portion of first TCO **115**. Yet another issue is that charge buildup under the  
20 bus bar can impose excess stress on the material layers and promote defect formation in this area. Finally, fabricating an isolation scribe in the conductor layer on the substrate adds further complication to the processing steps. Embodiments described herein may overcome these problems and others.

**[0054]** **Figure 2A** is a partial cross-section showing an improved architecture of an EC  
25 device, **200**. In this illustrated embodiment, the portion of first TCO **115** that would have extended below bus bar 1 is removed prior to fabrication of EC stack **125**. In this embodiment, diffusion barrier **110** extends to under bus bar 1 and to the edge of the EC device. In some embodiments, the diffusion barrier extends to the edge of glass **105**, that is, it covers area **140**. In other embodiments, a portion of the diffusion barrier may also be  
30 removed under the bus bar 1. In the aforementioned embodiments, the selective TCO removal under bus bar 1 is performed prior to fabrication of EC stack **125**. Edge deletion processes to form areas **140** (e.g., around the perimeter of the glass where the spacer forms a seal with the glass) can be performed prior to device fabrication or after. In certain

embodiments, an isolation scribe trench, **150a**, is formed if the edge delete process to form **140** creates a rough edge or otherwise unacceptable edge due to, e.g., shorting issues, thus isolating a portion, **135a**, of material from the remainder of the EC device. As exemplified in the expanded portion of EC device **200** depicted in **Figure 2A**, since there is no portion of TCO **115** under bus bar 1, the aforementioned problems such as unwanted coloring and charge buildup may be avoided. Also, since diffusion barrier **110** is left intact, at least co-extensive with EC stack **125**, sodium ions are prevented from diffusing into the EC stack **125** and causing unwanted conduction or other problems.

[0055] In certain embodiments, a band of TCO **115** is selectively removed in the region under where bus bar 1 will reside once fabrication is complete. That is, the diffusion barrier **110** and first TCO **115** may remain on the area **140**, but a width of the first TCO **115** is selectively removed under bus bar 1. In one embodiment, the width of the removed band of TCO **115** may greater than the width of the bus bar 1 which resides above the removed band of TCO once device fabrication is complete. Embodiments described herein include an EC device having the configuration as depicted and described in relation to **Figure 2A** with a selectively removed band of TCO **115**. In one embodiment, the remainder of the device is as depicted and described as in relation to **Figures 1A-C**.

[0056] A device similar to device **200** is depicted in **Figures 2B** and **2C**, showing the device architecture including laser isolation trenches and the like. **Figures 2B** and **2C** are drawings of an improved device architecture of disclosed embodiments. In certain embodiments, there are fewer, or no, laser isolation trenches made during fabrication of the device. These embodiments are described in more detail below.

[0057] **Figures 2D** and **2E** depict an electrochromic device, **205**, which has architecture very similar to device **200**, but it has neither a laser isolation scribe **150a**, nor an isolated region, **135a**, of the device that is non-functional. Certain laser edge delete processes leave a sufficiently clean edge of the device such that laser scribes like **150a** are not necessary. One embodiment is an optical device as depicted in **Figures 2D** and **2E** but not having isolation scribes **160** and **165**, nor isolated portions **170** and **175**. One embodiment is an optical device as depicted in **Figures 2D** and **2E** but not having isolation scribe **155**, nor isolated portion **145**. One embodiment is an optical device as depicted in **Figures 2D** and **2E** but not having isolation scribes **160**, **165**, or **155**, nor isolated portions **145**, **170**, and **175**. In certain embodiments, fabrication methods do not include any laser isolation scribes and thus produce optical devices having no physically isolated non-functional portions of the device.

[0058] As described in more detail below, certain embodiments include devices where the one or more material layers of the device and the second (upper) conductor layer are not co-extensive with the first (lower) conductor layer; specifically, these portions overhang the first conductor layer about some portion of the perimeter of the area of the first conductor. These overhanging portions may or may not include a bus bar. As an example, the overhanging portions as described in relation to **Figure 2A** or **3** do have a bus bar on the second conductor layer.

[0059] **Figure 3** is a partial cross-section showing an improved electrochromic device architecture, **300** of disclosed embodiments. In this illustrated embodiment, the portions of TCO **115** and diffusion barrier **110** that would have extended below bus bar 1 are removed prior to fabrication of EC stack **125**. That is, the first TCO and diffusion barrier removal under bus bar 1 is performed prior to fabrication of EC stack **125**. Edge deletion processes to form areas **140** (e.g., around the perimeter of the glass where the spacer forms a seal with the glass) can be performed prior to device fabrication (e.g., removing the diffusion barrier and using a mask thereafter) or after device fabrication (removing all materials down to the glass). In certain embodiments, an isolation scribe trench, analogous to **150a** in **Figure 2A**, is formed if the edge deletion process to form **140** creates a rough edge, thus isolating a portion, **135a** (see **Figure 2A**), of material from the remainder of the EC device.

[0060] Referring again to **Figure 3**, as exemplified in the expanded portion of device **300**, since there is no portion of TCO **115** under bus bar 1, therefore the aforementioned problems such as unwanted coloring and charge buildup may be avoided. In this example, since diffusion barrier **110** is also removed, sodium ions may diffuse into the EC stack in the region under bus bar 1; however, since there is no corresponding portion of TCO **115** to gain and hold charge, coloring and other issues are less problematic. In certain embodiments, a band of TCO **115** and diffusion barrier **110** is selectively removed in the region under where bus bar 1 will reside; that is, on the area **140**, the diffusion barrier and TCO may remain, but a width of TCO **115** and diffusion barrier **110** is selectively removed under and at least co-extensive with bus bar 1. In one embodiment, the width of the removed band of TCO and diffusion barrier is greater than the width of the bus bar which resides above the removed band once device fabrication is complete. Embodiments described herein include an EC device having the configuration as depicted and described in relation to **Figure 3**. In one embodiment, the remainder of the device is as depicted and described as in relation to

**Figures 1A-C.** In certain embodiments, there are fewer, or no, laser isolation trenches made during fabrication of the device.

[0061] Embodiments include an optical device as described in relation to **Figure 3**, where the remainder is as device **205** as described in relation to **Figures 2D** and **2E**. One embodiment is an optical device as depicted in **Figure 3**, but not having isolation scribes **160** and **165**, nor isolated portions **170** and **175**, as depicted **Figures 2D** and **2E**. One embodiment is an optical device as depicted in **Figure 3**, but not having isolation scribe **155**, nor isolated portion **145**, as depicted in **Figures 2D** and **2E**. One embodiment is an optical device as depicted in **Figure 3**, but not having isolation scribes **160**, **165**, or **155**, nor isolated portions **145**, **170**, and **175**, as depicted in **Figures 2D** and **2E**. Any of the aforementioned embodiments may also include an isolation scribe analogous to scribe **150** as depicted in relation to **Figures 1A-D**, but not an isolation scribe analogous to scribe **120**. All embodiments described herein obviate the need for a laser isolation scribe analogous to scribe **120**, as described in relation to **Figures 1A-D**. In addition, the goal is to reduce the number of laser isolation scribes needed, but depending upon the device materials or lasers used for example, the scribes other than scribe **120** may or may not be necessary.

[0062] As described above, in certain embodiments, devices are fabricated without the use of laser isolation scribes, that is, the final device has no isolated portions that are non-functional. Exemplary fabrication methods are described below in terms of having no isolation scribes; however, it is to be understood that one embodiment is any device as described below, where the device has the functional equivalent (depending on its geometry) of the isolation scribes as described in relation to **Figures 1A-D**, but not isolation scribe **120**. More specifically, one embodiment is an optical device as described below, but not having isolation scribes **160** and **165** as depicted **Figures 2D** and **2E**. One embodiment is an optical device as described below, but not having isolation scribe **155** as depicted in **Figures 2D** and **2E**. One embodiment is an optical device as described below, but not having isolation scribes **160**, **165**, or **155** as depicted in **Figures 2D** and **2E**. Any of the aforementioned embodiments may also include an isolation scribe analogous to scribe **150** as depicted in relation to **Figures 1A-D**.

[0063] One embodiment is a method of fabricating an optical device including one or more material layers sandwiched between a first conducting layer (e.g., first TCO **115**) and a second conducting layer (e.g., second TCO **130**). The method includes: (i) receiving a substrate including the first conducting layer over its work surface; (ii) removing a first width



of the first conducting layer from between about 10% and about 90% of the perimeter of the substrate; (iii) depositing the one or more material layers of the optical device and the second conducting layer such that they cover the first conducting layer and, where possible, extend beyond the first conducting layer about its perimeter; (iv) removing a second width, narrower than the first width, of all the layers about substantially the entire perimeter of the substrate, where the depth of removal is at least sufficient to remove the first conducting layer; (v) removing at least one portion of the second transparent conducting layer and the one or more layers of the optical device thereunder thereby revealing at least one exposed portion of the first conducting layer; and (vi) applying a bus bar to the at least one exposed portion of the first transparent conducting layer; where at least one of the first and second conducting layers is transparent. In one embodiment, (ii) includes removing the first width of the first conducting layer from between about 50% and about 75% around the perimeter of the substrate.

**[0064]** In one embodiment, a portion of the edge of the first conducting layer remaining after (ii) is tapered as described in more detail below. The tapered portion of the edge may include one, two or more sides if the transparent conductor is of a polygonal shape after (ii). In some cases, the first conducting layer is polished before (ii), and then optionally edge tapered. In other cases, the first conducting layer is polished after (ii), with or without edge tapering. In the latter cases, tapering can be prior to polish or after polishing.

**[0065]** In one embodiment, the at least one exposed portion of the first conducting layer exposed is fabricated along the perimeter portion of the optical device proximate the side or sides of the substrate where the first conducting layer was not removed in (ii). In certain embodiments, the exposed portion of the first conducting layer is not an aperture, or hole, through the one or more material layers and second conducting layer, but rather the exposed portion is an area that sticks out from an edge portion of the functional device stack layers. This is explained in more detail below with reference to particular examples.

**[0066]** The method may further include applying at least one second bus bar to the second conducting layer, particularly on a portion that does not cover the first conducting layer. In one embodiment, the optical device is an electrochromic device and may be all solid-state and inorganic. The substrate may be float glass and the first conducting layer may include tin oxide, e.g. fluorinated tin oxide. In one embodiment, (iii) is performed in an all vacuum integrated deposition apparatus. In certain embodiments, the method further includes depositing a vapor barrier layer on the second conducting layer prior to (iv).

[0067] In one embodiment, the at least one exposed portion of the first conducting layer is fabricated along the length of one side of the optical device, in one embodiment along the length of the side of the optical device proximate the side of the substrate where the first conducting layer was not removed in (ii). In one embodiment, the at least one second bus bar is applied to the second conducting layer proximate the side of the optical device opposite the at least one exposed portion of the first conducting layer. If a vapor barrier is applied a portion is removed in order to expose the second conductor layer for application of the at least one second bus bar. These methods are described below in relation to specific embodiments with relation to **Figures 4A-D**.

10 [0068] **Figure 4A** is a process flow, **400**, describing aspects of a method of fabricating an electrochromic device or other optical device having opposing bus bars, each applied to one of the conductor layers of the optical device. The dotted lines denote optional steps in the process flow. An exemplary device, **440**, as described in relation to **Figures 4B-C**, is used to illustrate the process flow. **Figure 4B** provides top views depicting the fabrication of device  
15 **440** including numerical indicators of process flow **400** as described in relation to **Figure 4A**. **Figure 4C** shows cross-sections of the lite including device **440** described in relation to **Figure 4B**. Device **440** is a rectangular device, but process flow **400** applies to any shape of optical device having opposing bus bars, each on one of the conductor layers. This aspect is described in more detail below, e.g. in relation to **Figure 4D** (which illustrates process flow  
20 **400** as it relates to fabrication of a round electrochromic device).

[0069] Referring to **Figures 4A** and **4B**, after receiving a substrate with a first conductor layer thereon, process flow **400** begins with an optional polishing of the first conductor layer, see **401**. In certain embodiments, polishing a lower transparent conductor layer has been found to enhance the optical properties of, and performance of, EC devices fabricated  
25 thereon. Polishing of transparent conducting layers prior to electrochromic device fabrication thereon is described in patent application, PCT/US 12/57606, titled, "Optical Device Fabrication," filed on September 27, 2012, which is hereby incorporated by reference in its entirety. Polishing, if performed, may be done prior to an edge deletion, see **405**, or after an edge deletion in the process flow. In certain embodiments, the lower conductor layer may be  
30 polished both before and after edge deletion. Typically, the lower conductor layer is polished only once.

[0070] Referring again to **Figure 4A**, if polishing **401** is not performed, process **400** begins with edge deleting a first width about a portion of the perimeter of the substrate, see **405**. The

edge deletion may remove only the first conductor layer or may also remove a diffusion barrier, if present. In one embodiment, the substrate is glass and includes a sodium diffusion barrier and a transparent conducting layer thereon, e.g. a tin-oxide based transparent metal oxide conducting layer. The substrate may be rectangular (e.g., the square substrate depicted  
5 in see **Figure 4B**). The dotted area in **Figure 4B** denotes the first conductor layer. Thus, after edge deletion according to process **405**, a width **A** is removed from three sides of the perimeter of substrate **430**. This width is typically, but not necessarily, a uniform width. A second width, **B**, is described below. Where width **A** and/or width **B** are not uniform, then their relative magnitudes with respect to each other are in terms of their average width.

10 [0071] As a result of the removal of the first width **A** at **405**, there is a newly exposed edge of the lower conductor layer. In certain embodiments, at least a portion of this edge of the first conductive layer may be optionally tapered, see **407** and **409**. The underlying diffusion barrier layer may also be tapered. The inventors have found that tapering the edge of one or more device layers, prior to fabricating subsequent layers thereon, has unexpected advantages  
15 in device structure and performance. The edge tapering process is described in more detail in relation to **Figures 8A** and **8B**.

[0072] In certain embodiments, the lower conductor layer is optionally polished after edge tapering, see **408**. It has been found, that with certain device materials, it may be advantageous to polish the lower conductor layer after the edge taper, as polishing can have  
20 unexpected beneficial effects on the edge taper as well as the bulk conductor surface which may improve device performance (as described above). In certain embodiments, the edge taper is performed after polish **408**, see **409**. Although edge tapering is shown at both **407** and **409** in **Figure 4A**, if performed, edge tapering would typically be performed once (e.g., at **407** or **409**).

25 [0073] After removal of the first width **A**, and optional polishing and/or optional edge tapering as described above, the EC device is deposited over the surface of substrate **430**, see **410**. This deposition includes one or more material layers of the optical device and the second conducting layer, e.g. a transparent conducting layer such as indium tin oxide (ITO). The depicted coverage is the entire substrate, but there could be some masking due to a  
30 carrier that must hold the glass in place. In one embodiment, the entire area of the remaining portion of the first conductor layer is covered including overlapping the first conductor about the first width **A** previously removed. This allows for overlapping regions in the final device architecture as explained in more detail below.

[0074] In particular embodiments, electromagnetic radiation is used to perform edge deletion and provide a peripheral region of the substrate, e.g. to remove transparent conductor layer or more layers (up to and including the top conductor layer and any vapor barrier applied thereto), depending upon the process step. In one embodiment, the edge deletion is performed at least to remove material including the transparent conductor layer on the substrate, and optionally also removing a diffusion barrier if present. In certain embodiments, edge deletion is used to remove a surface portion of the substrate, e.g. float glass, and may go to a depth not to exceed the thickness of the compression zone. Edge deletion is performed, e.g., to create a good surface for sealing by at least a portion of the primary seal and the secondary seal of the IGU. For example, a transparent conductor layer can sometimes lose adhesion when the conductor layer spans the entire area of the substrate and thus has an exposed edge, despite the presence of a secondary seal. Also, it is believed that when metal oxide and other functional layers have such exposed edges, they can serve as a pathway for moisture to enter the bulk device and thus compromise the primary and secondary seals.

[0075] Edge deletion is described herein as being performed on a substrate that is already cut to size. However, edge deletion can be done before a substrate is cut from a bulk glass sheet in other disclosed embodiments. For example, non-tempered float glass may be cut into individual lites after an EC device is patterned thereon. Methods described herein can be performed on a bulk sheet and then the sheet cut into individual EC lites. In certain embodiments, edge deletion may be carried out in some edge areas prior to cutting the EC lites, and again after they are cut from the bulk sheet. In certain embodiments, all edge deletion is performed prior to excising the lites from the bulk sheet. In embodiments employing "edge deletion" prior to cutting the panes, portions of the coating on the glass sheet can be removed in anticipation of where the cuts (and thus edges) of the newly formed EC lites will be. In other words, there is no actual substrate edge yet, only a defined area where a cut will be made to produce an edge. Thus "edge deletion" is meant to include removing one or more material layers in areas where a substrate edge is anticipated to exist. Methods of fabricating EC lites by cutting from a bulk sheet after fabrication of the EC device thereon are described in U.S. Patent Application, serial number 12/941,882 (now U.S. Patent No. 8,164,818), filed November 8, 2010, and U.S. Patent Application, serial number 13/456,056, filed April 25, 2012, each titled "Electrochromic Window Fabrication Methods" each of which is hereby incorporated by reference in its entirety. One of ordinary skill in the art would appreciate that if one were to carry out methods described herein on a bulk glass

sheet and then cut individual lites therefrom, in certain embodiments masks may have to be used, whereas when performed on a lite of desired end size, masks are optional.

[0076] Exemplary electromagnetic radiation includes UV, lasers, and the like. For example, material may be removed with directed and focused energy one of the wavelengths 248 nm, 355 nm (UV), 1030 nm (IR, e.g. disk laser), 1064 nm (e.g. Nd:YAG laser), and 532 nm (e.g. green laser). Laser irradiation is delivered to the substrate using, e.g. optical fiber or open beam path. The ablation can be performed from either the substrate side or the EC film side depending on the choice of the substrate handling equipment and configuration parameters. The energy density required to ablate the film thickness is achieved by passing the laser beam through an optical lens. The lens focuses the laser beam to the desired shape and size. In one embodiment, a "top hat" beam configuration is used, e.g., having a focus area of between about 0.005 mm<sup>2</sup> to about 2 mm<sup>2</sup>. In one embodiment, the focusing level of the beam is used to achieve the required energy density to ablate the EC film stack. In one embodiment, the energy density used in the ablation is between about 2 J/cm<sup>2</sup> and about 6 J/cm<sup>2</sup>.

[0077] During a laser edge delete process, a laser spot is scanned over the surface of the EC device, along the periphery. In one embodiment, the laser spot is scanned using a scanning F theta lens. Homogeneous removal of the EC film is achieved, e.g., by overlapping the spots' area during scanning. In one embodiment, the overlap is between about 5% and about 100%, in another embodiment between about 10% and about 90%, in yet another embodiment between about 10% and about 80%. Various scanning patterns may be used, e.g., scanning in straight lines, curved lines, and various patterns may be scanned, e.g., rectangular or other shaped sections are scanned which, collectively, create the peripheral edge deletion area. In one embodiment the scanning lines (or "pens," i.e. lines created by adjacent or overlapping laser spots, e.g. square, round, etc.) are overlapped at the levels described above for spot overlap. That is, the area of the ablated material defined by the path of the line previously scanned is overlapped with later scan lines so that there is overlap. That is, a pattern area ablated by overlapping or adjacent laser spots is overlapped with the area of a subsequent ablation pattern. For embodiments where overlapping is used, spots, lines or patterns, a higher frequency laser, e.g. in the range of between about 11 KHz and about 500 KHz, may be used. In order to minimize heat related damage to the EC device at the exposed edge (a heat affected zone or "HAZ"), shorter pulse duration lasers are used. In one example, the pulse duration is between about 100 fs (femtosecond) and about 100 ns (nanosecond), in another embodiment the pulse duration is between about 1 ps (picosecond) and about 50 ns,

in yet another embodiment the pulse duration is between about 20 ps and about 30 ns. Pulse duration of other ranges can be used in other embodiments.

[0078] Referring again to **Figures 4A** and **4B**, process flow **400** continues with removing a second width, **B**, narrower than the first width **A**, about substantially the entire perimeter of the substrate, see **415**. This may include removing material down to the glass or to a diffusion barrier, if present. After process flow **400** is complete up to **415**, e.g. on a rectangular substrate as depicted in **Figure 4B**, there is a perimeter area, with width **B**, where there is none of the first transparent conductor, the one or more material layers of the device, or the second conducting layer -removing width **B** has exposed diffusion barrier or substrate. Within this perimeter area is the device stack, including the first transparent conductor surrounded on three sides by overlapping one or more material layers and the second conductor layer. On the remaining side (e.g., the bottom side in **Figure 4B**) there is no overlapping portion of the one or more material layers and the second conductor layer. It is proximate this remaining side (e.g., bottom side in **Figure 4B**) that the one or more material layers and the second conductor layer are removed in order to expose a portion (bus bar pad expose, or "BPE"), **435**, of the first conductor layer, see **420**. The BPE **435** need not run the entire length of that side, it need only be long enough to accommodate the bus bar and leave some space between the bus bar and the second conductor layer so as not to short on the second conductor layer. In one embodiment, the BPE **435** spans the length of the first conductor layer on that side.

[0079] As described above, in various embodiments, a BPE is where a portion of the material layers are removed down to the lower electrode or other conductive layer (e.g. a transparent conducting oxide layer), in order to create a surface for a bus bar to be applied and thus make electrical contact with the electrode. The bus bar applied can be a soldered bus bar, and ink bus bar and the like. A BPE typically has a rectangular area, but this is not necessary; the BPE may be any geometrical shape or an irregular shape. For example, depending upon the need, a BPE may be circular, triangular, oval, trapezoidal, and other polygonal shapes. The shape may be dependent on the configuration of the EC device, the substrate bearing the EC device (e.g. an irregular shaped window), or even, e.g., a more efficient (e.g. in material removal, time, etc.) laser ablation pattern used to create it. In one embodiment, the BPE spans at least about 50% of the length of one side of an EC device. In one embodiment, the BPE spans at least about 80% of the length of one side of an EC device. Typically, but not necessarily, the BPE is wide enough to accommodate the bus bar, but should allow for some

space at least between the active EC device stack and the bus bar. In one embodiment, the BPE is substantially rectangular, the length approximating one side of the EC device and the width is between about 5 mm and about 15 mm, in another embodiment between about 5 mm and about 10 mm, and in yet another embodiment between about 7 mm and about 9 mm. As mentioned, a bus bar may be between about 1 mm and about 5 mm wide, typically about 3 mm wide.

[0080] As mentioned, the BPE is fabricated wide enough to accommodate the bus bar's width and also leave space between the bus bar and the EC device (as the bus bar is only supposed to touch the lower conductive layer). The bus bar width may exceed that of the BPE (and thus there is bus bar material touching both the lower conductor and glass (and/or diffusion barrier) on area **140**), as long as there is space between the bus bar and the EC device (in embodiments where there is an L3 isolation scribe, the bus bar may contact the deactivated portion, e.g. see **145** in **Figure 1A**). In embodiments where the bus bar width is fully accommodated by the BPE, that is, the bus bar is entirely atop the lower conductor, the outer edge, along the length, of the bus bar may be aligned with the outer edge of the BPE, or inset by about 1 mm to about 3 mm. Likewise, the space between the bus bar and the EC device is between about 1 mm and about 3 mm, in another embodiment between about 1 mm and 2 mm, and in another embodiment about 1.5 mm. Formation of BPEs is described in more detail below, with respect to an EC device having a lower electrode that is a TCO. This is for convenience only, the electrode could be any suitable electrode for an optical device, transparent or not.

[0081] To make a BPE, an area of the bottom TCO (e.g. first TCO) is cleared of deposited material so that a bus bar can be fabricated on the TCO. In one embodiment, this is achieved by laser processing which selectively removes the deposited film layers while leaving the bottom TCO exposed in a defined area at a defined location. In one embodiment, the absorption characteristics of the bottom electrode and the deposited layers are exploited in order to achieve selectivity during laser ablation, that is, so that the EC materials on the TCO are selectively removed while leaving the TCO material intact. In certain embodiments, an upper portion (depth) of the TCO layer is also removed in order to ensure good electrical contact of the bus bar, e.g., by removing any mixture of TCO and EC materials that might have occurred during deposition. In certain embodiments, when the BPE edges are laser machined so as to minimize damage at these edges, the need for an L3 isolation scribe line to

limit leakage currents can be avoided - this eliminates a process step, while achieving the desired device performance results.

[0082] In certain embodiments, the electromagnetic radiation used to fabricate a BPE is the same as described above for performing edge deletion. The (laser) radiation is delivered to the substrate using either optical fiber or the open beam path. The ablation can be performed from either glass side or the film side depending on the choice of the electromagnetic radiation wavelength. The energy density required to ablate the film thickness is achieved by passing the laser beam through an optical lens. The lens focuses the laser beam to the desired shape and size, e.g. a "top hat" having the dimensions described above, in one embodiment, having an energy density of between about 0.5 J/cm<sup>2</sup> and about 4 J/cm<sup>2</sup>. In one embodiment, laser scan overlapping for BPE is done as described above for laser edge deletion. In certain embodiments, variable depth ablation is used for BPE fabrication. This is described in more detail below.

[0083] In certain embodiments, e.g. due to the selective nature of the absorption in an EC film, the laser processing at the focal plane results in some amount (between about 10 nm and about 100 nm) of residue, e.g. tungsten oxide, remaining on the exposed area of the lower conductor. Since many EC materials are not as conductive as the underlying conductor layer, the bus bar fabricated on this residue does not make full contact with the underlying conductor, resulting in voltage drop across the bus bar to lower conductor interface. The voltage drop impacts coloration of the device as well as impacts the adhesion of the bus bar to the lower conductor. One way to overcome this problem is to increase the amount of energy used for film removal, however, this approach results in forming a trench at the spot overlap, unacceptably depleting the lower conductor. To overcome this problem the laser ablation *above the focal plane* is performed, i.e. the laser beam is defocused. In one embodiment, the defocusing profile of the laser beam is a modified top hat, or "quasi top hat." By using a defocused laser profile, the fluence delivered to the surface can be increased without damaging the underlying TCO at spot overlap region. This method minimizes the amount of residue left in on the exposed lower conductor layer and thus allows for better contact of the bus bar to the lower conductor layer.

[0084] Referring again to **Figures 4A** and **4B**, after forming the BPE, bus bars are applied to the device, one on exposed area **435** of the first conductor layer (e.g., first TCO) and one on the opposite side of the device, on the second conductor layer (e.g., second TCO), on a portion of the second conductor layer that is not above the first conductor layer, see **425**.



This placement of the bus bar 1 on the second conductor layer avoids coloration under the bus bar (analogous to bus bar 1 in **Figures 2A** or **3**) and the other associated issues with having a functional device under this bus bar. In this example, there are no laser isolation scribes necessary in fabrication of the device - this is a radical departure from conventional fabrication methods, where one or more isolation scribes leave non-functional device portions remaining in the final construct.

[0085] **Figures 4B** indicates cross-section cuts **Z-Z'** and **W-W** of device **440**. The cross-sectional views of device **440** at **Z-Z'** and **W-W** are shown in **Figure 4C**. The depicted layers and dimensions are not to scale, but are meant to represent functionally the configuration. In this example, the diffusion barrier was removed when width **A** and width **B** were fabricated. Specifically, perimeter area **140** is free of first conductor layer and diffusion barrier; although in one embodiment the diffusion barrier is left intact to the edge of the substrate about the perimeter on one or more sides. In another embodiment, the diffusion barrier is co-extensive with the one or more material layers and the second conductor layer (thus width **A** is fabricated at a depth to the diffusion barrier, and width **B** is fabricated to a depth sufficient to remove the diffusion barrier). In this example, there is an overlapping portion, **445**, of the one or more material layers about three sides of the functional device. On one of these overlapping portions, on the second TCO, bus bar 1 is fabricated. In one embodiment, a vapor barrier layer is fabricated co-extensive with the second conductor layer. A vapor barrier is typically highly transparent, e.g. aluminum zinc oxide, a tin oxide, silicon dioxide and mixtures thereof, amorphous, crystalline or mixed amorphous-crystalline. In this embodiment, a portion of the vapor barrier is removed in order to expose the second conductor layer for bus bar 1. This exposed portion is analogous to area **435**, the BPE for bus bar 2. In certain embodiments, the vapor barrier layer is also electrically conductive, and exposure of the second conductor layer need not be performed, i.e. the bus bar may be fabricated on the vapor barrier layer. For example, the vapor barrier layer may be ITO, e.g. amorphous ITO, and thus be sufficiently electrically conductive for this purpose. The amorphous morphology of the vapor barrier may provide greater hermeticity than a crystalline morphology.

[0086] **Figure 4C** depicts the device layers overlying the first TCO, particularly the overlapping portion, **445**. Although not to scale, cross section **Z-Z'** for example, depicts the conformal nature of the layers of the EC stack and the second TCO following the shape and contour of the first TCO including the overlapping portion **445**. Cross section **Z-Z'** is

reproduced in **Figure 7** and modified for illustrative purposes to show detail of a problem sometimes encountered with such overlapping configurations. Referring to **Figure 7**, the transition to overlap **445**, where the upper device layers overlay the edge of the first TCO, e.g. depending upon the device materials and thickness of the layers, may form fissures, **700**, as depicted in the expanded portion (left). It is believed that these fissures are due to the stress related to the upper device layers having to follow an abrupt transition over the edge of the first TCO (in this example). Fissures **700** may form along the edges of the device where the overlying layers cover such abrupt edges. These fissures may cause electrical shorting, as there is an exposed path between the first and second TCO's, and ions may short the device as the ion conducting layer (or functional equivalent) is breached at the fissure. These shorts cause coloration aberrations and poor performance of the electrochromic device.

Embodiments herein overcome this problem by tapering (sloping or otherwise modifying) the lower device layers about at least a portion of their edge, particularly the lower transparent conducting layer, so that the overlying layers will not encounter such stresses. This is referred to herein as "edge tapering." Although edge tapering is described in certain embodiments, other stress mitigation topology may be used such as edge rounding, stepping, and beveling. Also, combinations of stress mitigation topology may be used.

[0087] Referring to **Figure 8A**, the edge portion, **800**, of the first TCO (diffusion barrier not depicted) is tapered, for example, by laser ablation. Thus **800** is an example of an edge taper. The tapered topography in this example is formed by a defocused laser (*supra*) so that smooth contours are formed rather than abrupt edges. In this example, the taper is a stepped contour, but this is not necessary. In a typical, but non-limiting example, a first TCO might be between about 0.25  $\mu\text{m}$  and about 1  $\mu\text{m}$  thick. The edge portion **800** having the tapered profile may be between about 0.25  $\mu\text{m}$  and about 1000  $\mu\text{m}$  wide, in another embodiment between about 0.5  $\mu\text{m}$  and about 100  $\mu\text{m}$  wide, in another embodiment between about 1  $\mu\text{m}$  and about 10  $\mu\text{m}$  wide. As described in relation to **Figures 4A and 4B**, the edge taper may be formed in the lower conductor layer before or after polishing of the lower conductor.

[0088] Referring again to **Figure 8A** and also **Figure 8B**, after device fabrication (as indicated by the downward pointing arrow) a resulting electrochromic device as described above has overlapping portions of the one or more material layers and the top conductor layer around three sides. The portion, **805**, of the upper layers overlaps edge portion **800**. Because of the sloped nature of edge portion **800**, it is believed the overlying device layers in portion **805** no longer experience the stress levels otherwise encountered when an abrupt edge

portion is below them. Portion **805** gradually transitions to portion **810** which lies on the glass substrate (or the diffusion barrier, not shown, portion **810** is analogous to portion **445** in **Figure 4C**). In this example, the edge taper **800** is fabricated on three sides of the first TCO in accord with fabrication methods described herein, though, it can be done along any  
5 fraction of the perimeter of the TCO remaining after edge deletion (including the edge portion of the TCO along the substrate edge, i.e. that not removed by edge deletion). In one embodiment, edge taper is performed only about the perimeter edge of the TCO formed by edge deletion. In one embodiment, edge taper is performed only along that portion of the perimeter edge of the TCO formed by edge deletion and opposite side of the device as the  
10 BPE.

[0089] Although **Figure 8A** depicts the lower conductor layer as tapered, this need not be the case. Edge tapering can be done, e.g., after one or more other layers have been deposited on the lower conductor layer so long as the overall result is lowering of stress of subsequently deposited layers. One embodiment is an electrochromic device with one or more layers  
15 below the uppermost layer having an edge taper on at least some portion of their perimeter edge. One embodiment is an electrochromic device with one or more layers below the uppermost layer having a stress mitigation topology on at least some portion of their perimeter edge. The stress mitigation topology may include edge taper, edge rounding, stepping and/or beveling.

[0090] One embodiment is a method of fabricating an optical device, the method including tapering one or more edges of an underlying material layer prior to fabrication of overlapping layers thereon. In one embodiment, the underlying material layer is the lower conductor layer. In one embodiment, tapering one or more edges of the lower conductor layer includes laser ablation. In one embodiment the laser is defocused so as to create smooth contours in  
20 the tapered edge portion. In one embodiment, the lower conductor layer is polished before the edge taper. In one embodiment, the lower conductor layer is polished after the edge taper.

[0091] As described, one or more laser isolation scribes may be needed, depending upon design tolerances, material choice and the like. **Figure 4G** depicts top-views of three  
30 devices, **440a**, **440b** and **440c**, each of which are variations on device **440** as depicted in **Figures 4B** and **4C**. Device **440a** is similar to device **440**, but includes L2 scribes (see above) that isolate first portions of the EC device along the sides orthogonal to the sides with the bus bars. Device **440b** is similar to device **440**, but includes an L3 scribe isolating and

deactivating a second portion of the device between the bus bar on the first (lower) conductor layer and the active region of the device. Device **440c** is similar to device **440**, but includes both the L2 scribes and the L3 scribe. Although the scribe line variations in **Figure 4G** are described in reference to devices **440a**, **440b** and **440c**, these variations can be used for any of the optical devices and lites of embodiments described herein. For example, one embodiment is a device analogous to device **440c**, but where the edge deletion does not span three sides, but rather only the side bearing the bus bar on the top TCO (or a portion long enough to accommodate the bus bar). In this embodiment, since there are no edge deletion portions on the two sides orthogonal to the bus bars (the right and left side of **440c** as depicted), the L2 scribes may be closer to these edges in order to maximize viewable area. Depending upon device materials, process conditions, aberrant defects found after fabrication, etc., one or more of these scribes may be added to ensure proper electrical isolation of the electrodes and therefore device function. Any of these devices may have a vapor barrier applied prior to, or after, one or all of these scribes. If applied after, the vapor barrier is not substantially electrically conductive; otherwise it would short out the device's electrodes when filling the laser scribe trenches. The above-described edge tapering may obviate the need for such scribes.

[0092] Referring again back to **Figure 7**, the right side of **Figure 7** includes a detailed portion of the cross section Z-Z' illustrating a problem sometimes encountered with BPE formation. Specifically, during laser ablation of the bus bar pad expose area, upon which bus bar 2 resides in this figure, the laser may not ablate away the top layers or ablate the lower conductor layer (first TCO in this instance) uniformly. Thus, there may be problematic issues with proper electrical connectivity between the bus bar and the lower conductor layer in areas **705**. These issues are described in more detail with reference to **Figures 9A** and **9B**.

[0093] Referring to **Figure 9A**, a cross section of an electrochromic device, **900**, having a top transparent conductor layer **905**, a device stack, **910**, and a lower transparent conductor layer, **915**. On a BPE of lower conductor layer **915**, is a bus bar, **920**, e.g., a silver ink bus bar. In the lower portion of **Figure 9A**, in detail, is shown a problem with the BPE portion of layer **915**. Depending upon the device materials, laser settings, device state, etc., the BPE may not be of uniform thickness. In this example, the laser ablation was uneven, leaving areas, **930**, where conductor layer **915** was completely removed, and areas, **925**, where layer **915** remains. Areas **930** prevent electrical conduction to the device stack due to cutting off electrical connectivity in the lower TCO. Areas **930** typically span some portion of the BPE,

if not all, and thus can be a problem. **Figure 9B** shows another problem that may occur. If the laser does not ablate deeply enough, in this example through the device stack, then there may be poor electrical connectivity between lower conductor **915** and bus bar **920**. In this example, there is electrical connectivity between bus bar **920** and conductor layer **915** in area **935**, where the device stack was penetrated by the laser during BPE, but a large area portion of the device stack remains between bus bar **920** and conductor layer **915** at area **940**. So, as illustrated in **Figure 9A**, the laser may ablate too deeply, and as illustrated in **Figure 9B**, the laser may not ablate sufficiently over the entire area of the BPE. This can happen, e.g., due to film absorption drift during laser ablation, both intra-device and inter-device. Methods described herein overcome these issues by applying varying laser ablation levels, e.g., along individual scribe lines during BPE fabrication. This is described in more detail in relation to **Figures 10A-F**.

[0094] **Figure 10A** depicts a cross sectional portion of an electrochromic device, **1000**. The lower TCO is ablated in areas **1005** along one side to form a BPE, **435**. In this example, each of three areas **1005** is ablated with a defocused laser such that the cross section is concave as depicted. In this example, each of the scribe lines is made at the same laser fluence level. Also, no overlap of the laser ablations was used, so that there are raised regions (in this case ridges) of the TCO material remaining between adjacent ablation lines. This is one example of using laser ablation of an overlying material down to an underlying conductor layer using varying laser ablation levels along a plurality of individual scribes. There are essentially three "knobs" for achieving variable ablation depth: pulse duration, fluence level and overlap of laser spot and/or pattern (line, shape formed by positioning of individual spots). In certain embodiments 100% overlap is used, e.g., multiple shots on a single spot location or multiple lines across the same area. Embodiments herein for achieving varying ablation depth use any one of these or any combination thereof.

[0095] One embodiment is a method of fabricating a BPE, the method comprising laser ablation of overlying material down to an underlying TCO layer using varying laser ablation levels along a plurality of individual scribe lines during fabrication of the BPE. In one embodiment, each of the individual scribe lines, of the plurality of scribe lines, is scribed using a quasi top hat at the same fluence level. Other patterns, besides lines, may be used so long as there is varying ablation depth. For example, a laser spot may be applied in a checkerboard pattern, with or without overlap of adjacent spots, where individual spots apply different pulse times to achieve varying ablation depth. In certain embodiments, at least two

individual scribe lines, of the plurality of scribe lines, are scribed using a different fluence level for each line. Such embodiments are described in more detail below.

[0096] **Figure 10B** depicts a cross sectional portion of an electrochromic device, **1010**, of an embodiment. The electrochromic device, **1010**, has a BPE **435** formed via laser ablation of the lower TCO using varying ablation depth along a plurality of laser ablation lines **1015**, **1020** and **1025**, along one edge of the device. In this example, the lines are formed by overlapping laser spots along each line, but where each line uses a different overlap percentage of the individual spots. In this example, there is also overlap of the lines; however in some embodiments there is no overlap between one or more lines. **Figure 10C** shows a top view of BPE **435** (any device described herein may have a BPE as described in relation to **Figures 10A-F**) that is made from three lines **1015**, **1020** and **1025**. These lines each are of varying depth of ablation into the TCO relative to the other lines, but have substantially the same depth of ablation within any given line. By using varying ablation depth, e.g. using different fluence level of the laser spot, overlap in the spots or lines, pulse duration, and combinations thereof, the BPE has multiple depth profiles and accounts for problems associated with variation in film absorption during laser ablation. That is, if the laser doesn't ablate deeply enough, or ablates too deeply, there is still a sufficient amount of exposed TCO in order to make good electrical contact with the bus bar along the device edge and thus good performance and coloration front during operation of the device. In this example, the TCO is ablated progressively more deeply as the laser is moved from each line to the next, so that the BPE is progressively thinner at the outer edge and thicker at the innermost surface near the device stack. The BPE depicted in **Figure 10B** shows gently sloped transitions between lines indicating that laser ablation paths were overlapping partially. The final BPE is a three-stepped construct as depicted. By using varying ablation depth, good electrical contact between the bus bar and the BPE is ensured because even if there is absorption variation, there will be complete penetration to the lower TCO by at least one of the ablation lines.

[0097] In one embodiment, laser ablation is used to remove material from at least two lines along the edge of the EC device, along each line at a different ablation depth. In one embodiment, the ablation depth is selected from at least the upper 10% of the lower TCO, at least the upper 25% of the lower TCO, at least the upper 50% of the lower TCO, and at least the upper 75% of the lower TCO.

[0098] **Figure 10D** depicts a cross sectional portion of an electrochromic device, **1030**, of an embodiment. Referring to **Figure 10D**, even if the materials above the bottom TCO vary in

absorption from the calculated value, e.g. the laser ablation does not dig as deeply into the stack as calculated due to loss of absorption for some reason, since there are multiple lines at different depths, the BPE process is successful, i.e. good electrical connectivity with bus bar **920** is achieved. In the example depicted in **Figure 10D**, the laser didn't ablate as deeply as calculated, e.g. line **1015** has some EC stack material remaining which would interfere with electrical contact between the BPE and a bus bar. But, lines **1020** and **1025** did penetrate down to the TCO and thus bus bar **920** makes good electrical contact with the lower TCO. **Figure 10E** depicts a cross sectional portion of an electrochromic device, **1040**, of an embodiment. **Figure 10E** depicts the scenario where the laser penetrates more deeply than calculated, e.g. when the absorption of the material layers drifts to a more increased state than expected. In this example, line **1025** has insufficient TCO thickness to conduct electricity properly, but the remaining lines, **1015** and **1020**, allow for good electrical connection with bus bar **920**.

[0099] **Figure 10F** depicts a cross sectional portion of an electrochromic device, **1050**, of an embodiment. **Figure 10F** illustrates that the varying depth of the laser lines need not be from less depth to more depth as one moves from inner portion of BPE to outer portion of BPE. In this example, the laser ablation depth is configured such that the BPE is thicker furthest from the EC device and thinnest closest to the device edge. This pattern may have advantage when, e.g., it is desirable to make absolutely sure there is no stack material between where the bus bar is fabricated on the BPE and the device stack. By penetrating more deeply into the TCO on the line (**1015**) proximate the EC device, this is achieved. In one embodiment, the laser is configured to progressively remove more of the underlying conductor layer in each of the plurality of scribe lines, the ablation area of each scribe line is overlapped at least partially with the ablation area of the previous scribe line, and plurality of scribe lines are fabricated with most removal of underlying conductor layer nearest to the device stack and least removal of underlying conductive layer furthest from the device stack. In one embodiment, the laser is configured to progressively remove more of the underlying conductor layer in each of the plurality of scribe lines, the ablation area of said at least two scribe lines is overlapped at least partially with the ablation area, and plurality of scribe lines are fabricated with least removal of underlying conductor layer nearest to the device stack and most removal of underlying conductive layer furthest from the device stack.

[0100] Although the varying fluence and/or overlap and/or pulse duration of laser ablation spots, lines or patterns in order to vary the ablation depth is described in reference to BPE

fabrication, it can also be used to create the edge taper as described herein. Nor are these methods limited to those embodiments, e.g., they can also be used to create isolation trenches, e.g., where two or more lines are ablated at different depths to ensure proper electrical (and optionally ionic) isolation of one section of an EC device from another. In one  
5 embodiment, an L3 scribe is fabricated where two or more scribe lines are used to fabricate the L3 scribe and at least two scribe lines each have a different ablation depth, with or without overlap of the lines.

[0101] The above described fabrication methods are described in terms of rectangular optical devices, e.g. rectangular EC devices. This is not necessary, as they also apply to other  
10 shapes, regular or irregular. Also, the arrangement of overlapping device layers as well as BPE and other features may be along one or more sides of the device, depending upon the need. In order to more fully describe the scope of the embodiments, these features are described in more detail below with respect to other shapes and configurations. As described in relation to **Figures 4A** and **4B**, the fabrications described below may also include other  
15 features such as polish of the lower transparent conductor layer, edge taper, multi-depth ablated BPE, etc. Description of these features was not given so as to avoid repetition, but one embodiment is any of the device configurations described below with one or more of the features described in relation to **Figures 4A** and **4B**.

[0102] **Figure 4D** is a top view schematic drawing depicting fabrication steps analogous to  
20 that described in relation to the rectangular substrate in **Figure 4B**, but on a round substrate, according to an embodiment. The substrate could also be oval. Thus as described previously, a first width **A** is removed, see **405**. The one or more material layers and second conductor layer (and optionally a vapor barrier) are applied over the substrate, see **410**. A second width **B** is removed from the entire perimeter of the substrate, see **415 (140a** is  
25 analogous to **140)**. A BPE, **435a**, is fabricated as described herein, see **420**. Bus bars are applied, see **425**, to make device **440d** (thus, for example, in accord with methods described above, the at least one second bus bar is applied to the second conducting layer proximate the side of the optical device opposite the at least one exposed portion of the first conducting layer).

[0103] **Figure 4E** is a top view schematic depicting fabrication analogous to that described in  
30 relation to the rectangular substrate in **Figure 4B**, but for angled bus bar application of an embodiment. Thus as described previously, a first width **A** is removed, see **405**, in this example from two orthogonal sides (one or both of the resulting edges of the lower TCO may



have edge taper). The one or more material layers and second conductor layer (and optionally a vapor barrier) are applied over the substrate, see **410**. A second width B is removed from the entire perimeter of the substrate, see **415**. A BPE, **435b**, is fabricated as described herein; see **420**, in this example along orthogonal sides opposite those from which width A was removed. Bus bars are applied, see **425**, to make device **440e** (thus, for example, in accord with methods described above, the at least one second bus bar is applied to the second conducting layer proximate the side of the optical device opposite the at least one exposed portion of the first conducting layer). Angled bus bars are described in U.S. Patent Application, serial number 13/452,032, filed April 20, 2012, and titled "Angled Bus Bar," which is hereby incorporated by reference in its entirety. Angled bus bars have the advantages of decreasing switching speed and localized current "hot spots" in the device as well as more uniform transitions.

[0104] Whatever the shape of the device, it can be incorporated into an insulated glass unit. Preferably, the device is configured inside the IGU so as to protect it from moisture and the ambient. **Figure 4F** depicts IGU fabrication where the optical device, e.g. an electrochromic device is sealed within the IGU. IGU, **460**, including a first substantially transparent substrate, **445**, a spacer, **450**, and a second substantially transparent substrate, **455**. Substrate **445** has an electrochromic device fabricated thereon (bus bars are shown as dark vertical lines on substrate **445**). When the three components are combined, where spacer **450** is sandwiched in between and registered with substrates **445** and **455**, IGU **460** is formed. The IGU has an associated interior space defined by the faces of the substrates in contact with adhesive sealant between the substrates and the interior surfaces of the spacer, in order to hermetically seal the interior region and thus protect the interior from moisture and the ambient. This is commonly referred to as the primary seal of an IGU. A secondary seal includes an adhesive sealant applied around the spacer and between the panes of glass (the spacer has smaller length and width than the substrates so as to leave some space between the glass substrates from the outer edge to the spacer; this space is filled with sealant to form the secondary seal). In certain embodiments, any exposed areas of the first conducting layer are configured to be within the primary seal of the IGU. In one embodiment, any bus bars are also configured to be within the primary seal of the IGU. In one embodiment, the area of the second conductor layer that is not over the first conductor layer is also configured to be within the primary seal of the IGU. Conventional electrochromic IGU's configure the bus bars either outside the spacer (in the secondary seal) or inside the spacer (in the interior volume of the IGU) in the viewable area of the IGU (sometimes one in the secondary seal,

the other in the viewable area). Conventional electrochromic IGU's also configure the EC device edges either running to the substrate edge or inside the spacer (within the interior volume of the IGU). The inventors have found it advantageous to configure the bus bars, laser scribes, and the like to be under the spacer, so as to keep them from the viewable area and, e.g., to free up the secondary seal so that electrical components therein do not interfere with the aforementioned features. Such IGU configurations are described in U.S. Patent Application, serial number 13/456,056, titled "Electrochromic Window Fabrication Methods," filed April 25, 2012, which is hereby incorporated by reference in its entirety. Controllers that fit into the secondary seal are described in U.S. Patent number 8,213,074, titled "Onboard Controllers for Multistate Windows," filed March 16, 2011, which is hereby incorporated by reference in its entirety. Methods described herein include sealing any exposed areas of the first conductor layer, edges of the device or overlapping regions of the one or more material layers, and the second conductor layer in the primary seal of the IGU. With or without a vapor barrier layer, such as silicon oxide, silicon aluminum oxide, silicon oxynitride, and the like, this sealing protocol provides superior moisture resistance to protect the electrochromic device while maximizing viewable area.

[0105] In certain embodiments, the fabrication methods described herein are performed using large-area float glass substrates, where a plurality of EC lites are fabricated on a single monolithic substrate and then the substrate is cut into individual EC lites. Similar, "coat then cut" methods are described in U.S. Patent number 8,164,818, filed November 8, 2010, and titled, "Electrochromic Window Fabrication Methods," which is hereby incorporated by reference in its entirety. In some embodiments, these fabrication principles are applied to the methods described herein, e.g., in relation to **Figures 4A - 4G**.

[0106] **Figures 4H and 4I** depict an EC lite fabrication process flow, similar to that described in relation to **Figure 4A**, but carried out on a large-area substrate as applied to coat then cut methods, according to embodiments. These fabrication methods can be used to make EC lites of varying shapes, e.g., as described herein, but in this example, rectangular EC lites are described. In this example, substrate **430** (e.g. as described in relation to **Figure 4A**, coated with a transparent conducting oxide layer) is a large-area substrate, such as float glass, e.g. a sheet of glass that is 5 feet by 10 feet. Analogous to operation **405** as described in relation to **Figure 4A**, edge deletion at a first width, **A**, is performed. Edge taper and/or polish may also be performed. In this example, since there are to be a plurality of EC devices (in this example, 12 devices) fabricated on a large substrate, the first width **A** may have one or more

components. In this example, there are two components,  $A_1$  and  $A_2$ , to width  $A$ . First, there is a width  $A_1$ , along the vertical (as depicted) edges of the substrate. Since there are neighboring EC devices, the width  $A_1$  is reflected in a coating removal that is twice the width  $A_1$ . In other words, when the individual devices are cut from the bulk sheet, the cuts in  
5 between neighboring devices along the vertical (as depicted) dimension will evenly bi-furcate the area where the coating is removed. Thus "edge deletion" in these areas accounts for where glass edges will eventually exist after the glass is cut (see for example Figure 4I).  
Second, along the horizontal dimension, a second  $A$ -width component,  $A_2$ , is used. Note, in certain embodiments width  $A_1$  is used about the entire perimeter of the substrate; however, in  
10 this example more width is provided to accommodate the bus bar that will be fabricated on the top transparent conductor layer (e.g. see **Figure 4C**, bus bar 1). In this example, width  $A_2$  is the same both at the top and bottom edge of the substrate and between neighboring EC devices. This is because the fabrication is analogous to that described in relation to **Figure 4B**, i.e., where the EC devices are cut from the substrate along the bottom edge of the  
15 transparent conductor area for each device (see **Figure 4G**).

[0107] Next, in operation **410**, the remaining layers of the EC device are deposited over the entire substrate surface (save any areas where clamps might hold the glass in a carrier, for example). The substrate may be cleaned prior to operation **410**, e.g., to remove contaminants from the edge deletion. Also edge taper on each of the TCO areas may be performed. The  
20 remaining layers of the EC device encapsulate the isolated regions of the transparent conductor on the substrate, because they surround these areas of transparent conductor (except for the back face which resides against the substrate or intervening ion barrier layer). In one embodiment, operation **410** is performed in a controlled-atmosphere all PVD process, where the substrate doesn't leave the coating apparatus or break vacuum until all the layers  
25 are deposited.

[0108] In operation **415**, edge deletion at a second width,  $B$ , narrower than the first width  $A$ , is performed. In this example, second width  $B$  is uniform. In between neighboring devices, second width  $B$  is doubled to account for cutting the substrate along lines evenly between two devices so that the final devices have a uniform edge deletion about them for the spacer to seal  
30 to the glass when an IGU is fabricated from each EC device. As illustrated in **Figure 4H**, this second edge deletion isolates individual EC lites on the substrate. In certain embodiments, the second width  $B$  may be much smaller than that needed to accommodate a spacer for IGU fabrication. That is, the EC lite may be laminated to another substrate and

thus only a small edge delete at width **B**, or in some embodiments no edge delete at the second width **B** is necessary.

[0109] Referring to **Figure 41**, operation **420** includes fabricating a BPE, **435**, where a portion of the EC device layers are removed to expose the lower conductor layer proximate the substrate. In this example, that portion is removed along the bottom (as depicted) edge of each EC device. Next, during operation **425**, bus bars are added to each device. In certain embodiments, the EC lites are excised from the substrate prior to bus bar application. The substrate now has completed EC devices. Next, the substrate is cut, operation **470**, to produce a plurality of EC lites **440**, in this example 12 lites. This is a radical departure from conventional coat then cut methods, where here, fully functional EC devices can be fabricated, including bus bars on a large area format glass sheet. In certain embodiments the individual EC lites are tested and optionally any defects mitigated prior to cutting the large format sheet.

[0110] Coat and then cut methods allow for high throughput manufacture because a plurality of EC devices can be fabricated on a single large area substrate, as well as tested and defect-mitigated prior to cutting the large format glass sheet into individual lites. In one embodiment, the large format glass pane is laminated with individual strengthening panes registered with each EC device prior to cutting the large format sheet. The bus bars may or may not be attached prior to lamination; for example, the mate lite may be coextensive with an area allowing some exposed portions of the top and bottom TCO's for subsequent bus bar attachment. In another example, the mate lite is a thin flexible material, such as a thin flexible glass described below, which is substantially co-extensive with the EC device or the entire large format sheet. The thin flexible mate lite is ablated (and lamination adhesive, if present in these areas) down to the first and second conductor layers so that bus bars may be attached to them as described herein. In yet another embodiment, the thin flexible mate lite, whether co-extensive with the entire large format sheet or the individual EC devices, is configured with apertures which are registered with the top conductor layer and the BPE during lamination. The bus bars are attached either before or after lamination with the mate lite, as the apertures allow for either operation sequence. The lamination and bus bar attachment may separately be performed prior to cutting the large sheet, or after.

[0111] In certain embodiments, when laminating, bus bar ink may be applied prior to lamination, where the ink is applied to the BPE and upper TCO, then pressed out from between these areas when laminated, e.g. to an aperture in the mate lite or continuing around

the edge of the laminate, to allow lead attach at a point located outside the laminated area. In another embodiment, a flat foil tape is applied to the top conductor and the BPE, the foil tape extends beyond the laminated region, such that wires can be soldered to the tape after lamination. In these embodiments, cutting must precede lamination unless, e.g., the lamination mate lites do not cover the entire surface of the large format substrate (e.g. as described in relation to roll-to-roll embodiments herein).

[0112] Lites **440**, laminated or not, may be incorporated into an IGU, e.g. as depicted in **Figure 4F**. In one embodiment, the individual EC lites are incorporated into an IGU and then one or more of the EC lites of the IGU is laminated with a strengthening pane (mate lite) as described herein or in U.S. Patent number 8,164,818. In other embodiments, e.g. as described herein, lamination may include a flexible substrate, e.g. the aforementioned lamination of an IGU where the mate lite is a flexible substrate, or e.g., lamination of the EC lite directly to a flexible substrate. Further such embodiments are described in relation to **Figure 4J**.

[0113] **Figure 4J** depicts roll-to-roll processing, **475**, forming laminates of electrochromic devices where the lamination uses a flexible mate lite. A substrate, **476**, is fed into a lamination line, in this example including a conveyer **477**. Substrate **476** may be an IGU with at least one EC lite incorporated, or substrate **476** can be a monolithic EC device, e.g., as described herein or substrate **476** can be a large format substrate with a plurality of EC lites fabricated thereon. In this example, a thin and flexible substrate, **478**, in this case a glass substrate is fed from a roll into the lamination line. In one embodiment one or more rolls are applied in parallel to a large format glass sheet including a plurality of EC devices, e.g., as described in relation to **Figure 4I**. For example, three separate and parallel rolls of the flexible substrate are fed into a lamination line that laminates the large format glass substrate lengthwise or widthwise such that three columns or rows of EC devices (see **Figure 4I**, upper portion) are each laminated with the flexible substrate. Thus using roll-to-roll processing, large format glass sheets can be laminated with flexible mate lite material and cut into individual EC lites. The large format glass sheet may be cut as each row is laminated or after the entire sheet is laminated. In certain embodiments, individual EC lites, or IGU's containing them, are laminated with roll-to-roll processing. More detail of roll-to-roll processing is described below.

[0114] Exemplary flexible substrates include thin and durable glass materials, such as Gorilla® Glass (e.g. between about 0.5 mm and about 2.0 mm thick) and Willow™ Glass,

commercially available from Corning, Incorporated of Corning New York. In one embodiment, the flexible substrate is less than 0.3 mm thick, in another embodiment the flexible substrate is less 0.2 mm thick, and in another embodiment the flexible substrate is about 0.1 mm thick. Such substrates can be used in roll-to-roll processing. Referring again to **Figure 4J**, adhesive is applied to substrate **476**, flexible substrate **478**, or both. Rollers **479** apply sufficient pressure to ensure good bonding between substrate **476** and flexible substrate **478**. Flexible substrate **478** is cut to match its lamination partner **476**, e.g., using a laser **480**. The final laminate structure, **481**, results. Using this roll-to-roll method, monolithic EC devices, IGU's or large format glass sheets bearing a plurality of EC lites can be strengthened with a thin flexible strengthening pane. These methods apply to any EC substrate, described herein or otherwise. In one embodiment, the monolithic EC lites as depicted in **Figure 41**, e.g. having been cut from the large area substrate, are fed into the lamination line to be laminated with the flexible substrate. In another embodiment, the large area substrate, having a plurality of EC devices fabricated thereon, is laminated with a flexible substrate of corresponding width, and after lamination, the individual, now laminated, EC devices are cut from the large area laminate, e.g., by row as lamination finishes or after lamination of the entire large format sheet. In another embodiment, the large area substrate, having a plurality of EC devices fabricated thereon, is laminated with a plurality of flexible substrates of corresponding width or length to individual EC lites, and after lamination, the EC devices, now laminated, are cut from the large area laminate, e.g. individually, or by row (or column).

[0115] As described, e.g. in relation to **Figure 4A-E**, EC devices may have two bus bars, one for each transparent conducting layer. However, methods herein also include fabrication of devices having more than one bus bar for each transparent conducting layer, specifically bus bars on opposing sides of each of the first and second conductor layer. This may be particularly important when fabricating larger EC devices that would otherwise require longer switching times due to the sheet resistance and having large-area devices.

[0116] **Figure 5A** describes aspects of a process flow, **500**, for fabricating an optical device have opposing bus bars on each of the first and second conductor layers, according to embodiments. For illustration, **Figure 5B** includes top views depicting the process flow described in relation to **Figure 5A** as it relates to fabrication of a rectangular electrochromic device. **Figure 5C** shows cross-sections of the electrochromic lite described in relation to **Figure 5B**.

[0117] Referring to **Figures 5A** and **5B**, process flow **500** begins with removing the first width **A** of the first conducting layer from two opposing sides at the perimeter of the substrate, see **505**. As described above, this may include removal of a diffusion barrier or not. A substrate with a first conductor layer, **530**, is depicted. After step **505**, two opposing edge portions of the substrate (or diffusion barrier) are exposed. Edge taper and polish steps may be performed as described in relation to **Figures 4A** and **4B**. The one or more material layers of the device and the second conductor layer (and optionally a moisture barrier) are applied to the substrate, see **510**. A second width **B** is removed from the entire perimeter of the substrate, see **515**. In this example, two BPE's, **435**, are fabricated, see **520**. Thus in accord with methods described above, the at least one exposed portion of the first conducting layer includes a pair of exposed portions fabricated along the lengths of the opposing sides of the optical device from which the first width was not removed in **505**. Bus bars are applied, see **525**, to make device **540** (thus, for example, in accord with methods described above, applying the at least one second bus bar to the second conducting layer includes applying a pair of second bus bars, each of the pair of second bus bars on opposing lengths of the second conducting layer and over areas where the first conducting layer was removed in **505**). **Figure 5B** indicates cross-sections **C-C** and **D-D'** of device **540**. Drawings of the cross-sectional views of device **540** at **C-C** and **D-D'** are shown in more detail in **Figure 5C**.

[0118] **Figure 5C** shows cross-sections **C-C** and **D-D'** of device **540**. In this example, the diffusion barrier was removed when width **A** and width **B** were removed. Specifically, perimeter area **140** is free of first conductor layer and diffusion barrier; although in one embodiment the diffusion barrier is left intact to the edge of the substrate about the perimeter on one or more sides. In another embodiment, the diffusion barrier is co-extensive with the one or more material layers and the second conductor layer (thus width **A** is fabricated at a depth to the diffusion barrier, and width **B** is fabricated to a depth sufficient to remove the diffusion barrier). In this example, there is an overlapping portion, **545**, of the one or more material layers only on opposing sides of the functional device. On both of these overlapping portions, on the second TCO, bus bars 1 are fabricated. In one embodiment, a vapor barrier layer is fabricated co-extensive with the second conductor layer. In this embodiment, two portions of the vapor barrier are removed in order to expose the second conductor layer for bus bars 1. These exposed portions are analogous to areas **435**, the BPEs for bus bars 2.

[0119] **Figure 5D** depicts an electrochromic device, **540a**, analogous to rectangular device **540**. Bus bars **550** are on the first conductor layer and bus bars **555** are on the second

conductor layer. Thus, the BPEs **435** are fabricated on opposing sides of the circular area and analogous opposing bus bars are applied to the second conductor layer.

**[0120]** **Figure 5E** depicts an electrochromic device, **540b**, in this example a triangular shaped device. In this example, area **140b** is analogous to areas **140** and **140a** in previously described devices. Device **540b** has one angled bus bar, **570**, and one linear bus bar, **580**. In this example, angled bus bar **570** is on the region, **565**, of the second conductor layer that is not over the first conductor layer, and linear bus bar **580** is on the BPE, **435**. Triangular optical devices are not limited to this particular configuration, e.g., the BPE could be along two orthogonal sides and have the angled bus bar, and the linear bus bar could be on the second conductor layer. The point is that methods described herein can be used to fabricate optical devices of virtually any shape. Also, various masking steps may be used to fabricate devices as described herein, although masking adds extra steps. Other embodiments include optical devices.

**[0121]** One embodiment is an optical device including: (i) a first conductor layer on a substrate, the first conductor layer including an area less than that of the substrate, the first conductor layer surrounded by a perimeter area of the substrate which is substantially free of the first conductor layer; (ii) one or more material layers including at least one optically switchable material, the one or more material layers configured to be within the perimeter area of the substrate and co-extensive with the first conductor layer but for at least one exposed area of the first conductor layer, the at least one exposed area of the first conductor layer free of the one or more material layers; and (iii) a second conductor layer on the one or more material layers, the second conductor layer transparent and co-extensive with the one or more material layers, where the one or more material layers and the second conductor layer overhang the first conductor layer but for the at least one exposed area of the first conductor layer. In one embodiment, the optical device further includes a vapor barrier layer coextensive with the second conductor layer. There may be a diffusion barrier between the substrate and the first conductor layer. The perimeter area of the substrate can include the ion diffusion barrier. In one embodiment, the at least one optically switchable material is an electrochromic material. In one embodiment, the substrate and the first conductor layer are also transparent. In one embodiment, the at least one exposed area of the first conductor layer includes a strip proximate the perimeter area of the substrate. The device may include a first bus bar on and within the area of the strip. The device may also include a second bus bar on the second conductor layer, the second bus bar configured to be on or disposed on a



portion of the second conducting layer that does not cover the first conducting layer, the portion proximate the perimeter area and opposite the first bus bar. In one embodiment, the first and second conductor layers and the one or more material layers are all solid-state and inorganic. In one embodiment, the substrate is float glass, tempered or untempered, and the first conducting layer includes tin oxide, e.g. fluorinated tin oxide. In one embodiment, the substrate is registered with a second substrate in an IGU. In one embodiment, any otherwise exposed areas of the first conducting layer are configured to be within the primary seal of the IGU, the bus bars may also be configured to be within the primary seal of the IGU as well as the area of the second conductor layer that is not over the first conductor layer. The optical device may be rectangular, round, oval, triangular and the like.

[0122] In certain embodiments, opposing bus bars on each conductor layer are used. In one embodiment, the at least one exposed area of the first conductor layer includes a pair of strips, each strip of the pair of strips on opposing sides of the first conductor layer proximate the perimeter area of the transparent substrate. Depending upon the shape of the device, the strips may be linear or curved, for example. The strips can include a first pair of bus bars, each of the first pair of bus bars on and within the area of each strip of the pair of strips. A second pair of bus bars on the second conductor layer can be included, each of the second pair of bus bars configured to be on or disposed on each of two portions of the second conducting layer that do not cover the first conducting layer, each of the two portions proximate the perimeter area and on opposing sides of the second conducting layer.

[0123] The first and second conductor layers and the one or more material layers of optical devices described herein may be all solid-state and inorganic. In one embodiment, the substrate is float glass, tempered or untempered, and the first conducting layer includes tin oxide, e.g. fluorinated tin oxide. The substrate may be registered in an IGU with an additional EC device or not. As described, the bus bars, any laser scribes, device edges, and/or exposed portions of the first conductor layer may be sealed in the primary seal of the IGU. Dual EC device IGU's are described in US Patent Application, serial number 12/851,514 (now U.S. Patent No. 8,270,059), filed August 5, 2010, and titled "Multi-pane Electrochromic Windows," which is hereby incorporated by reference in its entirety. One embodiment is a multi-pane window as described in that application, having one or more EC devices as described herein. One embodiment is any optical device described herein which does not include a laser isolation scribe. One embodiment is any optical device described herein which does not include an inactive portion of the optical device.

[0124] As described above in relation to **Figures 4H** and **4I**, some embodiments include coat then cut fabrication. **Figures 5F** and **5G** depict a process flow similar to that described in relation to **Figure 5A** and carried out on a large-area substrate as applied to coat then cut methods of disclosed embodiments. This is an example of fabricating EC devices having two  
5 opposing bus bars on each transparent conducting layer. The lamination embodiments described above also apply to the coat then cut embodiments described below.

[0125] Referring to **Figure 5F**, a large area substrate, **530**, has a transparent conducting layer thereon (as indicated by the dotted pattern). During operation **505**, an edge delete is performed at a first width **A**. The edge delete between what will be neighboring EC devices  
10 is made to be double of **A**, so that each EC device has an equivalent edge delete width **A**. In operation **510**, the remaining EC device layers are applied. Next, see **515**, the edge delete at width **B**, narrower than width **A**, is performed. In this example, the isolated EC device precursors are analogous to those described in **Figure 5B** after operation **515**.

[0126] Referring to **Figure 5G**, operation **520** creates bus bar pad expose regions **435**, in this  
15 example, two for each EC device. Operation **525** includes application of bus bars, two for each of the transparent conductor layers. In operation **570**, the large area substrate is cut to produce, in this example, 12 EC devices **540**. As described above in relation to **Figures 4H-J**, these may be incorporated into IGUs, or laminated directly, for example, using a thin flexible substrate.

[0127] As described above, thin flexible substrates may be used as strengthening panes (mate  
20 lites) for EC lites, e.g. EC lites fabricated as described herein. In certain embodiments, thin flexible substrates are used as *substrates* for the EC lite fabrication process. For example, one embodiment includes any of the EC device fabrication methods described herein performed on a thin flexible substrate as described herein, e.g. Gorilla<sup>®</sup> Glass or Willow<sup>™</sup>  
25 Glass. In some embodiments, fabrication is performed using a roll-to-roll fabrication scheme. Examples of this embodiment are described below in relation to **Figures 6A** and **6B**.

[0128] **Figure 6A** depicts roll-to-roll fabrication, **600**, of electrochromic devices on thin  
30 flexible substrates and optional lamination with rigid substrates. **Figure 6A** is a fusion of a chart-type process flow with block diagrams including functional descriptions of apparatus and device features. The actual apparatus for performing the described fabrication may be in any orientation, but in one embodiment, the flexible substrate is preferably vertical. In

another embodiment, the substrate is vertical and the process operations are performed in a "top down" format, where the substrate is fed into the line from a first height, passes downward through the fabrication process, and ends at a second height, lower than the first height. In this example, a thin flexible substrate, **478a** (as described above), includes a transparent conductive oxide layer. An example of this substrate is Willow Glass™, which is commercially available with an ITO coating from Corning, Incorporated of Corning, New York. The heavy dotted arrow in Figure 6A indicates the direction of motion of the flexible substrate through various modules.

[0129] First, the flexible substrate is fed into an edge deletion module, **605**. In this module, the edge deletion of a first width (as described herein) from the transparent conductor layer is performed. The substrate may optionally be cleaned (not depicted in **Figure 6A**) of any contaminants resulting from the first edge delete. Also, in accord with embodiments described herein, e.g. in relation to **Figures 4A** and **4B**, the transparent conducting layer may be given an edge taper and/or polishing process (not depicted). Next, the thin flexible substrate enters a coater, **610**, where the remaining layers of the EC device are deposited, in this example, using a vacuum integrated all-PVD sputter apparatus. Such apparatus are described in US Patent number 8,243,357, titled, "Fabrication of Low Defectivity Electrochromic Devices," filed on May 11, 2011, which is hereby incorporated by reference in its entirety. After the flexible substrate is coated with the EC device, a second edge delete (as described herein) is carried out, in this example, in a module **615**. Edge deletion may optionally be followed by edge taper (not shown). Next is BPE fabrication, **620**, followed by application of bus bars, see **625**. Optionally, the flexible substrate may be laminated with a mate lite, see **630**, e.g. as described in relation to **Figure 4J**. The mate lite may be flexible as the substrate, or a rigid substrate, such as annealed glass or a polymeric substrate. In this example, the flexible substrate is laminated with annealed glass. The flexible substrate is then cut, either to match the rigid substrate to which it is laminated (as depicted) which produces laminated EC devices **640**, or as a monolithic flexible EC device (not shown). In the latter embodiment, the flexible EC device may be coated with a vapor barrier and/or encapsulation layer prior to or after cutting from the bulk material.

[0130] Depending upon the width of the flexible substrate, there may be one or more EC devices fabricated along the width of the flexible substrate as it passes through modules/process flows **605-635**. For example, if the flexible substrate is as wide as a large area float glass substrate as described herein, lamination with the large area substrate will

produce a corresponding large-area laminate. Individual EC lite laminates can be cut from that large area laminate, e.g. as described above.

[0131] In some embodiments, a flexible EC device laminate is desired. In one embodiment, the flexible substrate bearing the plurality of EC devices is itself laminated with another flexible substrate. **Figure 6B** depicts fabrication, **650**, of electrochromic devices on flexible glass substrates and subsequent lamination with flexible substrates. In this example, flexible substrate **478a** (as described above) having a transparent conductor layer thereon is fed through fabrication line processes **605 - 625** as described in relation to **Figure 6A**. Then, the flexible substrate, having a plurality of EC devices thereon, is laminated with another flexible substrate, in this example substrate **478** as described above, via appropriate application of lamination adhesive and rollers **630**. The newly formed laminate is cut, e.g. via laser, see **635**, to form individual flexible EC laminates. **665**, which, e.g., can pass along conveyer **477** for further processing. As described above, the flexible substrate "mate lite" may be patterned with apertures to accommodate the bus bars, or ablated to reveal TCO and the bus bars (process **625**) added after lamination, either before or after cutting into individual laminated EC lites.

[0132] Although the foregoing embodiments have been described in some detail to facilitate understanding, the described embodiments are to be considered illustrative and not limiting. It will be apparent to one of ordinary skill in the art that certain changes and modifications can be practiced within the scope of the above description and the appended claims.

## CLAIMS

*We claim:*

1. A method of fabricating an optical device comprising one or more material layers sandwiched between a first and a second conducting layer, the method comprising:
  - 5 (i) receiving a substrate comprising the first conducting layer over its work surface;
  - (ii) removing a first width of the first conducting layer from between about 10% and about 90% of the perimeter of the substrate;
  - 10 (iii) depositing said one or more material layers of the optical device and the second conducting layer such that they cover the first conducting layer and, where possible, extend beyond the first conducting layer about its perimeter;
  - (iv) removing a second width, narrower than the first width, of all the layers about substantially the entire perimeter of the substrate, wherein the depth  
15 of removal is at least sufficient to remove the first conducting layer;
  - (v) removing at least one portion of the second transparent conducting layer and the one or more layers of the optical device thereunder, thereby revealing at least one exposed portion of the first conducting layer; and
  - 20 (vi) applying a bus bar to said at least one exposed portion of the first transparent conducting layer,wherein at least one of the first and second conducting layers is transparent.
2. The method of claim 1, wherein (ii) comprises removing the first width of the first conducting layer from between about 50% and about 75% around the perimeter of the substrate.
- 25 3. The method of claim 2, wherein said at least one exposed portion of the first conducting layer exposed is fabricated along the perimeter portion of the optical device proximate the side or sides of the substrate where the first conducting layer was not removed in (ii).
4. The method of claim 3, further comprising applying at least one second bus bar to the  
30 second conducting layer.

5. The method of claim 4, wherein said at least one second bus bar is applied to the second conducting layer on a portion that does not cover the first conducting layer.
6. The method of claim 5, further comprising fabricating at least one L2 scribe line to isolate a portion of the optical device orthogonal the bus bar.
- 5 7. The method of claim 5, further comprising fabricating an L3 scribe line to isolate a portion of the optical device between the bus bar and an active region of the optical device.
8. The method of claim 5, further comprising:  
fabricating at least one L2 scribe line to isolate a portion of the optical device  
10 orthogonal the bus bar; and  
fabricating an L3 scribe line to isolate a portion of the optical device between the bus bar and an active region of the optical device.
9. The method of claim 4, wherein the depth of removal sufficient to remove at least the first conducting layer in (iv) is sufficient to remove the diffusion barrier, and wherein  
15 said at least one second bus bar is applied to the second conducting layer on a portion that does not cover the first conducting layer or the diffusion barrier.
10. The method of claim 9, further comprising fabricating at least one L2 scribe line to isolate a portion of the optical device orthogonal the bus bar.
11. The method of claim 9, further comprising fabricating an L3 scribe line to isolate a  
20 portion of the optical device between the bus bar and an active region of the optical device.
12. The method of claim 9, further comprising:  
fabricating at least one L2 scribe line to isolate a portion of the optical device  
orthogonal to the bus bar; and  
25 fabricating an L3 scribe line to isolate a portion of the optical device between the bus bar and an active region of the optical device.
13. The method of claim 12, wherein the optical device is an electrochromic device.
14. The method of claim 13, wherein the electrochromic device is all solid-state and inorganic.

15. The method of claim 14, wherein the substrate is float glass and the first conducting layer comprises fluorinated tin oxide.
16. The method of claim 8, wherein (iii) is performed in an all vacuum integrated deposition apparatus.
- 5 17. The method of claim 8, further comprising depositing a vapor barrier layer on the second conducting layer prior to (iv).
18. The method of claim 8, wherein both the first and second conducting layers are transparent.
19. The method of claim 18, wherein the substrate is transparent.
- 10 20. The method of claim 12, wherein the substrate is rectangular.
21. The method of claim 20, wherein (ii) comprises removing the first width of the first conducting layer from three sides about the perimeter of the substrate.
22. The method of claim 21, wherein said at least one exposed portion of the first conducting layer is fabricated along the length of one side of the optical device.
- 15 23. The method of claim 22, wherein said at least one exposed portion of the first conducting layer is fabricated along the length of the side of the optical device proximate the side of the substrate where the first conducting layer was not removed in (ii).
24. The method of claim 23, wherein said at least one second bus bar is applied to the  
20 second conducting layer proximate the side of the optical device opposite said at least one exposed portion of the first conducting layer.
25. The method of claim 24, wherein the optical device is an electrochromic device.
26. The method of claim 25, wherein the electrochromic device is all solid-state and inorganic.
- 25 27. The method of claim 26, wherein the substrate is float glass, tempered or untempered, and the first conducting layer comprises fluorinated tin oxide.

28. The method of claim 27, wherein (iii) is performed in an all vacuum integrated deposition apparatus.
29. The method of claim 28, further comprising depositing a vapor barrier layer on the second conducting layer prior to (iv).
- 5 30. The method of claim 12, wherein (ii) comprises removing the first width of the first conducting layer from two opposing sides at the perimeter of the substrate.
31. The method of claim 30, wherein said at least one exposed portion of the first conducting layer comprises a pair of exposed portions fabricated along the lengths of the opposing sides of the optical device from which the first width was not removed  
10 in (ii).
32. The method of claim 31, wherein (vi) comprises applying a bus bar to each of said pair of exposed portions of the first conducting layer.
33. The method of claim 32, wherein applying said at least one second bus bar to the second conducting layer comprises applying a pair of second bus bars, each of said  
15 pair of second bus bars on opposing lengths of the second conducting layer and over areas where the first conducting layer was removed in (ii).
34. The method of claim 33, wherein the optical device is an electrochromic device.
35. The method of claim 34, wherein the electrochromic device is all solid-state and inorganic.
- 20 36. The method of claim 35, wherein the substrate is float glass, tempered or untempered, and the first conducting layer comprises fluorinated tin oxide.
37. The method of claim 36, wherein (iii) is performed in an all vacuum integrated deposition apparatus.
38. The method of claim 37, further comprising depositing a vapor barrier layer on the  
25 second conducting layer prior to (iv).
39. The method of claim 12, wherein the substrate is circular or oval.
40. The method of claim 39, wherein the substrate is glass.



41. The method of claim 40, wherein said at least one second bus bar is applied to the second conducting layer proximate the side of the optical device opposite said at least one exposed portion of the first conducting layer.
42. The method of claim 41, wherein the optical device is an electrochromic device.
- 5 43. The method of claim 42, wherein the electrochromic device is all solid-state and inorganic.
44. The method of claim 43, wherein the substrate is float glass, tempered or untempered, and the first conducting layer comprises fluorinated tin oxide.
45. The method of claim 44, wherein (iii) is performed in an all vacuum integrated  
10 deposition apparatus.
46. The method of claim 45, further comprising depositing a vapor barrier layer on the second conducting layer prior to (iv).
47. The method of claim 39, wherein (ii) comprises removing the first width of the first conducting layer from two opposing portions about the perimeter of the substrate.
- 15 48. The method of claim 47, wherein said at least one exposed portion of the first conducting layer comprises a pair of exposed portions fabricated along the perimeter of the substrate on the portions of the optical device between the two opposing portions from which the first width was removed in (ii).
49. The method of claim 48, wherein (vi) comprises applying a bus bar to each of said  
20 pair of exposed portions of the first conducting layer.
50. The method of claim 49, wherein applying said at least one second bus bar to the second conducting layer comprises applying a pair of opposing second bus bars, each bus bar in one of the areas of the second conducting layer proximate the perimeter of the substrate between the pair of exposed portions of the first conducting layer.
- 25 51. The method of claim 50, wherein the optical device is an electrochromic device.
52. The method of claim 51, wherein the electrochromic device is all solid-state and inorganic.

53. The method of claim 52, wherein the substrate is float glass, tempered or untempered, and the first conducting layer comprises fluorinated tin oxide.
54. The method of claim 53, wherein (iii) is performed in an all vacuum integrated deposition apparatus.
- 5 55. The method of claim 54, further comprising depositing a vapor barrier layer on the second conducting layer prior to (iv).
56. The method of any one of claims 13, 25, 34, 42 and 51, further comprising fabricating an IGU from the electrochromic device.
57. The method of claim 56, wherein any remaining exposed areas of the first conducting  
10 layer are configured to be within the primary seal of the IGU.
58. The method of claim 57, wherein all bus bars are also configured to be within the primary seal of the IGU.
59. The method of claim 56, further including laminating the IGU with a flexible glass material.
- 15 60. The method of claim 59, wherein the flexible glass material is Gorilla® Glass or Willow™ Glass.
61. The method of claim 43, wherein the substrate is a flexible glass, about 0.5 mm or less in thickness, and the first conducting layer comprises tin oxide, optionally with indium and/or fluoride.
- 20 62. The method of claim 61, wherein (iii) is performed in an all vacuum integrated deposition apparatus.
63. The method of claim 62, further comprising depositing a vapor barrier layer on the second conducting layer prior to (iv).
64. The method of claim 61, wherein the flexible glass is Gorilla® Glass or Willow™  
25 Glass.
65. The method of claim 62, wherein the flexible glass is Willow™ Glass.

66. The method of claim 65, further comprising laminating the EC device with either a rigid glass substrate or a flexible substrate.
67. The method of claim 66, wherein the flexible substrate is Gorilla® Glass or Willow™ Glass.
- 5 68. The method of any one of claims 1 - 67, wherein the substrate is a large area substrate and a plurality of the EC devices is fabricated thereon, followed by cutting the large area substrate to form the individual EC devices from the plurality of the EC devices.
69. The method of claim 68, wherein lamination is carried out on the large area format substrate prior to cutting.
- 10 70. An optical device comprising:
- (i) a first conductor layer on a substrate, the first conductor layer comprising an area less than that of the substrate, the first conductor layer surrounded by a perimeter area of the substrate which is substantially free of the first conductor layer;
  - 15 (ii) one or more material layers comprising at least one optically switchable material, said one or more material layers configured to be within the perimeter area of the substrate and co-extensive with the first conductor layer but for at least one exposed area of the first conductor layer, said at least one exposed area of the first conductor layer free of said one or more material layers; and
  - 20 (iii) a second conductor layer on said one or more material layers, said second conductor layer being transparent and being co-extensive with the one or more material layers,
- wherein the one or more material layers and the second conductor layer overhang the first conductor layer but for said at least one exposed area of the first conductor.
- 25 71. The optical device of claim 70, further comprising a vapor barrier layer coextensive with the second conductor layer.
72. The optical device of claim 70, further comprising an ion diffusion barrier between the substrate and the first conductor layer.

73. The optical device of claim 72, wherein the perimeter area of the substrate includes the ion diffusion barrier.
74. The optical device of claim 70, wherein said at least one optically switchable material is an electrochromic material.
- 5 75. The optical device of claim 74, wherein the substrate and the first conductor layer are also transparent.
76. The optical device of claim 75, wherein said at least one exposed area of the first conductor layer comprises a strip proximate the perimeter area of the substrate.
- 10 77. The optical device of claim 76, further including a first bus bar on and within the area of the strip.
78. The optical device of claim 77, further including a second bus bar on the second conductor layer, said second bus bar configured to be on a portion of the second conductor layer that does not cover the first conductor layer, said portion proximate the perimeter area and opposite the first bus bar.
- 15 79. The optical device of claim 78, wherein the first and second conductor layers and the one or more material layers are all solid-state and inorganic.
80. The optical device of claim 79, wherein the substrate is float glass, tempered or untempered, and the first conductor layer comprises fluorinated tin oxide.
- 20 81. The optical device of claim 80, wherein the substrate is registered with a second substrate in an IGU.
82. The optical device of claim 81, wherein any exposed areas of the first conductor layer are configured to be within the primary seal of the IGU.
83. The optical device of claim 82, wherein all bus bars are also configured to be within the primary seal of the IGU.
- 25 84. The optical device of claim 83, wherein the area of the second conductor layer that is not over the first conductor layer is also configured to be within the primary seal of the IGU.

85. The optical device of claim 84, the optical device being rectangular.
86. The optical device of claim 84, the optical device being round or oval.
87. The optical device of claim 84, the optical device being triangular.
88. The optical device of claim 85, wherein said at least one exposed area of the first  
5 conductor layer comprises a pair of strips, each strip of the pair of strips on opposing  
sides of the first conductor layer proximate the perimeter area of the transparent  
substrate.
89. The optical device of claim 88, further including a first pair of bus bars, each of the  
first pair of bus bars on and within the area of each strip of the pair of strips.
- 10 90. The optical device of claim 89, further including a second pair of bus bars on the  
second conductor layer, each of said second pair of bus bars configured to be on each  
of two portions of the second conductor layer that do not cover the first conductor  
layer, each of said two portions proximate the perimeter area and on opposing sides of  
the second conductor layer.
- 15 91. The optical device of claim 90, wherein the first and second conductor layers and the  
one or more material layers are all solid-state and inorganic.
92. The optical device of claim 91, wherein the substrate is float glass, tempered or  
untempered, and the first conductor layer comprises fluorinated tin oxide.
93. The optical device of claim 92, wherein the substrate is registered with a second  
20 substrate in an IGU.
94. The optical device of claim 93, wherein any exposed areas of the first conductor layer  
are configured to be within the primary seal of the IGU.
95. The optical device of claim 94, wherein all bus bars are also configured to be within  
the primary seal of the IGU.
- 25 96. The optical device of claim 95, wherein the area of the second conductor layer that is  
not over the first conductor layer is also configured to be within the primary seal of  
the IGU.

97. The optical device of claim 96, the optical device being rectangular.

98. The optical device of claim 96, the optical device being round or oval.

99. The optical device of claim 96, the optical device being triangular.

5 100. The optical device of any one of claims 70 - 99, which does not comprise a laser isolation scribe.

101. The optical device of any one of claims 70 - 99, which does not comprise an inactive portion of the optical device.

102. The optical device of any one of claims 70-99, wherein the substrate is a flexible glass.

10 103. The optical device of claim 102, wherein the flexible glass is Gorilla® Glass or Willow™ Glass.

104. The optical device of claim 103, wherein the IGU is laminated to a flexible glass.

15 105. The optical device of claim 104, wherein the flexible glass is Gorilla® Glass or Willow™ Glass.

20 106. A large area substrate laminate comprising:  
a large area substrate comprising a plurality of all solid state and inorganic EC devices thereon; and  
a strengthening pane,  
wherein at least one of the large area substrate and the strengthening pane are a flexible glass that is 0.5 mm thick or less.

107. The large area substrate laminate of claim 106, wherein both the large area substrate and the strengthening pane are the flexible glass.

25 108. A method of fabricating an optical device, the method including tapering one or more edges of an underlying material layer prior to fabrication of overlapping layers thereon.

109. The method of claim 108, wherein the underlying material layer is the lower conductor layer and the optical device is an electrochromic device.
110. The method of claim 108, wherein tapering one or more edges of the lower conductor layer includes laser ablation.
- 5 111. The method of claim 110, wherein the laser is defocused so as to create smooth contours in the tapered edge portion.
112. An electrochromic device comprising a lower transparent conductor layer having one or more tapered edges.
- 10 113. The electrochromic device of claim 112, wherein the lower transparent conductor layer is between about 0.25  $\mu\text{m}$  and about 1  $\mu\text{m}$  thick.
114. The electrochromic device of claim 113, wherein the tapered portion of the one or more tapered edges is between about 0.25  $\mu\text{m}$  and about 1000  $\mu\text{m}$  wide.
115. A method of fabricating a bus bar pad expose, the method comprising laser ablation of overlying material down to an underlying conductor layer using varying laser ablation depths along a plurality of individual scribe lines during fabrication of the bus bar pad expose.
- 15 116. The method of claim 115, wherein each of the individual scribe lines, of the plurality of scribe lines, is scribed using a quasi top hat at the same fluence level.
117. The method of claim 115, wherein at least two individual scribe lines, of the plurality of scribe lines, is scribed using a different fluence level.
- 20 118. The method of claim 117, wherein the laser is configured to progressively remove more of the underlying conductor layer in each of the plurality of scribe lines, the ablation area of each scribe line is overlapped at least partially with the ablation area of the previous scribe line, and plurality of scribe lines are fabricated with least removal of underlying conductor layer nearest to the device stack and most removal of underlying conductive layer furthest from the device stack.
- 25 119. The method of claim 117, wherein the laser is configured to progressively remove more of the underlying conductor layer in each of the plurality of scribe lines,

the ablation area of said at least two scribe lines is overlapped at least partially with the ablation area, and plurality of scribe lines are fabricated with least removal of underlying conductor layer nearest to the device stack and most removal of underlying conductive layer furthest from the device stack.

- 5 120. The method of claim 117, wherein the laser is configured to progressively  
remove more of the underlying conductor layer in each of the plurality of scribe lines,  
the ablation area of each scribe line is overlapped at least partially with the ablation  
area of the previous scribe line, and plurality of scribe lines are fabricated with most  
removal of underlying conductor layer nearest to the device stack and least removal of  
10 underlying conductive layer furthest from the device stack.





Fig. 1A




Fig. 1B




Fig. 1C




Fig. 1D




Fig. 2A




Fig. 2B






Fig. 2C

6/30



*Fig. 2D*



*Fig. 2E*





Fig. 3



**Fig. 4A**



9/30







Fig. 4B




*Fig. 4C*

11/30




*Fig. 4D*

12/30




*Fig. 4E*



*Fig. 4F*

14/30



**Fig. 4G**

15/30





Fig. 4H



*Fig. 4I*







Fig. 4J



*Fig. 5A*

19/30




Fig. 5B








Fig. 5C




*Fig. 5D*



*Fig. 5E*



*Fig. 5F*



*Fig. 5G*




Fig. 6A









Fig. 6B



*Fig. 7*



*Fig. 8B*






Fig. 9A







Fig. 9B




*Fig. 10A*




*Fig. 10B*




*Fig. 10C*



*Fig. 10D*



*Fig. 10E*



*Fig. 10F*

## INTERNATIONAL SEARCH REPORT

International application No.  
**PCTYUS2012/068817****A. CLASSIFICATION OF SUBJECT MATTER****G02F 1/15(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

G02F 1/15; H01M 618; G02F 1/153; G03B 13/00; G02F 1/155; G02F 115; G09G 5/00; B05D 5/06

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) &amp; Keywords: electrochromic window, various edge deletion, laser scribe, thin film electrical conductor layers, tapering and similar terms

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y A	US 2011-0211247 A1 (MARK KOZLOWSKI et al.) 1 September 2011 See paragraphs [0089]-[0095] , [0106] , [0127H0132] ; and figures 6A, 6B, 7A.	115-120 71-73 ,100 1-67 ,70 ,74-99 ,101-114
X Y A	US 7777933 B2 (FABIENNE PIRoux et al.) 17 August 2010 See column 2, lines 48-59 ; column 4, lines 12-26 ; column 5, lines 35-48 ; column 6, line 1 - column 8, line 28 ; and figures 1-5.	70 ,74-99 ,101-107 71-73 ,100 1-67 ,108-120
X A	US 6822778 B2 (RAYMOND T. WESTFALL et al) 23 November 2004 See column 6, lines 9-33 ; and figures 1-4.	108-114 1-67 ,70-107 ,115-120
A	US 2011-0260961 A1 (MARK SAMUEL BURDIS) 27 October 2011 See paragraphs [0048]-[0064] ; and figures 4A-4C.	1-67 ,70-120
A	US 7719751 B2 (PETER EGERTON et al.) 18 May 2010 See column 2, line 10 - column 3, line 21 ; and figures 3A-3E.	1-67 ,70-120

 Further documents are listed in the continuation of Box C. See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

28 March 2013 (28.03.2013)

Date of mailing of the international search report

**29 March 2013 (29.03.2013)**

Name and mailing address of the ISA/KR

Korean Intellectual Property Office  
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan  
City, 302-70 1, Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

LEE, Dong Yun

Telephone No. 82-42-481-8734



INTERNATIONAL SEARCH REPORT

International application No.

PCT/US2012/068817

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

- 1.  Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
  
- 2.  Claims Nos.: 69  
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:  
  
Claim 69 refers to a multiple dependent claim that refers to another multiple dependent claim. Therefore, the meaning of the technical feature to which this refers is vague and unclear.
  
- 3.  Claims Nos.: 68  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

- 1.  As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
  
- 2.  As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
  
- 3.  As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
  
  
  
  
  
  
  
  
  
  
- 4.  No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

- Remark on Protest**
- The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
  - The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
  - No protest accompanied the payment of additional search fees.



## INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT /US2012/068817

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 201 1-021 1247 A 1	01.09.2011	CN 102388340 A	21.03.2012
		CN 102388341 A	21.03.2012
		EP 2414890 A2	08.02.2012
		EP 2414891 A2	08.02.2012
		US 2010-243427 A1	30.09.2010
		US 2010-245973 A1	30.09.2010
		W0 2010-120535 A2	21.10.2010
		W0 2010-120535 A3	10.02.2011
		wo 2010-120537 A2	21.10.2010
		wo 2010-120537 A3	10.02.2011
US 7//933 B2	17.08.2010	AT 474247 T	15.07.2010
		BR P10618600A2	06.09.2011
		CA 2630566 A1	24.05.2007
		CN 101310217 A	19.11.2008
		CN 101310217 B	20.04.2011
		DE 6020060 155 10 D1	26.08.2010
		EP 1952194 A1	06.08.2008
		EP 1952194 B1	14.07.2010
		FR 2893427 A1	18.05.2007
		FR 2893427 B1	04.01.2008
		JP 2009-516226 A	16.04.2009
		KR 10-2008-0070657 A	30.07.2008
		RU 200812382 1 A	27.12.2009
		RU 2420772 C2	10.06.2011
US 2009-006703 1 A1	12.03.2009		
wo 2007-057605 A1	24.05.2007		
US 6822778 B2	23.11.2004	us 2003-01377 12 A1	24.07.2003
		us 6515787 B1	04.02.2003
US 201 1-026096 1 A1	27.10.2011	us 8228587 B2	24.07.2012
		wo 201 1-133294 A1	27.10.2011
US 7719751 B2	18.05.2010	EP 2349939 A2	03.08.2011
		us 2010-0067090 A1	18.03.2010
		wo 2010-033485 A2	25.03.2010
		wo 2010-033485 A3	01.07.2010