



(86) Date de dépôt PCT/PCT Filing Date: 2007/07/19
(87) Date publication PCT/PCT Publication Date: 2008/01/24
(45) Date de délivrance/Issue Date: 2019/04/30
(85) Entrée phase nationale/National Entry: 2009/01/16
(86) N° demande PCT/PCT Application No.: US 2007/016343
(87) N° publication PCT/PCT Publication No.: 2008/011088
(30) Priorité/Priority: 2006/07/20 (US11/490,458)

(51) Cl.Int./Int.Cl. *A61K 8/34* (2006.01),
A61B 42/00 (2016.01), *A61L 27/54* (2006.01),
A61Q 19/00 (2006.01)

(72) Inventeurs/Inventors:
WANG, SHIPING, US;
CHEN, SEONG FONG, MY;
LOW, CHII YHI, MY;
WONG, WEI CHEONG, MY;
BERGER, IDA, US

(73) Propriétaire/Owner:
ALLEGIANCE CORPORATION, US

(74) Agent: GOWLING WLG (CANADA) LLP

(54) Titre : COMPOSITION DE REVETEMENT NON AQUEUSE POUR ARTICLES ELASTOMERES ET ARTICLES LES
CONTENANT

(54) Title: NONAQUEOUS COATING COMPOSITION FOR ELASTOMERIC ARTICLES AND ARTICLES CONTAINING
THE SAME

(57) **Abrégé/Abstract:**

The invention described herein relates to a therapeutic, moisturizing coating composition for elastomeric articles which is applied directly onto the skin-contacting surface of the article as part of the manufacturing process. The coating composition is thermally stable and subsequently transfers when in contact with a skin surface to convert into a liquid "lotion" form during wearing of the article. The coating composition provides therapeutic benefits to the wearer's skin as a result of wearing the article, such as improved skin moisturization, softness of feel, improved skin elasticity and firmness, and reduced redness and irritation. The invention is particularly useful in medical gloves, including examination and surgical gloves.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
24 January 2008 (24.01.2008)

PCT

(10) International Publication Number
WO 2008/011088 A3

(51) International Patent Classification:

A61L 31/08 (2006.01) A61B 19/04 (2006.01)

(21) International Application Number:

PCT/US2007/016343

(22) International Filing Date: 19 July 2007 (19.07.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

11/490,458 20 July 2006 (20.07.2006) US

(71) Applicant (for all designated States except US): **ALLEGIANCE CORPORATION** [US/US]; 1430 Waukegan Road, McGaw Park, IL 60085-6787 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **WANG, Shiping** [US/US]; 1508 Forever Avenue, Libertyville, IL 60048 (US). **CHEN, Seong, Fong** [MY/MY]; 11a Gerbang Minden, Gelugor Penang, 11700 (MY). **LOW, Chii, Yhi** [MY/MY]; EB2-2 Lorong Kenari, Sungai Ara, Bayan Lepas, Penang, 11800 (MY). **WONG, Wei, Cheong** [MY/MY]; 265 Taman Rambai, Jalan Rambai 1 Kulim, Kedah (MY). **BERGER, Ida** [US/US]; 199 Laen Court, Buffalo Grove, IL 60089 (US).

(74) Agent: **STELTER, Daniel, C.**; Allegiance Corporation, 1430 Waukegan Road, McGaw Park, IL 60085-6787 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- with information concerning one or more priority claims considered void

(88) Date of publication of the international search report:

12 June 2008

(54) Title: NONAQUEOUS COATING COMPOSITION FOR ELASTOMERIC ARTICLES AND ARTICLES CONTAINING THE SAME

(57) Abstract: The invention described herein relates to a therapeutic, moisturizing coating composition for elastomeric articles which is applied directly onto the skin-contacting surface of the article as part of the manufacturing process. The coating composition is thermally stable and subsequently transfers when in contact with a skin surface to convert into a liquid "lotion" form during wearing of the article. The coating composition provides therapeutic benefits to the wearer's skin as a result of wearing the article, such as improved skin moisturization, softness of feel, improved skin elasticity and firmness, and reduced redness and irritation. The invention is particularly useful in medical gloves, including examination and surgical gloves.



WO 2008/011088 A3

NONAQUEOUS COATING COMPOSITION FOR ELASTOMERIC ARTICLES AND ARTICLES CONTAINING THE SAME

5

BACKGROUND OF THE INVENTION

The invention relates to the field of medical devices. In particular, the invention relates to a nonaqueous coating composition for skin-contacting surfaces of elastomeric articles. Elastomeric articles, which are used in contact with the wearer's skin, are well known. Articles such as medical gloves and condoms, for example, can be worn by the user for extended periods of time. Because certain elastomeric articles are used with relatively higher frequency as well as with prolonged duration, important characteristics of such articles include their physical properties and their comfort of use.

A variety of medical gloves, e.g., surgical gloves and examination gloves, are well known and readily available in the medical field. The chemical and physical properties of elastomers used in such gloves have been researched, and gloves exhibiting desirable properties in accordance with their usage have been developed. Properties such as tensile strength and elongation modulus, as well as coatings and lubricants, which enhance their usage and/or donning characteristics, have been investigated. A variety of elastomeric polymer compositions have been examined as well, including formulations using natural and synthetic latex.

When gloves are worn for extended periods of time, body heat is generated by the hand and perspiration that can cause overhydration damaging the protection afforded by the stratum corneum. After the gloves are removed from the hand and the sweat evaporates, the skin of the hand can become dry, sensitive and sometimes, infected. Such undesirable skin conditions can lead to even more serious skin

problems as a result of the loss of epidermal lipid barrier layer, which preserves skin moisture.

Pre-donning skin lotions have been developed for application to the user's skin prior to donning gloves. Such lotions are typically applied separately to the skin, and the glove is then donned afterward. Other lotions are applied to the skin after the glove has been removed. Therapeutic skin-moisturizing gloves containing water-activatable material on a skin-contacting surface are described in Berry U.S. Patent No. 5,869,072. The water-activatable material disclosed in this reference includes polyvinyl alcohol, as well as additional ingredients such as moisturizers. Chou U.S. Patent No. 6,274,154 describes an elastomeric glove wherein the skin-contacting surface contains an aloe vera coating in the dry state. One problem associated with many lotions or creams is the deterioration of glove performance as a result of adverse effects on barrier and physical properties of the elastomer. Another problem associated with pre-coated gloves is their ability to withstand sterilization treatment and/or elevated thermal environments, encountered during the manufacturing process and storage. Yet another problem with such lotions or creams is the use of oily emollients, which can produce an uncomfortable greasy feeling.

Certain elastomeric articles, such as surgical gloves, are worn for extended periods of time during medical procedures. The comfort, maintenance of skin moisture, and reduction of skin irritation have become of increasing interest. One difficulty associated with developing elastomeric gloves which are both functional and comfortable to the user's skin has been the balancing of their desirable physical (e.g., tactile) attributes in combination with beneficial and therapeutic results for the user's skin. Even more difficult is the accomplishment of these physical and comfort

characteristics while at the same time also providing thermal stability and topical therapeutic benefit.

Accordingly, there is a need in the field of skin-contacting elastomeric articles for improvements in their comfort to the user. Particularly advantageous would be the development of an elastomeric glove which is pre-coated with a nonaqueous therapeutic skin care treating composition which is thermally stable.

SUMMARY OF THE INVENTION

The invention provides an elastomeric article comprising a therapeutic coating composition on the skin-contacting surface that can be applied to the article during its manufacture and subsequently afford a comfortable and therapeutic effect to the wearer's skin while maintaining the desirable physical properties of the article. A coating composition has been discovered which is compatible with medical gloves, is thermally stable, has no substantial adverse effect on its physical properties, has reduced irritation of the wearer's skin, has a non-sticky feel, has good surface-to-skin transference, and has reduced inter-surface and intra-surface tackiness between like elastomeric articles. Particularly surprising is it has been discovered that not only does the coating composition reduce the adverse effects of wearing elastomeric articles over time, but it improves the condition of the wearer's skin. Even more surprising is that such a formulation could be developed with a combination of ingredients that can "survive" the conditions of article (e.g., glove) manufacturing. Elastomeric articles with which the invention can be used include industrial gloves, medical gloves (i.e., examination and surgical gloves), condoms, and the like. The invention is particularly useful in examination and surgical gloves.

The invention provides a nonaqueous therapeutic coating applied to the skin-contacting surface of the elastomeric article, said coating composition comprising a moisturizing agent; and wherein said coating composition is applied directly onto said elastomeric article surface. The therapeutic nonaqueous coating composition transfers
5 onto the wearer's skin during use, providing the topical benefits afforded by the ingredients of the composition.

The nonaqueous coating composition continues to provide prolonged therapeutic benefit to the skin following its removal. The coating composition is chemically compatible with the elastomeric materials, and has no substantial impact
10 on the physical properties of the article. The coating composition of the invention is thermally stable and survives elevated temperatures associated with manufacturing and certain sterilization treatments. Additional ingredients can be combined with the composition of the invention, such as lubricants, anti-tacking agents, antimicrobial agents and time release or sustained release agents as well.

15 An important aspect of the coating composition of the invention is the collective skin moisturization efficacy of multiple coating composition ingredients. The therapeutic skin properties of the coating composition are accomplished in part by the discovery that some of the ingredients possess dual functionalities, wherein at least one of their functions is beneficial skin moisturization. The moisturizing
20 functionality of the coating composition is premised upon at least two of the following moisturization effects. First, some of the ingredients of the composition function as water-soluble (or perspiration-soluble) moisturizers, such as glycerin and sorbitol. Second, some of the ingredients function as skin penetrative moisturizers, such as panthenol. Third, some ingredients can function as prolonged skin surface
25 moisturizers, such as film-forming polymers such as chitosan. Furthermore,

combinations of the above can be employed to suit the nature of wear associated with different elastomeric article types. For example, since examination gloves are worn for relatively shorter time periods, the prolonged skin surface moisturizer(s) used can be optional.

5 The invention provides a nonaqueous coating composition for skin-contacting surfaces of elastomeric articles comprising at least one polyhydric alcohol moisturizer and at least one alphahydroxy lactone. Preferred polyhydric alcohol moisturizers are glycerol, sorbitol, and pantothenol. A preferred alphahydroxy lactone is gluconolactone.

10 The invention also provides an elastomeric article comprising a nonaqueous coating composition on the skin-contacting surface, the coating comprising at least one polyhydric alcohol moisturizer and at least one alphahydroxy lactone.

The term “transfer” is meant to refer to the means by which the nonaqueous coating composition of this invention is transmitted to the wearer’s skin. After donning the

15 glove, the coating is transferred to the wearer’s skin. The transfer or transmission of the coating to the skin is facilitated by the perspiration and body temperature of the wearer. Also, the action of the glove rubbing against the skin will also assist with the transference. The invention provides a process for making a skin-contacting elastomeric article providing enhanced therapeutic properties to the skin of the

20 wearer, the process comprising: applying a nonaqueous coating composition to the skin-contacting surface of the elastomeric article, the coating composition comprising at least one polyhydric alcohol moisturizer and at least one alphahydroxy lactone.

The process can be used in the manufacture of examination and surgical gloves.

The invention further provides a method of therapeutically treating the skin on the

25 hands of an individual in need of said treatment comprising the steps of: providing an

elastomeric glove comprising a nonaqueous coating composition comprising at least one polyhydric alcohol moisturizer and at least one alphahydroxy lactone; donning the glove on the hand; wearing the glove for a period of time sufficient to permit transfer of the coating composition onto the skin surface of the hand; and subsequently removing the glove from the hand. The therapeutic treatments include improved skin moisturization, reduced flaking, softness of feel, improved skin elasticity and firmness, reduced redness and irritation, and reduced appearance of wrinkles.

The invention also provides a nonaqueous coating composition for use in a solid state on the skin-contacting surface of an elastomeric article, said coating composition comprising: at least one water soluble, liquid carrier selected from the group consisting of polyhydric alcohols, glycols, alkoxylated alcohols, propylene glycol esters, fatty acid mono- and diglycerides, ethoxylated triglycerides, ethoxylated glycerol esters, polyoxyethylene diglycerol ethers, polyoxypropylene diglycerol ethers, polypropylene glycol ethers, and combinations thereof, at least one moisturizing agent; and wherein said composition is essentially water free and transfers upon contact with skin.

The invention further provides an elastomeric article having a nonaqueous coating composition in a solid state provided on the skin-contacting surface thereof, said coating composition comprising: at least one carrier selected from the group consisting of polyhydric alcohols, glycols, alkoxylated alcohols, propylene glycol esters, fatty acid mono- and diglycerides, ethoxylated triglycerides, ethoxylated glycerol esters, polyoxyethylene diglycerol ethers, polyoxypropylene diglycerol ethers, polypropylene glycol ethers, and combinations thereof, at least one moisturizing agent; and wherein said composition is essentially water free prior to application to the elastomeric article, and transfers upon contact with skin.

The invention further provides a nonaqueous therapeutic coating composition for use in a solid state on the skin-contacting surface of an elastomeric article, said coating composition comprising: glycerin in an amount of 50%-90% by weight of the composition; and sorbitol in an amount of at least 0.1% by weight of the composition; wherein said composition is essentially water free and transfers upon contact with skin.

The invention further provides an elastomeric article comprising a nonaqueous therapeutic coating composition in a solid state provided on the skin-contacting surface thereof, said coating composition comprising: glycerin in an amount of 50%-90% by weight of the composition; and sorbitol in an amount of at least 0.1% by weight of the composition; wherein said composition is essentially water free prior to application to the elastomeric article and transfers upon contact with skin.

The invention further provides a process for the production of an elastomeric article having a non-aqueous coating composition thereon, said process comprising: providing a non-aqueous coating composition comprising: at least one carrier selected from the group consisting of polyhydric alcohols, glycols, alkoxyated alcohols, fatty acid esters, propylene glycol esters, fatty acid mono- and diglycerides, ethoxylated triglycerides, ethoxylated glycerol esters, polyoxyethylene diglycerol ethers, polyoxypropylene diglycerol ethers, polypropylene glycol ethers, and combinations thereof, at least one moisturizing agent; heating said non-aqueous coating composition; contacting the skin-contacting surface of said elastomeric article with said heated non-aqueous coating composition to form a coated elastomeric article; and cooling the coated elastomeric article.

The invention further provides a process for the production of an elastomeric article having a nonaqueous coating composition thereon, said process comprising: heating a nonaqueous coating composition as defined above; contacting the skin-contacting surface of said elastomeric article with said heated nonaqueous coating composition to form a coated elastomeric article; and cooling the coated elastomeric article.

Additional embodiments and advantages of the invention will become apparent from the following description.

DETAILED DESCRIPTION OF THE INVENTION

The term “therapeutic” is meant to refer to the effect of improving skin-related properties of moisture, elasticity, comfort, non-irritation, preservation of protective skin barrier properties, and the like.

The term is used relative to “dry state” or “nonaqueous state”, which is used herein to indicate the substantial absence of moisture or water. As used herein, the term “thermally stable” and “thermal stability” when referring to the properties of the coating composition of the invention is meant to indicate that the coating composition can
5 withstand elevated temperatures of about 90° C. The nonaqueous coating composition according to the invention is adapted for application directly onto a skin-contacting surface of an elastomeric article as part of the manufacturing process. The processing temperature includes both the temperature at which the formulation is prepared and the temperature at which the formulation is applied to the glove. The processing temperature for coating
10 composition may range from about 20°C to about 100°C. The heating decreases the viscosity of the

formulation and assists with the ease of application to the skin-contacting side of the glove.

The coating composition of the invention is particularly suited for elastomeric articles which include, as part of their anticipated usage, intimate contact with a
5 wearer's skin surface and prolonged residence thereon. Suitable skin-contacting elastomeric articles include, but are not limited to, gloves (e.g., industrial, medical, and surgical gloves), condoms, finger cots, and the like. Elastomeric articles per se to be treated according to the invention can be manufactured using conventional techniques and equipment readily available to those skilled in the art. For example,
10 elastomeric gloves can be made using conventional former-dipping-curing techniques and equipment, such as that described in Yeh, U.S. Patent No. 6,391,409.

Elastomers or elastomeric substrates upon which the coating composition can be applied can include any natural or synthetic elastomeric polymer which is
15 chemically compatible with the coating composition ingredients and appropriate for the intended use, e.g., surgical environment. Suitable elastomers include, but are not limited to, synthetic and natural rubber latex. Natural rubber that can be used includes rubber made from *hevea* rubber latex and *guayule* rubber latex. Synthetic rubber polymers which can be used include nitrile rubber, polyurethane, polyisoprene,
20 polychloroprene, styrene block co-polymers and blends thereof. Synthetic rubbers that can be used also include acrylic diene block co-polymers, acrylic rubber, butyl rubber, EPDM rubber, polybutadiene, chlorosulfonated polyethylene rubber, and fluororubber.

One important characteristic of the invention is that the nonaqueous coating
25 composition can be applied directly onto the surface of the article as part of the

manufacturing process. The coating composition is packaged, stored, and presented in a solid state on the article surface. Thus, when in intimate contact with the skin surface the coating composition converts into a liquid "lotion" form during wear. It is during this stage that the coating composition transfers and provides an initial therapeutic and moisturizing benefit to the wearer which remains on the skin surface for a period of time after the article is removed.

Glycerin has a dual functionality within the nonaqueous coating composition of this invention. It serves as both a carrier and a moisturizer. The term "carrier" is meant to refer to an organic, stable, non-volatile material, which serves as a vehicle for delivering ingredients of the nonaqueous coating composition on to the glove. It is a liquid at either or both room temperature and at the processing temperature. It has a boiling point of 290°C and a vapor pressure ranging from about 0.001 mm Hg at 25°C to about 760 mm Hg at 290°C. The "carrier" in this nonaqueous composition is considered a unique property in this invention.

Other examples of organic carriers include: polyhydric alcohols such as polyglycerols such as diglycerol and polyglycerol-3; glycols such as ethylene glycol, propylene glycol, butylene glycol, diethylene glycol, dipropylene glycol, triethylene glycol and tripropylene glycol; alkoxylated alcohols: such as glycereth-7 and glycereth-26; fatty acid esters such as ethylene glycol esters such as glycol stearate, glycol palmitate and glycol oleate; propylene glycol esters such as propylene glycol myristate and propylene glycol laurate; fatty acid mono- and diglycerides such as glyceryl laurate, glyceryl oleate, diglycerin capriate and diglycerin oleate; ethoxylated triglycerides such as polyethylene glycol caprylic/capric triglycerides, polyethylene glycol caprylic/capric glycerides; ethoxylated glycerol esters such as polyethylene glycol glyceryl fatty esters; polyoxyethylene diglycerol ethers such as

POE (6) diglycerol ether and POE (40) diglycerol ether; polyoxypropylene diglycerol ethers such as POP (4) diglycerol ether and POP (24) diglycerol ether; and polypropylene glycol ethers such as PPG-14 butyl ether and PPG-3 myristyl ether. The carrier within can also consist of a combination of any of the materials listed
5 above.

Moisturizers that can be used in the coating composition include polyhydric alcohol emollients and/or moisturizers. At least one moisturizer is present, but combinations of two or more moisturizers can be use as well. Suitable polyhydric alcohol moisturizers that can be used include, but are not limited to, glycerin and
10 sorbitol. Preferably, a combination of glycerin and sorbitol is used. An example of glycerin or 1,2,3-propanetriol that can be used is Glycon™ G 300 (available from Aldrich Chemical Company, Milwaukee, Wisconsin). One example of sorbitol or D-glucitol that can be used is available from Aldrich Chemical Company, Milwaukee, Wisconsin.

15 Moisturizer ingredients can be present in an amount up to about 95.00% by weight of the total composition. Preferably, the moisturizer is present in an amount ranging from about 10.00% to about 95.00% by weight. Glycerin moisturizer can be present individually in an amount ranging from about 50.00% to about 90.00% by weight, preferably from about 60.00% to about 89.00% by weight of the total
20 nonaqueous composition. Sorbitol as a moisturizer can be present individually in an amount ranging from about 0.1% to about 6.00%, preferably from about 0.50% to about 4.00% by weight.

Additional moisturizing agents can be used in conjunction with the above-described polyhydric alcohols. The additional moisturizing agents can likewise be
25 polyhydric alcohols. Preferably, the composition of the invention comprises

pantothenol or 2,4-dihydroxy-N-(3-hydroxypropyl)-3,3-dimethylbutanamide (a.k.a. pro-vitamin B), which, in vivo, increases topical moisture retention thereby prolonging elasticity and suppleness of the skin, reduces inflammation and irritation of the skin, and stimulates epithelization. Suitable pantothenol for use in the
5 invention is available from Aldrich Chemical Company, Milwaukee, Wisconsin and Daiichi Fine Chemicals, Japan, as well as Ritapan™ DL (available from RITA Corporation, Woodstock, Illinois).

The pro-vitamin B form, pantothenol, is preferred for use in the composition. Pantothenoic acid, the acid form of pantothenol, is a member of the B-complex
10 vitamins and is also a structural component of acyl carrier proteins (ACP) as an essential component of fatty acid synthetase complex. The stability of pantothenoic acid is, however, highly sensitive to pH fluctuations. The pro-vitamin form pantothenol is preferred because it is more stable and easily absorbed, and converts into the acid form in vivo. Additional moisturizing agents such as pantothenol can be
15 present in an amount ranging from about 0.10% to about 5.00% by weight, preferably from about 1.50% to about 3.00% by weight of the total nonaqueous composition.

The coating nonaqueous composition can further comprise a hydroxyacid as a skin exfoliant. Hydroxyacids enhance proliferation of skin cells and increases ceramide biosynthesis keratinocytes, regulates epidermal thickness and improves
20 desquamation resulting in smoother skin and youthful appearance. Suitable hydroxyacids that can be used include monocarboxylic acids, dicarboxylic acids and polyhydroxy acids, and their intramolecular lactones, esters and salt forms. Examples of monocarboxylic acids include both alpha and beta forms. Gluconolactone or D-glucono-1,5-lactone is preferred because it provides a therapeutic effect with
25 relatively less skin irritation. One example of gluconolactone that can be used is

Glucono-delta-Lactone available from Daniels Archer Midland/DL, United Kingdom or Jungbunzlauer, Newton Center, Massachusetts. Hydroxyacid(s) such as gluconolactone can be present in an amount ranging from about 0.10% to about 5.00% by weight, preferably from about 0.10% by weight to about 2.00% by weight of the total nonaqueous composition.

Donning agents that can be used include quaternary ammonium halide salts which additionally exhibit antimicrobial properties. A preferred quaternary ammonium halide salt is cetylpyridinium chloride or 1-hexadecylpyridinium chloride. One example of cetylpyridinium which can be used is CPC available from Zeeland Chemicals, Zeeland, Michigan.

Other donning agents that can be used include silicone-based compounds, including polyalkylsiloxanes. One example of a polyalkylsiloxane that can be used is polydimethylsiloxane dispersion,. Other silicone-related donning agents can be used that also function as skin protecting agents as well, such as dimethicone.

Donning agents such as cetylpyridinium chloride can be present in an amount ranging from about 0.00% to about 8.00% by weight, preferably from about 0.10% to about 6.00% by weight of the total nonaqueous composition. Other donning agents can be present in an amount ranging from about 0.10% to about 8.00%, preferably from about 0.10% to about 0.25% by weight of the total composition. The coating composition can also include a pH adjuster, which can be an inorganic acid, organic acid, or combination thereof. The amount of pH adjuster to be added will, of course, vary but is preferred that the compound and amount be selected to adjust the pH value to from about pH 4 to about pH 7. Preferred are non-irritating pH adjusters, such as citric acid or 2-hydroxy-1,2,3-propane-tricarboxylic acid, which is available from Aldrich Chemical Company, Milwaukee, Wisconsin. The pH adjuster(s) such as

citric acid can be present in an amount ranging from about 0% to about 2.00% by weight of the total nonaqueous composition.

Anti-tack agents that can be used in the coating composition include silicones such as silicone oil, silicone resins, silicone gums and silicone elastomers, cationic
5 polymers such as polydiethyldimethyl ammonium chloride, fatty acid salts and esters such as potassium stearate and trimethylolpropane triisostearate, carboxylic ester of hydroxyalkylamide such as erucamide, fluoro-compounds such as PTFE (polytetrafluoroethylene) and phosphate salts such as ammonium alkyl phosphate (such as Darvan LTM available from R.T. Vanderbilt, Norwalk, Connecticut). Anti-
10 tack agent(s) can be present in an amount ranging from about 0.25% to about 8.00% by weight of the total nonaqueous composition.

The nonaqueous coating composition of the invention preferably contains a hydration promoter to facilitate uptake and absorption of topical moisture (water) needed to "activate" the coating composition. Preferred hydration promoters include
15 those, which additionally function as buffers to an acidic pH adjuster when present, such as sodium citrate. One example is 1,2,3-propanetricarboxylic acid trisodium salt, such as sodium citrate dihydrate available from Aldrich Chemical Company, Milwaukee, Wisconsin. Hydration promoter(s) such as sodium citrate can be present in an amount ranging from about 0% to about 8.00%, preferably from about 0.5% to
20 about 4.00% by weight of the total nonaqueous composition.

Other therapeutic and cosmetic agents can be used as well, such as "anti-aging" compounds. Cosmetic agents that can be used include retinol, and/or those that can also function as exfoliants, such as alpha hydroxy lactones, such as gluconolactone. Fragrances and coloring agents can also be used in the nonaqueous
25 coating formulation to render the composition more appealing to the user.

As a further embodiment, the coating composition can comprise a plasticizer to facilitate uniform distribution. Preferred plasticizers include esters such as triethyl citrates, because of its additional chemical function as a buffer in the formulation.

One example of suitable triethyl citrate or 1,2,3-propanetricarboxylic acid, 2-hydroxy-
5 , triethyl ester is Hydagen™ CAT available from Cognis, Cincinnati, Ohio.

Plasticizer(s) such as Hydagen™ CAT can be present in an amount ranging from 0% to about 1.00%, preferably from 0% to about 0.50% by weight of the total composition.

Prior to application to the surface of the elastomeric article, the inventive
10 nonaqueous coating composition needs to be heated, so as to be applied to the surface in liquid state. The nonaqueous coating composition can be heated to temperatures from about 20°C to at least about 100°C prior to glove application. It can be applied using a variety of coating techniques. Suitable coating techniques include dipping and spraying. The coating composition is subsequently cooled to a highly viscous or
15 solid state as part of the manufacturing process. Application and finishing techniques that can be used in accordance with the invention include the tumbling process and the spraying process. The spraying method is preferred for preparing surgeon's or surgical gloves. The tumbling method is preferred for preparing examination gloves. The examples contain descriptions of each of these processes in greater detail.

20 The spray method is a process that applies the heated coating composition onto the glove using a spraying apparatus. In this process, the gloves are placed into a tumbler including a spraying device. The coating composition is sprayed in the liquid state in multiple and non-continuous steps. Alternatively, the tumbling method is a process that applies the coating composition in liquid state onto the glove surface by
25 placing the gloves into a tumbler and then filling the tumbler with the coating

composition liquid. The gloves are then tumbled or washed. A tumbling process that can be used, for example, can be similar to that described in Chen et al. U.S. patent application Serial No. 10/666,650 filed September 17, 2003, now pending. Additional processes are discussed in patent applications: 10/676,793 filed September 30, 2003,
5 10/719,573 filed November 22, 2003, and 11/056,628 filed February 9, 2005.

An important aspect of the coating composition of the invention is the collective skin moisturization efficacy of multiple coating composition ingredients, and some of the coating composition ingredients of the invention can possess dual functionality. The humectant functionality of the coating composition is premised
10 upon at least two of the following moisturization effects. First, some of the ingredients of the composition function as moisturizers, such as glycerin and sorbitol. Second, some of the ingredients function as skin penetrative moisturizers, such as pantothenol. Third, some ingredients can function as prolonged skin surface moisturizers, such as film-forming polymers such as chitosan. Furthermore,
15 combinations of the above can be employed to suit the characteristics associated with different elastomeric article types. For example, since examination gloves are worn for relatively shorter time periods, the prolonged skin surface moisturizer(s) used can be optional.

Variations of the above ingredients and the addition of other ingredients are
20 possible in accordance with the invention, provided the therapeutic effect of the formulation on the skin is not significantly compromised. The ingredients of the coating composition, when combined, must be capable of participating in the therapeutic, moisturizing, non-irritating, moisturizing effect on the wearer's skin.

When the elastomeric article is intended for extended wear, such as a
25 surgeon's glove, the coating composition preferably further comprises a water-soluble

film forming polymer. Suitable water-soluble, film forming polymers which can be used include natural or synthetic film forming polymers. Preferred are cationic carrier-soluble film forming polymers. Suitable film forming polymers which can be used in accordance with the invention include, but are not limited to, cellulose and cellulose derivatives, polyvinyl pyrrolidone (PVP) and polyvinyl pyrrolidone derivatives, and polysaccharides. Preferably, polysaccharides are used as the carrier-soluble film-forming polymer, and most preferred, as the film-forming polymer is chitosan.

Chitosan can be prepared from naturally occurring chitin, which can be obtained from crustacean and insect exoskeletal material. Chitosan is also referred to as deacetylated chitin, poly-D-glucosamine, poliglucan, beta-1,4-poly-D-glucosamine, and beta-(1,4)-2-amino-2-deoxy-D-glucose. Chitosan and its derivatives can be used in accordance with the invention. One source of chitosan that can be used is deacetylchitin and its derivatives which are soluble/dispersible in the carrier of this invention. When present, film-forming polymer(s) such as chitosan can be present in an amount ranging from 0.00% to about 1.00% by weight of the total composition.

Water should not be present in any significant amount. Preferably, water is present up to about 1.0% by weight of the total inventive coating composition. Those skilled in the art may appreciate that the carriers and components of the formulation are not absolutely anhydrous. Overall, variations of the proportions and amounts of the ingredients can be adjusted provided such modifications do not substantially compromise the desired properties of the resulting formulation according to the invention.

In another embodiment, particle technology can also be used in conjunction with the coating composition to further enhance the collective benefits and properties

of the invention. In particular, microporous particles can be included in the formulation to provide a number of additional properties, such as sustained release or time release of ingredients. Preferably, the microporous particles that can be used are those impregnated with skin care ingredients that can be incorporated into the

5 inventive coating. Microporous particle technology that can be used as a component of the coating composition of the invention includes that which is described in U.S. Patent No. Reissue No. 33,429, U.S. Patent No. 4,873,091, U.S. Patent No. 4,690,825, U.S. Patent No. 5,028,435, U.S. Patent No. 5,035,890, U.S. Patent No. 5,968,543, U.S. Patent No. 5,955,109, U.S. Patent No. 5,073,365, U.S. Patent No.

10 5,135,740, U.S. Patent No. 5,145,675, U.S. Patent No. 5,145,685, U.S. Patent No. 5,156,843, U.S. Patent No. 5,316,774, U.S. Patent No. 5,458,890, U.S. Patent No. 5,840,293, U.S. Patent No. 5,871,722, and U.S. Patent No. 5,851,538.

One particular microsp sponge particle of interest is Microsp sponge 5700 (available from Cardinal Health, Inc., Somerset, New

15 Jersey), which can controllably release particle-absorbed dimethicone by diffusion.

The coating composition of the invention can further contain additional beneficial ingredients provided such are chemically compatible with the composition of the invention and do not adversely affect the desired therapeutic properties of the composition. Additional ingredients that can be included in the coating composition

20 include, but are not limited to, antimicrobial agents, anti-inflammatory agents, topical cleansing agents, anti-perspiration agents, organic solvents, and the like.

The coating composition of the invention can also be applied to elastomeric article surfaces using conventional equipment and techniques readily available to those skilled in the field of manufacturing elastomeric articles, including on-line and

25 off-line techniques such as dipping, spraying, tumbling, and the like. For preparing a

coated surgeon's glove, the preferred method of application is off-line spraying. For the preparation of a coated exam glove, the preferred on-line method of application is dip coating, and the preferred off-line method is the tumbling method of coating.

Using a surgeon's glove as an example, the user removes the glove from a
5 dispenser or package. Prior to donning the glove, the user typically scrubs their hands with surgical scrub solution followed by rinsing with water. After wiping their hands dry with a sterile towel, the user dons the glove by placing the hand into the glove such that the glove generally conforms to the shape of the user's hand. At this point, the moisture and heat from the user's skin interacts with the coating composition
10 thereby hydrating and melting the composition and converting it into a liquid "lotion"-type phase. Upon hydration and melting of the coating composition, the comfort, and therapeutic benefits such as moisturization of the skin become realized. Furthermore, after removal of the glove, the coating composition remains on the user's skin thereby providing continued therapeutic benefit to the skin.

15 The following examples further illustrate the invention. Unless otherwise noted, % is meant to indicate percent by weight of the total weight of the nonaqueous composition.

**Example 1 - Previous Aqueous Preparation of Coating Composition for Surgical
Gloves**

A previous aqueous coating was prepared by initially determining the amount of each ingredient desired using conventional ingredient amount calculation methods.

- 5 After the amount of ingredients has been determined, the total amount of water was added to a beaker and continually stirred as each of the ingredients were added. The composition was stirred at ambient temperature for at least about one hour until a stable, homogenous solution was formed. The pH and viscosity of the composition was measured in accordance with ASTM E70-97 (Standard Test Method
10 for pH of Aqueous Solutions with the Glass Electrode) and ASTM D5225-98 (Standard Test Method for Measuring Solution Viscosity of Polymers with a Differential Viscometer). Using these methods, the pH was between 4.8 and 6.0, and the viscosity was measured at between 15 and 45 cps at room temperature using a spindle no. 4 at 60 rpm. The resulting composition was then deposited into a glass
15 container and sealed with a lid.

The resulting liquid coating formulation had the following composition:

Formula 1:

Ingredient:	Amount (w/w %)
Chitosan	0.10
Citric acid	0.10
Glycerin	0.25
Sorbitol	0.75
Pantothenol	0.50
Gluconolactone	0.25
Triethyl citrate	0.50
Cetylpyridinium chloride	1.00
Silicone dispersion	0.25
Sodium citrate	0.40
Alkyl phosphate ammonium salt	1.00
Deionized water	94.90
Total:	100.00

5

Example 2A – Previous Aqueous Preparation of Coated Glove (Spraying Method)

A surgeon's glove containing a previous aqueous coating composition on the skin-contacting surface was prepared as follows:

The uncoated glove was prepared in accordance with conventional glove forming techniques and equipment. A former in the shape of a glove was provided and coated with a coagulant composition and subsequently dried. The coagulant-

10

coated former was then dipped into polyisoprene latex to coat the former and the latex was leached with water, coated with a powder layer, and cured on the coated former. After curing, the polyisoprene glove was rinsed, dried, and stripped from the former.

Prior to coating, the gloves were turned inside-out and pre-rinsed and
5 chlorinated using a chlorinator with chlorine solution with a chlorine strength of about 300 ppm to about 1000 ppm. After chlorination, the gloves were post-rinsed prior to coating.

To coat the glove, the chlorinated gloves were removed from the chlorinator, turned inside out such that the skin-contacting surface was exposed and placed in a
10 tumbler equipped with a spray nozzle. The gloves were then sprayed. Then, the gloves were dried for a sufficient period of time.

Tumbler design is an important aspect of the preparation of the gloves in order to ensure an even uniform coating of the glove surface. For example, a drum having a diameter of about 43 inches and a total length of about 25 inches can have a total
15 perforated area of about 11.5 inches and a remaining non-perforated area of about 13.5 inches relative to drum length. The non-perforated area of the drum is determined so that some of the gloves to be placed within remain in the non-perforated area for lubrication and so that suction air flow is reduced in the area. The revolution speed can vary. For example, a revolution speed ranging from about 25
20 rpm to about 35 rpm can be used, preferably from about 31 rpm to about 32 rpm.

Initial drying can be conducted at a temperature of about 32° C increasing to about 50° C, for a period of about 15 minutes. The first spraying can commence after 15 minutes of tumbling. After the first spraying, the gloves were then tumbled for an additional 60 seconds, and subjected to a second spraying for about 170 seconds and
25 tumbled again for an additional 60 seconds. A third spraying was applied for about

170 seconds, followed by tumbling at a temperature of about 60° C for a period of about 2 minutes of cooling. The spraying step was repeated until the desired amount of coating has been applied to the gloves prior to 25 minutes heat tumbling and 2 minutes cooling cycle.

- 5 At the conclusion of the tumbling stage, the gloves were removed from the tumbler for the turning stage. During the turning process, the gloves were manually turned inside out and then subjected to the final drying at a temperature of about 55° C for a period of about 15 minutes. The gloves were then allowed to cool for a period of about 3 minutes. The gloves were then dried at a temperature of about 34° C for a
- 10 period of about 20 minutes. The gloves containing the previous aqueous coating composition in dry-state can then be packaged and sterilized.

Example 2B – Previous Aqueous Preparation of Coated Glove (Tumbling Method)

An examination glove containing a previous aqueous coating composition on the skin-contacting surface were prepared as follows:

Prior to coating, the gloves were post-processed by chlorination. First, the
5 gloves were turned inside-out exposing the skin-contacting surface and placed into the chlorinator. The glove was then be pre-rinsed and chlorinated using a chlorinated solution with a chlorine strength of about 400 ppm to about 700 ppm. After chlorination, the gloves were post-rinsed prior to coating.

For coating, the chlorinated gloves were removed from the chlorinator and
10 placed into a tumbler for aqueous coating and heat drying steps. Excessive water was removed from the gloves by spinning the gloves for a period of about 5 minutes. The tumbler was then filled with an aqueous lotion solution such as per Example 3, Formula 2 or Example 4, Formula 3. The gloves were then be tumbled in the composition for a period of about 10 minutes. The composition was then drained
15 from the tumbler.

The gloves were dried in the tumbler in a heating cycle at a temperature of about 50° C for a period of about 30 minutes, and subsequently cooled in a cool-down cycle for a period of about 5 minutes. The gloves were then removed from the tumbler and manually turned inside-out. The gloves were then dried again in a dryer
20 at a temperature of about 60° C for a period of about 60 minutes and then allowed to cool to room temperature for about 10 minutes.

In the preparation of coated articles according to the present invention used a process similar to Example 2B for examination gloves and Example 2A for surgeon's gloves except that the drying step was deleted. Cooling began after the application of
25 the nonaqueous coating. One of ordinary skill in the art can make adjustments and

modifications to the above process parameters as appropriate for particular circumstances.

Example 3 – Previous Aqueous Lotion Formulation for Natural Rubber Examination**Glove****Formula 2:**

Ingredient	Amount (% w/w)
Citric acid	0.10
Glycerin	0.10
Sorbitol	0.30
Pantothenol	0.20
Gluconolactone	0.20
Sodium citrate	0.40
Silicone dispersion	0.12
Alkyl phosphate ammonium salt	0.74
Water	97.84
Total:	100.00

Example 4 – Inventive Nonaqueous Coating**Inventive Formula 3**

Ingredient	Amount (% w/w)
Citric acid	0.40
Glycerin	87.87
Sorbitol	3.03
Pantothenol	2.02
Gluconolactone	1.01
Trisodium Citrate Dihydrate	1.62
Alkyl phosphate ammonium salt	4.04
Total:	100.00

The inventive formula set out above was investigated against pure glycerin
5 and deionized water for viscosity as measured against temperature. This test was
conducted in accordance with ASTM D 2196-05. It is interesting to note that the
glycerin based formula 3 had a consistently higher viscosity over the temperature
range of 20-90°C. More specifically, at 20°C the inventive glycerin based
formulation had a viscosity of about 2200 cP, while pure glycerin had a viscosity of
10 about 1750 cP. This confirms that the inventive formulation is a highly viscous,
almost solid composition at room temperature. One aspect of the present invention
resides in the discovery that a nonaqueous lotion formulation that can be applied to
the skin contacting surface of a elastomeric article. The inventive composition is
applied by a novel nondehydration process wherein the lotion composition can be
15 transferred to the skin during and after wearing the elastomeric article. The inventive
nondehydration process and inventive composition provides the elastomeric article

with an enhanced performance without compromising glove properties such as barrier strength, donning ease, softness, and aging durability.

The inventive coating composition was prepared as follows. With continuous stirring at 50-65°C, the ingredients were added to glycerin as follows: pantothenol, gluconolactone, citric acid, trisodium citrate dihydrate, sorbitol, and Darvan L. There was a 10 minute lapse between the additions of each ingredient. The composition was stirred at 60°C increasing the temperature to about 90°C in about one hour. A stable homogeneous clear solution was formed. The pH was between 5.6 and 5.7 and the viscosity was measured at 16s (ASTM D 4212).

10 **Example 5 - Inventive Process.**

This experiment was conducted to determine if there was any mass loss during the process of application. Reference is made to Examples 1 – 4. This example describes the treatment of both surgical and exam gloves.

Nontreated polyisoprene surgical gloves were prepared in accordance with conventional glove forming and equipment known to those skilled in the art. Prior to coating, the gloves were pre-rinsed and chlorinated with chlorine strength of about 300ppm to about 400ppm. After chlorination, the gloves were prerinsed and pre-treated with lubricant prior to coating.

To treat the gloves, the gloves were turned inside out, such that the skin contacting surface is exposed. The gloves were then placed in tumbler equipped with a spray nozzle. The gloves were heated to about 70°C in the tumbler for about 5 minutes. The gloves were then sprayed with the inventive Formula 3, while spraying took place for a period of about 20 seconds. At the conclusion of spraying, the coating was allowed to solidify on the gloves with cooling at 60°C for about 30 minutes. The gloves were then cooled to ambient temperature in about 3 minutes and

then inverted. The coating weight for the surgical glove was from about 50mg per glove to about 180mg per glove. The gloves were then packaged and sterilized. These treated, surgical polyisoprene glove will hereinafter be referred to as Sample 1.

Prior to the coating of the nitrile exam gloves, they were pre-rinsed with chlorine at a strength of about 600ppm to about 700ppm. After chlorination, the gloves were then pre-rinsed prior to coating. Nitrile exam gloves were treated in a similar manner as set out above for the surgical glove. The nitrile exam gloves were also coated using the formulation of the invention set out in Formula 3. It only differed in the solidification time of 35 minutes at 60°C. Thus, the nondehydration process can be applied to a variety of glove substrates. The coating weight of the exam gloves is from about 5mg per glove to about 80mg per glove.

Example 6 – Inventive Nonaqueous Coating

Inventive Formula 4:

Ingredient	Amount (% w/w)
Citric acid	0.39
Glycerin	84.46
Sorbitol	2.91
CPC	3.89
Pantothenol	1.94
Gluconolactone	0.97
Trisodium Citrate Dihydrate	1.55
Alkyl phosphate ammonium salt	3.89
Total:	100.00

Sample 2 was prepared using Inventive Formula 4 and the inventive process of Example 5 (without the lubricant pre-treatment).

Example 7 – Determination of Coating Weight

The coating weight of the gloves were determined by using an extraction process. First, ten treated gloves and ten non-treated gloves are placed in a desiccator for 30 minutes. Each set of gloves were weighed and inverted so that the skin contacting side would be washed. The gloves were washed and tumbled rigorously with water for about 2.5 minutes in a large container. The water was removed and the gloves were washed and tumbled three more times. The gloves were then dried for 30 minutes at 60°C. The gloves are then inverted and dried for an additional 30 minutes at 60°C. The gloves were then placed in a desiccator for 30 minutes and re-weighed.

The glove washing process for the exam glove differed from the surgical glove in three aspects. First, prior to being placed in the desiccator, the exam gloves were pre-dried at about 75°C for about 30 minutes. Second, the cuffs of the exam gloves were tied with rubber bands prior to glove washing. Third, the gloves were dried at 80°C for 30 minutes.

Various factors affect the appropriate amount (load level) of coating composition applied to the glove, such as glove temperature, composition temperature, number of sprays, distance of glove from spray nozzle, total solids content of composition. The amount of coating (lotion per glove) can be calculated from total lotion spray and load size (number of gloves). Sprayer settings also affect the coating process, including cylinder pressure, liquid pressure, air pressure, and air cap type. Adjustments to appropriate or optimal manufacturing parameters can be selected by those skilled in the glove manufacturing field.

Example 8 – Inventive Glove Evaluation

Glove Performance

Section A: Treated vs. Non-Treated Glove

The glove performance was examined using a panel of evaluators, which involved nine individuals instructed to don and wear gloves treated with the inventive formulation and gloves that had received no treatment at all. Both the nontreated and treated (Sample 1) gloves were sterilized 34-40kGy and aged (at 40°C) for seven days, prior to the glove performance evaluation. Panelists donned the non-lotion treated and lotion-treated (Sample 1) gloves with dampened hands and wore them for 15 minutes. The evaluation required the individuals to assess the donning ability, transfer, quick dry, and silky feel properties of the glove on a scale of 1 through 4, 1 indicating a poor performance and a 4 indicating an excellent performance. Wet donning is the measure of the ease with which one can don the glove. Transfer is the amount of coating transferred to the hand after wearing the glove. Skin dry is the speed at which your hand dries after donning and removing the glove. The silky feel of the glove is defined as the smoothness and lack of tackiness after wearing the glove. The results for this study, utilizing a surgical glove, are shown in the following table:

Glove ID	Wet Donning	Transfer	Skin Dry	Silky Feel
Non-Treated	2.9	2.7	3.4	2.8
Treated (Sample 1)	3.1	3.0	2.5	2.4

The above evaluation demonstrates that a glove treated with the inventive non-aqueous formulation (Sample 1) provides a surprisingly better wet donning performance than the nontreated glove. Additionally, it gives a greater transfer of lotion to the skin. The skin drying at a slower rate further confirmed this affect.

Overall, the silky feel of the glove is not negatively impacted by the greater transference of lotion to the hand.

Section B: Non-aqueous Composition vs. Aqueous Composition

5 Surgical gloves, Sample 2, were prepared in a according to Example 5 above using Formula 3 (nonaqueous coating composition) and were compared with Sample 3, gloves treated with an aqueous coating composition, (Formula 4 of Example 5 of the parent patent). Both sets of gloves were sterilized 34-40kGy and aged (at 40°C) for seven days, prior to the glove performance evaluation. These gloves were
10 evaluated according to the method described in Section A above. The results of this study are shown in the following table:

Glove ID	Wet Donning	Transfer	Skin Dry	Silky Feel
Treated with non-aqueous composition (Sample 2)	2.3	2.6	2.1	2.2
Treated with aqueous composition (Sample 3)	2.3	2.4	2.6	2.5

The above evaluation demonstrates that a glove treated with the non-aqueous coating composition of the present invention (Sample 2, Formula 4) provides a similar
15 glove performance to a glove treated with an aqueous coating composition (Sample 3, see Formula 1). The therapeutic non-aqueous coating composition transfers onto the wearer's skin during use, providing the topical benefits such as good wet donning, transference, quick skin dry and silky feel, which is afforded by the ingredients of the composition, which mainly consists of the carrier glycerin.

20

Physical Properties:

The physical properties of the coating on the glove's physical performance was evaluated. ASTM D 3577-01a was used for surgical gloves and ASTM D 6319-

00 was used for the exam gloves. These were before and after values subsequent to aging at 70°C for 24 hours. The treated gloves were compared to the gloves without treatment. The evaluation of tensile strength, modulus at 300% and 500% elongation was also measured. The results for these findings can be found in the

5 following tables:

Sample 1 (Surgical)	Before Age			After Age		
	ASTM D 3577-01a ^{e2}	Non- Treated	Treated	ASTM D 3577-01a ^{e2}	Non- Treated*	Treated*
Tensile (MPa)	≥ 17	23.0	22.5	≥ 12	21.0	23.3
Modulus @ 300% (MPa)	N/A	1.27	1.27	N/A	1.18	1.18
Modulus @ 500% (MPa)	≤ 7.0	2.26	2.06	N/A	1.86	1.86
Elongation (%)	≥ 650	1042	1052	≥ 490	1002	1002

Sample 2 (Exam)	Before Age			After Age		
	ASTM D 6319-00a ^{e3}	Non- Treated*	Treated*	ASTM D 6319-00a ^{e3}	Non- Treated*	Treated*
Tensile (MPa)	≥ 14	15.4	15.7	≥ 14	15.3	17.2
Modulus @ 300% (MPa)	N/A	3.33	3.43	N/A	3.04	4.3
Modulus @ 500% (MPa)	N/A	10	8.34	N/A	9.22	16.1
Elongation (%)	≥ 500	540	569	≥ 400	550	510

* The aging conducted on the surgical treated and non-treated gloves was at 70°C/24h, which differs from ASTM method of 70°C/7days.

10 The glove tensile strength and elongation of the treated surgical and exam gloves are not only similar to non-treated gloves, but also meet the ASTM standards for surgical and exam gloves. The nonaqueous coating of the present invention does not have any negative impact on the physical properties of the treated gloves.

The coatings according to the present invention can be applied to various
15 substrates including, but not limited to, medical gloves made with different materials such as natural rubber, polyisoprene, polyvinyl chloride, nitrile rubber, polychloroprene rubber, thermoplastic elastomers, and the like. Further, combinations of any of these materials are also possible.

20 **Industrial Applicability:**

The invention provides a coating composition for the skin-contacting surfaces of elastomeric articles which provide beneficial therapeutic skin treatment to the wearer's skin. The advantages afforded by the invention are particularly useful in elastomeric articles which are associated with prolonged periods of wear, such as

5 surgical gloves, where deterioration of skin quality can occur as a result of such prolonged wear. Elastomeric articles made according to the invention can be used in a variety of contexts in addition to the medical field, such as food preparation or cosmetic usage environments. Accordingly, gloves made according to the invention not only reduce the adverse effects on the wearer's skin typically associated with

10 elastomeric gloves worn for long periods of time, but improve the condition of the wearer's skin.

The scope of the claims should not be limited by the preferred embodiments set forth in the examples, but should be given the broadest interpretation consistent with the description as a whole.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A nonaqueous therapeutic coating composition for the skin-contacting surface of an elastomeric article, said coating composition comprising:
 - glycerin in an amount ranging from 50.00% to 90.00% by weight of the composition; and
 - sorbitol in an amount ranging from 0.1% to 6.0% by weight of the composition; wherein said composition comprises less than 1.0% water by weight of the composition and transfers upon contact with skin, and
 - wherein the nonaqueous therapeutic coating composition is adapted for application directly onto the skin-contacting surface of the elastomeric article.
2. The nonaqueous therapeutic coating composition according to claim 1, further comprising a hydration promoter.
3. The nonaqueous therapeutic coating composition according to claim 2, wherein said hydration promoter comprises sodium citrate.
4. The nonaqueous therapeutic coating composition according to claim 3, further comprising an organic solvent.
5. An elastomeric article comprising the nonaqueous therapeutic coating composition of any one of claims 1 to 4 on the skin-contacting surface of said article.
6. A nonaqueous therapeutic coating composition for the skin-contacting surface of an elastomeric article, said coating composition comprising:
 - glycerin in an amount ranging from 50.00% to 90.00% by weight of the composition;
 - sorbitol in an amount ranging from 0.1% to 6.0% by weight of the composition;
 - and
 - a transferable film-forming polymer,

wherein said composition comprises less than 1.0% water by weight of the composition and transfers upon contact with skin, and

wherein the nonaqueous therapeutic coating composition is adapted for application directly onto the skin-contacting surface of the elastomeric article.

7. The nonaqueous therapeutic coating composition according to claim 6, wherein said film-forming polymer is selected from the group consisting of polysaccharides, cellulose, cellulose derivatives, polyvinyl pyrrolidone, polyvinyl pyrrolidone derivatives and combinations thereof.

8. The nonaqueous therapeutic coating composition according to claim 7, wherein said polysaccharide comprises chitosan.

9. An elastomeric article comprising the nonaqueous therapeutic coating composition of claim 6, 7 or 8 on the skin-contacting surface of said article.

10. A nonaqueous therapeutic coating composition for the skin-contacting surface of an elastomeric article, said coating composition comprising:

glycerin in an amount ranging from 50.00% to 90.00% by weight of the composition;

sorbitol in an amount ranging from 0.1% to 6.0% by weight of the composition;
and

an exfoliant,

wherein said composition comprises less than 1.0% water by weight of the composition and transfers upon contact with skin, and

wherein the nonaqueous therapeutic coating composition is adapted for application directly onto the skin-contacting surface of the elastomeric article.

11. The nonaqueous therapeutic coating composition according to claim 10, wherein said exfoliant comprises hydroxyacid.

12. The nonaqueous therapeutic coating composition according to claim 10, wherein said exfoliant comprises gluconolactone.

13. An elastomeric article comprising the nonaqueous therapeutic coating composition of claim 10, 11 or 12 on the skin-contacting surface of said article.

14. A nonaqueous therapeutic coating composition for the skin-contacting surface of an elastomeric article, said coating composition comprising:

glycerin in an amount ranging from 50.00% to 90.00% by weight of the composition;

sorbitol in an amount ranging from 0.1% to 6.0% by weight of the composition;
and

microporous particles,

wherein said composition comprises less than 1.0% water by weight of the composition and transfers upon contact with skin, and

wherein the nonaqueous therapeutic coating composition is adapted for application directly onto the skin-contacting surface of the elastomeric article.

15. An elastomeric article comprising the nonaqueous therapeutic coating composition of claim 14 on the skin-contacting surface of said article.

16. A process for the production of an elastomeric article, said process comprising contacting the skin-contacting surface of said elastomeric article with a non-aqueous therapeutic coating composition according to any one of claims 1-4, 6-8, 10-12 and 14.

17. The process according to claim 16, wherein the step of contacting comprises tumbling or spraying.

18. The process according to claim 16 or 17, further comprising heating the nonaqueous therapeutic coating composition prior to the contacting step and cooling the elastomeric article after the contacting step.