



Office de la Propriété  
Intellectuelle  
du Canada

Un organisme  
d'Industrie Canada

Canadian  
Intellectual Property  
Office

An agency of  
Industry Canada

CA 2742392 A1 2010/06/03

(21) **2 742 392**

(12) **DEMANDE DE BREVET CANADIEN**  
**CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2009/11/02  
(87) Date publication PCT/PCT Publication Date: 2010/06/03  
(85) Entrée phase nationale/National Entry: 2011/05/02  
(86) N° demande PCT/PCT Application No.: US 2009/062912  
(87) N° publication PCT/PCT Publication No.: 2010/062709  
(30) Priorité/Priority: 2008/11/03 (US12/263,704)

(51) Cl.Int./Int.Cl. *C07F 9/40* (2006.01),  
*C08G 59/30* (2006.01)

(71) **Demandeur/Applicant:**  
3M INNOVATIVE PROPERTIES COMPANY, US


(72) **Inventeurs/Inventors:**  
LIM, LISA S., US;  
PYUN, EUMI, US;  
RULE, JOSEPH D., US

(74) **Agent:** SMART & BIGGAR

(54) Titre : DERIVES PHOSPHORES DE SILSESQUIOXANNE EN TANT QU'AGENTS IGNIFUGEANTS  
(54) Title: PHOSPHORUS-CONTAINING SILSESQUIOXANE DERIVATIVES AS FLAME RETARDANTS

**(57) Abrégé/Abstract:**

A phosphorus-containing silsesquioxane is represented by the formula  $[R^1_3SiO_{1/2}]^m[R^2SiO_{3/2}]^n[R^3SiO_{3/2}]^p[(R^4O)_2PO(CH_2)_xSiO_{3/2}]^q$  wherein each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group;  $x$  represents an integer of from 1 to 8;  $m$  is a positive number less than 1.5;  $n$  and  $q$  are positive numbers greater than 0 and less than 1; and  $p$  is a number greater than or equal to 0 and less than 1. Further,  $(n + p)/q$  is in a range of from 0.5 to 99, and  $(n + p + q) = 1$ . Curable and cured compositions comprising the phosphorus-containing silsesquioxane are disclosed.



## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
3 June 2010 (03.06.2010)(10) International Publication Number  
WO 2010/062709 A2(51) International Patent Classification:  
*C07F 9/40* (2006.01)      *C08G 59/30* (2006.01)

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:  
PCT/US2009/062912(22) International Filing Date:  
2 November 2009 (02.11.2009)(25) Filing Language:  
English(26) Publication Language:  
English(30) Priority Data:  
12/263,704 3 November 2008 (03.11.2008) US(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).(72) Inventors: **LIM, Lisa, S.**; 7908 S. Twelve Pines Drive, Sandy, Utah 84094 (US). **PYUN, Eumi**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **RULE, Joseph, D.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).(74) Agents: **WRIGHT, Bradford, B.** et al.; 3M Center, Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

## Published:

- without international search report and to be republished upon receipt of that report (Rule 48.2(g))



WO 2010/062709 A2

(54) Title: PHOSPHORUS-CONTAINING SILSESQUIOXANE DERIVATIVES AS FLAME RETARDANTS

(57) Abstract: A phosphorus-containing silsesquioxane is represented by the formula  $[R^1_3SiO_{1/2}]m[R^2_2SiO_{3/2}]n[R^3SiO_{3/2}]p[(R^4O)_2PO(CH_2)_xSiO_{3/2}]q$  wherein each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group;  $x$  represents an integer of from 1 to 8;  $m$  is a positive number less than 1.5;  $n$  and  $q$  are positive numbers greater than 0 and less than 1; and  $p$  is a number greater than or equal to 0 and less than 1. Further,  $(n + p)/q$  is in a range of from 0.5 to 99, and  $(n + p + q) = 1$ . Curable and cured compositions comprising the phosphorus-containing silsesquioxane are disclosed.

## PHOSPHORUS-CONTAINING SILSESQUIOXANE DERIVATIVES AS FLAME RETARDANTS

5

### TECHNICAL FIELD


The present disclosure broadly relates to flame retardants and their use in epoxy resins.

### BACKGROUND

10 Current flame retardants used in epoxy resins have a number of problems. For example, brominated and other halogen-containing flame retardants typically produce toxic and corrosive combustion products. Inorganic hydrates, which typically decompose to produce water, must typically be used in such high amounts that they compromise the physical properties of the epoxy resin. Moreover, halogen-based fire retardants have been the 15 subject of various environmental regulatory concerns.

### SUMMARY

The present disclosure provides a phosphorus-containing silsesquioxane represented by the formula



wherein

each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group;

$x$  represents an integer of from 1 to 8;

$m$  is a positive number less than 1.5;

25  $n$  and  $q$  are positive numbers greater than 0 and less than 1; and

$p$  is a number greater than or equal to 0 and less than 1, wherein  $(n + p)/q$  is in a range of from 0.5 to 99, and further wherein  $(n + p + q) = 1$ .

In some embodiments, each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents an alkyl group having from 1 to 8 carbon atoms. In some embodiments, each  $R^1$  represents a methyl group, and each  $R^2$  and  $R^3$  is independently selected from the group consisting of a methyl

30

5

group, a cyclohexyl group, a cyclopentyl group, and an isopropyl group. In some embodiments, x is 2. In some embodiments, the phosphorus-containing silsesquioxane has a number average molecular weight in a range of from 500 to 10000 grams per mole. In some embodiments, the phosphorus-containing silsesquioxane has a number average molecular weight in a range of from 1000 to 4000 grams per mole.

Silsesquioxanes according to the present disclosure are useful; for example, as flame retardants, and are especially useful in combination with non-halogen flame retardants.

10

Accordingly, in another aspect, the present disclosure provides a curable composition comprising an epoxy resin, an effective amount of curative for the polyepoxide, and a phosphorus-containing silsesquioxane according to the present disclosure.

In some embodiments, the curable composition further comprises an effective amount of curative for the thermosetting resin. In some embodiments, the thermosetting resin comprises a curable epoxy resin.

15

And in yet another aspect, the present disclosure provides a cured composition comprising a thermoset resin and a phosphorus-containing silsesquioxane according to the present disclosure.

As used herein:

"hydrocarbyl group" refers to a univalent group formed by removing a hydrogen atom from a hydrocarbon;

20

"non-halogenated" means free of halogen atoms;

"thermosetting" means capable of being chemically crosslinked; and


"thermoset" means sufficiently chemically crosslinked that it will not exhibit melt flow.

25

## DETAILED DESCRIPTION

Silsesquioxanes have frameworks formed of Si—O—Si linkages. They are commonly formed by condensation of one or more organosilanes (for example, trialkoxysilane derivatives).

Silsesquioxanes according to the present disclosure are represented by the formula



Each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group. Useful hydrocarbyl groups include aliphatic groups (for example, linear, cyclic, and/or branched alkyl groups) and aromatic (for example, aryl, aralkyl, or alkaryl groups) groups. Exemplary hydrocarbyl groups include: alkyl groups having from 1 to 8 carbon atoms such as, for example, methyl, ethyl, propyl, isopropyl, butyl, pentyl, hexyl, isoctyl, cyclohexyl, methylcyclohexyl, and cyclopentyl groups; aryl groups such as, for example, phenyl; aralkyl groups such as for example, methylphenyl and ethylphenyl groups; and aralkyl groups such as phenylethyl and phenylmethyl groups. Those embodiments in which  $R^1$  is a methyl group are typically desirable. Similarly, those embodiments in which  $R^2$  and  $R^3$  independently represent methyl group(s), cyclohexyl group(s), cyclopentyl group(s), and isopropyl group(s) are typically desirable, especially in combination with  $R^1$  being a methyl group.

The variable  $x$  represents an integer of from 1 to 8; for example, 1, 2, 3, 4, 5, 6, 7, or 8. Those embodiments in which  $x$  is 2 are typically desirable.

The variable  $m$  represents a positive number (that is, any number greater than zero) less than 1.5; for example, 0.001, 0.01, 0.1, 0.3, 0.5, 0.75, 1, 1.25, or 1.49.

The variables  $n$  and  $q$  represent positive numbers that are greater than 0 and less than 1; for example, 0.01, 0.1, 0.3, or 0.5.

The variable  $p$  is a number greater than or equal to 0 and less than 1; for example 0, 0.01, 0.1, 0.3, 0.5, 0.75, or 0.99.

The variables  $x$ ,  $m$ ,  $n$ ,  $p$ , and  $q$ , may be used in any combination subject to two constraints:

- (1) the quantity  $(n + p)/q$  is in a range of from 0.5 to 99; and
- (2) the quantity  $(n + p + q)$  equals 1.

The phosphorus-containing silsesquioxane may have any molecular weight meeting the abovementioned criteria. As is typical with silsesquioxanes, they may exist as a single compound or as mixture of silsesquioxanes having different molecular weights. In such cases, it is common practice in the art to refer to an average molecular weight (for example, a number average molecular weight). Silsesquioxanes having a number average molecular

weight in a range of from 500 to 10000 grams per mole (for example, 1000 to 4000 grams per mole) are typically particularly suitable for use as flame retardants in thermosetting resins.

Silsesquioxanes according to the present disclosure may be made, for example, by condensation of corresponding trialkoxysilanes, which may be prepared according to known methods or purchased from commercial sources. In a representative synthesis, the trialkoxysilane derivatives are combined with formic acid and heated at elevated temperature (for example, about 80 °C) sufficient to remove alcoholic byproducts generated by condensation of the trialkoxysilanes to form the corresponding silsesquioxane. Any residual silanol groups can be capped with  $(CH_3)_3Si-$  groups; for example, by addition of hexamethyldisilazane or hexamethyldisiloxane. Volatiles (including any unreacted starting materials) can be removed by heating under vacuum.

Respective amounts of n, p, and q can be controlled by controlling the amount of the corresponding trialkoxysilanes.

Silsesquioxanes according to the present disclosure are useful; for example, as flame retardants, and are especially useful in combination with non-halogenated flame retardants, wherein it may be possible to lower the overall amount by weight of the flame retardant that is necessary to pass industry standard tests for flame retardancy; for example, to obtain a UL94-V0 rating of a thermoset resin (according to test method UL 94 "Standard for Tests for Flammability of Plastic Materials for Parts in Devices and Appliances", Section 8, 20 mm Vertical Burning Test (updated through May 22, 2001) issued by Underwriters Laboratories of Northbrook, Illinois). Examples of non-halogenated flame retardants include: boehmite, organoborates, organophosphates, organophosphites, and organophosphinates (for example, as EXOLIT OP1230 and EXOLIT OP930 available from Clariant Corp. of Charlotte, North Carolina).

The present disclosure also provides a curable composition comprising a thermosetting resin, optionally an effective amount of curative for the thermosetting resin, and a phosphorus-containing silsesquioxane according to the present disclosure. Examples of thermosetting resins include epoxy resins (one-part and/or two-part), urethane resins (one-part and/or two-part), cyanate resins, phenolic resins, and acrylic resins. Desirably, for electronics applications the thermosetting resin is electronic grade.

Exemplary thermosetting resins include a two-part epoxy resin available as 3M SCOTCHCAST ELECTRICAL INSULATING RESIN 4 from 3M Company of Saint Paul, Minnesota. Examples of useful epoxy resins include 2,2-bis[4-(2,3-epoxypropoxy)-phenyl]propane (diglycidyl ether of bisphenol A) and materials available as EPON 828, 5 EPON 1004, and EPON 1001F, commercially available from Shell Chemical Co., DER-331, DER- 332 and DER-334, commercially available from Dow Chemical Co. Other suitable epoxy resins include glycidyl ethers of phenol formaldehyde novolac (for example, DEN-43 and DEN-428, commercially available from Dow Chemical Co.).

Optionally, the thermosetting resin may contain one or more hardeners, initiators 10 and/or catalysts (collectively referred to herein as "curative"), typically in an amount that is effective for chemically cross-linking the thermosetting resin (that is, an effective amount of curative). The choice of curative and the amount to use typically will depend on the type of thermosetting resin selected, and will be well known to the skilled artisan. Exemplary curatives for epoxy resins include amines (including imidazoles), mercaptans, and Lewis 15 acids.

The phosphorus-containing silsesquioxane may be used in any amount in curable and/or cured compositions according to the present disclosure. For example, the phosphorus-containing silsesquioxane may be present in an amount in a range of from 1 to 20 percent by weight, typically 4 to 10 percent by weight, and more typically 4-8 percent by weight, based 20 on the total weight of the curable and/or cured composition.

The curable compositions may be formed by simple mixing; however, it is generally desirable to use a technique capable of forming a uniform dispersion. In one technique, flame retardant and/or phosphorus-containing silsesquioxane are mixed into the thermosetting resin using a high shear mixer such as, for example, a high speed mixer available as 25 SPEEDMIXER DAC 150FVZ from FlackTek, Inc. of Landrum, South Carolina.

The curable compositions may be cured, for example by conventional methods well known in the art, including by mixing (in the case of two-part thermosetting resins), heating, exposure to actinic or thermal radiation, or any combination thereof resulting in a cured composition

Objects and advantages of this disclosure are further illustrated by the following non-limiting examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and, details, should not be construed to unduly limit this disclosure.

5

## EXAMPLES

Unless otherwise noted, all parts, percentages, ratios, etc. in the Examples and the rest of the specification are by weight.

Materials used in the example are listed in Table 1 (below).

TABLE 1

Hexyltrimethoxysilane was obtained from TCI America of Portland, Oregon.
Methyltrimethoxysilane was obtained from Aldrich Chemical Co. of Milwaukee, Wisconsin.
Hexamethyldisiloxane, hexamethyldisilazane, and formic acid were obtained from Alfa-Aesar Co. of Ward Hill, Massachusetts.
Diethylphosphatoethyltriethoxysilane was obtained from Gelest Inc., of Morrisville, Pennsylvania.
SC4 refers to 3M SCOTCHCAST ELECTRICAL INSULATING RESIN 4, which is a two-part epoxy resin obtained from 3M Company of St. Paul, Minnesota.
OP1230 refers to EXOLIT OP1230 a flame retardant based on a metal organophosphinate salt obtained from Clariant Corp. of Charlotte, North Carolina.

10

### *UL94 20 mm Vertical Burn Test*

The UL 94 "Standard for Tests for Flammability of Plastic Materials for Parts in Devices and Appliances", Section 8, 20 mm Vertical Burning Test (updated June 8, 2000) issued by Underwriters Laboratories of Northbrook, IL was used, except that only the

15

indicated number of replicates were tested. Summary criteria for the test are given in Table 2 (below):

TABLE 2

CRITERIA CONDITIONS	94 V-0	94 V-1	94 V-2
Flame Time, T1 or T2	≤ 10 seconds	≤ 30 seconds	≤ 30 seconds
Flame Time, T1 + T2	≤ 50 seconds	≤ 250 seconds	≤ 250 seconds
Glow Time, T3	≤ 30 seconds	≤ 60 seconds	≤ 60 seconds
Did the specimen burn up to holding clamp? Yes/No	No	No	No
Did the specimen drip flaming particles that ignited the cotton indicator? Yes/No	No	No	Yes

5

In Table 2 (above) T<sub>1</sub> refers to the afterflame time after first flame application. T<sub>2</sub> refers to the afterflame time after second flame application time. T<sub>3</sub> refers to the afterglow time after second flame application.

## 10 Cone Calorimeter Burn Test

Cone Calorimeter burn test were done in accordance to ASTM E1354-08, "Standard Test Method for Heat and Visible Smoke Release Rates for Materials and Products Using an Oxygen Consumption Calorimeter" (2008). Fire Growth Rate (FIGRA), which is not included in ASTM E1354-08 was calculated as the peak heat release rate divided by the time to peak heat release. Percent Reduction of FIGRA was determined using a control specimen tested on the same day as the test specimen.

### 15 Comparative Example A

Methyltrimethoxysilane (100 grams, 0.73 mole), hexyltrimethoxysilane (151.5 grams, 0.73 mole), and formic acid (202.7 grams, 4.40 moles) were placed in a 1-liter round bottom

20

flask with magnetic stirring. The flask was heated in a 70 °C oil bath for 35 minutes with distillation to collect the volatile byproducts. Hexamethyldisiloxane (96 grams, 0.59 mole) was then added and the solution was heated in a 65 °C oil bath at reflux for 50 minutes.

5 Volatile byproducts were then removed under vacuum. Hexane (200 mL) and hexamethyldisilazane (97 g, 0.60 mole) were added and the solution was suction filtered. The volatile components of the filtrate were removed under vacuum, first at room temperature and then with heating in a 90 °C oil bath. The resulting product, Comparative Silsesquioxane A, was a viscous, colorless liquid.  $^1\text{H}$  NMR analysis was consistent with the following formula:  $[(\text{CH}_3)_3\text{SiO}_{1/2}]_{0.4}[\text{CH}_3\text{SiO}_{3/2}]_{0.5}[\text{C}_6\text{H}_{13}\text{SiO}_{3/2}]_{0.5}$ .

10 The number average molecular weight was measured by GPC relative to polystyrene standards as 680 grams/mole.

*Example 1*

15 Methyltrimethoxysilane (15 grams, 0.110 mole), hexyltrimethoxysilane (22.7 grams, 0.110 mole), diethylphosphatoethyltriethoxysilane (11.9 grams, 0.036 mole) and formic acid (35.4 grams, 0.770 mole) were combined in a 250-milliter round-bottomed flask, and magnetically stirred in an 80 °C oil bath with distillation of volatile byproducts over 25 minutes. Hexamethyldisiloxane (32 grams, 0.197 mole) was added and the mixture was stirred for an additional 65 minutes in the 80 °C oil bath. Volatile byproducts were removed under vacuum. Hexane (25 g) and hexamethyldisilazane (25 g, 0.155 mole) were then added and the solution was stirred for 35 minutes. The volatile products were removed under vacuum to give Silsesquioxane 1 as a viscous, colorless liquid.  $^1\text{H}$  NMR analysis was consistent with the formula:

$[(\text{CH}_3)_3\text{SiO}_{1/2}]_{0.38}[\text{CH}_3\text{SiO}_{3/2}]_{0.43}[\text{C}_6\text{H}_{13}\text{SiO}_{3/2}]_{0.43}[(\text{C}_2\text{H}_5\text{O})_2\text{PO}(\text{CH}_2)_2\text{SiO}_{3/2}]_{0.14}$

20 The number average molecular weight was measured by GPC relative to polystyrene standards as 1600 grams/mole.

*Flame Retardancy Testing*

Various thermosetting compositions were prepared and tested according to the UL94, 20 mm Vertical Burn Test by combining the indicated flame retardant(s) in SC4 epoxy resin in the amounts indicated in Tables 3 and 4 (below). All the compositions listed in Table 3 (below) had T3 = 0 seconds, did not burn to the holding clamp, and did not ignite cotton as in UL 94 above. All the parameters in Table 4 are as defined in ASTM E1354-08 except FIGRA (column 7 in Table 4). FIGRA = Fire growth rate and is calculated as the peak heat release rate (column 5 in Table 4) divided by the time to peak heat release rate (column 6 in Table 4). Reduction of FIGRA in Table 4 is the percentage difference in FIGRA for each row compared to the control 100 parts SC4 (row 1). In Table 4, MJ = megajoules; m<sup>2</sup> = square meter; and kW = kilowatts. The cone calorimeter instrument measurements have a known error on the order of +/- 10 percent.

TABLE 3

EXAMPLE	THERMOSETTING COMPOSITION	REPLICATE	UL94 20 mm Vertical Burn Test	
			DRIP?	PASS/FAIL V0-V2
COMPARATIVE EXAMPLE B1	94 parts SC4, 6 parts OP1230	1	No	Fail
		2	No	Fail
		3	No	Fail
		4	No	Fail
COMPARATIVE EXAMPLE B2	93 parts SC4, 7 parts OP1230	1	No	Fail
		2	No	V1
COMPARATIVE EXAMPLE B3	92 parts SC4, 8 parts OP1230	1	No	V1
		2	No	V1
COMPARATIVE EXAMPLE C	93 parts SC4, 6 parts OP1230, 1 part Comparative Silsesquioxane A	1	No	V1
		2	No	V0
EXAMPLE 2	93 parts SC4, 6 parts OP1230, 1 part Silsesquioxane 2	1	No	V0
		2	No	V0
EXAMPLE 3	99 parts SC4, 1 part Silsesquioxane 2	1	No	Fail
		2	No	Fail
EXAMPLE 4	93 parts SC4, 7 part Silsesquioxane 2	1	No	Fail
		2	No	V1

TABLE 4


EXAMPLE	THERMOSETTING COMPOSITION	Total Heat Release, MJ/m <sup>2</sup>	Average. Heat Release Rate, kW/m <sup>2</sup>	Peak Heat Release Rate, kW/m <sup>2</sup>	Peak at time, seconds	FIGRA	Percent Reduction of FIGRA
COMPARATIVE EXAMPLE D	100 parts SC4	175	920	2006	145	13.83	0.0
COMPARATIVE EXAMPLE B1	94 parts SC4, 6 parts OP1230	150	484	707	205	3.45	75.6
COMPARATIVE EXAMPLE B2	93 parts SC4, 7 parts OP1230	133	408	852	215	3.96	71.6
COMPARATIVE EXAMPLE B3	92 parts SC4, 8 parts OP1230	129	389	710	230	3.09	77.8
COMPARATIVE EXAMPLE C	93 parts SC4, 6 parts OP1230, 1 part Comparative Silsesquioxane A	150	698	1379	155	8.90	37.1
EXAMPLE 2	93 parts SC4, 6 parts OP1230, 1 part Silsesquioxane 2 1% S-2	145	425	639	210	3.04	78.0
EXAMPLE 3	99 parts SC4, 1 part Silsesquioxane 2	162	662	1515	165	9.18	34.1
EXAMPLE 4	93 parts SC4, 7 part Silsesquioxane 2	155	378	613	110	5.57	60.0

All patents and publications referred to herein are hereby incorporated by reference in their entirety. Various modifications and alterations of this disclosure may be made by those skilled in the art without departing from the scope and spirit of this disclosure, and it should be understood that this disclosure is not to be unduly limited to the illustrative embodiments set forth herein.

5

What is claimed is:

1. A phosphorus-containing silsesquioxane represented by the formula



5 wherein

each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group;

$x$  represents an integer of from 1 to 8;

$m$  is a positive number less than 1.5;

$n$  and  $q$  are positive numbers greater than 0 and less than 1; and

10  $p$  is a number greater than or equal to 0 and less than 1, wherein  $(n + p)/q$  is in a range of from 0.5 to 99, and further wherein  $(n + p + q) = 1$ .

2. The phosphorus-containing silsesquioxane of claim 1, wherein each of  $R^1$ ,  $R^2$ ,  $R^3$ ,  $R^4$  independently represents an alkyl group having from 1 to 8 carbon atoms.


15 3. The phosphorus-containing silsesquioxane of claim 1, wherein: each  $R^1$  represents a methyl group; and each  $R^2$  and  $R^3$  is independently selected from the group consisting of a methyl group, a cyclohexyl group, a cyclopentyl group, and an isopropyl group.

20 4. The phosphorus-containing silsesquioxane of claim 3, wherein  $x$  is 2.

5. The phosphorus-containing silsesquioxane of claim 1, wherein the phosphorus-containing silsesquioxane has a number average molecular weight in a range of from 500 to 10000 grams per mole.

25 6. The phosphorus-containing silsesquioxane of claim 1, wherein the phosphorus-containing silsesquioxane has a number average molecular weight in a range of from 1000 to 4000 grams per mole.

7. A curable composition comprising:  
a thermosetting resin; and  
a phosphorus-containing silsesquioxane represented by the formula



5 wherein

each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group;

$x$  represents an integer of from 1 to 8;

$m$  is a positive number less than 1.5;

$n$  and  $q$  are positive numbers greater than 0 and less than 1; and

10  $p$  is a number greater than or equal to 0 and less than 1, wherein  $(n + p)/q$  is in a range of from 0.5 to 99, and further wherein  $(n + p + q) = 1$ .

8. The curable composition of claim 7, further comprising an effective amount of curative for the thermosetting resin.


15

9. The curable composition of claim 7, wherein the thermosetting resin comprises a curable epoxy resin.

10. The curable composition of claim 7, wherein each  $R^1$  represents a methyl group; and  
20 each  $R^2$  and  $R^3$  is independently selected from the group consisting of a methyl group, a cyclohexyl group, a cyclopentyl group, and an isopropyl group, and  $x$  is 2.

11. The curable composition of claim 7, wherein the phosphorus-containing silsesquioxane has a number average molecular weight in a range of from 500 to 10000 grams  
25 per mole.

12. A cured composition comprising:  
a thermoset resin; and  
a phosphorus-containing silsesquioxane represented by the formula



5 wherein

each of  $R^1$ ,  $R^2$ ,  $R^3$ , and  $R^4$  independently represents a hydrocarbyl group;  
 $x$  represents an integer of from 1 to 8;  
 $m$  is a positive number less than 1.5;  
 $n$  and  $q$  are positive numbers greater than 0 and less than 1; and  
10  $p$  is a number greater than or equal to 0 and less than 1, wherein  $(n + p)/q$  is in a range of from 0.5 to 99, and further wherein  $(n + p + q) = 1$ .

13. The curable composition of claim 12, wherein the thermosetting resin comprises a curable epoxy resin.

15

14. The cured composition of claim 12, wherein each  $R^1$  represents a methyl group; and each  $R^2$  and  $R^3$  is independently selected from the group consisting of a methyl group, a cyclohexyl group, a cyclopentyl group, and an isopropyl group, and  $x$  is 2.

20 15. The cured composition of claim 12, wherein the phosphorus-containing silsesquioxane has a number average molecular weight in a range of from 500 to 10000 grams per mole.

25