

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 February 2003 (06.02.2003)

PCT

(10) International Publication Number
WO 03/010385 A1

(51) International Patent Classification⁷: D21H 13/12 (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/US02/22580

(22) International Filing Date: 17 July 2002 (17.07.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 09/911,528 24 July 2001 (24.07.2001) US

(71) Applicant: E. I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventors: AMPUERO AUZA, Jaime, A.; Saatlenzengstrasse 22, CH-8050 Zurich (CH). LEVIT, Mikhail, R.; 1018 Baldwin Road, Richmond, VA 23229 (US). NELSON, Arthur, R.; 5310 Watercrest Road, Midlothian, VA 23112 (US).

(74) Agent: GRIFFITHS, John, E.; E. I. Du Pont De Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 03/010385 A1

(54) Title: NONWOVEN MATERIAL FOR LOW FRICTION BEARING SURFACES

(57) Abstract: The present invention relates to a saturable nonwoven material comprising fluoropolymer floc and aramid floc, which can be used as a substrate for a liner for self-lubricating bearings and for other applications.

TITLE**NONWOVEN MATERIAL FOR LOW FRICTION BEARING SURFACES**

5

BACKGROUND OF THE INVENTION**1. Field of the Invention**

This invention relates to saturable nonwoven materials comprising fluoropolymer fibers and other additional wettable structural organic fibers. Such nonwovens may be used as a liner material for self-lubricating bearing surfaces, as a sealant, in filtration systems, as electrical insulation and in other applications.

2. Description of the Related Art

The use of a woven or knitted fabric as a liner material for self-lubricating bearings is well known in the art. These woven or knitted fabrics typically consist of fluoropolymer yarn and structural yarns (for example, cotton, polyester or glass fiber etc.).

U.S. Patent Nos. 2,804,886 (White), 3,055,788 (Stanhope et al.), 3,037,893 (White) and GB 861,506 (Wright et al.) disclose the use of woven fluoropolymer fabric in friction applications. However, liners based on such fabrics are very expensive and typically limited to a thickness of about 0.127 mm or greater. Such woven fabrics known in the industry require complex and expensive manufacturing processes and are characterized by a significant resistance to heat flow. This heat resistance results in the bearings becoming overheated at or above relative speeds in the range of

about 0.5 m/s causing increased levels of friction, thus reducing their service life, as indicated by a significant loss of liner material, thereby limiting their operating conditions and requiring more numerous 5 replacements of such liners which results in increased production or operating costs.

Also, a nonwoven structure comprising fluoropolymer fibers and an amount of a binder sufficient to provide an appropriate level of wet and 10 dry strength to the nonwoven structure is well known in the art. U.S. Patent 3,114,672 (Schott) discloses such a material, wherein it can be used for the filtration of hot gases that are chemically active.

Also known in the art, is a pressboard 15 material, which consists of m-aramid fiber, m-aramid fibrids, and fluoropolymer fiber. The pressboard material is primarily utilized as electrical insulation as is described in U.S. Patent 4,888,578 (Hendren, Provost et al.).

20 The present invention offers the advantage of providing a saturable or open porous, nonwoven structure, which can be impregnated with a resin such that the resin permeates throughout the entire structure, comprising fluoropolymer fibers blended with 25 other additional wettable structural organic fibers. Additionally, saturable nonwoven structures having the thickness of the present invention and the applications of the present invention have not been described in the art. Further, the present invention addresses the 30 problems recognized within the industry that are encountered through the use of thick woven fabrics by providing a thin structure. Further, the present invention offers several other advantages in that it can be used at higher speeds than conventional

materials, or it can be used at similar speeds as conventional materials yet have an increased service life, and it may be utilized at higher loading capacities.

5

SUMMARY OF THE INVENTION

The present invention relates to a saturable nonwoven material comprising a blend of fluoropolymer 10 fibers and other additional wettable structural organic fibers along with any incumbent fibers used in paper or other sheet structures including, but not limited to polyester, rayon, cellulose, aramid, polyamide, wool, cotton, polyolefin (with structural fibers) and 15 combinations thereof, which can be used as a liner material for self-lubricating bearings and other applications. The additional wettable structural organic fibers impart new characteristics to the saturable nonwoven material of the present invention, 20 such as friction resistance.

The invention also relates to a paper or a sheet or a prepreg comprising the saturable nonwoven structure of the present invention and a resin, as well as to a self-lubricating bearing.

25 Further, the present invention relates to a process for making a saturable nonwoven material of the present invention comprising the steps of:

- a.) delivering an aqueous dispersion of a mixture comprising wettable structural organic floc, 30 fluoropolymer floc, and optionally a binder onto a screen of a papermaking device;
- b.) withdrawing water from the aqueous dispersion to leave a wet paper felt;
- c.) drying the wet paper felt; and

d.) optionally, calendering the dried nonwoven material for further densification of the material.

5

DETAILED DESCRIPTION

The present invention provides a saturable nonwoven material that is useful, for example, as a liner of self-lubricating bearings or other low friction load bearing surfaces. Further, the present invention may be used in filtration systems due to its chemical resistance, and as electrical insulation due to its low dielectric constant and low dissipation factor and in other applications, for example, in flange material utilized in industrial piping where chemical resistance is a necessary property.

A saturable nonwoven material of the present invention comprises a mixture of fluoropolymer floc and one or more other additional wettable structural organic floc, and may optionally contain a binder. Preferably, the fluoropolymer floc comprises at least about 30% by weight of the mixture. Additionally, the binder, when utilized comprises up to about 30% by weight of the mixture. Those practitioners skilled in the art would recognize and understand when such a binder would be necessary. Also, the present invention preferably has a substantially uniform distribution of the fluoropolymer floc, the at least one additional wettable structural organic floc, and the optional binder when the binder utilized. However, such a distribution is not a requirement.

The term "structure", when used in conjunction with "fiber" or "floc", refers to fiber or floc that performs a reinforcement function providing

structural integrity and strength. It also refers to a non-flowing support fiber or floc allowing fluoropolymer film from the fluoropolymer fiber to flow during the use of the bearing. The structural fiber or 5 floc allows for greater wear resistance of the present invention. Additionally, the fiber or floc provides frictional melt resistance to the present invention.

The term "wettable" refers to a structural organic floc that is wettable by a thermoset resin 10 composition including, but not limited to, epoxy, phenolics and polyamides.

The term "self-lubricating", as used herein, refers to a bearing wherein no additional lubricant, such as grease, oil or other lubricant, is required due 15 to the bearing by itself having a polymer surface with a low coefficient of friction which results in a low wear.

The saturable nonwoven material of the present invention may be made in a conventional wet-20 laid papermaking process, which includes dispersing fibers in water, pouring the dispersion on a screen, dewatering the dispersion under the action of gravity and a vacuum with formation of the sheet, and drying. Wet pressing (compression) of the sheet against one 25 felt or between two felts can be performed prior to drying to increase the sheet's density and strength and reduce its water content before drying. This process also includes the optional use of a binder, wherein such binders include, but are not limited to, aramid 30 fibrils. Other binders known within the industry may also be used in the process, for example, water-soluble poly (vinyl alcohol) fibers, poly (vinyl acetate) dispersions, fluoropolymer dispersions, and different types of pulps including cellulose. Other methods of

making a saturable nonwoven material of the present invention include, but are not limited to, dry-laid methods of manufacturing which are well known within the art, such as the spunlace process, in which fibers 5 are deposited on a screen from air dispersion followed by hydroentangling.

The formed saturable nonwoven material of the present invention may optionally be calendered, depending on the density and strength requirements of 10 the final material.

A prepreg based on the saturable nonwoven material of the present invention can be made by any known technique with the usage of a matrix resin solution or dispersion or melt having an ability to 15 reasonably flow into the structure of the present invention. The matrix resin can be one of either high or low viscosity. However, if the matrix resin has a high viscosity it should be dissolved in solution. Whereas, if a low viscosity matrix resin is utilized, 20 the solution or dispersion may not be necessary.

As used herein, "prepreg" refers to a nonwoven fibrous material impregnated by a resin, but still has enough formability to be compressed and/or shaped during preparation of the final composite. In 25 the case of thermosets, they are usually in a curing stage B (partially soluble) in the prepreg and can be cured additionally to stage C (cross-linked, not soluble) later.

The saturable nonwoven materials of the present invention have a basis weight of about 17 g/m² 30 to about 810 g/m² and a thickness of about 0.02mm to about 8.0mm.

Several methods may be utilized for the preparation of a self-lubricating bearing of the

present invention. Method 1 generally comprises the steps of applying one or several layers of the prepreg to a metal surface then followed by the application of pressure and temperature (if necessary). Method 2

5 generally comprises the steps of applying one or several layers of the prepreg to a mandrel with a release agent applied to the mandrel of any shape, but preferably round, and then overwinding this structure with fiberglass and resin to form a composite bearing.

10 Method 3 generally comprises the steps of applying one or several layers of the prepreg to a mandrel with a release agent applied to the mandrel of any shape, but preferably round, and then overmolding with a thermoplastic or an elastomer to form bearings.

15 Further, it is surprising and unexpected that a saturable nonwoven structure comprising fluoropolymer fibers and the other additional wettable structural organic fibers can provide the same level of expected performance or improved performance and the same

20 expected work life or improved work life of self-lubricating bearings as a woven or knitted fabric.

The term "floc", as used herein, means fibers that are cut to a short length and which are customarily used in the preparation of wet-laid sheets.

25 The fluoropolymer floc has a length of from about 3 to about 30 millimeters. A preferred length is from about 5 to about 13 millimeters. Fluoropolymer floc is made by cutting continuous fluoropolymer fibers of poly(tetrafluoroethylene) (PTFE) produced using paste extrusion or matrix spinning. Examples of fluoropolymer fibers include, but are not limited to,

30 poly(tetrafluoroethylene-co-hexafluoropropylene (FEP), poly(tetrafluoroethylene-co-perfluoro(alkoxy vinyl ether)) (PFA), modified poly(ethylene-co-

tetrafluoroethylene) (ETFE), poly(vinylidene fluoride) (PVDF), poly(chlorotrifluoroethylene) (PCTFE) and other fibers made of perfluorinated polymers.

However, matrix spun PTFE fibers are preferred, such as

5 those prepared by dispersion spinning, dry spinning, wet spinning, and melt spinning. Additionally different types of strong and thermostable floc can be used as wettable structural organic floc including, but not limited to polyester, rayon, aramid, cellulose, 10 polyamide, polyolefin, wool, cotton and combinations thereof. The wettable structural organic floc has a length of from about 2 to about 30 millimeters.

Wettable structural organic fibers have less potential for negative health effects during both processing and

15 final usage when compared with structural inorganic fibers. Generally, structural inorganic fibers are more hazardous if inhaled or precipitated on the skin or eyes. Additionally, incorporation of structural inorganic fibers in the nonwoven structure of the

20 present invention greatly restricts the ability to obtain a uniform distribution of the fluoropolymer floc, additional wettable structural floc and the optional binder. Further, use of structural inorganic fibers restricts the ability to obtain a light and thin

25 liner because such fibers do not provide the requisite level of integrity and strength to the nonwoven structure. Aramid floc is preferred due to its high thermal stability, dimensional stability and high strength. Aramid floc is made by cutting continuous

30 aramid fibers. The present invention will be described in terms of using aramid floc. However, the other above-noted types of structural floc could be substituted therefore and still be within the scope of the invention.

The term "aramid fiber", as used herein, means aromatic polyamide fiber, wherein at least 85% of the amide (-CONH-) linkages are attached directly to two aromatic rings.

5 Optionally, additives can be used with the aramid and dispersed throughout the polyfiber structure. It has been found that up to as much as about 10 percent by weight of other polymeric material can be blended with the aramid. It has also been found
10 that copolymers can be used having as much as about 10 percent of other diamines substituted for the diamine of the aramid or as much as about 10 percent of other diacid chlorides substituted for the diacid chloride of the aramid.

15 Different types of binders can be used in the manufacturing of the saturable nonwoven material by wet-laid (papermaking) techniques. Aramid fibrils are the preferred type of the binder due to their thermal stability, high binding ability and their action as an
20 aid for better dispersion in water of hydrophobic fluoropolymer floc. The binder may also comprise a mixture of at least one aramid fiber and a wet-strength resin. However, other binders known to those
25 practitioners skilled in the art can also be used, for example, water-soluble poly (vinyl alcohol) fibers, poly (vinyl acetate) dispersions, fluoropolymer dispersions, and different types of pulps including cellulose.

30 The term "fibrils", as used herein, means very small, nongranular, fibrous or film-like particles with at least one of their three dimensions being of minor magnitude relative to the largest dimension. These particles are prepared by precipitation of a solution of polymeric material using a non-solvent

under high shear. The term "aramid fibrids", as used herein, means non-granular film-like particles of aromatic polyamide having a melting point or decomposition point above 320°C. The fibrids have an 5 largest dimension length in the range of about 0.2mm to about 1mm with a length-to-width aspect ratio of about 5:1 to about 10:1. The thickness dimension is on the order of a fraction of a micron, for example, about 0.1mm to about 1.0 microns. Use of such aramid fibrids 10 in a never-dried state, while not required, is preferred. The fibrids can be deposited as a binder physically entwined about the aramid floc component of a paper.

In addition to aromatic polyamide, aramid 15 fibrids can optionally comprise dyes, pigments, additives such as antistatic agents, surfactants, or fillers such as carbon black, silica and titanium dioxide.

The present invention is further directed to 20 a saturable nonwoven material or a saturable sheet structure comprising a blend of fluoropolymer floc and one or more wettable structural organic floc. The composition of the nonwoven material can optionally include up to about 30% by weight of a binder, wherein 25 a fibrous binder or fibrid binder is preferred.

The saturable nonwoven material of the present invention can be made by any conventional process for wet-lay or dry-lay forming a nonwoven sheet. An example of such a process for making the 30 sheet of the invention is one that includes the steps of:

- a) delivering an aqueous dispersion of a mixture of fluoropolymer floc, other wettable structural organic floc and

optionally a binder onto a screen in a papermaking device;

- b) withdrawing water from the aqueous dispersion to leave a wet nonwoven felt;
- 5 c) drying the wet nonwoven felt; and
- d) optionally, calendaring the formed and dried nonwoven material of the present invention, thereby increasing its density and strength.

10 The saturable nonwoven material of this invention relates to a fine liner. This liner allows for a broad range of thicknesses, including a thickness below 0.127mm. Preferably the liner has a thickness in the range of about 0.02 to about 5.0 mm and most preferably in the range of about 0.05 to about 2.0 mm. Additionally the present invention relates to a self-lubricated bearing made with the liner. It is expected that the thin structures of the present invention will ensure for greater load bearing capacity, lower clearances, higher stiffness and facilitated heat transfer in the bearing. Furthermore, the use of thermally conductive fibers increase the thermal conductivity of the liner and increases thus the operating speed range of the bearing.

25

TEST METHODS

The following test methods were used in the Examples provided below. The tensile strength of nonwoven materials of the present invention was 30 measured on an Instron-type testing machine using test specimens 2.54 cm wide and a gage length of 18 cm, in accordance with ASTM D 828-93.

The thickness and basis weight of saturable nonwoven materials were determined by measuring the

thickness and the weight of an area of a sample of the test nonwoven sheet in accordance with ASTM D 645/D 645-M-96 and ASTM D 646-96, respectively.

The friction performance of model flat 5 bearing surfaces was tested on a High-Frequency, Linear-Oscillation (SRV) Test Machine from Optimol GmbH (ASTM D5707-97) at the Swiss Federal Laboratories for Materials Testing and Research - EMPA. Various samples of impregnated non-woven sheets have been produced and 10 applied onto steel substrates using epoxy type resins.

Linearly reciprocating Ball-on-Flat sample sliding tests were conducted on these samples in addition to samples made with a standard woven fluoropolymer liner (reference) under the following 15 conditions:

Test parameters:

20	Type of contact:	Ball on disc
	Ball diameter:	10 mm
	Ball material:	100Cr6 steel
	Vertical load:	stepwise 50, 100, 150 N
25	Amplitude:	+/- 2mm
	Frequency:	13.3 Hz
	Number of cycles:	96'000
	Temperature:	25°C
	Relative Humidity:	55 +/- 5 0%

The test results show that the friction 30 coefficients measured with the saturable nonwoven sheets of this invention (Example 1) lay at or below the values measured on the standard woven liner (Comparative Example 3). The wear rate in saturable nonwoven structures of this invention (Example 1), as 35 measured by the interface position between ball and sample, is less than the wear rate measured on standard woven liners (Comparative Example 3) or on nonwoven

structures without additional structural fiber
(Comparative Example 2).

EXAMPLES

5

Example 1

An aqueous dispersion containing mixture of
fluoropolymer floc, meta-aramid floc, meta-aramid
10 fibrils and wet-strength resin was made at such
relative content of non-aqueous components (percents by
weight) as follows:

Fluoropolymer floc about 45.5%,
Meta-aramid floc about 36.4%,
15 Meta-aramid fibrils about 9.1%, and
Wet-strength resin about 9.0%.

The dispersions were poured into an
approximately 21 cm x 21 cm handsheet mold and a wet-
laid sheet was formed. The sheet was placed between two
20 pieces of blotting paper, hand couched with a rolling
pin, and dried in a hand sheet dryer at about 190°C.

The fluoropolymer floc was
polytetrafluoroethylene floc of linear density 0.71
tex and length 0.67 cm (sold by E. I. du Pont de
25 Nemours and Company under trade name TEFLON® floc).

The meta-aramid fibrils were made from
poly(metaphenylene isophthalamide) as described in U.S.
Pat. 3,756,908.

The meta-aramid floc was poly(metaphenylene
30 isophthalamide) floc of linear density 0.22 tex and
length of 0.64 cm (sold by E. I. du Pont de Nemours and
Company under the trade name NOMEX® floc).

The wet-strength resin was KYMENE® 557 LX
resin (sold by Hercules Chemical Company).

The properties of the final nonwoven material are shown in Table 1.

The prepared nonwoven material was wetted with room temperature curing epoxy composition 5 including, but not limited to, Scotch-Weld DP-460 epoxy adhesive (sold by the 3M Company) and squeezed between flat metal surface and metal roll. Produced prepreg was attached to the plate from stainless steel and pressed against the plate. After curing for 12 hours, a model 10 self-lubricating bearing was ready.

The model bearing was tested on a friction performance at different levels of loading. The results of the test are shown in Table 2.

15 **Example 2 (Comparative Example)**

An aqueous dispersion containing a mixture of fluoropolymer floc and meta-aramid fibrils was made at such relative content of non-aqueous components (percents by weight) as follows:

20 Fluoropolymer floc at about 91.0%, and
Meta-aramid fibrils at about 9.0%.

A wet-laid handsheet was prepared as in Example 1, but with additional hot compression at about 300°C and about 30 psi for about 5 minutes.

25 The fluoropolymer floc was a mixture of about 8 percent by weight of polytetrafluoroethylene floc having a linear density of about 0.71 tex and a length of about 0.67 cm and about 12% by weight of PFA floc having a linear density of about 1.10 tex and a length 30 of about 0.67 cm (sold by E. I. du Pont de Nemours and Company under trade name TEFLON® floc).

The meta-aramid fibrils were made from poly(metaphenylene isophthalamide) as described in U.S. Pat. 3,756,908.

The properties of the final nonwoven material are shown in Table 1.

A model self-lubricating bearing was prepared and tested as in Example 1.

5 Results of the friction test are shown in Table 2.

Example 3 (Comparative Example)

10 DACRON®/TEFLON® bearing fabric, a plane weave based on TEFLON® and DACRON continuous filament yarns having a linear density of 44 tex each (sold by Bally Ribbon Mills), was impregnated by epoxy resin as in Example 1 and a model self-lubricating bearing was prepared by the same technique.

15 Results of the friction test are shown in Table 2.

Example 4 (Comparative Example)

20 An aqueous dispersion containing mixture of fluoropolymer floc, meta-aramid floc, meta-aramid fibrils and wet-strength resin was made at such relative content of non-aqueous components (percents by weight) as follows:

25 Fluoropolymer floc 45.5%,
Meta-aramid floc 24.5%,
Meta-aramid fibrils 20.0%, and
Wet-strength resin 10.0%.

30 A sheet of nonwoven material was prepared as in example 1 and all components of the composition were the same as in Example 1. Properties of the nonwoven material are shown in Table 1.

 During preparation of the prepreg it was impossible to achieve full wetting of the nonwoven

sheet with a resin due to a high content of the binder in the formed sheet.

Table 1

5

Example	Basis weight g/m ²	Thickness mm
1	90	0.28
2	130	0.37
3	240	0.38
4	90	0.26

10

Table 2

Example	Coefficient of friction at loading 25-30 N	Coefficient of friction at loading 100-150 N	Wear after 800 min loading at 100N (mkm)
1	0.18	0.20	45
2	0.22	0.22	110
3	0.22	0.25	100

WHAT IS CLAIMED IS:

1. A saturable nonwoven material comprising a mixture dispersed therein of at least one fluoropolymer floc; and at least one wettable structural organic floc.
2. The saturable nonwoven material according to claim 1, further comprising a binder wherein the binder is up to about 30% by weight of the saturable nonwoven material.
3. The saturable nonwoven material of claim 1, wherein the fluoropolymer floc is at least about 30% by weight of the mixture.
4. The saturable nonwoven material of claim 1, wherein the fluoropolymer floc comprises at least one perfluoronated polymer.
5. The saturable nonwoven material of claim 2, wherein the binder comprises at least one fibrous material.
6. The saturable nonwoven material of claim 2, wherein the binder comprises at least one aramid fibrid.
7. The saturable nonwoven material of claim 2, wherein the binder comprises a mixture of at least one aramid fibrid and a resin.
8. A prepreg comprising the saturable nonwoven material of claim 1 and a matrix resin.
9. A self-lubricating bearing comprising the saturable nonwoven material of claim 1.

10. A saturable nonwoven material comprising a mixture dispersed therein of about 40% to about 60% by weight of a fluoropolymer floc; and about 10% to about 40% by weight of a wettable structural organic floc.

11. The saturable nonwoven material according to claim 10, further comprising about 10% to about 20% by weight of a binder.

12. A saturable nonwoven material comprising a mixture dispersed therein of about 40% to about 60% by weight of a fluoropolymer floc; and about 60% to about 40% by weight of a meta-aramid floc.

13. A saturable nonwoven material comprising a mixture dispersed therein of about 45% by weight of a fluoropolymer floc; about 36% by weight of a meta-aramid floc; about 10% by weight of a meta-aramid fibrid; and about 9% of a resin.

14. A process for making the saturable nonwoven material of claim 1 comprising the steps of:

a.) delivering an aqueous dispersion of a mixture comprising wettable structural organic floc, fluoropolymer floc and optionally a binder onto a screen of a papermaking device;

b.) withdrawing water from the aqueous dispersion to leave a wet paper felt; and

c.) drying the wet paper felt.

15. The process according to claim 14, further comprising calendering the dried nonwoven material for further densification of the material.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 02/22580

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 D21H13/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 D21H D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 011 118 A (YAMABAYASHI TOSHIHARU ET AL) 4 January 2000 (2000-01-04) column 6, line 20-29; claims 1-11; examples 1-8 ---	1-3, 10, 12, 14
X	US 4 886 578 A (PROVOST RICHARD L ET AL) 12 December 1989 (1989-12-12) claims 1-8 ---	1, 2, 10, 12-14
X	US 5 688 370 A (HAGEN DONALD F ET AL) 18 November 1997 (1997-11-18) claims 1-26 --- -/-	1, 2, 14

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority, claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

26 September 2002

Date of mailing of the international search report

04/10/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Karlsson, L

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 02/22580

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 07, 31 March 1999 (1999-03-31) & JP 02 015509 A (E I DU PONT DE NEMOURS & CO), 19 January 1990 (1990-01-19) abstract ---	1,14
X	EP 1 030 543 A (MATSUSHITA ELECTRIC IND CO LTD) 23 August 2000 (2000-08-23) claims 1-16 ---	1,8
X	US 5 954 962 A (ADILETTA JOSEPH G) 21 September 1999 (1999-09-21) claims 1-32 ---	1
A	US 5 194 484 A (LOGOTHETIS ANESTIS L) 16 March 1993 (1993-03-16) the whole document ---	1-14
A	WO 96 29146 A (MINNESOTA MINING & MFG) 26 September 1996 (1996-09-26) the whole document ---	1-14
A	US 3 756 908 A (GROSS G) 4 September 1973 (1973-09-04) the whole document ---	1-14
A	US 4 361 619 A (FORSTEN HERMAN H ET AL) 30 November 1982 (1982-11-30) the whole document -----	1-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/22580

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 6011118	A	04-01-2000		AT 199385 T CA 2227976 A1 DE 69611915 D1 DE 69611915 T2 WO 9706204 A1 EP 0842214 A1 JP 9188767 A	15-03-2001 20-02-1997 05-04-2001 27-09-2001 20-02-1997 20-05-1998 22-07-1997
US 4886578	A	12-12-1989		JP 2015509 A JP 2665537 B2	19-01-1990 22-10-1997
US 5688370	A	18-11-1997		CA 2177983 A1 DE 69412286 D1 DE 69412286 T2 EP 0735920 A1 JP 9507786 T WO 9517247 A1 US 5702610 A	29-06-1995 10-09-1998 03-12-1998 09-10-1996 12-08-1997 29-06-1995 30-12-1997
JP 02015509	A	19-01-1990		JP 2665537 B2 US 4886578 A	22-10-1997 12-12-1989
EP 1030543	A	23-08-2000		JP 2000239995 A EP 1030543 A1	05-09-2000 23-08-2000
US 5954962	A	21-09-1999		US 5709798 A DE 69602443 D1 DE 69602443 T2 EP 0833971 A2 JP 11507997 T WO 9700347 A2	20-01-1998 17-06-1999 05-01-2000 08-04-1998 13-07-1999 03-01-1997
US 5194484	A	16-03-1993		DE 69230436 D1 DE 69230436 T2 EP 0605577 A1 ES 2141726 T3 JP 6511029 T WO 9306156 A1	20-01-2000 15-06-2000 13-07-1994 01-04-2000 08-12-1994 01-04-1993
WO 9629146	A	26-09-1996		EP 0927281 A1 WO 9629146 A1 WO 9812385 A1	07-07-1999 26-09-1996 26-03-1998
US 3756908	A	04-09-1973		DE 2209076 A1 FR 2127801 A5 GB 1336691 A	07-09-1972 13-10-1972 07-11-1973
US 4361619	A	30-11-1982		CA 1166169 A1 DE 3272694 D1 EP 0066414 A2 JP 1607317 C JP 2014456 B JP 57205566 A JP 1619753 C JP 2036704 B JP 61160466 A JP 2191755 A KR 8800384 B1	24-04-1984 25-09-1986 08-12-1982 13-06-1991 09-04-1990 16-12-1982 30-09-1991 20-08-1990 21-07-1986 27-07-1990 20-03-1988