



HU000025085T2

(19) **HU****MAGYARORSZÁG**
Szellemi Tulajdon Nemzeti Hivatala(11) Lajstromszám: **E 025 085**(13) **T2**

EURÓPAI SZABADALOM SZÖVEGÉNEK FORDÍTÁSA

(21) Magyar ügyszám: **E 10 718369**(22) A bejelentés napja: **2010. 04. 29.**(51) Int. Cl.: **C08F 8/22** (2006.01)**C07C 17/12** (2006.01)**C08F 112/08** (2006.01)

(96) Az európai bejelentés bejelentési száma:

EP 20100718369

(97) Az európai bejelentés közzétételi adatai:

EP 2424904 A1 **2010. 11. 04.**

(86) A nemzetközi (PCT) bejelentési szám:

PCT/US 10/032937

(97) Az európai szabadalom megadásának meghirdetési adatai:

EP 2424904 B1 **2015. 01. 07.**

(87) A nemzetközi közzétételi szám:

WO 10127091

(30) Elsőbbségi adatok:

174902 P **2009. 05. 01.** **US**

(73) Jogosult(ak):

Albemarle Corporation, Baton Rouge, LA
70801-1765 (US)

(72) Feltaláló(k):

LAYMAN, William, J. Jr., Baton Rouge LA 70816 (US)**GE, Zhongxin, Baton Rouge LA 70816 (US)****MACK, Arthur, G., Prairieville LA 70769 (US)****CHENG, Chi, Hung, Baton Rouge, LA 70809 (US)****COLONIUS, Neal, J., Baton Rouge LA 70817 (US)****JONES, Sarah, C., Baton Rouge LA 70802 (US)****ANDERSON, Steven, A., Baton Rouge, LA 70808 (US)**

(74) Képviselő:

Lezsák Gábor, Danubia Szabadalmi és Jogi
Iroda Kft., Budapest

(54)

Alacsony molekulatömegű aromás polimer készítmények brómozása

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 424 904 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
07.01.2015 Bulletin 2015/02

(51) Int Cl.:
C08F 8/22 ^(2006.01) **C07C 17/12** ^(2006.01)
C08F 112/08 ^(2006.01)

(21) Application number: **10718369.1**

(86) International application number:
PCT/US2010/032937

(22) Date of filing: **29.04.2010**

(87) International publication number:
WO 2010/127091 (04.11.2010 Gazette 2010/44)

(54) **BROMINATION OF LOW MOLECULAR WEIGHT AROMATIC POLYMER COMPOSITIONS**

BROMIERUNG VON ZUSAMMENSETZUNGEN NIEDERMOLEKULARER AROMATISCHER
POLYMERE

BROMATION DE COMPOSITIONS DE POLYMÈRES AROMATIQUES DE FAIBLE MASSE
MOLECULAIRE

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL
PT RO SE SI SK SM TR**

(30) Priority: **01.05.2009 US 174902 P**

(43) Date of publication of application:
07.03.2012 Bulletin 2012/10

(73) Proprietor: **Albemarle Corporation**
Baton Rouge, LA 70801-1765 (US)

(72) Inventors:
• **LAYMAN, William, J. Jr.**
Baton Rouge
LA 70816 (US)
• **GE, Zhongxin**
Baton Rouge
LA 70816 (US)
• **MACK, Arthur, G.**
Prairieville
LA 70769 (US)

- **CHENG, Chi, Hung**
Baton Rouge,
LA 70809 (US)
- **COLONIUS, Neal, J.**
Baton Rouge
LA 70817 (US)
- **JONES, Sarah, C.**
Baton Rouge
LA 70802 (US)
- **ANDERSON, Steven, A.**
Baton Rouge,
LA 70808 (US)

(74) Representative: **UEXKÜLL & STOLBERG**
Patentanwälte
Beselerstrasse 4
22607 Hamburg (DE)

(56) References cited:
WO-A1-2007/005233 WO-A1-2008/154453
US-A- 5 677 390 US-A1- 2007 004 870
US-A1- 2007 142 566


Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 424 904 B1

Description

BACKGROUND

- 5 [0001] A new highly-effective class of low molecular weight brominated aromatic polymer compositions has recently been discovered in our laboratories. These compositions have the formula:



- 10 wherein n is an average number in the range of 2.9 to 3.9, wherein each x is the same or different and is a whole number in the range of 3 to 5, the average number of all of the x's in the composition being in the range of 3.50 to 3.80 and the weight percent of bromine as determined by X-Ray Fluorescence Spectroscopy (XRF) in the polymer being in the range of 73.4 to 74.5. A detailed description of these new brominated aromatic polymer compositions and their preparation and uses is presented in commonly-owned Provisional U.S. Patent Application No. 61/119,289, filed December 2, 2008.

- 15 [0002] WO 2007/005233 A1 discloses a process of preparing brominated styrenic polymer, which process comprises maintaining a reaction mixture formed from (i) a brominating agent, (ii) a solution of styrenic polymer in a solvent, and (iii) aluminum halide catalyst in which the halogen atoms are bromine or chlorine with at least one such halogen atom being a bromine atom, at one or more temperatures in the range of -20 to +20°C so that bromination of polymer occurs, and terminating the bromination of polymer in such reaction mixture in a bromination time of 20 minutes or less.


- 20 [0003] US 2007/142566 discloses a process of preparing brominated anionic styrenic polymer having a reduced volatile bromobenzene content, which process comprises: A) concurrently feeding into a reaction zone components comprised of (i) a brominating agent, (ii) aluminum halide catalyst in which the halide atoms are bromine or chlorine or both, and (iii) anionic styrenic polymer having a GPC number average molecular weight in the range of 2,000 to 30,000 in the form of a solution or slurry in a solvent to form a reaction mixture, wherein said components are fed (1) individually as at least three separate feeds or (2) as at least two separate feeds, one feed of which contains no more than two of (i), (ii), and (iii), and another feed of which contains the third of (i), (ii), (iii) either individually or in combination with no more than one other of (i), (ii), and (iii), to thereby form a reaction mixture containing a liquid phase, and maintaining said reaction mixture at 10°C or less whereby bromination of anionic styrenic polymer occurs, the components being proportioned such that the amount of aluminum halide being fed is at 0.8 mole percent or less in relation to the molar amount of aromatic monomer units in the anionic styrenic polymer being fed, and such that the dried brominated anionic styrenic polymer referred to in C) hereinafter will have a bromine content in the range of 60 to 71 wt%; B) deactivating the catalyst in, and washing away bromide ions and catalyst residues from 1) substantially the entire reaction mixture or 2) portions of the reaction mixture that have exited from the reaction zone; and C) recovering brominated anionic styrenic polymer product from the reaction mixture and drying such product whereby the dried brominated anionic styrenic polymer has a bromine content in the range of 60 to 71 wt% and a volatile bromobenzene content which is no more than 600 ppm (wt/wt).

- 30 [0004] The process technology described in the foregoing Provisional Patent Application yields products having a combination of desirable properties. Nevertheless, it would be of advantage if still further improvements in the process technology could be found whereby the process would be even more efficient in terms of utilization of articles of commerce and reduced product quality sensitivity to recycle streams, in particular recycled bromination solvents. Additionally, it would be of advantage if these process improvements could be achieved without sacrifice of key flame retardant characteristics such as initial solution color, Hunter Color Yellowness Index, thermal color stability, and minimal thermal HBr content. Indeed, it would be of considerable advantage if one or more of these properties could be enhanced while achieving the foregoing further improvements in process technology.

- 45 [0005] This invention is deemed to have achieved most, if not all, of these objectives in a highly efficient and effective manner.

BRIEF NON-LIMITING SUMMARY OF THE INVENTION

- 50 [0006] This invention provides, among other things, a process which comprises brominating an aromatic polymer composition of the formula:



(I)

wherein n is an average number in the range of 2.5 to 8 with the proviso that 1,3-diphenylpropane, a compound of formula (I) in which n is 0, optionally is present in this aromatic polymer composition in an amount of not more than 1 GPC area %, and with the further proviso that this aromatic polymer composition optionally further contains toluene in an amount of not more than 0.1 GPC area %, to form a brominated aromatic polymer composition having a bromine content as determined by XRF in the range of 70 to 76 weight percent, which process comprises brominating said aromatic polymer composition with liquid bromine in the presence of an aluminum halide bromination catalyst and in the absence of light, at a bromination temperature in the range of -10°C to $+5^{\circ}\text{C}$, and in which the molar ratio of total amount of bromine fed:total amount of catalyst fed is in the range of 200:1 to 500:1, which process is further characterized in that:

- a) the total amount of said catalyst is charged into a reactor which is at a temperature in the range of -25°C to 0°C , said reactor containing an inert atmosphere and a portion of bromination solvent such that the initial weight percentage of said catalyst expressed as aluminum is in the range of 0.02 wt% to 0.04 wt%;
- b) within 2 hours after completing the charge of the catalyst, separate concurrent feeds of (i) bromine, and (ii) a solution of said aromatic polymer composition in the bromination solvent are initiated, said feeds being conducted such that said solution and the liquid bromine are fed to maintain a substantially constant molar ratio of aromatic polymer composition to bromine entering the reactor; and
- c) wherein on completion of the feeds and an optional ride time of no greater than 60 minutes, the weight percentage of aluminum relative to the total of the mass of the bromination solvent and the brominated aromatic polymer composition in the reactor is greater than 0.015 wt%.

[0007] Desirably, 1,3-diphenylpropane is present in the above aromatic polymer composition in an amount in the range of not more than 1 GPC area %, or toluene is present in the above aromatic polymer composition in an amount of not more than 0.1 GPC area %, or both of 1,3-diphenylpropane and toluene are present in the above aromatic polymer composition in the amounts specified


[0008] Other important features and advantages of this invention will be still further apparent from the ensuing description, accompanying drawing, and appended claims.

BRIEF DESCRIPTION OF THE FIGURES OF THE DRAWING

[0009] FIG. 1 is a plot of two sets of thermal color measurements of brominated aromatic polymer compositions made using different aluminum catalyst concentrations, wherein these respective data sets were obtained at two different temperatures.

FURTHER DETAILED DESCRIPTION OF THE INVENTION

[0010] The brominated aromatic polymer compositions formed by the processes of this invention can be represented by the following formula:



(II)

wherein n is an average number in the range of 2.5 to 8 (desirably in the range of 2.9 to 3.9, and which when rounded off to whole numbers, becomes an average number in the range of 3 to 4), wherein each x is the same or different and is a whole number in the range of 3 to 5, the average number of all of the x 's in the composition being in the range of 3.0 to 3.8 (desirably in the range of 3.5 to 3.8) and the weight percent of bromine as determined by X-Ray Fluorescence Spectroscopy (XRF) in the polymer being in the range of 70 to 76 (desirably in the range of 73.4 to 74.5).

[0011] Available experimental results indicate that these brominated aromatic polymer compositions provide especially desirable results when produced by bromination, pursuant to this invention, of aromatic polymer compositions of formula (I) as described above, in which n is an average number in the range of 2.9 to 3.9, and which when rounded off to whole numbers, becomes an average number in the range of 3 to 4, and in which additionally, the aromatic polymer composition is further characterized by having an M_w in the range of 650 to 750, an M_n in the range of 500 to 600, an M_z in the range of 830 to 1120, and a polydispersity in the range of 1.2 to 1.35, particularly when in the bromination process of this invention, the solution of the aromatic polymer composition in the bromination solvent is passed through a solid absorbent to remove polar amine impurities prior to being fed into the reaction mass in a manner described herein.

[0012] For convenience, the substrates used in the bromination processes of this invention, namely, the aromatic polymer compositions, are often referred to in the singular as "APC" and in the plural as "APC's". Similarly, the brominated aromatic polymer compositions formed in the processes of this invention are often referred to in the singular as "BAPC" and in the plural as "BAPC's".

[0013] As regards bromination of polymeric aromatic compounds derived from styrene, it is generally understood that a key process parameter is the molar ratio of aluminum halide catalyst to the total amount of bromine charged during the bromination process. It has now been found, quite unexpectedly, that there are other key process parameters which can exert a profound influence upon the quality of the BAPC's formed in the practice of this invention. Unlike higher molecular weight styrene-derived polymers, which have high viscosities that limit the concentrations in which they can be fed to a reaction mass, the APC's used as substrates in the bromination processes of this invention do not suffer from these viscosity limitations. Consequently, in the development of this invention, it was surprisingly found that additional modes of operations exist that provide BAPC's of superior properties.

[0014] More particularly, it has been found that initial color of the BAPC as well as its thermal color performance and other thermal properties, including thermal HBr evolution, are greatly influenced by the catalyst concentration in the reaction mass throughout the course of the bromination reaction. An important trend that was unexpectedly discovered was that at higher catalyst concentrations significant improvements in these color properties were obtained.

[0015] Thus, a key feature of the bromination processes of this invention is the manner in which the three reagents involved in the bromination reaction (the APC, the bromine, and the bromination catalyst) are brought together and maintained throughout the course of the reaction. By bringing those reagents together in balanced proportions discovered in the development of this invention, there is provided a kinetic regime that provides a superior BAPC product.

[0016] By judicious, previously uncharted selection of the concentration of the APC in the bromination solvent, and the initial concentration of the bromination catalyst in the bromination solvent charged to the reactor, it was found that one can operate the bromination process such that the catalyst concentration varies little during the course of the bromination, despite the fact that the reaction mass is constantly increasing as a result of the substances being brought into the reactor. This has been proven to be a superior mode of operation for use in the practice of this invention.

[0017] Hence, unless a suitable relationship among the concentrations of the APC and the catalyst in the bromination solvent is utilized during the process, a process condition can be reached in which catalyst concentration varies significantly over the course of the bromination. Such variations in catalyst concentrations lead to undesired side products when catalyst concentrations are high and can lead to undesired thermal and color properties when catalyst concentrations are low. If both of these conditions are experienced during the bromination, *i.e.*, variance during the bromination from high to low catalyst concentrations during the bromination, a particularly deleterious impact on product purity, quality, and performance is experienced. An example of such would be a very dilute APC feed with a consequent very high initial catalyst concentration -- a condition commonly utilized in bromination reactions involving high molecular weight substrates -- whereby during the course of the bromination, the catalyst concentration is decreased significantly.

[0018] Additionally, if concentrations of the APC and the initial concentration of the bromination catalyst in the bromination solvent are both too high such that a relatively constant, high catalyst concentration exists throughout the course of most, if not all, of the bromination, then the result is undesired cleavage of the APC leading to undesirable impurity content. Conversely, if concentrations of the APC and the initial concentration of the bromination catalyst in the bromination solvent are both too low such that a relatively constant, low catalyst concentration exists throughout the course of most, if not all, of the bromination, then the result is formation of a BAPC having undesired initial color, thermal color, and thermal properties.

[0019] As noted above, one important feature of this invention was the unexpected discovery of a trend that at higher catalyst concentrations significant improvements in a number of color and stability properties were obtained. This trend is depicted in FIG. 1. The data points shown in FIG. 1 were developed in two sets of thermal treatments of BAPC samples produced using samples of BAPC materials individually produced in 14 experimental pilot plant runs. These pilot plant

runs were conducted under generally similar reaction conditions with minor variations which are the consequence of the different sizes of the volume of the APC feed relative to the volume of the initial reactor charge of catalyst and bromination solvent. As shown, these data points show the relationship between (i) the solution color of each of the thermally treated BAPC's and (ii) the average aluminum catalyst concentration utilized in each of the corresponding 14 runs. The upper trend line relates to the data obtained at 300°C thermal treatment of the BAPC samples. The lower trend line relates to the data obtained at 250°C thermal treatment of the BAPC samples. The details of these thermal treatments are set forth hereinafter in connection with analytical methods used. In both data sets the experimental results demonstrate that a functional dependence of increased thermal color stability with increased catalyst concentration used in the preparation of the BAPC. From the data presented in FIG. 1, it can be seen that to achieve superior color and superior thermal stability properties, it is best to operate the bromination process such that on average the catalyst weight percentage should be maintained above a threshold level. As one of skill in this art will now appreciate, one should not operate with a catalyst weight percentage that is high enough to cause undesirable degradation of the APC used and/or the BAPC formed. Such degradations have been experienced at aluminum halide catalyst levels in runs in which the initial catalyst loading was as low as 0.2 wt% aluminum chloride in bromochloromethane (BCM) which corresponds to initial 0.04 wt% charge of aluminum halide catalyst, expressed as aluminum. Therefore, pursuant to this invention, the initial weight percentage of the aluminum halide catalyst expressed as aluminum is in the range of 0.02 wt% to 0.04 wt%, and on completion of the feeds and an optional ride time of no greater than 60 minutes, the weight percentage of aluminum relative to the total of the mass of the bromination solvent and the brominated aromatic polymer composition in the reactor is greater than 0.015 wt%.

[0020] In conducting the bromination processes of this invention, the separate concurrent feeds of bromine and a solution of APC are initiated within 2 hours after completing the charge of the catalyst. Typically, this time period can be one hour or less. On a laboratory scale, this time period can be as short as 30 minutes or less. It is important that the slurry of catalyst in bromination solvent has cooled to the desired initial bromination reaction temperature prior to initiating the feeds. Extended periods of contact of the catalyst in the bromination reaction, *i.e.*, greater than 2 hours prior to initiation of bromination, has resulted in BAPC products having inferior properties.

[0021] The catalysts used in the processes of this invention are typically aluminum halide catalysts. Of these, aluminum chloride is most desirable for use in the present processes because of its low cost and ready availability. One skilled in the art would understand that upon entering the reaction mass, the aluminum chloride will undergo halogen exchange reaction leading to complex mixtures of aluminum halides containing bromine atoms with and/or without chlorine atoms. Use of an aluminum tribromide is deemed suitable for the process of this invention. However as it is not an item of commerce, it is a less desirable catalyst.

[0022] A variety of bromination solvents are available for use in the processes of this invention. Non-limiting examples of such solvents include methylene bromide, ethylene dibromide, methylene chloride, ethylene dichloride, propyl bromide, and similar halohydrocarbons. Bromochloromethane is a particularly desirable solvent for use in the processes of this invention. Typically, the bromination can be conducted with APC concentrations as low as 10 wt% and as high as 50 wt%, but it is desirable to utilize concentrations in the range of 20 wt% to 40 wt%.

[0023] A feature of the invention is to limit contact between BAPC product and aluminum halide catalyst in the absence of bromine. Thus, the reaction is typically conducted and quenched as soon as practical, hence, ride times of less than 1 hour, preferably less than 10 minutes, are desirable. Longer ride times provide little benefit in terms of increasing bromine content of the BAPC product and are detrimental to the properties of the BAPC product.

[0024] In conducting the bromination, it is highly desirable to ensure that the feeds of bromine and the solution of APC in bromination solvent enter the catalyst-containing reaction mixture in close proximity to each other. This is done to create locally high and balanced concentrations of APC, bromine, and the bromination catalyst. Such feeds can be impinging or non-impinging subsurface feeds. Alternatively, such feeds can be feeds that are introduced above the surface of the reaction mixture, provided that these feeds remain spaced apart until they come in contact with the surface of the reaction mass. The trajectory should be such that the loci of reaction mass surface contact are in close proximity to each other without premature contact with each other. It is understood that in certain reactor configurations the feed can be initially above the surface, but finish below the surface, based on the lengths of the diplegs, injectors, or other liquid feeding means.

[0025] Quenching of the reaction mass is typically conducted using water. However, use of aqueous solutions of hydrazine hydrate is more desirable because in addition to quenching the aluminum halide catalyst, the hydrazine hydrate reduces bromine to HBr. Such quenching shortens contact time of the BAPC with bromine and thereby provides a product with superior color and reduced thermal HBr content. Typically, dilute aqueous solutions of hydrazine hydrate in the range of 0.1 to 1 wt% are effective quenching media. Amounts outside this range can be used, if desired. In any given case, the amount used should be sufficient to ensure that all elemental bromine is consumed during the quenching operation. In as much as the bromination reaction mixture is typically saturated with HBr which is recovered for recycle, it is desirable to form an aqueous quench mixture having an HBr concentration between 20 and 26 wt%. Therefore, it is desirable to use a charge of about 0.4 part by weight of quench solution per each part by weight of BAPC contained

in the reaction mass.

[0026] Upon completion of the quenching, and after agitation of the reaction mass has been discontinued, the quenched reaction mass is isolated from the aqueous mixture by means of a phase separation. Suitable methods for effecting this phase separation include use of a simple phase cut, decantation, liquid/liquid centrifugation, or the like. After the phase separation, it is desirable to wash the resultant reaction mass one or more times with fresh water. Such operations can be conducted in a batch or continuous mode.

[0027] After the quenching and ensuing washing steps, it is beneficial to agitate the quenched bromination reaction mass with an alkaline borohydride solution to decompose polar bromoamine-derived impurities. This treatment is typically conducted at a temperature in the range of 25°C to 80°C and for a time period sufficient for the decomposition to be complete, as evidenced by decolorization of the reaction mass and breaking of any emulsion that may exist. Ordinarily, this alkaline borohydride treatment is conducted at a temperature in the range of 25°C to 64°C using a 0.3 to 1.0 wt% solution of NaBH₄ in 5% aqueous NaOH solution. If desired, other alkaline borohydrides may be employed in this operation. However, NaBH₄ is particularly desirable because of its ready availability and proven effectiveness, which results in low treatment cost. Upon completion of the treatment, agitation is interrupted and the phases are separated, being careful to remove any rag or emulsion remnants that have migrated to the aqueous organic interface. Failure to do so has resulted in incorporation of impurities in the BAPC that have been shown to lead to poor thermal color performance.

[0028] The following Examples illustrate the preparation of the APC used in the conducting a bromination process in accordance with this invention, in one case (Example 1) using fresh toluene and *N,N,N,N'*-tetramethylethylenediamine (TMEDA) and in a second case (Example 2) using a mixture of fresh toluene and TMEDA together with some recycled toluene which contains recovered and recycled TMEDA. Also shown (Example 3) is a blending operation in which wiped film evaporation is used for removing volatile components (toluene, TMEDA, and 1,3-diphenylpropane) from the APC. Bromination of the APC pursuant to the process technology of this invention is illustrated by Example 4. These Examples are presented for illustrative purposes and are not intended to limit, nor should they be interpreted as limiting, the scope of this invention to only the specific details set forth therein.

EXAMPLE 1

Preparation of an APC Substrate for Bromination

[0029] In this operation, fresh toluene as well as other fresh reactants were used. A glass-lined, 378.5 l (100-gallon) jacketed reactor equipped with an overhead condenser, submerged thermal well/thermal couple and a bottom drain valve. Temperature was maintained at a set point by controlling the temperature of the water flowing through the jacket using a steam control valve. Vigorous agitation was accomplished by means of a three-blade, retreat-curve agitator on a variable speed drive. The reactor is essentially free of all wetted PTFE parts or other polymeric fluorinated materials or elastomers.

[0030] The reactor was maintained under an inert dry N₂ atmosphere during all operations. The reactor was charged with the chain transfer agent(s) through a dip leg by means of pressure transfer from a portable tank. Alkyl lithium, additional solvents and the amine promoter (TMEDA) were all fed subsurface to the stirred chain transfer agent(s) through the same dip leg. Styrene was pressure transferred from a portable, pressure vessel by means of a metering valve through a 60.96 cm (24") cylindrical column (7.62 cm (3") dia. ≈ 2.72 kg (6 lbs.)) of 0.3 nm (3Å) mol sieves (Zeochem) and delivered as a fine stream or spray above the surface of the reaction mixture through a slit feed nozzle.

[0031] Toluene 140 pounds, (689 mol) was charged to the reactor; Karl Fischer moisture analysis indicated 7 ppm residual H₂O. Agitation began. The solvent was heated to 78°C by applying tempered water to the vessel jacket. Upon reaching the set point temperature, 2.09 kg (4.6 pounds) of TMEDA (18.0 mol), in 4.54 kg (10 pounds) of toluene (49.24 mol) was charged to the reactor through the dip leg below the surface of the agitated toluene reaction mixture. The feed line was then flushed with 9.07 kg (20 pounds) (98 mol) of anhydrous toluene. Next, 2.0 kg (4.4 lb) n-BuLi solution (23.5 wt% in cyclohexane) (7.32 mol n-BuLi) was charged through the subsurface feed line forming the characteristic bright red-orange color of TMEDA complexed benzyl lithium anion with concomitant off gassing of butane. The feed line was then flushed with 10.0 kg (22 pounds) (108 mol) of anhydrous toluene. 197.8 kg (436 lb) of styrene (99+%, 1899 mol, American Styrenics) were fed over 153 minutes. The styrene was added by means of pressure transfer from a nitrogen regulated portable tank through a metering valve at a constant feed rate of 1.29 kg (2.84 lb)/min. The reactor was allowed to ride for 5 minutes to make certain the reaction was complete.

[0032] The reaction mixture was quenched at 70°C with 37.85 l (10 gallons) of 0.75 wt% ammonium chloride solution which had been deoxygenated overnight by sparging with nitrogen gas. The reaction mixture was washed two more times with 37.85 l (10 gallons) of deoxygenated water. Phase cuts were rapid and required little settling time. Water and any rag or emulsion was removed through the bottom drain valve. A sample of the washed crude reaction mixture was analyzed by GPC (Mp: 312, M_n: 466, M_w: 673, M_z: 934, polydispersity (PD): 1.44).

[0033] The reactor was heated to atmospheric boiling point using tempered water on the vessel jacket. Steam was then applied to the reactor jacket to increase the temperature of the reactor jacket to 140°C. Cyclohexane, residual moisture and toluene boiled, condensed in the overhead condenser, and drained to a drum until a pot temperature of 135°C was observed. The reactor was cooled to 50°C. Vacuum was applied to the vessel and the reactor was heated to boiling point. Steam was then applied to the reactor jacket to increase the temperature of the reactor jacket to 140°C. Vacuum was used to decrease the reactor pressure to 4666 Pa (35 mm Hg). Cyclohexane, residual moisture and toluene boiled, condensed in the overhead condenser, and drained to a drum until a pot temperature of 135°C was observed. An aliquot was removed from the reactor for analysis via GPC (Mp: 314, M_n : 468, M_w : 676, M_z : 940, polydispersity (PD): 1.44). The reaction mass (252.7 kg (557 lbs)) was collected in a 1325 l (350-gallon) tote bin.

EXAMPLE 2

Partial Use of Recycled Toluene to Form Crude APC, a Precursor Material

for WFE Treatment

[0034] In this Example, a portion of a composite composed predominately of toluene, TMEDA, cyclohexane, and 1,3-diphenylpropane recovered from prior runs was used. Thus, this Example demonstrates use of recycled toluene as part of the total toluene charged.

[0035] Fresh toluene 18.14 kg (40 pounds), (197 mol) and 44 kg (97 lb) of recycled toluene (containing 97.1%, 42.73 kg (94.2 lb), 464 mol toluene; 1.7%, 0.73 kg (1.6 lb), 6.2 mol TMEDA; 0.3%, 0.14 kg (0.3 lb), 0.7 mol, 1,3-diphenylpropane; 0.9%, 0.41 kg (0.9 lb), 4.9 mol cyclohexane) was charged to the reactor; Karl Fischer moisture analysis indicated 7 ppm residual H₂O. Agitation began. The solvent was heated to 79° C by applying tempered water to the vessel jacket. Upon reaching the set point temperature, 1.63 kg (3.6 pounds) of fresh make-up TMEDA (12.8 mol), in 4.54 kg (10 pounds) of toluene (49.24 mol) was charged to the reactor through the dip leg below the surface of the agitated toluene reaction mixture. The feed line was then flushed with 9.07 kg (20 pounds) (99 mol) of anhydrous toluene. Next, 2 kg (4.4 lb) n-BuLi solution (23.6 wt% in cyclohexane) (7.4 mol n-BuLi) was charged through the subsurface feed line forming the characteristic bright red-orange color of TMEDA complexed benzyl lithium anion with concomitant off gassing of butane. The feed line was then flushed with 10 kg (22 pounds) (108 mol) of anhydrous toluene. 196 kg (432 lb) of styrene (99+%, 1881 mol, American Styrenics) were fed over 150 minutes. The styrene was added by means of pressure transfer from a nitrogen regulated portable tank through a metering valve at a constant feed rate of 1.31 kg (2.88 lb)/min. The reactor was allowed to ride for 5 minutes to make certain the reaction was complete.

[0036] The reaction mixture was quenched at 70°C with 37.85 l (10 gallons) of 0.75 wt% ammonium chloride solution which had been deoxygenated overnight. The reaction mixture was washed with a second 37.85 l (10 gallons) of deoxygenated water. Phase cuts were rapid and required little settling time. Water and any rag or emulsion was removed through the bottom drain valve. A sample of the washed crude reaction mixture was analyzed by GPC (Mp: 303, M_n : 462, M_w : 677, M_z : 959, PD: 1.47).

[0037] The reactor was heated to atmospheric boiling point using tempered water on the vessel jacket. Steam was then applied to the reactor jacket to increase the temperature of the reactor jacket to 140°C. Cyclohexane, residual moisture and toluene boiled, condensed in the overhead condenser, and drained to a drum until a pot temperature of 135°C was observed. The reactor was cooled to 50°C. Vacuum was applied to the vessel and the reactor was heated to boiling point. Steam was then applied to the reactor jacket to increase the temperature of the reactor jacket to 140°C. Vacuum was used to decrease the reactor pressure to 4666 Pa (35 mm Hg). Cyclohexane, residual moisture and toluene boiled, condensed in the overhead condenser, and drained to a drum until a pot temperature of 135°C was observed. An aliquot was removed from the reactor for analysis via GPC (Mp: 301, M_n : 459, M_w : 672, M_z : 950, PD: 1.46). The reaction mass (246.8 kg (544 lbs)) was collected in a 1325 l (350-gallon) tote bin.

EXAMPLE 3

Blending of Crude APC Batches and WFE Purification of the Blend to Form APC

[0038] A total of 12 all fresh runs were made following the general procedure of Example 1 above with the M_n after the vacuum strip ranging from 403 to 483 and an M_w ranging from 566 to 721. A total of 13 recycled toluene runs were made following the general procedure of Example 2 above with the M_n after the vacuum strip ranging from 404 to 463 and an M_w ranging from 568 to 688. Possible causes of these ranges are small variations in the temperature, stirring speed or feed rate. The 12 all fresh runs were combined with the 13 recycle runs and run through an industrial size wiped film evaporator (WFE), a sample was analyzed by GPC: (Mp: 413, M_n : 552, M_w : 693, M_z : 878, PD: 1.26). A 19.9 l (five-gallon) sample of the composite was stripped in the laboratory giving a very similar result: (Mp: 418, M_n : 569,

M_w : 729, M_z : 946, PD: 1.28).

EXAMPLE 4

5 Preparation of BAPC Solutions

[0039] Fourteen batches of APC's formed as in Example 3 in the form of solutions in BCM were individually brominated in a 189 l (50-gallon) glass-lined, jacketed vessel capable of using ethylene glycol for heat exchange (heating or cooling) or steam for heating. The reactor was equipped with a pitched-blade glass-lined agitator with a nitrogen seal. Both batch reactions had a target reaction feed time of about 3 hours, a target reaction temperature between -2 to 2°C with a targeted final bromine concentration of 74 ± 0.5 wt%. The bromination reaction involved separately and concurrently feeding bromine and the APC over a three hour period. The ratio of the APC to bromine was held constant and closely monitored throughout the reaction to create a final product with a specified bromine concentration. After feeding was complete, the reaction mass was held in the reactor for 45 minutes while the temperature was brought up to ~6°C. Any excess bromine in the reaction mass was quenched with water. This was followed by a water wash, and then another wash using a caustic and sodium borohydride solution at ~60°C to neutralize remaining HBr. The presence of sodium borohydride in the wash solution is deemed to break down aminic compounds present in the reaction mass that can form color bodies in the final isolated product. The reaction mass is finally washed again with water to a neutral pH.

[0040] Bromine was fed via pressure transfer from a stainless steel 18.9 l (5-gallon) milkcan lined with Teflon® PFA resin (a perfluoroalkoxy copolymer resin; DuPont), the resin being hereinafter referred to as PFA. The milkcan used is 22.8 cm (9") ID, 35.4 cm (14") tall without the liner, with a 0.56 cm (0.22") thick lining around the entire internal surface area of the can. Including the lining, the actual fill volume of the can is ~ 17.4 l (~ 4.6 gallons). The can is equipped with a 1 cm (3/8") PFA dipleg, and 3 additional 1.27 cm (1/2") ports that were used for nitrogen pressure, a PSD with holder, and venting down. A 5.06 cm (2") center port on the can had a PFA plug secured with a Nitronic 60 nut.

[0041] There were two feed diplegs used in these reactions. The first dipleg is a solid pipe of Teflon® fluoropolymer, with 2 x 0.63 cm (1/4") holes drilled through the entire length of the pipe. There is 0.63 cm (1/4") PFA tubing run from top to bottom of each of the void spaces, which are spread 1.9 cm (3/4") apart. The tubing is secured in place at each end with drilled-through pipe-to-tubing male connectors and PFA nuts/ferrules. The other dipleg is similar in shape, but has 1 cm (3/8") drilled through fittings on the top flange, with 2 x 1 cm (3/8") tubing runs extending through the void space of a hollow pipe of Teflon® fluoropolymer. The tubing connects ~ 50.6 cm (~ 20 inches) down via PFA fittings to the top of a solid mixing nozzle made of Teflon® fluoropolymer. This nozzle is screwed into threads on the inside of the pipe of Teflon® fluoropolymer, and impinges the two feeds before they enter the reactor through a 0.32 cm (1/8") hole at the bottom of the nozzle. Both diplegs are ~ 60.7 cm (~ 24") in length from the bottom flange of the dipleg, and extend into the reactor approximately 5.06 cm (2") above the tip of the agitator blades.

[0042] Catalyst was introduced to the reactor through a charge bomb composed of a 2.53 cm (1") stainless steel (SS) block valve, a 1x3.8 cm (1 1/2") SS reducer, and a 3.8 cm

[0043] (1 1/2") full port SS-lined brass block valve. The catalyst charge to the bomb was performed in a N₂ purged glove box, through the 3.8 cm (1.5") full port valve. Following the charge, a 1.26 cm (1/2") SS tee was fitted to the top of the 3.8 cm (1.5") valve to attach a pressure gauge and to charge N₂ to the bomb. The entire setup screwed onto a reducing flange on a reactor nozzle via the 2.53 cm (1") block valve.

[0044] Aqueous phase cuts were all conducted using a PFA dipleg. It was a length of 1.26 cm (1/2") PFA tubing that was straightened out, and grooved at the end to hold PFA ferrules in place. The ferrules allowed for the tubing to be pushed down and lowered into the reactor for decanting the aqueous phase, but prevented the tubing from coming out of the reactor beyond the drilled through PFA fitting and cap that held the tubing in place. The dipleg tubing ran from the reactor, straight to a box made from Plexiglas® resin that was used for sampling the aqueous material during cuts. There were deliberately no fittings between the dipleg nozzle at the reactor and this sample point to lower the risk of aqueous exposure related to additional points of failure present in the line.

[0045] Table 1 summarizes for each of batch bromination reactions 1-14 (BAPC 1-14), the components, the amounts thereof used, the catalyst weight percent loadings, and the color characteristics, thermal properties, and bromine levels of lab scale isolated smaller sample batches of the BAPC solids.

TABLE 1 (1 lb = 0.4536 kg)

BAPC Example	1	2	3	4	5	6	7
Charges							
BCM kg (lbs)	133.81 (295)	131.27 (289.4)	131.54 (290)	131.54 (290)	131.54 (290)	131.54 (290)	131.63 (290.2)
AlCl ₃ kg (lbs)	0.111 (0.245)	0.111 (0.245)	0.111 (0.245)	0.118 (0.260)	0.128 (0.282)	0.135 (0.298)	0.135 (0.298)
APC in BCM kg (lbs)	34.07 (75.1)	31.80 (70.1)	30.30 (66.8)	32.93 (72.6)	31.21 (68.8)	32.98 (72.7)	34.29 (75.6)
wt% APC	26	26	26	26	26	26	26
APC fed kg (lbs)	8.85 (19.5)	8.26 (18.2)	7.89 (17.4)	8.57 (18.9)	8.12 (17.9)	8.57 (18.9)	8.94 (19.7)
Bromine	104.0	99.7	95.9	103.8	104.1	103.9	105.4
BAPC (kg (lbs) est.)	32.43 (71.5)	30.89 (68.1)	29.62 (65.3)	32.11 (70.8)	31.70 (69.9)	32.16 (70.9)	32.84 (72.4)
Total Mass (100% HBr evolved)	366	357	355	360	359	360	362
Initial AlCl ₃ wt%	0.083%	0.085%	0.084%	0.090%	0.097%	0.103%	0.103%
Final AlCl ₃ wt% (est.)	0.067%	0.069%	0.069%	0.072%	0.079%	0.083%	0.082%
Avg. AlCl ₃ wt% (est.)	0.075%	0.077%	0.077%	0.081%	0.088%	0.093%	0.092%
Hunter Color YI	4.78	4.58	4.44	13.62	4.24	5.39	4.27

Results							
Solution Color (Delta E)	1.82	1.60	1.57	3.44	1.27	1.79	1.64
Thermal color 250 °C	11.83	12.94	13.69	13.75	10.40	10.15	11.35
Thermal color 300 °C	22.45	22.73	22.72	19.52	19.15	19.93	20.48
Thermal HBr (ppm)	167	106	110	171	118	198	139
T _g (°C)	117.34	122.42	132.77	107.05	120.88	115.93	125.48
Wt% Br	73.6	74.2	75.1	72.5	73.9	73.6	74.4

TABLE 1 Continued

BAPC Example	8	9	10	11	12	13	14
Charges							
BCM kg (lbs)	131.63 (290.2)	102.06 (225)	102.06 (225)	102.60 (226.2)	97.52 (215)	102.06 (225)	102.06 (225)
AlCl ₃ kg (lbs)	0.133 (0.293)	0.131 (0.289)	0.132 (0.291)	0.1315 (0.290)	0.1315 (0.290)	0.1334 (0.294)	0.1334 (0.294)
APC in BCM kg (lbs)	35.38 (78)	32.53 (71.7)	32.25 (71.1)	31.66 (69.8)	25.40 (56)	31.53 (69.5)	33.25 (73.3)
Wt% APC	26	28	28	28	36	28	26
APC fed kg (lbs)	9.21 (20.3)	9.12 (20.1)	9.03 (19.9)	8.85 (19.5)	9.16 (20.2)	8.85 (19.5)	9.66 (19.1)
Bromine	104.4	108.6	108.6	107.0	110.3	106.4	104.4
BAPC (kg (lbs) est)	32.89 (72.5)	33.75 (74.4)	33.75 (74.2)	33.11 (73.0)	34.16 (75.3)	32.98 (72.7)	32.34 (71.3)
Total Mass (100% HBr evolved)	362	299	299	299	290	297	296
Initial AlCl ₃ wt%	0.101%	0.128%	0.129%	0.128%	0.135%	0.131%	0.131%
Final AlCl ₃ wt% (est)	0.081%	0.097%	0.097%	0.097%	0.100%	0.099%	0.099%
Avg. AlCl ₃ wt% (est)	0.091%	0.113%	0.113%	0.113%	0.117%	0.115%	0.115%
Results							
Hunter Color YI	4.72	4.28	4.3	4.13	3.62	4.81	5.27
Solution Color (Delta E)	1.78	1.06	1.55	1.36	1.10	2.00	2.72
Thermal color 250 °C	10.61	6.00	7.00	7.04	6.28	8.30	8.60
Thermal color 300 °C	20.42	12.85	12.43	15.74	17.07	17.26	19.8
Thermal HBr (ppm)	148	138	225	135	63	100	97
T _g (°C)	121.04	121.33	120.43	127.68	125.38	123.86	--
Wt% Br	73.9	74	74	74.6	73.4	74.1	74

[0046] Example 5 illustrates desirable precipitation procedures. The procedure used in forming Blend 4 also illustrates a novel treatment procedure of this invention that can be utilized during BAPC recovery to further improve its initial and thermal color properties.

EXAMPLE 5

Precipitation Procedure

5 **[0047]** A 30-liter oil-jacketed glass reactor was fitted with for distillation, and was equipped for mechanical stirring using a Teflon® fluoropolymer pitched-blade impeller (reversed pitch to pump against vortex) and a 0.32 cm (1/8") subsurface feed line made of Teflon® fluoropolymer. The reactor is charged with 24 liters of water and heated to 98°C. A 10 liter stainless milk can was charged with 17 kg of an 18 wt% BAPC solution. The content of the milk can pressure transferred to precipitation medium through the 0.32 cm (1/8 inch) feed line over a period of 2.5 hours and at a pot temperature in the range of about 94-96°C. Upon completion of the feed the reactor is allowed to warm to 99°C and held at that temperature for 5 minutes. The content of the reactor is then cooled to about 60°C and the slurry is drained through a bottom drain valve into five 7.57 l (2-gallon) polyethylene carboys.

10 **[0048]** The solid BAPC was isolated using a Rousselet Robatel 30.36 cm (12-inch) basket centrifuge initially operating at 950 rpms. Upon completion of the initial centrifugation the speed is increased to 1700 rpms to ring out the cake. The solid (about 4 kgs of wetcake) is collected and placed in Pyrex® borosilicate glass drying trays and dried in a nitrogen purged oven for 36 hours at 105°C, then further dried at 105°C under full vacuum for 6 hours. The procedure typically yields 3 kg of a dry free flowing white powder.

15 **[0049]** Table 2 summarizes the complete analytical results on four Kilo Lab scale (30-liter reactor) precipitations of BAPC blends formed from selected batches made in Example 4. Comparison of improved thermal color for Blend 4 relative to Blend 3 demonstrates the benefits of having, pursuant to this invention, some level of NaBH₄ present in the precipitation solvent (water) during the isolation procedure. In addition, Table 2 shows the components used in making the selected batches.

TABLE 2

25	Large Scale Precipitation	1	2	3	4
	BAPC Blend	1 and 2	3 and 5	3, 5 and 9	3, 5 and 9
	Approx. Blend Ratio	50:50	50:50	25:25:50	25:25:50
30	Residual BCM (ppm)	52	32	< 1	< 1
	Sodium borohydride present in precipitator (ppm)	0	0	0	250
	Residual DBM (ppm)	0	0	< 1	< 1
	Residual H ₂ O (ppm)	141	83	49	62
35	XRF wt% Br	74.2	74.8	74	74.4
	T _g (°C) (DSC)	120.13	128.47	124.46	124.5
	TGA				
40	1% Wt. Loss (°C)	321.15	322.73	321.98	328.25
	5% Wt. Loss (°C)	356.99	355.56	357.82	360.21
	10% Wt. Loss (°C)	370.21	369.48	370.35	372.27
	50% Wt. Loss (°C)	406.66	406.78	406.23	406.72
45	Thermal HBr 300°C (ppm)	152	116	126	10
	GPC				
	M _w	2637	2640	2569	2569
50	M _n	1951	1958	1907	1907
	M _z	3903	3873	3808	3808
	PD	1.352	1.348	1.347	1.347
	Color (Solids)				
55	L	95.94	95.8	90.22	90.06
	a	-0.09	-0.31	-1.13	-1.11

(continued)

Large Scale Precipitation	1	2	3	4
b	2.18	2.02	2.48	2.35
YI	3.99	3.54	4.01	3.77
Color (Solution)				
L	99.53	99.81	99.65	99.59
a	0.03	-0.12	-0.13	-0.12
b	1.44	1.03	1.07	0.98
Delta E	1.65	1.17	1.29	1.25
Thermal Color				
250°C/15min	10.19	10.48	8.46	6.32
300°C/20min	18.62	19.74	20.73	17.62

Analytical Methods


[0050] Except for thermal color analysis, applicable analytical methods for assaying properties of APC's and BAPC's are set forth in International Publication Number WO 2008/154453 A1 having an International Publication Date of 18 December 2008. The procedure for thermal color analysis is as follows: A custom made metal heating block from J-Kem Scientific (St. Louis, MO) featuring 12 heating ports with diameters to snugly fit 20 ml flat bottom scintillation vials is used. The heating block is placed in a nitrogen-purged glove box and heated to the test temperature (either 250 or 300°C). Duplicate 5-gram samples of the BAPC powder are placed in 20 ml scintillation vials to be heat treated in the heating block. The material in the vials are heated for the specified time (15 minutes at 250°C or 20 minutes at 300°C). Upon completion of the heat treatment or thermal aging period, the samples are immediately removed from the block and cooled under nitrogen. The samples are dissolved to make a 10 wt% solution in chlorobenzene. The solution color is of the dissolved sample in terms of L, a, b and Delta E is measured and compared to a chlorobenzene blank standard (L=100, a=0, b=0) using a Hunter Lab ColorQuest XE Colorimeter (Reston, VA).

[0051] The invention may comprise, consist, or consist essentially of the materials and/or procedures recited herein.

[0052] Except as may be expressly otherwise indicated, the article "a" or "an" if and as used herein is not intended to limit, and should not be construed as limiting, a claim to a single element to which the article refers. Rather, the article "a" or "an" if and as used herein is intended to cover one or more such elements, unless the text expressly indicates otherwise.

Claims

1. A process which comprises brominating an aromatic polymer composition of the formula:



wherein n is an average number in the range of 2.5 to 8 with the proviso that 1,3-diphenylpropane, a compound of formula (I) in which n is 0, optionally is present in this aromatic polymer composition in an amount of not more than 1 GPC area %, and with the further proviso that this aromatic polymer composition optionally further contains toluene in an amount of not more than 0.1 GPC area %, to form a brominated aromatic polymer composition having a bromine content as determined by XRF in the range of 70 to 76 weight percent, which process comprises brominating


said aromatic polymer composition with liquid bromine in the presence of an aluminum halide bromination catalyst and in the absence of light, at a bromination temperature in the range of -10°C to +5°C, and in which the molar ratio of total amount of bromine fed:total amount of catalyst fed is in the range of 200:1 to 500:1, which process is further **characterized in that**:

- a) the total amount of said catalyst is charged into a reactor which is at a temperature in the range of -25°C to 0°C, said reactor containing an inert atmosphere and a portion of bromination solvent such that the initial weight percentage of said catalyst expressed as aluminum is in the range of 0.02 wt% to 0.04 wt%;
 - b) within 2 hours after completing the charge of the catalyst, separate concurrent feeds of (i) bromine, and (ii) a solution of said aromatic polymer composition in the bromination solvent are initiated, said feeds being conducted such that said solution and the liquid bromine are fed to maintain a substantially constant molar ratio of aromatic polymer composition to bromine entering the reactor; and
 - c) wherein on completion of the feeds and an optional ride time of no greater than 60 minutes, the weight percentage of aluminum relative to the total of the mass of the bromination solvent and the brominated aromatic polymer composition in the reactor is greater than 0.015 wt%.
2. A process as in Claim 1 further **characterized in that** said solution of said aromatic polymer composition in the bromination solvent is a solution containing 20 to 40 wt% of said aromatic polymer composition.
 3. A process as in Claim 2 further **characterized in that** said bromination solvent is at least predominately bromo-chloromethane.
 4. A process as in any of Claims 1-3 further **characterized in that** upon completion of the feed or of the optionally used ride time, the bromination reaction mass is transferred to a reaction vessel containing a dilute solution of hydrazine hydrate in water and the resultant mixture is agitated so that the catalyst and bromine are quenched.
 5. A process as in Claim 4 wherein said dilute solution is a 0.1 to 1.0 wt% solution of hydrazine hydrate in water.
 6. A process as in Claim 5 wherein the amount of said 0.1 to 1.0 wt% solution of hydrazine hydrate in water is 0.4 parts by weight of said solution per each 0,4536 kg (pound) by weight of brominated aromatic polymer composition present in the bromination reaction mass.
 7. A process as in any of Claims 4-6 further **characterized in that** upon completion of the quenching, the agitation is discontinued, the quenched reaction mass is isolated from the aqueous mixture by means of a phase separation, and optionally, the resultant reaction mass is washed with fresh water.
 8. A process as in any of Claims 4-7 further **characterized in that** the quenched bromination reaction mass is further treated by agitating the quenched bromination reaction mass with an alkaline borohydride solution to decompose polar bromoamine-derived impurities, said treatment being at a temperature in the range of 25°C to 80°C and for a time period sufficient for the decomposition to be complete, as evidenced by decolorization of the reaction mass and breaking of any emulsion that may exist.
 9. A process as in any of Claims 4-8 further **characterized in that** the brominated aromatic polymer composition is recovered from the reaction mass by precipitation from near boiling or boiling hot water in the presence of alkaline borohydride, and wherein optionally, prior to said precipitation the reaction mass is dried azeotropically and passed through a solid absorbent to remove polar impurities.
 10. A process as in any of Claims 1-9 wherein the aluminum halide bromination catalyst as charged into the reactor is aluminum chloride.
 11. A process as in any of Claims 1-10 wherein said feeding is further **characterized in that** the feeds of bromine and said solution of aromatic polymer composition are in close proximity to each other.
 12. A process as in Claim 11 wherein said feeds are impinging or non-impinging subsurface feeds.
 13. A process as in Claim 11 wherein said feeds are spaced apart and are non-impinging feeds to the surface of the reaction mass.

14. A process as in Claim 1 wherein n is an average number in the range of 2.9 to 3.9 and wherein said bromine content as determined by XRF is in the range of 73.4 to 74.5 weight percent.
15. A process as in Claim 14 wherein said aromatic polymer composition has an M_w in the range of 650 to 750, an M_n in the range of 500 to 600, an M_z in the range of 830 to 1120, and a polydispersity in the range of 1.2 to 1.35.
16. A process as in any of Claims 1-15 wherein the solution of the aromatic polymer composition in the bromination solvent is passed through a solid absorbent to remove polar amine impurities prior to feeding.
17. A process as in Claim 1 wherein (i) 1,3-diphenylpropane is present in said aromatic polymer composition in an amount in the range of not more than 1 GPC area %, or (ii) toluene is present in said aromatic polymer composition in an amount of not more than 0.1 GPC area %, or (iii) both of 1,3-diphenylpropane and toluene are present in said aromatic polymer composition in the amounts specified.
18. A process as in any of Claims 1-13 wherein said bromine content as determined by XRF is in the range of 73.4 to 74.5 weight percent.

Patentansprüche

1. Verfahren, bei dem eine Zusammensetzung aus aromatischem Polymer der Formel:



wobei n eine durchschnittliche Zahl im Bereich von 2,5 bis 8 ist, mit der Maßgabe, dass 1,3-Diphenylpropan, eine Verbindung der Formel (I), bei der n 0 ist, gegebenenfalls in der Zusammensetzung aus aromatischem Polymer in einer Menge von nicht mehr als 1 GPC Flächen-% vorhanden ist und mit der weiteren Maßgabe, dass dies Zusammensetzung aus aromatischem Polymer gegebenenfalls ferner Toluol in einer Menge von nicht mehr als 0,1 GPC Flächen-% enthält,

bromiert wird, um eine Zusammensetzung aus bromiertem, aromatischem Polymer zu bilden, die einen Bromgehalt, bestimmt durch XRF, im Bereich von 70 bis 76 Gew.-% aufweist, wobei das Verfahren das Bromieren der Zusammensetzung aus aromatischem Polymer mit flüssigem Brom in Gegenwart eines Aluminiumhalogenid-Bromierungskatalysators und in Abwesenheit von Licht bei einer Bromierungstemperatur im Bereich von -10°C bis $+5^{\circ}\text{C}$ umfasst, wobei das Molverhältnis der Gesamtmenge an zugeführtem Brom: Gesamtmenge an zugeführtem Katalysator im Bereich von 200:1 bis 500:1 liegt,

wobei das Verfahren ferner **dadurch gekennzeichnet ist, dass:**

a) die Gesamtmenge des Katalysators in einen Reaktor eingeführt wird, der bei einer Temperatur im Bereich von -25°C bis 0°C vorliegt, wobei der Reaktor eine inerte Atmosphäre und einen Teil eines Bromierungslösungsmittels enthält, so dass der Anfangsgewichtsprozentsatz des Katalysators, ausgedrückt als Aluminium, im Bereich von 0.02 Gew.-% bis 0.04 Gew.-% liegt,

b) innerhalb von 2 Stunden nach Vervollständigen der Zuführung des Katalysators mit separaten Zuführungen von (i) Brom und (ii) einer Lösung der Zusammensetzung aus aromatischem Polymer in dem Bromierungslösungsmittel begonnen wird, wobei die Zuführungen so durchgeführt werden, dass die Lösung und das flüssige Brom zugeführt werden, um ein im Wesentlichen konstantes Molverhältnis von dem Reaktor zugeführter Zusammensetzung aus aromatischem Polymer zu dem Reaktor zugeführtem Brom aufrechtzuerhalten, und

c) nach Vervollständigen der Zuführungen und einer optionalen Wartedauer vom nicht mehr als 60 Minuten der Gewichtsprozentsatz von Aluminium relativ zu der Gesamtmasse des Bromierungslösungsmittel und der Zusammensetzung aus bromiertem, aromatischem Polymer in dem Reaktor größer als 0.015 Gew.-% ist.


2. Verfahren nach Anspruch 1, ferner **dadurch gekennzeichnet, dass** die Lösung der Zusammensetzung aus aromatischem Polymer in dem Bromierungslösungsmittel einer Lösung ist, die 20 bis 40 Gew.-% der Zusammensetzung aus aromatischem Polymer enthält.
- 5 3. Verfahren nach Anspruch 2, ferner **dadurch gekennzeichnet, dass** das Bromierungslösungsmittel zumindest überwiegend Bromchlormethan ist.
4. Verfahren nach einem der Ansprüche 1 bis 3, ferner **dadurch gekennzeichnet, dass** nach Vervollständigung der Zufuhr oder der optional verwendeten Wartedauer die Bromierungsreaktionsmasse in ein Reaktionsgefäß überführt wird, das eine verdünnte Lösung von Hydrazinhydrat in Wasser enthält, und die resultierende Mischung bewegt wird, so dass der Katalysator und das Brom abgeschreckt werden.
- 10 5. Verfahren nach Anspruch 4, bei dem die verdünnte Lösung eine 0.1 bis 1.0 Gew.-% Lösung von Hydrazinhydrat in Wasser ist.
- 15 6. Verfahren nach Anspruch 5, bei dem die Menge der 0.1 bis 1.0 Gew.-% Lösung von Hydrazinhydrat in Wasser 0.4 Gewichtsteile der Lösung pro jeweils 0,4536 kg (engl. Pfund) Gewicht an Zusammensetzung aus bromiertem, aromatischem Polymer beträgt, das in der Reaktionsmasse vorhanden ist.
- 20 7. Verfahren nach einem der Ansprüche 4 bis 6, ferner **dadurch gekennzeichnet, dass** nach Vervollständigung des Abschreckens die Bewegung unterbrochen wird, die abgeschreckte Reaktionsmasse aus der wässrigen Mischung mittel Phasentrennung isoliert wird und gegebenenfalls die resultierende Reaktionsmasse mit frischem Wasser gewaschen wird.
- 25 8. Verfahren nach einem der Ansprüche 4 bis 7, ferner **dadurch gekennzeichnet, dass** die abgeschreckte Reaktionsmasse ferner behandelt wird, indem die abgeschreckte Reaktionsmasse zusammen mit einer alkalischen Borhydrid-Lösung bewegt wird, um polare, von Bromamine abgeleitete Verunreinigungen zu zersetzen, wobei die Behandlung bei einer Temperatur im Bereich von 25°C bis 80°C und über einen Zeitraum durchgeführt wird, die für die vollständige Zersetzung ausreichen, die durch Entfärbung der Reaktionsmasse und Brechen irgendeiner
- 30 möglicherweise vorliegenden Emulsion angezeigt wird.
9. Verfahren nach einem der Ansprüche 4 bis 8, ferner **dadurch gekennzeichnet, dass** die Zusammensetzung aus bromiertem, aromatischem Polymer aus der Reaktionsmasse durch Ausfällung aus heißem Wasser nahe dem Siedepunkt in Gegenwart von alkalischem Borhydrid gewonnen wird, und bei dem die Reaktionsmasse vor der Ausfällung gegebenenfalls azeotrop getrocknet und durch ein festes Absorbionsmittel geführt wird, um polare Verunreinigungen zu entfernen.
- 35 10. Verfahren nach einem der Ansprüche 1 bis 9, bei dem der Aluminiumhalogenid-Bromierungskatalysator, wie er in den Reaktor eingeführt wird, Aluminiumchlorid ist.
- 40 11. Verfahren nach einem der Ansprüche 1 bis 10, bei dem das Zuführen ferner **dadurch gekennzeichnet ist, dass** die Zuführungen von Brom und der Lösung der Zusammensetzung aus aromatischem Polymer in enger Nähe zueinander erfolgen.
- 45 12. Verfahren nach Anspruch 11, bei dem die Zuführungen aufprallende Zuführungen oder nicht-aufprallende Zuführungen unter der Oberfläche sind.
13. Verfahren nach Anspruch 11, bei dem die Zuführungen mit Abstand voneinander erfolgen und nicht-aufprallende Zuführungen auf die Oberfläche der Reaktionsmasse sind.
- 50 14. Verfahren nach Anspruch 1, bei dem n eine durchschnittliche Zahl im Bereich von 2,9 bis 3,9 ist und bei dem der Bromgehalt, bestimmt durch XRF, im Bereich von 73,4 bis 74,5 Gew.-% liegt.
- 55 15. Verfahren nach Anspruch 14, bei dem die Zusammensetzung aus aromatischem Polymer ein M_w im Bereich von 650 bis 750, ein M_n im Bereich von 500 bis 600 und ein M_z im Bereich von 830 bis 1120 sowie eine Polydispersität im Bereich von 1,2 bis 1,35 aufweist.
16. Verfahren nach einem der Ansprüche 1 bis 15, bei dem die Lösung der Zusammensetzung aus bromiertem, aro-

matischem Polymer in dem Bromierungslösungsmittel durch ein festes Absorptionsmittel geführt wird, um vor der Zufuhr polare Amin-Verunreinigungen zu entfernen.

17. Verfahren nach Anspruch 1, bei dem (i) 1,3-diphenylpropan in der Zusammensetzung aus aromatischem Polymer in einer Menge im Bereich von nicht mehr als 1 GPC Flächen-% vorhanden ist oder (ii) Toluol in der Zusammensetzung aus aromatischem Polymer in einer Menge von nicht mehr als 0,1 GPC Flächen-% vorhanden ist oder (iii) beide von 1,3-Diphenylpropan und Toluol in der Zusammensetzung aus aromatischem Polymer in den angegebenen Mengen vorhanden sind.
18. Verfahren nach einem der Ansprüche 1 bis 13, bei dem der Bromgehalt, bestimmt durch XRF, im Bereich von 73,4 bis 74,5 Gew.-% liegt.

Revendications

1. Procédé qui comprend la bromation d'une composition polymère aromatique de la formule :



dans laquelle n est un nombre moyen dans la plage de 2,5 à 8 à condition que le 1,3-diphénylpropane, un composé de formule (I) dans laquelle n est 0, soit éventuellement présent dans cette composition polymère aromatique dans une quantité ne dépassant pas 1 % de la surface de chromatographie par perméation sur gel (CPG), et à condition en outre que cette composition polymère aromatique contienne en outre éventuellement du toluène dans une quantité ne dépassant pas 0,1 % de la surface de CPG, pour former une composition polymère aromatique bromée ayant une teneur en brome telle que déterminée par fluorescence X dans la plage de 70 à 76 % en poids, lequel procédé comprend la bromation de ladite composition polymère aromatique avec du brome liquide en la présence d'un catalyseur de bromation d'halogénure d'aluminium et en l'absence de lumière, à une température de bromation dans la plage de -10°C à +5°C, et dans lequel le rapport molaire de la quantité totale de la charge bromée:quantité totale de charge catalytique est dans la plage de 200:1 à 500:1, lequel procédé est en outre **caractérisé en ce que** :

- a) la quantité totale dudit catalyseur est chargée dans un réacteur qui est à une température dans la plage de -25°C à 0°C, ledit réacteur contenant une atmosphère inerte et une portion de solvant de bromation de telle sorte que le pourcentage en poids initial dudit catalyseur exprimé en tant qu'aluminium soit dans la plage de 0,02 % en poids à 0,04 % en poids ;
- b) deux heures maximum après avoir terminé la charge du catalyseur, les charges d'alimentation séparées de (i) brome, et (ii) d'une solution de ladite composition polymère aromatique dans le solvant de bromation sont initiées, lesdites charges d'alimentation étant conduites de telle sorte que ladite solution et le brome liquide soient chargés pour maintenir un rapport molaire sensiblement constant entre la composition polymère aromatique et le brome pénétrant dans le réacteur ; et
- c) dans lequel une fois les charges effectuées et au bout d'un temps de parcours éventuel ne dépassant pas 60 minutes, le pourcentage en poids de l'aluminium par rapport au total de la masse du solvant de bromation et de la composition polymère aromatique bromée dans le réacteur est supérieur à 0,015 % en poids.
2. Procédé selon la revendication 1, **caractérisé en outre en ce que** ladite solution de ladite composition polymère aromatique dans le solvant de bromation est une solution contenant de 20 à 40 % en poids de ladite composition polymère aromatique.
3. Procédé selon la revendication 2, **caractérisé en outre en ce que** ledit solvant de bromation est au moins principalement du bromochlorométhane.
4. Procédé selon l'une quelconque des revendications 1 à 3, **caractérisé en outre en ce qu'**une fois la charge effectuée

ou au bout du temps de parcours éventuel utilisé, la masse réactionnelle de bromation est transférée vers une cuve de réaction contenant une solution diluée d'hydrazine hydrate dans de l'eau et le mélange résultant est agité de telle sorte que le catalyseur et le brome soient désactivés.

- 5 5. Procédé selon la revendication 4, dans lequel ladite solution diluée est une solution de 0,1 à 1,0 % en poids d'hydrazine hydrate dans de l'eau.
6. Procédé selon la revendication 5, dans lequel la quantité de ladite solution de 0,1 à 1,0 % en poids d'hydrazine hydrate dans de l'eau est de 0,4 parties en poids de ladite solution pour chaque 0,4536 kg (livre) en poids de composition polymère aromatique bromée présente dans la masse réactionnelle de bromation.
7. Procédé selon l'une quelconque des revendications 4 à 6, **caractérisé en outre en ce qu'une** fois la désactivation opérée, l'agitation est discontinuée, la masse réactionnelle désactivée est isolée du mélange aqueux au moyen d'une séparation de phases, et, éventuellement, la masse réactionnelle résultante est lavée à de l'eau douce.
8. Procédé selon l'une quelconque des revendications 4 à 7, **caractérisé en outre en ce que** la masse réactionnelle de bromation désactivée est en outre traitée en agitant la masse réactionnelle de bromation désactivée avec une solution de borohydrure alcalin pour décomposer les impuretés dérivées d'une bromoamine polaire, ledit traitement étant à une température dans la plage de 25°C à 80°C et pendant une période de temps suffisante pour que la décomposition soit terminée, comme mis en évidence par la décoloration de la masse réactionnelle et la floculation de n'importe quelle émulsion pouvant exister.
9. Procédé selon l'une quelconque des revendications 4 à 8, **caractérisé en outre en ce que** la composition polymère aromatique bromée est récupérée à partir de la masse réactionnelle par précipitation à partir d'eau en ébullition ou proche de l'ébullition en la présence de borohydrure alcalin, et dans lequel, éventuellement, avant ladite précipitation, la masse réactionnelle est séchée azéotropiquement et passée à travers un absorbant solide pour éliminer les impuretés polaires.
10. Procédé selon l'une quelconque des revendications 1 à 9, dans lequel le catalyseur de bromation à base d'halogénure d'aluminium tel que chargé dans le réacteur est du chlorure d'aluminium.
11. Procédé selon l'une quelconque des revendications 1 à 10, dans lequel ladite alimentation est en outre **caractérisée en ce que** les charges de brome et de ladite solution de composition polymère aromatique sont à proximité étroite l'une de l'autre.
12. Procédé selon la revendication 11, dans lequel lesdites charges sont des charges en subsurface incidentes ou non incidentes.
13. Procédé selon la revendication 11, dans lequel lesdites charges sont espacées et sont des charges non incidentes sur la surface de la masse réactionnelle.
14. Procédé selon la revendication 1, dans lequel n est un nombre moyen dans la plage de 2,9 à 3,9 et dans lequel ladite teneur en brome telle que déterminée par fluorescence X, est dans la plage de 73,4 à 74,5 % en poids.
15. Procédé selon la revendication 14, dans lequel ladite composition polymère aromatique a un M_w dans la plage de 650 à 750, un M_n dans la plage de 500 à 600, un M_z dans la plage de 830 à 1120, et une polydispersité dans la plage de 1,2 à 1,35.
16. Procédé selon l'une quelconque des revendications 1 à 15, dans lequel la solution de la composition polymère aromatique dans le solvant de bromation est passée à travers un absorbant solide pour éliminer les impuretés d'amine polaire avant l'alimentation.
17. Procédé selon la revendication 1, dans lequel (i) du 1,3-diphénylpropane est présent dans ladite composition polymère aromatique dans une quantité dans la plage ne dépassant pas 1 % de la surface de CPG, ou (ii) du toluène est présent dans ladite composition polymère aromatique dans une quantité ne dépassant pas 0,1 % de la surface de CPG, ou (iii) à la fois du 1,3-diphénylpropane et du toluène sont présents dans ladite composition polymère aromatique dans les quantités spécifiées.

EP 2 424 904 B1

18. Procédé selon l'une quelconque des revendications 1 à 13, dans lequel ladite teneur en brome, telle que déterminée par fluorescence X, est dans la plage de 73,4 à 74,5 % en poids.

5

10

15

20

25

30


35

40

45

50

55



REFERENCES CITED IN THE DESCRIPTION


This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 61119289 A [0001]
- WO 2007005233 A1 [0002]
- US 2007142566 A [0003]
- WO 2008154453 A1 [0050]

Szabadalmi igénypontok

1. Eljárás, amely tartalmazza az alábbi képletű aromás polimer készítmény bromózását:



ahol n jelentése egy, a 2,5-8 tartományba eső átlagérték, azzal a megkötéssel, hogy az 1,3-difenilpropán, amely egy (I) képletű vegyület, amelyben n értéke 0, adott esetben jelen van 1 GPC terület%-nál nem nagyobb mennyiségben ezen aromás polimer készítményben, és azzal a további megkötéssel, hogy ezen aromás polimer készítmény adott esetben tartalmaz továbbá toluolt 0,1 GPC terület%-nál nem nagyobb mennyiségben, és így képzünk XRF-fel meghatározott 70-76 tömeg% tartományba eső brómtartalom értékkel rendelkező bromozott aromás polimer készítményt, amely eljárás tartalmazza az aromás polimer készítmény bromózását folyadék brómmal alumínium-halid bromozó katalizátor jelenlétében és fény hiányában, $-10 - +5$ °C tartományba eső bromozási hőmérsékleten, és amelyben a teljes betáplált brómmennyiségnek a teljes betáplált katalizátormennyiségre vonatkoztatott molaránya a 200:1 - 500:1 tartományba esik, és amely eljárás továbbá azzal jellemzett, hogy

a) a katalizátor teljes mennyiségét a reaktorba töltjük, amely reaktor $-25 - 0$ °C hőmérsékletű, a reaktor tartalmaz inert atmoszférát és a bromozó oldószer egy részét úgy, hogy a katalizátor kezdeti tömegszázaléka alumíniumban kifejezve a 0,02-0,04 tömeg% tartományba esik;

b) a katalizátor betöltésének befejezésétől számított két órán belül, párhuzamosan, külön betáplálásként (i) brómot és (ii) aromás polimer készítmény a bromozó oldószerrel készült oldatát adagoljuk, a betáplálásokat úgy vezetjük, hogy az oldat és a folyadék bróm betáplálása során az aromás polimer készítménynek a reaktorba lépő brómra vonatkoztatott alapvetően konstans molarányát tartjuk fenn; és

c) ahol a betáplálások és a 60 percnél nem hosszabb opcionális lefutási idő befejeztével a bromozó oldószer és a bromozott aromás polimer készítmény teljes tömegére vonatkoztatott alumínium tömeg% a reaktorban 0,015 tömeg%-nál nagyobb.

2. Az 1. igénypont szerinti eljárás, továbbá azzal jellemezve, hogy az aromás polimer készítmény bromozó oldószerrel készült oldata egy oldat, amely 20-40 tömeg%-ban tartalmazza az aromás polimer készítményt.

3. A 2. igénypont szerinti eljárás, továbbá azzal jellemezve, hogy a bromozó oldószer legalább túlnyomórészi bróm-klórmetan.

4. Az 1-3. igénypontok bármelyike szerinti eljárás, továbbá azzal jellemezve, hogy a betáplálás vagy az adott esetben alkalmazott lefutási idő befejeztével a brómozási reakciótömeget átvezetjük vízben oldott hidrazin-hidrárt hígító oldatot tartalmazó reakcióedénybe és a kapott elegyet kevertetjük, és ezzel a katalizátort és a brómot lefojtjuk.

5. A 4. igénypont szerinti eljárás, ahol a hígító oldat hidrazin-hidrárt 0,1-1,0 tömeg%-os vizes oldata.

6. Az 5. igénypont szerinti eljárás, ahol a hidrazin-hidrárt 0,1-1,0 tömeg%-os vizes oldatának mennyisége az oldat 0,4 tömegrésze minden, a brómozási reakciótömegben jelen lévő 0,4536 kg (font) brómozott aromás polimer készítmény tömegére vetítve.

7. A 4-6. igénypontok bármelyike szerinti eljárás, továbbá azzal jellemezve, hogy a lefojtás befejeztével a kevertetést megszakítjuk, a lefojtott reakciótömeget izoláljuk fázisszeparáció segítségével a vizes elegyből, és adott esetben a kapott reakciótömeget friss vízzel mossuk.

8. A 4-7. igénypontok bármelyike szerinti eljárás, továbbá azzal jellemezve, hogy a lefojtott brómozási reakciótömeget tovább kezeljük a lefojtott brómozási reakciótömeg alkáli-bórhidrid oldattal történő kevertetésével és így lebontjuk a szennyező poláris brómamin-származékokat, a kezelést 25-80°C tartományba eső hőmérsékleten annyi ideig végezzük, amely elegendő a lebomlás teljessé tételéhez, amelyet a reakciótömeg elszíntelenülődése és az esetlegesen jelen lévő emulzió megtörése indikál.

9. A 4-8. igénypontok bármelyike szerinti eljárás, továbbá azzal jellemezve, hogy a brómozott aromás polimer készítményt visszanyerjük a reakciótömegből forráshoz közeli vagy forráshoz közel lévő vízből alkáli-bórhidrid jelenlétében végzett kicsapással, és ahol adott esetben a kicsapást megelőzően a reakciótömeget azeotróposan szárítjuk és szilárd abszorbensen hajtjuk át a poláris szennyezők eltávolítására.

10. Az 1-9. igénypontok bármelyike szerinti eljárás, ahol a reaktorba töltött alumínium-halid brómozó katalizátor alumínium-klorid.

11. Az 1-10. igénypontok bármelyike szerinti eljárás, ahol a betáplálás tovább jellemzett azzal, hogy a bróm és az aromás polimer készítmény betáplálásai egymáshoz szoros közelségben vannak.

12. A 11. igénypont szerinti eljárás, ahol a betáplálások ütköző vagy felszín alatti nem-ütköző betáplálások.

13. A 11. igénypont szerinti eljárás, ahol a betáplálások térben elválasztottak és nem-ütközők a reakciótömeg felületére nézve.

14. Az 1. igénypont szerinti eljárás, ahol n jelentése egy, a 2,9-3,9 tartományba eső átlagérték, és ahol az XRF-fel meghatározott brómtartalom a 73,4-74,5 tömeg% tartományba esik.

15. A 14. igénypont szerinti eljárás, ahol az aromás polimer készítmény a 650-750 tartományba eső M_w , az 500-600 tartományba eső M_n , a 830-1120 tartományba eső M_v , és az 1,2-1,35 tartományba eső polidisperszítás értékkel rendelkezik.

16. Az 1-15. igénypontok bármelyike szerinti eljárás, ahol az aromás polimer készítmény brómozó oldószerrel készült oldatát szilárd abszorbensen hajtjuk át a poláris amin szennyezők eltávolítására a betáplálást megelőzően.

17. Az 1. igénypont szerinti eljárás, ahol (i) 1,3-difenilpropán van jelen 1 GPC terület%-nál nem nagyobb mennyiségben az aromás polimer készítményben, vagy (ii) toluol van jelen 0,1 GPC terület%-nál nem nagyobb mennyiségben az aromás polimer készítményben, vagy (iii) 1,3-difenilpropán és toluol is jelen van ezen aromás polimer készítményben a meghatározott mennyiségekben.

18. Az 1-13. igénypontok bármelyike szerinti eljárás, ahol az XRF-fel meghatározott brómtartalom a 73,4-74,3 tömeg% tartományba esik.