



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21C 9/147, 9/10	A1	(11) International Publication Number: WO 98/23810 (43) International Publication Date: 4 June 1998 (04.06.98)
(21) International Application Number: PCT/SE97/01852 (22) International Filing Date: 6 November 1997 (06.11.97) (30) Priority Data: 9604350-0 26 November 1996 (26.11.96) SE (71) Applicant (for all designated States except US): SUNDS DEFIBRATOR INDUSTRIES AB [SE/SE]; S-851 94 Sundsvall (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): BOKSTRÖM, Monica [SE/SE]; Bjärne 3251, S-860 25 Kovland (SE). HÄGGQVIST, Jan-Erik [SE/SE]; Lindvägen 12, S-862 33 Kvissleby (SE). (74) Common Representative: SUNDQVIST, Hans; Sunds Defibrator Industries AB, Strandbergsgatan 61, S-112 51 Stockholm (SE).		(81) Designated States: AU, BR, CA, CN, JP, NO, NZ, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: METHOD FOR CONTROLLING OXYGEN DELIGNIFICATION OF PULP (57) Abstract A method of controlling oxygen delignification of pulp, i.e. reduction of the kappa number of the pulp, where the delignification is carried out in two stages, and the main portion of the chemicals required for the delignification is added to the first stage. The ingoing kappa number of the pulp prior to the delignification and the reduction of the kappa number of the pulp during the total delignification in the two stages are used for adjusting the chemical addition to the first stage. The control is carried out so that higher ingoing kappa number yields lower charge and higher kappa number reduction yields higher charge, calculated per reduced kappa number unit. Said chemical addition to the first stage in its turn is used for control the temperature in the second stage.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD FOR CONTROLLING OXYGEN DELIGNIFICATION OF PULP

This invention relates to the control of a method for oxygen delignification of lignocellulosic material in two steps at medium consistency, i.e. 8-16%.

Since the introduction of oxygen delignification at medium consistency, not much development work has been invested in this process. When chlorine free bleaching and closure of bleach plants came into being, the interest in extended delignification, i.e. further reduction of the kappa number with oxygen, has increased. Extended delignification with oxygen in one or several stages, however, can result in deteriorated pulp quality. Application of proper conditions, however, can bring about several advantages.

With extended oxygen delignification the pulp yield could also be maintained better than at extended cooking, i.e. cooking to lower kappa number.

At a multi-stage method, the chemicals can be distributed between the stages so as to create optimum conditions in each stage. Other conditions could also be optimized for each stage.

The object of the present invention is a method of controlling oxygen delignification in such a manner, that a lower kappa number is obtained without deterioration of the pulp properties. By using the extended delignification according to the invention, the total delignification can amount to 50-85% of the lignin content (kappa number) of unbleached pulp. The method is carried out at medium consistency in two subsequent steps. The characterizing features of the invention are defined in the attached claims.

The invention is described in greater detail in the following, with reference to the accompanying Figure, which schematically shows a plant for carrying out the method according to the invention.

In the plant shown cooked pulp is pumped at medium consistency, i.e. 8-16%, by a first pump 1 from the brown pulp

washing to oxygen delignification. Alkali is charged to the pulp ahead of the first pump 1. After this pump 1 a first mixer 2 is used for admixing oxygen to the pulp. The pulp is thereafter supplied into a first reactor 3, in which the first delignification stage is carried out. The pulp is moved from there, possibly by means of a second pump 4, via a second mixer 5 for admixing steam and possibly more oxygen and alkali to a second reactor 6 for the second delignification stage. After the second reactor 6 the pulp is moved to a blow tank 7 and further to subsequent processing stages.

The method thus implies that the delignification is carried out in two subsequent stages. To the first reactor 3 a high alkali addition as well as a high oxygen addition are made. This means a charge of 10-50 kg alkali (NaOH) per ton pulp, preferably 10-35 kg/ton. The oxygen charge should be 10-50 kg/ton pulp, preferably 10-30 kg/ton.

The temperature of the pulp at its feed to the reactor 3 shall be below 90°C, preferably 75-90°C. The retention time in the reactor 3 should be relatively short, 5-30 min, preferably 15-25 min.

The pressure in the first reactor 3 should be 4-15 bar. The high pressure, together with the high alkaliness of the pulp and the high oxygen charge, result in a high delignification rate. At the same time, the rate of the cellulose degradation is held on a low level due to the relatively low temperature and the short retention time.

After the first delignification stage in the first reactor 3 the pulp is moved to the second delignification stage in the second reactor 6. The temperature in the second reactor 6 should be higher than in the first reactor 3. The temperature difference, however, shall be less than 20°C, preferably 10-15°C. In order to bring about the necessary increase in temperature, steam is supplied to the second mixer 5.

The pressure in the second reactor should be 2-5 bar and lower than in the first reactor 3. The retention time should be relatively long, 45-180 min, preferably 60-120 min.

The second delignification stage is primarily a long

extraction stage, where, in relation to the first step, the increased temperature and extended retention time give extended delignification. At temperatures above 90°C, thus, good extraction/leaching rate is obtained.

The entire or main part of the chemical addition is made to the first stage. To the second stage preferably a very small or no addition of alkali or oxygen should be made, not even for compensating for the consumption in the first stage. The alkaliness of the pulp can thereby be held relatively low in the second stage. Hereby cellulose degradation is substantially avoided, in spite of high temperature and long retention time.

The charge of alkali and oxygen to the second stage, respectively, can be up to 5 kg/ton pulp.

The control of the oxygen delignification according to the invention is based on forward control, which means it implies the least possible back feed coupling. The control is carried out as follows.

The kappa number of the ingoing pulp is measured and compared to the desired value (set value) of the kappa number of the pulp after the oxygen delignification. The reduction of the kappa number thus determined is used for adjusting the chemical addition (oxygen, alkali) to the first stage. A greater kappa number reduction implies higher charge, calculated per reduced kappa number unit. The level of the kappa number of the ingoing pulp is also used for adjusting the chemical charge, so that a higher ingoing kappa number implies a lower charge, calculated per reduced kappa number unit. For instance, a kappa number reduction of about 60%, such as from kappa 25 to kappa 10, implies an alkali charge measured in kg NaOH/ton pulp of about 2.2 times (ingoing kappa minus outgoing kappa). A delignification of 50% from kappa 25 to kappa 12,5 implies an alkali charge of 2.0 times (ingoing kappa minus outgoing kappa). A delignification of 50% from kappa 20 to kappa 10 implies an alkali charge of 2.2 times (ingoing kappa minus outgoing kappa). The exact factor is corrected in each individual case by means of obtained kappa number in relation

to final pH value. If the final pH is somewhat high and the kappa number somewhat low the alkali charge is adjusted somewhat downwards. If the final pH is somewhat low and the kappa number somewhat high the alkali charge is adjusted somewhat upwards.

Oxygen is charged in the relation 1:1 to the alkali charge, but with a maximum oxygen charge of 25-30 kg/ton pulp. When the degree of delignification is higher, i.e. when the alkali charge exceeds 25-30 kg NaHO/ton pulp, the ratio between oxygen and alkali charge is reduced. Thereby it is possible to avoid gas channeling as a result of large gas amounts.

The temperature level in the second stage is controlled partly in the usual way by the production level, so-called kappa factor control, and partly by the chemical addition to the first stage, so that a higher chemical charge to the first stage should result in a higher temperature in the second stage. The temperature is controlled so that a final pH of 10.5-11.5, preferably 10.7-11.0, is obtained. The factor between a change in chemical charge and the temperature level is adjusted manually by means of a final pH as mentioned above. However, the increase in temperature between the first and second stage should always be less than 20°C, preferably 10-15°C, in order to avoid too large cellulose degradation due to high temperature.


Normally, however, no compensation takes place of the temperature in the first stage to the chemical addition and production level. The pulp ingoing to the first stage is not heated, but it might need some cooling, so that a temperature suitably low for the process is obtained, below 90°C.

The control of the oxygen delignification according to the invention implies that a high delignification degree with good selectivity can be obtained. A low and even kappa number and an even pH-value can be obtained after the second delignification stage.

Claims

1. A method of controlling oxygen delignification of pulp, i.e. reduction of the kappa number of the pulp, where the delignification is carried out in two stages, and the main portion of the chemicals required for the delignification is added to the first step, **characterized** in that the ingoing kappa number of the pulp prior to the delignification and the reduction of the kappa number of the pulp during the total delignification in the two stages are used for adjusting the chemical addition to the first stage, so that a higher ingoing kappa number yields lower charge and greater kappa number reduction yields higher charge, calculated per reduced kappa number unit, and that said chemical addition to the first stage in its turn is used for control of the temperature in the second stage.
2. A method as defined in claim 1, **characterized** in that the temperature in the second stage is controlled so that a final pH of 10.5-11.5 is obtained.
3. A method as defined in claim 1 or 2 **characterized** in that the entire chemical addition required for the delignification is made in the first stage.

1/1



INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 97/01852

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: D21C 9/147, D21C 9/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: D21C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CA 1057906 A (SOININEN, JAAKKO ET AL), 10 July 1979 (10.07.79), claim 1 --	1
A	US 5217575 A (AKE BACKLUND), 8 June 1993 (08.06.93) --	1-3
A	US 4419184 A (AKE BACKLUND), 6 December 1983 (06.12.83) --	1-3
A	US 4840703 A (ERKKI MALMSTEN), 20 June 1989 (20.06.89) --	1-3

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 February 1998

Date of mailing of the international search report

03-03-1998

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Marianne Bratsberg
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 97/01852

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,A	WO 9715715 A1 (SUNDS DEFIBRATOR INDUSTRIES AB), 1 May 1997 (01.05.97) -- -----	1-3

INTERNATIONAL SEARCH REPORT

Information on patent family members

03/02/98

International application No.

PCT/SE 97/01852

Patent document cited in search report			Publication date	Patent family member(s)			Publication date
CA	1057906	A	10/07/79	SE	7506844	A	15/12/75
US	5217575	A	08/06/93	CA	1337843	A	02/01/96
				FI	91896	B,C	13/05/94
				JP	2145883	A	05/06/90
				SE	467582	B,C	10/08/92
				SE	8803705	A	19/04/90
US	4419184	A	06/12/83	BR	8104972	A	20/04/82
				CA	1170430	A	10/07/84
				DE	3129010	A	13/05/82
				FR	2489516	A,B	05/03/82
				JP	1478660	C	27/01/89
				JP	57071486	A	04/05/82
				JP	63025118	B	24/05/88
				SE	421019	B,C	16/11/81
US	4840703	A	20/06/89	AT	391718	B	26/11/90
				BR	8505604	A	12/08/86
				DE	3538618	A	10/07/86
				FR	2572742	A,B	09/05/86
				JP	2004718	B	30/01/90
				JP	61113889	A	31/05/86
				SE	463106	B,C	08/10/90
				SE	8505246	A	09/05/86
				SU	1542423	A	07/02/90
WO	9715715	A1	01/05/97	AU	7348396	A	15/05/97
				SE	505141	C	30/06/97
				SE	9503720	A	24/04/97