

**(12) PATENT
(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 199955731 B2
(10) Patent No. 754738**

(54) Title
A process to improve the drainage rate and retention of fines during papermaking

(51)⁷ International Patent Classification(s)
D21H 017/29 D21H 017/44
D21H 017/37 D21H 021/06
D21H 017/42 D21H 021/10

(21) Application No: **199955731** (22) Application Date: **1999.08.18**

(87) WIPO No: **WO00/11267**

(30) Priority Data

(31) Number **09/152695** (32) Date **1998.08.19** (33) Country **US**

(43) Publication Date : **2000.03.14**

(43) Publication Journal Date : **2000.05.11**

(44) Accepted Journal Date : **2002.11.21**

(71) Applicant(s)
BetzDearborn Inc.

(72) Inventor(s)
Frank J. Sutman; Richard A. Hobirk

(74) Agent/Attorney
SPRUSON and FERGUSON, GPO Box 3898, SYDNEY NSW 2001

(56) Related Art
US 5584966
US 5595630



55731/99

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D21H 17/29, 17/37, 17/42, 17/44, 21/06, 21/10		A1	(11) International Publication Number: WO 00/11267 (43) International Publication Date: 2 March 2000 (02.03.00)
<p>(21) International Application Number: PCT/US99/18915</p> <p>(22) International Filing Date: 18 August 1999 (18.08.99)</p> <p>(30) Priority Data: 09/152,695 19 August 1998 (19.08.98) US</p> <p>(71) Applicant: BETZDEARBORN INC. [US/US]; 4636 Somerton Road, P.O. Box 3002, Trevose, PA 19053-6783 (US).</p> <p>(72) Inventors: SUTMAN, Frank, J.; 9748 Chesterfield Drive, Jacksonville, FL 32257 (US). HOBIRK, Richard, A.; 950 Azalea Lane, Fernandina Beach, FL 32034 (US).</p> <p>(74) Agents: KULLER, Mark, D. et al.; Hercules Incorporated, Law Dept.– Intellectual Property, 8216 SW, Hercules Plaza, 1313 N. Market Street, Wilmington, DE 19894 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: A PROCESS TO IMPROVE THE DRAINAGE RATE AND RETENTION OF FINES DURING PAPERMAKING</p> <p>(57) Abstract</p> <p>A method of improving drainage rate and retention of fines which is effective in unfilled, newsprint-type furnish without a silica/bentonite-type particle is disclosed. The method comprises adding a cationic or amphoteric starch, and a cationic polyelectrolyte followed by the addition of a high molecular weight anionic polyacrylamide copolymer.</p>			

A PROCESS TO IMPROVE THE DRAINAGE RATE AND RETENTION OF FINES DURING PAPERMAKING

PAPERMAKING AID

FIELD OF THE INVENTION

5

The present invention relates to the production of paper or paperboard, and more particularly, to a method for improving the retention and/or drainage properties of mechanical pulp-based furnish in the formation of newsprint, directory stock, ground wood specialty stock.

10

BACKGROUND OF THE INVENTION

Paper production involves the formation and dewatering of a web of cellulose fibers and optional fillers, and is generally performed in the presence of additives which can improve the end product or the papermaking operation. Many grades of paper include substantial levels of inorganic fillers such as kaolinite, calcium carbonate and titanium dioxide. For example, good quality paper, often referred to as fine paper, may be made from high grade, bleached chemical pulp, and may contain 5 to 35%, by weight of dry paper, of inorganic fillers. In the production of such paper, it is common to use retention aids and drainage aids. Such retention and drainage aids have proven to be cost effective in the production of filled or fine paper for some time.

There is, however, a very large scale production of paper that is substantially unfilled. For instance, the production of newsprint. The unfilled paper is substantially free of filler, and often there is no deliberate addition of filler to the pulp from which the paper is made. Over the past 5 few years, the use of retention aids in the production of newsprint and other mechanical pulp containing grades of paper has become increasingly common. The most common treatments are cationic polyacrylamides, poly(ethylene oxides), and poly(ethyleneimines).

10 U.S. Patent No. 4,305,781 discloses a process for enhancing drainage and retention of substantially unfilled paper which comprises including in the suspension a combination of a water soluble, high molecular weight substantially nonionic polymer and a bentonite-type clay.

15 The effectiveness of a nonionic poly(ethyleneoxide) of high molecular weight for fines retention in newsprint stock was disclosed in "Application of Polymeric Flocculant in Newsprint Stock Systems for Fines Retention Improvement", C. H. Tay, Tappi, Volume 63, No. 6, June 20 1980. This article also notes that anionic retention aids tend to impair stock drainage characteristics.

25 In "Retention Aids for Quality Improvements in Newsprint", D.S. Honig, 1988 Paper Makers Conference at 219, it is stated that based upon a large number of research articles on retention aids for newsprint, the overall conclusions have been that conventional polyacrylamides (as single or multiple component systems) are ineffective or uneconomical. This paper goes on to discuss the use of cationic polyacrylamides as well as a dual component low molecular weight cationic polymer/low pKa 30 anionic polyacrylamide treatment as a retention aid in newsprint

production. The author concludes that cationic polyacrylamides are less complex, equal or more effective, and in particular, effective at lower dose level than the alternative treatment.

5 In treatments shown to enhance drainage and fines retention which employ anionic polyacrylamides, a silicate (such as colloidal silica or polysilicate microgel) or bentonite is a required component. See for example, U.S. Patents Nos. 4,643,801; 5,584,966 and 5,595,630.

Summary of the Invention

10 The present inventors have discovered a novel drainage and retention aid treatment which is effective in newsprint-type furnish without a silica/bentonite-type particle. The novel drainage and retention aid treatment of the present invention comprises the sequential or concurrent addition of (i) a cationic or amphoteric starch and (ii) a cationic polyelectrolyte followed by the addition of a high molecular weight anionic polyacrylamide.

15 Accordingly, in a first embodiment of the invention there is provided a process to improve the drainage rate and retention of fines during papermaking with a mechanical pulp-based furnish containing less than 5%, by weight of dry paper, of fillers in a papermaking process while maintaining sheet formation properties, comprising the steps of:

20 A. adding to an aqueous paper furnish containing pulp, sequentially or in combination:

- (i) a cationic or amphoteric starch; and
- (ii) a cationic polyelectrolyte; and

25 B. adding to said aqueous paper furnish containing pulp and said cationic or amphoteric starch and said cationic polyelectrolyte, a high molecular weight anionic acrylamide copolymer, wherein the molecular weight of said anionic acrylamide copolymer is greater than about 10,000,000,

wherein the papermaking process is substantially free of silica and bentonite, with no such materials intentionally added.

Detailed Description of the Invention

30 The present invention relates to a process for the manufacture of paper which provides rapid water drainage and good retention of fines during the forming and dewatering of a paper furnish. The present invention relates to improved water drainage and retention of fines in the formation of paper from a mechanical pulp containing furnish which is substantially unfilled. This refers to papers such as newsprint, directory, and ground wood specialty. Unfilled paper is substantially free of filler, generally containing less than 5%, by weight of dry paper, of filler, and often there is no deliberate addition of filler to the pulp from which the



paper or board is made. The paper often contains recycled fiber as a furnish component which may incorporate small (<5%) levels of fillers in the finished sheet.

5 The present invention relates to an additive combination for unfilled paper processing which enhances water drainage and retention of fines. The additive combination of the present invention is substantially free of microparticle treatment materials such as silica, polysilicate, polysilicate microgels, and clays such as bentonite. The term "substantially free" as used herein means that while a trace amount of such materials may be present, they are not intentionally added to and are not necessary to achieve the efficacy of the treatment combination of the present invention.

15 The treatment combination of the present invention comprises: an anionic, high molecular weight polyacrylamide; a cationic or amphoteric starch and an organic or inorganic cationic polyelectrolyte. The treatment combination of the present invention is added to an unfilled pulp furnish in a dosage (on an active product basis) of from about 2.5 to 20 lbs. per ton (1.25 to 10 kg/metric ton) of starch, about 0.25 to 1 lbs. per ton (0.125 to .5 kg/metric ton) of cationic organic polyelectrolyte, or about 5 lbs. per ton (2.5 kg per metric ton) inorganic cationic polyelectrolyte, and a 0.25 to 0.75 lbs. per ton (0.125 to 0.375 kg/metric ton) of high molecular weight anionic polyacrylamide. In use of the treatment combination, the order of addition between the starch and the cationic polyelectrolyte is interchangeable, although it is preferred to add the starch first.

20 Both the starch and the cationic polyelectrolyte must be added prior to addition of the anionic polyacrylamide.

25 The starch component of the treatment combination of the present invention may be dent corn, waxy maize, or potato-based and either



cationic or amphoteric in nature. The degree of quaternary ammonium substitution on the starch is preferably between about 0.1 and 0.4%, with about 0.3 to 0.4% most preferred.

5 The cationic polyelectrolyte component of the treatment combination of the present invention may be organic in nature, such as an epichlorohydrin-dimethylamine (EPI-DMA) condensate polymer, an EPI-DMA-ethylenediamine (EDA) condensation polymer, diallyldimethylammonium chloride (poly DADMAC) a polyethylene- imine, 10 or a polyamidoamine-based material. It may also be inorganic in nature such alum, polyaluminum chloride or other aluminum-based compounds.

15 The high molecular weight, anionic acrylamide of the present invention is preferably an essentially linear acrylamide/sodium acrylate copolymer. Other anionic acrylamide copolymers such as 2-acrylamido-2-methyl propane sulfonic acid (AMPS, a registered trademark of Lubrizol) would also be effective. By high molecular weight we referred to molecular weights preferably above 1,000,000 and most preferably above about 10,000,000. The mole percent anionic charge of the anionic 20 acrylamide component can range from about 20 to 70% with a 30 mole percent negative charge material found to be particularly effective.

25 The present invention will now be further described with reference to a number of specific examples, which are to be regarded solely as illustrative and not as restricting the scope of the present invention.

Examples

30 The data in the following examples was generated using a laboratory drainage device using a laboratory prepared 75% stone

ground wood/25% bleached soft wood kraft furnish. The drainage device drains stock through a 40 mesh wire while under the influence of vacuum. The vacuum reservoir set point remains constant throughout the test, but the level of vacuum under the wire changes as a function of drainage

5 rate, the air flow resistance of the wire, and the air flow resistance of the forming pad. Simultaneously, a rotating foil underneath the wire provides pressure pulses to the forming sheet. Drainage rate and vacuum level data are collected during a drainage process which typically lasts only a few seconds. The target retained basis weight on the wire is that of an

10 on machine application (for newsprint 48 grams per square meter). The amount of fibers required to meet the basis weight target is contained in a 250 gram dilute stock sample. When drainage has been completed, the vacuum continues to be applied to the formed pad for a fixed period of time. This allows an equilibrium vacuum level to be determined.

15 Three response variables were used to evaluate the effectiveness of the treatments tested. The corrected drainage time (CDT) based upon the elapsed time between the start of the test and the point where 90% of drainage has occurred (where 225 grams of filtrate has passed through

20 the wire). A linear correction is used to adjust the raw drainage time for differences between the actual OD pad mass and the target. The first pass fines retention (FPFR) was based upon the OD mass of the retained pad and the original stock dry mass and fines content and is calculated in a conventional fashion. The vacuum level in the cavity underneath the

25 wire reaches a maximum just before the air/water interface breaks through the wire. The ratio of this maximum to the equilibrium vacuum has been defined as the peak to equilibrium vacuum ratio (PEVR). The PEVR has been shown to be related to the effects of chemical treatment on sheet formation. A low PEVR is indicative of better sheet formation.

The data which the CDT and PEVR are based upon are generated via a high speed data acquisition system. Testing was done in five replicates per condition to increase the degree of data precision.

5 Example 1

In Table 1, the results of a treatment sequence of cationic starch/alum (a cationic polyelectrolyte)/anionic polyacrylamide with and without colloidal silica are summarized. In addition, the order of addition 10 of cationic starch and alum were reversed. A comparison when alum was replaced by an EPI/DMA/EDA condensation polymer is also shown. In Table 1 the materials employed were as follows: a cold water soluble amphoteric potato starch with a cationic degree of substitution of 0.3 mole percent; ANPAM, a polyacrylamide having a 30 mole percent 15 sodium acrylate/acrylamide ratio of high molecular weight. In Table 1 all dosages shown in parenthesis are stated in pounds per ton of actives. An untreated control and a conventional dual cationic treatment program of an EPI/DMA/EDA coagulant plus a cationic polyacrylamide were run for comparative purposes.

20

Table 1

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
	Starch (20)/Alum (5)/ANPAM (0.5)/Colloidal Silica (2)	2.46	17.19	1.49
25	Starch (20)/Alum (5)/ANPAM (0.5)	2.52	17.96	1.50
	Alum (5)/starch (20)/ANPAM (0.5)	2.49	23.66	1.42
30	Starch (20)/EPI/DMA/EDA (0.5)/ANPAM (0.5)	2.48	18.35	1.47
	Untreated Control	3.00	-5.25	1.88

The data in Table 1 shows that removing colloidal silica from a cationic starch/cationic polyelectrolyte/anionic high molecular weight polyacrylamide treatment shows no significant difference in drainage time, fines retention and PEVR. This was surprising due to prior art 5 teachings that colloidal silica or other micro particle material is essential in such treatments, and that anionic polyacrylamides are not favored as newsprint retention aids. The data also shows that an organic polyelectrolyte can be substituted for alum without significantly effecting the results, but may be used at only 10% of the alum dosage. In Table 1, 10 the negative value for FPFR untreated control is a result of the relatively coarse wire as compared to screens used for traditional stock fines fractionation. This means that stock retention on the wire during this test series is more difficult than any Britt fines fractionation jar.

15 Example 2

In Table 2, the testing, as summarized in Table 1, was repeated on a second, separately prepared batch of furnish. In addition, independent testing of starch, ANPAM, and alum were run.

20

Table 2

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
25	Starch (20)/Alum (5) ANPAM (0.5)/Colloidal Silica (1)	3.06	22.99	1.10
	Starch (20)/Alum (5)/ANPAM (0.5)	3.05	24.26	1.11
	Alum (5)/Starch (20)/ANPAM (0.5)	3.18	22.29	1.09
30	Starch (20)/EPI/DMA/EDA (0.5)/ANPAM (0.5)	3.18	22.80	1.15
	Starch (20)/ANPAM (0.5)	3.63	15.22	1.20

Table 2 - Continued

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
5	EPI/DMA/EDA (0.5)/ANPAM (0.5)	3.77	13.38	1.15
	Starch (20)	3.60	13.00	1.09
	Alum (5)	4.34	2.05	1.19
	ANPAM (0.5)	4.77	0.84	1.28
	Untreated Control	5.43	-0.90	1.34

10

Example 3

In Table 3 testing to evaluate the effects of cationic starch dosage was undertaken. The data shows that while the formation indicators remain relatively constant, there was a marked sensitivity to starch dosage in the drainage and retention responses.

Table 3

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
	Starch (20)/EPI/DMA/EDA (0.5)/ANPAM (0.5)	3.18	22.80	1.15
25	EPI/DMA/EDA (0.5)/Starch (20)/ANPAM (0.5)	3.22	22.89	1.14
	Starch (10)/EPI/DMA/EDA (0.5/ANPAM (0.5)	3.26	18.57	1.13
	EPI/DMA/EDA (0.5)/Starch (10)/ANPAM (0.5)	3.44	18.18	1.15
30	Starch (5)/EPI/DMA/EDA (0.5)/ANPAM (0.5)	3.38	16.84	1.15

Table 3 - Continued

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
5	EPI/DMA/EDA (0.5)/Starch(5)/ANPAM (0.5)	3.47	17.84	1.16
	Starch (0)/EPI/DMA/EDA (0.5)/ANPAM (0.5)	3.77	13.38	1.15
10	EPI/DMA/EDA (0.5)/Starch (0)/ANPAM (0.5)	3.77	13.38	1.15

Example 4

In Table 4, the effects of cationic polyelectrolyte dosage on the
15 combination of the present invention were studied.

Table 4

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
20	Starch (20)/EPI/DMA/EDA (1.0)/ANPAM (0.5)	3.03	23.54	1.10
	Starch (20)/ EPI/DMA/EDA (0.75)/ANPAM (0.5)	3.12	20.21	1.12
25	Starch (20)/ EPI/DMA/EDA (0.5)/ ANPAM (0.5)	3.18	22.80	1.15
	Starch (20)/ EPI/DMA/EDA (0.25)/ANPAM (0.5)	3.22	26.80	1.15
30	Starch (20)/EPI/DMA/EDA (0)/ANPAM (0.5)	3.63	15.22	1.20

Example 5

5 In Table 5, the effect of anionic, high molecular weight polyacrylamide dosage in the combination of the present invention and similar combinations, which include a colloidal silica, was tested.

Table 5

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR%</u>	<u>PEVR</u>
10	Starch (20)/Alum (5)/ANPAM (0.75)	3.02	26.42	1.18
	Starch (20)/Alum (5)/ANPAM (0.75)/Colloidal Silica (2)	2.90	25.48	1.14
15	Starch (20)/Alum (5)/ANPAM (0.5)	3.05	24.26	1.11
	Starch (20)/Alum (5)/ANPAM (0.5)//Colloidal Silica (1)	3.06	22.99	1.10
20	Starch (20)/Alum (50)/ANPAM (0.25)	3.22	19.24	1.09
	Starch (20)/Alum (5)/ANPAM (0.25)/Colloidal Silica (2)	3.04	22.19	1.12

Example 6

30 In Table 6(B), a variety of anionic, high molecular weight polyacrylamide polymers was evaluated. All of this type of polymer tested were efficacious. Products having 20 to 40 mole percent anionic range were preferred with Treatment B being most preferred. Table 6(A) summarizes the properties of anionic polymers tested.

TABLE 6(A)

	<u>Treatment</u>	<u>Form</u>	<u>Mole % AA</u>	<u>Relative Molecular Weight (10⁶)</u>
5	A	Powder	20	11
	B	Emulsion	30	21
	C	Powder	30	12
10	D	Emulsion	30	21
	E	Powder	30	18
	F	Emulsion	40	23
	G	Powder	40	18
	H	Powder	70	15
15	I	Powder	100	6

Table 6(B)

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
20	Starch (20)/EPI/DMA/EDA (0.5)/A(0.5)	3.26	19.22	1.16
	Starch (20)/EPI/DMA/EDA(0.5)/B (0.5)	3.03	23.54	1.10
	Starch (20)/EPI/DMA/EDA(0.5)/C (0.5)	3.27	15.32	1.14
	Starch(20)/EPI/DMA/EDA(0.5)/D (0.5)	3.31	18.23	1.20
25	Starch (20)/EPI/DMA/EDA(0.5)/E (0.5)	3.23	19.61	1.16
	Starch (20)/EPI/DMA/EDA(0.5)/F (0.5)	3.17	23.48	1.12
	Starch (20)/EPI/DMA/EDA(0.5)G (0.5)	3.34	17.76	1.14
	Starch (20)/EPI/DMA/EDA(0.5)/H (0.5)	3.37	13.24	1.19
	Starch (20)/EPI/DMA/EDA(0.5)/I (0.5)	3.44	9.66	1.22

Example 7

5 In Table 7(B), the effect of various organic cationic polyelectrolyte materials in the combination of the present invention was tested. All of the tested materials were efficacious. Table 7(A) summarizes the properties of the organic cationic polyelectrolytes tested.

Table 7(A)

10	<u>Treatment</u>	<u>Description</u>
	J	Branched EPI/DMA/EDA condensate
15	K	Linear EPI/DMA condensate - lower molecular weight
	L	Linear EPI/DMA condensate - higher molecular weight
20	M	Poly diallyldimethylammonium dichloride (DADMAC)-lower molecular weight
	N	Poly diallyldimethylammonium chloride - higher molecular weight
25	O	Polyamidopolyamine epichlorohydrin condensate
	P	Polyethyleneimine

Table 7(B)

30	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
	Starch (5)/J (0.5)/ANPAM (0.5)	3.04	10.97	1.18
35	Starch (5)/K (0.5)/ANPAM (0.5)	3.25	10.79	1.23
	Starch (5)/L (0.5)/ANPAM (0.5)	3.21	9.46	1.25
	Starch (5)/M (0.5)/ANPAM (0.5)	3.15	13.58	1.22

Table 7(B) - Continued

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
5	Starch (5)/N (0.5)/ANPAM (0.5)	3.16	14.57	1.27
	Starch (5)/O (0.5)/ANPAM (0.5)	3.40	9.35	1.28
	Starch (5)/P (0.5)/ANPAM (0.5)	3.05	22.33	1.24

Example 8

10 In Table 8(B), the efficacy of various modified starches in the combination of the present invention was tested. All of the starches tested were efficacious. In general, the more highly substituted starches were preferred. Table 8(A) summarizes the properties of commercially 15 available starches tested.

Table 8(A)

	<u>Treatment</u>	<u>Source</u>	<u>Degree of Cationic Substit. (Mole %)</u>	<u>Ionic Function</u>	<u>Degree of Anionic Substit. (Mole %)</u>	<u>Ionic Function</u>
20	Q	Potato-Cold Water Soluble	0.30	Quat. Amine	unknown	phosphate
25	R	Dent Corn	0.20	Quat. Amine	0	
30	S	Dent Corn	0.28	Quat. Amine	0	
35	T	Dent Corn	0.35	Quat. Amine	0	
	U	Waxy Maize	0.18	Quat. Amine	0	

Table 8(A) - Continued

			Degree of Cationic Substit. (mole %)	Ionic Function	Degree of Anionic Substit. (mole %)	Ionic Function
5	<u>Treatment</u>	<u>Source</u>				
	V	Waxy Maize	0.28	Quat. Amine	0	
10	W	Waxy Maize	0.35	Quat. Amine	0	
15	X	Potato	0.18	Quat. Amine	0.3	phosphate
	Y	Potato	0.28	Quat. Amine	0.3	phosphate
20	Z	Potato	0.35	Quat. Amine	0.3	phosphate

Table 8(B)

	<u>Treatment</u>	<u>CDT(Sec.)</u>	<u>FPFR %</u>	<u>PEVR</u>
25	Q (10)/J(0.5)/ANPAM (0.5)	3.03	17.71	1.25
	R (10)/J(0.5)/ANPAM (0.5)	3.00	20.82	1.24
	S (10)/J (0.5)/ANPAM (0.5)	3.02	16.49	1.32
	T (10)/J (0.5)/ANPAM (0.5)	2.96	21.39	1.22
30	U (10)/J (0.5)/ANPAM (0.5)	2.97	17.58	1.24
	V (10)/J (0.5)/ANPAM (0.5)	3.08	17.41	1.23
	W (10)/J (0.5)/ANPAM (0.5)	2.94	22.87	1.22
	X (10)/J (0.5)/ANPAM (0.5)	3.05	14.13	1.25
	Y (10)/J (0.5)/ANPAM (0.5)	3.02	17.44	1.25
35	Z (10)/J (0.5)/ANPAM (0.5)	2.94	22.64	1.22

The claims defining the invention are as follows:

1. A process to improve the drainage rate and retention of fines during papermaking with a mechanical pulp-based furnish containing less than 5%, by weight of 5 dry paper, of fillers in a papermaking process while maintaining sheet formation properties, comprising the steps of:

A. adding to an aqueous paper furnish containing pulp, sequentially or in combination:

- 10 (i) a cationic or amphoteric starch; and
- (ii) a cationic polyelectrolyte; and

B. adding to said aqueous paper furnish containing pulp and said cationic or amphoteric starch and said cationic polyelectrolyte, a high molecular weight anionic acrylamide copolymer, wherein the molecular weight of said anionic acrylamide copolymer is greater than about 10,000,000,

15 wherein the papermaking process is substantially free of silica and bentonite, with no such materials intentionally added.

2. The process of claim 1 wherein said cationic or amphoteric starch is selected from the group consisting of potato starch, dent corn starch, and waxy maize starch.

3. The process of claim 2 wherein said starch has a degree of quaternary 20 ammonium substitution between about 0.1 and 0.4%.

4. The process of any one of claims 1 to 3 wherein said cationic polyelectrolyte is selected from the group consisting of epichlorohydrin-dimethylamine condensation polymers, epichlorohydrin-dimethylamine-ethylenediamine condensation polymers, diallyldimethylammonium chloride, polyethyleneimines, polyamidoamines, alum, and 25 polyaluminium chloride.

5. The process of claim 1 wherein said acrylamide copolymer is a linear acrylamide/sodium acrylate copolymer.

6. The process of claim 1 wherein said acrylamide copolymer is a linear acrylamide/2-acrylamide-2-methyl propane sulfonic acid.

30 7. The process of claim 1 wherein the mole percent anionic charge of said acrylamide copolymer ranges from about 20% to about 70%.

8. A process to improve the drainage rate and retention time of fines during papermaking with a mechanical pulp-based furnish, substantially as hereinbefore described with reference to any one of the examples.

35

Dated 25 September, 2002

BetzDearborn Inc.

Patent Attorneys for the Applicant/Nominated Person
SPRUSON & FERGUSON

