




(72) DHANUKA, Vinodkumar Ramniranjan, IN

(72) PACHA, Fakhruddin Esmail, IN

(71) UNILEVER PLC, GB

(51) Int.Cl.⁶ C11D 17/06

(30) 1995/12/20 (9526097.2) GB

(54) **PROCEDE POUR PREPARER UN DETERGENT GRANULAIRE**

(54) **A PROCESS FOR PREPARING A GRANULAR DETERGENT**

(57) L'invention concerne un procédé pour produire un détergent en poudre ou une composition pour ce détergent, consistant à effectuer une granulation dans un granulateur à cisaillement élevé ou bas, suivie par une granulation dans un mélangeur à cisaillement très bas, par exemple dans un lit fluidisé. Le procédé permet de produire des poudres ayant une densité apparente choisie dans une plage très large, sans étape d'atomisation.

(57) A process for producing a detergent powder or a composition therefor involving partial granulation in a high or low shear granulator followed by granulation in a very low shear mixer, for example a fluid bed is disclosed. The process allows powders to be produced over a wide range of bulk densities without the use of a spray-drying step.

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C11D 17/06	A1	(11) International Publication Number: WO 97/22685 (43) International Publication Date: 26 June 1997 (26.06.97)
(21) International Application Number: PCT/EP96/05582 (22) International Filing Date: 2 December 1996 (02.12.96) (30) Priority Data: 9526097.2 20 December 1995 (20.12.95) GB (71) Applicant (for AU BB CA GB IE IL KE LC LK LS MG MW NZ SD SG SZ TT UG only): UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB). (71) Applicant (for all designated States except AU BB CA GB IE IL KE LC LK LS MG MW NZ SD SG SZ TT UG): UNILEVER N.V. [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL). (72) Inventors: DHANUKA, Vinodkumar, Ramniranjan; 306, Par- ijat, Lallubhai Park Road, Vile Parle West, Mumbai, Maharashtra-400056 (IN). PACHA, Fakhruddin, Esmail; B-11, Nazir Apartments, 139 Azad Road, Vile Parle East, Mumbai, Maharashtra-400057 (IN). (74) Agent: MOLE, Peter, Geoffrey; Unilever plc, Patent Division, Colworth House, Sharnbrook, Bedford MK44 1LQ (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: A PROCESS FOR PREPARING A GRANULAR DETERGENT (57) Abstract A process for producing a detergent powder or a composition therefor involving partial granulation in a high or low shear granulator followed by granulation in a very low shear mixer, for example a fluid bed is disclosed. The process allows powders to be produced over a wide range of bulk densities without the use of a spray-drying step.		

A PROCESS FOR PREPARING A GRANULAR DETERGENT

The present invention relates to a process for the preparation of granular detergent or cleaning compositions with a wide range of bulk densities of between about 300-1300 g/l. More particularly the process of the invention makes use of a novel combination of high or low speed mixer/granulator in combination with a very low shear granulator. There has been considerable interest in detergent industry to develop processes for the production of granulated detergent powders exhibiting specific bulk densities. In the detergent industry powders exhibiting different bulk densities are available and specific processes are used to target specific ranges of bulk densities.

There are a number of single step processes which produce powders within a very narrow range of bulk densities. Two stage granulation processes for production of powders of bulk densities greater than 600 g/l are also known.

JP 60 072 999A (Kao) and GB 2 166 452B (Kao) disclose processes in which detergent sulphononic acid, sodium carbonate and water are mixed in a strongly shearing apparatus; the solid mass obtained is cooled to 40°C or below and pulverized; and the fine powder thus obtained is granulated.

There has also been considerable recent interest in the use of high-speed mixer/granulators in the preparation of high-bulk-density detergent powders. For example, EP 158 419B (Hashimura) discloses a process in which nonionic surfactant and soda ash are mixed and granulated in a reactor having horizontal and vertical blades rotating at different speeds, to give a detergent powder built with sodium carbonate and containing a high level of nonionic surfactant.

RECEIVED
JAN 10 1998
PCT/EP96/05582

C2016

2

Patent Application No. WO93/23523 describes a process for the continuous production of granular detergent and/or cleaning compositions exhibiting bulk densities between 600 and 1100 g/l by a two-stage granulation in two mixer/granulators arranged in series where 40-100% of the solid and liquid ingredients based on the total weight of solid and liquid ingredients used is pregranulated in a first low speed mixer granulator and the granulate from the first stage is mixed with the remaining solid and/or liquid ingredients in a second high speed mixer granulator and converted into a granulate where the content of the granules having diameters greater than 2 mm is less than 25 wt. per cent. The low speed granulator used in the first granulation stage provided peripheral velocities of the mixing elements between 2 m/s and 7 m/s. Preferred low speed mixer granulators are, e.g., the plough mixers made by Lodige, Germany and the intensive mixer made by IMA PVC, Germany. The high speed mixer granulator provides for a peripheral velocity of the mixing elements of 8 m/s to 35 m/s. A suitable high speed mixer granulator is, for example, that made by Schugi, The Netherlands.

EP 0 264 049 describes a three-step process for the preparation of dyestuff granules comprising a two-step granulation phase followed by a drying step. Granulation is performed by mixing in a high-speed mixer/granulator and directly feeding the obtained product into a slow-speed mixer/granulator, a granulation liquid being added in both granulation steps. The material leaving the slow-speed mixer/granulator is then fed directly into a fluid-bed drier, where it is sprayed with a formulation aid.

AMENDED SHEET

C2016

2a

Indian Patent No. 170497 describes a process for preparing a high bulk density granular detergent composition with bulk density of at least 650 g/l which comprises treating a particulate starting material in a first step in a high speed mixer/densifier, the mean residence time being about 5-30 seconds and in a second step in a moderate-speed granulator/densifier whereby it is brought into or maintained in a deformable stage, the mean residence time being 1-10 minutes, and a final step in a drying and/or cooling apparatus. Preferably, the particle starting material is already brought into and/or maintained in a deformable stage in the first step. An example of a suitable high speed mixer/densifier which may be used in this process is Lodige

AMENDED SHEET

C2016

3

CB30 recycler. Other examples of suitable high speed mixers/densifiers are, for instance, Schugi® granulator or a Draise® .K-TTP80. An example of a suitable moderate speed granulator/densifier which may be used in this process is a Lodige® KM300 mixer also referred to as a plough share mixer. Another suitable machine is, for example, Draise® K-T160.

EP-A-544 356 describes a detergent composition and a continuous process of producing detergent powders having bulk density of, for example, 600 g/l and above. This invention comprises treating a particulate starting material in a high speed mixer/densifier characterised in that 0.1-50% by weight as calculated on the granular detergent surfactant of liquid surfactant composition is mixed with the starting material during the treating process. For obtaining a very high bulk density powder, the detergent powder obtained by the process of the invention may be further treated in a second step in a moderate speed granulator/densifier whereby it is brought into or maintained in a deformable state, the mean residence time being 1-10 minutes and thereafter in a third step in drying/cooling apparatus for example as described in EP-A-367, 339.

Thus, high bulk density powders have either been produced by a single step granulation or by a suitable combination of a low speed mixer granulator in combination with a high speed mixer granulator or a high speed mixer granulator combined with a low speed mixer granulator. The low speed mixer granulators generally operate with tip speeds in the range 2-7 m/s and the high speed granulators operate with tip speeds in the range 8-35 m/s.

It is an object of the present invention to provide a process for preparing granular detergent or cleaning compositions in

AMENDED SHEET

C2016

4

which the bulk density of the compositions may be selected as desired between 300 - 1300 g/l.

5 We have found that granular detergents or cleaning compositions having bulk densities between 300 - 1300 g/l may be produced by effecting partial granulation in a high or low speed mixer granulator optionally with simultaneous heating and/or drying and/or cooling followed by completion of granulation under very low shear optionally with drying or
10 cooling. The desired bulk density of a granular composition may be obtained by appropriately regulating the granulation steps in the two different granulation stages.

15 Thus the present invention relates to a process for preparing granular detergents or cleaning compositions having bulk densities between 300 - 1300 g/l comprising -

mixing a particulate starting material in a low or high speed mixer/granulator;

20 adding a liquid binder and subjecting the mixture to partial granulation in the low or high speed mixer/granulator;

25 transferring the partially granulated mixture to a very low shear granulator selected from the group consisting of fluid bed and rotating bowl mixer/granulators;

30 adding further liquid binder to the mixture for a time sufficient to complete granulation and to thereby obtain a granular powder composition of desired bulk density.

Preferably, the process according to the invention comprises -

AMENDED SHEET

C2016

5

i) placing all the particulate starting materials including a builder and an alkaline inorganic material and optionally flow aids in a low or high speed mixer/granulator;

5

ii) mixing the particulate starting materials to obtain a substantially uniform particulate mix;

10

iii) adding a predetermined quantity of liquid binder to effect simultaneous granulation of the particulate mix, to provide a part-granulated powdered mix;

15

iv) introducing said part granulated powdered mix into a fluid bed or rotating bowl mixer/granulator, and;

v) adding the balance quantity of liquid binder to complete the granulation process over a sufficient time to obtain the required properties of the powder.

20

A preferred bulk density range for the final product is from 350 to 1000 g/l.

25

The quantities of liquid binder added in steps (iii) and (v) depends upon the final product density desired, as explained below.

30

The extent of granulation in the low or high speed mixer/granulation and the very low shear granulator can be controlled typically as below depending on the final product density desired.

35

If the powder bulk density is at the low end, i.e. 300-650 g/l, more preferably from 350-650 g/l, then preferably from 5% to 75% by weight of the total liquid binder should be added in the low/high speed mixer. Then, the remaining 95%

AMENDED SHEET

C2016

6

to 25% of the total liquid binder should be added in the very low shear granulator.

If, on the other hand, the bulk density is at the higher end, i.e. 550-1300 g/l, more preferably from 550-1000 g/l, then preferably from 75% to 95% by weight of the total liquid binder should be added in the low/high speed mixer. Then, the remaining 25% to 5% of the total liquid binder should be added in the very low shear granulator.

Obviously, there is some overlap in the aforementioned ranges. However, the low end range could be applicable to 300 (or 350) to 550 g/l bulk density and/or the higher end to 650 to 1300 (or 1000) g/l.

The process of the invention may be carried out in batch or continuous mode of operation.

The choice of the high or low speed mixer/granulator is important. Suitable examples of high speed mixers of the present invention include the Lodige® CB machine and suitable examples of moderate speed mixers include the Lodige® KM machine. Other suitable equipment include the Drais® T160 series manufactured by Draise Werke GmbH, Germany; the Littleford mixer with internal chopping blades, and the turbine type miller mixer having several blades on an axis of rotation. A low or high speed mixer granulator has a stirring action and/or a cutting action which may be operated independently of one another. Preferred types of low or high speed mixer granulator are mixers of the Fukae® FS-G series; Diosna® V series ex Dierks & Sohne, Germany; Pharma Matrix® ex T.K. Fielder Ltd;, England. Other mixers suitable for use in the process of the invention are the Fuji® VG-C series ex Fuji Sangyo Co., Japan; the Roto® ex Zanchetta & Co. srl, Italy and Schugi® Flexomix granulator.

C2016

7

Yet another mixer found to be suitable for use in the process of the invention is the Lodige (Trade Mark) FM series (ploughshare mixers) batch mixer ex Morton Machine Co. Ltd., Scotland or a Farberg mixer.

5

The typical tip velocity of these mixers is in the range of 1 - 40 m/s.

10

Preferred very low shear granulators or mixer/granulators are fluid bed and rotating bowl mixers. A typical fluidised bed is operated at a superficial air velocity of about 0.1-1.5 m/s, either under positive or negative pressure and an inlet air temperature ranging from -10°C or 5°C to 80°C or even up to 200°C.

15

20

According to the present invention a final granulometry may be defined, for example that percentage of particles falling within a given size range. The mixture of particulate starting material and liquid binder is then granulated in the high/low speed mixer/granulator to a granulometry different to the final granulometry, for example having a greater quantity of fine particles. The partially granulated mixture is then granulated to the final granulometry in the very low shear granulator. Densification of the material may occur simultaneously with granulation in the high/low speed mixer/granulator, or very low shear granulator. Granular detergent compositions according to the present invention should preferably have less than 5% by weight of granules less than 180 microns in diameter.

25

30

The process of the invention is highly flexible in terms of the selection of actives, their levels, the formulations.

35

Preferably, the products of the process of the invention contain anionic surfactant.

The process of the present invention is especially flexible concerning the particulate starting materials. The starting material is suitably chosen from the compounds commonly used in detergent formulations such as builders, alkaline salts, detergent active materials and mixtures thereof. Compositions containing phosphate and/or zeolite are preferably used as starting materials.

The process may with advantage be used to prepare detergent compositions containing from 5 to 50 wt%, especially from 15 to 35 wt%, of anionic surfactant, this anionic surfactant being derived wholly or in part from an in situ neutralisation reaction in steps (iii) and/or (v).

The liquid binder may comprise, water, anionic surfactant, nonionic surfactant or mixtures thereof.

The process of the invention is of special interest for the production of detergent powders of components containing relatively high levels of anionic surfactant, for example, from 18 to 35 wt%, more especially 15 to 30 wt%, but it is equally useful for the preparation of powders containing lower levels of anionic surfactant for example up to 20 wt% and including the particulate starting material which very preferably contains an alkaline inorganic material, preferably an alkaline salt, in particular an alkaline carbonate, bicarbonate or mixture thereof.

Preferably, the unneutralised acid is added in a substantially stoichiometric amount. It is, however, possible that the alkaline material could be in excess. For example, the excess alkaline material may act as a builder.

In order to produce anionic surfactant in-situ the particulate starting material preferably contains a solid

alkaline material, for example sodium carbonate and the liquid binder preferably contains an acid corresponding to the anionic surfactant to be produced, for example LAS acid.

The anionic surfactant prepared at least in part by in situ neutralisation may, for example, be selected from linear alkylbenzene sulphonates, alpha-olefin sulphonates, internal olefin sulphonates, fatty acid ester sulphonates and combinations thereof. The process of the invention is especially useful for producing compositions containing alkylbenzene sulphonates, by in situ neutralisation of the corresponding alkylbenzene sulphonic acid.

The present inventors have discovered that the final bulk density of the product of the present process may be altered by varying the percentage of unneutralised acid added in the high/low speed mixer/granulator and in the very low shear granulator. For a low bulk density, the greater part of the unneutralised acid should be added in the very low shear granulator. For example, the respective quantities of unneutralised liquid acid added in the two steps may be as set out on page 6 above.

Other anionic surfactants that may be present in compositions prepared by the process of the invention include primary and secondary alkyl sulphates, alkyl ether sulphates, and dialkyl sulphosuccinates and mixtures thereof. Anionic surfactants are of course well known and the skilled reader will be able to add to this list by reference to the standard textbooks on this subject.

If an especially high content of anionic surfactant in the final product is desired, additional anionic surfactant, in salt form rather than in acid precursor form, may be added after granulation. Solid particulate anionic surfactant may

also be added at an earlier stage in the process. Thus, the process of the invention represents a versatile route for incorporating high levels of anionic surfactant in powders.

As previously indicated, nonionic surfactants and/or high active mixtures may also be present. These too are well known to those skilled in the art, and include primary and secondary alcohol ethoxylates. Neutralised anionic surfactant may be mixed with non-ionics surfactants.

Other types of non-soap surfactant, for example, cationic, zwitterionic, amphoteric or semipolar surfactants, may also be present, if desired. Many suitable detergent-active compounds are available and are fully described in the literature, for example, in "Surface-Active Agents and Detergents", Volumes I and II, by Schwartz, Perry and Berch.

If desired, soap may also be present, to provide foam control and additional detergency and builder properties.

The detergency builder present in the starting material may be any conventional builder used for removing the free calcium ions in wash liquor and for other known benefits associated with builders. Examples of suitable builders include tripolyphosphate salts, for example of sodium, zeolite, citrates, soda ash, layered silicates etc. The amount of builder material incorporated as part of the starting material is such that the final builder content in the composition is between 5 to 60% and preferably between 10 to 35% by weight.

Typically, detergent compositions produced by the process of the invention may comprise from 0 to 40 wt% of anionic surfactant, from 0 to 30 wt% of nonionic surfactant and from 0 to 5 wt% of fatty acid soap.

C2016

11

The detergent compositions of the present invention may be complete detergent compositions in themselves, or they may be used as detergent components which may be mixed with other conventional materials, for example bleaches and enzymes to produce a fully formulated product.

The detergent composition may optionally comprise of one or more flow aids which may be selected from dicamol, crystalline or amorphous alkali silicates, calcites, diatomaceous earth, precipitated silica, magnesium sulphate, precipitated calcium carbonate, or mixtures thereof etc. The flow aid may be present in a quantity of 0.1-15 wt%.

Detergent compositions that may be prepared by the process of the invention may contain appropriate amounts of other conventional ingredients, for example filler (for example, an inorganic salt such as NaCl), bleaches, enzymes, lather boosters or lather controllers as appropriate, antiredeposition and anti-incrustation agents, perfumes, dyes and fluorescers. These may be incorporated in the product at any suitable stage, and the skilled detergent formulator will have no difficulty in deciding which ingredients are suitable for admixture in the low or high-shear mixer/granulator, or the very low shear granulator.

The compositions may contain a total of from 10 to 70 wt% of water-soluble crystalline inorganic salts, which may comprise, for example, sodium carbonate, sodium sulphate, sodium tripoly-phosphate, sodium ortho- or pyrophosphate, or sodium meta- or orthosilicate. Especially preferred compositions contain from 10 to 50 wt%, of soluble crystalline inorganic salts.

Where the very low shear granulator comprises a fluidised bed, very fine particles will automatically be elutriated.

AMENDED SHEET

C2016

12

The resulting fine powder removed by the air stream from the fluidised bed may be returned to the very low shear granulator or to the high/low speed mixer/granulator.

- 5 The invention will now be illustrated by way of example with reference to the following Examples.

EXAMPLE I

- 10 11 Kgs of Sodium Tripolyphosphate, 15 Kgs of Soda Ash and 13 Kgs of fine salt were charged into a ploughshare mixer. The mass was mixed for 30 seconds. 1 Kg of sulphonic acid was incorporated into the ploughshare mixer for a period of over 2 to 5 minutes while continuing to run the main agitator and chopper. Thereafter 1 Kg of precipitated silica was
15 added to the mixer and mixed for 30 seconds.

The partly granulated powder was transferred to a fluid bed. The part granulated powder was fluidised by supply of air.

20

9 Kg. of sulphonic acid was sprayed onto the mass using a twin fluid atomiser to complete granulation. The powder was discharged and sieved through a 10 mesh sieve.

25

The bulk density was 480 g/l.

EXAMPLES II-VI

30

The procedure of example I was repeated by altering the amount of addition of the sulphonic acid in the two stages. The bulk densities of the final powder were measured and these are listed in Table I.

TABLE I

EXAMPLES	LAS Addition (Kg)		Product BD (g/l)
	In Ploughshare	In Fluid Bed	
I	1	9	480
II	2.5	7.5	500
III	5	5	530
IV	7.5	2.5	550
V	8.5	1.5	600
VI	9	1	750

EXAMPLE VII

12 Kg of Sodium tripolyphosphate, 5 Kg of zeolite and 20 Kg of Soda ash were mixed in a ploughshare mixer for 30 Sec. 2 Kg of Sulphonic acid was sprayed over one minute while the mixture was agitated and chopped. The entire mass was transferred to a fluid bed and fluidised by supply of air and 12 Kg Sulphonic acid was sprayed using a twin fluid atomiser. The powder was discharged and sieved through a 10 mesh sieve. The bulk density of this powder was 400 g/l.

EXAMPLE VIII

12 Kg of Sodium sulphate, 10 Kg of sodium carbonate, 13 Kg of zeolite was charged into a ploughshare mixer. The mass was mixed for 30 seconds. 1.5 Kg of molten stearic acid followed by 2.5 Kg of Non-ionics ($C_{12}EO_5$) and 2.5 Kg sulphonic acid were added into the ploughshare mixer over 5 minutes while continuing to run the main agitator and chopper. 1.75 Kg of

silicate solution (40% concentration) was also added to the mixer and mixed for 2 minutes.

The partly granulated powder was transferred to a fluid bed and fluidised by supply of air. 0.5 Kg of sulphonic acid was sprayed on to the mass using a twin fluid atomiser to complete granulation. The powder was discharged and sieved through a 10 mesh sieve. The bulk density was 900 g/l.

EXAMPLES IX

22.5 kg of sodium chloride, 16 kg of sodium carbonate, 1.5 kg of precipitated calcium carbonate and 1 kg of Dicomol was charged into a ploughshare mixer. The mass was mixed for 30 seconds. 2.5 kg of sulphonic acid was sprayed over one minute while the mixture was agitated and chopped. The entire mass was transferred to a fluid bed and fluidised by supply of air was transferred to a fluid bed and fluidised by supply of air and 6.5 kg sulphonic acid was sprayed using a twin fluid atomiser. The powder was discharged and sieved through a 10 mesh sieve. The bulk density of this powder was 550 g/l.

EXAMPLE X

22.5 kg of sodium sulphate, 13.7 kg of sodium carbonate, 1 kg of STPP and 2 kg of zeolite was charged into a ploughshare mixer. The mass was mixed for 30 seconds. 2.5 kg of sulphonic acid was sprayed over one minute while the mixture was agitated and chopped. The entire mass was transferred to a fluid bed and fluidised by supply of air and 5.3 kg sulphonic acid was sprayed using a twin fluid atomiser. The powder was discharged and sieved through a 10 mesh sieve. The bulk density of this powder was 650 g/l.

C2016

15

CLAIMS

1. A process for preparing a granular detergent or cleaning composition or component having a bulk density between 300 and 1300 g/l comprising mixing a particulate starting material in a low or high speed mixer/granulator, adding a liquid binder to the mixer/granulator and subjecting the resulting mixture to partial granulation, to produce a partially granulated mixture, transferring partially granulated mixture to a fluid bed or rotating bowl mixer/granulator, adding further liquid binder to the mixture for a time sufficient to complete granulation and thereby to obtain the granular powder composition of desired bulk density.

2. A process according to claim 1 in which the partially granulated mixture is transferred to a fluid bed.

3. A process according to claim 1 or claim 2 in which the particulate starting material comprises a detergent builder.

4. A process according to any preceding claim in which the liquid binder comprises an acid precursor of an anionic surfactant.

5. A process according to any preceding claim in which the particulate starting material comprises alkaline inorganic material, preferably an alkali metal carbonate.

6. A process according to claim 5, wherein the alkaline inorganic material is present in an amount in stoichiometric excess of the acid precursor of the anionic surfactant.

C2016

16

7. A process according to any preceding claim, for producing a granular, detergent or cleaning composition or component of bulk density in the region of 350 - 650 g/l comprises the steps of:

5

(a) adding from 5 to 75% by weight of the total amount of liquid binder to the low/high speed mixer/granulator; and

10

(b) adding the remaining from 95 to 25% by weight of the total amount of liquid binder in the fluid bed or rotating bowl mixer/granulator.

15

8. A process according to claims 1 - 6, being for preparing a granular detergent or cleaning composition or component having a bulk density in the range 550 - 1000 g/l comprising the steps of:

20

(a) adding from 75 to 95% by weight of the total amount of liquid binder in the low/high speed mixer/granulator; and

25

(b) adding the remaining from 25 to 5% by weight of the total liquid binder in the fluid bed or rotating bowl mixer/granulator.

30

9. A process according to any preceding claim, being for producing a granular detergent component or composition containing anionic surfactant.

C2016

16a

10. A granular detergent or cleaning composition or component produced by the process of any preceding claim, and comprising:

5 from 5 to 50% by weight of anionic surfactant,
preferably from 15 to 30% by weight anionic surfactant,

from 0 to 40% by weight of nonionic surfactant,

10 from 0 to 5% by weight of fatty acid soap, and

from 5 to 60% by weight, preferably from 10 to 35% by weight, builder material.