



- (51) **International Patent Classification:**
C03C 8/04 (2006.01) C03C 8/24 (2006.01)
- (21) **International Application Number:**
PCT/US2012/053010
- (22) **International Filing Date:**
30 August 2012 (30.08.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
13/238,358 21 September 2011 (21.09.2011) US
- (71) **Applicant (for all designated States except US):** GUARD-
IAN INDUSTRIES CORP. [US/US]; 2300 Harmon
Road, Auburn Hills, MI 48326-1714 (US).
- (72) **Inventor; and**
- (75) **Inventor/Applicant (for US only):** DENNIS, Timothy, A.
[US/US]; 4226 Bloomdale Road, Bloomdale, OH 44817
(US).
- (74) **Agent:** RHOA, Joseph, A.; Nixon & Vanderhye P.C., 901
North Glebe Road, 11th Floor, Arlington, VA 22203-1808
(US).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) **Title:** VANADIUM -BASED FRIT MATERIALS AND METHODS OF MAKING THE SAME




FIG. 4

(57) **Abstract:** Certain example embodiments relate to improved seals for glass articles. Certain example embodiments relate to a composition used for sealing an insulated glass unit. In certain example embodiments the composition includes in mol % 45-50 vanadium oxide, 20-23 barium oxide, 9-12 zinc oxide, and at least four additional additives. For instance, another additive that is a different metal oxide or different metal chloride may be provided. In certain example embodiments, a vacuum insulated glass unit includes first and second glass substrates that are sealed together with a seal that includes the above-described composition.

VANADIUM-BASED FRIT MATERIALS AND METHODS OF MAKING THE SAME**CROSS REFERENCE TO RELATED APPLICATION**

[0001] This application is a continuation-in-part of U.S. Application No. 12/929,875, filed February 22, 2011, the entire contents of which are hereby incorporated by reference.

FIELD OF THE INVENTION

[0002] Certain example embodiments of this invention relate to improved frit materials for glass articles (e.g., for use in vacuum insulated glass or VIG units), and/or methods of making the same, as well as articles including such improved frit materials and/or methods of making the same. More particularly, certain example embodiments relate to vanadium-based frit materials having a reduced melting point, and/or methods of making the same. In certain example embodiments, the improved insulated seals are used in connection with vacuum insulated glass (VIG) units, and/or a method is provided for sealing VIG units with the improved seals.

BACKGROUND AND SUMMARY OF EXAMPLE EMBODIMENTS OF THE INVENTION

[0003] Vacuum IG units are known in the art. For example, see U.S. Patent Nos. 5,664,395, 5,657,607, and 5,902,652, the disclosures of which are all hereby incorporated herein by reference.

[0004] Figs. 1-2 illustrate a conventional vacuum IG unit (vacuum IG unit or VIG unit). Vacuum IG unit 1 includes two spaced apart glass substrates 2 and 3, which enclose an evacuated or low pressure space 6 there between. Glass sheets/substrates 2 and 3 are interconnected by peripheral or edge seal of fused solder glass 4 and an array of support pillars or spacers 5.

[0005] Pump out tube 8 is hermetically sealed by solder glass 9 to an aperture or hole 10 which passes from an interior surface of glass sheet 2 to the bottom of recess 11 in the exterior face of sheet 2. A vacuum is attached to pump out tube 8 so that the interior cavity between substrates 2 and 3 can be evacuated to create a low pressure area or space 6. After

evacuation, tube 8 is melted to seal the vacuum. Recess 11 retains sealed tube 8. Optionally, a chemical getter 12 may be included within recess 13.

[0006] Conventional vacuum IG units, with their fused solder glass peripheral seals 4, have been manufactured as follows. Glass frit in a solution (ultimately to form solder glass edge seal 4) is initially deposited around the periphery of substrate 2. The other substrate 3 is brought down over top of substrate 2 so as to sandwich spacers 5 and the glass frit/solution there between. The entire assembly including sheets 2, 3, the spacers, and the seal material is then heated to a temperature of approximately 500°C, at which point the glass frit melts, wets the surfaces of the glass sheets 2, 3, and ultimately forms hermetic peripheral or edge seal 4. This approximately 500°C temperature is maintained for from about one to eight hours. After formation of the peripheral/edge seal 4 and the seal around tube 8, the assembly is cooled to room temperature. It is noted that column 2 of U.S. Patent No. 5,664,395 states that a conventional vacuum IG processing temperature is approximately 500°C for one hour. Inventors Lenzen, Turner and Collins of the '395 patent have stated that "the edge seal process is currently quite slow: typically the temperature of the sample is increased at 200°C per hour, and held for one hour at a constant value ranging from 430°C and 530°C depending on the solder glass composition." After formation of edge seal 4, a vacuum is drawn via the tube to form low pressure space 6.

[0007] The composition of conventional edge seals are known in the art. See, for example, U.S. Patent Nos. 3,837,866; 4,256,495; 4,743,302; 5,051,381; 5,188,990; 5,336,644; 5,534,469; 7,425,518, and U.S. Publication No. 2005/0233885, the disclosures of which are all hereby incorporated herein by reference.

[0008] Unfortunately, the aforesaid high temperatures and long heating times of the entire assembly utilized in the formulation of edge seal 4 are undesirable. This is especially the case when it is desired to use a heat strengthened or tempered glass substrate(s) 2, 3 in the vacuum IG unit. As shown in Figs. 3-4, tempered glass loses temper strength upon exposure to high temperatures as a function of heating time. Moreover, such high processing temperatures may adversely affect certain low-E coating(s) that may be applied to one or both of the glass substrates in certain instances.

[0009] Fig. 3 is a graph illustrating how fully thermally tempered plate glass loses original temper upon exposure to different temperatures for different periods of time, where the original center tension stress is 3,200 MU per inch. The x-axis in Fig. 3 is exponentially representative of time in hours (from 1 to 1,000 hours), while the y-axis is indicative of the

percentage of original temper strength remaining after heat exposure. Fig. 4 is a graph similar to Fig. 3, except that the x-axis in Fig. 4 extends from zero to one hour exponentially.

[0010] Seven different curves are illustrated in Fig. 3, each indicative of a different temperature exposure in degrees Fahrenheit ($^{\circ}\text{F}$). The different curves/lines are 400°F (across the top of the Fig. 3 graph), 500°F , 600°F , 700°F , 800°F , 900°F , and 950°F (the bottom curve of the Fig. 3 graph). A temperature of 900°F is equivalent to approximately 482°C , which is within the range utilized for forming the aforesaid conventional solder glass peripheral seal 4 in Figs. 1-2. Thus, attention is drawn to the 900°F curve in Fig. 3, labeled by reference number 18. As shown, only 20% of the original temper strength remains after one hour at this temperature (900°F or 482°C). Such a significant loss (i.e., 80% loss) of temper strength may be undesirable.

[0011] As seen in Figs. 3-4, the percentage of remaining tempering strength varies based on the temperature that is exposed to the tempered glass. For example, at 900°F only about 20% of the original temper strength remains. When the temperature that the sheet is exposed to is reduced to 800°F , about 428°C , the amount of strength remaining is about 70%. Finally, a reduction in temperature to about 600°F , about 315°C , results in about 95% of the original temper strength of the sheet remaining. As will be appreciated, it is desirable to reduce any temper strength losses as a result of exposing a tempered sheet of glass to high temperatures.

[0012] As noted above, the creation of VIG units includes the creation of a hermetic seal that can withstand the pressure applied from the vacuum created on inside of the unit. As also discussed above, the creation of the seal may conventionally involve temperatures of at or above 500°C . These temperatures are required in order to obtain a high enough temperature in order for the frit material used for the seal to melt and form the required seal for the VIG units. As shown above, such a temperature can result in a strength reduction for VIG units using tempered glass.

[0013] One conventional solution to sealing glass substrates together is to use an epoxy. However, in the case of VIG units, epoxy compositions may be insufficient to hold a seal on a vacuum. Furthermore, epoxies may be susceptible to environmental factors that may further reduce their effectiveness when applied to VIG units.

[0014] Another conventional solution is to use a frit solution that contains lead. As is known, lead has a relatively low melting point. Accordingly, temperatures for sealing the VIG units may not need to be as high for other frit materials, and thus the tempering strength of tempered glass substrates may not be reduced by the same amount required for other frit

based materials. However, while lead based frits may resolve the above structural issues, the usage of lead in the frit may create new problems. Specifically, the health consequences to the population for products that contain lead. Additionally, certain countries (e.g., in the European Union) may impose strict requirements on the amount of lead that can be contained in a given product. Indeed, some countries (or customers) may require products that are completely lead-free.

[0015] Thus, it will be appreciated that techniques for creating improved seals for glass articles are continuously sought after. It also will be appreciated that there exists a need in the art for improved seals and the like that can be integrated with tempered glass units, such as, for example, VIG units. The seals may be designed to allow for reduced temperature sealing such that annealed or tempered glass can be sealed without detrimental impact on the properties of the glass.

[0016] In certain example embodiments, a frit material may provide glass to frit bonding sufficient for VIG purposes (e.g., in terms of structural strength). In certain example embodiments, the provided frit may provide proper glass wetting properties. In certain example embodiments, the frit may seal and have structural strength and a homogenous glassy structure to provide an adequate barrier to prevent vacuum degradation in example VIG units over a period of time.

[0017] In certain instances, improvements in melt flow may enable improved frit matching to glass expansion and/or increase process tolerances to frit bead variations. Improved wetting and bonding properties of a frit material may increase VIG yield by reducing bonding failures of the frit to the glass. A reduction in crystallization may additionally or alternatively facilitate a selected composition to meeting different heating environments (e.g., an internal seal, an external seal, etc).

[0018] In certain example embodiments, a frit material having a composition is provided. The frit material may include vanadium oxide between about 50% and 60% weight, barium oxide between about 27% and 33% weight, and zinc oxide between about 9% and 12% weight. In certain example embodiments, the frit material may also include at least one additive selected from among: Ta_2O_5 , Ti_2O_3 , SrCl_2 , GeO_2 , CuO , AgO , Nb_2O_5 , B_2O_3 , MgO , SiO_2 , TeO_2 , Ti_2O_3 , Y_2O_3 , SnF_2 , SnO_2 , CuCl , SnCl_2 , CeO_2 , AgCl , In_2O_3 , SnO , SrO , MgO , MoO_3 , CsCO_3 , CuCl_2 , and Al_2O_3 .

[0019] In certain example embodiments, a vacuum insulated glass (VIG) unit is provided. The VIG unit may include first and second substantially parallel, spaced apart glass substrates. An edge seal is provided around a periphery of the first and second

substrates to form a hermetic seal there between and at least partially defining a gap between the first and second substrates. The gap defined between the first and second substrates is at a pressure less than atmospheric. The edge seal includes a frit material, e.g., as made from a base composition as described herein.

[0020] In certain example embodiments, a method of making a frit material is provided. A base composition is provided to a holder. The base composition includes vanadium oxide between about 50% and 60% weight, barium oxide between about 27% and 33% weight, zinc oxide between about 9% and 12% weight, and at least one additive selected from among: Ta_2O_5 , Ti_2O_3 , SrCl_2 , GeO_2 , CuO , AgO , Nb_2O_5 , B_2O_3 , MgO , SiO_2 , TeO_2 , Ti_2O_3 , Y_2O_3 , SnF_2 , SnO_2 , CuCl , SnCl_2 , CeO_2 , AgCl , In_2O_3 , SnO , SrO , MgO , MoO_3 , CsCO_3 , CuCl_2 , and Al_2O_3 . The base composition is melted. The base composition is cooled or allowed to cool, forming an intermediate glass article. The intermediate glass article is ground to make the frit material.

[0021] In certain example embodiments, a method of making a vacuum insulated glass (VIG) unit is provided. First and second glass substrates in substantially parallel, spaced apart relation to one another are provided. The first and second glass substrates using a frit material are sealed together, with a gap being defined between the first and second substrates. The sealing being performed by melting the frit material at a temperature of no more than about 400 degrees C. Where the frit material has been formed from a base composition including vanadium oxide between about 50% and 60% weight, barium oxide between about 27% and 33% weight, zinc oxide between about 9% and 12% weight, and at least one oxide or chloride-base additive.

[0022] In certain example embodiments, a frit material having a composition is provided. The frit material may include vanadium oxide between about 50% and 60% weight (40-55% molar, more preferably 45-50% molar), barium oxide (e.g., barium carbonate that converts in whole or in part to BaO) between about 23% and 33% weight (15-35% molar, more preferably 20-23% molar), and zinc oxide between about 9% and 12% weight (15-25% molar, more preferably 19-22% molar). The frit material includes at least a first and second additive selected from among SnCl_2 , CuCl_2 , MoO_3 , TeO_2 , Ta_2O_5 , Nb_2O_5 , Al_2O_3 , SiO_2 , and CsCO_3 .

[0023] Certain example embodiments may include at least two additives. For example SnCl_2 and SiO_2 . Certain example embodiments may include three or four additives selected from among SiO_2 , SnCl_2 , Al_2O_3 , and TeO_2 . Certain example embodiments may use

between 5 and 10 different additives that are selected from among: SnCl_2 , CuCl_2 , MoO_3 , TeO_2 , Ta_2O_5 , Nb_2O_5 , Al_2O_3 , SiO_3 , and CsCO_3 .

[0024] The features, aspects, advantages, and example embodiments described herein may be combined in any suitable combination or sub-combination to realize yet further embodiments.

BRIEF DESCRIPTION OF THE DRAWINGS

[0025] These and other features and advantages may be better and more completely understood by reference to the following detailed description of exemplary illustrative embodiments in conjunction with the drawings, of which:

[0026] FIGURE 1 is a cross-sectional view of a conventional vacuum IG unit;

[0027] FIGURE 2 is a top plan view of the bottom substrate, edge seal, and spacers of the Fig. 1 vacuum IG unit taken along the section line illustrated in Fig. 1;

[0028] FIGURE 3 is a graph correlating time (hours) versus percent tempering strength remaining, illustrating the loss of original temper strength for a thermally tempered sheet of glass after exposure to different temperatures for different periods of time;

[0029] FIGURE 4 is a graph correlating time versus percent tempering strength remaining similar to that of Fig. 3, except that a smaller time period is provided on the x-axis;

[0030] FIGURE 5 is cross-sectional view of a vacuum insulated glass unit according to certain example embodiments;

[0031] FIGURE 6 is a flowchart illustrating a process for making a vacuum insulated glass unit with a frit material according to certain example embodiments;

[0032] FIGURES 7A-7D are graphs summarizing properties of compositions according to certain example embodiments;

[0033] FIGURES 8A-8C are graphs summarizing the quality of compositions according to certain exemplary embodiments;

[0034] FIGURE 9 is a graph showing results when additional elements are added to compositions according to certain example embodiments;

[0035] FIGURES 10A-10C show graphs summarizing impacts of additives being added to vanadium based frits according to certain example embodiments;

[0036] FIGURES 11A-11C show graphs summarizing absorption in the visible and infrared wavelengths for vanadium based frits according to certain example embodiments; and

[0037] FIGURES 12A-12C are graphs summarizing flow characteristics of example frit materials according to certain example embodiments.

DETAILED DESCRIPTION OF EXAMPLE EMBODIMENTS OF THE INVENTION

[0038] The following description is provided in relation to several example embodiments which may share common characteristics, features, etc. It is to be understood that one or more features of any one embodiment may be combinable with one or more features of other embodiments. In addition, single features or a combination of features may constitute an additional embodiment(s).

[0039] Certain example embodiments may relate to glass units (e.g., VIG units) that include two glass substrates sealed with an improved seal, e.g., of or including a vanadium-based frit material. In certain example embodiments an improved seal may include the following materials: vanadium oxide, barium oxide, and zinc oxide. In addition, certain example embodiments may include one or more of the following compounds: Ta_2O_5 , Ti_2O_3 , $SrCl_2$, GeO_2 , CuO , AgO , Nb_2O_5 , B_2O_3 , MgO , SiO_2 , TeO_2 , Tl_2O_3 , Y_2O_3 , SnF_2 , SnO_2 , $CuCl$, $SnCl_2$, CeO_2 , $AgCl$, In_2O_3 , SnO , SrO , MgO , MoO_3 , $CsCO_3$, $CuCl_2$, and Al_2O_3 .

[0040] Fig. 5 is cross-sectional view of a vacuum insulated glass unit according to certain example embodiments. VIG unit 500 may include first and second glass substrates 502a and 502b that are spaced apart and define a space therebetween. The glass substrates 502a and 502b may be connected via an improved seal 504, of or including a vanadium-based frit. Support pillars 506 may help maintain the first and second substrates 502a and 502b in substantially parallel spaced apart relation to one another. It will be appreciated that the CTE of the improved seal 504 and the glass substrates 502a and 502b may substantially match one another. This may be advantageous in terms of reducing the likelihood of the glass cracking, etc. Although Fig. 5 is described in relation to a VIG unit, it will be appreciated that the improved seal 504, of or including a vanadium-based frit may be used in connection with other articles and/or arrangements including, for example, insulating glass (IG) units and/or other articles.

[0041] Fig. 6 is a flowchart illustrating a process for preparing a frit material to be used in making a vacuum insulated glass unit according to certain example embodiments. In step 600, base compounds are combined and disposed into an appropriate container (e.g., a heat resistant container such as, for example, a ceramic container). In step 602, the combined

compound is melted. Preferably, the temperature to melt the combined material may be at least 1000°C. In certain exemplary embodiments, the combined compound is melted at 1000°C for between 30 to 60 minutes. In certain exemplary embodiments, the combined compound is melted at 1100°C for 60 minutes. In certain exemplary embodiments, the combined compound is melted at 1200°C for 60 minutes. In certain exemplary embodiments, the melting temperature is a cycle that includes 500°C for 15 minutes, 550°C for 15 minutes, 600°C for 15 minutes, and a ramp up to 1000°C for 60 minutes.

[0042] After the combined compounds are melted, the material may be cooled in step 604, e.g., to form a glass sheet. After cooling, the glass may be crushed or ground into fine particulates in step 606. In certain example embodiments, the size of the particulates may be no larger than about 100 mesh. Once the glass is ground into a powder, it may be disposed between the substrates in step 608. In certain example embodiments, the powder may be dispensed as a paste with a binder. Heat may then be applied in step 610 to the glass substrate and the powder. In certain example embodiments, the heat may be between 300°C and 400°C, or more preferably between 325°C and 375°C. It will be appreciated that when heat of the above temperatures is applied to tempered glass that the tempered glass may lose a reduced amount of strength versus when heat of in excess of 350°C is applied to the tempered glass. Thus, certain example embodiments preferably involve a frit melting temperature of less than 500°C, more preferably less than 425°C, and sometimes less than 350°C.

[0043] In certain example embodiments, the combined compounds include the following materials: vanadium oxide, barium oxide, and zinc oxide.

[0044] Figs. 7A-7D show graphs summarizing properties of compositions according to certain example embodiments.

[0045] The table below corresponds to the data shown in Fig. 7A with those compositions with a melt quality of less than 4 (on a scale of 0 to 5) omitted from the table.

Table 1, Normalized Moles of Batch Composition								
V ₂ O ₅	BaO	ZnO	BaO/ZnO	Bi ₂ O ₃	B ₂ O ₃	Tg(C)	Tx1(C)	Rating
43.66%	9.87%	46.47%	0.21			320	410	4
39.01%	13.25%	37.37%	.35	2.18%	8.20%	312	430	4
47.33%	12.96%	24.41%	0.53	9.95%	5.53%	305	380	4
50.24%	23.38%	21.39%	1.33			320	425	4
51.54%	26.26%	16.46%	1.60	5.75%		320	410	4.5

[0046] The melts shown in Fig. 7A were applied to a microscope glass slide with a temperature of 375°C applied for 15 minutes. Fig. 7B shows a graph that includes the crystallization temperature (first crystallization peak – Tx1 – of the above table) of the above melts. According to certain exemplary embodiments, a preferred temperature for Tx1 may be between about 375°C and 425°C, preferably about 400°C.

[0047] Fig. 7C shows the transition glass temperatures, T_g, compared the above melts. The graph showing exemplary data shows that T_g values between about 290C and 335C may be preferred for the above compositions.

[0048] Fig. 7D includes the above melts in a graph showing the melt quality versus the barium/zinc ratio.

[0049] Figs. 8A-8C show graphs that summarize the quality of compositions according to certain exemplary embodiments. Fig. 8A summarizes the V₂O₅ percentage used in certain exemplary compositions. Fig. 8B summarizes the BaO percentage used in certain exemplary compositions. Fig. 8C summarizes the ZnO percentage used in certain exemplary compositions. As shown in the illustrative graphs, a vanadium percentage of between about 51% and 53% may be preferable according to certain example embodiments.

[0050] Below, tables 2A-2C show exemplary compositions according to certain example embodiments. Additionally, examples 7-15 in the tables correspond to graphs 8A-8C. For the compositions shown in the below tables, BaCO₃ factor of 1.287027979 was used to convert to a BaO resulting compound.

Table 2A										
Ex.	Weight Percentage			Weight Normal	Weights of Batch Composition for 25 grams			Normalized Weight Percentage		
	V ₂ O ₅	BaO	ZnO		V ₂ O ₅	BaO	ZnO	V ₂ O ₅	BaO	ZnO
1	60	30	10	0.23	13.800	8.880	2.300	55.24	35.55	9.21
2	52.5	25	10	0.27	14.175	8.687	2.700	55.45	33.99	10.56
3	45	20	10	0.31	13.950	7.980	3.100	55.73	31.88	12.39
4	45	10	20	0.32	14.400	4.118	6.400	57.79	16.53	25.68
5	52.5	10	25	0.28	14.700	3.604	7.000	58.09	14.24	27.66
6	60	10	30	0.25	15.000	3.218	7.500	58.33	12.51	29.16
7	52.5	25	10	0.24	12.600	7.722	2.400	55.45	33.99	10.56
8	57.5	25	10	0.25	14.375	8.044	2.500	57.69	32.28	10.03

9	47.5	25	10	0.28	13.300	9.009	2.800	52.97	35.88	11.15
10	52.5	27.5	10	0.26	13.650	9.202	2.600	53.63	36.15	10.22
11	57.5	27.5	10	0.25	14.375	8.848	2.500	55.88	34.40	9.72
12	47.5	27.5	10	0.27	12.825	9.556	2.700	51.13	38.10	10.77
13	52.5	22.5	10	0.28	14.700	8.108	2.800	57.40	31.66	10.93
14	57.5	22.5	10	0.26	14.950	7.529	2.600	59.61	30.02	10.37
15	47.5	22.5	10	0.29	13.775	8.398	2.900	54.94	33.49	11.57

Table 2B							
Ex.	Moles of Batch			Normalized Moles			Glass Type
	V ₂ O ₅	BaO	ZnO	V ₂ O ₅	BaO	ZnO	
1	0.3037	0.1801	0.1132	50.87%	30.17%	18.95%	amorphous
2	0.3049	0.1722	0.1298	50.24%	28.38%	21.39%	glassy
3	0.3064	0.1616	0.1522	49.41%	26.05%	24.54%	amorphous
4	0.3177	0.0838	0.3156	44.31%	11.68%	44.01%	amorphous
5	0.3194	0.0722	0.3400	43.66%	9.87%	46.47%	amorphous
6	0.3207	0.0634	0.3584	43.19%	8.54%	48.27%	amorphous
7	0.3049	0.1722	0.1298	50.24%	28.38%	21.39%	glassy
8	0.3172	0.1636	0.1233	52.51%	27.08%	20.41%	glassy
9	0.2912	0.1818	0.1370	47.74%	29.80%	22.46%	glassy
10	0.2949	0.1832	0.1255	48.85%	30.35%	20.80%	glassy
11	0.3073	0.1743	0.1194	51.12%	29.00%	19.87%	glassy
12	0.2811	0.1931	0.1323	46.35%	31.83%	21.81%	glassy
13	0.3156	0.1604	0.1344	51.70%	26.28%	22.01%	glassy
14	0.3278	0.1521	0.1274	53.97%	25.05%	20.98%	glassy
15	0.3021	0.1697	0.1421	49.20%	27.65%	23.15%	glassy

[0051] The rating shown in Table 2C is based off of depositing the ground composition on a microscope glass slide and heating the composition at about 375°C for between 10 and 30 minutes.

Table 2C					
Example	T _g (C°)	T _{x2} (C°)	T _{x2} (C°)	T _{x1} – T _g	Rating

1	280	330	540	50	0.0
2	320	425	525	105	4.0
3	280	430	550	150	0.0
4	280	320	365	40	0.0
5	320	410	560	90	4.0
6	285	425	560	140	0.0
7	315	390	530	75	4.5
8	295, 325	415	535	90	5.0
9	320	420	525	100	4.5
10	325	410	540	85	4.5
11	315	395	530	80	4.5
12	330	415	560	85	4.0
13	315	400	530	85	5.0
14	305	395	530	90	4.0
15	320	395	525	75	4.5

[0052] Fig. 9 shows a graph with results of adding additional elements (e.g., Bi_2O_3 and B_2O_3) to a vanadium based frit. Corresponding data shown in Fig. 9 is also displayed below in Table 3.

Table 3								
Ex.	V ₂ O ₅	BaO	ZnO	Bi ₂ O ₃	B ₂ O ₃	T _g (C)	T _{x1} (C)	DSC Responses
1	65.39%	14.87%	12.46%	0.00%	7.28%	320	430	medium weak
2	60.96%	13.86%	11.61%	0.00%	13.57%	240	415	very weak
3	69.71%	15.85%	13.28%	1.16%	0.00%	315	405	strong peaks
4	64.69%	14.71%	12.32%	1.08%	7.20%	325	440	very weak
5	68.91%	15.67%	13.13%	2.29%	0.00%	320	410	medium weak
6	64.00%	14.56%	12.19%	2.13%	7.12%	320	425	very weak
7	59.74%	13.59%	11.38%	1.99%	13.30%	315	410	very weak
8	60.34%	13.72%	11.49%	1.00%	13.43%	315	400	very weak
9	70.53%	16.04%	13.43%	0.00%	0.00%	315	380	strong peaks

[0053] In certain example embodiments, a strong DSC response may correspond to a good remelt quality. In certain example embodiments, the addition of bismuth in concentrations of between about 0% and 3% may result in increased remelt flow quality.

[0054] In certain example embodiments, a frit that includes V_2O_5 , BaO, and ZnO may further include one or more additives. In certain example embodiments, the additives may be between about 0.5% and 15% weight. According to certain example embodiments, the additives may be added to a base composition that includes between about 50% and 60% weight V_2O_5 , 27% and 33% weight BaO, and 9% and 12% weight ZnO.

[0055] Below, Tables 4A-4D show results of including additives to the base composition of V_2O_5 , BaO, and ZnO. Table 4D shows the melt quality on a scale of about 0 to 5 for each of the compositions. Figs. 10A-10C show graphs corresponding to the data shown in the below tables. A $BaCO_3$ factor of 1.2870 was used to form the BaO used for the following examples.

Table 4A									
Ex	Weights (gm)					Normalized Weights			
	V2O5	BaO	ZnO	Additive Type	Amount	V2O5	BaO	ZnO	Additive
1	52.5	22.5	10	TeO2	2	14.175	7.819	2.700	0.540
2	52.5	22.5	10	TeO2	4	13.650	7.529	2.600	1.040
3	52.5	22.5	10	Ta2O5	5	13.650	7.529	2.600	1.300
4	52.5	22.5	10	Ta2O5	10	13.125	7.240	2.500	2.500
5	52.5	22.5	10	Ti2O3	5	13.650	7.529	2.600	1.300
6	52.5	22.5	10	Ti2O3	10	13.125	7.240	2.500	2.500
7	52.5	22.5	10	SrCl2	2	14.175	7.819	2.700	0.540
8	52.5	22.5	10	SrCl2	4	13.650	7.529	2.600	1.040
9	52.5	22.5	10	GeO2	1	14.175	7.819	2.700	0.270
10	52.5	22.5	10	GeO2	2	14.175	7.819	2.700	0.540
11	52.5	22.5	10	CuO	1	14.175	7.819	2.700	0.270
12	52.5	22.5	10	CuO	2	14.175	7.819	2.700	0.540
13	52.5	22.5	10	AgO	1.5	14.175	7.819	2.700	0.405
14	52.5	22.5	10	AgO	3	14.175	7.819	2.700	0.810
15	52.5	22.5	10	Nb2O5	3	14.175	7.819	2.700	0.810
16	52.5	22.5	10	Nb2O5	6	13.650	7.529	2.600	1.560
17	52.5	22.5	10	B2O3	.8	14.175	7.819	2.700	0.216

18	52.5	22.5	10	B2O3	1.6	14.175	7.819	2.700	0.432
----	------	------	----	------	-----	--------	-------	-------	-------

Table 4B

Ex	Normalized Weight Percentage				Moles of Batch Composition			
	V2O5	BaO	ZnO	Additive	V2O5	BaO	ZnO	Additive
1	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.013
2	55.00	30.34	10.48	4.19	0.302	0.154	0.129	0.026
3	54.43	30.02	10.37	5.18	0.299	0.152	0.127	0.012
4	51.75	28.54	9.86	9.86	0.285	0.145	0.121	0.022
5	54.43	30.02	10.37	5.18	0.299	0.152	0.127	0.011
6	51.75	28.54	9.86	9.86	0.285	0.145	0.121	0.022
7	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.013
8	55.00	30.34	10.48	4.19	0.302	0.154	0.129	0.026
9	56.78	31.32	10.82	1.08	0.312	0.159	0.133	0.010
10	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.020
11	56.78	31.32	10.82	1.08	0.312	0.159	0.133	0.014
12	56.17	30.99	10.70	2.14	0.309	0.157	0.131	0.027
13	56.48	31.15	10.76	1.61	0.311	0.158	0.132	0.013
14	55.58	30.66	10.59	3.18	0.306	0.155	0.130	0.026
15	55.58	30.66	10.59	3.18	0.306	0.155	0.130	0.012
16	53.87	29.71	10.26	6.16	0.296	0.151	0.126	0.023
17	56.91	31.39	10.84	0.87	0.313	0.159	0.133	0.012
18	56.42	31.12	10.75	1.72	0.310	0.158	0.132	0.025

Table 4C

Ex	Normalized Moles							
	V2O5	BaO	ZnO	Additive	Tg (C)	(Tx1(C)	Tx2(C)	Tx1-Tg
1	50.57%	25.71%	21.53%	2.20%	315	400	525	85
2	49.48%	25.16%	21.07%	4.30%	315	420	530	105
3	50.68%	25.76%	21.58%	1.99%	320	450		130
4	49.69%	25.26%	21.16%	3.90%	320	450	530	130
5	50.71%	25.78%	21.59%	1.92%	305	390	495	85

6	49.75%	25.29%	21.18%	3.77%	295	390	470	95
7	50.56%	25.70%	21.53%	2.21%	315	405	530	90
8	49.47%	25.15%	21.06%	4.32%	315	400	530	85
9	50.83%	25.84%	21.64%	1.68%	315	395	530	80
10	49.99%	25.41%	21.28%	3.31%	315	400	530	85
11	50.56%	25.71%	21.53%	2.20%	315	385	525	70
12	49.47%	25.15%	21.06%	4.31%	320	395	545	75
13	50.61%	25.73%	21.55%	2.12%	305	390	525	85
14	49.55%	25.19%	21.10%	4.16%	300	380		80
15	50.68%	25.76%	21.58%	1.98%	315	425	550	110
16	49.69%	25.26%	21.16%	3.89%	325	440	465	115
17	50.66%	25.75%	21.57%	2.02%	315	410	540	95
18	49.66%	25.25%	21.14%	3.95%	320	405	545	85

Table 4D		
Example	Melt Quality @ 375C, 15min	Melt Quality at 350C, 15min
1	5.0	4.0
2	4.5	4.0
3	4.5	2.0
4	5.0	2.0
5	4.5	4.5
6	5.0	5.0
7	5.5+	5.0
8	5.0	4.5
9	4.5	4.5
10	4.5	4.5
11	4.5	2.0
12	4.0	2.0
13	4.0	5.0
14	3.5	4.0
15	4.5	2.0
16	5.0	2.0

17	4.0	4.5
18	3.5	2.0

[0056] In certain example embodiments, the molar composition of an additive to a base composition higher than is shown in tables 4A-4D. Table 5A shows additives with an increased additive amount (on a % mole basis). The base composition used with the additive amount may be based on, for example, the base composition shown in Row 1 of Tables 4A-4D. The additives shown in Table 5, in the selected quantities displayed, may improve melt quality when compared to the above base composition. A melt type of Glassy indicates that a “button” of the compound melted onto a glass plate, forming a homogenous glassy structure. Sinter indicates that the compound (in a powder form) fused together, but remained in a powder form.

Table 5				
Example	Additive Type	Amount	Melt Type (350C for 20 minutes)	Adhesion to glass substrate.
1	CuCl	4.00%	Glassy	No Stick
2	SnCl ₂	3.99%	Glassy	No Stick
3	SnCl ₂	5.99%	Glassy, Slight Flow	Slight stick
4	SiO ₂	6.02%	More Glassy	No Stick
5	Al ₂ O ₃	6.00%	Glassy	No Stick
6	CeO ₂	4.00%	Sinter	No Stick
7	TeO ₂	3.99%	Glassy	Slight stick
8	TeO ₂	6.01%	Glassy	Slight stick
9	Tl ₂ O ₃	3.99%	Glassy, Slight Flow	No Stick
10	Tl ₂ O ₃	6.01%	Glassy, Slight Flow	No Stick

[0057] Accordingly, in certain example embodiments, additives of a relatively increased amount (e.g., versus those shown in Fig. 4) may be added to a base composition. In certain example embodiments, the additives may include, for example, CuCl, SnCl₂, SiO₂, Al₂O₃, and TeO₂. It will be appreciated that toxic nature of thallium oxide (Tl₂O₃) may preclude its use in certain instances.

[0058] In certain example embodiments, two or more additives may be included in a base compound. Table 6 shows the results of adding two additives to an exemplary base composition. Table 6 includes example melts at 375 and 350. Additionally, 13mm buttons

of the exemplary compounds were tested on a glass plate. The structural strength of the resulting exemplary compound are also shown in the far right column.

Table 6								
Ex	Add 1	Add 2	Amount 1 (Mole %)	Amount 2 (Mole %)	Melt Quality (375C 15- 20 Min)	Melt Quality (350C 15- 20 Min)	13mm Button 350C 20 Min	Strength
1	TeO ₂	Al ₂ O ₃	3.01	3.01	4.5	5.5	glassy	Fractures
2	TeO ₂	Al ₂ O ₃	2.99	5.01	5	4	glassy	Fractures
3	TeO ₂	Al ₂ O ₃	4.02	3.01	6	5.5	glassy	Fractures
4	TeO ₂	Al ₂ O ₃	3.99	5.00	5	4.5	glassy	Fractures
5	TeO ₂	Al ₂ O ₃	5.01	2.99	4.5	4.5	glassy	Fractures
6	TeO ₂	Al ₂ O ₃	5.00	5.00	5	4.5	glassy	Fractures
7	TeO ₂	SiO ₂	3.01	3.00	5	5.5	glassy	Fractures
8	TeO ₂	SiO ₂	2.99	5.02	5	4.5	glassy	Fractures
9	TeO ₂	SiO ₂	4.00	2.99	5	4	glassy	Fractures
10	TeO ₂	SiO ₂	3.99	4.99	5	4.5	Less glassy	Fractures
11	TeO ₂	SiO ₂	5.00	2.99	4.5	4.5	Less glassy	Hard
12	TeO ₂	SiO ₂	5.00	4.99	4.5	4.5	Less glassy	Hard
13	SnCl ₂	Al ₂ O ₃	3.01	3.01	5	6	more glassy	Hard
14	SnCl ₂	Al ₂ O ₃	3.00	5.01	5	5.5	glassy	Hard
15	SnCl ₂	Al ₂ O ₃	4.01	3.01	4.5	6	glassy	Hard
16	SnCl ₂	Al ₂ O ₃	4.00	4.99	5.5	6	glassy	Hard
17	SnCl ₂	Al ₂ O ₃	5.00	2.99	5.5	5.5	glassy	Fractures
18	SnCl ₂	Al ₂ O ₃	5.00	5.00	5.5	5.5	more glassy	Hard
19	SnCl ₂	SiO ₂	3.00	3.00	4.5	4.5	glassy	Hard
20	SnCl ₂	SiO ₂	3.00	4.99	5	6	glassy	Hard
21	SnCl ₂	SiO ₂	4.00	2.99	6	6	glassy	Fractures

22	SnCl ₂	SiO ₂	4.01	4.99	5.5	5.5	glassy	Fractures
23	SnCl ₂	SiO ₂	5.00	2.99	5	5.5	glassy	Hard
24	SnCl ₂	SiO ₂	5.00	4.99	5.5	5.5	glassy	Fractures
25	Al ₂ O ₃	SiO ₂	3.01	3.00	4.5	4	less glassy	Hard
26	Al ₂ O ₃	SiO ₂	2.99	4.99	5	5.5	less glassy	Hard
27	Al ₂ O ₃	SiO ₂	4.00	2.99	4.5	4.5	less glassy	Hard
28	Al ₂ O ₃	SiO ₂	4.00	4.99	5	4.5	less glassy	Hard
29	Al ₂ O ₃	SiO ₂	5.01	2.99	5	4.5	less glassy	Hard
30	Al ₂ O ₃	SiO ₂	5.01	4.99	4	2	less glassy	Hard

[0059] Accordingly, certain example may include two additives similar to those found in examples 3, 16, and 21 as shown in Table 6 (e.g., TeO₂ with SiO₂, SnCl₂ with Al₂O₃, and SnCl₂ with SiO₂). In certain example embodiments, the addition of two or more additives may have beneficial results on an exemplary base composition. For example the addition of SiO₂ to another additive may increase the strength of the overall frit.

Alternatively, or in addition, TeO₂ combined with other additives may increase the melt flow and glass wetting qualities of the frit when compared to a base frit.

[0060] In certain example embodiments, the combination of SnCl₂ with SiO₂ and/or Al₂O₃ may result in an increase in structural strength for the resulting frit material.

[0061] In certain example embodiments, one or more additives may be added to a base composition where the amount is between 1% and 10% by weight or between about 1% and 6% normalized moles for a batch. In certain example embodiments, additives may be added in a smaller amount, for example between about 0.1% and 1% by weight. In certain example embodiments a batch for a base composition (in grams) may include V₂O₅ at 52.5, BaO at 22.5, ZnO at 10. In certain example embodiments, additives added to the above base composition may include: 1) TeO₂ at 3.85gm and Al₂O₃ at 1.84gm; 2) SnCl₂ at 4.65gm and Al₂O₃ at 3.12gm; 3) SnCl₂ at 4.55gm and SiO₂ at 1.08gm. Correspondingly, the additives may then have a normalized weight percentage of: 1) TeO₂ at 1.00 and Al₂O₃ at .48; 2) SnCl₂

at 1.21 and Al₂O₃ at .81; 3) SnCl₂ at 1.18 and SiO₂ at .28. These examples may correspond to examples 3, 16, and 21 in the above table 6.

[0062] Figs 11A-11C show graphs illustrating absorption in the visible and infrared wavelengths for vanadium based frits according to certain example embodiments. As shown in the graphs, example vanadium based frits may have absorption of at least 90% across a substantial breadth of the visible and IR spectrum. In certain example embodiments the absorption may be about 95%. As discussed in co-pending application Serial No. 12/929,874, filed on February 22, 2011, entitled "IMPROVED FRIT MATERIALS AND/OR METHOD OF MAKING VACUUM INSULATING GLASS UNITS INCLUDING THE SAME" (atty. dkt. no. 3691-2307), the entire contents of which are incorporated herein by reference, frit materials with high visible/IR absorption may be advantageous.

[0063] Fig. 11A shows the absorption properties of a vanadium based frit with TeO₂ and Al₂O₃ used as additives (e.g., Ex. 3 of Table 6). Fig. 11B shows the absorption properties of a vanadium based frit with SnCl₂ and Al₂O₃ used as additives (e.g., Ex. 16 of Table 6). Fig. 11C shows the absorption properties of a vanadium based frit with SnCl₂ and SiO₂ used as additives (e.g., Ex. 21 of Table 6).

[0064] In certain example embodiments, the application of IR energy to a frit material may be based on a heating profile where the IR energy applied to the frit varies over time. Exemplary heating profiles may be found in co-pending application Serial No. 12/929,874 (atty. dkt. no. 3691-2307), the entire contents of which are incorporated herein by reference.

[0065] In certain example embodiments, a base composition may be augmented by 3 or 4 additives. For example, a batch for a base composition (in grams) may include V₂O₅ at 52.5, BaO at 22.5, ZnO at 10. Accordingly, three and/or more additives from among TeO₂, SnCl₂, Al₂O₃, and SiO₂ may be selected to augment the base composition. The ranges (in grams) for the additives may vary between 0 to 7.5 grams per additive. Thus, on a normalized molar percentage the above additives may be included at between 0% and 6%. Thus, the normalized molar percentage of a base composition may be V₂O₅ at between about 43% and 50%, BaO between about 22% and 26%, ZnO between about 18% and 22%. In certain example embodiments, additives (on a normalized molar basis) of TeO₂ at around 2%, SnCl₂ around 2%, Al₂O₃ around 2%, and SiO₂ around 4% may be added to the base composition.

[0066] The techniques, compositions, etc disclosed herein may be used other methods and/or systems for forming a VIG unit. For example, a vanadium based frit may be used to form an edge seal of a VIG unit. Systems, apparatuses, and/or methods used for creating a

VIG unit may be described in co-pending application 12/929,876, filed on February 22, 2011, entitled "LOCALIZED HEATING TECHNIQUES INCORPORATING TUNABLE INFRARED ELEMENT(S) FOR VACUUM INSULATING GLASS UNITS, AND/OR APPARATUSES FOR THE SAME" (atty. dkt. no 3691-2108), the entire contents of which are hereby incorporated by reference.

[0067] Certain example embodiments may include three or more additives to a base composition that includes vanadium pentoxide; barium carbonate that converts in whole or in part to barium oxide; and zinc oxide. The above three "base" frit elements may be included at 35-55% molar for V_2O_5 , 15-35% for BaO, and 15-25% molar for ZnO or, more preferably, 40-50% molar for V_2O_5 , 20-30% for BaO, and 18-22% molar for ZnO.

[0068] Along with an example base frit composition, one or more additives may be added. The additives may include, for example:

- 1) $SnCl_2$ at between 1-10% molar, which may help reduce glass softening temperatures and/or reduce crystallization in certain example embodiments;
- 2) $CuCl_2$ at between 1-5% molar, which may help reduce glass softening temperature in certain example embodiments;
- 3) MoO_3 at between 1-6% molar, which may help reduce glass softening temperatures in certain example embodiments;
- 4) TeO_2 at between 1-10% molar, which may help increase glass flow ability and/or wetting to a substrate glass in certain example embodiments;
- 5) Ta_2O_5 at between 0.5-5% molar, which may help increase softening temperature and/or increase crystallization temperature in certain example embodiments;
- 6) Nb_2O_5 at between 0.5-6% molar, which may help increase softening temperature and/or increase crystallization temperature in certain example embodiments;
- 7) Al_2O_3 at between 0.5-5% molar, which may help increase softening, weathering ability, chemical durability, and/or mechanical strength in certain example embodiments;
- 8) SiO_2 at between 0.5-5% molar, which may help increase softening, weathering ability, chemical durability, and/or mechanical strength in certain example embodiments; and
- 9) $CsCO_3$ at between 0.5-4% molar, which may help increase melt flow and/or reduce wetting ability in certain example embodiments.

[0069] In certain example embodiments, four or more additives, more preferably six or more additives may be added to the above base composition. It will be appreciated that as the number of the additives increases, the interactions between the various additives may produce different results based on the relative weighting of one or more additives (or the base

composition). It also will be appreciated that the increased number of additives may create synergistic effects (e.g., in terms of glass softening temperature, flowability, and/or other adjustments) that otherwise might not be observable.

[0070] In certain example embodiments, one or more additives may be introduced through the frit creation process rather than being expressly introduced. For example, additive ingredients may be introduced into a frit material as a result of firing the frit material in a crucible. For instance, some ingredients may be “leached” from the crucible and into the frit material. In certain example embodiments, Al_2O_3 and SiO_2 may be leached by this process.

[0071] Tables 7-10 show example frit compositions according to certain example embodiments. The different tables each include one or more additives that are varied while the other ingredients are kept substantially the same between the example compounds of the give table.

[0072] In tables 7A-7C, molybdenum oxide is varied between the example compounds; in tables 8A-8C tellurium oxide is varied between the example compounds; in tables 9A-9C cesium carbonate is varied between the example compounds; and in tables 10A-10D tantalum oxide and niobium oxide are varied between the example compounds.

[0073] Tables 7A, 8A, 9A, and 10A show the example frit compositions by normalized weight percentage. Tables 7B, 8B, 9B, and 10B show the example frit compositions by normalized mole percent. The values given in tables 7-10 A and B are normalized to approximately 100% for shown compositions. For example, V_2O_5 from example 1 in table 7A is 54.88% by weight of the frit composition for the frit composition. Similarly, V_2O_5 for the same example frit composition is shown as 49.76% mole of the resulting frit composition (e.g., from Table 7B). Thus, the normalized weight and mole percentages may add up to about 100% for the example frit compositions shown in the various tables herein. Tables 7C, 8C, 9C, 10C, and 10D show exemplary results for the example frit compositions. As can be seen in the results of the above noted tables (e.g., tables 7-10), performance of one or more of the above examples may be improved over a base frit material, or a frit material with only one additive as discussed above. For example, example frit materials 9 and 11 shown in Table 8 show good flow at 375 degrees C (5 and 6.5, respectively).

Table 7A - MoO_3 Examples

Example	Normalized Weight Percentage								
	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
1	54.88	26.61	10.45	0.87	4.15	1.38	0.00	0.00	1.65
2	54.64	26.49	10.41	1.31	4.13	1.37	0.00	0.00	1.64
3	54.39	26.38	10.36	1.75	4.11	1.37	0.00	0.00	1.64
4	54.15	26.26	10.31	2.19	4.10	1.36	0.00	0.00	1.63
5	53.91	26.14	10.27	2.63	4.08	1.36	0.00	0.00	1.62
6	53.67	26.02	10.22	3.07	4.06	1.35	0.00	0.00	1.62

Table 7B - MoO ₃ Examples									
Ex.	Normalized Moles of Batch Composition								
	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
1	49.76%	22.24%	21.18%	0.99%	4.29%	0.51%	0.00%	0.00%	1.02%
2	49.50%	22.12%	21.08%	1.50%	4.27%	0.51%	0.00%	0.00%	1.02%
3	49.25%	22.01%	20.97%	2.00%	4.24%	0.51%	0.00%	0.00%	1.01%
4	49.00%	21.90%	20.86%	2.50%	4.22%	0.51%	0.00%	0.00%	1.01%
5	48.75%	21.79%	20.75%	3.00%	4.20%	0.50%	0.00%	0.00%	1.00%
6	48.50%	21.67%	20.65%	3.50%	4.18%	0.50%	0.00%	0.00%	1.00%

Table 7C - MoO ₃ Examples						
Ex.	Test Results					
	Slides 350C 15 min	Slides 375C 15 min	375C 13mm button 20 min	Results	400C 13mm button 20 min	Results
1	5.0	5.5	12.39	glass	13.76	light haze
2	3.0	4.5	12.80	glass	14.06	light haze
3	4.0	5.5	12.51	glass	14.14	light haze
4	4.5	5.0	13.08	glass	14.22	light haze
5	5.5	5.0	12.93	glass	14.26	light haze
6	5.5	5.5	12.88	glass	14.50	light haze

Table 8A – TeO ₂ Examples

Example	Normalized Weight Percentage								
	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
7	54.84	26.59	10.45	2.67	2.42	1.38	0.00	0.00	1.65
8	54.56	26.46	10.39	2.66	2.91	1.37	0.00	0.00	1.64
9	54.29	26.33	10.34	2.65	3.39	1.37	0.00	0.00	1.63
10	54.02	26.19	10.29	2.63	3.88	1.36	0.00	0.00	1.63
11	53.74	26.06	10.24	2.62	4.37	1.35	0.00	0.00	1.62
12	53.47	25.93	10.18	2.61	4.86	1.34	0.00	0.00	1.61
13	53.20	25.80	10.13	2.59	5.34	1.34	0.00	0.00	1.60
14	52.92	25.66	10.08	2.58	5.83	1.33	0.00	0.00	1.59

Table 8B – TeO ₂ Examples									
Ex.	Normalized Moles of Batch Composition								
	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
7	49.61%	22.17%	21.12%	3.06%	2.50%	0.51%	0.00%	0.00%	1.02%
8	49.36%	22.06%	21.01%	3.04%	3.00%	0.51%	0.00%	0.00%	1.02%
9	49.11%	21.95%	20.91%	3.03%	3.50%	0.51%	0.00%	0.00%	1.01%
10	48.85%	21.83%	20.80%	3.01%	4.00%	0.51%	0.00%	0.00%	1.01%
11	48.59%	21.72%	20.69%	2.99%	4.50%	0.50%	0.00%	0.00%	1.00%
12	48.34%	21.60%	20.58%	2.98%	5.00%	0.50%	0.00%	0.00%	1.00%
13	48.09%	21.49%	20.47%	2.96%	5.50%	0.50%	0.00%	0.00%	0.99%
14	47.83%	21.38%	20.36%	2.95%	6.00%	0.49%	0.00%	0.00%	0.98%

Table 8C – TeO ₂ Examples						
Ex.	Test Results					
	Slides 350C 15 min	Slides 375C 15 min	375C 13mm button 20 min	Results	400C 13mm button 20 min	Results
7	5.5	6.0	12.89	glass	14.37	haze
8	3.0	6.5	13.08	glass	14.63	light haze
9	3.0	5.0	13.38	glass	14.93	light haze
10	6.5	5.0	13.17	glass	14.66	light haze
11	4.5	6.5	13.04	glass	14.72	glass
12	6.0	6.5	12.72	glass	14.53	light haze
13	5.5	5.0	12.94	glass	14.59	light haze
14	5.5	6.0	13.24	glass	14.92	light haze

Table 9A – CsCO ₃ Examples										
	Normalized Weight Percentage									
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅	CsCO ₃
15	52.95	25.68	10.09	2.58	4.31	1.33	0.00	0.00	1.59	1.47
16	52.69	25.55	10.04	2.57	4.29	1.32	0.00	0.00	1.59	1.97
17	52.43	25.43	9.99	2.56	4.26	1.32	0.00	0.00	1.58	2.44
18	52.17	25.30	9.94	2.54	4.24	1.31	0.00	0.00	1.57	2.92
19	51.91	25.17	9.89	2.53	4.22	1.31	0.00	0.00	1.56	3.41
20	51.65	25.05	9.84	2.52	4.20	1.30	0.00	0.00	1.55	3.89

Table 9B – CsCO ₃ Examples										
	Normalized Moles of Batch Composition (%)									
Ex.	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅	CsCO ₃
15	48.23	21.55	20.53	2.97	4.47	0.50	0.00	0.00	0.99	0.75
16	48.11	21.50	20.48	2.96	4.46	0.50	0.00	0.00	0.99	1.00
17	47.99	21.45	20.43	2.96	4.45	0.50	0.00	0.00	0.99	1.25
18	47.87	21.39	20.38	2.95	4.44	0.50	0.00	0.00	0.99	1.50
19	47.74	21.34	20.33	2.94	4.43	0.49	0.00	0.00	0.98	1.75
20	47.62	21.28	20.27	2.93	4.41	0.49	0.00	0.00	0.98	2.00

Table 9C – CsCO ₃ Examples						
	Test Results					
Ex.	Slide 350C - 15 min	Slide 375C - 15 min	13mm button - 375C 20 min	Results	13mm button - 400C 20 min	Results
15	5.5	6.5	13.40	glass	14.88	haze
16	5.5	5.5	13.05	glass	15.40	glass
17	4.0	6.5	13.60	glass	15.17	light haze
18	4.5	6.5	13.33	glass	14.81	haze
19	6.0	4.5	13.28	glass	14.59	haze
20	4.5	7.0	13.97	glass	16.36	light haze

Table 10A – Ta ₂ O ₅ and Nb ₂ O ₅ Examples									
	Normalized Weight Percentage								
Example	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
21	53.87	26.12	10.26	2.63	3.37	1.34	0.00	0.00	2.41
22	53.42	25.90	10.18	2.60	3.34	1.34	0.00	0.00	3.22
23	52.98	25.69	10.09	2.58	3.31	1.33	0.00	0.00	4.01
24	53.59	25.99	10.21	2.61	3.35	2.65	0.00	0.00	1.60
25	53.15	25.77	10.12	2.59	3.32	2.65	0.00	0.00	2.39
26	52.71	25.56	10.04	2.57	3.29	2.65	0.00	0.00	3.18
27	52.28	25.35	9.96	2.55	3.27	2.63	0.00	0.00	3.97

28	52.86	25.63	10.07	2.58	3.30	3.97	0.00	0.00	1.59
29	52.43	25.43	9.99	2.56	3.28	3.94	0.00	0.00	2.38
30	52.00	25.21	9.90	2.54	3.25	3.94	0.00	0.00	3.16
31	51.57	25.01	9.82	2.51	3.22	3.93	0.00	0.00	3.93

Table 10B – Ta ₂ O ₅ and Nb ₂ O ₅ Examples									
Normalized Moles of Batch Composition									
Ex.	V ₂ O ₅	BaO	ZnO	MoO ₃	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
21	48.87%	21.84%	20.81%	3.01%	3.48%	0.50%	0.00%	0.00%	1.50%
22	48.61%	21.73%	20.70%	3.00%	3.46%	0.50%	0.00%	0.00%	2.00%
23	48.37%	21.62%	20.59%	2.98%	3.44%	0.50%	0.00%	0.00%	2.50%
24	48.87%	21.84%	20.81%	3.01%	3.48%	1.00%	0.00%	0.00%	1.00%
25	48.62%	21.73%	20.70%	3.00%	3.46%	1.00%	0.00%	0.00%	1.50%
26	48.37%	21.62%	20.59%	2.98%	3.44%	1.00%	0.00%	0.00%	2.00%
27	48.12%	21.51%	20.49%	2.96%	3.43%	1.00%	0.00%	0.00%	2.50%
28	48.62%	21.73%	20.70%	3.00%	3.46%	1.50%	0.00%	0.00%	1.00%
29	48.37%	21.62%	20.59%	2.98%	3.44%	1.50%	0.00%	0.00%	1.50%
30	48.12%	21.50%	20.49%	2.96%	3.43%	1.50%	0.00%	0.00%	2.00%
31	47.87%	21.39%	20.38%	2.95%	3.41%	1.50%	0.00%	0.00%	2.50%

Table 10C – Ta ₂ O ₅ and Nb ₂ O ₅ Examples						
Test Results						
Ex.	Slide 350C - 15 min	Slide 375C - 15 min	13mm button - 375C 20 min	Results	13mm button - 400C 20 min	Results
21	4.5	6.5	13.24	glass	15.21	glass
22	4.0	6.5	12.42	glass	14.50	glass
23	2.5	6.0	12.24	glass	14.55	glass
24	4.5	6.5	12.56	glass	14.47	glass
25	3.0	5.0	12.35	glass	14.16	glass
26	4.5	6.0	12.19	glass	14.88	glass
27	4.5	5.0	12.30	glass	14.48	glass
28	3.0	5.5	12.16	glass	14.34	glass
29	3.0	5.5	11.62	glass	14.07	glass
30	3.0	5.5	11.79	glass	14.20	glass
31	3.0	6.0	11.77	glass	13.96	glass

Table 10D – Ta ₂ O ₅ and Nb ₂ O ₅ Examples		
Test Results Continued		
Example	13mm button – 425C 20 min	Result
21	16.07	Haze
22	15.86	Haze
23	16.08	light haze
24	14.79	Haze
25	15.99	Glass

26	16.40	light haze
27	16.15	light haze
28	15.33	Haze
29	15.55	Glass
30	15.71	light haze
31	14.57	Haze

[0074] In certain example embodiments, the use of Ta₂O₅ and/or Nb₂O₅ may help reduce the crystallization of the frit material. As the percentage of contribution by such additives increases, the softening temperature (e.g., a temperature at which the frit material may flow) may also increase. In certain example embodiments, such properties may be desirable for a tip off seal in a VIG unit (e.g., sealing the vacuum hole in a VIG unit).

[0075] Frit materials used for tipping off a vacuum hole may have different desirable properties than frit materials for a perimeter seal for a VIG unit. For example, a frit material used in a tip off seal may be completely or substantially exposed to IR and therefore may reach a higher temperature than that of a perimeter seal. Conversely, the perimeter seal may have the glass absorb some percentage of the SWIR directed at the frit of a perimeter seal (e.g., 10%-30% of the SWIR). Thus, an exemplary frit material (e.g., example 21) may be used for a perimeter seal while example 26 may be used for tip off seal.

[0076] As shown in Table 10D, the example frit compositions may provide increased resistance, or greater tolerance, to crystallization. The example compositions shown in Tables 7-10 were done in an alumina crucible. With such a crucible, a certain amount of Al₂O₃ and SiO₂ may be “leached” from the crucible during the frit preparation process. Thus, while Al₂O₃ and SiO₂ may not be shown in the above tables 7 – 10, these additives (or others depending on the crucible type) may yet be present in the frit composition due to the leaching process from the crucible. The leaching of Al₂O₃ and SiO₂ may be a result of melting or firing the frit compositions at certain temperatures (e.g., 800C degrees C, 1000 degrees C, etc). Different firing temperatures and/or different lengths of time of firing may affect the amount of material leached from the crucible. The variation of Al₂O₃ and SiO₂ may change the frit performance for sealing at 375 degrees C and 400 degrees C.

[0077] In certain example embodiments, Al₂O₃ may be included in a frit material at between 0% and 2% normalized moles by composition, or at a normalized weight percentage between 0% and 1.2%, or more preferably about 0.8%. SiO₂ may be included at between 1 and 5% normalized mole by composition and/or between about 0.5 and 2% by weight, and more preferably about 1.2% by normalized weight. The inventor has determined that in

certain instances, having SiO₂ or Al₂O₃ in amount greater than about 2-5%, resulted in undesirable flow qualities of the frit composition. In particular, when bonding to an example glass substrate, in certain instances, higher percentages of SiO₂ or Al₂O₃ (e.g., in excess of 2 or 4%) resulted in concrete like qualities for the final frit composition.

[0078] Table 11 shows example results in a platinum crucible. Such a crucible may reduce or even prevent the leaching of excess additives during the firing process of the frit material.

Table 11									
Platinum Crucible – Normalized Moles (%)									
V ₂ O ₅	BaO	ZnO	CuCl	SnCl ₂	TeO ₂	Ta ₂ O ₅	Al ₂ O ₃	SiO ₂	Nb ₂ O ₅
44.56	21.96%	18.21%	1.42%	4.66%	3.88%	0.47%	1.19%	2.73%	0.93%
44.25	21.81%	18.09%	1.41%	4.62%	3.85%	0.46%	1.20%	3.38%	0.92%
43.95	21.66%	17.96%	1.40%	4.59%	3.83%	0.46%	1.19%	4.05%	0.91%
44.38	21.87%	18.14%	1.41%	4.64%	3.86%	0.46%	1.60%	2.71%	0.92%
44.08	21.72%	18.02%	1.40%	4.61%	3.84%	0.46%	1.59%	3.36%	0.92%
43.78	21.57%	17.89%	1.39%	4.57%	3.81%	0.46%	1.58%	4.03%	0.91%
44.20	21.78%	18.07%	1.41%	4.62%	3.85%	0.46%	1.99%	2.70%	0.92%
43.89	21.63%	17.94%	1.40%	4.59%	3.82%	0.46%	1.99%	3.38%	0.91%
43.60	21.48%	17.82%	1.39%	4.56%	3.80%	0.46%	1.98%	4.01%	0.91%

[0079] Figs. 12A-12C are graphs summarizing flow characteristics of example frit materials according to certain example embodiments.

[0080] Fig. 12A shows that, at 375 degrees C, increasing Ta₂O₅ percentage may cause an increase in the initial softening temperature and resulting reduction in the flow (e.g., the diameter of the 13mm button) for the example frit material. In certain example embodiments, increasing Nb₂O₅ percentage may provide less of a reduction in flow. As noted above, a frit (e.g., Ex. 21) with this composition may be used for a perimeter seal of a VIG unit.

[0081] Fig. 12B shows that, at 400 degrees C, Ex. 21 has improved flow characteristics. For example, with 1.0% Ta₂O₅, the frit flows well.

[0082] Fig. 12C shows, at 425 degrees C, Ex. 21 continuing to flow at higher temperatures, although, as shown above in Table 10D, the frit composition may become crystallized at such a temperature. However, Ex. 26 may continue to have good flow and has only a slight crystallization. Accordingly, Ex. 26 may continue to flow at higher temperatures.

[0083] It will be appreciated by those skilled in the art that CTE adjustments may be carried out on the overall frit material (e.g., the compound) for the glass wetting and bonding properties of the frit to cooperate with an underlying substrate (e.g., a glass substrate). In

certain example embodiments, CTE matching compounds may be added for these and/or other purposes.

[0084] It will be appreciated that one or more metal oxide, chloride, and/or fluoride additives may be used as additives in different embodiments of this invention. Furthermore, in certain example implementations, the metal oxide, chloride, and/or fluoride additives may be stoichiometric or sub-stoichiometric.

[0085] As used herein, the terms “on,” “supported by,” and the like should not be interpreted to mean that two elements are directly adjacent to one another unless explicitly stated. In other words, a first layer may be said to be “on” or “supported by” a second layer, even if there are one or more layers there between.

[0086] While the invention has been described in connection with what is presently considered to be the most practical and preferred embodiment, it is to be understood that the invention is not to be limited to the disclosed embodiment, but on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

WHAT IS CLAIMED IS:

1. A frit material having a composition, comprising:

Ingredient	Normalized Mole %
vanadium oxide	~45-50%,
barium oxide	~20-23%, and
zinc oxide	~19-21%; and

a least six additives selected from the group consisting of: Ta_2O_5 , Ti_2O_3 , SrCl_2 , GeO_2 , CuO , AgO , Nb_2O_5 , B_2O_3 , MgO , SiO_2 , TeO_2 , Ti_2O_3 , Y_2O_3 , SnF_2 , SnO_2 , SnCl_2 , CeO_2 , AgCl , In_2O_3 , SnO , SrO , MoO_3 , CsCO_3 , and Al_2O_3 .

2. The frit material of claim 1, wherein at least one of said at least six additives is Nb_2O_5 at between about 1-3 normalized mole %.

3. The frit material of any preceding claim, wherein at least one of said at least six additives is MoO_3 at between about 2.75-3.25 normalized mole %.

4. The frit material of any preceding claim, wherein at least one of said at least six additives is TeO_2 at between about 3.40-4.50 normalized mole %.

5. The frit material of any preceding claim, wherein at least one of said at least six additives is Ta_2O_5 at between about .5-1.5 normalized mole %

6. The frit material of any preceding claim, wherein the at least six additives include: MoO_3 , TeO_2 , Ta_2O_5 , Al_2O_3 , SiO_2 , and Nb_2O_5

7. The frit material of claim 6, wherein the Al_2O_3 and SiO_2 is included at amounts resulting from preparing MoO_3 , TeO_2 , Ta_2O_5 , and Nb_2O_5 in a crucible made of at least alumina and/or silica.

8. The frit material of any preceding claim, wherein the MoO_3 , TeO_2 , Ta_2O_5 , Al_2O_3 , SiO_2 , and Nb_2O_5 are included at the follow percentages:

Ingredient	Normalized Mole %
MoO_3	2.75%-3.25%

TeO ₂	3.25%-4.00%
Ta ₂ O ₅	0.25%-2.5%
Al ₂ O ₃ ,	0.5%-2.5%
SiO ₂ ,	1.5%-4.5%
Nb ₂ O ₅	1.00%-3.00%.

9. The frit material of claim 1, wherein MoO₃, Nb₂O₅, and Ta₂O₅ are included in the at least six additives.

10. The frit material of claim 9, wherein more Nb₂O₅ than Ta₂O₅ is included in the composition.

11. The frit material of any preceding claim, wherein the frit material has a melting temperature less than or equal to about 400 degrees C.

12. A vacuum insulated glass (VIG) unit, comprising:
first and second substantially parallel, spaced apart glass substrates;
an edge seal provided around a periphery of the first and second substrates to form a hermetic seal therebetween and at least partially defining a gap between the first and second substrates,

wherein the gap is provided at a pressure less than atmospheric,

wherein the edge seal is formed from a frit material at least initially having a composition according to claim 1.

13. A method of making a frit material, the method comprising:
providing a composition to a holder, the composition comprising:

Ingredient	by normalized mole %
vanadium oxide	~45-50%,
barium oxide	~20-23%, and
zinc oxide	~19-22%; and

a least four additives selected from the group consisting of: Ta₂O₅, Ti₂O₃, SrCl₂, GeO₂, CuO, AgO, Nb₂O₅, B₂O₃, MgO, SiO₂, TeO₂, Tl₂O₃, Y₂O₃, SnF₂, SnO₂, SnCl₂, CeO₂, AgCl, In₂O₃, SnO, SrO, MoO₃, CsCO₃, and Al₂O₃.

melting the composition;

cooling the melted composition and/or allowing the melted composition to cool so as to form an intermediate glass article;
grinding the intermediate glass article in making the frit material.

14. The method of claim 13, wherein the holder is made of at least alumina and/or silica, whereby as a result of melting the composition, Al_2O_3 and SiO_2 are leached from the holder into the composition.

15. The method of claim 14, wherein an amount of Al_2O_3 leached from the holder is between about 0.5% and 2% normalized moles, and an amount of SiO_2 leached from the holder is between about 0.5 and 2% normalized moles.

16. The method of any of claims 13-15, wherein the at least four additives comprises Nb_2O_5 at between about 1-3 normalized mole %.

17. The method of any of claims 13-16, wherein the at least four additives comprises MoO_3 at between about 2.75-3.25 normalized mole %.

18. The method of any of claims 13-17, wherein the at least four additives comprises Ta_2O_5 at between about .5-1.5 normalized mole %.

19. The method of any of claims 13-18, wherein the at least four additives comprises TeO_2 at between about 3-4 normalized mole %.

20. The method of any of claims 13-19, wherein the at least four additives include MoO_3 , TeO_2 , Ta_2O_5 , Al_2O_3 , SiO_2 , and Nb_2O_5 .

21. The method of any of claims 13-20, wherein the at least four additives include MoO_3 , TeO_2 , Ta_2O_5 , Al_2O_3 , SiO_2 , and Nb_2O_5 , which are included at the following percentages:

Ingredient	Normalized Mole %
MoO_3	2.75%-3.25%
TeO_2	3.25%-4.00%
Ta_2O_5	0.25%-2.5%

Nb₂O₅ 1.00%-3.00%.

22. The method of any of claims 13-21, wherein MoO₃, Nb₂O₅, and Ta₂O₅ are included in the at least four additives.

23. The method of claim 22, wherein more Nb₂O₅ than Ta₂O₅ is included in the composition.

24. The method of any of claims 13-23, wherein the frit material has a melting temperature less than or equal to about 400 degrees C.

25. A method of making a vacuum insulated glass (VIG) unit, the method comprising:



providing first and second glass substrates in substantially parallel, spaced apart relation to one another;

sealing together the first and second glass substrates using a frit material, a gap being defined between the first and second substrates,

wherein the sealing is performed by melting the frit material at a temperature of no more than about 400 degrees C, the frit material having been formed from a base composition including:

Ingredient	Normalized Mole %
vanadium oxide	~45-50%,
barium oxide	~20-23%, and
zinc oxide	~19-22%; and
at least four oxide-, chloride-, and/or fluoride-based additives.	

26. The method of claim 25, wherein the at least four oxide-, chloride-, and/or fluoride-based additives include MoO₃, TeO₂, Ta₂O₅, Al₂O₃, SiO₂, and Nb₂O₅.






FIG. 3




FIG. 4




Fig. 6




Fig. 7A




Fig. 7B




Fig. 7C

Transition Glass Temperature Compared to Slide Melt Quality




Fig. 7D




Fig. 8A




Fig. 8B




Fig. 8C




Fig. 9




Fig. 10A




Fig. 10B




Fig. 10C




Fig. 11A




Fig. 11B




Fig. 11C




Fig. 12A




Fig. 12B



400C 13mm Button for Ta₂O₅ and Nb₂O₅ Matrix

Fig. 12C



INTERNATIONAL SEARCH REPORT

International application No
PCT/US2012/053010

A. CLASSIFICATION OF SUBJECT MATTER
INV. C03C8/04 C03C8/24
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 2012/115796 A1 (GUARDIAN INDUSTRIES [US]; DENNIS TIMOTHY A [US]) 30 August 2012 (2012-08-30) abstract paragraph [0061]	13,14, 24,25
X	----- US 2005/233885 A1 (YOSHIDA MASAHIRO [JP] ET AL) 20 October 2005 (2005-10-20) cited in the application abstract paragraph [0001] paragraph [0091] example v8; table 3 examples v35, v38; table 5	1-26
X	----- US 2006/003883 A1 (YOSHIDA MASAHIRO [JP] ET AL) 5 January 2006 (2006-01-05) abstract claim 1; examples g1,g2	1-26

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

16 November 2012

Date of mailing of the international search report

27/11/2012

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Picard, Sybille

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2012/053010

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2012115796 A1	30-08-2012	US 2012213951 A1 WO 2012115796 A1	23-08-2012 30-08-2012
US 2005233885 A1	20-10-2005	CN 1738776 A CN 101016196 A EP 1595856 A1 JP 4299021 B2 JP 2004250276 A KR 20050105167 A KR 20100049651 A TW 1274746 B US 2005233885 A1 US 2007184963 A1 US 2007191203 A1 WO 2004074198 A1	22-02-2006 15-08-2007 16-11-2005 22-07-2009 09-09-2004 03-11-2005 12-05-2010 01-03-2007 20-10-2005 09-08-2007 16-08-2007 02-09-2004
US 2006003883 A1	05-01-2006	CN 1787978 A EP 1642871 A1 HK 1090910 A1 JP 3914245 B2 US 2006003883 A1 WO 2005000755 A1	14-06-2006 05-04-2006 30-05-2008 16-05-2007 05-01-2006 06-01-2005