

(12) PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. AU 199935394 B2
(10) Patent No. 754614

- (54) Title
Process for the hydrogenation of phenyl acetylene in a styrene-containing medium with the aid of a catalyst
- (51)⁷ International Patent Classification(s)
C07C 007/167
- (21) Application No: **199935394** (22) Application Date: **1999.04.26**
- (87) WIPO No: **WO99/55648**
- (30) Priority Data
- | | | |
|----------------|-------------------|--------------|
| (31) Number | (32) Date | (33) Country |
| 1009014 | 1998.04.28 | NL |
- (43) Publication Date : **1999.11.16**
(43) Publication Journal Date : **2000.01.20**
(44) Accepted Journal Date : **2002.11.21**
- (71) Applicant(s)
DSM N.V.
- (72) Inventor(s)
Hubertus Johannes Mechtilda Bosman; Edwin Jacco Grootendorst; Leonardus Hubertus Postma; Theodorus Maria Smeets
- (74) Agent/Attorney
SPRUSON and FERGUSON,GPO Box 3898,SYDNEY NSW 2001




PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁶ : C07C 7/167</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/55648</p> <p>(43) International Publication Date: 4 November 1999 (04.11.99)</p>
<p>(21) International Application Number: PCT/NL99/00245</p> <p>(22) International Filing Date: 26 April 1999 (26.04.99)</p> <p>(30) Priority Data: 1009014 28 April 1998 (28.04.98) NL</p> <p>(71) Applicant (for all designated States except US): DSM N.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): BOSMAN, Hubertus, Johannes, Mechtilda [NL/NL]; Wielewaalstraat 13, NL-6135 EN Sittard (NL). GROOTENDORST, Edwin, Jacco [NL/NL]; Ankersweg 57, NL-6123 AJ Born (NL). POSTMA, Leonardus, Hubertus [NL/NL]; St. Pieterstraat 101A, NL-6463 CX Kerkrade (NL). SMEETS, Theodorus, Maria [NL/NL]; Burg. Eussenstraat 6, NL-6181 BP Stein (NL).</p> <p>(74) Agent: SCHELTUS, Irma; Octrooibureau DSM, P.O. Box 9, NL-6160 MA Geleen (NL).</p>	<p>(81) Designated States: AE, AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: PROCESS FOR THE HYDROGENATION OF PHENYL ACETYLENE IN A STYRENE-CONTAINING MEDIUM WITH THE AID OF A CATALYST</p>		
<p>(57) Abstract</p> <p>The invention relates to a process for the hydrogenation of phenyl acetylene in a styrene-containing medium with the aid of a supported nickel catalyst with a nickel content of 10-25 wt.%. This process is by preference used for the hydrogenation of phenyl acetylene in a styrene-containing medium which contains more than 30 wt.% of styrene.</p>		



PROCESS FOR THE HYDROGENATION OF PHENYL ACETYLENE
IN A STYRENE-CONTAINING MEDIUM
WITH THE AID OF A CATALYST

The invention relates to a process for the hydrogenation of phenyl acetylene in a styrene-containing medium with the aid of a catalyst and in the presence of hydrogen gas.

Styrene is often polymerized to polystyrene. In the styrene-containing medium which is used for this purpose, the phenyl acetylene causes undesirable side reactions during the polymerization, such as cross-linking of the polymer chains. It is therefore of importance to keep the phenyl acetylene content of the styrene-containing medium as low as possible.

The above-mentioned process for the hydrogenation of phenyl acetylene is known from JP-A-55,35368.

Said patent publication describes a process for the hydrogenation of phenyl acetylene in a mixture of styrene, phenyl acetylene and o-xylene with the aid of a palladium or nickel catalyst. In the specific Example hydrogenation is effected with the aid of a palladium catalyst on an alumina carrier.

A drawback of the use of a palladium catalyst is that a palladium catalyst, when used for the hydrogenation of phenyl acetylene in a styrene-containing medium with minor



amounts of impurities, rapidly loses its activity and thus has a short service life. This is a major drawback because it entails high catalyst regeneration costs. Further, regeneration of the catalyst means loss of production or the need to have a second reactor which is put on stream while the catalyst is being regenerated in the first reactor.

The aim of the invention is to provide a catalyst which does not present said drawback or only to a lesser extent.

The invention is characterized in that the catalyst is a supported nickel catalyst with a nickel content of 10-25 wt.%. Surprisingly it has appeared now that in a same styrene-containing medium a nickel catalyst is much less sensitive to impurities and thus has a much longer service life. This is all the more surprising in that a person skilled in the art, relying on his knowledge of catalysts, would not be likely to opt for a nickel catalyst instead of a palladium catalyst, since a nickel catalyst normally has a lower activity and selectivity than a palladium catalyst in the conversion of acetylenes to alkenes (see for instance J.A. Moulijn, P.W.N.M. van Leeuwen and R.A. van Santen, Catalysis, Elsevier, 1993, pp. 180-181).

Further advantages of application of a nickel catalyst are that the price of a nickel catalyst is lower than that of a palladium catalyst and that nickel catalysts are commercially available with a larger catalytically active surface area.

The nickel catalyst applied according to the invention is a supported nickel catalyst. Examples



of suitable carrier materials are: silica, α -, θ - and γ -alumina, zeolites, carbon and oxidic carriers, such as for instance magnesium oxide, titanium oxide and zirconium oxide. Mixtures of different carrier materials can also be used. By preference, θ - and γ -alumina, silica or carbon are used as carrier material. Particular preference is given to θ - or γ -alumina as carrier material, because this is an inert carrier material with a large total surface area and a good poor volume distribution.

The nickel catalyst is synthesized for instance in the following way. The nickel is applied onto the carrier material by impregnating it with a solution of nickel salts. Water is commonly used as solvent. Then the impregnated carrier material is dried and subsequently calcinated at elevated temperature. The nickel oxide thus obtained is then activated on the carrier material through a treatment with hydrogen at elevated temperature. A high degree of dispersion of the nickel on the carrier results in a catalyst with a large catalytically active surface area. The higher the catalytically active surface area in the catalyst, the better the phenyl acetylene is hydrogenated.

For economical and technical reasons the nickel content of the nickel catalyst is kept as low as possible. A nickel catalyst with a higher nickel content is more expensive and when the nickel content becomes higher, the dispersion of the nickel in the catalyst is worse.

The nickel content of the catalyst is

normally 10-25 wt.%. Supported nickel catalysts are commercially available with for instance 10, 15 or 20 wt.% of nickel. The nickel content of the nickel catalyst preferably is 11 to 25 wt.%.

5 Most preferably the nickel content of the catalyst is more than 11 and less or equal to 20 wt.%.

Besides the nickel the catalyst can also contain minor amounts of other compounds which enhance the activity and selectivity of the catalyst. Examples
10 of such compounds are: chromium, gold, rhodium and ruthenium. The catalyst can also be modified with sulphur-containing compounds.

When its activity in the hydrogenation of phenyl acetylene has declined strongly, the nickel
15 catalyst can be regenerated. Regeneration is effected for instance by treating the contaminated catalyst with steam and air at a high temperature, for instance 300 to 350°C, followed by reduction with hydrogen at the same temperature. If the catalyst is lightly
20 contaminated it can also be regenerated by merely treating it with hydrogen at an elevated temperature of 100-300 °C.

When naphtha, gas condensates and LPG are cracked, cracked petrol is formed. This cracked petrol
25 mainly contains aliphatic and aromatic compounds with 6-9 carbon atoms, including 1-50 wt.% of styrene. Fractionation of this cracked petrol yields a C8 fraction which contains 30-70 wt.% of styrene. When this C8 fraction is extracted with a solvent and then
30 distilled, a styrene-rich fraction is obtained which may contain more than 95 wt.% of styrene. The cracked

petrol, the C8 fraction as well as the styrene-rich fraction can be used as styrene-containing medium.

A styrene-containing medium can also be obtained by means of chemical synthesis. Alkylation of benzene with ethene gives ethyl benzene, which through
5 dehydrogenation can be converted into a styrene-containing medium which besides styrene can also contain ethyl benzene and phenyl acetylene.

The invention is not restricted, however,
10 to the hydrogenation of phenyl acetylene in the above-mentioned styrene-containing media. Styrene-containing media which have been obtained in another way can also be employed.

The styrene-containing media can comprise
15 up to 99.99 wt.% of styrene.

The styrene-containing medium preferably comprises more than 30 wt.% of styrene. By particular preference, the styrene-containing medium is a C8 hydrocarbon fraction which comprises more than 30 wt.%
20 of styrene.

In the hydrogenation of phenyl acetylene in the styrene-containing medium it is preferred for all phenyl acetylene in the styrene-containing medium to be converted to styrene or ethyl benzene, with a limited
25 amount of phenyl acetylene or styrene being hydrogenated to ethyl benzene.

The phenyl acetylene content of a styrene-containing medium is normally between 0.01 and 5 wt.% relative to the styrene present in the styrene-
30 containing medium. During the hydrogenation process according to the invention this content is reduced.

Said content is preferably reduced to less than 100 ppm, by particular preference to less than 10 ppm in the styrene-containing medium.

The process for the hydrogenation of phenyl acetylene in a styrene-containing medium is carried out in a reactor. The catalyst on a support is present in the reactor. The reactor is fed with the styrene-containing medium and hydrogen gas. The hydrogen gas can optionally have been diluted with another, inert gas such as for instance nitrogen gas. The styrene-containing medium and the hydrogen gas can be mixed before being fed to the reactor.

The reactor can be operated as a two-phase or as a three-phase reactor.

If the reactor is operated as a two-phase reactor, then the hydrogen gas that is required for the hydrogenation of the phenyl acetylene is fully dissolved in the styrene-containing medium that is supplied to the reactor.

If the reactor is operated as a three-phase reactor the styrene-containing medium and the hydrogen gas are fed in at the bottom of the reactor and the product is obtained at the top of the reactor. It is also possible to supply the styrene-containing medium and the hydrogen gas at the top of the reactor and to recover the product at the bottom of the reactor. The reactor can also be operated as a countercurrent reactor, with for instance the hydrogen gas being supplied at the bottom of the reactor and the styrene-containing medium at the top. The product is recovered at the bottom of the reactor.

By preference the styrene-containing medium and the hydrogen gas are supplied at the bottom of the reactor, because there is less backmixing then and thus less styrene and phenyl acetylene react further to form ethyl benzene.

The nickel catalyst is preferably present in a fixed bed in the reactor. The styrene-containing medium and the hydrogen gas are contacted with this fixed bed.

A fixed bed is a bed of solid catalyst parts that can have different shapes and can be, for instance, granules, pellets, extrudates, spheres, triloops and gaudruloops. The fixed bed can also consist of a monolith or of miniliths.

The hydrogen pressure in the reactor is usually between 0 and $300 \cdot 10^5$ Pa overpressure, preferably between 0 and $50 \cdot 10^5$ Pa overpressure. Preferably a low pressure is applied, because then the reactor does not have to have a thick wall and is therefore less costly.

The temperature is usually between 0 and 100 °C, preferably between 15 and 50 °C. If the temperature rises above 50 °C, polymerization of styrene occurs during the reaction.

The process according to the invention is preferably carried out with a hydrogen : phenyl acetate molar ratio ≥ 1 . By preference this molar ratio is between 1 and 10. For commercial-scale applications this molar ratio is preferably between 1 and 4. The molar ratio is kept as low as possible in order to prevent conversion of styrene and phenyl acetylene into

ethyl benzene.

The average residence time of the styrene-containing medium in the reactor should not be too long, because then more styrene and/or phenyl acetylene
5 react(s) further to ethyl benzene. The average residence time should not be too short either, because then the degree of conversion of phenyl acetylene to styrene is too low. A measure for the average residence time is the liquid hourly space velocity (LHSV).

10 The process according to the invention is usually carried out with a LHSV of between 0.1 and 100 per hour, preferably between 1 and 10 per hour.

The invention will now be elucidated by means of examples, without being restricted thereto.

15

Examples:

Example I

A reactor with a capacity of 1 m³ was
20 completely filled with a fixed bed consisting of a nickel catalyst on θ -alumina. The catalyst contained 15 wt.% of nickel.

A C8 fraction comprising 50 wt.% of styrene, 8 wt.% of ethyl benzene and 0.8 wt.% of phenyl
25 acetylene was supplied to the bottom of this reactor. Hydrogen gas was also supplied to the bottom of the reactor, the hydrogen gas : phenyl acetylene molar ratio being kept between 2 and 3. The LHSV was 4 h⁻¹ and the contact time was 15 minutes.

30 Further data of the reaction are presented in Table 1. The data were registered after different

on-stream times of the reactor. Measurements were carried out after 10, 100 and 220 days.

Comparative Example A

5 In the reactor of example I a hydrogenation reaction was carried out with a palladium catalyst instead of a nickel catalyst. A palladium catalyst on γ -alumina containing 0.2 wt.% of palladium was used. The other reaction conditions were the same as in
10 example I. The service life of this catalyst was only 10 days. After 10 days the degree of conversion of phenyl acetylene had declined to the point where continuation of the hydrogenation reaction with this catalyst was not sensible any more.

15 Further data of the reaction are presented in Table 1.

Example II

20 In the reactor of Example I a hydrogenation reaction was carried out with the catalyst according to Example I after regeneration. The catalyst was regenerated by treating it with steam and air at 300 °C, followed by reduction with hydrogen at the same temperature.

25 The LHSV was 6 hr⁻¹ and the contact time was 10 minutes. The other reaction conditions were the same as in Example I.

30 Data after different on-stream times of the reactor were registered. Measurements were carried out after 10 and 100 days. Further data of the reaction are presented in Table 1.

The catalyst contained 15 wt.% of nickel.

At the bottom of the reactor a C8 fraction was supplied, containing 50 wt.% of styrene, 8 wt.% of ethyl benzene and 0.8 wt.% of phenyl acetylene.. The
5 LHSV was 5 hr⁻¹, the hydrogen pressure was 3 bar and the inlet temperature was 40 °C. Hydrogen gas was also supplied via the reactor bottom, with a varying hydrogen gas / phenyl acetylene molar ratio, as indicated in Table 2. From Table 2 it appears that at a
10 higher hydrogen gas / phenyl acetylene molar ratio the conversion of phenyl acetylene increases. Some styrene is reacted further to ethyl benzene, however, causing the net styrene yield to decrease a little again.

15 Example IV

Example III was repeated, using a nickel catalyst on θ -alumina containing 20 wt.% of nickel instead of 15 wt.%. The inlet temperature was 30 °C. The other reaction conditions were the same as in Example
20 III. Hydrogen gas was supplied via the reactor bottom, with a varying hydrogen gas / phenyl acetylene molar ratio, as indicated in Table 2. From Table 2 it appears that at a higher nickel content of the catalyst the same degree of conversion of phenyl acetylene is
25 obtained with a lower hydrogen / phenyl acetylene molar ratio. From this example it also appears that when the hydrogen / phenyl acetylene molar ratio is too high, styrene is also hydrogenated.

Table 2

Example	H ₂ / ph (mol/mol)	X _{ph} (%)	S (%)
III	3	98.5	0.3
	5	99.9	0.1
	7	99.9	0.1
IV	1	91	0.4
	2	99.9	0.2
	3	99.9	-0.2

Explanation of the symbols:

- 5 X_{ph} = conversion of phenyl acetylene
H₂/ph = molar ratio hydrogen / phenyl acetylene
S = net styrene yield in the medium leaving the reactor relative to the medium supplied to the reactor

10

Example V

Example III was repeated at elevated temperature and with a LHSV of 5.5 hr⁻¹. At a temperature of 70 °C the conversion of phenyl acetylene was 94% at the start of the experiment. After 5 days the conversion of phenyl acetylene had declined to 30%.

At a temperature of 90 °C the conversion of phenyl acetylene was 100% at the start of the experiment. After 4 days the conversion of phenyl acetylene had declined to 40%.

20

The strong decline of the conversion of phenyl acetylene is due to formation of polystyrene on the catalyst surface at higher temperatures, resulting in loss of catalyst activity.

AMENDED SET OF CLAIMS

1. Process for the hydrogenation of phenyl acetylene in a styrene-containing medium with the aid of a catalyst and in the presence of hydrogen gas, characterized in that the catalyst is a nickel catalyst with a nickel content of 10-25 wt.% supported on a carrier material and in that the hydrogen gas / phenyl acetylene molar ratio is 1-10.
2. Process according to claim 1, characterized in that the nickel content of the catalyst is 11-25 wt.%.
3. Process according to any one of claims 1-2, characterized in that the carrier material is θ - or γ -alumina.
4. Process according to any one of claims 1-3, characterized in that the catalyst is a fixed-bed catalyst with which the styrene-containing medium and the hydrogen gas are contacted.
5. Process according to any one of claims 1-4, characterized in that the styrene-containing medium and the hydrogen gas are supplied at the bottom of the reactor.
6. Process according to any one of claims 1-5, characterized in that the hydrogen gas / phenyl acetylene molar ratio is 1-4.
7. Process according to any one of claims 1-6, characterized in that the phenyl acetylene content of the styrene-containing medium is 0.01-5 wt.%.
8. Process according to any one of claims 1-7, characterized in that the temperature is between 15 and 50 °C.
9. Process according to any one of claims 1-8, characterized in that the LHSV is between 0.1 and 100 per hour.
10. Process according to any one of claims 1-8, characterized in that the LHSV is between 1 and 10 per hour.
11. Process according to any one of claims 1-10, characterized in that the styrene-containing medium contains \geq 30 wt.% of styrene.



10-05-2000

14

NL 009900245

9271WO

Enclosure 1.2

10.05.00

12. Process according to any one of claims 1-10, characterized in that the styrene-containing medium is a C8 hydrocarbon fraction containing ≥ 30 wt.% of styrene.



AMENDED SHEET