



(11)

EP 3 907 326 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:

06.11.2024 Bulletin 2024/45

(21) Application number: **19907909.6**

(22) Date of filing: **24.12.2019**

(51) International Patent Classification (IPC):

D06M 13/224 ^(2006.01) **D04H 1/4258** ^(2012.01)
D04H 1/492 ^(2012.01) **D06M 13/02** ^(2006.01)
D06M 13/148 ^(2006.01) **D06M 13/184** ^(2006.01)
D06M 15/53 ^(2006.01) **D06M 15/643** ^(2006.01)
D06M 101/04 ^(2006.01) **D06M 13/17** ^(2006.01)
D04H 1/74 ^(2006.01)

(52) Cooperative Patent Classification (CPC):

D04H 1/74; D04H 1/4258; D04H 1/492;
D06M 13/02; D06M 13/148; D06M 13/17;
D06M 13/188; D06M 13/224; D06M 15/53;
D06M 15/643; D06M 15/6436; D06M 2200/40

(86) International application number:

PCT/JP2019/050497

(87) International publication number:

WO 2020/141592 (09.07.2020 Gazette 2020/28)

(54) **STAPLE FIBER TREATMENT AGENT, STAPLE FIBER, AND METHOD FOR MANUFACTURING SPUN-LACE NON-WOVEN CLOTH**

STAPELFASERBEHANDLUNGSMITTEL, STAPELFASER UND VERFAHREN ZUR HERSTELLUNG VON SPINNVLIESSTOFF

AGENT DE TRAITEMENT DE FIBRES DISCONTINUES, FIBRE DISCONTINUE ET PROCÉDÉ DE FABRICATION DE TISSU NON TISSÉ HYDROLIÉ

(84) Designated Contracting States:

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **04.01.2019 JP 2019000238**

(43) Date of publication of application:

10.11.2021 Bulletin 2021/45

(73) Proprietor: **Takemoto Yushi Kabushiki Kaisha**
Gamagori-shi, Aichi 443-8611 (JP)

(72) Inventors:

- **OHGAI, Takashige**
Gamagori-shi, Aichi 443-8611 (JP)
- **ICHIKAWA, Toshiki**
Gamagori-shi, Aichi 443-8611 (JP)

• **KOMURO, Toshihiro**

Gamagori-shi, Aichi 443-8611 (JP)

(74) Representative: **Petraz, Gilberto Luigi et al**
GLP S.r.l.

Viale Europa Unita, 171
33100 Udine (IT)

(56) References cited:

EP-A1- 2 712 956 WO-A1-2016/104106
CN-A- 106 176 291 DE-A1- 3 932 032
JP-A- 2014 105 396 JP-A- 2014 240 530
JP-A- 2014 240 530 JP-A- 2015 145 545
JP-A- 2018 040 100 JP-A- 2018 071 013
JP-A- 2018 071 013 JP-B2- H0 154 047
US-A- 5 258 129 US-A1- 2005 136 098

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

TECHNICAL FIELD

5 **[0001]** The present invention relates to a short fiber treatment agent according to claim 1, a short fiber to which the short fiber treatment agent is applied, and a method for manufacturing a spunlace nonwoven fabric using short fibers to which the short fiber treatment agent is applied, and the use of the short fiber treatment agent in the treatment of viscose rayon short fibers

10 BACKGROUND ART

[0002] Natural fibers such as cotton fibers, regenerated fibers such as rayon, and synthetic fibers such as polyolefin are generally used as raw material fibers for nonwoven fabrics. A treatment of applying a nonwoven fabric treatment agent containing a surfactant and the like to surfaces of raw material fibers is performed in some cases to impart, to the raw material fibers, various characteristics such as lubricity and bundling properties required in manufacturing of non-woven fabrics.

[0003] In the related art, nonwoven fabric treatment agents disclosed in Patent documents 1 and 2 are known. Patent document 1 discloses a configuration of a nonwoven fabric treatment agent containing a mineral oil, a fatty acid ester, and a polyoxyalkylene polyhydric alcohol fatty acid ester. Patent document 2 discloses a configuration of a fiber treatment agent for hydroentanglement through highly pressurized water jets containing a polyhydric alcohol fatty acid ester sulfate salt, a mineral oil, and a polyoxyalkylene polyhydric alcohol fatty acid ester.

JP2018071013 is directed to a fiber treatment agent for spunlace that contains a polyoxyalkylene derivative and aliphatic acid and/or oil and fat, and discloses at Example 18 that the fiber treatment agent contains a polyoxyethylene stearyl ester (corresponding to the "fatty acid derivative" defined in claim 1 of the present application), hardened castor oil (corresponding to the "at least one selected from fatty acids and oils and fats" defined in claim 1 of the present application), and polyoxyethylene polyoxypropylene glycol that includes 20 oxyethylene units and 30 oxypropylene units. However, there is no disclosure or suggestion in this prior art document that the fiber treatment agent may contain any other polyhydric alcohol than polyoxyethylene polyoxypropylene glycol that includes 20 oxyethylene units and 30 oxypropylene units.

CN106176291 is directed to a baby hand swipe compounding solution that may contain propylene glycol or polyethylene glycol (corresponding to the "polyhydric alcohol" defined in claim 1 of the present application) as a moisturizing agent or castor oil (corresponding to the "at least one selected from fatty acids and oils and fats" defined in claim 1 of the present application) as a skin care agent. However, there is no disclosure or suggestion in this prior art document that the baby hand swipe compounding solution may further contain "a fatty acid derivative" as defined in claim 1 of the present application. Although this prior art document discloses the use of PEG-35 hydrogenated castor oil and PEG-45 castor oil as solubilizing agents, such compounds do not fall under the "fatty acid derivative" defined in claim 1 of the present application since the "fatty acid derivative" has 0.1 to 30 moles of alkylene oxide added. This document further discloses the use of an aliphatic alcohol ethoxylate as a nonionic surfactant, but which does not fall under the "fatty acid derivative" defined in claim 1 of the present application. Furthermore, there is no disclosure or suggestion that the baby hand swipe compounding solution is used as a short fiber treatment agent composition.

EP2712956 is directed to a processing agent for synthetic fibers that contains five components, Components A to E. Examples of Component B include polyoxyethylene oleate and polyoxyethylene stearate, each of which corresponds to the "fatty acid derivative" defined in claim 1 of the present application. Examples of Component A, some of which may correspond to the "at least one selected from fatty acids and oils and fats" defined in claim 1 of the present application. However, there is no disclosure or suggestion that the processing agent may contain "polyhydric alcohol" as defined in claim 1 of the present application. Furthermore, the processing agent of this prior art document is used by applying to filament yarns, which are long fibers. There is no disclosure or suggestion that the processing agent is a short fiber treatment agent, which is used, for example, for manufacturing a spunlace nonwoven fabric.

JP2015145545 is directed to a synthetic fiber treatment agent that contains a specific ester and a nonionic surfactant. Examples of the nonionic surfactant include polyethylene glycol dilaurate, polyethylene glycol monooleate, polyethylene glycol dioleate, and polyethylene glycol distearate, each of which corresponds to the "fatty acid derivative" defined in claim 1 of the present application. Moreover, the synthetic fiber treatment agent may further contain ethylene glycol or propylene glycol, which corresponds to the "polyhydric alcohol" defined in claim 1 of the present application. However, there is no disclosure or suggestion in this prior art document that the synthetic fiber treatment agent may further contain "at least one selected from fatty acids and oils and fats" as defined in claim 1 of the present application. Furthermore, the synthetic fiber treatment agent is used by applying to filament yarns, which are long fibers.

PRIOR ART LITERATURE

PATENT LITERATURE

5 [0004]

Patent document 1: International Publication No. WO 2016/104106

Patent document 2: Japanese Patent No. 6096061

10 SUMMARY OF THE INVENTION

PROBLEM TO BE SOLVED BY THE INVENTION

15 [0005] The nonwoven fabric treatment agents of the related art, however, have a problem of frequent bubble formation in water used for hydroentanglement in a step of manufacturing nonwoven fabrics, that is, a problem of foaming when the treatment agent dropped from raw material fibers is mixed into water.

[0006] The present invention has been made in view of these circumstances, and an object thereof is to provide a short fiber treatment agent that can inhibit foaming of water used for hydroentanglement. Another object of the present invention is to provide a short fiber to which the short fiber treatment agent is applied. Still another object of the present invention is to provide a method for manufacturing a spunlace nonwoven fabric using short fibers to which the short fiber treatment agent is applied.

MEANS FOR SOLVING THE PROBLEM

25 [0007] As a result of study to solve the problem, the inventors of the present invention have found that a short fiber treatment agent according to present claim 1 including a specific fatty acid derivative, a specific fatty acid or oil or fat, a specific polyhydric alcohol and a specific lubricant is definitely suitable.

[0008] A short fiber treatment agent for solving the above-mentioned problem contains a fatty acid derivative, at least one selected from fatty acids and oils and fats, a polyhydric alcohol excluding polyoxyethylene polyoxypropylene glycol that includes 20 oxyethylene units and 30 oxypropylene units, and a lubricant as claimed. The fatty acid derivative has a structure in which an alkylene oxide is added, at a ratio of 0.1 to 30 mol, to 1 mol of a fatty acid having 12 to 24 carbon atoms. The fatty acids have 12 to 24 carbon atoms. The oils and fats are at least one selected from vegetable oils, animal oils, and hardened oils thereof. The polyhydric alcohol has 2 to 6 hydroxy groups in the molecule. The short fiber treatment agent composition also comprises at least one lubricant selected from a hydrocarbon compound, an ester excluding the oils and fats and a silicone.

[0009] It is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, and the polyhydric alcohol in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 99.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, and the content of the polyhydric alcohol be 0.1 to 90 parts by mass.

40 [0010] It is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, and the lubricant in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 98.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, the content of the polyhydric alcohol be 0.1 to 90 parts by mass, and the content of the lubricant be 1 to 20 parts by mass.

45 [0011] It is preferable that the at least one lubricant is a silicone.

[0012] The short fiber treatment agent preferably further contains an anionic surfactant.

[0013] In this case, it is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, and the anionic surfactant in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 98.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, the content of the polyhydric alcohol be 0.1 to 90 parts by mass, and the content of the anionic surfactant be 1 to 20 parts by mass. It is reminded that the oils and fats are at least one selected from vegetable oils, animal oils, and hardened oils thereof.

[0014] The short fiber treatment agent may have a configuration including both an anionic surfactant and at least one lubricant selected from a hydrocarbon compound, an ester excluding the oils and fats, and a silicone.

55 [0015] In this case, it is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, the anionic surfactant, and the lubricant in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 97.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, the content

of the polyhydric alcohol be 0.1 to 90 parts by mass, the content of the anionic surfactant be 1 to 20 parts by mass, and the content of the lubricant be 1 to 20 parts by mass.

[0016] A short fiber to be treated with the short fiber treatment agent is preferably viscose rayon.

[0017] A short fiber for solving the above-mentioned problem is a short fiber to the surface of which the short fiber treatment agent is applied.

[0018] A method for manufacturing a spunlace nonwoven fabric for solving the above-mentioned problem includes a first step and a second step. The first step is a step of carding fibers having a length of 100mm or shorter, to the surface of which the short fiber treatment agent composition as indicated above is applied, to manufacture a web. The second step is a step of entangling the web obtained in the first step through water jets.

EFFECT OF THE INVENTION

[0019] The present invention succeeds in inhibiting foaming of water used for hydroentanglement when short fibers to which a short fiber treatment agent is applied are hydroentangled.

MODES FOR CARRYING OUT THE INVENTION

(First embodiment)

[0020] A first embodiment will now be described that embodies a short fiber treatment agent according to the present invention. The short fiber treatment agent contains the following fatty acid derivative, at least one selected from the following fatty acids and the following oils and fats, the following polyhydric alcohol and the following lubricant.

[0021] The fatty acid derivative has a structure in which an alkylene oxide is added to 1 mol of a fatty acid having 12 to 24 carbon atoms at a ratio of 0.1 to 30 mol. Specific examples of fatty acid derivatives include (1) polyoxyalkylene alkyl (or alkylene) esters obtained by addition reaction of an alkylene oxide to saturated or unsaturated fatty acids, such as polyoxyethylene (in which the number n of oxyethylene units (= the number of moles of ethylene oxide added) is 20, that is, n = 20) oleate, polyoxyethylene (n = 10) oleate, polyoxyethylene (n = 30) oleate, polyoxyethylene (n = 5) stearate, polyoxyethylene (n = 10) stearate, polyoxyethylene (n = 10) lauryl esters, and polyoxyalkylene (n = 10, in which the number m of oxypropylene units (= the number of moles of propylene oxide added) is 10, that is, m = 10) stearyl esters; (2) polyalkylene glycol alkyl (or alkylene) esters obtained by addition reaction of a polyalkylene glycol to saturated or unsaturated fatty acids, such as polyethylene glycol (molecular weight: 400) monooleate, polyethylene glycol (molecular weight: 600) dioleate, polyethylene glycol (molecular weight: 1,000) monostearate, polyethylene glycol (molecular weight: 400) dilaurate, and polyethylene glycol (molecular weight: 1,000) distearate; and (3) esters of oils and fats of polyoxyalkylene obtained by addition reaction of an alkylene oxide to oils and fats, such as polyoxyethylene (n = 30) castor oil esters, polyoxyalkylene (n = 10, m = 10) castor oil esters, polyoxyethylene (n = 10) hardened castor oil esters, and a reaction product of a coconut fatty acid and 10 moles of ethylene oxide. The components may be used alone or in a combination of two or more kinds thereof. In addition, an addition form of ethylene oxide and propylene oxide is not particularly limited and may be any form of block addition, random addition, and a combination of block addition and random addition in a case where ethylene oxide and propylene oxide are contained as an alkylene oxide.

[0022] The fatty acids have 12 to 24 carbon atoms. Specific examples of fatty acids having 12 to 24 carbon atoms include lauric acid, myristic acid, palmitic acid, stearic acid, oleic acid, linoleic acid, linolenic acid, arachidic acid, behenic acid, lignoceric acid, and coconut fatty acids. The components may be used alone or in a combination of two or more kinds thereof.

[0023] The oils and fats are at least one selected from vegetable oils, animal oils, and hardened oils thereof. Specific examples of oils and fats include castor oil, sesame oil, tall oil, palm oil, palm kernel oil, coconut oil, rapeseed oil, lard, beef tallow, whale oil, and hardened oils thereof. The components may be used alone or in a combination of two or more kinds thereof.

[0024] The polyhydric alcohol has 2 to 6 hydroxy groups in the molecule. The polyhydric alcohol used in the present embodiment is selected from polyhydric alcohols excluding polyoxyethylene (in which the number of oxyethylene units is 20) polyoxypropylene (in which the number of oxypropylene units is 30) glycol. Specific examples of the polyhydric alcohol include ethylene glycol, propylene glycol, pentanediol, hexanediol, glycerin, pentaerythritol, sorbitol, sorbitan, polyethylene glycol, polypropylene glycol, and a reaction product of propylene glycol and an alkylene oxide. The components may be used alone or in a combination of two or more kinds thereof.

[0025] The ratio among the contents of the fatty acid derivative, the fatty acids, the oils and fats, and the polyhydric alcohol in the short fiber treatment agent of the present embodiment is not limited. It is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, and the polyhydric alcohol in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 99.99 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10

parts by mass, and the content of the polyhydric alcohol be 0.1 to 90 parts by mass. The effects of the present invention can be further improved with this configuration.

[0026] The short fiber treatment agent of the present embodiment further contains at least one lubricant selected from a hydrocarbon compound, an ester excluding the oils and fats, and a silicone. The effects of the present invention can be further improved by blending the lubricant. The lubricant components may be used alone or in a combination of two or more kinds thereof.

[0027] Specific examples of hydrocarbon compounds include mineral oils and paraffin wax.

[0028] Specific examples of esters include butyl stearate, stearyl stearate, glycerin monooleate, glycerin trioleate, sorbitan monolaurate, sorbitan trilaurate, sorbitan monooleate, sorbitan trioleate, sorbitan monostearate, and sorbitan tristearate.

[0029] Specific examples of silicones include dimethyl silicone, amino-modified silicones, and polyoxyalkylene-modified silicones.

[0030] The ratio among the contents of the fatty acid derivative, the fatty acids, the oils and fats, the polyhydric alcohol, and the lubricant in the short fiber treatment agent of the present embodiment is not limited. It is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, and the lubricant in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 98.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, the content of the polyhydric alcohol be 0.1 to 90 parts by mass, and the content of the lubricant be 1 to 20 parts by mass, . The effects of the present invention can be further improved with this configuration.

[0031] The short fiber treatment agent of the present embodiment preferably further contains an anionic surfactant. The effects of the present invention can be further improved by blending the anionic surfactant. The type of anionic surfactant is not particularly limited, and examples thereof include (1) alkali metal salts of phosphoric acid esters of aliphatic alcohols, such as alkali metal salts of lauryl phosphoric acid esters, alkali metal salts of cetyl phosphoric acid esters, alkali metal salts of oleyl phosphoric acid esters, and alkali metal salts of stearyl phosphoric acid esters; (2) alkali metal salts of phosphoric acid esters in which at least one alkylene oxide selected from ethylene oxide and propylene oxide is added to aliphatic alcohols, such as alkali metal salts of polyoxyethylene (n = 5) lauryl ether phosphoric acid esters, alkali metal salts of polyoxyethylene (n = 5) oleyl ether phosphoric acid esters, and alkali metal salts of polyoxyethylene (n = 10) stearyl ether phosphoric acid esters; (3) alkali metal salts of sulfonic acid esters of aliphatic alcohols, such as alkali metal salts of lauryl sulfonic acid esters, alkali metal salts of oleyl sulfonic acid esters, alkali metal salts of stearyl sulfonic acid esters, and alkali metal salts of tetradecane sulfonic acid; (4) alkali metal salts of sulfuric acid esters of aliphatic alcohols, such as alkali metal salts of lauryl sulfuric acid esters, alkali metal salts of oleyl sulfuric acid esters, and alkali metal salts of stearyl sulfuric acid esters; (5) alkali metal salts of sulfuric acid esters in which at least one alkylene oxide selected from ethylene oxide and propylene oxide is added to aliphatic alcohols, such as alkali metal salts of polyoxyethylene (n = 3) lauryl ether sulfuric acid esters, alkali metal salts of polyoxyethylene (n = 5) lauryl ether sulfuric acid esters, alkali metal salts of polyoxyalkylene (n = 3, m = 3) lauryl ether sulfuric acid esters, alkali metal salts of polyoxyethylene (n = 3) oleyl ether sulfuric acid esters, and alkali metal salts of polyoxyethylene (n = 5) oleyl ether sulfuric acid esters; (6) alkali metal salts of sulfuric acid esters of fatty acids, such as alkali metal salts of sulfuric acid esters of fatty acids of castor oil, alkali metal salts of sulfuric acid esters of fatty acids of sesame oil, alkali metal salts of sulfuric acid esters of fatty acids of tall oil, alkali metal salts of sulfuric acid esters of fatty acids of soybean oil, alkali metal salts of sulfuric acid esters of fatty acids of rapeseed oil, alkali metal salts of sulfuric acid esters of fatty acids of palm oil, alkali metal salts of sulfuric acid esters of fatty acids of lard, alkali metal salts of sulfuric acid esters of fatty acids of beef tallow, and alkali metal salts of sulfuric acid esters of fatty acids of whale oil; (7) alkali metal salts of sulfuric acid esters of oils and fats, such as alkali metal salts of sulfuric acid esters of castor oil, alkali metal salts of sulfuric acid esters of sesame oil, alkali metal salts of sulfuric acid esters of tall oil, alkali metal salts of sulfuric acid esters of soybean oil, alkali metal salts of sulfuric acid esters of rapeseed oil, alkali metal salts of sulfuric acid esters of palm oil, alkali metal salts of sulfuric acid esters of lard, alkali metal salts of sulfuric acid esters of beef tallow, and alkali metal salts of sulfuric acid esters of whale oil; (8) alkali metal salts of fatty acids, such as alkali metal salts of lauric acid, alkali metal salts of oleic acid, and alkali metal salts of stearic acid; and (9) alkali metal salts of sulfosuccinic acid esters of aliphatic alcohols, such as alkali metal salts of dioctyl sulfosuccinic acid. The components may be used alone or in a combination of two or more kinds thereof.

[0032] The ratio among the contents of the fatty acid derivative, the fatty acids, the oils and fats, the polyhydric alcohol, and the anionic surfactant in the short fiber treatment agent of the present embodiment is not limited. It is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, and the anionic surfactant in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 98.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, the content of the polyhydric alcohol be 0.1 to 90 parts by mass, and the content of the anionic surfactant be 1 to 20 parts by mass. The effects of the present invention can be further

improved with this configuration.

[0033] The ratio among the contents of the fatty acid derivative, the fatty acids, the oils and fats, the polyhydric alcohol, the anionic surfactant, and the lubricant in the short fiber treatment agent of the present embodiment is not limited. It is preferable that when the total content of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, the anionic surfactant, and the lubricant in the short fiber treatment agent is taken as 100 parts by mass, the content of the fatty acid derivative be 5 to 97.89 parts by mass, the content of the at least one selected from the fatty acids and the oils and fats be 0.01 to 10 parts by mass, the content of the polyhydric alcohol be 0.1 to 90 parts by mass, the content of the anionic surfactant be 1 to 20 parts by mass, and the content of the lubricant be 1 to 20 parts by mass. The effects of the present invention can be further improved with this configuration.

[0034] The short fiber treatment agent of the present embodiment preferably further contains a nonionic surfactant other than the above-mentioned components as another component. Specific examples of nonionic surfactant other than the above-mentioned components include (1) polyoxyalkylene alkyl (or alkenyl) ethers obtained by addition reaction of an alkylene oxide to saturated or unsaturated aliphatic monohydric alcohols, such as polyoxyethylene (n = 10) lauryl ethers, polyoxyethylene (n = 20) stearyl ethers, polyoxyethylene (n = 30) oleyl ethers, polyoxyethylene (n = 10) alkyl (having 12 or 13 carbon atoms) ethers, and polyoxyalkylene (n = 10, m = 10) lauryl ethers; (2) polyoxyalkylene polyhydric alcohol ethers obtained by addition reaction of an alkylene oxide to aliphatic polyhydric alcohols, such as polyoxyethylene (n = 10) sorbitan monolaurate, polyoxyethylene (n = 20) sorbitan monooleate, polyoxyethylene (n = 20) sorbitan monostearate, and polyoxyethylene (n = 20) sorbitan tristearate; (3) polyoxyalkylene alkylphenol ethers obtained by addition reaction of an alkylene oxide to an alkylphenol, such as polyoxyethylene (n = 10) octylphenol ethers and polyoxyethylene (n = 10) nonylphenol ethers; and (4) polyoxyalkylene amino ethers obtained by addition reaction of an alkylene oxide to saturated or unsaturated aliphatic amines, such as polyoxyethylene (n = 5) octyl amino ethers, polyoxyethylene (n = 8) lauryl amino ethers, and polyoxyethylene (n = 20) stearyl amino ethers. The nonionic surfactants may be used alone or in a combination of two or more kinds thereof. The content of the nonionic surfactant is not limited.

[0035] Short fibers to which the short fiber treatment agent of the present embodiment is applied are generally called staple fibers, and include no long fiber generally called filament fiber. The length of the short fibers in the present invention is 100 mm or shorter and more preferably 51 mm or shorter. Examples of fibers include natural fibers, such as cotton fibers and cotton fibers treated by exposure; regenerated fibers, such as viscose rayon fibers, high-tenacity rayon fibers, super high-tenacity rayon fibers, high-wet-modulus rayon fibers, solvent-spun rayon fibers, polynosic fibers, cupra fibers, and acetate fibers; and synthetic fibers, such as polyolefin fibers, polyester fibers, polyamide fibers, acrylic fibers, polyvinyl chloride fibers, and composite fibers composed of two or more kinds of thermoplastic resins. Among the examples, viscose rayon fibers, high-tenacity rayon fibers, super high-tenacity rayon fibers, high-wet-modulus rayon fibers, and solvent-spun rayon fibers are preferable, and viscose rayon fibers are particularly preferable.

[0036] According to the first embodiment, the following effects can be obtained.

(1) When short fibers to which the claimed short fiber treatment agent is applied are hydroentangled, it is possible to curb bubble formation due to mixing of the short fiber treatment agent that has dropped from the short fibers into water, that is, inhibit foaming of water used for hydroentanglement. Thereby, operation efficiency can be improved in a step of manufacturing a nonwoven fabric.

(Second embodiment)

[0037] A second embodiment will now be described that embodies a short fiber according to the present invention. The short fiber of the present embodiment is a short fiber to which the short fiber treatment agent of the first embodiment is applied. As a method of applying the short fiber treatment agent, a known method such as an immersion method, a spray method, or a roller method may be applied. The step in which the short fiber treatment agent is applied is not particularly limited, and examples thereof include a step after a refining step, and a spinning step.

[0038] The above-mentioned short fibers can be adopted as short fibers to be treated with the short fiber treatment agent of the present embodiment.

[0039] The form of the short fiber treatment agent of the first embodiment when applied to the short fibers may be, for example, an organic solvent solution or an aqueous liquid. In a method of treating short fibers, it is preferable that the short fiber treatment agent of the first embodiment be diluted with water to obtain an aqueous liquid having a concentration of 0.5% to 20% by mass, and that the aqueous liquid be applied to short fibers such that the ratio of the short fiber treatment agent of the first embodiment which does not contain a solvent is 0.1% to 1% by mass relative to the short fibers.

(Third embodiment)

[0040] A third embodiment will now be described that embodies a method for manufacturing a spunlace nonwoven fabric according to the present invention.

[0041] A spunlace nonwoven fabric is manufactured by sequentially performing a web formation step (first step) and a hydroentanglement step (second step).

(Web formation step)

[0042] The web formation step is a step of carding short fibers to which the above-mentioned short fiber treatment agent is applied, and thereby manufacturing a web. The carding can be performed using a known carding machine. Examples thereof include a flat card, a combination card, and a roller card.

(Hydroentanglement step)

[0043] The hydroentanglement step is a step of entangling the web obtained in the web formation step through water jets. Fibers can be formed into a sheet shape when the web is subjected to highly pressurized water jets and thereby the fibers are entangled with each other due to the pressure of the water jets. A drying step or a winding step may be appropriately performed after performing the hydroentanglement step.

[0044] According to the second and third embodiments, the following effects can be obtained in addition to the effects of (1).

[0045] (2) Since it is possible to inhibit foaming of water used in hydroentanglement, the hydroentanglement can be suitably performed in the case of circulating water used in the hydroentanglement. Accordingly, texture of a spunlace nonwoven fabric can be favorable.

[0046] (3) It is possible to reduce unpleasant odor of a short fiber to which the short fiber treatment agent is applied can be reduced.

[0047] The first to third embodiments may be modified as follows. The first to third embodiments and the following modifications can be implemented in combination with each other within a technically consistent range.

- A component generally used in treatment agents such as an antioxidant or an ultraviolet absorbent may be further added to the treatment agent of the embodiments described above for maintaining quality of the treatment agent as long as the effects of the present invention are not impaired.

EXAMPLES

[0048] Examples will now be given below to described the features and effects of the present invention more specifically, but the present invention is not limited to these examples. In the following description of working examples and comparative examples, "part" means "part by mass," and "%" means "% by mass."

Experimental Part 1 (preparation of short fiber treatment agent)

(Example 1)

[0049] The following materials were used as raw materials for the short fiber treatment agent. A numerical value of each component indicates the content thereof in the short fiber treatment agent.

Fatty acid derivative: polyoxyethylene (n = 20) oleate (A-1) 20%

Oils and fats: beef tallow (B-1) 5%

Polyhydric alcohol: ethylene glycol (C-1) 70%

Lubricant: stearyl stearate (D-1) 2%

Anionic surfactant: potassium salts of lauryl phosphoric acid ester (E-1) 3%

900 parts of water was added to 100 parts of the short fiber treatment agent prepared such that the mixing ratios was as described above, the mixture was stirred at 50°C, and thereby an aqueous liquid containing 10% of the short fiber treatment agent was prepared.

(Examples 2 to 15 and Comparative Examples 1 to 6)

[0050] A short fiber treatment agent was prepared in the same procedure as in Example 1 except that materials and mixing ratios shown in Table 1 were adopted. In addition, an aqueous liquid containing 10% of a short fiber treatment agent was obtained by the same procedure as in Example 1. In Table 1, the type of each component used in the respective examples and the content (%) of each component in the treatment agent are shown in the column of "Fatty acid derivative," the column of "Fatty acids, or oils and fats," the column of "Polyhydric alcohol," the column of "Lubricant," the column of "Anionic surfactant," and the column of "Other."

Experimental Part 2 (applying short fiber treatment agent to viscose rayon fibers (short fibers))

[0051] The aqueous liquid of the short fiber treatment agent of each of the examples shown in Table 1 was further diluted, and thereby a 0.2% emulsion of the short fiber treatment agent was prepared. The emulsion was applied to viscose rayon fibers having a fineness of 1.3×10^{-4} g/m (1.2 deniers) and a fiber length of 38 mm by a spray lubrication method such that an amount attached (excluding a solvent) to the fibers was 0.2% by mass. Thereafter, humidity was controlled overnight in an atmosphere of $25^{\circ}\text{C} \times 40\%$ RH using a hot air dryer at 80°C , and thereby viscose rayon fibers to which the short fiber treatment agent was applied were obtained.

Experimental Part 3 (evaluation of short fiber treatment agent)

(Evaluation test)

[0052] A foaming property test and an unpleasant odor test were conducted using the viscose rayon fibers to which the short fiber treatment agents of Examples 1 to 15 and Comparative Examples 1 to 6 were applied. The procedure of each test is shown below. Table 1 shows test results in the column of "Foaming property test" and the column of "Unpleasant odor test."

(Foaming property test)

[0053] First, 20 g of the viscose rayon fibers was put into 150 g of water. The viscose rayon fibers were taken out after 15 minutes and squeezed using a hand juicer. 10 g of the squeezed liquid was put in a 25 ml graduated cylinder equipped with a stopper, shaken vigorously for 30 seconds, allowed to stand still for 30 seconds, and then shaken vigorously again for 30 seconds. After being allowed to stand still for 5 minutes, the height from the liquid surface to the top surface of foam was measured.

Evaluation criteria of foaming property test

[0054]

- ∞ (excellent): the height from the liquid surface to the top surface of foam was less than 1 mm.
- (good): the height from the liquid surface to the top surface of foam was 1 mm or more and less than 2 mm.
- × (poor): the height from the liquid surface to the top surface of foam was 2 mm or more.

(Unpleasant odor test)

[0055] 20 g of the viscose rayon fibers was put into 150 g of water. After it was sealed for 30 minutes, 10 testers each checked it for odor.

Evaluation criteria of unpleasant odor test

[0056]

- ∞ (excellent): 2 or fewer testers judged that there was odor.
- (good): 3 to 6 testers judged that there was odor.
- × (poor): 7 or more testers judged that there was odor.

Examples 9 to 15 are reference examples.

[0057]

Table 1

	Fatty acid derivative		Fatty acid, or oil or fat		Polyhydric alcohol		Lubricant		Anionic surfactant		Other		Foaming property test	Unpleasant odor test
	Type	Ratio (parts by mass)	Type	Ratio (parts by mass)	Type	Ratio (parts by mass)	Type	Ratio (parts by mass)	Type	Ratio (parts by mass)	Type	Ratio (parts by mass)		
Ex. 1	A-1	20	B-1	5	C-1	70	D-1	2	E-1	3			oo	oo
Ex. 2	A-2	10	B-2	5	C-2	5	D-2	9	E-2	1			oo	oo
	A-3	70												
Ex. 3	A-4	45	B-3	9	C-3	40	D-3	1	E-3	5			oo	oo
Ex. 4	A-5	50	B-4	0.5	C-4	19.5	D-4	15	E-4	15			oo	oo
Ex. 5	A-2	65	B-2	5	C-5	5	D-2	10					oo	oo
					C-6	15								
Ex. 6	A-6	20	B-5	5	C-7	70	D-5	5					oo	oo
Ex. 7	A-7	40	B-6	10	C-8	40	D-6	10					oo	oo
Ex. 8	A-2	9	B-1	21	C-2	2	D-7	15	E-1	4			oo	o
	A-8	40							E-5	9				
Ex. 9	A-6	80	B-6	5	C-5	5			E-3	10			o	o
Ex. 10	A-3	45.5	B-7	4	C-3	49.5			E-2	1			o	o
Ex. 11	A-7	80	B-2	2	C-5	10			E-2	5			o	o
			B-8	3										
Ex. 12	A-9	50	B-9	6	C-9	40			E-6	4			o	o
Ex. 13	A-6	90.8	B-14	0.05	C-2	0.15			E-3	9			o	o
Ex. 14	A-7	87	B-10	3	C-5	10							o	o
Ex. 15	A-8	30	B-11	9	C-10	61					F-1	40	o	o
Comp. Ex. 1	A-10	43					D-7	21	E-5	21	F-2	43	x	x
							D-8	15						
Comp. Ex. 2							D-9	60			F-3	60		
							D-10	20			F-4	240	x	x
							D-11	20						
Comp. Ex. 3	A-3	95	B-3	5									x	x
Comp. Ex. 4	A-2	25	B-12	4					E-2	20			x	x
	A-3	51												
Comp. Ex. 5	A-10	79			C-2	10	D-4	1	E-3	10			x	x
Comp. Ex. 6			B-13	1	C-1	64	D-8	15	E-3	20			x	x

[0058] In Table 1, the following symbols are used:

A-1: polyoxyethylene (n = 20) oleate;

- A-2: polyoxyethylene (n = 5) stearate;
- A-3: polyoxyethylene (n = 10) stearate;
- A-4: polyethylene glycol (molecular weight: 400) dilaurate;
- A-5: polyethylene glycol (molecular weight: 1,000) distearate;
- 5 A-6: a reaction product of a coconut fatty acid and 10 moles of ethylene oxide;
- A-7: polyethylene glycol (molecular weight: 600) dioleate;
- A-8: polyoxyethylene (n = 10) oleate;
- A-9: polyoxyethylene (n = 30) oleate;
- 10 A-10: polyethylene glycol (molecular weight: 400) monooleate;
- B-1: beef tallow;
- B-2: stearic acid;
- B-3: palmitic acid;
- B-4: coconut oil;
- B-5: palm oil;
- 15 B-6: behenic acid;
- B-7: hardened palm oil;
- B-8: hardened castor oil;
- B-9: castor oil;
- B-10: oleic acid;
- 20 B-11: lard;
- B-12: tall oil;
- B-13: lauric acid;
- B-14: coconut fatty acid;
- C-1: ethylene glycol;
- 25 C-2: polyethylene glycol (molecular weight: 400);
- C-3: polypropylene glycol (molecular weight: 600);
- C-4: propylene glycol;
- C-5: polyethylene glycol (molecular weight: 600);
- C-6: a reaction product of propylene glycol and an alkylene oxide (average molecular weight: 3,000);
- 30 C-7: polyethylene glycol (molecular weight: 2,000);
- C-8: sorbitan;
- C-9: sorbitol;
- C-10: glycerin;
- D-1: stearyl stearate;
- 35 D-2: mineral oil (viscosity: 500 seconds);
- D-3: dimethyl silicone;
- D-4: mineral oil (viscosity: 180 seconds);
- D-5: amino silicone;
- D-6: paraffin wax;
- 40 D-7: mineral oil (viscosity: 60 seconds);
- D-8: glycerin monooleate;
- D-9: mineral oil (viscosity: 80 seconds);
- D-10: sorbitan tristearate;
- D-11: sorbitan monostearate;
- 45 E-1: potassium salt of lauryl phosphoric acid;
- E-2: sodium salt of dioctyl sulfosuccinate;
- E-3: sodium salt of tetradecane sulfonate;
- E-4: sodium oleate;
- E-5: sodium salt of sulfuric acid ester of beef tallow;
- 50 E-6: potassium stearate;
- F-1: polyoxyethylene (n = 5) stearyl ether;
- F-2: polyoxyethylene (n = 20) sorbitan monostearate;
- F-3: polyoxyethylene (n = 20) sorbitan tristearate;
- F-4: polyoxyethylene (n = 20) sorbitan monostearate.

[0059] As can be clearly seen from the results in Table 1, the present invention succeeds in inhibiting foaming of water used for hydroentanglement. In addition, there is the effect in which it is possible to reduce unpleasant odor of a fiber to which the short fiber treatment agent is applied.

Claims

1. A short fiber treatment agent composition for fibers having a length of 100mm or shorter, comprising:

5 a fatty acid derivative;
 at least one selected from fatty acids and oils and fats;
 a polyhydric alcohol excluding polyoxyethylene polyoxypropylene glycol that includes 20 oxyethylene units and
 30 oxypropylene units, and
 at least one lubricant selected from a hydrocarbon compound, an ester excluding the oils and fats, and a silicone,
 wherein
 the fatty acid derivative is a compound obtained by adding an alkylene oxide, at a ratio of 0.1 to 30 mol, to 1
 mol of a fatty acid having 12 to 24 carbon atoms,
 the fatty acids have 12 to 24 carbon atoms,
 the oils and fats are at least one selected from vegetable oils, animal oils, and hardened oils thereof, and
 15 the polyhydric alcohol has 2 to 6 hydroxy groups in the molecule.

2. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 1,
 wherein assuming that the sum of the amounts of the fatty acid derivative, the at least one selected from the fatty
 acids and the oils and fats, and the polyhydric alcohol in the short fiber treatment agent composition is 100 parts by
 20 mass, the amount of the fatty acid derivative is 5 to 99.89 parts by mass, the amount of the at least one selected
 from the fatty acids and the oils and fats is 0.01 to 10 parts by mass, and the amount of the polyhydric alcohol is
 0.1 to 90 parts by mass.

3. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 1,
 25 the at least one lubricant is a silicone.

4. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 1 or
 3, wherein assuming that the sum of the amounts of the fatty acid derivative, the at least one selected from the fatty
 acids, vegetable oils, animal oils, and hardened oils thereof, the polyhydric alcohol, and the lubricant in the short
 30 fiber treatment agent composition is 100 parts by mass, the amount of the fatty acid derivative is 5 to 98.89 parts
 by mass, the amount of the at least one selected from the fatty acids, vegetable oils, animal oils, and hardened oils
 thereof is 0.01 to 10 parts by mass, the amount of the polyhydric alcohol is 0.1 to 90 parts by mass, and the amount
 of the lubricant is 1 to 20 parts by mass.

5. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 1,
 further comprising an anionic surfactant which is at least one selected from the group consisting of alkali metal salts
 of phosphoric acid esters of aliphatic alcohols, alkali metal salts of phosphoric acid esters in which at least one
 alkylene oxide selected from ethylene oxide and propylene oxide is added to aliphatic alcohols, alkali metal salts of
 sulfonic acid esters of aliphatic alcohols, alkali metal salts of sulfuric acid esters of aliphatic alcohols, alkali metal
 40 salts of sulfuric acid esters in which at least one alkylene oxide selected from ethylene oxide and propylene oxide
 is added to aliphatic alcohols, alkali metal salts of sulfuric acid esters of fatty acids, alkali metal salts of sulfuric acid
 esters of oils and fats, alkali metal salts of fatty acids, and alkali metal salts of sulfosuccinic acid esters of aliphatic
 alcohols.

6. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 5,
 wherein assuming that the sum of the amounts of the fatty acid derivative, the at least one selected from the fatty
 acids and the oils and fats, the polyhydric alcohol, and the anionic surfactant in the short fiber treatment agent
 composition is 100 parts by mass, the amount of the fatty acid derivative is 5 to 98.89 parts by mass, the amount
 of the at least one selected from the fatty acids and the oils and fats is 0.01 to 10 parts by mass, the amount of the
 50 polyhydric alcohol is 0.1 to 90 parts by mass, and the amount of the anionic surfactant is 1 to 20 parts by mass.

7. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 1 or
 3, further comprising an anionic surfactant which is at least one selected from the group consisting of alkali metal
 salts of phosphoric acid esters of aliphatic alcohols, alkali metal salts of phosphoric acid esters in which at least one
 alkylene oxide selected from ethylene oxide and propylene oxide is added to aliphatic alcohols, alkali metal salts of
 sulfonic acid esters of aliphatic alcohols, alkali metal salts of sulfuric acid esters of aliphatic alcohols, alkali metal
 55 salts of sulfuric acid esters in which at least one alkylene oxide selected from ethylene oxide and propylene oxide
 is added to aliphatic alcohols, alkali metal salts of sulfuric acid esters of fatty acids, alkali metal salts of sulfuric acid

esters of oils and fats, alkali metal salts of fatty acids, and alkali metal salts of sulfosuccinic acid esters of aliphatic alcohols.

8. The short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to claim 7, wherein assuming that the sum of the amounts of the fatty acid derivative, the at least one selected from the fatty acids and the oils and fats, the polyhydric alcohol, the anionic surfactant, and the lubricant in the short fiber treatment agent composition is 100 parts by mass, the amount of the fatty acid derivative is 5 to 97.89 parts by mass, the amount of the at least one selected from the fatty acids and the oils and fats is 0.01 to 10 parts by mass, the amount of the polyhydric alcohol is 0.1 to 90 parts by mass, the content of the anionic surfactant is 1 to 20 parts by mass, and the amount of the lubricant is 1 to 20 parts by mass.
9. Use of the short fiber treatment agent composition according to any one of claims 1 to 8, in the treatment of viscose rayon fibers having a length of 100mm or shorter.
10. A short fiber to which the short fiber treatment agent composition for fibers having a length of 100mm or shorter, according to any one of claims 1 to 8 is applied, wherein the short fiber treatment agent composition is applied to the surface of the short fiber and wherein the fiber has a length of 100mm or shorter.
11. A method for manufacturing a spunlace nonwoven fabric, the method comprising a first step and a second step, wherein

the first step is a step of carding fibers having a length of 100mm or shorter, to the surface of which the short fiber treatment agent composition according to any one of claims 1 to 8 is applied to manufacture a web, and the second step is a step of entangling the web obtained in the first step through water jets.

Patentansprüche

1. Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer, die
 - ein Fettsäurederivat,
 - mindestens einen aus Fettsäuren sowie Ölen und Fetten ausgewählten Bestandteil,
 - einen mehrwertigen Alkohol, außer Polyoxyethylen-Polyoxypropylenglykol, der 20 Oxyethyleneinheiten und 30 Oxypropyleneinheiten aufweist, und
 - mindestens ein aus einer Kohlenwasserstoffverbindung, einem Ester außer Öle und außer Fette und einem Silikon ausgewähltes Schmiermittel aufweist, wobei
 - das Fettsäurederivat eine Verbindung ist, die durch Zugabe eines Alkylenoxids im Verhältnis von 0,1 bis 30 Mol zu 1 Mol einer Fettsäure mit 12 bis 24 Kohlenstoffatomen erhalten wird,
 - die Fettsäuren 12 bis 24 Kohlenstoffatome haben,
 - die Öle und Fette mindestens ein aus pflanzlichen Ölen, tierischen Ölen und gehärteten Ölen davon ausgewählter Bestandteil sind und
 - der mehrwertige Alkohol 2 bis 6 Hydroxygruppen im Molekül aufweist.
2. Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 1, wobei unter der Vorgabe, dass die Summe der Mengen des Fettsäurederivats, des mindestens einen aus den Fettsäuren sowie den Ölen und Fetten ausgewählten Bestandteils und des mehrwertigen Alkohols in der Kurzfaserbehandlungsmittelzusammensetzung 100 Massenanteile beträgt, die Menge des Fettsäurederivats 5 bis 99,89 Massenanteile, die Menge des mindestens einen aus den Fettsäuren sowie den Ölen und Fetten ausgewählten Bestandteils 0,01 bis 10 Massenanteile und die Menge des mehrwertigen Alkohols 0,1 bis 90 Massenanteile beträgt.
3. Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 1, wobei das mindestens eine Schmiermittel ein Silikon ist.
4. Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 1 oder 3, wobei unter der Vorgabe, dass die Summe der Mengen des Fettsäurederivats, des mindestens einen aus den Fettsäuren, pflanzlichen Ölen, tierischen Ölen und gehärteten Ölen davon ausgewählten Bestandteils, des mehrwertigen Alkohols und des Schmiermittels in der Kurzfaserbehandlungsmittelzusammensetzung 100 Massenanteile beträgt, die Menge des Fettsäurederivats 5 bis 98,89 Massenanteile, die Menge des mindestens einen aus

den Fettsäuren, pflanzlichen Ölen, tierischen Ölen und gehärteten Ölen davon ausgewählten Bestandteils 0,01 bis 10 Massenanteile, die Menge des mehrwertigen Alkohols 0,1 bis 90 Massenanteile und die Menge des Schmiermittels 1 bis 20 Massenanteile beträgt.

- 5 **5.** Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 1, die weiterhin ein anionisches Tensid aufweist, das mindestens eines ausgewählt aus der Gruppe bestehend aus Alkalimetallsalzen von Phosphorsäureestern aliphatischer Alkohole, Alkalimetallsalzen von Phosphorsäureestern, bei denen mindestens ein Alkylenoxid ausgewählt aus Ethylenoxid und Propylenoxid zu aliphatischen Alkoholen hinzugefügt wird, Alkalimetallsalzen von Sulfonsäureestern aliphatischer Alkohole, Alkalimetallsalzen von Schwefelsäureestern aliphatischer Alkohole, Alkalimetallsalzen von Schwefelsäureestern, bei denen mindestens ein Alkylenoxid ausgewählt aus Ethylenoxid und Propylenoxid zu aliphatischen Alkoholen hinzugefügt wird, Alkalimetallsalzen von Schwefelsäureestern von Fettsäuren, Alkalimetallsalzen von Schwefelsäureestern von Ölen und Fetten, Alkalimetallsalzen von Fettsäuren und Alkalimetallsalzen von Sulfobernsteinsäureestern aliphatischer Alkohole ist.
- 10
- 15 **6.** Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 5, wobei unter der Vorgabe, dass die Summe der Mengen des Fettsäurederivats, des mindestens einen aus den Fettsäuren sowie den Ölen und Fetten ausgewählten Bestandteils, des mehrwertigen Alkohols und des anionischen Tensids in der Kurzfaserbehandlungsmittelzusammensetzung 100 Massenanteile beträgt, die Menge des Fettsäurederivats 5 bis 98,89 Massenanteile, die Menge des mindestens einen aus den Fettsäuren sowie den Ölen und Fetten ausgewählten Bestandteils 0,01 bis 10 Massenanteile, die Menge des mehrwertigen Alkohols 0,1 bis 90 Massenanteile und die Menge des anionischen Tensids 1 bis 20 Massenanteile beträgt.
- 20
- 25 **7.** Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 1 oder 3, die weiterhin ein anionisches Tensid aufweist, das mindestens eines ausgewählt aus der Gruppe bestehend aus Alkalimetallsalzen von Phosphorsäureestern aliphatischer Alkohole, Alkalimetallsalzen von Phosphorsäureestern, bei denen mindestens ein Alkylenoxid ausgewählt aus Ethylenoxid und Propylenoxid zu aliphatischen Alkoholen hinzugefügt wird, Alkalimetallsalzen von Sulfonsäureestern aliphatischer Alkohole, Alkalimetallsalzen von Schwefelsäureestern aliphatischer Alkohole, Alkalimetallsalzen von Schwefelsäureestern, bei denen mindestens ein Alkylenoxid ausgewählt aus Ethylenoxid und Propylenoxid zu aliphatischen Alkoholen hinzugefügt wird, Alkalimetallsalzen von Schwefelsäureestern von Fettsäuren, Alkalimetallsalzen von Schwefelsäureestern von Ölen und Fetten, Alkalimetallsalzen von Fettsäuren und Alkalimetallsalzen von Sulfobernsteinsäureestern aliphatischer Alkohole ist.
- 30
- 35 **8.** Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß Anspruch 7, wobei unter der Vorgabe, dass die Summe der Mengen des Fettsäurederivats, des mindestens einen aus den Fettsäuren sowie den Ölen und Fetten ausgewählten Bestandteils, des mehrwertigen Alkohols, des anionischen Tensids und des Schmiermittels in der Kurzfaserbehandlungsmittelzusammensetzung 100 Massenanteile beträgt, die Menge des Fettsäurederivats 5 bis 97,89 Massenanteile, die Menge des mindestens einen aus den Fettsäuren sowie den Ölen und Fetten ausgewählten Bestandteils 0,01 bis 10 Massenanteile, die Menge des mehrwertigen Alkohols 0,1 bis 90 Massenanteile, der Gehalt des anionischen Tensids 1 bis 20 Massenanteile und die Menge des Schmiermittels 1 bis 20 Massenanteile beträgt.
- 40
- 45 **9.** Verwendung der Kurzfaserbehandlungsmittelzusammensetzung gemäß einem der Ansprüche 1 bis 8 bei der Behandlung von Viskosefasern mit einer Länge von 100 mm oder kürzer.
- 50 **10.** Kurzfaser, auf die die Kurzfaserbehandlungsmittelzusammensetzung für Fasern mit einer Länge von 100 mm oder kürzer gemäß einem der Ansprüche 1 bis 8 aufgetragen wird, wobei die Kurzfaserbehandlungsmittelzusammensetzung auf die Oberfläche der Kurzfaser aufgetragen wird und wobei die Faser eine Länge von 100 mm oder kürzer hat.
- 55 **11.** Verfahren zur Herstellung eines Spunlace-Vliesstoffs, das einen ersten und einen zweiten Schritt aufweist, wobei
der erste Schritt ein Schritt ist, bei dem Fasern mit einer Länge von 100 mm oder kürzer, auf deren Oberfläche die Kurzfaserbehandlungsmittelzusammensetzung gemäß einem der Ansprüche 1 bis 8 aufgetragen wurde, kardiert werden, um einen Faserflor herzustellen, und
der zweite Schritt ein Schritt ist, bei dem der im ersten Schritt hergestellte Faserflor durch Wasserstrahlen verfilzt wird.

Revendications

1. Une composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, comprenant :

un dérivé d'acide gras ;
 au moins un élément choisi parmi les acides gras et les huiles et graisses ;
 un alcool polyhydrique excluant le polyoxyéthylène polyoxypropylène glycol qui comprend 20 unités oxyéthylène et 30 unités oxypropylène, et
 au moins un lubrifiant choisi parmi un composé hydrocarboné, un ester excluant les huiles et graisses, et une silicone,
 le dérivé d'acide gras étant un composé obtenu en ajoutant un oxyde d'alkylène, à un rapport de 0,1 à 30 moles, à 1 mole d'un acide gras ayant 12 à 24 atomes de carbone,
 les acides gras ayant 12 à 24 atomes de carbone,
 les huiles et graisses étant au moins une huile choisie parmi les huiles végétales, les huiles animales et les huiles durcies de celles-ci, et
 l'alcool polyhydrique ayant 2 à 6 groupes hydroxy dans la molécule.

2. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon la revendication 1, dans laquelle en supposant que la somme des quantités du dérivé d'acide gras, dudit au moins un, choisi, parmi les acides gras et les huiles et graisses, et de l'alcool polyhydrique dans la composition d'agent de traitement de fibres courtes soit de 100 parties en masse, la quantité du dérivé d'acide gras va de 5 à 99,89 parties en masse, la quantité dudit au moins un, choisi, parmi les acides gras et les huiles et graisses est de 0,01 à 10 parties en masse, et la quantité de l'alcool polyhydrique est de 0,1 à 90 parties en masse.

3. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon la revendication 1, dans laquelle ledit au moins un lubrifiant est un silicone.

4. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon la revendication 1 ou 3, dans laquelle en supposant que la somme des quantités du dérivé d'acide gras, dudit au moins un, choisi, parmi les acides gras, les huiles végétales, les huiles animales et les huiles durcies de celles-ci, l'alcool polyhydrique et le lubrifiant dans la composition d'agent de traitement de fibres courtes est de 100 parties en masse, la quantité du dérivé d'acide gras est de 5 à 98,89 parties en masse, la quantité d'au moins un choisi parmi les acides gras, les huiles végétales, les huiles animales et les huiles durcies de celles-ci est de 0,01 à 10 parties en masse, la quantité de l'alcool polyhydrique est de 0,1 à 90 parties en masse et la quantité du lubrifiant est de 1 à 20 parties en masse.

5. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon la revendication 1, comprenant en outre un tensioactif anionique qui est au moins un élément choisi dans le groupe constitué par des sels de métaux alcalins d'esters d'acide phosphorique d'alcools aliphatiques, des sels de métaux alcalins d'esters d'acide phosphorique dans lesquels au moins un oxyde d'alkylène choisi parmi l'oxyde d'éthylène et l'oxyde de propylène est ajouté à des alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfonique d'alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfurique d'alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfurique dans lesquels au moins un oxyde d'alkylène choisi parmi l'oxyde d'éthylène et l'oxyde de propylène est ajouté à des alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfurique d'acides gras, des sels de métaux alcalins d'esters d'acide sulfurique d'huiles et de graisses, des sels de métaux alcalins d'acides gras et des sels de métaux alcalins d'esters d'acide sulfosuccinique d'alcools aliphatiques.

6. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon la revendication 5, dans laquelle en supposant que la somme des quantités du dérivé d'acide gras, dudit au moins un, choisi, parmi les acides gras et les huiles et graisses, l'alcool polyhydrique et le tensioactif anionique dans la composition d'agent de traitement de fibres courtes est de 100 parties en masse, la quantité du dérivé d'acide gras est de 5 à 98,89 parties en masse, la quantité dudit au moins un, choisi, parmi les acides gras et les huiles et graisses est de 0,01 à 10 parties en masse, la quantité de l'alcool polyhydrique est de 0,1 à 90 parties en masse et la quantité du tensioactif anionique est de 1 à 20 parties en masse.

7. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins,

selon la revendication 1 ou 3, comprenant en outre un tensioactif anionique qui est au moins un, choisi, dans le groupe constitué par des sels de métaux alcalins d'esters d'acide phosphorique d'alcools aliphatiques, des sels de métaux alcalins d'esters d'acide phosphorique dans lesquels au moins un oxyde d'alkylène choisi parmi l'oxyde d'éthylène et l'oxyde de propylène est ajouté à des alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfonique d'alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfurique d'alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfurique dans lesquels au moins un oxyde d'alkylène choisi parmi l'oxyde d'éthylène et l'oxyde de propylène est ajouté à des alcools aliphatiques, des sels de métaux alcalins d'esters d'acide sulfurique d'acides gras, des sels de métaux alcalins d'esters d'acide sulfurique d'huiles et de graisses, des sels de métaux alcalins d'acides gras et des sels de métaux alcalins d'esters d'acide sulfosuccinique d'alcools aliphatiques.

8. La composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon la revendication 7, dans laquelle en supposant que la somme des quantités du dérivé d'acide gras, dudit au moins un, choisi, parmi les acides gras et les huiles et graisses, l'alcool polyhydrique, le tensioactif anionique et le lubrifiant dans la composition d'agent de traitement de fibres courtes est de 100 parties en masse, la quantité du dérivé d'acide gras est de 5 à 97,89 parties en masse, la quantité dudit au moins un, choisi, parmi les acides gras et les huiles et graisses est de 0,01 à 10 parties en masse, la quantité de l'alcool polyhydrique est de 0,1 à 90 parties en masse, la teneur en tensioactif anionique est de 1 à 20 parties en masse et la quantité du lubrifiant est de 1 à 20 parties en masse.

9. Utilisation de la composition d'agent de traitement de fibres courtes selon l'une quelconque des revendications 1 à 8, dans le traitement de fibres de rayonne viscosse ayant une longueur de 100 mm ou moins.

10. Une fibre courte à laquelle est appliquée la composition d'agent de traitement de fibres courtes pour des fibres ayant une longueur de 100 mm ou moins, selon l'une quelconque des revendications 1 à 8, la composition d'agent de traitement de fibres courtes étant appliquée sur la surface de la fibre courte et la fibre ayant une longueur de 100 mm ou moins.

11. Un procédé de fabrication d'une étoffe non-tissée hydroliée (« spunlace » en anglais), le procédé comprenant une première étape et une deuxième étape,

la première étape étant une étape de cardage de fibres ayant une longueur de 100 mm ou moins, à la surface desquelles la composition d'agent de traitement de fibres courtes selon l'une quelconque des revendications 1 à 8 est appliquée pour fabriquer une bande, et

la deuxième étape étant une étape d'enchevêtrement de la bande obtenue dans la première étape par des jets d'eau.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2018071013 B [0003]
- CN 106176291 [0003]
- EP 2712956 A [0003]
- JP 2015145545 B [0003]
- WO 2016104106 A [0004]
- JP 6096061 B [0004]