

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
1 August 2002 (01.08.2002)

PCT

(10) International Publication Number
WO 02/058844 A1(51) International Patent Classification⁷: B01J 31/02, C07C 45/29, 45/30, 51/16, 51/29, C08F 2/38, C07C 7/20, C08K 5/3492, C07D 211/94

(21) International Application Number: PCT/EP02/00340

(22) International Filing Date: 15 January 2002 (15.01.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
01810059.4 23 January 2001 (23.01.2001) EP

(71) Applicant (for all designated States except IT, US): CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).

(71) Applicant (for IT only): CIBA SPECIALTY CHEMICALS S.P.A. [IT/IT]; Via Pila, 6/3, Fraz. Pontecchio Marconi, I-40037 Sasso Marconi (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ZEDDA, Alessandro [IT/CH]; Klybeckstrasse 79, CH-4057 Basel (CH). SALA, Massimiliano [IT/IT]; Via Einstein, 136, I-41100 Modena (IT). SCHNEIDER, Armin [DE/DE]; Lehenerstrasse 59, 79106 Freiburg (DE).


(74) Common Representative: CIBA SPECIALTY CHEMICALS HOLDING INC.; Patentabteilung, Klybeckstrasse 141, CH-4057 Basel (CH).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: STABLE FREE NITROXYL RADICALS AS OXIDATION CATALYSTS AND PROCESS FOR OXIDATION



WO 02/058844 A1

(57) Abstract: The instant invention relates to stable free nitroxyl radicals of formula (I) at least one of the substituents R is -O- and the others are hydrogen or OH; X is -NR₁R₂, wherein R₁ and R₂ are independently hydrogen, C₁-C₁₈alkyl or together with the nitrogen atom to which they are bound from a 5 or 6 membered ring which may be further interrupted by an O atom. Further subjects of the invention are an oxidation process for alcohols to aldehydes or ketones or to carboxylic acids in the presence of a compound of formula (I) and the use of stable free nitroxyl radicals of formula (I) as oxidation catalysts.



European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

Published:

— *with international search report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Stable Free Nitroxyl Radicals as Oxidation Catalysts and Process for Oxidation

The instant invention relates to stable free nitroxyl radicals. Stable free nitroxyl radicals are useful for a variety of industrial applications, such as for example as stabilizers to prevent vinyl aromatic monomers from premature polymerization during distillation or purification, as polymerization regulators in controlled radical polymerization processes and as oxidation catalysts in heterogeneous and homogenous oxidation reactions. They are particularly useful as catalysts for the selective oxidation of alcohols to aldehydes or ketones or to carboxylic acids using an alkali hypohalite as oxidizing agent. Consequently an oxidation process and the use of these stable free nitroxyl radicals as oxidation catalysts are also subjects of the invention.

Selectivity is of primary importance in oxidation processes. Further functional groups present in the molecule, such as, for example, double bonds, should generally not be affected under the conditions chosen. Often, the targeted oxidation of secondary alongside primary alcohol functions or *vice versa* is desired, without the respective other function being affected. In the synthesis of aldehydes from primary alcohols, carboxylic acids are often formed as by-products of the oxidation reaction (over-oxidation), and the oxidation of 1,2-diols or α -hydroxyketones is frequently accompanied by C-C cleavage reactions.

It is known that primary and secondary alcohols can be converted into the corresponding carbonyl compounds using aqueous sodium hypochlorite solution in the presence of catalytic amounts of organic nitroxyl radicals (A. E. J. de Nooy, A. C. Besemer, H. van Bekkum, *Synthesis*, 1996, 1153).

It is also known, that alcohols can be oxidized by Cu(I) and oxygen in the presence of a nitroxyl radical (2,2,6,6-tetramethylpiperidin-1-oxyl, TEMPO). This is for example described by Semmelhack, M. F.; Schmid, Christopher R.; Cortes, David A.; Chou, Chuen S. Oxidation of alcohols to aldehydes with oxygen and cupric ion, mediated by nitrosonium ion in J. Am. Chem. Soc. (1984), 106(11), 3374-6.

Hitherto such reactions - especially when 2,2,6,6-tetramethylpiperidin-1-oxyl (TEMPO) has been used - have predominantly been carried out in homogeneous phase. The reactions were carried out either stoichiometrically or catalytically in respect of TEMPO or the oxidation


- 2 -

product resulting therefrom. The working up of the reaction products in such processes often proves to be awkward and involved, since a great deal of effort is required to remove the catalyst and its attendant products.

It has now, surprisingly, been found that specific cyclic oligomeric stable free nitroxyl radicals are ideal catalysts in homogenous and heterogeneous oxidation reactions, which can easily be removed from the reaction products.

Furthermore the instant compounds have high catalytic activity and excellent selectivity.


One subject of the invention is therefore a compound of formula (I)



at least one of the substituents R is $-O\bullet$ and the others are hydrogen or OH;
 X is $-NR_1R_2$, wherein R_1 and R_2 are independently hydrogen, C_1-C_{18} alkyl or together with the nitrogen atom to which they are bound form a 5 or 6 membered ring which may be further interrupted by an O atom;
 HY is an organic or inorganic acid; and
 n is 0 or a number from 1-4.

- 3 -

Preferably X is a structural element of formulae



Most preferably X is of formula (II).

Preferred is a compound of formula (I) wherein at least two of the substituents R are -O•, more preferably 50 to 100% of the substituents R are -O•.

Preferably HY is selected from the group consisting of a halogen containing inorganic protonic acid, a phosphorous containing inorganic acid, a sulfur containing inorganic acid, a C₁-C₄alkyl carboxylic acid, or a perfluor C₁-C₄alkyl carboxylic acid or an aromatic carboxylic acid. More preferably HY is HCl, HClO₄, HBr, HPF₆, H₃PO₄, H₂SO₄, CF₃COOH, CH₃COOH, HCOOH or benzoic acid.

Particularly preferred compounds are those wherein n is 0.

The compounds may be prepared from the corresponding amine precursors (R is H) which are for example described in US 4,442,250. When X is of formula (II), the amine precursor is a commercial product, Chimassorb® 966, sold by Ciba Specialty Chemicals.

The oxidation may be carried out in analogy to the oxidation of 4-hydroxy-2,2,6,6-tetramethylpiperidine described in US 5,654,434 with hydrogen peroxide. Another also suitable oxidation process is described in WO 00/40550 using peracetic acid.

As described before the oxidation must not necessarily be carried out until all piperidine nitrogen atoms are oxidized. It can be stopped at many stages before, thus leading to a product mixture which contains NH, NOH and NO• moieties.

A subject of the invention is therefore a process for the selective oxidation of alcohols to ketones or to aldehydes in organic solvents by means of an oxidizing agent, which

- 4 -

comprises carrying out the oxidation in the presence of a homogenous or heterogeneous oxidation catalyst of formula (I).

A further subject of the invention is a process for the selective oxidation of alcohols to ketones or to carboxylic acids in aqueous solvents by means of an oxidizing agent, which comprises carrying out the oxidation in the presence of a homogenous or heterogeneous oxidation catalyst of formula (I).

It is one of the advantages that the compound of formula (I) can be protonated by inorganic acids and recovered from organic solvents by washing out with water.

Examples for oxidation agents are oxygen containing organic or inorganic compounds.

Typical are organic peracids, such as peracetic acid, H_2O_2 , hypohalites, halites, halides and oxygen itself or combinations of them.

Preferred is a process for the selective oxidation of alcohols to ketones or to aldehydes or of alcohols to carboxylic acids by means of peracetic acid, H_2O_2 , hypohalites, halites, halides and oxygen itself or combinations of them, under neutral or alkaline conditions or metal ions like Cu(I), Cu(II), Ru (II), Co(II), Mn(II) and mixtures thereof and oxygen as oxidizing agent, which comprises carrying out the oxidation in the presence of a homogenous or heterogeneous oxidation catalyst of formula (I).

The oxidation catalyst may also be a mixture of compounds of formula (I).

Preferably the oxidation catalyst is added in an amount of from 0.1 to 20 %, more preferably from 0.5% to 10% and most preferably from 0.5 to 5%, by weight, based on the alcohol used.

Generally, a process which comprises carrying out the oxidation by means of an alkali hypohalite under neutral or alkaline conditions is preferred.

Preference is given to a process that uses as the alkali hypohalite LiOCl, NaOCl, KCl, LiOBr, NaOBr or KOBr.

LiOCl, NaOCl and KCl are especially preferred, NaOCl being more especially preferred.

- 5 -

The hypohalite, is preferably added in the form of an aqueous solution to the alcohol to be oxidized. The concentration may vary within a wide range and is preferably from 5 % to 20 % by weight, especially from 10 to 15 % by weight, of active chlorine based on the alcohol to be oxidized.

Together with the oxidizing agent, the aqueous solution can be rendered neutral or alkaline by means of a buffer. Preferred buffers are aqueous solutions of alkali or alkaline earth hydroxides, alkali or alkaline earth carbonates and the corresponding hydrogen carbonates and alkali or alkaline earth phosphates and the corresponding hydrogen and dihydrogen phosphates.

Alkali hydrogen carbonates are especially preferred, sodium hydrogen carbonate being more especially preferred.


Preferably the process is carried out at a temperature of less than 30°C, more preferably at a temperature between 5° C and 20° C.

The pH value of the aqueous oxidation solution after the addition of the desired buffer is in the range from 7 to 12, especially in the range from 8 to 11 and more especially in the range from 8 to 10.

The alcohol to be oxidized may be a monoalcohol, diol or a polyol, monomeric or polymeric like starch or pulp, water soluble or water insoluble or molecules containing other functional groups besides hydroxy.

In the case of liquid alcohols, the reaction can be carried out without the addition of further solvents, but it can be advantageous to carry out the oxidation in a higher dilution.

The compounds of formula (I) may also be used as polymerization regulators in controlled free radical polymerization, as for example described in US 5,322,912, as polymerization inhibitors during distillation or purification of vinyl aromatic monomers or as flame retardants.

Preparation ExamplesExample 1

R= H, O° at least one is O°

In a 500 ml three necked flask 50 gr of CHIMASSORB® 966, toluene 250 ml, and 42 g of potassium carbonate were added. The heterogeneous mixture was cooled at 5-10°C and with vigorous stirring 72.5 g of a solution of peracetic acid (35%) in acetic acid was added slowly over about 1 h. The reaction mixture was allowed to stand for 2 h at 5-10°C and 10 g of potassium carbonate were added; after that the temperature was spontaneously allowed to rise to 25°C and the reaction was continued for additional 2 h at 25-30°C; after that the temperature was increased until to 50°C and maintained for 1 h. The mixture was then concentrated under reduced pressure and the crude product was washed with water and dried under vacuum. 44 g of the desired rose-coloured product was obtained.

In order to increase the purity of the nitroxyl product, the crystallization of unreacted CHIMASSORB ® 966 has been repeated four times in dichloromethane. The organic layer has then concentrated and dried under vacuum; obtaining a rose coloured solid having the following analytical data:

Melting range: 267 - 270 °C

Nitroxyl Yield by ESR: 95%

- 7 -


Example 2

In a flask 1 g of the product from example 1 was added to 100 g of a 37% solution of hydrochloric acid in water. The mixture was stirred for 8 hours at room temperature, until a homogeneous yellow-coloured solution was obtained. The water was evaporated and the remaining salt was dried under vacuum.

Examples for the use as catalyst in oxidation reactions

Example A

Use as homogeneous catalyst for alcohol oxidation in organic solvents



In a flask 0.072 g (0.05 mmol) of the product from example 1, 2.5 g (19.2 mmol) of 2-octanol and 10 ml of dichloromethane and 2.8 gr of KHCO₃ (20% sol.) were added; the heterogeneous mixture was cooled to 10-15°C then was dropped 13.8 g of an aqueous solution of NaOCl (10.5%). After 3 hours the crude organic layer was analyzed using GC: 98.6 % of 2-octanone was obtained as desired product.


Example B

Recovery of the catalyst

The organic layer of the reaction mixture in Example A was separated from the aqueous phase and stirred with 10 ml of concentrated HCl (37% in water). After 30 minutes the colorless organic layer was separated from the slightly yellow colored aqueous phase. The water was evaporated and the separated salt of the catalyst was dried under vacuum.

Example C

Use as heterogeneous catalyst for alcohol oxidation in organic solvents




- 8 -

In a flask 0.072 g (0.05 mmol) of the product from example 1, 2.5 g (19.2 mmol) of 2-octanol, 10 ml of toluene and 2.8 gr of KHCO₃ (20% sol.) were added; the heterogeneous mixture was cooled to 10-15°C then were added 13.2 g of an aqueous solution of NaOCl (10.5%). After 2 hours the crude organic layer was analyzed using GC and ¹H- ¹³C-NMR and 100% of 2-octanone was obtained as desired product. The catalyst was recovered by filtration of the crude reaction mixture.

Example D


Use as heterogeneous catalyst for the selective oxidation of primary alcohols in organic solvents



In a flask 0.06 g (0.042 mmol) of the product from example 1, 2.5 g (17.1 mmol) of 2-ethyl-1,3-hexane-diol and 10 ml of toluene were added; the heterogeneous mixture was cooled to 10-15°C then was dropped 9.8 g of an aqueous solution of NaOCl (13%) maintaining the pH between 8.5-9.5 using a water solution of NaHCO₃. After 2 hours the crude organic layer was analyzed using GC and ¹H- ¹³C-NMR and 77% of 2-ethyl, 3-hydroxy-hexanal was obtained as desired product. The catalyst was recovered by filtration of the crude reaction mixture.

Example E

Use as heterogeneous catalyst for the oxidation of alcohols in water




- 9 -

In a flask 0.02 g (0.014 mmol) of the product from example 1, 0.195 g (1.0 mmol) of methyl- α -D-glucopyranoside and 10 ml of water were added; the mixture was kept at room temperature then was dropped 8 ml of an aqueous solution of NaOCl (0.5M) maintaining the pH at 9.5 using a 0.12 M solution of NaOH. After 24 hours the crude organic layer was analyzed using HPLC. 96% of the carboxy acid was obtained as desired product. The catalyst was recovered by filtration of the crude reaction mixture.

Example E


Use as homogeneous catalyst for the oxidation of alcohols in water



In a flask 0.30 g (0.2 mmol) of the product from Example 2, 2.5 g (20.8 mmol) of diethyleneglycolmonomethylether and 10 ml of water were added; the mixture was cooled to 10-15°C then was dropped 48 g of an aqueous solution of NaOCl (13%) maintaining the pH between 6-7 using a water solution of KH₂PO₄. After 4 hours the crude solution was analyzed using GC and ¹H- and ¹³C-NMR. 95% of the carboxy acid was obtained as desired product. The catalyst was recovered by precipitation at pH > 8 and filtration of the reaction mixture.

Example F


Use as catalyst for the oxidation of alcohols in absence of solvent



In a flask 125 μ l (0.8 mmol) of the 2-octanol, 3.2 mg (8 μ mol) of the product from example I and 2.86 ml NaOCl-solution (0.35M; 1.0 mmol; pH 9.1 with KHCO₃) were added; the mixture was maintained at room temperature under vigorously stirring. After one hour the crude organic layer was analyzed using GC: 100 % of 2-octanone was obtained as desired product. The catalyst was recovered by filtration of the crude reaction mixture.


Claims

1. A compound of formula (I)



at least one of the substituents R is -O• and the others are hydrogen or OH;
X is -NR₁R₂, wherein R₁ and R₂ are independently hydrogen, C₁-C₁₈alkyl or together with the nitrogen atom to which they are bound form a 5 or 6 membered ring which may be further interrupted by an O atom;
HY is an organic or inorganic acid; and
n is 0 or a number from 1-4.

2. A compound according to claim 1 wherein X is a structural element of formulae



- 11 -

3. A compound according to claim 1 wherein n is 0 and at least two of the substituents R are -O•.
4. A process for the selective oxidation of alcohols to ketones or to aldehydes or of alcohols to carboxylic acids by means of an oxidizing agent, which comprises carrying out the oxidation in the presence of a homogenous or heterogeneous oxidation catalyst of formula (I).
5. A process for the selective oxidation of alcohols to ketones or to aldehydes or of alcohols to carboxylic acids according to claim 4 by means of peracetic acid, H₂O₂, hypohalites, halites, halides and oxygen itself or combinations of them, under neutral or alkaline conditions or metal ions like Cu(I), Cu(II), Ru (II), Co(II), Mn(II) and mixtures thereof and oxygen as oxidizing agent,
which comprises carrying out the oxidation in the presence of a homogenous or heterogeneous oxidation catalyst of formula (I).
6. A process according to claim 5, which comprises adding the oxidation catalyst in an amount of from 0.1 to 20 % by weight, based on the alcohol used.
7. A process according to claim 5, which comprises carrying out the oxidation by means of an alkali hypohalite selected from LiOCl, NaOCl, KOCl, LiOBr, NaOBr or KOBr under neutral or alkaline conditions.
8. A process according to claim 5, which comprises carrying out the reaction at a temperature of less than 30°C and at a pH of between 7 and 12.
9. The use of a compound of formula (I) as catalyst for the selective oxidation of alcohols to ketones or aldehydes or to carboxylic acids.
10. The use of a compound of formula (I) as polymerization regulator in controlled free radical polymerization, as polymerization inhibitor during distillation or purification of vinyl aromatic monomers or as flame retardant.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 02/00340

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J31/02 C07C45/29 C07C45/30 C07C51/16 C07C51/29
C08F2/38 C07C7/20 C08K5/3492 C07D211/94

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J C07C C08F C08K C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 01 92228 A (KIRNER HANS JUERG ;SCHAAF PAUL ADRIAAN V D (CH); SCHWARZENBACH FRA) 6 December 2001 (2001-12-06) page 25; claims ---	1-3, 10
A	DULOG L ET AL: "A 2 5-CYLOTRIPHOSPHAZENE WITH NITROXYL GROUPS AS MODEL FOR A PARAMAGNETIC POLY(ORGANO-2 5-PHOSPHAZENE)" MAKROMOLEKULARE CHEMIE, MACROMOLECULAR CHEMISTRY AND PHYSICS, HUTHIG UND WEPF VERLAG, BASEL, CH, vol. 189, no. 11, 1 November 1988 (1988-11-01), pages 2611-2615, XP000020438 ISSN: 0025-116X the whole document ---	1-3 -/-



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

- *&* document member of the same patent family

Date of the actual completion of the international search

17 May 2002

Date of mailing of the international search report

10/06/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Goebel, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/00340

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	"Chimassorb(TM) 966 - Sterically Hindered Amine Light Stabilizer" INTERNET, 'Online! XP002199387 Retrieved from the Internet: <URL: http://www.cibasc.com/adservices/doc.asp?t=tds&a=CHIMASSORB+966&b=PA%5FPlastics&c=ZZ&.pdf > 'retrieved on 2002-05-16! Technical information sheet, Ciba Specialty Chemicals the whole document ----	1-3,10
A	US 4 442 250 A (CANTATORE GIUSEPPE) 10 April 1984 (1984-04-10) cited in the application examples 2-5,7-9 ----	1-3,10
A	CONNOLLY T J ET AL: "Photochemical Synthesis of TEMPO-capped Initiators for @?Living@? Free Radical Polymerization" TETRAHEDRON LETTERS, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL, vol. 37, no. 28, 8 July 1996 (1996-07-08), pages 4919-4922, XP004029548 ISSN: 0040-4039 the whole document ----	1,10
A	US 5 322 912 A (GEORGES MICHAEL K ET AL) 21 June 1994 (1994-06-21) cited in the application column 7, line 1 -column 8, line 56; claims 1,10 ----	1,10
A	NOOY DE A E J ET AL: "ON THE USE OF STABLE ORGANIC NITROXYL RADICALS FOR THE OXIDATION OF PRIMARY AND SECONDARY ALCOHOLS" SYNTHESIS, GEORG THIEME VERLAG. STUTTGART, DE, 1 October 1996 (1996-10-01), pages 1153-1174, XP002072173 ISSN: 0039-7881 cited in the application the whole document ----	1,4-9
A	SEMMLER M F ET AL: "Oxidation of alcohols to aldehydes with oxygen and cupric ion, mediated by nitrosonium ion" JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, AMERICAN CHEMICAL SOCIETY, WASHINGTON, DC, US, vol. 106, no. 11, 1984, pages 3374-3376, XP002114880 ISSN: 0002-7863 cited in the application the whole document ----	1,4-9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No	
PCT/EP 02/00340	

Patent document cited in search report	Publication date		Patent family member(s)	Publication date
WO 0192228	A 06-12-2001	AU WO	6745201 A 0192228 A2	11-12-2001 06-12-2001
US 4442250	A 10-04-1984	IT DE GB JP JP JP	1195277 B 3236070 A1 2107707 A ,B 1728499 C 4011548 B 58072585 A	12-10-1988 14-04-1983 05-05-1983 19-01-1993 28-02-1992 30-04-1983
US 5322912	A 21-06-1994	AU BR CA CN DE DE EP ES JP JP KR MX WO US US	5295593 A 9305751 A 2126670 A1 1087349 A ,B 69329848 D1 69329848 T2 0621878 A1 2153388 T3 3260023 B2 6199916 A 260274 B1 9307085 A1 9411412 A1 5401804 A 5549998 A	08-06-1994 28-01-1997 26-05-1994 01-06-1994 15-02-2001 26-04-2001 02-11-1994 01-03-2001 25-02-2002 19-07-1994 01-07-2000 30-06-1994 26-05-1994 28-03-1995 27-08-1996