



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2242551 C 2005/10/11

(11)(21) **2 242 551**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 1996/12/18
(87) Date publication PCT/PCT Publication Date: 1997/07/17
(45) Date de délivrance/Issue Date: 2005/10/11
(85) Entrée phase nationale/National Entry: 1998/07/08
(86) N° demande PCT/PCT Application No.: GB 1996/003120
(87) N° publication PCT/PCT Publication No.: 1997/025476
(30) Priorité/Priority: 1996/01/12 (9600686.1) GB

(51) Cl.Int.⁷/Int.Cl.⁷ D21H 21/40, D21H 13/16, D21H 15/10

(72) Inventeurs/Inventors:
HOWLAND, PAUL, GB;
FOULKES, JONATHAN PAUL, GB

(73) Propriétaire/Owner:
PORTALS LIMITED, GB

(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : PAPIER INFALSIFIABLE
(54) Title: SECURITY PAPER

(57) **Abrégé/Abstract:**

The invention relates to security paper and in particular to a method for the manufacture of security paper which is provided with high-quality watermarks. In particular such a method comprises forming a papermaking suspension comprising cellulosic fibres and polyvinyl alcohol fibres, which polyvinyl alcohol fibres are soluble in water at temperatures of from 95° to 100 °C, dewatering the papermaking suspension through an embossed wire mesh or other embossed means, wherein the embossing creates a profile of peaks and troughs corresponding to the light and dark areas of the watermark, and the formed paper after dewatering with the watermark feature is thereafter dried to provide the resulting security paper.



PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21H 13/16, 15/10, 21/40	A1	(11) International Publication Number: WO 97/25476 (43) International Publication Date: 17 July 1997 (17.07.97)
(21) International Application Number: PCT/GB96/03120 (22) International Filing Date: 18 December 1996 (18.12.96) (30) Priority Data: 9600686.1 12 January 1996 (12.01.96) GB (71) Applicant (for all designated States except US): PORTALS LIMITED [GB/GB]; 6 Agar Street, London WC2N 4DE (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): HOWLAND, Paul [GB/GB]; 71 Springfield Close, Andover, Hampshire SP10 2QR (GB). FOULKES, Jonathan, Paul [GB/GB]; 9 Weyhill Gardens, Weyhill, Andover, Hampshire P11 0QS (GB). (74) Agent: BOULT WADE TENNANT; 27 Furnival Street, London EC4A 1PQ (GB).		(81) Designated States: AU, BG, BR, CA, CN, CZ, HU, JP, KP, KR, KZ, LK, MX, PL, RO, RU, SI, TR, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: SECURITY PAPER (57) Abstract The invention relates to security paper and in particular to a method for the manufacture of security paper which is provided with high-quality watermarks. In particular such a method comprises forming a papermaking suspension comprising cellulosic fibres and polyvinyl alcohol fibres, which polyvinyl alcohol fibres are soluble in water at temperatures of from 95° to 100 °C, dewatering the papermaking suspension through an embossed wire mesh or other embossed means, wherein the embossing creates a profile of peaks and troughs corresponding to the light and dark areas of the watermark, and the formed paper after dewatering with the watermark feature is thereafter dried to provide the resulting security paper.		

- 1 -

Security Paper

The invention relates to security paper and in particular to a method for the manufacture of security paper which are provided with high-quality watermarks.

It is well-known to those skilled in the art of papermaking that the tear strength of paper can be increased by the use of relatively long synthetic fibres. Cotton fibres used in the manufacture of security paper such as banknote paper are typically 1mm long. Tear-enhancing synthetic fibres are however typically in the region of 3 to 5mm long. It is further well-known in the papermaking art that the doublefold and tensile strength properties are generally also improved by the addition of synthetic fibres, but only if such fibres can be effectively bonded into the surrounding matrix of cotton fibres. Bonding of the appropriate type has been achieved in the past by three techniques:-

1. One technique is to use a fibre which is capable of hydrogen bonding such as viscose or polyvinyl alcohol. This technique is of limited value because the surface area of synthetic fibres is generally rather low compared to that of natural fibres with the consequence that the hydrogen bonding forces with individual synthetic fibres are proportionately less than for a cellulosic fibre. This reduction in bonding forces is only partially compensated by using fibres of greater length than cellulosic or other natural fibres.

- 2 -

2. Use has been made to impregnate a substrate with a strong bonding agent such as polyvinyl alcohol or gelatin. In practice it is rather difficult to make this method work effectively without resorting to either solvent-based systems and/or hot calendaring, neither of which are desirable due to their high cost. In the case of solvent-based systems, environmental considerations also mitigate against this approach.

10

3. Use has also been made of binder fibre incorporated with a synthetic reinforcing fibre. The binding fibre must be capable of either melting or dissolving during the drying process thereby serving to bond the synthetic and natural components of the fibre substrate.

15

Dutch Patent publication No.9301835 discloses a procedure for manufacturing paper for security applications and in addition to cellulose fibres, uses insoluble polyvinyl alcohol fibres, or a quantity of soluble and insoluble polyvinyl alcohol fibres. The use of the insoluble polyvinyl alcohol fibres improves the strength and stiffness of the paper compared with paper containing only cellulose fibres. In comparison with paper using other synthetic fibres such as polyamide or polyethylene fibres, the paper in accordance with this patent publication exhibits better stiffness and definition of a watermark. The soluble polyvinyl alcohol fibres which may be used in accordance with the disclosure are those which dissolve in water at a temperature 60°C or higher and during the dissolving the soluble fibres disappear. The molecules of polyvinyl alcohol act as a binding

25

30

- 3 -

agent and may provide a surface effect such that no normal surface treatment is required in order to provide a good print performance. The specification as a whole makes it clear that reasonable watermark quality is achieved even though a synthetic fibre is used, namely the insoluble polyvinyl alcohol fibres. In contrast to the invention disclosed in Dutch patent publication No.9301835 this present invention is concerned with obtaining improved strength relative to security paper made from cellulosic fibres alone and also improved watermark quality relative to other types of insoluble PVOH fibre by the use of a certain amount of polyvinyl alcohol fibres which have the ability to dissolve at temperatures of 95°C to 100°C.

The mould made panel watermark is one of the most critical and important security features used in bank notes to deter forgery. This is clearly illustrated by the almost universal use of such watermarks throughout the world's currencies. It is critical to the counterfeit deterrent value of a watermark that it be of the highest quality.

Judging the quality of a watermark is essentially a subjective issue. However those skilled in the art of producing mould made panel watermarks, referred to as shadow watermarks in Dutch patent application 9310835, are familiar with several distinct quality criteria. A high quality watermark is distinguished by three key features:

First, it should be sharply defined; that is to say, the image should not be woolly or smudged.

- 4 -

Second, it should be highly contrasted; that is to say, there should be a marked difference between the light and dark areas when viewed in transmitted light. The light areas, known as highlights should be much lighter than the non-watermarked area. The dark areas should be distinctly darker than the surrounding non-watermarked area.

Third, in order to present the watermark to best effect and to ensure consistent reproducibility of its image the background formation of the paper (non-watermarked area) should be uniform.

Of all the above qualities, the dark area contrast is the easiest to quantify. This can be done by estimating the quantity of fibre in the higher grammage areas of the watermark in comparison to the non-watermarked area.

The above-mentioned Dutch application does not describe the criteria used for judging watermark quality. Furthermore, it does not state which of the subjective aspects of watermark quality are used to make judgements about the watermark quality of the paper containing insoluble PVOH fibres and that containing other synthetic fibres or only cotton fibre.

The traditional approach to the use of synthetic fibres in papermaking leads one skilled in the art to choose a fibre which has maximum hydrogen bonding, maximum length consistent with paper formation and an optimal chemical bonding system. It should also be understood that the tear-strength in particular is a

- 5 -

function primarily of fibre strength and the double-fold property is a function of both fibre strength and bonding strength.

5 In the production of security paper such as banknote paper, it is important to maximise the two important physical properties, namely tear-strength and double-fold values. The teaching in the art is that in order to achieve good results in respect of these two physical properties it is appropriate to use a reinforcing fibre which will be undamaged either by heat or water in order to maintain maximum fibre strength. It has now been surprisingly discovered that the use of polyvinyl alcohol fibres which are soluble in the papermaking process at least to some extent at temperatures between 95° and 100°C, but which nevertheless maintain strength properties throughout the entire papermaking process including the drying stages. In particular it has been discovered that security paper made in accordance with the method of this invention is not weakened during the drying stages during which the fibres are surrounded by water at a temperature approaching 100°C prior to the evaporation of the water.

25 Accordingly, the present invention provides a method for the manufacture of security paper, such as banknote paper, which method comprises forming a papermaking suspension comprising cellulosic fibres and polyvinyl alcohol fibres, which polyvinyl alcohol fibres are soluble in water at temperatures of from 95° to 100°C, dewatering the papermaking suspension through an embossed wire mesh or other embossed means, wherein the embossing creates a profile of peaks and

- 6 -

troughs corresponding to the light and dark areas of the watermark, and the formed paper after dewatering with the watermark feature is thereafter dried to provide the resulting security paper.

5

The cellulosic fibres may comprise at least 50% of the papermaking suspension and they may be both linter and comber fibres; additionally, fibres may be linen hemp or manila (abaca) fibres. It is preferred that cellulose fibres are present in an amount of at least 80% by weight and more preferably at least 90% by weight. The polyvinyl alcohol fibres which are soluble in water at temperature of from 95° to 100° C may be present in amounts of up to about 10% by weight and are preferably present in an amount of 2 to 10% and more preferably from 4 to 8% by weight based on the weight of the fibres in the papermaking suspension.

The polyvinyl alcohol fibres which are soluble in water at temperatures of from 95° to 100°C preferably have a length up to 5mm and more preferably from 3 to 5mm; the denier of these fibres may, for example, be up to 2 denier, or preferably 0.3 to 2 denier and more preferably 1 denier.

The polyvinyl alcohol fibres which are soluble in water at temperature of from 95° to 100°C may have a core formed from some different polymeric fibre material, for example polyester, a polyamide viscose or a water-insoluble polyvinyl alcohol. These fibres with the core may be considered to be equivalent to normal polyvinyl alcohol fibres in that they provide a polyvinyl alcohol surface which is essential in the

- 7 -

method according to this invention in order to obtain good strength properties as well as the good watermark which is for practical purposes an essential for high security documents especially banknotes. The polyvinyl alcohol fibres having the described core may be produced by a co-extrusion process or a 0.5 to 0.8 denier fibre tow of the core material may be passed through a bath of polyvinyl alcohol having a molecular weight of 50,000 to 150,000 wherein a coating of polyvinyl alcohol is applied to the fibre. The fibre is then dried and subsequently heat treated in order to increase the solubility of the polyvinyl alcohol to a value within the 95° to 100°C range, e.g. 99°C. The resulting tow fibre is then cut to produce a staple fibre length of say 5mm. Fibres produced in this way provide enhanced strength properties and improved bonding characteristics and also have a greatly reduced impact on the normal deterioration of watermark quality in comparison to their uncoated fibres.

It is an essential part of the present invention that high quality watermarks are achieved. As is well known, if the mobility of the papermaking fibres is insufficient, the watermark becomes poor or virtually indiscernible. This is because, either the hydrodynamic forces are insufficient to move the fibres or alternatively because the fibre mobility is hampered by their length. Such immobility prevents fibres from accumulating in the troughs of the watermark embossing and from migrating away from the peaks of such embossings during the forming process and results in a poor quality watermark. It is known that the usual papermaking cotton fibres for security

- 8 -

papers are in the region of 1mm long whilst synthetic fibres are generally used in the region of 3-5mm long. It is well known that the greater length of the synthetic fibres generally causes them to produce a
5 markedly inferior watermark by virtue of their inherent lesser mobility.

It is a marked feature of the present invention that the polyvinyl alcohol fibres which are soluble in
10 water at a temperature from 95°C to 100°C, because of their inherent lubricity, exhibit greatly improved mobility during the paper forming stage which in turn results in a markedly improved watermark quality when compared to paper containing insoluble polyvinyl
15 alcohol fibres such as disclosed in Dutch patent publication number 9 301 835. A superior performance of the polyvinyl alcohol fibres required for the present process is clear from both the definition and contrast of watermarks made using these fibres.

20

When the papermaking fibres are in suspension prior to the paper-forming process, the fibre concentration is typically 0.2%, as is well known in the art. At this concentration, there is a natural
25 tendency for the fibres to interact. For long fibres, such interaction results in the fibres clumping together. This clumping together may lead to flocculation and we have found that the tendency to clump or to flocculate is markedly less in dispersion
30 of fibres as a result of the presence in the suspension of the polyvinyl alcohol fibres which are soluble in water at temperatures from 95° to 100°C in comparison to the insoluble fibres described in Dutch patent publication number 9 301 835.

- 9 -

The use of polyvinyl alcohol fibres which are soluble in water at temperatures of from 90° to 100°C can provide the benefit of both good strength properties in paper and superior watermark properties. This is a truly surprising
5 combination of valuable properties and is not found when use is made of other water soluble polyvinyl alcohol fibres or insoluble (reinforcing) polyvinyl alcohol fibres.

The preferred polyvinyl alcohol fibres for use in this
10 invention are those produced by the process of wet spinning.

The invention will now be described by way of example.

15 Example 1:

A furnish was produced, containing 5% by weight on total dry fibre of 5mm, VPB102 PVOH fibres (Kuraray Co. Ltd., Tokyo) (soluble at 99°C, 5 mm long) and 95% by weight cotton fibres prepared in the usual way. This was applied
20 to an embossed mould on a paper machine for paper in the manner commonly used for banknote paper. The wet paper was then processed in the usual way through the following sequential processes: pressing, drying, polyvinyl alcohol impregnation, further drying, calendering and finally
25 reeling.

The paper thus produced was tested for doublefold and tear strength. The watermark was visually assessed according to the subjective criteria previously described.
30 Paper made in exactly the same way but from a furnish comprising 100% by weight cotton fibre was also tested by way of comparison.

- 10 -

The following results were obtained:

	Furnish composition	Grammage	Doublefold		Tear	
			MD	CD	MD	CD
5	95% cotton, 5% VPB102 x 5mm	83	5200	3000	1040	1200
	100% cotton	83	3400	2160	800	960

10 MD = machine direction
CD = cross section
Conditions - 50% RH

15	Furnish composition	Watermark		Background
		Contrast	Definition	
	95% cotton, 5% VPB102 x 5mm	good	good	good
	100% cotton	good	good	good

20

Example 2

One of the surprising aspects of the present invention is the distinct improvement in watermark quality achieved by fibres whose solubility is around 25 99°C compared to those that are insoluble such as the VPB103 fibres described in the above-mentioned Dutch patent application. This is illustrated by results from tests carried out on such fibres.

30 In a direct comparison of two fibre types, VPB103 (insoluble, 3mm long) described in the previously mentioned Dutch application and VPB102 (soluble at 99°C, 3mm long) being one of the preferred fibres for this application, the following results were obtained.
35 The assessment was divided into three categories,

- 11 -

good, fair, poor as judged by one skilled in the art. The paper was produced on British Standard hand sheet machine and contained 5% by weight of PVOH fibres.

Fibre Types	Watermark		Background
	Contrast	Definition	
VPB 102	Good	Good	Good
VPB 103	Fair	Fair	Fair

Further tests revealed the following empirical data relating to the watermark contrast. This showed the percent additional fibre thickness over the dark areas of the watermark compared to the non-watermarked area was far greater for the VPB102 fibres than for the VPB103 fibres.

Fibre Types	<u>Watermark Contrast</u> % thickness increase relative to non-watermarked area	
	Portrait watermark	Bar watermark
VPB102	14%	8%
VPB103	10%	4%

The contrast achieved by the VPB102 relative to the VPB103 was 40% better for the portrait watermark and 100% better for the bar watermark. This is a truly remarkable and surprising difference in performance and illustrates clearly the benefit represented by the fibre selection identified in this patent application.

- 12 -

CLAIMS

1. A method for the manufacture of security paper, which method comprises forming a papermaking suspension comprising cellulosic fibres and polyvinyl alcohol fibres wherein the cellulosic fibres are present in an amount of at least 80% by weight of the total weight of the fibres in the suspension and the polyvinyl alcohol fibres are present in an amount of from 2 to 10% by weight based on the weight of the fibres, characterised in that the polyvinyl alcohol fibres are soluble in water at temperatures of from 95° to 100°C, insoluble below 95°C and are 3 to 5 mm in length, wherein the papermaking suspension comprising cellulosic fibres and the polyvinyl alcohol fibres are dewatered through an embossed wire mesh, wherein the embossing creates a profile of peaks and troughs corresponding to the light and dark areas of a watermark, and the thus formed paper with the watermark feature after dewatering is thereafter dried to provide the resulting security paper.
2. A method as claimed in claim 1, wherein the security paper is banknote paper.
3. A method as claimed in claim 1 or claim 2, wherein the cellulosic fibres are present in an amount of at least 90% by weight of the total weight of the fibres in the suspension.
4. A method as claimed in any one of claims 1 to 3, wherein the said polyvinyl alcohol fibres are present in an amount of from 4 to 8% by weight based on the weight of the fibres.
5. A method as claimed in any one of claims 1 to 4, wherein the polyvinyl alcohol fibres are 0.3 to 2 denier.
6. A method as claimed in claim 5, wherein the polyvinyl alcohol fibres are 1 denier.
7. A method as claimed in any one of claims 1 to 6, wherein the polyvinyl alcohol fibres have a core formed from a polyester, a polyamide or viscose.