

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2016366239 B2**

(54) Title
Steel sheet for cans and production method for steel sheet for cans

(51) International Patent Classification(s)
C23C 28/00 (2006.01) **C25D 11/38** (2006.01)
C25D 5/16 (2006.01) **C25D 21/12** (2006.01)
C25D 5/26 (2006.01) **C25F 3/08** (2006.01)
C25D 9/10 (2006.01)

(21) Application No: **2016366239** (22) Date of Filing: **2016.12.01**

(87) WIPO No: **WO17/098994**

(30) Priority Data

(31) Number	(32) Date	(33) Country
2015-241871	2015.12.11	JP

(43) Publication Date: **2017.06.15**

(44) Accepted Journal Date: **2019.10.03**

(71) Applicant(s)
JFE Steel Corporation

(72) Inventor(s)
Nakagawa, Yusuke;Suzuki, Takeshi;Suto, Mikito;Kojima, Katsumi;Baba, Yuya

(74) Agent / Attorney
Davies Collison Cave Pty Ltd, Level 15 1 Nicholson Street, MELBOURNE, VIC, 3000, AU

(56) Related Art
JP 03-177599 A

(12) 特許協力条約に基づいて公開された国際出願

(19) 世界知的所有権機関
国際事務局

(43) 国際公開日
2017年6月15日(15.06.2017)



(10) 国際公開番号
WO 2017/098994 A1

- (51) 国際特許分類:
C23C 28/00 (2006.01) *C25D 11/38* (2006.01)
C25D 5/16 (2006.01) *C25D 21/12* (2006.01)
C25D 5/26 (2006.01) *C25F 3/08* (2006.01)
C25D 9/10 (2006.01)
- (21) 国際出願番号: PCT/JP2016/085796
- (22) 国際出願日: 2016年12月1日(01.12.2016)
- (25) 国際出願の言語: 日本語
- (26) 国際公開の言語: 日本語
- (30) 優先権データ:
特願 2015-241871 2015年12月11日(11.12.2015) JP
- (71) 出願人: J F E スチール株式会社 (JFE STEEL CORPORATION) [JP/JP]; 〒1000011 東京都千代田区幸町二丁目2番3号 Tokyo (JP).
- (72) 発明者: 中川 祐介 (NAKAGAWA Yusuke); 〒1000011 東京都千代田区幸町二丁目2番3号 J F E スチール株式会社 知的財産部内 Tokyo (JP). 鈴木 威 (SUZUKI Takeshi); 〒1000011 東京都千代田区幸町二丁目2番3号 J F E スチール株式会社 知的財産部内 Tokyo (JP). 須藤 幹人 (SUTO Mikito); 〒1000011 東京都千代田区幸町二丁目2番3号 J F E スチール株式会社 知的財産部内 Tokyo (JP). 小島 克己 (KOJIMA Katsumi); 〒1000011 東京都千代田区幸町二丁目2番3号 J F E スチール株式会社 知的財産部内 Tokyo (JP). 馬場 雄也 (BABA Yuya); 〒1000011 東京都千代田区幸町二丁目2番3号 J F E スチール株式会社 知的財産部内 Tokyo (JP).
- (74) 代理人: 渡辺 望稔, 外 (WATANABE Mochitoshi et al.); 〒1010032 東京都千代田区岩本町2丁目3番3号 友泉岩本町ビル6階 Tokyo (JP).
- (81) 指定国 (表示のない限り、全ての種類の国内保護が可能): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) 指定国 (表示のない限り、全ての種類の広域保護が可能): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), ユーラシア (AM, AZ, BY, KG, KZ, RU, TJ, TM), ヨーロッパ (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).
- 規則 4.17 に規定する申立て:
— 出願し及び特許を与えられる出願人の資格に関する申立て (規則 4.17(ii))
- 添付公開書類:
— 国際調査報告 (条約第 21 条(3))

(54) Title: STEEL SHEET FOR CANS AND PRODUCTION METHOD FOR STEEL SHEET FOR CANS

(54) 発明の名称: 缶用鋼板およびその製造方法

(57) Abstract: Provided is a steel sheet for cans that has an excellent surface appearance. Also provided is a production method for the steel sheet for cans. The steel sheet for cans has, on the surface thereof, in order from the steel sheet side, a chromium metal layer and a hydrous chromium oxide layer. The chromium metal layer is deposited in an amount of 65-200 mg/m², and the hydrous chromium oxide layer is deposited in an amount of 3-15 mg/m² in terms of chromium. The chromium metal layer includes: a flat chromium metal layer that has a thickness of at least 7 nm; and a granular chromium metal layer that includes granular protrusions that are formed on the surface of the flat chromium metal layer. The maximum grain size of the granular protrusions is 100 nm or smaller. The number density of the granular protrusions per unit area is 10/μm² or higher.

(57) 要約: 表面外観に優れる缶用鋼板およびその製造方法を提供する。上記缶用鋼板は、鋼板の表面に、上記鋼板側から順に、金属クロム層およびクロム水和酸化物層を有し、上記金属クロム層の付着量が、65～200mg/m²であり、上記クロム水和酸化物層のクロム換算の付着量が、3～15mg/m²であり、上記金属クロム層が、厚さが7nm以上である平板状金属クロム層と、上記平板状金属クロム層の表面に形成された粒状突起を有し、上記粒状突起の最大粒径が100nm以下であり、かつ、上記粒状突起の単位面積あたりの個数密度が10個/μm²以上である粒状金属クロム層と、を含む。



WO 2017/098994 A1

STEEL SHEET FOR CANS AND PRODUCTION METHOD FOR STEEL SHEET
FOR CANS

TECHNICAL FIELD

[0001]

The present invention relates to a steel sheet for cans and a method of manufacturing the same.

BACKGROUND ART

[0002]

Cans, which serve as containers for beverages and foods, are useful for storing the contents over a long period of time and are therefore used all over the world. Cans are roughly classified into the following two types: a two-piece can that is obtained by subjecting a metal sheet to drawing, ironing, stretching and bending to integrally form a can bottom and a can body and then joining the can body with a top lid by seaming; and a three-piece can that is obtained by machining a metal sheet into a tubular shape, welding the tubular metal sheet by a wire seam process to form a can body, and then joining the opposite ends of the can body separately with lids by seaming.

[0003]

Conventionally, a tin-plated steel sheet (so-called tin plate) has been widely used as a steel sheet for cans.

Nowadays, however, an electrolytic chromate treated steel sheet (hereinafter also called tin free steel (TFS)) having a chromium metal layer and a hydrated chromium oxide layer costs much less and is more excellent in paint adhesion than tin plates and is therefore expanding its range of application.

Besides, in connection with reduction in washing waste liquid and CO₂ for environmental reasons, cans using a steel sheet laminated with an organic resin film such as PET (polyethylene terephthalate) is drawing attention as an alternative technique that enables a coating process and a baking process to be omitted, and also in this context, the use of TFS having excellent adhesion to an organic resin film is expected to continuously expand.

[0004]

Meanwhile, since TFS is inferior to a tin plate in weldability, a hydrated chromium oxide layer which is an insulating coating at the surface layer is mechanically polished and removed immediately before welding to thereby make welding possible at present.

In industrial production, however, there are many problems in that, for instance, metal powder generated through polishing may be mixed in the contents, a burden of maintenance such as cleaning of can manufacturing equipment

increases, and the risk of a fire caused by metal powder increases.

[0005]

To cope with it, a technique for welding TFS without polishing is proposed by, for instance, Patent Literature 1. In the technique disclosed by Patent Literature 1, anodic electrolysis treatment is carried out between prior-stage and posterior-stage cathodic electrolysis treatments to thereby form a number of defect portions in a chromium metal layer, and then chromium metal is formed into a shape of granular protrusions through the posterior-stage cathodic electrolysis treatment. According to this technique, in welding, the granular protrusions of chromium metal destroy a hydrated chromium oxide layer that is a factor inhibiting welding at the surface layer, thereby reducing contact resistance and improving weldability.

CITATION LIST

PATENT LITERATURE

[0006]

Patent Literature 1: JP 63-186894 A

SUMMARY OF INVENTION

[0007]

The present inventors studied a steel sheet for cans

specifically described in Patent Literature 1 and found that, in some cases, they had poor surface appearance.

[0008]

The present invention aims to provide a steel sheet for cans having excellent surface appearance and a method of manufacturing the same.

[0009]

The present inventors have made an intensive study and as a result found that the decrease in the diameter of chromium metal granular protrusions improves surface appearance. The present invention has been thus completed.

[0010]

Specifically, the present invention provides the following [1] to [9].

[1] A steel sheet for cans comprising, on a surface of a steel sheet, a chromium metal layer and a hydrated chromium oxide layer stacked in this order from a steel sheet side,

wherein the chromium metal layer has a coating weight of 65 to 200 mg/m²,

wherein the hydrated chromium oxide layer has a coating weight of 3 to 15 mg/m² in terms of chromium amount,

and

wherein the chromium metal layer includes:

a flat chromium metal layer with a thickness of not less than 7 nm; and

a granular chromium metal layer having granular protrusions formed on a surface of the flat chromium metal layer, the granular protrusions having a maximum diameter of not more than 100 nm and a number density per unit area of not less than 10 protrusions/ μm^2 .

[2] The steel sheet for cans according to [1] above, wherein the granular protrusions have a maximum diameter of not more than 50 nm.

[3] The steel sheet for cans according to [2] above, wherein the granular protrusions have a maximum diameter of not more than 30 nm.

[4] The steel sheet for cans according to any one of [1] to [3] above, wherein the granular protrusions have a number density per unit area of not less than 50 protrusions/ μm^2 .

[5] The steel sheet for cans according to [4] above, wherein the granular protrusions have a number density per unit area of not less than 100 protrusions/ μm^2 .

[6] The steel sheet for cans according to any one of [1] to [5] above, wherein the flat chromium metal layer has

a thickness of not less than 10 nm.

[7] A method of manufacturing a steel sheet for cans for obtaining the steel sheet for cans according to any one of [1] to [6] above, the method comprising:

subjecting a steel sheet to prior-stage cathodic electrolysis treatment using an aqueous solution that contains Cr in an amount of not less than 0.5 mol/L and F in an amount of more than 0.10 mol/L and is free of sulfuric acid except for sulfuric acid inevitably incorporated therein, followed by anodic electrolysis treatment at an electric quantity density of more than 0.3 C/dm² but less than 5.0 C/dm², and then by posterior-stage cathodic electrolysis treatment.

[8] The method of manufacturing a steel sheet for cans according to [7] above, wherein the posterior-stage cathodic electrolysis treatment is a final electrolysis treatment.

[9] The method of manufacturing a steel sheet for cans according to [7] or [8] above, wherein the aqueous solution used in the prior-stage cathodic electrolysis treatment, the anodic electrolysis treatment and the posterior-stage cathodic electrolysis treatment comprises only one type of aqueous solution.

[0011]

The present invention provides a steel sheet for cans having excellent surface appearance and a method of manufacturing the same.

DETAILED DESCRIPTION OF THE INVENTION

[0012]

[Steel Sheet for Cans]

A steel sheet for cans of the invention includes, on a surface of a steel sheet, a chromium metal layer and a hydrated chromium oxide layer stacked in this order from the steel sheet side, the chromium metal layer having a coating weight of 50 to 200 mg/m², and the hydrated chromium oxide layer having a coating weight of 3 to 15 mg/m² in terms of chromium amount. The chromium metal layer includes: a flat chromium metal layer with a thickness of not less than 7 nm; and a granular chromium metal layer having granular protrusions formed on a surface of the flat chromium metal layer, the granular protrusions having a maximum diameter of not more than 100 nm and a number density per unit area of not less than 10 protrusions/μm².

When the maximum diameter of the granular protrusions of the granular chromium metal layer is 100 nm or less, the steel sheet for cans of the invention can have excellent surface appearance.

In the present invention, the term "coating weight" refers to the coating weight per one side of a steel sheet.

The constituent elements of the invention are described in detail below.

[0013]

[Steel Sheet]

The type of the steel sheet is not particularly limited. In general, steel sheets used as materials for containers (e.g., a low carbon steel sheet and an ultra low carbon steel sheet) can be used. A manufacturing method of the steel sheet, a material thereof and the like are also not particularly limited. The steel sheet is manufactured through a process starting with a typical billet manufacturing process, followed by such processes as hot rolling, pickling, cold rolling, annealing and temper rolling.

[0014]

[Chromium Metal Layer]

The steel sheet for cans of the invention has the chromium metal layer on a surface of the foregoing steel sheet.

The role of chromium metal in typical TFS is to suppress the exposure of a surface of the steel sheet serving as the basic material and thereby improve corrosion

resistance. When the amount of chromium metal is too small, the steel sheet is inevitably exposed, and this may lead to poor corrosion resistance.

In the present invention, the coating weight of the chromium metal layer is not less than 65 mg/m² because this leads to excellent corrosion resistance of the steel sheet for cans, and is preferably not less than 70 mg/m² and more preferably not less than 80 mg/m² because this leads to further excellent corrosion resistance.

[0015]

In contrast, when the amount of chromium metal is too large, high-melting chromium metal is to cover the entire surface of the steel sheet, and this induce significant decrease in weld strength in welding and significant generation of dust, which may lead to poor weldability.

In the present invention, the coating weight of the chromium metal layer is not more than 200 mg/m² because this leads to excellent weldability of the steel sheet for cans, and is preferably not more than 180 mg/m² and more preferably not more than 160 mg/m² because this leads to further excellent weldability.

[0016]

<Measurement Methods of Coating Weights>

The coating weight of the chromium metal layer and

the coating weight of the hydrated chromium oxide layer (described later) in terms of chromium amount are measured as follows.

First, for the steel sheet for cans having formed thereon the chromium metal layer and the hydrated chromium oxide layer, the amount of chromium (total amount of chromium) is measured with an X-ray fluorescence device. Next, the steel sheet for cans is subjected to alkaline treatment, i.e., is immersed in 6.5N-NaOH at 90°C for 10 minutes, and then, again, the amount of chromium (amount of chromium after alkaline treatment) is measured with an X-ray fluorescence device. The amount of chromium after alkaline treatment is taken as the coating weight of the chromium metal layer.

Thereafter, the equation (amount of alkali-soluble chromium) = (total amount of chromium) - (amount of chromium after alkaline treatment) is calculated, and the amount of alkali-soluble chromium is taken as the coating weight of the hydrated chromium oxide layer in terms of chromium amount.

[0017]

The chromium metal layer as above includes the flat chromium metal layer and the granular chromium metal layer having the granular protrusions formed on a surface of the

flat chromium metal layer.

Next, those layers included in the chromium metal layer are described in detail.

[0018]

<Flat Chromium Metal Layer>

The flat chromium metal layer mainly serves to improve corrosion resistance by covering a surface of the steel sheet.

The flat chromium metal layer in the invention needs to have, in addition to corrosion resistance which is generally required of TFS, a sufficient thickness such that the flat chromium metal layer would not be destroyed by granular protrusion-shaped chromium metal provided at the surface layer and hence the steel sheet is not exposed when the steel sheet for cans inevitably comes into contact with another steel sheet for cans at handling.

[0019]

In connection with this, the present inventors conducted a rubbing test of a steel sheet for cans with another steel sheet for cans so as to check rust resistance and found that, when the flat chromium metal layer has a thickness of not less than 7 nm, rust resistance is excellent. More specifically, the thickness of the flat chromium metal layer is not less than 7 nm because this

leads to excellent rust resistance of the steel sheet for cans, and is preferably not less than 9 nm and more preferably not less than 10 nm because this leads to further excellent rust resistance.

Meanwhile, the upper limit of the thickness of the flat chromium metal layer is not particularly limited and is, for instance, not more than 20 nm and preferably not more than 15 nm.

[0020]

(Measurement Method of Thickness)

The thickness of the flat chromium metal layer is measured as follows.

First, a cross section sample of a steel sheet for cans having formed thereon a chromium metal layer and a hydrated chromium oxide layer is produced by a focused ion beam (FIB) method and observed at a magnification of 20000X with a scanning transmission electron microscope (TEM). Next, in a sectional shape observation on a bright-field image, focusing on a portion where only a flat chromium metal layer is present with no granular protrusions, a line analysis is conducted by energy dispersive X-ray spectrometry (EDX) to obtain intensity curves (horizontal axis: distance, vertical axis: intensity) of chromium and iron, and those curves are used to determine the thickness

of the flat chromium metal layer. To be more specific, in the chromium intensity curve, the point at which the intensity is 20% of the maximum is taken as the uppermost layer, while the cross point with the iron intensity curve is taken as the boundary point with iron, and the distance between those two points is taken as the thickness of the flat chromium metal layer.

[0021]

The coating weight of the flat chromium metal layer is preferably not less than 10 mg/m², more preferably not less than 30 mg/m² and even more preferably not less than 40 mg/m² because this leads to excellent rust resistance of the steel sheet for cans.

[0022]

<Granular Chromium Metal Layer>

The granular chromium metal layer is a layer having the granular protrusions formed on a surface of the flat chromium metal layer described above, and mainly serves to improve weldability by reducing contact resistance between to-be-welded portions of the steel sheet for cans. The assumed mechanism of reduction in contact resistance is described below.

The hydrated chromium oxide layer covering the chromium metal layer is a non-conductive coating and

therefore has higher electric resistance than chromium metal, so that the hydrated chromium oxide layer works as a factor inhibiting welding. By forming the granular protrusions on a surface of the chromium metal layer, the granular protrusions destroy the hydrated chromium oxide layer using the surface pressure applied when to-be-welded portions of the steel sheet for cans come into contact with each other in welding, and the granular protrusions become current-carrying points of welding current, whereby the contact resistance greatly decreases.

[0023]

When the number of the granular protrusions of the granular chromium metal layer is too small, current-carrying points in welding should decrease in number, and this may prevent the contact resistance from being lowered, resulting in poor weldability.

In the present invention, the number density of the granular protrusions per unit area is not less than 10 protrusions/ μm^2 because this leads to excellent weldability of the steel sheet for cans, and is preferably not less than 15 protrusions/ μm^2 , more preferably not less than 20 protrusions/ μm^2 , even more preferably not less than 30 protrusions/ μm^2 , particularly preferably not less than 50 protrusions/ μm^2 and most preferably not less than 100

protrusions/ μm^2 because this leads to further excellent weldability.

Because too high a number density of the granular protrusions per unit area may affect the color tone or the like, the upper limit of the number density per unit area is preferably not more than 10000 protrusions/ μm^2 , more preferably not more than 5000 protrusions/ μm^2 , even more preferably not more than 1000 protrusions/ μm^2 and particularly preferably not more than 800 protrusions/ μm^2 in order to achieve further excellent surface appearance of the steel sheet for cans.

[0024]

The present inventors found that, when the maximum diameter of the granular protrusions of the chromium metal layer is too large, this affects the hue or the like of the steel sheet for cans, and a brown pattern appears in some cases, resulting in a poor surface appearance. The possible reasons of the above are for example as follows: the granular protrusions absorb short-wavelength (blue) light, and accordingly, reflected light thereof is attenuated, so that a reddish brown color appears; the granular protrusions diffuse reflected light, so that the overall reflectance decreases and the color gets darker.

Therefore, in the present invention, the maximum

diameter of the granular protrusions of the granular chromium metal layer is set to 100 nm or less. As a result, the steel sheet for cans can have an excellent surface appearance. This is probably because the granular protrusions with a smaller diameter serve to suppress absorption of short-wavelength light and suppress dispersion of reflected light.

The maximum diameter of the granular protrusions of the granular chromium metal layer is preferably not more than 80 nm, more preferably not more than 50 nm and even more preferably not more than 30 nm because this leads to further excellent surface appearance of the steel sheet for cans.

The lower limit of the maximum diameter is not particularly limited and is preferably, for instance, not less than 10 nm.

[0025]

(Measurement Methods of Diameter of Granular Protrusions and Number Density Thereof per Unit Area)

The diameter of the granular protrusions of the granular chromium metal layer and the number density thereof per unit area are measured as follows.

First, a surface of the steel sheet for cans having formed thereon the chromium metal layer and the hydrated

chromium oxide layer is subjected to carbon deposition to produce an observation sample by an extraction replica method. Subsequently, a micrograph of the sample is taken at a magnification of 20000X with a scanning transmission electron microscope (TEM), the taken micrograph is binarized using software (trade name: ImageJ) and subjected to image analysis, and the diameter (as a true circle-equivalent value) and the number density per unit area are determined through back calculation of the area occupied by the granular protrusions. The maximum diameter is the diameter that is maximum in observation fields as obtained by taking micrographs of five fields at a magnification of 20000X, and the number density per unit area is the average of number densities in the five fields.

[0026]

[Hydrated Chromium Oxide Layer]

Hydrated chromium oxide is deposited along with chromium metal on a surface of the steel sheet and mainly serves to improve corrosion resistance. In the present invention, the coating weight of the hydrated chromium oxide layer in terms of chromium amount is set to at least 3 mg/m² for the purpose of ensuring corrosion resistance of the steel sheet for cans.

[0027]

Meanwhile, hydrated chromium oxide is inferior to chromium metal in conductivity, and accordingly, too much amount of hydrated chromium oxide leads to excessive resistance in welding, which may cause generation of dust, occurrence of splash, and a variety of weld defects such as blowhole formation associated with overwelding, thus resulting in poor weldability of the steel sheet for cans.

Therefore, in the present invention, the coating weight of the hydrated chromium oxide layer in terms of chromium amount is not more than 15 mg/m^2 because this leads to excellent weldability of the steel sheet for cans, and is preferably not more than 13 mg/m^2 , more preferably not more than 10 mg/m^2 and still more preferably not more than 8 mg/m^2 because this leads to further excellent weldability.

[0028]

The measurement method of the coating weight of the hydrated chromium oxide layer in terms of chromium amount is as described above.

[0029]

[Method of Manufacturing Steel Sheet for Cans]

Next, the method of manufacturing steel sheet for cans according to the present invention is described.

The method of manufacturing steel sheet for cans

2016366239 18 Jul 2018

- 19 -

according to the present invention (hereinafter also simply called "manufacturing method of the invention") is a method of manufacturing the foregoing steel sheet for cans of the invention, the method comprising subjecting a steel sheet to prior-stage cathodic electrolysis treatment using an aqueous solution that contains Cr in an amount of not less than 0.5 mol/L and F in an amount of more than 0.10 mol/L and is free of sulfuric acid except for sulfuric acid inevitably incorporated therein, followed by anodic electrolysis treatment at an electric quantity density of not less than 0.1 C/dm² but less than 5.0 C/dm², and then by posterior-stage cathodic electrolysis treatment.

[0030]

Typically, in cathodic electrolysis treatment in an aqueous solution containing a hexavalent chromium compound, a reduction reaction occurs at a steel sheet surface, whereby chromium metal is deposited, and hydrated chromium oxide that is an intermediate product before becoming chromium metal is deposited on the chromium metal surface. This hydrated chromium oxide is unevenly dissolved through intermittent electrolysis treatment or long time immersion in an aqueous solution of a hexavalent chromium compound, and in the subsequent cathodic electrolysis treatment, chromium metal granular protrusions are formed.

[0031]

In the present invention, since the anodic electrolysis treatment is carried out between the two cathodic electrolysis treatments, chromium metal is dissolved over the entire surface of the steel sheet at multiple sites, and those sites become starting points of formation of the chromium metal granular protrusions in the subsequent cathodic electrolysis treatment. The flat chromium metal layer is deposited in the prior-stage cathodic electrolysis treatment which is cathodic electrolysis treatment carried out before the anodic electrolysis treatment, and the granular chromium metal layer (granular protrusions) is deposited in the posterior-stage cathodic electrolysis treatment which is cathodic electrolysis treatment carried out after the anodic electrolysis treatment.

[0032]

The amounts of deposition of the layers can be controlled by electrolysis conditions in the respective electrolysis treatments.

The aqueous solution and the electrolysis treatments used in the manufacturing method of the invention are described in detail below.

[0033]

[Aqueous Solution]

The aqueous solution used in the manufacturing method of the invention is an aqueous solution that contains Cr in an amount of not less than 0.5 mol/L and F in an amount of more than 0.10 mol/L and is free of sulfuric acid except for sulfuric acid inevitably incorporated therein.

[0034]

The amount of F in the aqueous solution influences dissolution of hydrated chromium oxide during immersion and dissolution of chromium metal during the anodic electrolysis treatment, and thus greatly influences the form of chromium metal deposited in the subsequent cathodic electrolysis treatment. Sulfuric acid also brings about the same effect; however, the effect generated by sulfuric acid is excessive, and as a consequence, uneven dissolution of hydrated chromium oxide causes local formation of huge granular protrusions, and dissolution of chromium metal extremely proceeds during the anodic electrolysis treatment. Thus, it may be difficult to form fine granular protrusions. Therefore, the aqueous solution in the invention is free of sulfuric acid except for sulfuric acid inevitably incorporated therein.

It should be noted that sulfuric acid is inevitably incorporated in certain raw materials such as chromium

trioxide in the industrial production process, so that the use of such raw materials results in inevitable incorporation of sulfuric acid into the resulting aqueous solution. The amount of sulfuric acid inevitably incorporated in the aqueous solution is preferably less than 0.001 mol/L and more preferably less than 0.0001 mol/L.

[0035]

The aqueous solution in the invention contains Cr in an amount of not less than 0.5 mol/L because this leads to highly efficient and stable deposition of chromium metal over a long period of time.

In addition, the aqueous solution in the invention contains F in an amount of more than 0.10 mol/L. As a result, even and fine dissolution of chromium metal proceeds over the entire surface during the anodic electrolysis treatment, and consequently, generation sites at which fine granular protrusions are generated in the posterior-stage cathodic electrolysis treatment can be obtained.

[0036]

It is preferable that one type of aqueous solution be solely used in the prior-stage cathodic electrolysis treatment, the anodic electrolysis treatment and the posterior-stage cathodic electrolysis treatment.

[0037]

<Hexavalent Chromium Compound>

The aqueous solution preferably contains a hexavalent chromium compound. The hexavalent chromium compound contained in the aqueous solution is not particularly limited, and examples thereof include chromium trioxide (CrO_3), dichromates such as potassium dichromate ($\text{K}_2\text{Cr}_2\text{O}_7$), and chromates such as potassium chromate (K_2CrO_4).

The hexavalent chromium compound content of the aqueous solution is preferably from 0.5 to 5.0 mol/L and more preferably from 0.5 to 3.0 mol/L in the amount of Cr.

[0038]

<Fluorine-Containing Compound>

The aqueous solution preferably contains a fluorine-containing compound. The fluorine-containing compound contained in the aqueous solution is not particularly limited, and examples thereof include hydrofluoric acid (HF), potassium fluoride (KF), sodium fluoride (NaF), hydrosilicofluoric acid (H_2SiF_6) and/or salts thereof. Examples of salts of hydrosilicofluoric acid include sodium silicofluoride (Na_2SiF_6), potassium silicofluoride (K_2SiF_6), and ammonium silicofluoride ($(\text{NH}_4)_2\text{SiF}_6$).

The fluorine-containing compound content of the aqueous solution is preferably more than 0.10 mol/L but not

more than 4.0 mol/L, more preferably from 0.15 to 3.0 mol/L and still more preferably from 0.20 to 2.0 mol/L in the amount of F.

[0039]

The temperature of the aqueous solution in each electrolysis treatment is preferably 20°C to 80°C and more preferably 40°C to 60°C.

[0040]

[Prior-Stage Cathodic Electrolysis Treatment]

Cathodic electrolysis treatment is carried out to deposit chromium metal and hydrated chromium oxide.

The electric quantity density (the product of the current density and the current application time) in the prior-stage cathodic electrolysis treatment is preferably 20 to 50 C/dm² and more preferably 25 to 45 C/dm² for the purpose of achieving a proper amount of deposition and ensuring an appropriate thickness of the flat chromium metal layer.

The current density (unit: A/dm²) and the current application time (unit: sec.) are suitably set based on the foregoing electric quantity density.

[0041]

The prior-stage cathodic electrolysis treatment need not be continuous electrolysis treatment. In other words,

the prior-stage cathodic electrolysis treatment may be intermittent electrolysis treatment in which an immersion period with no current application is inevitably present since electrolysis is carried out with separate electrodes in industrial production. In the case of intermittent electrolysis treatment, the total electric quantity density preferably falls within the foregoing ranges.

[0042]

[Anodic Electrolysis Treatment]

The anodic electrolysis treatment serves to dissolve chromium metal deposited in the prior-stage cathodic electrolysis treatment so as to form generation sites of the chromium metal granular protrusions to be generated in the posterior-stage cathodic electrolysis treatment. When dissolution excessively proceeds in the anodic electrolysis treatment, this may cause a decreased number of generation sites and hence lower number density of the granular protrusions per unit area, variation in distribution of the granular protrusions due to uneven progression of dissolution, and a small thickness of the flat chromium metal layer of less than 7 nm.

[0043]

The chromium metal layer formed in the prior-stage cathodic electrolysis treatment and the anodic electrolysis

treatment is mainly composed of the flat chromium metal layer. In order to have the flat chromium metal layer with a thickness of 7 nm or more, it is necessary to ensure the chromium metal amount of not less than 50 mg/m² after the prior-stage cathodic electrolysis treatment and the anodic electrolysis treatment.

[0044]

From the foregoing factors, the electric quantity density (the product of the current density and the current application time) in the anodic electrolysis treatment is more than 0.3 C/dm² but less than 5.0 C/dm². Also described is an electric quantity density in the anodic electrolysis treatment of not less than 0.1C/dm². The upper limit of the electric quantity density in the anodic electrolysis treatment is preferably not more than 3.0 C/dm² and more preferably not more than 2.0 C/dm².

The current density (unit: A/dm²) and the current application time (unit: sec.) are suitably set based on the foregoing electric quantity density.

[0045]

The anodic electrolysis treatment need not be continuous electrolysis treatment. In other words, the anodic electrolysis treatment may be intermittent electrolysis treatment because electrolysis is carried out

separately for each set of electrodes in industrial production and accordingly, an immersion period with no current application is inevitably present. In the case of intermittent electrolysis treatment, the total electric quantity density preferably falls within the foregoing ranges.

[0046]

[Posterior-Stage Cathodic Electrolysis Treatment]

As described above, cathodic electrolysis treatment is carried out to deposit chromium metal and hydrated chromium oxide. In particular, the posterior-stage cathodic electrolysis treatment allows the chromium metal granular protrusions to be generated at the foregoing generation sites serving as starting points. In this process, when the electric quantity density is too high, the chromium metal granular protrusions may excessively grow, leading to a coarse grain size.

For this reason, in the posterior-stage cathodic electrolysis treatment, the electric quantity density is preferably less than 30.0 C/dm^2 , more preferably not more than 25.0 C/dm^2 and still more preferably not more than 7.0 C/dm^2 . The lower limit thereof is not particularly limited and is preferably not less than 1.0 C/dm^2 and more preferably not less than 2.0 C/dm^2 .

The current application time (unit: sec.) is suitably set based on the foregoing current density and electric quantity density.

[0047]

The posterior-stage cathodic electrolysis treatment need not be continuous electrolysis treatment. In other words, the posterior-stage cathodic electrolysis treatment may be intermittent electrolysis treatment because electrolysis is carried out separately for each set of electrodes in industrial production and accordingly, an immersion period with no current application is inevitably present. In the case of intermittent electrolysis treatment, the total electric quantity density preferably falls within the foregoing ranges.

[0048]

Preferably, the posterior-stage cathodic electrolysis treatment is the final electrolysis treatment. In other words, preferably, the posterior-stage cathodic electrolysis treatment is not followed by another electrolysis treatment (cathodic or anodic electrolysis treatment, particularly cathodic electrolysis treatment). More preferably, as the electrolysis treatments, only the prior-stage cathodic electrolysis treatment, the anodic electrolysis treatment and the posterior-stage cathodic

electrolysis treatment are carried out using one type of aqueous solution.

When the posterior-stage cathodic electrolysis treatment is the final electrolysis treatment, the coating weight of the hydrated chromium oxide layer in terms of chromium amount and the maximum diameter of the granular protrusions of the granular chromium metal layer can be prevented from excessively increasing.

[0049]

Even when the posterior-stage cathodic electrolysis treatment is the final electrolysis treatment, however, the posterior-stage cathodic electrolysis treatment may be followed by immersion treatment in which the steel sheet is immersed in a hexavalent chromium compound-containing aqueous solution in an electroless state, for the purpose of controlling the amount of hydrated chromium oxide layer and reforming the hydrated chromium oxide layer. Even with the immersion treatment as above, the thickness of the flat chromium metal layer and the diameter and number density of the granular protrusions of the granular chromium metal layer are not at all affected thereby.

The hexavalent chromium compound contained in the aqueous solution used in the immersion treatment is not particularly limited, and examples thereof include chromium

trioxide (CrO_3), dichromates such as potassium dichromate ($\text{K}_2\text{Cr}_2\text{O}_7$), and chromates such as potassium chromate (K_2CrO_4).

EXAMPLES

[0050]

The present invention is specifically described below by way of examples. However, the present invention should not be construed as being limited to the following examples.

[0051]

[Manufacture of Steel Sheet for Cans]

Each steel sheet (tempered grade: T4CA) as produced to a sheet thickness of 0.22 mm was subjected to normal degreasing and pickling. Subsequently, the relevant aqueous solution shown in Table 1 below was circulated by a pump at a rate equivalent to 100 mpm in a fluid cell, and electrolysis treatment was carried out using lead electrodes under the conditions shown in Table 2 below, thereby manufacturing a steel sheet for cans that is TFS. The steel sheet for cans as manufactured was rinsed with water and dried by a blower at room temperature.

To be more specific, only in Comparative Example 2, the prior-stage cathodic electrolysis treatment, the anodic electrolysis treatment and the posterior-stage cathodic electrolysis treatment were conducted using a first solution (aqueous solution E), and then cathodic

electrolysis treatment was conducted using a second solution (aqueous solution F). In the other examples, the prior-stage cathodic electrolysis treatment, the anodic electrolysis treatment and the posterior-stage cathodic electrolysis treatment were conducted using solely the first solution (relevant one out of aqueous solutions A to E).

[0052]

[Coating Weight]

For each of the manufactured steel sheet for cans, the coating weight of the chromium metal layer (Cr metal layer) and the coating weight of the hydrated chromium oxide layer (hydrated Cr oxide layer) in terms of chromium amount (stated simply as "Coating weight" in Table 2 below) were measured. The measurement methods are as described above. The results are shown in Table 2 below.

[0053]

[Cr metal layer structure]

For the Cr metal layer of each of the manufactured steel sheet for cans, the thickness of the flat chromium metal layer (flat Cr metal layer) and the maximum diameter of the granular protrusions of the granular chromium metal layer (granular Cr metal layer) as well as the number density thereof per unit area were measured. The

measurement methods are as described above. The results are shown in Table 2 below.

[0054]

[EVALUATION]

The manufactured steel sheet for cans were evaluated for the following factors. The evaluation results are shown in Table 2 below.

[0055]

<Rust Resistance>

Two samples were cut out from each of the manufactured steel sheet for cans. One sample (30 mm x 60 mm) was fixed to a rubbing tester for use as an evaluation sample, while the other sample (10 mm x 10 mm) was fixed to a head, and the head was moved 10 strokes over a length of 60 mm at a surface pressure of 1 kgf/cm² and a rubbing rate of 1 second per reciprocation. Thereafter, the evaluation sample was allowed to stand in a constant temperature and humidity chamber at 40°C and 80% RH for 7 days. Then, the evaluation sample was observed at low magnification with an optical microscope, and a micrograph thereof was subjected to image analysis to determine the rust occurrence area fraction of a rubbed portion. The evaluation was made according to the following criteria. For practical use, when the result is A, B or C, the steel sheet for cans can

be rated as having excellent rust resistance.

A: Rust occurrence of less than 1%

B: Rust occurrence of not less than 1% but less than 2%

C: Rust occurrence of not less than 2% but less than 5%

D: Rust occurrence of not less than 5% but less than 10%

E: Rust occurrence of not less than 10% or rust occurrence at somewhere other than a rubbed portion
[0056]

<Color Tone>

For each of the manufactured steel sheet for cans, the L value was measured according to the Hunter-type color difference measurement defined in JIS Z 8730 of old version (1980) and evaluated according to the following criteria. For practical use, when the result is A, B or C, the steel sheet for cans can be rated as having excellent surface appearance.

A: An L value of not less than 70

B: An L value of not less than 67 but less than 70

C: An L value of not less than 65 but less than 67

C-D: An L value of not less than 63 but less than 65

D: An L value of not less than 60 but less than 63

E: An L value of less than 60

[0057]

<Contact Resistance>

Each of the manufactured steel sheet for cans was subjected to thermocompression bonding of an organic resin film and heat treatment for which posterior heating had been simulated, and then contact resistance was measured. More specifically, samples of each of the steel sheet for cans were separately traveled through a film laminating device at a roll pressure of 4 kg/cm², a plate feed speed of 40 mpm, and a plate surface temperature after passing rolls of 160°C, and subjected to the posterior heating in a batch furnace (and retained at a target temperature of 210°C for 120 seconds), whereafter the samples having undergone the posterior heating were superposed on each other. Subsequently, 1 mass% Cr-Cu electrodes of DR type were machined to a tip diameter of 6 mm and a curvature of R40 mm, the superposed samples were sandwiched by these electrodes and retained at a pressure of 1 kgf/cm² for 15 seconds, then 10A current was supplied thereto, and the contact resistance between the sample plates was measured. The measurement was made for ten cases, and the average thereof was taken as a contact resistance value to be evaluated according to the following criteria. For

practical use, when the result is A, B or C, the steel sheet for cans can be rated as having excellent weldability.

A: Contact resistance of not more than 50 $\mu\Omega$

B: Contact resistance of more than 50 $\mu\Omega$ but not more than 100 $\mu\Omega$

C: Contact resistance of more than 100 $\mu\Omega$ but not more than 300 $\mu\Omega$

D: Contact resistance of more than 300 $\mu\Omega$ but not more than 1000 $\mu\Omega$

E: Contact resistance of more than 1000 $\mu\Omega$

[0058]

[Table 1]

Table 1

Aqueous solution	Composition		
	Whole	mol/L	
		Cr	F
A	CrO ₃ 0.5mol/L NaF 0.20mol/L	0.50	0.200
B	CrO ₃ 0.75mol/L NaF 0.20mol/L	0.75	0.200
C	CrO ₃ 1.0mol/L NaF 0.20mol/L	1.00	0.200
D	CrO ₃ 0.5mol/L NaF 0.10mol/L	0.50	0.100
E	CrO ₃ 0.8mol/L Na ₂ SiF ₆ 0.011mol/L	0.80	0.064
F	CrO ₃ 0.4mol/L Na ₂ SiF ₆ 0.001mol/L	0.40	0.005

[0059]

[Table 2]

Table 2

	First solution										Second solution					Coating weight		Cr metal layer structure			Rust Resistance	Color Tone	Contact resistance		
	Aqueous solution	Prior-stage cathodic electrolysis treatment			Anodic electrolysis treatment			Posterior-stage cathodic electrolysis treatment			Temp.	Aqueous solution	Temp.	Current density	Cathodic electrolysis treatment			Cr metal layer	Hydrated Cr oxide layer	Flat Cr metal layer				Granular Cr metal layer	
		Current density	Current application time	Electric quantity density	Current density	Current application time	Electric quantity density	Current density	Current application time	Electric quantity density					Maximum diameter	Density									
																	Thickness							nm	Protrusions /μm ²
°C	A/dm ²	sec.	C/dm ²	A/dm ²	sec.	C/dm ²	A/dm ²	sec.	C/dm ²	°C	A/dm ²	sec.	C/dm ²	mg/m ²	mg/m ²	nm	nm	Protrusions /μm ²							
EX 1	A	45	60	0.65	39	2	0.25	0.5	60	0.05	3	—	—	—	92	6	14.2	25	140	A	A	A			
EX 2	A	45	60	0.65	39	4	0.25	1	60	0.05	3	—	—	—	90	3	12.6	20	120	A	A	A			
EX 3	A	45	60	0.65	39	8	0.25	2	60	0.15	9	—	—	—	92	5	11.2	80	110	A	B	A			
EX 4	A	45	60	0.65	39	12	0.25	3	60	0.15	9	—	—	—	77	6	10.7	70	80	A	B	A			
EX 5	A	45	60	0.50	30	1	0.50	0.5	60	0.15	9	—	—	—	114	3	11.2	30	220	A	A	A			
EX 6	A	45	60	0.50	30	2	0.50	1	60	0.20	12	—	—	—	109	4	9.0	60	250	B	B	A			
EX 7	A	45	60	0.50	30	4	0.50	2	60	0.25	15	—	—	—	92	4	8.2	80	170	C	B	A			
EX 8	B	45	60	0.50	30	1	0.50	0.5	60	0.20	12	—	—	—	117	4	12.3	30	165	A	A	A			
EX 9	B	45	60	0.50	30	2	0.50	1	60	0.25	15	—	—	—	115	6	11.0	80	80	A	B	A			
EX 10	B	45	60	0.50	30	4	0.50	2	60	0.30	18	—	—	—	109	4	8.9	75	75	C	B	A			
EX 11	C	45	60	0.50	30	1	0.50	0.5	60	0.20	12	—	—	—	117	5	13.3	30	200	A	A	A			
EX 12	C	45	60	0.50	30	2	0.50	1	60	0.25	15	—	—	—	120	4	11.6	70	85	A	B	A			
EX 13	C	45	60	0.50	30	4	0.50	2	60	0.30	18	—	—	—	112	5	10.5	80	65	A	B	A			
OE 1	D	45	60	0.50	30	2	0.50	1	60	0.25	15	—	—	—	110	8	11.0	160	30	A	E	A			
OE 2	E	50	80	0.30	24	5	0.50	2.5	40	0.50	20	F	40	2	0.80	1.6	70	10	3.5	120	40	E	C-D	A	
OE 3	E	50	40	0.70	28	5	0.20	1	50	0.20	10	—	—	—	61	10	4.0	1000	12	E	E	D			

EX: Example

OE: Comparative Example

[0060]

As is evident from the results shown in Table 2, it was revealed that the steel sheet for cans of Examples 1 to 13 had excellent surface appearance.

In contrast, in Comparative Example 1 using the aqueous solution D (NaF: 0.10 mol/L), the maximum diameter per unit area of the granular protrusions of the granular chromium metal layer was 160 nm and thus large, resulting in poor surface appearance.

In Comparative Example 2 in which a series of electrolysis treatments (the prior-stage cathodic electrolysis treatment, anodic electrolysis treatment and posterior-stage cathodic electrolysis treatment) using the first solution was followed by cathodic electrolysis treatment using the second solution, for example, the maximum diameter of the granular protrusions of the granular chromium metal layer was 120 nm and thus large, resulting in poor surface appearance.

In Comparative Example 3, the maximum diameter of the granular protrusions of the granular chromium metal layer was 1000 nm and thus large, resulting in poor surface appearance.

The reference in this specification to any prior publication (or information derived from it), or to any

matter which is known, is not, and should not be taken as an acknowledgment or admission or any form of suggestion that that prior publication (or information derived from it) or known matter forms part of the common general knowledge in the field of endeavour to which this specification relates.

Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", and variations such as "comprises" and "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS

[Claim 1]

A steel sheet for cans comprising, on a surface of a steel sheet, a chromium metal layer and a hydrated chromium oxide layer stacked in this order from a steel sheet side,

wherein the chromium metal layer has a coating weight of 65 to 200 mg/m²,

wherein the hydrated chromium oxide layer has a coating weight of 3 to 15 mg/m² in terms of chromium amount, and

wherein the chromium metal layer includes:

a flat chromium metal layer with a thickness of not less than 7 nm; and

a granular chromium metal layer having granular protrusions formed on a surface of the flat chromium metal layer, the granular protrusions having a maximum diameter of not more than 100 nm and a number density per unit area of not less than 10 protrusions/ μm^2 .

[Claim 2]

The steel sheet for cans according to claim 1, wherein the granular protrusions have a maximum diameter of not more than 50 nm.

[Claim 3]

The steel sheet for cans according to claim 2,

wherein the granular protrusions have a maximum diameter of not more than 30 nm.

[Claim 4]

The steel sheet for cans according to any one of claims 1 to 3, wherein the granular protrusions have a number density per unit area of not less than 50 protrusions/ μm^2 .

[Claim 5]

The steel sheet for cans according to claim 4, wherein the granular protrusions have a number density per unit area of not less than 100 protrusions/ μm^2 .

[Claim 6]

The steel sheet for cans according to any one of claims 1 to 5, wherein the flat chromium metal layer has a thickness of not less than 10 nm.

[Claim 7]

A method of manufacturing a steel sheet for cans for obtaining the steel sheet for cans according to any one of claims 1 to 6, the method comprising:

subjecting a steel sheet to prior-stage cathodic electrolysis treatment using an aqueous solution that contains Cr in an amount of not less than 0.5 mol/L and F in an amount of more than 0.10 mol/L and is free of sulfuric acid except for sulfuric acid inevitably

incorporated therein, followed by anodic electrolysis treatment at an electric quantity density of more than 0.3 C/dm² but less than 5.0 C/dm², and then by posterior-stage cathodic electrolysis treatment.

[Claim 8]

The method of manufacturing a steel sheet for cans according to claim 7, wherein the posterior-stage cathodic electrolysis treatment is a final electrolysis treatment.

[Claim 9]

The method of manufacturing a steel sheet for cans according to claim 7 or 8, wherein the aqueous solution used in the prior-stage cathodic electrolysis treatment, the anodic electrolysis treatment and the posterior-stage cathodic electrolysis treatment comprises only one type of aqueous solution.