

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



A standard linear barcode is located at the bottom of the page, spanning most of the width. It is used for tracking and identification of the document.

**(43) International Publication Date
2 February 2012 (02.02.2012)**

(10) International Publication Number
WO 2012/016053 A1

(51) International Patent Classification:
C08L 23/08 (2006.01) *H01L 31/0203* (2006.01)
B32B 17/10 (2006.01) *H01L 31/0216* (2006.01)
B32B 27/32 (2006.01)

(21) International Application Number: PCT/US2011/045738

(22) International Filing Date: 28 July 2011 (28.07.2011)

(25) Filing Language: English

(26) **Publication Language:** English

12/847,293 30 July 2010 (30.07.2010) US
(71) Application filed in the U.S. Patent and Trademark Office (US), E. I. DU

(11) **Applicant for the designated States except US:** E. I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, Delaware 19898 (US).

(72) Inventors; and

(75) **Inventors/Applicants (for US only):** PREJEAN, George, Wyatt [US/US]; #3 Stratford, Orange, Texas 77632 (US). BENNETT, Alison, Margaret, Anne [GB/US]; 507 Falkirk Road, Wilmington, Delaware 19803 (US).

(74) **Agent: KOURTAKIS, Maria, M.**; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).

(81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: CROSS-LINKABLE IONOMICRIC ENCAPSULANTS FOR PHOTOVOLTAIC CELLS

FIG. 1



(57) Abstract: Provided herein is a blend composition useful as a cross-linkable encapsulant layer and consisting essentially of two ethylene copolymers and optionally one or more additives. The first ethylene copolymer comprises copolymerized units of ethylene, optionally a first olefin having the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and a second olefin having the formula $\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$. At least a portion of the carboxylic acid groups have been neutralized to form carboxylate salts. The second ethylene copolymer consists essentially of copolymerized units of ethylene, optionally a first olefin having the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and a third olefin having the formula $\text{CH}_2=\text{C}(\text{R}^4)\text{D}$. R^1 , R^3 and R^4 represent hydrogen or an alkyl group; R^2 represents an alkyl group; and D represents a moiety containing an epoxy group. Further provided are solar cell modules comprising the encapsulant layer. The encapsulant layer comprises the blend composition or the product of cross-linking the blend composition, in which some carboxylate groups of the second olefin have reacted with some epoxy groups of the third olefin.

TITLE OF THE INVENTION

CROSS-LINKABLE IONOMERIC ENCAPSULANTS

FOR PHOTOVOLTAIC CELLS

5

FIELD OF THE INVENTION

The invention is directed to a cross-linked or cross-linkable encapsulant for solar cell modules. In particular, the cross-linkable encapsulant consists essentially of a blend composition of two ethylene copolymers, with a first ethylene copolymer incorporating residues of an unsaturated carboxylic acid and a second ethylene copolymer incorporating residues of a moiety containing an epoxy group. At least a portion of the carboxylic acid groups have been neutralized to form carboxylate salts. In the cross-linked encapsulant layer, the carboxylate groups have been caused to react with the epoxy groups.

15

BACKGROUND OF THE INVENTION

Several patents and publications are cited in this description in order to more fully describe the state of the art to which this invention pertains. The entire disclosure of each of these patents and publications is incorporated by reference herein.

Because solar cells provide a sustainable energy resource, their use is rapidly expanding. Solar cells can typically be categorized into two types based on the light absorbing material used, i.e., bulk or wafer-based solar cells and thin film solar cells.

25 Monocrystalline silicon (c-Si), poly- or multi-crystalline silicon (poly-Si or mc-Si) and ribbon silicon are the materials used most commonly in forming the more traditional wafer-based solar cells. Solar cell modules derived from wafer-based solar cells often comprise a series of about 180 to about 240 μm thick self-supporting wafers (or cells) that are soldered together and electrically connected. Such a panel of solar cells, along with a layer of conductive paste and/or connecting wires deposited on its surface, may be referred to as a solar cell assembly. The solar cell assembly may be encapsulated by, sandwiched between, or laminated between polymeric encapsulants. The resulting structure may be further sandwiched between

two protective outer layers (i.e., front sheet and back sheet) to form a weather resistant module. The protective outer layers may be formed of glass, metal sheets or films, or plastic sheets or films. In general, however, the outer layer that faces to the sunlight needs to be sufficiently transparent to allow photons reach the solar cells.

5

In the increasingly important alternative, thin film solar cells, the commonly used materials include amorphous silicon (a-Si), microcrystalline silicon (μ c-Si), cadmium telluride (CdTe), copper indium selenide (CuInSe_2 or CIS), copper indium/gallium diselenide ($\text{CuIn}_x\text{Ga}_{(1-x)}\text{Se}_2$ or CIGS), light absorbing dyes, organic semiconductors, etc. By way of example, thin film solar cells are described in e.g., U.S. Patent Nos. 5,507,881; 5,512,107; 10 5,948,176; 5,994,163; 6,040,521; 6,123,824; 6,137,048; 6,288,325; 6,258,620; 6,613,603; and 6,784,301; and U.S. Patent Publication Nos. 20070298590; 20070281090; 20070240759; 20070232057; 20070238285; 15 20070227578; 20070209699; 20070079866; 20080223436; and 20080271675.

15

Thin film solar cells with a typical thickness of less than 2 μm are produced by depositing the semiconductor materials onto a substrate, generally in multiple layers. Further, connecting wires, metal conductive 20 coatings, and/or metal reflector films may be deposited over the surface of the thin film solar cells to constitute part of the thin film solar cell assembly. The substrate may be formed of glass or a flexible film and may also be referred to as superstrate in those modules in which it faces towards the sunlight. Similarly to the wafer-based solar cell modules, the thin film solar 25 cell assemblies are further encapsulated by, laminated between, or sandwiched by, polymeric encapsulants, which are further laminated between or sandwiched by protective outer layers. In certain embodiments, the thin film solar cell assembly may be only partially encapsulated by the encapsulant, which means that only the side of the thin film solar cell assembly that is opposite from the substrate (or superstrate) is laminated to a polymeric encapsulant and then a protective outer layer. In such a construction, the thin film solar cell assembly is sandwiched by the substrate (or superstrate) and the encapsulant.

Encapsulants fulfill several important functions in the solar cell module. For example, they encase and protect the solar cell materials, which may be brittle or otherwise susceptible to physical insults, such as abrasion. In addition, in some solar cell modules the encapsulant adheres 5 the solar cells to the module's outer layers. The need for durable, transparent, easily processible encapsulants has led to the investigation of thermoplastic polymers, such as ethylene vinyl acetate (EVA), poly(vinyl butyral) (PVB), and the ionomers of ethylene acid copolymers. These materials have a long history of use as interlayers in safety glass laminates, 10 and therefore the advantages of their use as encapsulants in solar cell modules are readily apparent. These advantages include, for example, one or more of good optical properties, suitable stability, durability, ease of processability, resistance to penetration, and favorable economic factors. Moreover, those who manufacture safety glass laminates are well-suited to 15 develop the skills and equipment necessary to laminate solar cell modules that incorporate these familiar materials as encapsulants.

In addition, cross-linking reactions have been investigated as a means to further improve the stability, durability and penetration resistance of thermoplastic polymeric encapsulants. For example, Japanese 20 Unexamined Patent Publication 2003-212967 describes a thermosetting resin which, before being thermally cured, is fluid and can be formed into a thin film.

Cross-linkable ethylene vinyl acetate (EVA) has also been widely 25 used as an encapsulant material in solar cell modules due to its low cost, high clarity, low modulus, low initial viscosity, low equilibrium moisture level, and good heat resistance. The use of cross-linkable EVA as encapsulant materials is not without disadvantages, however. For example, the liberation of acetic acid by EVA can lead to corrosion and yellowing of the EVA encapsulant. Also, peroxides are often incorporated in the EVA encapsulant 30 as a reagent of the cross-linking reaction. Thus, the shelf life of the EVA encapsulant may be reduced by the peroxides' decomposition. Further disadvantageously, peroxides decompose to evolve oxygen, which may cause optical flaws such as bubbles to form in the EVA encapsulant.

Finally, these EVA sheets must be produced at comparatively low extrusion temperatures to prevent premature cross-linking, that is, cross-linking prior to lamination to form the solar cell module. Premature cross-linking may render the EVA unprocessable so that the lamination of the solar 5 cell modules cannot take place at typical temperatures. A prematurely cross-linked EVA will not flow to conform to the solar cells and other components of the solar cell module, nor will it adhere the solar cells to the outer layers of the module.

It is therefore apparent that a need exists for a cross-linkable 10 thermoplastic polymeric encapsulant material that can be processed in the melt at typical extrusion temperatures and typical lamination temperatures.

SUMMARY OF THE INVENTION

Accordingly, provided herein is a blend composition useful as a cross-linkable encapsulant layer and consisting essentially of two ethylene 15 copolymers and optionally one or more additives. The first ethylene copolymer comprises copolymerized units of ethylene, optionally a first olefin having the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and a second olefin having the formula $\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$. At least a portion of the carboxylic acid groups in 20 the second olefin have been neutralized to form carboxylate salts. The second ethylene copolymer consists essentially of copolymerized units of ethylene, optionally a first olefin having the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and a third olefin having the formula $\text{CH}_2=\text{C}(\text{R}^4)\text{D}$. R^1 , R^3 and R^4 represent 25 hydrogen or an alkyl group; R^2 represents an alkyl group; and D represents a moiety containing an epoxy group. Further provided are solar cell modules comprising the encapsulant layer. The encapsulant layer comprises the blend composition or the product of cross-linking the blend composition, in which some acid groups of the second olefin have reacted with some epoxy groups of the third olefin.

These and various other advantages and features of novelty that 30 characterize the invention are pointed out with particularity in the claims annexed hereto and forming a part hereof. For a better understanding of the invention, its advantages, and the objects obtained by its use, however, reference should be made to the drawings which form a further part hereof,

and to the accompanying descriptive matter, in which there is illustrated and described a preferred embodiment of the invention.

BRIEF DESCRIPTION OF DRAWINGS

5 FIG. 1 is a cross-sectional view of a solar cell module, not drawn to scale.

FIG. 2 is a cross-sectional view of a second solar cell module, not drawn to scale.

10 FIG. 3 is a cross-sectional view of a third solar cell module, not drawn to scale.

DETAILED DESCRIPTION OF THE INVENTION

The following definitions apply to the terms as used throughout this specification, unless otherwise limited in specific instances.

15 Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. In case of conflict, the specification, including definitions, will control.

20 As used herein, the terms "comprises," "comprising," "includes," "including," "containing," "characterized by," "has," "having" or any other variation thereof, are intended to cover a non-exclusive inclusion. For example, a process, method, article, or apparatus that comprises a list of elements is not necessarily limited to only those elements but may include other elements not expressly listed or inherent to such process, method, 25 article, or apparatus.

30 The transitional phrase "consisting of" excludes any element, step, or ingredient not specified in the claim, closing the claim to the inclusion of materials other than those recited except for impurities ordinarily associated therewith. When the phrase "consists of" appears in a clause of the body of a claim, rather than immediately following the preamble, it limits only the element set forth in that clause; other elements are not excluded from the claim as a whole.

The transitional phrase "consisting essentially of" limits the scope of a claim to the specified materials or steps and those that do not materially

affect the basic and novel characteristic(s) of the claimed invention. A 'consisting essentially of' claim occupies a middle ground between closed claims that are written in a 'consisting of' format and fully open claims that are drafted in a 'comprising' format. Optional additives as defined herein, at 5 levels that are appropriate for such additives, and minor impurities are not excluded from a composition by the term "consisting essentially of".

When a composition, a process, a structure, or a portion of a composition, a process, or a structure, is described herein using an open-ended term such as "comprising," unless otherwise stated the description 10 also includes an embodiment that "consists essentially of" or "consists of" the elements of the composition, the process, the structure, or the portion of the composition, the process, or the structure.

The term "substantially free", as used herein with respect to a composition and a component, refers to a composition that includes no more 15 than an adventitious amount of the component. Stated alternatively, the composition includes no added amount of the component, only the amount that is commonly present in the raw materials from which the composition is produced. In some commercially available materials, the level of adventitious components is less than less than 2.5%, 1.0%, less than 0.5%, 20 or less than 0.1% by weight, based on the weight of the commercially available material.

The articles "a" and "an" may be employed in connection with various elements and components of compositions, processes or structures described herein. This is merely for convenience and to give a general 25 sense of the compositions, processes or structures. Such a description includes "one or at least one" of the elements or components. Moreover, as used herein, the singular articles also include a description of a plurality of elements or components, unless it is apparent from a specific context that the plural is excluded.

30 The term "or", as used herein, is inclusive; that is, the phrase "A or B" means "A, B, or both A and B". More specifically, a condition "A or B" is satisfied by any one of the following: A is true (or present) and B is false (or not present); A is false (or not present) and B is true (or present); or both A

and B are true (or present). Exclusive "or" is designated herein by terms such as "either A or B" and "one of A or B", for example.

The term "about" means that amounts, sizes, formulations, parameters, and other quantities and characteristics are not and need not be exact, but may be approximate and/or larger or smaller, as desired, reflecting tolerances, conversion factors, rounding off, measurement error and the like, and other factors known to those of skill in the art. In general, an amount, size, formulation, parameter or other quantity or characteristic is "about" or "approximate" whether or not expressly stated to be such.

In addition, the ranges set forth herein include their endpoints unless expressly stated otherwise. Further, when an amount, concentration, or other value or parameter is given as a range, one or more preferred ranges or a list of upper preferable values and lower preferable values, this is to be understood as specifically disclosing all ranges formed from any pair of any upper range limit or preferred value and any lower range limit or preferred value, regardless of whether such pairs are separately disclosed. The scope of the invention is not limited to the specific values recited when defining a range.

When materials, methods, or machinery are described herein with the term "known to those of skill in the art", "conventional" or a synonymous word or phrase, the term signifies that materials, methods, and machinery that are conventional at the time of filing the present application are encompassed by this description. Also encompassed are materials, methods, and machinery that are not presently conventional, but that will have become recognized in the art as suitable for a similar purpose.

Unless stated otherwise, all percentages, parts, ratios, and like amounts, are defined by weight.

As used herein, the term "copolymer" refers to polymers comprising copolymerized units resulting from copolymerization of two or more comonomers. In this connection, a copolymer may be described herein with reference to its constituent comonomers or to the amounts of its constituent comonomers, for example "a copolymer comprising ethylene and 18 weight % of acrylic acid", or a similar description. Such a description may be considered informal in that it does not refer to the comonomers as

copolymerized units; in that it does not include a conventional nomenclature for the copolymer, for example International Union of Pure and Applied Chemistry (IUPAC) nomenclature; in that it does not use product-by-process terminology; or for another reason. As used herein, however, a description 5 of a copolymer with reference to its constituent comonomers or to the amounts of its constituent comonomers means that the copolymer contains copolymerized units (in the specified amounts when specified) of the specified comonomers. It follows as a corollary that a copolymer is not the product of a reaction mixture containing given comonomers in given 10 amounts, unless expressly stated in limited circumstances to be such. The term “terpolymer” refers to polymers consisting essentially of three comonomers.

The terms “epoxy group”, “ethylene oxide group” and “oxirane ring” are synonymous and used interchangeably herein to refer to a substituted or 15 unsubstituted group having the formula -CROCR₂, wherein the oxygen atom is bound to both carbons and the carbons are bound to each other. When the R groups are hydrogen atoms, the ethylene oxide group is unsubstituted. The ethylene oxide group may be singly or multiply substituted. Stated alternatively, one, two or three of the R groups may be other than hydrogen 20 atoms.

The terms “alkyl group” and “alkylene group”, as used herein alone or in combined form, such as, for example, “alkoxy group”, refer to saturated hydrocarbon groups that have from 1 to 8 carbon atoms and that may be branched or unbranched. An alkyl group has one bond to a carbon atom 25 available for substitution, and an alkylene group has two bonds to one or more carbon atoms available for substitution.

The term “ionomer”, as used herein, refers to a polymer that comprises ionic groups that are carboxylate salts, for example, ammonium carboxylates, alkali metal carboxylates, alkaline earth carboxylates, 30 transition metal carboxylates and/or combinations of such carboxylates. Such polymers are generally produced by partially or fully neutralizing the carboxylic acid groups of precursor or parent polymers that are acid copolymers, as defined herein, for example by reaction with a base. An example of an ionomer as used herein is a zinc ionomer, for example a

copolymer of ethylene and methacrylic acid wherein all or a portion of the carboxylic acid groups of the copolymerized methacrylic acid units are in the form of zinc carboxylates.

Finally, the term "solar cell" as used herein includes any article which can convert light into electrical energy. Solar cells useful in the invention include, but are not limited to, wafer-based solar cells (e.g., c-Si or mc-Si based solar cells), thin film solar cells (e.g., a-Si, μ c-Si, CdTe, or Cl(G)S based solar cells), and organic solar cells.

Provided herein is a solar cell module that comprises (A) at least one encapsulant layer comprising a cross-linked or cross-linkable blend composition of Ethylene Copolymer 1 and Ethylene Copolymer 2 and B) a solar cell assembly comprising one or a plurality of solar cells.

Ethylene Copolymer 1 is a copolymer comprising copolymerized units of ethylene, optionally of a first olefin of the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and of a second olefin of the formula $\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$, wherein R^1 is hydrogen or an alkyl group; R^2 is an alkyl group, or R^2 is an alkyl group substituted with an $-\text{OH}$ group, such as a hydroxyethyl group, or R^2 is an alkyl group substituted with an alkoxy group, such as a methoxyethyl or an ethoxy ethyl group; and R^3 is hydrogen or an alkyl group.

Suitable first olefins having the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$ include, without limitation, methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate, butyl acrylate, and butyl methacrylate. Preferably, the first olefin having the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$ is *n*-butyl acrylate, methyl acrylate or *iso*-butyl acrylate. Suitable second olefins having the formula $\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$ include, without limitation, acrylic acids and methacrylic acids.

In addition, the Ethylene Copolymer 1 may optionally further comprise other suitable additional comonomers, such as unsaturated carboxylic acids having 2 to 10, or preferably 3 to 8 carbons, or derivatives thereof. Suitable acid derivatives include acid anhydrides, amides, and esters. Esters are preferred. Specific examples of preferred esters of unsaturated carboxylic acids include, but are not limited to, methyl acrylates, methyl methacrylates, ethyl acrylates, ethyl methacrylates, propyl acrylates, propyl methacrylates, isopropyl acrylates, isopropyl methacrylates, butyl acrylates, butyl

methacrylates, isobutyl acrylates, isobutyl methacrylates, tert-butyl acrylates, tert-butyl methacrylates, octyl acrylates, octyl methacrylates, undecyl acrylates, undecyl methacrylates, octadecyl acrylates, octadecyl methacrylates, dodecyl acrylates, dodecyl methacrylates, 2-ethylhexyl acrylates, 2-ethylhexyl methacrylates, isobornyl acrylates, isobornyl methacrylates, lauryl acrylates, lauryl methacrylates, 2-hydroxyethyl acrylates, 2-hydroxyethyl methacrylates, glycidyl acrylates, glycidyl methacrylates, poly(ethylene glycol)acrylates, poly(ethylene glycol)methacrylates, poly(ethylene glycol) methyl ether acrylates, 10 poly(ethylene glycol) methyl ether methacrylates, poly(ethylene glycol) behenyl ether acrylates, poly(ethylene glycol) behenyl ether methacrylates, poly(ethylene glycol) 4-nonylphenyl ether acrylates, poly(ethylene glycol) 4-nonylphenyl ether methacrylates, poly(ethylene glycol) phenyl ether acrylates, poly(ethylene glycol) phenyl ether methacrylates, vinyl acetates, 15 vinyl propionates, and combinations of two or more thereof. Examples of preferred comonomers include, but are not limited to, methyl (meth)acrylates, butyl (meth)acrylates, vinyl acetates, and combinations of two or more thereof.

Neither the first olefin nor the second olefin nor the other suitable 20 additional comonomer, however, is a dicarboxylic acid or a diester, monoester or anhydride of a dicarboxylic acid. Dicarboxylic acids include maleic acid, fumaric acid, itaconic acid, citraconic acid, mesaconic acid, and the like. In addition, Ethylene Copolymer 1 preferably does not incorporate other comonomers in any significant amount. Stated alternatively, it is 25 preferable that Ethylene Copolymer 1 consist essentially of copolymerized residues of ethylene and the second olefin, or that Ethylene Copolymer 1 consist essentially of copolymerized residues of ethylene, the optional first olefin and the second olefin.

Ethylene Copolymer 1 comprises about 5 to about 40 wt%, or about 30 10 to about 35 wt%, or about 10 to about 30 wt% of copolymerized residues of the first olefin of formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, when the first olefin is present. Ethylene Copolymer 1 further comprises about 2 to about 30 wt%, or about 5 to about 20 wt%, or about 5 to about 15 wt%, based on the total weight of the copolymer, of copolymerized residues of the olefin of the formula

$\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$. The remainder of Ethylene Copolymer 1 comprises copolymerized residues of ethylene and up to about 5 wt% of optional additional comonomers, if any. These weight percentages are based on the total weight of Ethylene Copolymer 1.

5 In fully protonated form, Ethylene Copolymer 1 has a melt flow rate or melt index (MFR or MI) of about 5 g/ 10 min or higher, about 10 g/10 min or higher, or about 30 to about 1000 g/10 min, or about 60 g/10 min or higher, or about 100 to about 500 g/10 min, as determined in accordance with ASTM D1238 at 190°C and under a weight of 2.16 kg.

10 Ethylene Copolymer 1 is an ionomer. In particular, at least a portion of the carboxylic acid groups of Ethylene Copolymer 1 are neutralized to form carboxylate salts. Ionomers and methods of synthesizing ionomers have been described at length elsewhere, for example in U.S. Patent No. 5,028,674, and U.S. Patent Appln. No. 12/610,678, filed on November 2, 15 2009, and the references cited therein. To obtain the ionomers used herein, the precursor acid copolymers may be neutralized by any conventional procedure, such as those described in U.S. Patent Nos. 3,404,134 and 6,518,365.

20 Preferred neutralization levels are about 10% to about 90%, about 20% to about 60%, or about 15% to about 30%. Neutralization level is expressed as the weight percentage of the acid present in the ionomer that is neutralized. For example, if the ionomer contains 15 wt% of methacrylic acid and the neutralization level is 25%, then 3.75 wt% of the acid groups are neutralized, based on the total weight of the copolymer.

25 In addition, Ethylene Copolymer 1 when neutralized has a melt flow rate or melt index (MFR or MI) of about 1 g/10 min or higher, or about 5 to about 500 g/10 min, or about 10 to about 500 g/10 min, as determined in accordance with ASTM D1238 at 190°C and under a weight of 2.16 kg.

30 Any stable cation and any combination of two or more stable cations are believed to be suitable as counterions to the carboxylate groups in the ionomer. Divalent cations, such as cations of alkaline earth metals and some transition metals, are preferred. Zinc is a preferred divalent cation. Still more preferably, Ethylene Copolymer 1 is a zinc ionomer in which about 10% to about 90%, about 20% to about 60%, or about 15% to about 30% of

the hydrogen atoms of the carboxylic acid groups of the precursor acid are replaced by a charge-equivalent amount of zinc cations.

In one particular example, Ethylene Copolymer 1 is a zinc ionomer of a copolymer of ethylene/*n*-butyl acrylate/acrylic acid, such as those available 5 from E. I. du Pont de Nemours and Company, Wilmington, DE ("DuPont") under the trademark Surlyn®.

Ethylene Copolymer 2 is a copolymer comprising copolymerized units of ethylene, optionally of the first olefin of the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and of a third olefin of the formula $\text{CH}_2=\text{C}(\text{R}^4)\text{D}$, wherein R^4 is hydrogen or an 10 alkyl group; D is selected from $-\text{CO}_2\text{R}^5$, $-\text{CO}_2\text{R}^6-\text{R}^5$, $-\text{R}^6-\text{R}^5$, $-\text{O}-\text{R}^5$, and $-\text{R}^5$; and wherein R^6 is an alkylene group and R^5 is a moiety containing an epoxy 15 group, such as a glycidyl group, a 1,2-cyclohexenyl oxide group, or a 1,2-epoxy group. Like the first and the second olefins and the optional additional comonomers, the third olefin is also not a dicarboxylic acid or a di-ester, mono-ester or anhydride of a dicarboxylic acid.

In addition, the Ethylene Copolymer 2 may optionally further comprise other suitable additional comonomers, as described above with respect to Ethylene Copolymer 1. Preferably, however, Ethylene Copolymer 2 preferably does not contain other comonomers in any significant amount.

20 Stated alternatively, it is preferable that Ethylene Copolymer 2 consist essentially of copolymerized residues of ethylene and the third olefin, or that Ethylene Copolymer 2 consist essentially of copolymerized residues of ethylene, the optional first olefin and the third olefin.

Whether the first olefin is present in Ethylene Copolymer 2 is 25 independent of whether it is also present in Ethylene Copolymer 1, and vice versa. Moreover, when the first olefin is present in both of Ethylene Copolymers 1 and 2, the olefin itself may be the same or different in each of the copolymers. For example, Ethylene Copolymer 1 may be a copolymer of ethylene/*n*-butyl acrylate/acrylic acid and Ethylene Copolymer 2 may be a 30 copolymer of ethylene/*n*-butyl acrylate/glycidyl methacrylate. Alternatively, Ethylene Copolymer 1 may be a copolymer of ethylene/methyl acrylate/acrylic acid and Ethylene Copolymer 2 may be a copolymer of ethylene/ethyl acrylate/glycidyl methacrylate.

Ethylene Copolymer 2 comprises about 3 to about 15 wt%, or about 3 to about 10 wt%, or about 4 to about 7 wt% of copolymerized residues of the third olefin of the formula $\text{CH}_2=\text{C}(\text{R}^4)\text{-D}$. It may optionally further comprise up to about 40 wt%, or about 5 to about 40 wt%, or about 10 to about 40 wt%, or about 20 to about 40 wt%, or about 20 to about 35 wt% of copolymerized residues of the first olefin of the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$. The remainder of Ethylene Copolymer 2 comprises copolymerized residues of ethylene and up to about 5 wt% of optional additional comonomers, if any. These weight percentages are based on the total weight of Ethylene Copolymer 2.

Preferably, Ethylene Copolymer 2 consists essentially of copolymerized residues of ethylene and the third olefin. Also preferably, Ethylene Copolymer 2 consists essentially of copolymerized residues of ethylene, the optional first olefin and the third olefin. In one particular example, the Ethylene Copolymer 2 is a copolymer of ethylene/*n*-butyl acrylate/glycidyl methacrylate, such as those available from DuPont under the trademark Elvaloy®. In another particular example, Ethylene Copolymer 2 is a copolymer of ethylene and glycidyl methacrylate.

In addition, Ethylene Copolymer 2 has a melt flow rate of about 5 to about 300 or about 5 to about 100 g/10 min, as determined in accordance with ASTM D1238 at 190°C and under a weight of 2.16 kg.

The ratio of the Ethylene Copolymer 1 and the Ethylene Copolymer 2 in the blend composition ranges from about 90:10 to about 10:90, or about 80:20 to about 20:80, or about 70:30 to about 30:70, or about 60:40 to about 40:60, or about 45:55 to 55:45, or the ratio is about 50:50 by weight based on the total weight of Ethylene Copolymer 1 and Ethylene Copolymer 2 in the blend composition.

The mole ratio of carboxylic acid and carboxylate groups in Ethylene Copolymer 1 to epoxy groups in Ethylene Copolymer 2 is preferably about 10:1 to 1:10, about 5:1 to 1:5, about 3:1 to 1:3, or about 2 to 1.

The blend composition of Ethylene Copolymer 1 and Ethylene Copolymer 2 can be prepared by any suitable process, such as melt blending, compounding, and extrusion to pelletized blend. Preferably, no water, no other solvents such as organic solvents and aromatic solvents,

and no plasticizers are added to the Ethylene Copolymer 1 and Ethylene Copolymer 2 during the blending process. Stated alternatively, in a preferred process, neat Ethylene Copolymer 1 is combined with neat Ethylene Copolymer 2 in a melt process to form a neat blend composition.

5 At no time during the preferred process do Ethylene Copolymers 1 and 2 include more than adventitious amounts of water, other solvent, or plasticizer.

During the blending and extruding processes, the temperature of the blend is preferably maintained at or below about 120°C, to prevent 10 premature cross-linking. More preferably, the temperature of the blend is maintained at or below about 110°C, 105°C or 100°C. At temperatures of about 100°C or higher, the carboxylate group in Ethylene Copolymer 1 reacts with the epoxy group in Ethylene Copolymer 2 to form a blend composition that is cross-linked. Without wishing to be bound by theory, it is 15 believed that the cross-linking reaction between an ionomer comprising acrylic acid residues and a copolymer comprising residues of glycidyl methacrylate operates by a mechanism in which a carboxylate group of the ionomer reacts to open an epoxide ring to form a hydroxyalkyl ester linkage.

Those of skill in the art are aware that the cross-linking reaction may 20 well proceed at temperatures that are below 120°C, or below 100°C. The kinetics of the reaction, however, are such that the blend composition may be held at 120°C or less for a significant amount of time (up to about 15 minutes) without cross-linking to the extent that the blend composition becomes intractable for further processing.

25 In addition, those of skill in the art are able to determine an appropriate level of cross-linking based on the physical properties that are desired in the cross-linked encapsulant layer. For example, higher levels of cross-linking are correlated with a higher flex modulus, better high temperature adhesion, lower melt indices, and better heat resistance.

30 Those of skill in the art are also aware that the time required to obtain a desired level of cross-linking depends directly on the concentration of carboxylic acid groups and epoxy groups. Likewise, the time required to obtain a desired level of cross-linking depends inversely on the temperature at which the cross-linking reaction is carried out, and also depends inversely

or in another negative logarithmic relationship on the melt index of the polymer blend.

Although the discussion above indicates that the cross-linking reaction requires heat, the reaction may also be carried out using catalysis, 5 or by using a combination of heat and catalysis. Both acid and base catalysts are suitable, including, without limitation, tertiary amines, phosphoric acid, Lewis acids such as boron trifluoride etherate ($\text{BF}_3 \cdot \text{Et}_2\text{O}$) and aluminum trichloride (AlCl_3), and substituted pyridines. Because acids can be corrosive, basic catalysts are preferred, and substituted pyridines 10 such as 4-dimethylamino-pyridine are particularly preferred. When present, the amount of the catalyst is preferably about 20 to about 200 ppm, based on the total weight of the blend.

The effect of the catalyst on reaction times and reaction temperatures is known to those of skill in the art. Briefly, however, when a catalyst is 15 present, the cross-linking reaction will be completed in a shorter time at a given reaction temperature, compared to a blend composition that includes the same Ethylene Copolymers 1 and 2 but no catalyst. Alternatively, the cross-linking reaction can be completed at a lower temperature, again compared to a blend composition that includes the same Ethylene 20 Copolymers 1 and 2 but no catalyst. Those of skill in the art are capable of adjusting the amount of catalyst to attain the desired reaction temperature and time.

In addition to Ethylene Copolymer 1 and Ethylene Copolymer 2, the blend composition may further include one or more suitable additive(s) that 25 are known in the art. Such additives include, but are not limited to, plasticizers, processing aids, flow enhancing additives, lubricants, pigments, dyes, optical brighteners, flame retardants, impact modifiers, nucleating agents, antiblocking agents (e.g., silica), thermal stabilizers, hindered amine light stabilizers (HALS), UV absorbers, UV stabilizers, dispersants, 30 surfactants, chelating agents, coupling agents, adhesives, primers, reinforcement additives (e.g., glass fiber), and combinations of two or more thereof. As is discussed above, plasticizers are preferably not included in the blend composition. Additives are described in detail in the *Kirk-Othmer*

Encyclopedia of Chemical Technology, 5th Edition, John Wiley & Sons (New Jersey, 2004).

Suitable additives may be present in the blend composition at a level of about 0.01 to about 15 wt%, or about 0.01 to about 10 wt%, or about 0.01 to 5 wt%, or about 0.01 to 1 wt%, in total, based on the total weight of the blend composition. At these levels, the additives do not detract from the basic and novel characteristics of the blend composition, nor do they significantly adversely affect the performance of encapsulant layer comprising the blend composition.

The incorporation of the optional additives, if any, into the blend composition can be carried out by any known process, such as, for example, by dry blending, by extruding a mixture of the various constituents, by the conventional masterbatch technique, or the like. See, again, the *Kirk-Othmer Encyclopedia*. Once more, it is important to avoid carrying out these procedures under conditions that will lead to the cross-linking of the blend composition.

Four notable additives that are useful in the blend composition are thermal stabilizers, UV absorbers, hindered amine light stabilizers, and silane coupling agents. First, thermal stabilizers have been described extensively. Any known thermal stabilizer may be suitable for use in the multilayer sheet. Preferred general classes of thermal stabilizers include, but are not limited to, phenolic antioxidants, alkylated monophenols, alkylthiomethylphenols, hydroquinones, alkylated hydroquinones, tocopherols, hydroxylated thiadiphenyl ethers, alkylidenebisphenols, O-, N- and S-benzyl compounds, hydroxybenzylated malonates, aromatic hydroxybenzyl compounds, triazine compounds, aminic antioxidants, aryl amines, diaryl amines, polyaryl amines, acylaminophenols, oxamides, metal deactivators, phosphites, phosphonites, benzylphosphonates, ascorbic acid (vitamin C), hydroxylamines, nitrones, thiosynergists, benzofuranones, indolinones, and the like and mixtures thereof. The blend composition may contain any effective amount of thermal stabilizers. Use of a thermal stabilizer is optional and in some instances is not preferred. When thermal stabilizers are used, they may be present in the blend composition at a level

of at least about 0.05 wt% and up to about 10 wt%, or up to about 5 wt%, or up to about 1 wt%, based on the total weight of the blend composition.

UV absorbers can be used and have also been extensively described. Any known UV absorber may be suitable for use in the blend composition.

5 Preferred general classes of UV absorbers include, but are not limited to, benzotriazole derivatives, hydroxybenzophenones, hydroxyphenyl triazines, esters of substituted and unsubstituted benzoic acids, and the like and mixtures thereof. The blend composition may contain any effective amount of UV absorbers. Use of a UV absorber is optional and in some instances is not preferred. When UV absorbers are utilized, they may be present in the blend composition at a level of at least about 0.05 wt%, and up to about 10 wt%, or up to about 5 wt%, or up to about 1 wt%, based on the total weight of the blend composition.

10

15 Hindered amine light stabilizers (HALS) can be used and are also well known in the art. Generally, hindered amine light stabilizers are secondary, tertiary, acetylated, N-hydrocarbyloxy substituted, hydroxyl-substituted N-hydrocarbyloxy substituted, or other substituted cyclic amines which are characterized by a substantial amount of steric hindrance, generally derived from aliphatic substitution on the carbon atoms adjacent to the amine function. The blend composition may contain any effective amount of hindered amine light stabilizers. Use of hindered amine light stabilizers is optional and in some instances is not preferred. When hindered amine light stabilizers are used, they may be present in the blend composition at a level of at least about 0.05 wt%, and up to about 10 wt%, or up to about 5 wt%, or up to about 1 wt%, based on the total weight of the blend composition.

20

25

30 Examples of silane coupling agents that are useful in the blend compositions include, but are not limited to, γ -chloropropylmethoxysilane, vinyltrimethoxysilane, vinyltriethoxysilane, vinyltris(β -methoxyethoxy) silane, γ -vinylbenzylpropyltrimethoxysilane, N- β -(N-vinylbenzylaminoethyl)- γ -aminopropyltrimethoxysilane, γ -methacryloxypropyltrimethoxysilane, vinyltriacetoxy silane, γ -glycidoxypolytrimethoxysilane, γ -glycidoxypoly triethoxysilane, β -(3,4-epoxycyclohexyl)ethyltrimethoxysilane, vinyltrichlorosilane, γ -mercaptopropylmethoxysilane, γ -aminopropyltriethoxysilane, N- β -(aminoethyl)- γ -aminopropyltrimethoxysilane, and mixtures of two or more

thereof. Silane coupling agents containing glycidoxyl groups, such as γ -glycidoxylpropyltrimethoxysilane, are preferred. The silane coupling agents are preferably incorporated in the blend composition at a level of about 0.01 to about 5 wt%, or about 0.05 to about 1 wt%, based on the total weight of

5 the blend composition.

The encapsulant layer used in the solar cell module may be derived from a sheet comprising the blend composition. The sheet may be in a single layer or in multilayer form. The term "single layer" refers to sheets that are made of or that consist essentially of the blend composition described above. When in a multilayer form, the sheet comprises sub-layers, and at least one of the sub-layers is made of or consists essentially of the blend composition, while the other sub-layer(s) may be made of or comprise any other suitable polymeric material(s), such as, for example, copolymers of α -olefins and α,β -ethylenically unsaturated carboxylic acids (i.e., acid copolymers), partially neutralized ionic acid copolymers (i.e., ionomers), ethylene/vinyl acetate copolymers, poly(vinyl acetals) (including acoustic grade poly(vinyl acetals)), polyurethanes, polyvinylchlorides, polyethylenes (e.g., linear low density polyethylenes), polyolefin block copolymer elastomers, copolymers of α -olefins and α,β -ethylenically unsaturated carboxylic acid esters (e.g., ethylene methyl acrylate copolymers and ethylene butyl acrylate copolymers), silicone elastomers, epoxy resins, and combinations of two or more thereof.

The total thickness of the sheet comprising the blend composition may range from about 1 to about 120 mils (about 0.025 to about 3 mm), or about 10 to about 90 mils (about 0.25 to about 2.3 mm), or about 15 to about 60 mils (about 0.38 to about 1.5 mm), or about 20 to about 60 mils (about 0.51 to about 1.5 mm), or about 20 to about 45 mils (about 0.51 to about 1.14 mm). When the sheet comprising the blend composition is in a multilayer form, the inner sub-layer comprising the blend composition may have a thickness ranging from about 10 to about 30 mils (about 0.25 to about 0.76 mm) while the surface sub-layer comprising the blend composition may have a thickness of about 1 to about 5 mils (about 0.025 to about 0.12 mm).

The sheet comprising the blend composition may have a smooth or rough surface on one or both sides. Preferably, the sheet has rough surfaces on both sides to facilitate deaeration during the lamination process. Rough surfaces can be created by mechanically embossing or by melt fracture during extrusion of the sheets followed by quenching so that surface roughness is retained during handling. The surface pattern can be applied to the sheet through well-known, common art processes. For example, the extruded sheet may be passed over a specially prepared surface of a die roll positioned in close proximity to the exit of the extruder die. This imparts the desired surface characteristics to one side of the molten polymer exiting the die. Thus, when the surface of such a die roll has minute peaks and valleys, it will impart a rough surface to the side of the polymer sheet that passes over the roll, and the rough surface will generally conform respectively to the valleys and peaks of the roll surface. Such die rolls are described in, e.g., U.S. Patent No. 4,035,549 and U.S. Patent Publication No. 2003/0124296.

The sheets comprising the blend composition may be produced by any suitable process. For example, the sheets may be formed by solution casting or dip coating. Preferred are melt processes such as cast film extrusion, compression molding, injection molding, lamination, blown film processes, extrusion coating, tandem extrusion coating, melt extrusion casting, melt coextrusion casting, melt extrusion coating, blown film processes, tandem melt extrusion coating processes, or any suitable melt processes known to those of skill in the art.

Preferably, the melt from which the sheet is formed consists essentially of Ethylene Copolymer 1, Ethylene Copolymer 2, and optional additives, if any. Also preferably, the melt is substantially free of solvents, including water and organic solvents. More preferably, the melt is substantially free of solvents and plasticizers.

When forming the melt in preparation for the extrusion process, pellets or powders of neat Ethylene Copolymers 1 and 2 may be provided. These neat powders or pellets may be combined in a "salt and pepper" blend before melting. Alternatively, Ethylene Copolymers 1 and 2 may be pre-mixed to form pellets of the blend composition. These pellets are then

melted in preparation for the extrusion process. The additives may be added to the pellets or powders before, during, or after melting.

Again, during the blending and sheeting processes, the temperature of the ethylene copolymer blend should be maintained at or below about 5 120°C, 115°C, 110°C, 105°C or 100°C, to avoid premature cross-linking. In some extrusion processes, the temperature of the melt is held at or below about 120°C and the temperature at the extrusion die is about 135°C or higher. Exposure of the unreacted blend composition to higher temperatures for short periods of time is not expected to generate an unacceptable 10 amount of premature cross-linking.

In forming the solar cell module, the encapsulant sheet comprising the uncross-linked blend composition is laminated to the solar cell assembly. The solar cells comprised by the solar cell assembly include any article or material that can convert light into electrical energy. Solar cells useful in the 15 invention include, but are not limited to, wafer-based solar cells (e.g., c-Si or mc-Si based solar cells, as described above in the background section) and thin film solar cells (e.g., a-Si, μ c-Si, CdTe, copper indium selenide (CIS), copper-indium-gallium selenide (CIGS), light absorbing dyes, or organic semiconductor based solar cells, as described above in the background 20 section). Within the solar cell assembly, it is preferred that the solar cells be electrically interconnected or arranged in a flat plane. In addition, the solar cell assembly may further comprise electrical wirings, such as cross ribbons and bus bars.

The solar cell assembly may be bifacial. In such an embodiment, all 25 the laminating materials positioned on either side of the solar cell assembly should be sufficiently transparent to allow adequate sunlight or reflected sunlight to reach the solar cells. Alternatively, the solar cell assembly may have a front sun-facing side (which is also referred to as a front side and, when in actual use conditions, generally faces toward the sun) and a back 30 non-sun-facing side (which is also referred to as a back side and, when in actual use conditions, generally faces away from the sun). The solar cells define the boundary between the front and back sides of the solar cell assembly. In such an assembly, all the materials that are present in the laminate layers positioned in the front sun-facing side of the solar cell

assembly should have sufficient transparency to allow adequate sunlight to reach the solar cells. The materials present in the laminate layers positioned in the back non-sun-facing side of the solar cell layer need not be transparent.

5 Further in this connection, copolymers consisting of copolymerized residues of ethylene and alpha, beta-unsaturated carboxylic acids such as the second olefin may have a degree of crystallinity that is relatively high. The same is true of copolymers consisting of copolymerized residues of ethylene and epoxy-functionalized olefins such as the third olefin.

10 Crystallinity can contribute to haze and lower transmission of light. Ethylene acid copolymers that include a third comonomer that is an ester of an alpha, beta-unsaturated carboxylic acid, such as the first olefin, in general have lower levels of crystallinity. Therefore, when the blend composition described herein is used in a front encapsulant layer, it is preferred that at

15 least one of Ethylene Copolymers 1 and 2 comprise the first olefin. More preferably, both Ethylene Copolymer 1 and Ethylene Copolymer 2 comprise the first olefin.

20 The solar cell module typically comprises at least one encapsulant layer comprising the blend composition, which is laminated to the solar cell assembly. Two components that are “laminated” to each other are bonded either directly (i.e., without any additional material between the two layers) or indirectly (i.e., with additional material, such as interlayer or adhesive materials, between the two layers). In certain laminates, the encapsulant layer comprising the blend composition is directly bonded to the solar cell

25 layer.

30 Solar cell assemblies may have somewhat uneven surfaces with peaks and voids. Therefore, during the lamination process, the encapsulant sheet comprising the blend composition will melt or soften to some degree, and will typically flow around the peaks and fill the voids of the solar cell assembly. Accordingly, when the thickness of the encapsulant layer is provided herein, unless otherwise specified in limited circumstances, it is the thickness of the encapsulant layer prior to lamination. In general, however, the encapsulant layer in the final module remains at an average total thickness of about 1 to about 120 mils (about 0.025 to about 3 mm), or about

10 to about 90 mils (about 0.25 to about 2.3 mm), or about 15 to about 60 mils (about 0.38 to about 1.5 mm), or about 20 to about 60 mils (about 0.51 to about 1.5 mm), or about 20 to about 45 mils (about 0.51 to about 1.14 mm).

5 The cross-linkable blend compositions described herein as encapsulant materials have a number of advantages over cross-linkable EVA compositions. For example, the blend compositions described herein can be made into sheets at an extrusion temperature as high as about 135°C without undergoing a significant degree of cross-linking. Further, the 10 relatively low initial viscosity of the blend compositions described herein also allows the encapsulant material to fully flow around the solar cell assembly during lamination and therefore minimize cell breakage. Yet further, the incorporation of the olefin of the formula $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$ (such as *n*-butyl acrylate) as a comonomer in one or both of Ethylene Copolymers 1 and 2 15 reduces the blend compositions' crystallinity and therefore improves the clarity of the encapsulant layer.

20 The solar cell module may further comprise additional encapsulant layers comprising other polymeric materials, such as acid copolymers, ionomers, ethylene/vinyl acetate copolymers, poly(vinyl acetals) (including acoustic grade poly(vinyl acetals)), polyurethanes, poly(vinyl chlorides), polyethylenes (e.g., linear low density polyethylenes), polyolefin block 25 copolymer elastomers, copolymers of α -olefins and α,β -ethylenically unsaturated carboxylic acid esters) (e.g., ethylene methyl acrylate copolymers and ethylene butyl acrylate copolymers), silicone elastomers, epoxy resins, and combinations of two or more thereof.

30 The solar cell module may further comprise an incident layer and/or a backing layer serving as the outermost layer or layers of the module at the sun-facing side and the non-sun-facing side of the solar cell module, respectively. The incident layer and the backing layer may comprise any suitable sheet or film. Suitable sheets include, for example, glass or plastic sheets, such as polycarbonates, acrylics, polyacrylates, cyclic polyolefins (e.g., ethylene norbornene polymers), polystyrenes (preferably polystyrenes prepared in the presence of metallocene catalysts), polyamides, polyesters, fluoropolymers, or combinations of two or more thereof. In addition, metal

sheets, such as aluminum, steel, galvanized steel, or ceramic plates may be used in the backing layer.

The term "glass" includes window glass, plate glass, silicate glass, sheet glass, low iron glass, tempered glass, tempered CeO-free glass, and 5 float glass, colored glass, specialty glass (such as those containing ingredients to control solar heating), coated glass (such as those sputtered with metals (e.g., silver or indium tin oxide) for solar control purposes), low E-glass, ToroglasTM glass (Saint-Gobain N.A. Inc., Trumbauersville, PA), SolexiaTM glass (PPG Industries, Pittsburgh, PA) and StarphireTM glass 10 (PPG Industries). Such specialty glasses are described in, e.g., U.S. Patent Nos. 4,615,989; 5,173,212; 5,264,286; 6,150,028; 6,340,646; 6,461,736; and 6,468,934. It is understood, however, that the type of glass to be selected for a particular module depends on the intended use.

Suitable films for the incident layer or the backing layer comprise 15 polymers that include but are not limited to, polyesters (e.g., poly(ethylene terephthalate) and poly(ethylene naphthalate)), polycarbonate, polyolefins (e.g., polypropylene, polyethylene, and cyclic polyolefins), norbornene polymers, polystyrene (e.g., syndiotactic polystyrene), styrene-acrylate copolymers, acrylonitrile-styrene copolymers, polysulfones (e.g., 20 polyethersulfone, polysulfone, etc.), nylons, poly(urethanes), acrylics, cellulose acetates (e.g., cellulose acetate, cellulose triacetates, etc.), cellophane, silicones, poly(vinyl chlorides) (e.g., poly(vinylidene chloride)), fluoropolymers (e.g., polyvinyl fluoride, polyvinylidene fluoride, polytetrafluoroethylene, and ethylene-tetrafluoroethylene copolymers), and 25 combinations of two or more thereof. The polymeric film may be non-oriented, or uniaxially oriented, or biaxially oriented.

Specific examples of films that may be used in the solar cell module outer layers (e.g., the incident layer or the backing layer) include, but are not limited to, polyester films (e.g., poly(ethylene terephthalate) films), 30 fluoropolymer films (e.g., Tedlar[®], Tefzel[®], and Teflon[®] films available from DuPont). Metal films, such as aluminum foil, may also be used as the backing layers. Further the films used in the solar cell module outer layers may be in the form of multi-layer films, such as a fluoropolymer/ polyester/fluoropolymer multilayer film (e.g., Tedlar[®]/PET/Tedlar[®] or TPT

laminate film available from Isovolta AG of Austria or from Madico of Woburn, MA).

5 The solar cell module may further comprise other functional film or sheet layers (e.g., dielectric layers or barrier layers) embedded within the module. Such functional layers may comprise any of the above mentioned polymeric films or those that are coated with additional functional coatings. For example, poly(ethylene terephthalate) (PET) films coated with a metal oxide coating, such as those described in U.S. Patent Nos. 6,521,825 and 6,818,819 and European Patent No.1182710, may function as oxygen and 10 moisture barrier layers in the laminates.

If desired, a layer of nonwoven glass fiber (scrim) may also be included between the solar cell layers and the encapsulant layers to facilitate deaeration during the lamination process and/or to serve as reinforcement for the encapsulants. The use of such scrim layers is described in, e.g., U.S. 15 Patent Nos. 5,583,057; 6,075,202; 6,204,443; 6,320,115; and 6,323,416 and European Patent No. 0769818.

20 A special film or sheet may be included to serve both the function of an encapsulant layer and an outer layer. One example of such a special sheet is Spallshield®, available from DuPont. Furthermore, any two or more of the contiguous film or sheet layers included in the module may be supplied in the form of a pre-formed multilayer film or sheet.

25 One or both surfaces of the incident layer films and sheets, the backing layer films and sheets, the encapsulant layers and other layers incorporated within the solar cell module may optionally undergo any suitable adhesion enhancing treatment. This adhesion enhancing treatment may take any form known within the art and includes flame treatments (see, e.g., U.S. Patent Nos. 2,632,921; 2,648,097; 2,683,894; and 2,704,382), plasma treatments (see e.g., U.S. Patent No. 4,732,814), electron beam treatments, oxidation treatments, corona discharge treatments, chemical 30 treatments, chromic acid treatments, hot air treatments, ozone treatments, ultraviolet light treatments, sand blast treatments, solvent treatments, and combinations of two or more thereof.

Also, the adhesion strength may be further improved by applying an adhesive or primer coating on the surface of the laminate layer(s). For

example, U.S. Patent No. 4,865,711 describes a film or sheet with improved bondability, which has a thin layer of carbon deposited on one or both surfaces. Other examples of suitable adhesives and primers include, without limitation, silanes, poly(allyl amine) based primers (see e.g., U.S. Patent 5 Nos. 5,411,845; 5,770,312; 5,690,994; and 5,698,329), and acrylic based primers (see e.g., U.S. Patent No. 5,415,942). The adhesive or primer coating may take the form of a monolayer of the adhesive or primer and have a thickness of about 0.0004 to about 1 mil (about 0.00001 to about 10 0.03 mm), or preferably, about 0.004 to about 0.5 mil (about 0.0001 to about 0.013 mm), or more preferably, about 0.004 to about 0.1 mil (about 0.0001 to about 0.003 mm).

Referring now to the drawings, wherein like reference numerals 15 designate corresponding structure throughout the views, and referring in particular to FIG. 1, when the solar cells are derived from wafer-based, self supporting solar cell units, the solar cell module (10) may comprise, in order of position from the front sun-facing side to the back non-sun-facing side, (a) an incident layer (11), (b) a front encapsulant layer (12), (c) a solar cell assembly (13) comprised of one or more electrically interconnected solar cells, (d) a back encapsulant layer (14), and (e) a backing layer (15), wherein 20 one or both of the front and back encapsulant layers (12 and 14) comprises the cross-linkable blend composition. In such a module, it is also possible that the solar cell assembly (13) may have a smaller lateral area compared to the encapsulant layers (12 and 14) and the outer protective layers (11 and 15). In this configuration, the two encapsulant layers (12 and 14) may come 25 in contact over the peripheral edges of the solar cell assembly (13) and bond to each other, forming a seal (16) around the edges of the solar cell assembly (13).

Referring now to FIG. 2, when the solar cell module 20 is derived from thin film solar cells, it may comprise, in order of position from the front sun-facing side to the back non-sun-facing side, (a) a solar cell layer (23) comprising a superstrate (23b) and a layer of thin film solar cell(s) (23a) deposited thereon at the non-sun-facing side, (b) a (back) encapsulant layer (24) comprising the cross-linkable blend composition, and (c) a backing layer (25). Referring now to FIG. 3, another solar cell module 30 that is derived

from thin film solar cells may comprise, again in order of position from the front sun-facing side to the back non-sun-facing side, (a) a transparent incident layer (31), (b) a (front) encapsulant layer (32) comprising the cross-linkable blend composition, and (c) a solar cell layer (33) comprising a layer of thin film solar cell(s) (33a) deposited on a substrate (33b) at the sun-facing side thereof.

Once more, thin films solar cells (23a or 33a) may have a smaller lateral area than that of the superstrate (23b) or substrate (33b) and that of the encapsulant layer (24 or 32), and therefore, the encapsulant layer (24 or 10 32) may come in contact and bond with the superstrate (23b) or substrate (33b) over the peripheral edges of the thin film solar cells (23a or 33a) and form a seal (26 or 36) around the edges of the thin film solar cells (23a or 33a).

If desired, the edges of the solar cell module may be sealed to reduce 15 moisture and air intrusion that lead to potential reduction of the efficiency and lifetime of the solar cell(s). The edges may be sealed by any means disclosed within the art. Suitable edge seal materials include, but are not limited to, butyl rubber, polysulfide, silicone, polyurethane, polypropylene elastomers, polystyrene elastomers, block copolymer elastomers (such as 20 styrene-ethylene-butylene-styrene (SEBS)), and the like.

Moreover, a plurality of the solar cell modules described above may be further linked in parallel or in series to form a solar cell array, in order to produce a desired voltage and current.

Any suitable lamination process may be used to prepare the solar cell 25 modules. In general, however, processes including a step in which the blend of Ethylene Copolymer 1 and Ethylene Copolymer 2 is heated to a temperature of about 135°C or higher, or of about 140°C to about 180°C, are preferred. As is described in detail above, the cross-links between Ethylene Copolymer 1 and Ethylene Copolymer 2 form during this high-temperature 30 step, and the rate at which the reaction proceeds depends on the temperature and melt index of the blend, on the concentration of catalyst, if any, and on the concentration of the reactive monomers.

In laminates, however, the rate at which the cross-linking reaction proceeds also depends on the heat transfer rate, or, more practically, on the

structure of the laminate. For example, laminates comprising outer layers made from materials such as polycarbonate sheets, which have low heat transfer coefficients, may require heating at higher temperatures or for longer times than laminates that comprise glass outer layers, with their 5 higher heat transfer coefficients. Alternatively, compared to laminates comprising glass sheets as outer layers, laminates comprising polyester films as their outer layers may require less time or lower temperatures to achieve the desired level of crosslinking. Although polyesters may have a lower heat transfer coefficient than glass, the relative small thickness of the 10 polyester films will allow for quicker heating than the relatively thicker glass sheets.

The following specific examples of suitable lamination processes are not limiting. In one process, the component layers of the solar cell module are stacked in the desired order to form a pre-lamination assembly. The 15 assembly is then placed into a bag capable of sustaining a vacuum ("a vacuum bag"), the air is drawn out of the bag by a vacuum line or other means, the bag is sealed while the vacuum is maintained (e.g., at least about 27-28 in. Hg (689-711 mm Hg)), and the sealed bag is placed in an autoclave and the pressure is raised to about 150 to about 250 psi (about 20 11.3 to about 18.8 bar), and a temperature of about 135°C to about 180°C, or about 135°C to about 160°C, or about 135°C to about 155°C, or about 145°C to about 155°C, for about 10 to about 50 min, or about 20 to about 45 min, or about 20 to about 40 min, or about 25 to about 35 min. A vacuum ring may be substituted for the vacuum bag. One type of suitable vacuum 25 bag is described in U.S. Patent No. 3,311,517. Following the heat and pressure cycle, the air in the autoclave is cooled without adding additional air to maintain pressure in the autoclave. After about 20 min of cooling, the excess air pressure is vented and the laminates are removed from the autoclave.

30 Alternatively, the pre-lamination assembly may be heated in an oven at about 80°C to about 120°C, or about 90°C to about 100°C, for about 20 to about 40 min, and thereafter, the heated assembly may be passed through a set of nip rolls so that the air in the void spaces between the individual layers

is squeezed out, and the edge of the assembly sealed. The assembly at this stage is referred to as a pre-press.

The pre-press may then be placed in an air autoclave where the temperature is raised to about 135°C to about 180°C, or about 135°C to 5 about 160°C at a pressure of about 100 to about 300 psi (about 6.9 to about 20.7 bar), or preferably about 200 psi (13.8 bar). These conditions are maintained for about 15 to about 60 min, or about 20 to about 50 min, after which the air is cooled while no further air is introduced to the autoclave. After about 20 to about 40 min of cooling, the excess air pressure is vented 10 and the laminated products are removed from the autoclave.

The solar cell modules may also be produced through non-autoclave processes. Such non-autoclave processes are described, e.g., in U.S. Patent Nos. 3,234,062; 3,852,136; 4,341,576; 4,385,951; 4,398,979; 15 5,536,347; 5,853,516; 6,342,116; and 5,415,909; in U.S. Patent Publication No. 2004/0182493; in European Patent No. 1235683 B1; and in PCT Patent Publication Nos. WO91/01880 and WO03/057478. Generally, the non-autoclave processes include heating the pre-lamination assembly and the application of vacuum, pressure or both. For example, the assembly may be successively passed through heating ovens and nip rolls.

20

The following examples are provided to describe the invention in further detail. These examples, which set forth a preferred mode presently contemplated for carrying out the invention, are intended to illustrate and not to limit the invention.

25

EXAMPLES

All melt indices (MI) and melt flow rates (MFR) reported herein were determined in accordance with ASTM D1238 at 190°C and 2.16 kg, and are reported in units of g/10 min, unless otherwise specified in limited 30 circumstances.

Example 1

Several 300-gram blends of a sodium ionomer (ethylene/methacrylic acid dipolymer, 11 weight % MAA, 37 % neutralized, Na^+ cation, MI of ionomer 10g/10 min) and an ethylene copolymer (66.75 wt% ethylene/28

wt% n-butyl acrylate/5.25 wt% glycidyl methacrylate, MI of 12 g/10 min) were prepared in a Brabender mixer at 120 °C at 50 rpm for 5 minutes. There was a significant initial MI reduction of the blends (125 °C MI test), especially at the higher sodium ionomer levels, showing that reaction between the two blend components did occur. Table 1, below, shows the comparison of the measured MI to the predicted MI. The predictions were made according to the blend rule, which assumes no reaction between the blend components.

5

Table 1

Blend wt% sodium ionomer/ wt% ethylene copolymer	MI Measured	MI Predicted
10 / 90	12	10.75
20 / 80	9	11.8
30 / 70	7.17	11.6
40 / 60	2.436	11.36
50 / 50	0.812	11.15
60 / 40	0	10.95

10

15

The melt flow of each blend (in a 10 minute period) was measured in a melt indexer with a 2160 gram weight at several different temperatures after being held at the specific temperature in the melt indexer for 10 minutes. As shown in Table 2 below, the blends retained some flow when heated for 10 minutes at temperatures up to 170 °C. If the blend were fully crosslinked, the predicted melt flow would be zero.

Table 2

Temper- ature	10%ionomer/ 90% ECP*	20%ionomer/ 80% ECP	30%ionomer/ 70% ECP	40%ionomer/ 60% ECP	50%ionomer/ 50%ECP	60%ionomer/ 40% ECP
130°C	1.68	1.33	1.12	0.38	0.4	n/a*
140°C	2.3	1.83	1.58	0.52	0.31	0.16
150°C	3.34	2.24	1.5	0.6	0.37	n/a
160°C	4.32	2.91	2.04	0.7	0.3	0.17
170°C	4.65	2.45	2.01	0.55	0.1	0.11

* "ECP" means "ethylene copolymer"; "n/a" means "not available".

Example 2

Three hundred grams of a blend of zinc ionomer (85 wt% ethylene/15 wt% methacrylic acid with 22% of the methacrylic groups neutralized, Zn²⁺ cation, MI = 14) and ethylene copolymer (66.75 wt% ethylene/28 wt% n-butyl acrylate/5.25 wt% glycidyl methacrylate, MI = 12) were prepared in a Brabender mixer at 120 °C at 50 rpm for 5 minutes. The blend composition was 20 wt% zinc ionomer and 80 wt% ethylene copolymer. The melt index (MI) of the blend was 4, when measured at 125°C and extrapolated to 190°C. Flow in a 10 minute period in a melt indexer with a 2160 gram weight was determined at several different temperatures after being held at the specific temperature in the melt indexer for 10 minutes. The results are shown in Table 3 below.

Table 3

Temp, °C	Melt Flow
130	0.6
140	0.66
150	0.35
160	0.09
170	0.0

These results show that crosslinking occurred as the temperature was raised, and the blend became completely crosslinked at 170 °C. Therefore, it is believed that a sheet made from this blend and used as a solar cell encapsulant will be completely crosslinked when laminated for 10 minutes at 170 °C.

While certain of the preferred embodiments of the present invention have been described and specifically exemplified above, it is not intended that the invention be limited to such embodiments. Rather, it is to be understood that even though numerous characteristics and advantages of the present invention have been set forth in the foregoing description, together with details of the structure and function of the invention, the disclosure is illustrative only, and changes may be made in detail, especially in matters of shape, size and arrangement of parts within the principles of the invention to the full extent indicated by the broad general meaning of the terms in which the appended claims are expressed.

WHAT IS CLAIMED IS:

1. A blend composition comprising about 10 to about 90 wt% of an Ethylene Copolymer 1 and about 10 to about 90 wt% of an Ethylene Copolymer 2, based on the total weight of the blend composition;
5 wherein said Ethylene Copolymer 1 consists essentially of copolymerized units of ethylene, optionally up to about 40 wt% of copolymerized units of a first olefin having a formula of $\text{CH}_2=\text{C}(\text{R}^1)\text{CO}_2\text{R}^2$, and about 2 to about 30 wt% of copolymerized units of a second olefin having a formula of $\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$,
10 wherein the weight percentages of the copolymerized units of the first olefin and of the second olefin are based on the total weight of said Ethylene Copolymer 1; wherein at least a portion of the carboxylic acid groups are neutralized to form carboxylate salts; wherein R^1 represents hydrogen or an alkyl group, R^2 represents an alkyl group,
15 and R^3 represents hydrogen or an alkyl group; and wherein said Ethylene Copolymer 2 consists essentially of copolymerized units of ethylene, optionally up to about 40 wt% of copolymerized units of the first olefin, and about 3 to about 15 wt% of copolymerized units of a third olefin having a formula of $\text{CH}_2=\text{C}(\text{R}^4)\text{-D}$,
20 wherein the weight percentages of the copolymerized units of the first olefin and of the third olefin are based on the total weight of said Ethylene Copolymer 2; wherein R^4 represents hydrogen or an alkyl group; wherein -D represents a moiety selected from the group consisting of $-\text{CO}_2\text{R}^5$, $-\text{CO}_2\text{R}^6\text{-R}^5$, $-\text{R}^6\text{-R}^5$, $-\text{O-R}^5$, and $-\text{R}^5$; wherein R^5 represents a moiety containing an epoxy group and R^6 represents an alkylene group;
25 with the proviso that none of said first, second or third olefins is a dicarboxylic acid or a di-ester, mono-ester or anhydride of the dicarboxylic acid.
- 30 2. The blend composition of Claim 1, wherein R^1 represents hydrogen or a methyl group, R^2 represents a butyl group, R^3 represents hydrogen or a methyl group, R^4 represents hydrogen or a methyl group, and -D is $-\text{R}^5$; or wherein the first olefin is *n*-butyl acrylate and the second

olefin is acrylic acid; or wherein the third olefin is glycidyl methacrylate.

3. A product of cross-linking the blend composition of claim 1 or claim 2, wherein at least a portion of the carboxylate groups of Ethylene Copolymer 1 are reacted with at least a portion of the epoxy groups of Ethylene Copolymer 2 to form cross-links between Ethylene Copolymer 1 and Ethylene Copolymer 2.

4. A process for making the blend composition of claim 1, comprising the steps of:

10 a) providing Ethylene Copolymer 1 and Ethylene Copolymer 2; and b) combining Ethylene Copolymer 1 and Ethylene Copolymer 2 in a melt at a temperature below 120°C.

5. A process for making a sheet consisting essentially of the blend composition of claim 1, comprising the steps of:

15 a) combining said Ethylene Copolymer 1 and said Ethylene Copolymer 2 in a melt at a temperature below 120°C; and b) forming a sheet from the melt, optionally by an extrusion process.

6. A sheet that is the product of the process of claim 5, wherein the sheet has one or more roughened surfaces; or wherein said process is an extrusion process and said extruded sheet has a thickness of from about 1 to about 120 mils (about 0.025 to about 3 mm); or wherein the extrusion process is a multilayer extrusion process, wherein the extruded sheet comprises at least one layer comprising the blend composition; or wherein the extrusion process is a multilayer extrusion process, wherein the extruded sheet comprises at least one layer comprising the blend composition, and wherein the layer comprising the blend composition is an inner layer having a thickness of from about 10 to about 30 mils (about 0.25 to about 0.76 mm), or wherein the layer comprising the blend composition is a surface layer having a thickness of about 1 to about 5 mils (about 0.025 to about 0.12 mm).

25 7. A solar cell module comprising a solar cell assembly and at least one encapsulant layer, wherein the at least one encapsulant layer consists

essentially of the blend composition of claim 1 or claim 2 or the cross-linked product of claim 3.

8. The solar cell module of claim 7, wherein the at least one encapsulant layer is directly laminated to the solar cell assembly; or wherein the solar cell assembly has a front sun-facing side and a back non-sun-facing side.

5 9. The solar cell module of Claim 8, which comprises a front encapsulant layer that is laminated to the front sun-facing side of the solar cell assembly and a back encapsulant layer that is laminated to the back non-sun-facing side of the solar cell assembly, wherein one of the front and back encapsulant layers is the at least one encapsulant layer, and wherein the other of the front and back encapsulant layers is cross-linked or uncross-linked and consists essentially of one or 10 more polymeric materials selected from the group consisting of copolymers comprising an α -olefin and an α,β -ethylenically unsaturated carboxylic acid, ionomers of copolymers comprising an α -olefin and an α,β -ethylenically unsaturated carboxylic acid, copolymers comprising ethylene and a moiety comprising an epoxy group, ethylene/vinyl acetate copolymers, poly(vinyl acetals), 15 polyurethanes, polyvinylchlorides, polyethylenes, polyolefin block copolymer elastomers, copolymers of an α -olefin and an α,β -ethylenically unsaturated carboxylic acid, silicone elastomers, epoxy resins, and combinations thereof;

20 or wherein the front and back encapsulant layers consist essentially of the blend composition or the product of cross-linking the blend composition, and wherein the blend composition of the front encapsulant layer and the blend composition of the back encapsulant layer are the same or different.

25 10. The solar cell module of claim 8 or claim 9, further comprising an incident layer, wherein the incident layer is an outermost surface layer of the module and is positioned on the front sun-facing side of the solar cell assembly, and wherein the incident layer is made of a material selected from the group consisting of (i) glass sheets, 30 (ii) polymeric sheets comprising a polymer selected from the group

consisting of polycarbonates, acrylics, polyacrylates, cyclic polyolefins, polystyrenes, polyamides, polyesters, fluoropolymers, and combinations of two or more thereof, and (iii) polymeric films comprising a polymer selected from the group consisting of polyesters, polycarbonate, polyolefins, norbornene polymers, polystyrene, styrene-acrylate copolymers, acrylonitrile-styrene copolymers, polysulfones, nylons, polyurethanes, acrylics, cellulose acetates, cellophane, poly(vinyl chlorides), fluoropolymers, and combinations of two or more thereof.

5 11. The solar cell module of any of claims 8 to 10, further comprising a backing layer, wherein the backing layer is an outermost surface layer of the module and is positioned on the back non-sun-facing side of the solar cell assembly, and wherein the backing layer is made of a material selected from the group consisting of (i) glass sheets,

10 (ii) polymeric sheets, (iii) polymeric films, (iv) metal sheets, and (v) ceramic plates, and wherein the polymeric sheets comprise a polymer selected from the group consisting of polycarbonates, acrylics, polyacrylates, cyclic polyolefins, polystyrenes, polyamides, polyesters, fluoropolymers, and combinations or two or more thereof; and the

15 polymeric films comprise a polymer selected from the group consisting of polyesters, polycarbonates, polyolefins, norbornene polymers, polystyrenes, styrene-acrylate copolymers, acrylonitrile-styrene copolymers, polysulfones, nylons, polyurethanes, acrylics, cellulose acetates, cellophanes, poly(vinyl chlorides), fluoropolymers,

20 and combinations of two or more thereof.

25 12. The solar cell module of any of claims 8 to 11, wherein the solar cells are wafer-based solar cells selected from the group consisting of crystalline silicon (c-Si) and multi-crystalline silicone (mc-Si) based solar cells and the module consists essentially of, in order of position,

30 (i) an incident layer, (ii) the front encapsulant layer, (iii) the solar cell assembly, (iv) the back encapsulant layer, and (v) a backing layer.

13. The solar cell module of any of claims 8 to 11, wherein the solar cells are thin film solar cells selected from the group consisting of amorphous silicon (a-Si), microcrystalline silicon (μ c-Si), cadmium

5 telluride (CdTe), copper indium selenide (CIS), copper indium/gallium diselenide (CIGS), light absorbing dyes, and organic semiconductor based solar cells, and wherein the solar cell module consists essentially of, in order of position, (i) an incident layer, (ii) a front encapsulant layer that is the at least one encapsulant layer comprising the blend composition or the product of cross-linking the blend composition, and (iii) the solar cell assembly, wherein the solar cell assembly further comprises a substrate upon which the thin film solar cells are deposited and the substrate is positioned such that the substrate is an outermost surface of the module and is positioned on the back non-sun-facing side of the solar cell assembly.

10 14. The solar cell module of any of claims 8 to 11, wherein the solar cells are thin film solar cells selected from the group consisting of amorphous silicon (a-Si), microcrystalline silicon (μ c-Si), cadmium telluride (CdTe), copper indium selenide (CIS), copper indium/gallium diselenide (CIGS), light absorbing dyes, and organic semiconductor based solar cells, and wherein the solar cell module consists essentially of, in order of position, (i) the solar cell assembly, (ii) a back encapsulant layer that is the at least one encapsulant layer comprising the blend composition, and (iii) a backing layer, wherein the solar cell assembly further comprises a superstrate upon which the thin film solar cells are deposited and the superstrate is positioned such that the superstrate is an outermost surface of the module on the front sun-facing side of the solar cell assembly.

15 20 25 30 35 40 45 50 55 60 65 70 75 80 85 90 95 100 105 110 115 120 125 130 135 140 145 150 155 160 165 170 175 180 185 190 195 200 205 210 215 220 225 230 235 240 245 250 255 260 265 270 275 280 285 290 295 300 305 310 315 320 325 330 335 340 345 350 355 360 365 370 375 380 385 390 395 400 405 410 415 420 425 430 435 440 445 450 455 460 465 470 475 480 485 490 495 500 505 510 515 520 525 530 535 540 545 550 555 560 565 570 575 580 585 590 595 600 605 610 615 620 625 630 635 640 645 650 655 660 665 670 675 680 685 690 695 700 705 710 715 720 725 730 735 740 745 750 755 760 765 770 775 780 785 790 795 800 805 810 815 820 825 830 835 840 845 850 855 860 865 870 875 880 885 890 895 900 905 910 915 920 925 930 935 940 945 950 955 960 965 970 975 980 985 990 995 1000 1005 1010 1015 1020 1025 1030 1035 1040 1045 1050 1055 1060 1065 1070 1075 1080 1085 1090 1095 1100 1105 1110 1115 1120 1125 1130 1135 1140 1145 1150 1155 1160 1165 1170 1175 1180 1185 1190 1195 1200 1205 1210 1215 1220 1225 1230 1235 1240 1245 1250 1255 1260 1265 1270 1275 1280 1285 1290 1295 1300 1305 1310 1315 1320 1325 1330 1335 1340 1345 1350 1355 1360 1365 1370 1375 1380 1385 1390 1395 1400 1405 1410 1415 1420 1425 1430 1435 1440 1445 1450 1455 1460 1465 1470 1475 1480 1485 1490 1495 1500 1505 1510 1515 1520 1525 1530 1535 1540 1545 1550 1555 1560 1565 1570 1575 1580 1585 1590 1595 1600 1605 1610 1615 1620 1625 1630 1635 1640 1645 1650 1655 1660 1665 1670 1675 1680 1685 1690 1695 1700 1705 1710 1715 1720 1725 1730 1735 1740 1745 1750 1755 1760 1765 1770 1775 1780 1785 1790 1795 1800 1805 1810 1815 1820 1825 1830 1835 1840 1845 1850 1855 1860 1865 1870 1875 1880 1885 1890 1895 1900 1905 1910 1915 1920 1925 1930 1935 1940 1945 1950 1955 1960 1965 1970 1975 1980 1985 1990 1995 2000 2005 2010 2015 2020 2025 2030 2035 2040 2045 2050 2055 2060 2065 2070 2075 2080 2085 2090 2095 2100 2105 2110 2115 2120 2125 2130 2135 2140 2145 2150 2155 2160 2165 2170 2175 2180 2185 2190 2195 2200 2205 2210 2215 2220 2225 2230 2235 2240 2245 2250 2255 2260 2265 2270 2275 2280 2285 2290 2295 2300 2305 2310 2315 2320 2325 2330 2335 2340 2345 2350 2355 2360 2365 2370 2375 2380 2385 2390 2395 2400 2405 2410 2415 2420 2425 2430 2435 2440 2445 2450 2455 2460 2465 2470 2475 2480 2485 2490 2495 2500 2505 2510 2515 2520 2525 2530 2535 2540 2545 2550 2555 2560 2565 2570 2575 2580 2585 2590 2595 2600 2605 2610 2615 2620 2625 2630 2635 2640 2645 2650 2655 2660 2665 2670 2675 2680 2685 2690 2695 2700 2705 2710 2715 2720 2725 2730 2735 2740 2745 2750 2755 2760 2765 2770 2775 2780 2785 2790 2795 2800 2805 2810 2815 2820 2825 2830 2835 2840 2845 2850 2855 2860 2865 2870 2875 2880 2885 2890 2895 2900 2905 2910 2915 2920 2925 2930 2935 2940 2945 2950 2955 2960 2965 2970 2975 2980 2985 2990 2995 3000 3005 3010 3015 3020 3025 3030 3035 3040 3045 3050 3055 3060 3065 3070 3075 3080 3085 3090 3095 3100 3105 3110 3115 3120 3125 3130 3135 3140 3145 3150 3155 3160 3165 3170 3175 3180 3185 3190 3195 3200 3205 3210 3215 3220 3225 3230 3235 3240 3245 3250 3255 3260 3265 3270 3275 3280 3285 3290 3295 3300 3305 3310 3315 3320 3325 3330 3335 3340 3345 3350 3355 3360 3365 3370 3375 3380 3385 3390 3395 3400 3405 3410 3415 3420 3425 3430 3435 3440 3445 3450 3455 3460 3465 3470 3475 3480 3485 3490 3495 3500 3505 3510 3515 3520 3525 3530 3535 3540 3545 3550 3555 3560 3565 3570 3575 3580 3585 3590 3595 3600 3605 3610 3615 3620 3625 3630 3635 3640 3645 3650 3655 3660 3665 3670 3675 3680 3685 3690 3695 3700 3705 3710 3715 3720 3725 3730 3735 3740 3745 3750 3755 3760 3765 3770 3775 3780 3785 3790 3795 3800 3805 3810 3815 3820 3825 3830 3835 3840 3845 3850 3855 3860 3865 3870 3875 3880 3885 3890 3895 3900 3905 3910 3915 3920 3925 3930 3935 3940 3945 3950 3955 3960 3965 3970 3975 3980 3985 3990 3995 4000 4005 4010 4015 4020 4025 4030 4035 4040 4045 4050 4055 4060 4065 4070 4075 4080 4085 4090 4095 4100 4105 4110 4115 4120 4125 4130 4135 4140 4145 4150 4155 4160 4165 4170 4175 4180 4185 4190 4195 4200 4205 4210 4215 4220 4225 4230 4235 4240 4245 4250 4255 4260 4265 4270 4275 4280 4285 4290 4295 4300 4305 4310 4315 4320 4325 4330 4335 4340 4345 4350 4355 4360 4365 4370 4375 4380 4385 4390 4395 4400 4405 4410 4415 4420 4425 4430 4435 4440 4445 4450 4455 4460 4465 4470 4475 4480 4485 4490 4495 4500 4505 4510 4515 4520 4525 4530 4535 4540 4545 4550 4555 4560 4565 4570 4575 4580 4585 4590 4595 4600 4605 4610 4615 4620 4625 4630 4635 4640 4645 4650 4655 4660 4665 4670 4675 4680 4685 4690 4695 4700 4705 4710 4715 4720 4725 4730 4735 4740 4745 4750 4755 4760 4765 4770 4775 4780 4785 4790 4795 4800 4805 4810 4815 4820 4825 4830 4835 4840 4845 4850 4855 4860 4865 4870 4875 4880 4885 4890 4895 4900 4905 4910 4915 4920 4925 4930 4935 4940 4945 4950 4955 4960 4965 4970 4975 4980 4985 4990 4995 5000 5005 5010 5015 5020 5025 5030 5035 5040 5045 5050 5055 5060 5065 5070 5075 5080 5085 5090 5095 5100 5105 5110 5115 5120 5125 5130 5135 5140 5145 5150 5155 5160 5165 5170 5175 5180 5185 5190 5195 5200 5205 5210 5215 5220 5225 5230 5235 5240 5245 5250 5255 5260 5265 5270 5275 5280 5285 5290 5295 5300 5305 5310 5315 5320 5325 5330 5335 5340 5345 5350 5355 5360 5365 5370 5375 5380 5385 5390 5395 5400 5405 5410 5415 5420 5425 5430 5435 5440 5445 5450 5455 5460 5465 5470 5475 5480 5485 5490 5495 5500 5505 5510 5515 5520 5525 5530 5535 5540 5545 5550 5555 5560 5565 5570 5575 5580 5585 5590 5595 5600 5605 5610 5615 5620 5625 5630 5635 5640 5645 5650 5655 5660 5665 5670 5675 5680 5685 5690 5695 5700 5705 5710 5715 5720 5725 5730 5735 5740 5745 5750 5755 5760 5765 5770 5775 5780 5785 5790 5795 5800 5805 5810 5815 5820 5825 5830 5835 5840 5845 5850 5855 5860 5865 5870 5875 5880 5885 5890 5895 5900 5905 5910 5915 5920 5925 5930 5935 5940 5945 5950 5955 5960 5965 5970 5975 5980 5985 5990 5995 6000 6005 6010 6015 6020 6025 6030 6035 6040 6045 6050 6055 6060 6065 6070 6075 6080 6085 6090 6095 6100 6105 6110 6115 6120 6125 6130 6135 6140 6145 6150 6155 6160 6165 6170 6175 6180 6185 6190 6195 6200 6205 6210 6215 6220 6225 6230 6235 6240 6245 6250 6255 6260 6265 6270 6275 6280 6285 6290 6295 6300 6305 6310 6315 6320 6325 6330 6335 6340 6345 6350 6355 6360 6365 6370 6375 6380 6385 6390 6395 6400 6405 6410 6415 6420 6425 6430 6435 6440 6445 6450 6455 6460 6465 6470 6475 6480 6485 6490 6495 6500 6505 6510 6515 6520 6525 6530 6535 6540 6545 6550 6555 6560 6565 6570 6575 6580 6585 6590 6595 6600 6605 6610 6615 6620 6625 6630 6635 6640 6645 6650 6655 6660 6665 6670 6675 6680 6685 6690 6695 6700 6705 6710 6715 6720 6725 6730 6735 6740 6745 6750 6755 6760 6765 6770 6775 6780 6785 6790 6795 6800 6805 6810 6815 6820 6825 6830 6835 6840 6845 6850 6855 6860 6865 6870 6875 6880 6885 6890 6895 6900 6905 6910 6915 6920 6925 6930 6935 6940 6945 6950 6955 6960 6965 6970 6975 6980 6985 6990 6995 7000 7005 7010 7015 7020 7025 7030 7035 7040 7045 7050 7055 7060 7065 7070 7075 7080 7085 7090 7095 7100 7105 7110 7115 7120 7125 7130 7135 7140 7145 7150 7155 7160 7165 7170 7175 7180 7185 7190 7195 7200 7205 7210 7215 7220 7225 7230 7235 7240 7245 7250 7255 7260 7265 7270 7275 7280 7285 7290 7295 7300 7305 7310 7315 7320 7325 7330 7335 7340 7345 7350 7355 7360 7365 7370 7375 7380 7385 7390 7395 7400 7405 7410 7415 7420 7425 7430 7435 7440 7445 7450 7455 7460 7465 7470 7475 7480 7485 7490 7495 7500 7505 7510 7515 7520 7525 7530 7535 7540 7545 7550 7555 7560 7565 7570 7575 7580 7585 7590 7595 7600 7605 7610 7615 7620 7625 7630 7635 7640 7645 7650 7655 7660 7665 7670 7675 7680 7685 7690 7695 7700 7705 7710 7715 7720 7725 7730 7735 7740 7745 7750 7755 7760 7765 7770 7775 7780 7785 7790 7795 7800 7805 7810 7815 7820 7825 7830 7835 7840 7845 7850 7855 7860 7865 7870 7875 7880 7885 7890 7895 7900 7905 7910 7915 7920 7925 7930 7935 7940 7945 7950 7955 7960 7965 7970 7975 7980 7985 7990 7995 8000 8005 8010 8015 8020 8025 8030 8035 8040 8045 8050 8055 8060 8065 8070 8075 8080 8085 8090 8095 8100 8105 8110 8115 8120 8125 8130 8135 8140 8145 8150 8155 8160 8165 8170 8175 8180 8185 8190 8195 8200 8205 8210 8215 8220 8225 8230 8235 8240 8245 8250 8255 8260 8265 8270 8275 8280 8285 8290 8295 8300 8305 8310 8315 8320 8325 8330 8335 8340 8345 8350 8355 8360 8365 8370 8375 8380 8385 8390 8395 8400 8405 8410 8415 8420 8425 8430 8435 8440 8445 8450 8455 8460 8465 8470 8475 8480 8485 8490 8495 8500 8505 8510 8515 8520 8525 8530 8535 8540 8545 8550 8555 8560 8565 8570 8575 8580 8585 8590 8595 8600 8605 8610 8615 8620 8625 8630 8635 8640 8645 8650 8655 8660 8665 8670 8675 8680 8685 8690 8695 8700 8705 8710 8715 8720 8725 8730 8735 8740 8745 8750 8755 8760 8765 8770 8775 8780 8785 8790 8795 8800 8805 8810 8815 8820 8825 8830 8835 8840 8845 8850 8855 8860 8865 8870 8875 8880 8885 8890 8895 8900 8905 8910 8915 8920 8925 8930 8935 8940 8945 8950 8955 8960 8965 8970 8975 8980 8985 8990 8995 9000 9005 9010 9015 9020 9025 9030 9035 9040 9045 9050 9055 9060 9065 9070 9075 9080 9085 9090 9095 9100 9105 9110 9115 9120 9125 9130 9135 9140 9145 9150 9155 9160 9165 9170 9175 9180 9185 9190 9195 9200 9205 9210 9215 9220 9225 9230 9235 9240 9245 9250 9255 9260 9265 9270 9275 9280 9285 9290 9295 9300 9305 9310 9315 9320 9325 9330 9335 9340 9345 9350 9355 9360 9365 9370 9375 9380 9385 9390 9395 9400 9405 9410 9415 9420 9425 9430 9435 9440 9445 9450 9455 9460 9465 9470 9475 9480 9485 9490 9495 9500 9505 9510 9515 9520 9525 9530 9535 9540 9545 9550 9555 9560 9565 9570 9575 9580 9585 9590 9595 9600 9605 9610 9615 9620 9625 9630 9635 9640 9645 9650 9655 9660 9665 9670 9675 9680 9685 9690 9695 9700 9705 9710 9715 9720 9725 9730 9735 9740 9745 9750 9755 9760 9765 9770 9775 9780 9785 9790 9795 9800 9805 9810 9815 9820 9825 9830 9835 9840 9845 9850 9855 9860 9865 9870 9875 9880 9885 9890 9895 9900 9905 9910 9915 9920 9925 9930 9935 9940 9945 9950 9955 9960 9965 9970 9975 9980 9985 9990 9995 9999




FIG. 1




FIG. 2




FIG. 3

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2011/045738

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08L23/08 B32B17/10 B32B27/32 H01L31/0203 H01L31/0216
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08L B32B H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00/63286 A1 (DU PONT [US]) 26 October 2000 (2000-10-26) page 5, lines 6-11,26; claims 1-6 -----	1-15
X	EP 0 382 401 A2 (MITSUI DU PONT POLYCHEMICAL [JP]) 16 August 1990 (1990-08-16) page 4, lines 27-42; claims 1-4 -----	1-4
X	WO 97/35910 A1 (DU PONT CANADA [CA]; FARKAS NICHOLAS [CA]) 2 October 1997 (1997-10-02) claims 1-37; example 3 -----	1-3
X	EP 0 341 731 A2 (DU PONT [US]) 15 November 1989 (1989-11-15) samples 4-8 to 4-24, samples 6-8,6-9,tables IV,VI -----	1,2
		-/-

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

7 October 2011

Date of mailing of the international search report

14/10/2011

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Knutzen-Mies, Karen

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2011/045738

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2008/118137 A2 (DU PONT [US]; HAYES RICHARD A [US]) 2 October 2008 (2008-10-02) claims 1-17 -----	6-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2011/045738

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
WO 0063286	A1	26-10-2000	BR	0011190 A		05-03-2002
			DE	60015107 D1		25-11-2004
			DE	60015107 T2		24-11-2005
			EP	1169390 A1		09-01-2002
			JP	2002542359 A		10-12-2002
<hr/>						
EP 0382401	A2	16-08-1990	CA	2008925 A1		31-07-1990
			DE	69007650 D1		05-05-1994
			DE	69007650 T2		21-07-1994
			JP	2202531 A		10-08-1990
			JP	2521807 B2		07-08-1996
			US	4968752 A		06-11-1990
<hr/>						
WO 9735910	A1	02-10-1997	AU	2020297 A		17-10-1997
			CA	2248123 A1		02-10-1997
<hr/>						
EP 0341731	A2	15-11-1989	AU	627176 B2		20-08-1992
			AU	3468089 A		16-11-1989
			BR	8902233 A		21-08-1990
			CA	1337306 C		10-10-1995
			CN	1038291 A		27-12-1989
			DE	68909303 D1		28-10-1993
			DE	68909303 T2		28-04-1994
			DK	235189 A		14-11-1989
			JP	2051544 A		21-02-1990
			MX	170059 B		05-08-1993
			US	5889114 A		30-03-1999
<hr/>						
WO 2008118137	A2	02-10-2008	US	2008099064 A1		01-05-2008
<hr/>						