

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
7 April 2005 (07.04.2005)

PCT

(10) International Publication Number
WO 2005/030902 A1

(51) International Patent Classification⁷: **C09K 11/78**,
H01J 61/44

PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(21) International Application Number:
PCT/IB2004/051781

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

(22) International Filing Date:
16 September 2004 (16.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03103593.4 29 September 2003 (29.09.2003) EP

Declaration under Rule 4.17:

— as to applicant's entitlement to apply for and be granted
a patent (Rule 4.17(ii)) for the following designations AE,
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ,
CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE,
EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS,
JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,
MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM,
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ,
TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM,
ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA,
SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE,
IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE,
SN, TD, TG)

(71) Applicant (for all designated States except US): **KONIN-
KLIJKE PHILIPS ELECTRONICS N.V.** [NL/NL];
Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KOP, Petrus, W., V.**
[NL/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven
(NL). **VAN LOON, Jacobus, J.** [NL/NL]; c/o Prof. Holst-
laan 6, NL-5656 AA Eindhoven (NL).

(74) Agent: **BOSMA, Rudolphus, H., A.**; Prof. Holstlaan 6,
NL-5656 AA Eindhoven (NL).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: BAKERY FLUORESCENT LAMP

(57) Abstract: The invention relates to a fluorescent lamp whereof the fluorescent layer consists of from 1 to 3 water-dispersible phosphors, such that said lamp has a peak wavelength in each of the red, green and deep-red wavelength regions, wherein said deep-red phosphor is derived from a non-activated green, water-dispersible phosphor. The fluorescent layer consists preferably of a red, Eu³⁺ activated phosphor, a green, Tb³⁺ activated phosphor and a deep-red Mn²⁺ activated phosphor, wherein said deep-red Mn²⁺ activated phosphor is a Tb³⁺, Mn²⁺ activated phosphor. The Tb³⁺, Mn²⁺ activated phosphor is preferably a (GdMg)B₅O₁₀:Ce³⁺, Tb³⁺, Mn²⁺ phosphor. Such phosphors can be applied as an aqueous suspension in the production process of a fluorescent lamp.

WO 2005/030902 A1

Bakery fluorescent lamp

The invention relates to a fluorescent lamp whereof the fluorescent layer consists of from 1 to 3 phosphors, such that said lamp has a peak wavelength in each of the red, green and deep-red wavelength regions.

Such a lamp is especially suitable for use in bakery stores and butcheries to improve the looks of their merchandise, and is marketed by Applicant as a colour 21 TL(D) lamp. It contains a phosphor blend which consists of a red phosphor, a green phosphor and a deep-red phosphor. The deep-red phosphor of this known lamp is a Mn^{2+} activated phosphor, more specifically $Mg_4GeO_{5.5}:Mn$, being designated herein as MGM, whereof the peak wavelength is located within the range from 625 to 670 nm inclusive.

The drawback of this known blend is the fact that MGM is not dispersible in water. Therefore the blend of phosphors must be deposited as a suspension in butyl acetate.

It would nevertheless be desirable to coat the lamps with the phosphors as an aqueous suspension, so that the processing can be executed more environmentally friendly.

It has now been found that an aqueous suspension of the phosphors can be prepared when the deep-red phosphor to be used, has the same basic structure as a green, water dispersible phosphor in non-activated state.

The invention therefore relates to a fluorescent lamp whereof the fluorescent layer consists of from 1 to 3 phosphors, such that said lamp has a peak wavelength in each of the red, green and deep-red wavelength regions, wherein said phosphors are water-dispersible and wherein said deep-red phosphor has the same basic structure as a non-activated green, water-dispersible phosphor.

It was further surprisingly found that the light output of such a lamp is increased with up to 10%, compared with the abovementioned known lamp.

Preferred phosphors to be used in the present fluorescent lamp are claimed in claims 2 to 6 inclusive. With respect to those phosphors the following is observed.

The red phosphor is preferably an Eu^{3+} activated phosphor, more preferably $Y_2O_3:Eu^{3+}$, being designated herein as YOX, whereof the peak wavelength is located within the range from 600 nm to 620 nm inclusive; the green phosphor is preferably a Tb^{3+} activated phosphor, more preferably $(GdMg)B_5O_{10}:Ce^{3+},Tb^{3+}$, being designated herein as CBT;

(CeGdMg)Al₁₁O₁₉:Tb³⁺, being designated herein as CAT, and LaPO₄:Ce³⁺,Tb³⁺, being designated herein as LAP, which phosphors have a peak wavelength located within the range from 540 to 548 nm inclusive.

The deep-red phosphor is preferably (GdMg)B₅O₁₀:Ce³⁺,Mn²⁺, being designated herein as CBM, and is most preferably further activated to show a peak wavelength in the green wavelength region, such as Tb³⁺,Mn²⁺ activated phosphor, such as (GdMg)B₅O₁₀:Ce³⁺,Tb³⁺,Mn²⁺, being designated herein as CBTM.

It is observed that a fluorescent lamp comprising phosphors such as YOX, CBT and CBTM is as such known from US-A-6,157,126. According to this reference the blend of phosphors to be used also comprises nevertheless a phosphor producing light at 400 to 460 nm, which means that a blue phosphor is present. There is no suggestion in this known reference that a combination of phosphors can be made without using a blue phosphor, which can be used as an aqueous suspension in the production process of a fluorescent lamp, to obtain a lamp which is especially suitable for butcheries and bakery stores.

Further, it is observed that the phosphor CBTM, thus consisting of (CeGdMg)B₅O₁₀:Tb³⁺,Mn²⁺, is known from US-A-4,602,188. As has been mentioned in this reference, such a phosphor will supply both the deep-red Mn²⁺ emission and the green Tb³⁺ emission. A combination of this known phosphor with at least one phosphor having red and green emission as proposed in the present invention, is not mentioned nor suggested.

Further, reference is made in US-B-6,489,716 to EP-0 023 068 describing a fluorescent lamp which employs the phosphor CBT, which phosphor should have comparably good emission characteristics and a higher stability compared with the phosphor CAT (cerium magnesium aluminate:Tb) and LAP (lanthanum phosphate:Ce, Tb). All three phosphors can nevertheless be used as a green phosphor in the present invention.

US-B-6,489,716 discloses a lamp with a luminescent layer containing three phosphors: as a first phosphor BSCT (gadolinium magnesium borate silicate, activated with cerium and terbium), as a second phosphor YOX, and as a third phosphor SAPE, which is activated with bivalent europium.

A phosphor being activated with bivalent europium is nevertheless a blue fluorescent substance. A combination of phosphors having red, green and deep-red emission as claimed in the present invention is not disclosed in US-B-6,489,716.

Preferred embodiments of a lamp according to the invention are defined in claims 7 to 10, inclusive.

With respect to the composition of the present blend of phosphors it is observed that when the main ingredient is the red phosphor YOX, the produced lamp will have a high light output and a low red percentage. When CBTM is the main ingredient, this will result in lamps with a lower light output but with a higher red percentage, as will be explained hereafter. It is thus possible to adapt the red percentage of the fluorescent lamp in compliance with the customer's wish, by changing the amount of CBTM.

Because the present blend of phosphors can be deposited on the wall of the lamp as an aqueous suspension, thus as one single layer, the process control will be improved and the logistic being simpler, which will result in a cost price reduction.

The invention also relates to the use of an aqueous suspension of the above indicated three phosphors in the production of a fluorescent lamp.

A preferred embodiment of such a use is defined in claim 7.

The invention will now further be explained by means of the following, non-limiting examples.

Example 1

An aqueous suspension of a phosphor blend (suspension 1) containing 70,5% YOX, 17,6% CBTM and 11,9% CBT was prepared. It was assumed that this phosphor blend should result in a lamp having a colour point with an y value of about 280 to 385. Because the actual y-value was about 10 points lower than anticipated, about 3% b.w. of CBT was added to the suspension.

From 18 W lamps produced by applying these suspensions, as well as a known lamp containing YOX, CBT and MGM as phosphors, applied by using butyl acetate, the relevant parameters of light intensity, x- and y-value of the colour point, as well as the red%, were determined. The results thereof are given in the following Table 1.

Table 1

	coating weight	Lm	x	y	red%
18 W butyl based		1061	0,478	0,400	5,75
suspension 1	1,40 g	1151	0,524	0,372	5,47
suspension 1 + 3,70% CBT	1,39 g	1190	0,514	0,381	5,15

It appears from Table 1 that the colour point (y), obtained by using the phosphor blend which added CBT, is a desired colour point.

Example 2

5 Example 1 was repeated, starting from a suspension 2, containing a blend of phosphors consisting of 36,2% YOX, 54,3% CBTM and 9,5% CBT. Again, the actual y-value was about 10 points lower than anticipated, so that about 3% b.w. of CBT was added to the suspension. The parameters of the lamps thus produced, were determined. The results thereof are given in the following Table 2.

10

Table 2

	coating weight	Lm	x	y	red%
18 W butyl based		1061	0,478	0,400	5,75
suspension 2	1,40 g	956	0,512	0,370	8,81
suspension 2 + 3,24% CBT	1,37 g	992	0,501	0,379	8,21

It appears from Table 2 that the colour point (y), obtained by using the phosphor blend with some extra added CBT, is a desired colour point.

15

Example 3

In this example a number of aqueous suspensions were prepared containing a phosphor blend having the compositions as mentioned in the following Table 3. From 18 W fluorescent lamps produced with these phosphors, the light intensity, the colour point parameters and the red% TL were measured. The results thereof are also summarized in the following Table 3 (the results being sorted by red% TL).

25

Table 3

Lamp number	Phosphor (% b.w.)			Light intensity Lumen	Colour point (x, y)		Red% TL
	YOX	CBTM	CBT		x	y	
1	59	15	26	1318	0,476	0,411	4,20
2	61	15	24	1298	0,482	0,406	4,34
3	62	16	22	1277	0,489	0,401	4,52
4	64	16	20	1255	0,495	0,395	4,69
5	52	23	25	1276	0,475	0,410	4,76
6	66	16	18	1226	0,503	0,390	4,88
7	53	23	23	1260	0,481	0,405	4,93
8	55	24	21	1233	0,487	0,399	5,13
9	45	30	25	1235	0,472	0,410	5,30
10	57	25	19	1205	0,494	0,394	5,37
11	46	31	23	1211	0,478	0,404	5,52
12	58	25	17	1179	0,502	0,388	5,63
13	47	32	21	1192	0,484	0,399	5,77
14	38	38	24	1189	0,470	0,409	5,92
15	49	33	18	1165	0,491	0,393	6,01
16	39	39	22	1162	0,476	0,404	6,16
17	50	34	16	1126	0,498	0,387	6,32
18	30	45	25	1161	0,463	0,412	6,32
19	40	40	20	1130	0,483	0,398	6,45
20	30	46	23	1135	0,468	0,408	6,55
21	41	42	18	1110	0,490	0,392	6,77
22	31	47	21	1108	0,475	0,401	6,92
23	42	43	15	1075	0,496	0,386	7,05
24	32	49	19	1077	0,481	0,397	7,17
25	33	50	17	1053	0,487	0,390	7,54
26	18 W butyl based phosphor blend of YOX, CBT and MGM			1061	0,478	0,400	5,75

It appears from Table 3 that lamp nr. 13 having a red percentage TL of 5,77%, with $x = 0,484$ and $y = 0,399$ is a lamp which is completely comparable with the known TL(D) 18 W lamp of colour no. 21. The composition of the blend of phosphors used in lamp nr. 13 was 47% b.w. of YOX, 32% b.w. of CBTM and 21% b.w. of CBT. It thus appeared
5 that the phosphor CBTM can be used instead of MGM in the production of a fluorescent lamp; it moreover results in an increase in light intensity of more than 10%.

It is observed that the invention has been explained by means of specific embodiments. It is nevertheless to be understood that these embodiments are merely illustrative and should in no way be construed as limiting the scope of the present invention.
10 Various modifications and variations may be made without departing from the scope and spirit of the invention, the scope of the invention being indicated by the appended claims rather than by the foregoing description.

CLAIMS:

1. A fluorescent lamp whereof the fluorescent layer consists of from 1 to 3 phosphors, such that said lamp has a peak wavelength in each of the red, green and deep-red wavelength regions, wherein said phosphors are water-dispersible, and wherein said deep-red phosphor has the same basic structure as a non-activated green, water-dispersible phosphor.
- 5
2. A fluorescent lamp as claimed in claim 1, wherein said phosphor having a peak wavelength in the red wavelength region is an Eu^{3+} activated phosphor, preferably $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$.
- 10
3. A fluorescent lamp as claimed in claim 1, wherein said phosphor having a peak wavelength in the green wavelength region is a Tb^{3+} activated phosphor, preferably selected from the group consisting of $(\text{CeGdMg})\text{Al}_{11}\text{O}_{19}:\text{Tb}^{3+}$; $\text{GdMgB}_5\text{O}_{10}:\text{Ce}^{3+},\text{Tb}^{2+}$ and $\text{LaPO}_4:\text{Ce}^{3+},\text{Tb}^{3+}$.
- 15
4. A fluorescent lamp as claimed in claim 1, wherein said phosphor having a peak wavelength in the deep-red wavelength region is a Mn^{2+} activated phosphor, preferably $(\text{GdMg})\text{B}_5\text{O}_{10}:\text{Ce}^{2+},\text{Mn}^{3+}$.
- 20
5. A fluorescent lamp as claimed in claim 4, wherein said phosphor having a peak wavelength in the deep-red wavelength region is further activated to show a peak wavelength in the green wavelength region.
- 25
6. A fluorescent lamp as claimed in claim 5, wherein said phosphor is a $\text{Tb}^{3+},\text{Mn}^{2+}$ activated phosphor, preferably $(\text{GdMg})\text{B}_5\text{O}_{10}:\text{Ce}^{3+},\text{Tb}^{3+},\text{Mn}^{2+}$.
7. A fluorescent lamp as claimed in claim 1, wherein said phosphors consist of: from 40-70%, preferably 50% b.w. of a red, Eu^{3+} activated phosphor, from 10-30%, preferably 17% b.w. of a green Tb^{3+} activated phosphor, from 10-50%, preferably 35% b.w. of a deep-red Mn^{2+} activated phosphor.

8. A fluorescent lamp as claimed in claim 7, wherein said Mn^{2+} activated phosphor is at least partially replaced by a Tb^{3+}, Mn^{2+} activated phosphor.
- 5 9. A fluorescent lamp as claimed in claim 1, wherein said lamp has a colour point (x, y) wherein x is a number in the range from 0,475 to 0,495, preferably 0,484, and y is a number in the range from 0,390 to 0,405, preferably 0,399.
- 10 10. A fluorescent lamp as claimed in claim 1, wherein said lamp has a red percentage LD in the range from 4-8, preferably 6,4.
11. Use of an aqueous suspension of a red, Eu^{3+} activated phosphor, a green, Tb^{3+} activated phosphor and a deep-red, Tb^{3+}, Mn^{2+} activated phosphor in the production of a fluorescent lamp.
- 15 12. Use according to claim 11, wherein said aqueous suspension consists of 40-70%, preferably 50% b.w. of $Y_2O_3:Eu^{3+}$, 10-30%, preferably 17% b.w. of $(GdMg)B_5O_{10}:Ce^{3+}, Tb^{3+}$, and 10-50%, preferably 35% b.w. of $(GdMg)B_5O_{10}:Ce^{3+}, Tb^{3+}, Mn^{2+}$. Abstract

INTERNATIONAL SEARCH REPORT

IB2004/051781

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C09K11/78 H01J61/44

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 C09K H01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 157 126 A (HASHIMOTO KENJIRO ET AL) 5 December 2000 (2000-12-05) cited in the application column 3, line 20 - line 28 column 3, line 41 - line 47 column 6, line 25 - line 36 column 9, line 7 - line 21 claims	1-12
X	US 6 144 152 A (VAN DER VOORT DICK) 7 November 2000 (2000-11-07) claims 1,5-7	1-4,9-11
A	EP 0 023 068 A (PHILIPS NV) 28 January 1981 (1981-01-28) cited in the application page 4, line 10 - line 25; example 39	1-12
	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

17 November 2004

Date of mailing of the international search report

25/11/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Lehnert, A

INTERNATIONAL SEARCH REPORT

IB2004/051781

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 585 692 A (SUGIMOTO YUJI ET AL) 17 December 1996 (1996-12-17) column 4, line 27 - line 38; example 1 -----	1-12

INTERNATIONAL SEARCH REPORT

IB2004/051781

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 6157126	A	05-12-2000	CN	1197910 A	04-11-1998
			EP	0865071 A2	16-09-1998
			ID	20044 A	17-09-1998
			JP	10312775 A	24-11-1998
			TW	473604 B	21-01-2002
US 6144152	A	07-11-2000	CN	1146012 T	14-04-2004
			EP	0976142 A1	02-02-2000
			WO	9933092 A1	01-07-1999
			JP	2001512625 T	21-08-2001
EP 0023068	A	28-01-1981	NL	7905680 A	27-01-1981
			CA	1147944 A1	14-06-1983
			DE	3060368 D1	24-06-1982
			EP	0023068 A1	28-01-1981
			ES	8104378 A1	01-07-1981
			HU	183186 B	28-04-1984
			JP	1302401 C	14-02-1986
			JP	56028282 A	19-03-1981
			JP	60023798 B	10-06-1985
			US	4319161 A	09-03-1982
US 5585692	A	17-12-1996	CN	1102751 A ,B	17-05-1995
			DE	69403401 D1	03-07-1997
			DE	69403401 T2	30-10-1997
			EP	0638626 A1	15-02-1995
			JP	6306359 A	01-11-1994
			WO	9419422 A1	01-09-1994
			KR	145528 B1	01-08-1998