




(86) **Date de dépôt PCT/PCT Filing Date:** 2012/08/23
(87) **Date publication PCT/PCT Publication Date:** 2013/03/07
(45) **Date de délivrance/Issue Date:** 2019/07/23
(85) **Entrée phase nationale/National Entry:** 2014/02/10
(86) **N° demande PCT/PCT Application No.:** SE 2012/050896
(87) **N° publication PCT/PCT Publication No.:** 2013/032387
(30) **Priorités/Priorities:** 2011/08/26 (SE1150774-6);
2012/01/09 (SE1250007-0)

(51) **Cl.Int./Int.Cl.** *B32B 38/14* (2006.01),
B27M 3/04 (2006.01), *B32B 21/06* (2006.01),
B44C 5/04 (2006.01), *E04F 15/02* (2006.01)
(72) **Inventeur/Inventor:**
PERVAN, DARKO, SE
(73) **Propriétaire/Owner:**
CERALOC INNOVATION AB, SE
(74) **Agent:** FETHERSTONHAUGH & CO.

(54) **Titre : REVETEMENT DE PANNEAU**
(54) **Title: PANEL COATING**



(57) **Abrégé/Abstract:**
The disclosure relates to a method for coating of a floor panel and a floor panel produced by the method. The disclosure relates to a method for producing a laminated product, for example a building panel, preferably a floor panel. The method comprises applying a paper (2) on one side of a wood fiber based core (3), e.g. an HDF panel, creating a décor (8) on the paper (2) by a digital printing process, applying a resin, preferably a melamine formaldehyde resin, on the paper (2), heating the décor (8) and the paper (2) with the resin, preferably by using an IR lamp; and applying heat and pressure in order to cure the resin and thereby obtain a laminated product. The disclosure also relates to alternative methods for producing a laminated product, and such a laminated product.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

7 March 2013 (07.03.2013)



(10) International Publication Number

WO 2013/032387 A1

(51) International Patent Classification:

B32B 38/14 (2006.01) B44C 5/04 (2006.01)
 B27M 3/04 (2006.01) E04F 15/02 (2006.01)
 B32B 21/06 (2006.01)

(21) International Application Number:

PCT/SE2012/050896

(22) International Filing Date:

23 August 2012 (23.08.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1150774-6 26 August 2011 (26.08.2011) SE
 1250007-0 9 January 2012 (09.01.2012) SE

(71) Applicant (for all designated States except US): **Välinge Flooring Technology AB** [SE/SE]; Prästavägen 513, SE-263 65 Viken (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **PERVAN, Darko** [SE/SE]; Bygatan 30, SE-263 61 Viken (SE).

(74) Agent: **WESTEMAN, Maria**; c/o Välinge Innovation AB, Prästavägen 513, SE-263 65 Viken (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:


— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

— with international search report (Art. 21(3))

(54) Title: PANEL COATING

Fig. 1a



(57) Abstract: The disclosure relates to a method for coating of a floor panel and a floor panel produced by the method. The disclosure relates to a method for producing a laminated product, for example a building panel, preferably a floor panel. The method comprises applying a paper (2) on one side of a wood fiber based core (3), e.g. an HDF panel, creating a décor (8) on the paper (2) by a digital printing process, applying a resin, preferably a melamine formaldehyde resin, on the paper (2), heating the décor (8) and the paper (2) with the resin, preferably by using an IR lamp; and applying heat and pressure in order to cure the resin and thereby obtain a laminated product. The disclosure also relates to alternative methods for producing a laminated product, and such a laminated product.

PANEL COATING

Technical field

The disclosure generally relates to the field of coating of panels, e.g. building panels. More particular, the disclosure relates to a method for coating of a
5 floor panel and a floor panel produced by the method.

Field of Application of the Invention

The present invention is particularly suitable for use in floating floors, which are formed of floor panels with a wood fiber core and a thin decorative wear
10 resistant surface. The following description of prior-art technique, problems of known systems and objects and features of the invention will therefore, as a non-restrictive example, be aimed above all at this field of application and in particular at floorings which are similar to traditional wood fiber based laminate floorings.

15 It should be emphasized that the invention can also be used in other applications as for example wall panels, ceilings, and furniture components and similar.

Known technology

20 Traditional laminated panels P intended to be used for e.g. flooring, wall panels or furniture components are produced by the following steps as shown in figure 1a:

- applying a melamine formaldehyde resin impregnated kraft paper as a balancing layer 4 on one side of a core 3 of wood fiber based material;
- 25 • applying a by melamine formaldehyde resin impregnated printed decor paper 2 on the other side of the core 3;
- applying a melamine formaldehyde resin impregnated transparent overlay paper 1 with wear resistant particles, for example aluminum oxide, on the décor paper; and
- 30 • curing the resins by applying heat and pressure in a continuous or discontinuous press to obtain a laminated product.

Typical press parameters are 40 bar pressure and a temperature of 160-200 C° with a pressing time of 12-30 seconds. Pressing of the top surface is generally made against an embossed press plate that created the surface structure of the panel. The décor paper that prior to impregnation has a weight of 60-80 g/m² comprises generally about 50wt% of melamine formaldehyde thermosetting resins. The resin content in the overlay may be even higher.

It is also known that an unimpregnated décor paper may be used to reduce the impregnation cost and to increase the stock lifetime of the printed decor paper since an impregnated paper has a maximum shelf lifetime of 6-12 months. Other disadvantages related to impregnated decorative papers are that the paper must be stored in a climate controlled warehouse in order to avoid sticking, that a minimum quantity of about 3 tons have to be impregnated in order to obtain low production costs and that the decorative paper swells and shrinks during impregnation and this creates problems when the printed pattern must be adapted to a panel size or the embossing pattern of the press plates.

As an alternative to the overlay paper, it is known to apply the melamine formaldehyde resin and the wear resistant particles on top of the decor paper in liquid form that subsequently is dried prior to pressing or in dry powder form mixed with for example wood fibers. Such a protective layer is referred to as "liquid overlay" or "powder overlay".

Furthermore it is known to apply an unimpregnated décor paper directly to the board and then add resin in wet liquid form in several steps on the board and on the décor paper, with intermediate drying zones to remove the water from the resin. The impregnation is made in line with the pressing operation

It is also known, as shown in figure 1b that an impregnated core paper may be applied as sublayer 12 under a decorative unimpregnated paper and that resins from the core paper may penetrate into the decorative paper during pressing. This production method is complicated and not cost efficient.

Traditional laminate floorings use a decorative paper that is printed prior to impregnation. Even when unimpregnated papers may be used, such papers are printed in separate printing operations and are thereafter applied on a core prior to pressing. Such printing gives the disadvantage that the decorative paper has to be positioned precisely on the core in order to match

the embossed surface of the press plate or the size of the machined floor panel.

Figures 1c, d show that digital printing technology based on a non contact process where a digital printing device 9 comprising a print head, usually a so called Piezo head, fires small drops of ink comprising a color substance on a substrate 2, may be used to create a décor. The major advantage is the production flexibility, which allows that small production volumes can be economically manufactured.

The digital print 8 is generally applied on a paper 2, which is already coated with a base layer comprising a base color or directly on the panel core, which generally also comprises a base layer. The digital print is covered by a transparent protective layer that may be a conventional overlay or a UV cured transparent lacquer.

Digital printing may also be used to print on the overlay paper sheet. The decorative paper provides the base coat and the print on the lower side of the impregnated overlay provides an additional pattern that is required to create a wood or stone design.

The decorative paper 2 or the overlay may be printed digitally prior impregnation 20 as shown in figure 1c or after impregnation 20 as shown in figure 1d. The end result is always that a digitally printed décor 8 is applied on a paper based print carrier 2 that is impregnated and thereafter applied as a separate printed and impregnated sheet on the core 3.

Definition of Some Terms

In the following text, the visible surface of the installed floor panel is called "front side", while the opposite side of the floor panel, facing the sub floor, is called "rear side". By "up" is meant towards the front side and by "down" towards the rear side. The sheet-shaped material that comprises the major part of a floor panel is called "core". By "surface layer" is meant all layers applied to the core closest to the front side and covering preferably the entire front side of the floorboard. By "decorative surface layer" is meant a layer, which is mainly intended to give the floor its decorative appearance. "Wear layer" or "protective layer" relates to a layer, which is mainly adapted to improve the durability of the front side. By "raw paper" is meant unimpregnated paper that does not comprise any thermosetting binders or a

paper that only comprises small amounts of thermosetting binders for example less than about 20 wt% and where a considerable part of the resin content in the pressed paper is injected during pressing from a layer above and/or below the paper.

5

Summary of the Invention and Objects thereof

An overall objective of the present invention is to provide an improved method for coating of panels. A specific objective is to avoid impregnation of the decorative paper and to eliminate the need for a precise positioning of the decorative paper on the core prior to pressing.

10

The present invention combines process flexibility and product features as listed a-d below.

The drawback of all known technologies using printed paper is that there is no method that combines maximum process flexibility and product features in terms of a) the use of unimpregnated or raw papers b) adding flexibility to the process by being able to choose the decor in the press line by printing the decor digitally with an inkjet printer, c) giving the surface of the pressed board a structure by using an embossed press plate that forms the board during pressing when the thermosetting resins are cured and d) giving the product impact and wear resistance as good as or better as traditional direct laminated panels.

15

20

By printing the décor after the paper is positioned on the core increases the accuracy of décor position and makes it possible to obtain an improved surface design. Avoiding impregnation of the paper gives cost advantages and increased production flexibility.

25

A first aspect of the inventions is a method for producing a laminated product, for example a building panel, preferably a floor panel, wherein the method comprising the steps of:

30

- applying a paper on one side of a wood fiber based core, e.g. an HDF panel,
- creating a décor on the paper by a digital printing process,
- applying a resin, preferably a melamine formaldehyde resin, on the paper;

- heating the décor and the paper with the resin, preferably by using an IR lamp; and
- applying heat and pressure in order to cure the resin and thereby obtain a laminated product.

5 Preferably, the step of creating the décor by the digital printing process is performed after the paper is applied to the core.

The method may further comprise the step of applying a powder based sub layer on the core and under the paper. Said powder based sub layer comprising wood fibers and a thermosetting powder resin, preferably a
10 melamine formaldehyde resin.

The powder sub based layer preferably comprises about 50wt% wood fibers and about 50wt% melamine resin (e.g. Kuaramin 773).

Alternatively the powder sub layer may preferably comprise about 60-80wt% wood fibers and 20-40wt% melamine/urea resins.

15 The method may further comprise the step of applying moisture on the powder based sub layer and thereafter applying heat in order to dry the powder based sub layer.

The method may further comprises the steps of:

- applying a liquid resin, preferably a melamine formaldehyde resin, on
20 the core; and
- drying the liquid resin, preferably by using an IR lamp,

before the paper is applied on the core.

The resin applied on the paper may be in powder or liquid form. The resin in powder form may be included in a mix comprising wood fibers and said resin
25 for forming a powder based overlay.

The method may further comprise the step of creating a décor on the powder resin applied on the paper by a digital printing process. This step may replace the printing on the paper.

The surface weight of the powder on the paper is preferably about 200 g/m.

30 The method may further comprise the step of applying moisture on the resin in powder form.

The method may further comprise the step of applying wear resistant particles, preferably aluminum oxide particles, on the paper before heating the décor.

5 The method may further comprise the step of applying additive particles, such as submicron particles based on silica or aluminum oxides, to improve the scuff resistance, on the paper before heating the décor.

The method may further comprise the step of applying cellulose fibers, preferably alpha cellulose fibers, on the paper, before heating the décor.

10 The method may further comprise the step of applying a layer on the other side of the core, before applying heat and pressure, to obtain a balancing layer.

The balancing layer may be a powder layer comprising wood fibers and a resin or a paper.

15 The surface weight of paper for the décor is preferably about 60, 70, 80 or 85g/m². Even thinner papers may be used with a surface weight of about 40 to 60 g/m², preferably 40 to 50 g/m².

The solid content of the resin is preferably in the range of about 50± 10 wt%., more preferably 50 ± 2 wt%.

20 The digital print may be a non-contact process comprising a Piezo print head that applies water-based drops. The color pigments may be applied in a separate step in dry form. The color pigments may be bonded by the water drops.

25 The press parameters may be in the range of about 20-60 bar, preferably about 40 bar and the temperature in the range of about 160-200 C°, preferably about 180 C°, with a pressing time of about 12-30 seconds.

30 As disclosed in WO2009/124704 it is also possible to add a layer of a powder mixture comprising wood powder, dry resin and potentially other additives under the décor paper to increase impact resistant, allow deeper embossing and to impregnate an unimpregnated décor paper from below during the curing process in the press.

A second aspect of the invention is a floor panel produced according to the first or the third aspect.

A third aspect of the invention is a method for producing a laminated product, for example a building panel, preferably a floor panel, wherein the method comprising the steps of:

- 5 • applying a powder based sub layer comprising wood fibers and a thermosetting resin on a wood fiber based core, e.g. an HDF panel,
- applying a raw paper on the powder based sub layer,
- applying a protective powder based or paper based overlay comprising a melamine formaldehyde resin and aluminum oxide on the raw paper;
- 10 • applying heat and pressure in order to impregnate the raw paper, to cure the resin and thereby obtain a laminated product.

The method may further comprise the step applying a powder based
balancing layer comprising wood fibers and a thermosetting resin on a rear
15 side of the core.

In one embodiment, the overlay may be a powder based overlay, and a paper overlay may be applied on the powder based overlay.

A fourth aspect of the invention is a floor panel comprising a core, a balancing
20 layer on a rear side of said core, and a surface layer on a front side of said core. The surface layer comprises a decorative paper, a protective transparent paper, a first powder based sub layer arranged under the decorative paper, and a second powder based sub layer arranged between the decorative paper and the protective transparent paper. The first and the
25 second sublayers comprise fibers having an average length, which is smaller than the average length of the fibers in the decorative and overlay papers.

The balancing layer may be a powder based balancing layer comprising wood fibers.

The wood fibers may in all embodiments be in powder form.

Another aspect of the invention provides a method for producing a laminated building panel, wherein the method comprises: applying a paper on one side of a wood fiber based core, after applying the paper on the core creating a décor on the paper by a digital printing process while paper is on core, applying a resin in powder form on the paper; heating the décor and the paper with the resin; and applying heat and pressure in order to cure the resin and thereby obtain a laminated product.

Another aspect of the invention provides a method for producing a laminated building panel, wherein the method comprises: applying a powder based sub layer comprising wood fibers and a thermosetting resin on a wood fiber based core, applying a raw paper on the powder based sub layer, applying a powder comprising a melamine formaldehyde resin and aluminum oxide on said raw paper to form a protective overlay on said raw paper; applying heat and pressure in order to impregnate the raw paper, to cure the resin and thereby obtain a laminated product.

Another aspect of the invention provides a method for producing a laminated building panel, wherein the method comprises: applying a paper on one side of a wood fiber based core, the paper being unimpregnated when the paper is applied on the core; digitally printing a décor directly onto the paper using a digital printer while paper is on the core; applying a resin directly on the paper while the paper is on the core and the paper remains unimpregnated; heating the paper, the décor, and the resin while the paper, the décor, and the resin are on the core; and simultaneously applying heat and pressure to cure the resin and thereby obtain a laminated product, the simultaneously applying heat and pressure being after the heating of the paper, the décor and the resin.

Another aspect of the invention provides method for producing a laminated building panel, wherein the method comprising the steps of: applying a powder based sublayer comprising wood fibers and a thermosetting resin on a wood fiber based core; applying a raw paper on the powder based sublayer; providing a décor on the raw paper by a digital printing process after the raw paper is applied on said powder

based sublayer; applying a protective powder based or paper based overlay comprising a resin and wear resistant particles on said raw paper; and applying heat and pressure in order to impregnate the raw paper and to cure the resins, thereby obtaining a laminated product.

5 Brief Description of the Drawings

Figs 1a-1d illustrate known laminated floor panels.

Figs 2a-2d illustrate a first embodiment of the invention.

Figs 3a-d illustrate a second embodiment of the invention.

Figs 4a-4d illustrate a third embodiment of the invention

Figs 5a-5c illustrate forming of the surface layer.

5 Description of Embodiments of the Invention

The disclosure will in the following be described in connection to exemplary embodiments.

Figures 2a -2d show a first embodiment of the invention.

Figure 2a shows a panel P comprising a core 3, preferably a HDF core and a
10 balancing layer 4 on the rear side of the core 3. The balancing layer 4 may be
a conventional kraft paper impregnated with a thermosetting resin, preferably
a melamine formaldehyde resin, or a powder backing comprising wood fibers
and a thermosetting resin, preferably a melamine formaldehyde resin. The
application of a powder backing is made by a scattering unit 10 in the same
15 way as shown in figure 4a. The spraying 11 and the drying device 7 will
stabilize the powder and create a balancing layer 4 that may be connected to
the core 3 such that the panel P may be turned with the rear side pointing
downwards prior to the application of the surface layers 1, 2, 12. A resin 5,
20 preferably a liquid thermosetting resin that preferably is a melamine
formaldehyde resin, is applied on the upper side of the core 3, preferably with
a roller 6 or by spraying. The resin is heated and dried by using a drying
device 7 such as for example an IR lamp, hot air, microwaves and similar.

Figure 2b shows a paper layer 2 that is applied on the dried resin. The paper
is preferably a raw paper. The paper may comprise a basic color or may be
25 partly printed. It is not necessary to align the paper precisely since there is no
final printed pattern on the paper 2.

Figure 2c shows a digital print 8 that is printed on the paper 2 by a digital
printing device 9. Digital printing is a non-contact process where a digital print
head, preferably a Piezo head, fires drops of a liquid substance on a
30 substrate and creates a pattern. The liquid substance may comprise color
pigments and may be water based. Alternatively the pigments may be applied
separately in dry powder form and the digital print head may essentially only
apply a liquid substance that may be transparent and that may comprise a

substance that acts as a binder and connects the pigments to the substrate. Non-bonded pigments may be removed by for example an air stream or gravity. Such a two-step digital binder and powder (BAP) printing is very cost efficient especially when large amounts of pigments are used to create a pattern. BAP allows that substantial amounts of pigmented powder may be applied for example more than 20 g/m² preferably about 20-50g/m².

Figure 2d shows that the paper 2 is coated with a liquid thermosetting resin, preferably a melamine formaldehyde resin, in order to create a protective layer 1 similar to a conventional overlay. The coating is preferably made in the same way as shown and described in figure 2a. The liquid resin comprises preferably aluminum oxide particles and/or cellulose fibers preferably alpha cellulose fibers.

A coating of the paper with a base color may also be made prior to the digital printing.

- 15 The first embodiment of the method comprises the step of:
- coating of a wood fiber based core 3, preferably an HDF panel, with a liquid melamine formaldehyde resin;
 - drying the liquid resin;
 - attaching a paper 2 to the core 3;
 - 20 • providing a décor 8 on the paper 2 by a digital printing process;
 - coating the paper 2 with the decor with a liquid melamine resin, preferably comprising aluminum oxide particles and/or cellulose fibers preferably alpha cellulose fibers;
 - drying the coating; and
 - 25 • applying heat and pressure to cure the resins and thereby obtain a laminated product.

An advantage is that it is possible to use an unprinted paper, which reduces the warehouse costs and improves the process flexibility. By printing the paper after the paper is attached to the core the accuracy of the décor position is improved.

The coating of the paper may be replaced or combined with a conventional overlay that is applied over the digitally printed paper.

Figures 3a-3d show a second embodiment of the invention. The forming of the balancing layer 4, the coating of the core 3 and the digital printing of the paper as shown in figures 3a-3c are the same as in the first embodiment. However, the protective layer 1 has been replaced with a powder overlay that is scattered by a scattering unit 10 in dry form over the paper 2 with the digital print 8 as shown in figure 3d. Said powder overlay preferably comprising fibers, preferably processed wood fibers, a resin, preferably a melamine formaldehyde resin, and wear resistant particles, preferably aluminum oxide. A liquid substance preferably comprising water may be sprayed on the powder overlay by a spraying device 11 and dried by a drying device 7 in order to stabilize the powder prior to the pressing operation.

The second embodiment of the first aspect of the method comprises the step of:

- coating of a wood fiber based core 3, preferably an HDF panel, with a liquid melamine formaldehyde resin;
- drying the liquid resin;
- attaching a paper 2 to the core 3;
- providing a décor 8 on the paper 2 by a digital printing process;
- applying a powder overlay 1 on the printed décor paper 2, said overlay 1 preferably comprising fibers, a resin, preferably a melamine formaldehyde resin, and wear resistant particles, preferably aluminum oxide,
- applying moisture on the powder overlay 1;
- drying the powder overlay 1; and
- applying heat and pressure to cure the resins and thereby obtain a laminated product.

A further advantage with the second embodiment is that the impact resistance is improved due to the substantial amounts of fibers in the resin matrix, obtained from the powder overlay.

Figures 4a – 4d show a third embodiment of the invention. Figure 4a shows that a powder sublayer 12 comprising a wood fibers and a thermosetting resin, preferably a melamine formaldehyde resin or a melamine/urea resin is applied on the upper side of the core 3. The balancing layer 4 may be a paper

or a powder backing as described above. The sublayer 12 may be applied in the same way as the powder overlay with a scattering unit 10. Preferably a spraying device 11 that applies moisture on the powder and a drying device 7 may also be used to stabilize the powder in order to facilitate the application of the paper 2 over the powder sub layer 12. Figures 4c and 4d show that the paper 2 is provided with a digital print 8 by a digital printing device 9 and preferably with a powder overlay 1 or a conventional paper overlay 1 as described above. The powder overlay 1 may be applied by a scattering unit 10, sprayed with water by a spraying device 11 and dried by a drying device 7.

The third embodiment of the method comprises the step of:

- applying a powder based sublayer 12 on a core 3, preferably an HDF panel, and preferably applying moisture on the sublayer and thereafter drying the sublayer;
- attaching a paper 2 on the sublayer 12;
- providing a décor 8 on the paper 2 by a digital printing process;
- applying a powder overlay 1 on the printed décor paper 2, said overlay preferably comprising fibers, a resin, preferably a melamine formaldehyde resin, and wear resistant particles, preferably aluminum oxide,
- applying moisture on the powder overlay 1;
- drying the powder overlay 1; and
- applying heat and pressure to cure the resins and thereby obtain a laminated product.

A further advantage with the third embodiment is that the demand for drying is decreased since no wet resins are applied. The sub layer 12 gives an increased impact resistance and possibility to form a surface with deep embossing. The sub layer 12 is a cost efficient way to provide a sufficient amount of binders that may penetrate into the paper 2 during pressing

The surface weight of the powder overlay is preferably about 200 g/m² but may be as low as 50 g/m² or exceed 400 g/m². The weight of the sub layer is preferably 100 – 500 g/m².

The invention makes it possible to reduce the weight of the décor paper since no impregnation is needed and there is no need for a high "wet strength".

The weight of the raw paper may be lower than 60 g/m² preferably about 40 to 50 g/m². The press parameters in the three embodiments above are
5 preferably about 40 bar and the temperature in the range of about 160-200 C°, preferably about 180 C°, with a pressing time of about 10 - 30 seconds depending on the layer thickness.

Figure 5a shows the surface layer prior to pressing according to the third aspect of the invention. The sub layer 12 comprises in this embodiment wood
10 fibers 14, dry thermosetting resin particles 15 and preferably also color pigments 13 that give the sub layer a basic color and prevents that the core surface is visible through the thin paper. This reduces the requirement on the digital print 8 and the print may be made with lower ink content, preferably with an ink content of less than 10 g/m². The powder overlay 1, which is
15 applied over the paper 2 with the digital print 8, comprises aluminum oxide particles 16, wood fibers 14 and resin particles 15. Figure 5b shows the surface layer after pressing. The powder has been compressed and the pressed surface layer has in this embodiment preferably a thickness T₂ that is less than about 80% and even more preferably less than about 50% of the
20 surface thickness T₁ prior to the pressing. The compression of the powder under heat and pressure, when the powder resin 15 becomes fluid, impregnates the paper 2 from above and from below and connects the surface layers to the core 3.

The basic principles of the invention to use a powder sub layer 12 to
25 impregnate a raw paper 2 during pressing may also be used even without the digital printing to produce a surface with a conventional raw decorative printed paper and preferably also with conventional overlay and/or a conventional balancing paper.

A preferred embodiment is a panel P comprising a powder based balancing
30 layer 4, a powder based sub layer 12 on the upper part of the core 3, a raw decorative paper 2 applied on the powder based sub layer 12 and a protective overlay 1 on the raw decorative paper.

The powder based balancing layer 4 gives an improved balancing of the panel P since the fiber properties and orientation in the balancing layer 4 and
35 the sub layer 12 may be similar and may result in the same shrinking after pressing and in different climate conditions. The protective overlay 1 may be

a powder or paper based protective layer as described in the embodiments above.

Figure 5c shows a surface layer comprising a powder overlay 1a and a paper overlay 1b applied on the powder overlay. Preferably the paper overlay 1b is a raw paper which during pressing is impregnated with resins from the powder overlay 1a under the paper overlay 1b. The advantage is that the paper overlay 1b protects the press plates from the wear caused by the aluminum oxide particles. Very thin overlay papers may be used with a weight of 20 – 30 g/m².

10 The surface layer according to this embodiment comprises a first powder based sub layer 12 under a decorative paper 2 and a second powder based sub layer 1a under a transparent paper located above the decorative paper 2.

A powder based layer is characterized in the mechanically processed fibers have an average length of about less than 1 mm. Fibers used in an HDF core or in paper are longer and have an average length of several mm. The surface of the panel P is characterized in that the fibers in first 12 and second 1a sub layers are smaller than the fibers in the decorative paper the paper overlay.

Several alternatives are possible. The powder overlay 1a may only comprise melamine formaldehyde resins and aluminum oxide particles. It may also comprise bleached transparent wood fibers. The paper overlay may be a conventional impregnated overlay with or without aluminum oxide particles.

The second sublayer 1a will improve the wear and impact resistance even in the case when a conventional overlay is used.

25 A raw and essentially transparent paper overlay may also be used as a print carrier. A digital print 8 is applied on the print carrier. The print may be applied prior to or after the application of the raw overlay on the core. The raw overlay is preferably applied on a powder based sub layer 12 comprising fibers 14, a thermosetting resin 15, and color pigments 13. A powder overlay or a second conventional overlay may be applied on the raw overlay as a protective layer 1. The raw overlay is during pressing impregnated from the resins in the sub layer 12 and in the protective layer 1.

EXAMPLE

In example 1 below the powder mix formulation for the balancing layer 4 and the first sub layer 12 used comprising 50 weight-% recycled MDF fibers (Välinge Innovation Sweden), 50 weight-% Melamine Formaldehyde resin (Preferably 4865, Dynea). The powder formulation for the second sub layer 1a used comprises processed bleached wood fibers of about 25 wt%, 65 wt% of melamine formaldehyde resin and 10 wt% of aluminum oxide particles

Example 1: Powder based panel obtained through heat and pressure.

10 A balancing layer 4 and a first sub layer 12 was formed by scattering 300 g/m² of powder on the rear side and the front side of a 9,7 mm HDF core.

A raw decorative paper 2 with a weight of 60 g/m² was applied on the first sub layer 12 and a second sub layer 1a was applied on the decorative paper by scattering 200 g/m² of powder.

15 A 25 g/m² raw overlay was applied on the second sub layer 1a.

The core with the surface and balancing layers was pressed in a press with a pressure of 40 kg/cm², during 20 seconds. The upper press table applied a heat of 170 degrees C on the surface layer and the lower press table applied a heat of 175 degrees C on balancing layer. The surface was pressed against a press plate with an embossing depth of 0,3 mm.

A panel with an embossed decorative structure and a small pre tension backwards and a slightly convex surface was obtained. All raw papers were impregnated and cured during the pressing operation.

CLAIMS:

1. A method for producing a laminated building panel, wherein the method comprises:

applying a paper on one side of a wood fiber based core,

5 after applying the paper on the core creating a décor on the paper by a digital printing process while paper is on core,

applying a resin in powder form on the paper;

heating the décor and the paper with the resin; and

applying heat and pressure in order to cure the resin and thereby obtain
10 a laminated product.
2. The method as claimed in claim 1, wherein the method further comprises applying a powder based sub layer on the core before the paper is applied on the core, said powder based sub layer comprising wood fibers and a powder resin.
3. The method as claimed in claim 2, wherein the method further
15 comprises applying moisture on the powder based sub layer and thereafter applying heat in order to dry the powder based sub layer.
4. The method as claimed in claim 1, wherein the method further comprises:

applying a liquid resin on the core; and

20 drying the liquid resin before the paper is applied on the core.
5. The method as claimed in claim 1, wherein the method further comprises applying moisture on the resin, where the resin is in powder form.

6. The method as claimed in claim 1, wherein the method further comprises applying wear resistant particles on the paper before the heating of the décor and the paper with the resin.
7. The method as claimed in claim 1, wherein the method further
5 comprises applying cellulose fibers on the paper, before the heating of the décor and the paper with the resin.
8. The method as claimed in claim 1, wherein the method further comprises applying a balancing layer on an opposite side of the core, before the applying of heat and pressure, to obtain a balancing layer.
- 10 9. The method as claimed in claim 8, wherein the balancing layer is a powder layer comprising wood fibers and a resin or the balancing layer is a paper.
10. The method as claimed in claim 2, wherein the paper is a raw paper with a weight of about 40-60 g/m².
11. The method as claimed in claim 2, wherein the paper is a raw paper
15 with a weight of about 40-50 g/m².
12. The method as claimed in claim 1, wherein a digital non-contact process is used comprising a Piezo print head that applies water based drops.
13. The method as claimed in claim 12, wherein color pigments are applied in a separate step in dry form and bonded by the water based drops.
- 20 14. The method as claimed in claim 1, wherein the heating of the décor and the paper is performed by an IR lamp prior to the applying of heat and pressure to cure the resin.
15. The method as claimed in claim 1, wherein the paper is a raw paper when the paper is applied on the one side of the wood fiber based core and when the
25 décor is created on the paper by the digital printing process.

16. The method as claimed in claim 1, wherein

the paper, the resin, and the décor on the one side of the wood fibre based core possess a thickness, and

the thickness of the paper, the resin, and the décor on the one side of
5 the wood fibre based core after the applying of the heat and pressure is less than
80% of the thickness of the paper, the resin, and the décor on the one side of the
wood fiber based core before the applying of the heat and pressure.

17. The method as claimed in claim 16, wherein the thickness of the paper,
the resin, and the décor on the one side of the wood fiber based core after the
10 applying of the heat and pressure is less than 50% of the thickness of the paper, the
resin, and the décor on the one side of the wood fiber based core before the applying
of the heat and pressure.

18. A method for producing a laminated building panel, wherein the method
comprises:

15 applying a powder based sub layer comprising wood fibers and a
thermosetting resin on a wood fiber based core,

applying a raw paper on the powder based sub layer,

applying a powder comprising a melamine formaldehyde resin and
aluminum oxide on said raw paper to form a protective overlay on said raw paper;

20 applying heat and pressure in order to impregnate the raw paper, to
cure the resin and thereby obtain a laminated product.

19. The method as claimed in claim 18, wherein a powder based balancing
layer comprising wood fibers and a thermosetting resin is applied on a rear side of
the core.

20. The method as claimed in claim 18, wherein a paper overlay is applied directly on top of the powder protective overlay before the applying of the heat and pressure.

21. A method for producing a laminated building panel, wherein the method
5 comprises:

applying a paper on one side of a wood fiber based core, the paper being unimpregnated when the paper is applied on the core;

digitally printing a décor directly onto the paper using a digital printer while paper is on the core;

10 applying a resin directly on the paper while the paper is on the core and the paper remains unimpregnated;

heating the paper, the décor, and the resin while the paper, the décor, and the resin are on the core; and

15 simultaneously applying heat and pressure to cure the resin and thereby obtain a laminated product, the simultaneously applying heat and pressure being after the heating of the paper, the décor and the resin.

22. Method for producing a laminated building panel, wherein the method comprising the steps of:

20 • applying a powder based sublayer comprising wood fibers and a thermosetting resin on a wood fiber based core;

• applying a raw paper on the powder based sublayer;

• providing a décor on the raw paper by a digital printing process after the raw paper is applied on said powder based sublayer;

- applying a protective powder based or paper based overlay comprising a resin and wear resistant particles on said raw paper; and

- applying heat and pressure in order to impregnate the raw paper and to cure the resins, thereby obtaining a laminated product.

5 23. The method according to claim 22, further comprising applying a powder based balancing layer comprising wood fibers and a thermosetting resin on a rear side of the core.

24. The method according to claim 22, further comprising applying a paper as a balancing layer on a rear side of the core.

10 25. The method according to claim 22 or 23, wherein said protective overlay is a powder based overlay, and wherein the method further comprises applying a paper overlay on the powder based overlay.

26. The method according to any one of claims 22 to 25, wherein the powder based sublayer is applied on the wood fiber based core by scattering.

15 27. The method according to any one of claims 22 to 26, wherein the protective overlay is powder based and wherein the method further comprises applying moisture, on the protective powder based overlay.

28. The method according to claim 27, further comprising drying the protective powder based overlay.

20 29. The method according to any one of claims 22 to 28, wherein the raw paper is impregnated from above and from below.

30. The method according to any one of claims 22 to 29, further comprising applying moisture on the powder based sublayer and thereafter drying the powder based sublayer.

31. The method according to any one of claims 22 to 30, further comprising attaching the raw paper to the powder based sublayer.

32. The method according to any one of claims 22 to 31, wherein the protective overlay is powder based and wherein the resin and the wear resistant
5 particles of the protective powder based overlay comprise a melamine formaldehyde resin and aluminum oxide, respectively.

33. The method according to any one of claims 22 to 32, wherein the protective overlay is powder based and wherein the protective powder based overlay further comprises wood fibres.

10 34. The method according to any one of claims 22 to 33, wherein the powder based sublayer further comprises color pigments.

35. The method according to any one of claims 22 to 34, wherein the thermosetting resin applied on the wood fiber based core is a melamine formaldehyde resin or a melamine/urea resin.

1/5

Fig. 1a




Fig. 1b




Fig. 1c





Fig. 1d



KNOWN TECHNOLOGY

2/5

Fig. 2a




Fig. 2b




Fig. 2c





Fig. 2d



3/5

Fig. 3a




Fig. 3b




Fig. 3c





Fig. 3d



4/5

Fig. 4a




Fig. 4b




Fig. 4c





Fig. 4d



5/5

Fig. 5a




Fig. 5b




Fig. 5c

