



(22) Date de dépôt/Filing Date: 1997/01/17  
 (41) Mise à la disp. pub./Open to Public Insp.: 1997/07/19  
 (45) Date de délivrance/Issue Date: 2004/06/29  
 (30) Priorité/Priority: 1996/01/18 (335.114) AR

(51) Cl.Int.<sup>6</sup>/Int.Cl.<sup>6</sup> C08L 17/00, C08J 11/00  
 (72) Inventeurs/Inventors:  
 LUPO, JOAQUIN, AR;  
 TRE, LUIS JACINTO, AR  
 (73) Propriétaires/Owners:  
 LUPO, JOAQUIN, AR;  
 TRE, LUIS JACINTO, AR  
 (74) Agent: GIERCZAK, EUGENE J. A.

(54) Titre : POUDRE DE CAOUTCHOUC HUMIDIFIEE OBTENUE PAR RECYCLAGE DE MATIERES RECUPEREES  
 (54) Title: HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS

(57) **Abrégé/Abstract:**

HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIAL of the type usable as raw material for the manufacture of several products applicable to such industries as building, automobile accessories, shoes, etc., replacing products such as wood, zinc sheet, fiber cement, plastic and any other rigid or semirigid material, as it contains from 66% to 77% of recycled material obtained by the grinding of 100% of discarded tires, and ground according to a mesh between 18 and 30 microns; from 15% to 22% of recycled plastic material, ground according to a mesh between 18 and 30 microns; and from 8% to 12% of a solution of acid with toluene or M.I.K. (methyl isobutyl ketone); said acid may be lactic, phosphoric or formic acid, its percentage in said solution being between 12% and 50%, while the percentages of toluene or M.I.K. are between 50% and 88%.



**HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS**

**ABSTRACT**

**HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS** of the type usable as raw material for the manufacture of several products applicable to such industries as building, automobile accessories, shoes, etc., replacing products such as wood, zinc sheet, fiber cement, plastic and any other rigid or semirigid material, as it contains from 66% to 77% of recycled material obtained by the grinding of 100% of discarded tires, and ground according to a mesh between 18 and 30 microns; from 15% to 22% of recycled plastic material, ground according to a mesh between 18 and 30 microns; and from 8% to 12% of a solution of acid with toluene or M.I.K. (methyl isobutyl ketone); said acid may be lactic, phosphoric or formic acid, its percentage in said solution being between 12% and 50%, while the percentages of toluene or M.I.K. are between 50% and 88%.

**HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS**

**DESCRIPTIVE REPORT**

This invention refers to a **HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS** of the type usable as raw material for the manufacture of several products applicable to such industries as building, automobile accessories, shoes, etc.

10           So far, recycling of discarded tires has constituted a serious problem worldwide, since, in principle, one of the main uses of such tires is to relocate them in the automobile market with the safety problems which that means.

          As noted in an article of the newspaper *Ámbito Financiero* of November 28, 1995, page 10, columns 4 through 6, ... **no efficient method to degrade used rubber has been discovered yet.** Experiments are being made to use it as fuel for boilers. As an example of the difficulties that the developed countries have as regards the disposal of this kind of waste ... Some **entrepreneurs** found the solution and the goldmine at the same time: the exportation to developing nations of used tires “**In the last few years thousands of containers of scrap goods have come to Argentina: in addition to endangering the life of automobile drivers they constitute a menace to the**

20           **local industry of tires and to job opportunities” ...**”.

          As observed in the first part of this article, no efficient method has been obtained so far for the degradation of rubber; we could also add that the same happens with plastic, for which reason an ecologically optimal way is to reuse these materials so that they do not turn into waste. The main goal of this invention refers precisely to the creation of a new raw material with sufficient versatility so as to be base material for several industrial applications.

          There exist in the market methods of reuse of tires, which employ at most 20% of the used tire, to which virgin rubber is added and the result is a product used for the

30           manufacture of, for example, solid tires for tricycles or bicycles, carpeting for auto-

mobiles, etc., with a reduced cost with respect to a product made entirely with virgin rubber.

Said procedures such as the one described in the foregoing paragraph fully reject the use of fabric and/or metal residues (existing in tires) which are burnt or thrown away.

10 In order to expand on even more the description of the field of application of used tires, we can cite the book *Gestión Integral de Residuos Sólidos* (Integral treatment of solid residues) which on pages 856 through 859, paragraph 15. 13, makes direct reference to the handling of used tires in the United States "... Every year in the United States approximately 281 million tires are replaced. It is estimated that 237 million are discarded. Ten million are reused and 33 million are recapped or retreaded. From 2 to 3 billion tires have remained stored in piles, and some millions more have been dumped illegally. Approximately 14 per cent of the discarded tires are used for fuel; it is estimated that 5 per cent is used for chipboard, rubber powder and miscellaneous uses and 4 per cent is exported ...".

20 The foregoing and the figures detailed above being taken into account, the large quantity of existing base material is clearly appreciated, and furthermore, as observed in the same book.. "... Generally, there are no specifications for the recycling of used tires because many of the applications are new and are not developed completely. The specifications for reusable tires vary according to the recappers, retreaders and remanufacturers of tires.

On the basis of all the foregoing, the **HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS**, which is ranked in a preferential position with respect to the recycling of used tires, since it is a new raw material capable of replacing with complete success in the manufacture of numberless items, wood, sheet zinc, fiber cement, plastic and any other rigid or semirigid material, allowing the use of 100 per cent of the material that comes from the used tire (rubber, fabric, etc.). The manufacturing cost of said raw material is equivalent to approxi-

mately 50% as contrasted with that of such substitutes which may be used in the manufacture of similar products (polyethylene, rubber, PVC, etc.).

In order to understand even more the characteristics of said **HUMIDIFIED RUBBER POWDER OBTAINED BY RECYCLING OF SCRAP MATERIALS** we detail below the different stages of the process of manufacture of the powder which is the object of this invention, which are as follows:

a) Tires are washed and dried by forced hot air or by normal ventilation.

b) With a special mill tires are cut up into small pieces which will be then ground.

10 c) With special mills, the rubber is ground until achieving the microns needed, and is selected with sieves whose mesh ranges from 18 to 30 microns, the rest is ground again until obtaining the necessary microns; it should be mentioned that in this process 100% of the scrap tires (rubber and fabric) is used. If tires with steel meshes are used, and if the disposal of the metal residues thereof is desired, the ground rubber undergoes a cleaning process through electromagnets which will remove the steel residues from the ground matter.

d) After this process, the recovered plastics, which are previously selected, are added, and they are washed and ground with adequate mills and sifted until the meshes are equivalent to those of tires.

20 e) Next comes the mixing stage in which rubber is put into conventional mixers which may be of the following type: paddle, disk (dispersing), drum, or others, then the plastic, and a solution composed of an acid (e.g. lactic acid, phosphoric acid or formic acid) and toluene or M.I.K. (methyl isobutyl ketone) are added in appropriate proportions until achieving a final homogeneous product which has an appearance of humidified powder, which is then ready for its use or packaging in containers suitable for that purpose.

It is pointed out that in accordance with environmental conditions both as regards humidity and temperature, and in order to maintain an obtained product with

constant characteristics, the acid - toluene or M.I.K. solution is to be regulated within a range of acid variation between 12 and 50%.

For the purpose of specifying even more the quantitative structure of the raw material in question, we will define it by reference percentage limits, as follows:

Discarded tires	77% - 66%
Recovered and ground plastics	15% - 22%
Acid with Toluene or M.I.K. solution	8% - 12%

Said solution being composed, according to the following percentages, of:

10	Acid	12 - 50%
	Toluene or M.I.K.	50 - 88%

Once said raw material is obtained, several products may be manufactured, according to two of the main varieties which may be obtained (rigid or semi-rigid), for example:

20	Rigid solid	Building (bricks, tiles, etc.) Pallets Telephone poles or electricity pylons Boxes (cases) for accumulators (storage batteries) for automobiles
	By extrusion	Pipes for sewers Downspouts
	By injection	Soles for shoes Gutters Sheets (it replaces pressboard, zinc, fiber cement) Roof tiles
	By pressing	Floor tiles

Moreover, the product obtained may be stuck with generic vinyl or synthetic glues, neoprene, cyanoacrylates or contact cement. It may also be painted for appropriate finishing.

As complementary information, we can adduce that in certain applications it is likely that the metal of the discarded tires should be removed (if they are tires with steel mesh), since if the product to be obtained is of semirigid nature, if bending occurs there exists the possibility of a tear on the wall, furthermore, if it is oxidized it may come off and this may result in an area of less resistance on the wall of the product.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A humidified rubber powder composition obtained by recycling scrap materials and adapted for use as raw material for manufacturing products said composition containing ;  
  
from 66% to 77% of particles of ground tires having a size of between 18 and 30 microns;  
  
from 15% to 22% of particles of ground plastic material, having a mesh size of between 18 and 30 microns; and  
  
from 8% to 12% of a solution of acid with toluene or methyl isobutyl ketone, said acid being selected from lactic acid , phosphoric acid, and formic acid, wherein the percentage of said acid in said solution by volume is between 12% and 50%, and the percentages of toluene or methyl isobutyl ketone by volume is between 50% and 88%.
2. A method for producing a humidified rubber powder composition adapted for use as raw material for manufacturing products by recycling scarp tires and plastic material comprising the steps of ;  
  
washing and drying the tries;  
  
cutting said tires into small pieces;

grinding said small pieces of tires to obtain tire particles;

selecting at least some of said tire particles in a size range of between 18 to 30

microns;

mixing said tire particles with particles of plastics of between 18 and 30 microns; and

mixing said rubber particles and said plastic particles and a solution composed of acid and toluene or methyl isobutyl ketone whereby to produce said composition.

3. A method for producing a humidified rubber powder composition according to claim 2, wherein said tires have steel mesh and said method includes the step of removing the steel mesh from the tire particles with electromagnets.