

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 August 2011 (18.08.2011)

(10) International Publication Number
WO 2011/098973 A1

PCT

(51) International Patent Classification:

D21H 21/54 (2006.01) **D21H 17/66** (2006.01)
D21H 17/65 (2006.01)

(21) International Application Number:

PCT/IB2011/050578

(22) International Filing Date:

11 February 2011 (11.02.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1000132-9 11 February 2010 (11.02.2010) SE

(71) Applicant (for all designated States except US): **STORA ENSO OYJ** [FI/FI]; Kanavaranta 1, FIN-00101 Helsinki (FI).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BACKFOLK, Kaj** [FI/FI]; Laajavuorentie 1B28, FI-40740 Jyväskylä (FI). **HEISKANEN, Isto** [FI/FI]; Kanava-aukio 10 as 13-14, FI-55100 Imatra (FI). **MIKKI, Nina** [FI/FI]; Miikinpolku 11, FI-55100 Imatra (FI).

(74) Agent: **NILSSON, Katarina**; Stora Enso AB, Group Intellectual, Property, Box 9090, S-650 09 Karlstad (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: SURFACE TREATMENT COMPOSITION

(57) Abstract: The invention relates to a surface treatment composition for paper, board or other fibrous webs. The composition of the invention comprises particles which comprise an active material and a supporting material. The active material comprises a salt or a multivalent metal, such as a divalent or trivalent metal. In accordance with the invention, the supporting material is adapted to release the active material from the particles when subjected to heat and/or pressure and/or a change in pH. Consequently, the active material's adverse effects on the rheology of the composition are avoided while its desired effects on the surface characteristics are retained or enhanced.



WO 2011/098973 A1

Surface treatment compositionTechnical field

5 The present invention relates to a surface treatment composition intended for the coating or sizing of paper, board or other fibrous webs.

Background of the invention

10

Paper, board and other fibre-based webs are often surface sized, pigmented or mineral coated to improve characteristics of the paper that affects the printability, such as the surface porosity, the absorptivity, the wettability, or the surface energy (the ink adhesion) of the paper. Today, the printability of uncoated paper is often optimized by the addition of additives to the surface-size or pigmentation recipe. The printability of coated paper is often optimized by optimizing the pigment characteristics, the amount and kind of binders used or by adding additives to the coating compositions. One problem with the addition of additives is that the additives are not always compatible with the other components in the coating, pigmentation or sizing composition.

25

New printing techniques, such as ink jet printing, puts high demands on the printing paper, since the ink must be quickly dried on the substrate and yet provide a high print quality. A desired quality involves a high optical print density, minimized feathering and bleeding and low strike-through. In recent years it has been found that when multivalent salts, such as calcium chloride, are added to the surface size, the applied ink will precipitate fast on the surface of the paper

30

and give rise to a significant improvement in print quality. This is especially advantageous in ink jet printing. US6207258 discloses a composition useful for surface treating a sheet substrate for ink jet printing, the composition
5 comprising a salt of a divalent metal.

Multivalent cations, e.g. calcium, are sometimes added to sizing or coating compositions in the form of lubricants, e.g. calcium stearate. However, the concentration of calcium,
10 in e.g. calcium stearate is not high enough to give rise to the desired effects on the print quality. Thus, the calcium amounts needs to be higher than traditionally used in such products in order to improve the print quality.

15 One problem with the addition of multivalent salts to coating and/or sizing compositions is that the high concentration of salt needed to achieve the desired effects oftentimes causes rheology problems and undesired precipitations. This is especially a problem when high amounts, such as 0,5-5 parts
20 of salt, is added to anionically charged sizing, pigmentation or coating compositions. Multivalent cations interact strongly with typical anionic-charged polymers or minerals, or additives which are used in papermaking. The stability of anionically charged particles can be improved by e.g.
25 providing steric or electrosteric stability. However, high amounts of electrolytes may cause colloidal flocculation and precipitation.

The printability may further be improved by lowering the pH
30 of a sizing or a coating layer composition e.g. by addition of an acid to the coating or sizing composition. However, not all sizing or coating agents are compatible with low pH. Calcium carbonate pigments can for example not be used at low

pH since calcium carbonate dissolves and foam is generated when calcium dioxide is released from calcium carbonate in an acid environment. A reduction in pH may also have a negative impact on rheological properties and on the runnability of the paper machine.

It is an object of the present invention to find a solution to the problem of adding additives, such as salts of multivalent metals, to sizing and/or coating compositions without disturbing the rheological profile of the composition.

Summary of the invention

The above object, and other advantages, is achieved by the surface treatment composition and the process of the present invention.

The invention relates to a surface treatment composition for paper, board or other fibrous webs. The composition of the invention comprises particles which comprise an active material and a supporting material. The active material comprises a salt of a multivalent metal, such as a divalent or trivalent metal. In accordance with the invention, the supporting material is adapted to release the active material from the particles when subjected to heat and/or pressure and/or a change in pH. In this way, the active material may be "trapped" in the particles at least until the composition is applied on the surface of the fibrous web and activated or stimulated in a later stage in the paper-making process. Consequently, the active material's adverse effects on the rheology of the composition are avoided while its desired effects on the surface characteristics are retained or

enhanced. The invention render it possible to dose a higher concentration of multivalent metals to a sizing or a coating composition without effecting the colloidal stability and hence the rheology of the composition negatively. In this way, the printability of the sized or coated paper or board can be improved. Moreover, use of the particles according to the invention also reduces the concentration of the free anion of the multivalent salt, e.g. a chloride ion, in the composition whereby the risk of corrosion is reduced. In one preferred embodiment of the invention, the multivalent metal salt is calcium chloride.

As used herein, the term "surface treatment composition" relates to a coating or a surface sizing composition or the like.

The active material may alternatively or additionally comprise at least one acid, such as citric acid, per acetic acid, hydrochloric acid or phosphoric acid. In this way, components, such as calcium carbonate, which do not normally comply with low pH, can be used while the benefits of low pH on the printing quality still can be obtained. In one embodiment, the active material comprises a monovalent or a multivalent salt and an acid. In this way, the print quality may be further improved, since the pH reduction and the salt have dual effect on the printing quality.

The supporting material of the particles may be selected from the group consisting of waxes, such as polyethylene waxes, propylene waxes, carnauba wax, micro wax, triglycerides, PEG, metal soaps, and co-polymers of e.g. styrene/acrylate or styrene/butadiene and a combination of any of these.

Preferably, the supporting material of the particles is inert and water-resistant, or has a pre-determined solubility rate.

The supporting material may be sensitive to heat and may have a melting point or a glass transition point between a 60-180 °C, preferably between 70-110 °C. When having a melting or a glass transition point within these intervals, the supporting material can be melted in the drying or calendering of the fibrous web formed by surface treating a web with the inventive composition, whereby the active material may be released from the particles in the drying or calendering section and bloomed to the surface of the web.

The supporting material may alternatively or additionally be sensitive to a pH change. The supporting material may, e.g. be dissolved when subjected to a low pH, such as at a pH below 7, or preferably between 5 and 7. A supporting material that is sensitive to pH could, e.g., be selected from the group of methyl acrylate-methacrylic acid copolymers, cellulose acetate succinate, hydroxyl propyl methyl cellulose phthalate, hydroxyl propyl methyl cellulose acetate succinate, hypromellose acetate succinate, polyvinyl acetate phthalate (PVAP), methyl methacrylate-methacrylic acid copolymers, sodium alginate or stearic acid or mixtures of the above. Stearic acid is an example of a supporting material that is sensitive to both low pH and high temperatures.

The particles may comprise a core comprising the active material, which core is encapsulated in a shell comprising the supporting material. By creating a core-shell structure, more defined particle morphology and better stability in the suspension can be obtained. The shell may be made of the

supporting material, e.g. of a co-polymer of styrene/acrylate, which is melted, dissolved or destroyed when subjected to heat and/or pressure and/or a change in pH whereby the material within the core may be released from the particle. The core may comprise the active material in a bonded or in a separate form. The active material may e.g. be particulate, crystalline salt. Alternatively, the core may be a composite of the active material and a binding material. The binding material may be selected from the group consisting of waxes, such as polyethylene waxes, polypropylene waxes, triglycerides and metal soaps. The binding material may have a melting point between 60-180 °C, preferably between 70-110 °C. The melting point of the binding material may be similar or the same as that of the supporting material. The core may further comprise surfactants and/or chelating agents.

The supporting material may further comprise dispersed finely divided particles of an acid, such as citric acid, per acetic acid, hydrochloric acid or phosphoric acid. In one embodiment, the particles are of a core/shell construction and the core comprises a mono- or multivalent salt as an active material and the cell comprises dispersed finely divided particles of an acid. In this way, both an acid and a salt can be added to a coating/sizing composition that normally is not compatible with low pH and/or a metal salt. When the supporting material is melted, dissolved or destroyed, after the composition is applied on a fibrous web, the acid is released causing a pH reduction whereby the printability is improved. Simultaneously, the salt is released whereby the printability is further improved.

In one embodiment of the invention the particles are composites of a supporting material and an active material. Such a composite particle may, e.g., be formed of a multivalent metal salt as the active material and calcium stearate as the supporting material.

The particles may comprise the active material, e.g. the multivalent metal salt, to an amount of at least 30 wt%, preferably 40-70w%, most preferably 70-80w%. In this way, the composition may comprise a high concentration of the active material. Thus, the particles may be added to e.g. coating compositions without causing colloidal destabilization.

The supporting material may be adapted to release the active material from the particles in a subsequent step on the paper machine after the composition has been applied to a surface of a fibrous web. The supporting material may, e.g., be adapted to release the active material in the subsequent drying or calendering of the web. Alternatively, the supporting material may be adapted to release the active material in a printing press at the printing of a paper or board formed by the invention.

The particles may further comprise at least one stabilizer, such as a surfactant or a hydrocolloid. The stabilizer should be selected so that it is compatible with the charge of the other coating or sizing components in the composition. If, e.g., the composition comprises anionic components, the stabilizer should preferably be neutral, amphoteric or anionic.

The present invention is especially advantageous when adding salts of multivalent metals to surface treatment compositions

that are anionically charged, since such compositions are especially sensitive to multivalent ions, even at small concentrations.

- 5 The surface treatment composition of the invention may further comprise other components commonly used in coating or sizing compositions. The composition may, e.g., further comprise starches, carboxymethylcellulose (CMC), polyvinyl alcohol (PVA), sizing agents commonly used, such as
- 10 alkylketene dimer (AKD) or acrylic co-polymers. The composition may further comprise acid copolymers, such as methyl acrylate.

The particles' average spherical diameter may be between 100-
15 0.01 μm , preferably between 50-0.1 μm and even more preferably between 10-0.5 μm or between 1-5 μm , or 0,5 - 1,5 μm . A particle with a spherical diameter within these intervals has about the same size as a pigment particle and would therefore not cause any rheological problems or coating
20 defects in e.g. film press or blade coating.

The invention further relates to a process for the manufacture of a surface-treated and printed paper or board, such as an inkjet or flexographic printed paper or board, or
25 other fibrous webs. Said process comprises the steps of forming a fibrous web from pulp, and coating or surface sizing the fibrous web with at least one layer of the surface treatment composition of the invention. The surface sizing of the fibrous web according to the invention may be applied at
30 the drying section, e.g. in a size press, or at the wet end of the paper machine. The process further comprises the subsequent step of treating the fibrous web so that the active material is released from the particles on the surface

of the fibrous web. This may be achieved in a subsequent step in the paper machine, e.g. at the drying or calendering of the surface-treated web or by changing the pH, e.g. by activating acids comprised in the composition by the

5 application of heat. The process further comprises the step of printing the resulting coated or surface sized paper or board by use of inkjet and/or flexographic printing techniques.

10 The invention further relates to a paper or board product comprising the surface treatment composition described above and a printed paper or board comprising these products, preferably being printed by inkjet and/or flexographic printing techniques. The printed paper or board comprising

15 these paper or board products may preferably be printed with inkjet technique using water based pigmented inks. The invention is, however, not limited to solely inkjet, but can further be used to improve print quality in e.g. flexography where water based dye or pigmented inks are used. The

20 invention is further applicable for hybrid printed products, in which one of the printing methods is based on pigmented water based inkjet inks. Moreover, the invention is also applicable for printing with hybrid inks, which here relates to inks containg both dye and pigment particles.

Detailed description of the invention

5 The surface-treatment composition of the present invention comprises particles that comprise high concentrations of active materials, which active materials are released from the particles in a controlled manner after the composition has been applied on the surface of a web. Use of such
10 particles in the composition decreases rheology and viscosity problems that are connected with prior art compositions comprising as high concentrations of the active materials as the inventive composition. Consequently, higher concentrations of the active materials may be used without
15 causing rheology or viscosity problems.

By the expression "release...from the particles" as used herein means that the active material is transformed from a state wherein it is held within or in another way being a part of a
20 particle to a state wherein the active material is not a part of a particle form, but in contact with the surface of the web. Thus, the active material might be released from the particle as a separate material, or it might be released from the particle in a bonded form, e.g. bonded or in another way
25 attached to the supporting or binding material.

The invention is especially advantageous when dosing salt of multivalent ions to sizing composition, especially to anionically charged sizing composition, in order to enhance
30 the inkjet printability of a paper or board. Said salts may e.g. be calcium chloride, aluminum chloride, magnesium chloride, magnesium bromide, calcium bromide, barium chloride, calcium nitrate, magnesium nitrate, barium nitrate,

calcium acetate, magnesium acetate or barium acetate. Said anionic sizing composition may e.g. comprise anionic rosin soap sizing agents, anionic polymeric styrene maleic anhydride sizing agents or polyaluminium chloride.

5

The particles of the invention can be of a shell/core construction, with the active material being encapsulated as a core within a shell of a supporting material. Such particles can be manufactured using e.g. an emulsion
10 polymerization method.

Alternatively, the particles may be of a composite construction, comprising a mixture of the active material and the supporting material. For example, instead of forming as
15 shell/core structure, the particles may be a composite of a calcium stearate and calcium chloride. Such a particle may comprise calcium to an amount of 50 weight% or more. A calcium stearate/calcium chloride particle may be formed by mixing calcium stearate with calcium chloride, in a batch
20 process. The formed particles are thereafter stabilized by use of e.g. starch and surfactants.

The particles may also be formed by e.g. dry blending calcium stearate and calcium chloride whereupon the mixture is milled
25 and finally fractionated. The particles can then be stabilized in solution by using the said stabilizing system.

The composite materials can also be created using a spinning method, such as wet spinning, electrospinning or
30 electrospraying. In such a method, a water soluble wax is, e.g., blended with calcium chloride and then spun. The temperature of the solution should preferably be above the melting point of the supporting or binding material, e.g.

wax, in order to ensure solubility and blendability with the added components. The materials can be spun or sprayed (particulates) directly onto a substrate or indirect onto another collector plate, or alternatively, into a solution.

Claims

1. A surface treatment composition for paper, board or other fibrous webs, which composition comprises particles which comprise an active material comprising a salt of a multivalent metal and a supporting material, wherein the supporting material is adapted to release the active material from the particles when subjected to heat and/or a change in pH or when subjected to heat and pressure.
2. A composition according to claim 1, wherein the active material comprises calcium salt, such as calcium chloride.
3. A composition according to anyone of claims 1-2, wherein the active material comprises an acid.
4. A composition according to anyone of claims 1-3, wherein the supporting material is selected from the group consisting of waxes, such as polyethylene waxes, polypropylene waxes, triglycerides, metal soaps, and copolymers of e.g. styrene/acrylate or styrene/butadiene or a combination of any of these.
5. A composition according to anyone of claims 1-5, wherein the supporting material is sensitive to heat and has a melting point or a glass transition point of between 60-180° C, preferably of between 70 - 110° C.
6. A composition according to anyone of claims 1-5, wherein the particles comprise a core comprising the active material, which core is encapsulated in a shell comprising the supporting material.

7. A composition according to claim 6, wherein the core comprises the active material and a binding material and wherein the shell is made of the supporting material.

5

8. A composition according to claim 7, wherein the binding material is selected from the group consisting of waxes, such as polyethylene waxes, triglycerides, metal soaps, or co-polymers of e.g. styrene/acrylate or styrene/butadiene.

10

9. A composition according to anyone of claims 1-8, wherein the particles comprises the active material to an amount of at least 50 weight%, preferably 75 weight%, most preferably 80 weight%.

15

10. A composition according to anyone of claims 1-9, wherein the supporting material is adapted to release the active material during calendering of a paper, board or fibrous web that has been surface treated with the composition.

20

11. A composition according to anyone of claims 1-9, wherein the supporting material is adapted to release the active material during drying of a paper, board or fibrous web that has been surface treated with the composition.

25

12. A composition according to anyone of claims 1-11, wherein the particles further comprise at least one stabilizer, such as a hydrocolloid and/or surfactants.

30

13. A composition according to anyone of claims 1-12, wherein the composition is anionically, amphoterically, or nonionically charged.

5 14. A composition according to anyone of claims 1-13, wherein the composition further comprises at least one sizing or coating agent.

15. A composition according to anyone of claims 1-14,
10 wherein the particles' spherical diameter is between 100-0.01 μm , preferably between 50-0.1 μm and most preferably between 10-0.5 μm .

16. A process for the manufacture of a surface-treated
15 and printed paper, board or other fibrous web comprising the following steps:

a) forming a fibrous web from pulp,
b) coating or surface sizing the fibrous web with at least one layer, wherein the fibrous web is coated or surface
20 sized with a surface treatment composition, which composition comprises particles which comprise an active material comprising a salt of a multivalent metal and a supporting material,
c) releasing the active material from the particles on the
25 surface of the fibrous web by the application of heat and/or pressure and/or a change of pH, and
c) printing the resulting coated or surface sized paper, board or fibrous web by use of inkjet and/or flexographic printing techniques.

30

17. A process according to claim 16, wherein the step c) of releasing the active material from the particles is accomplished in the drying of the fibrous web.

18. A process according to claim 16, wherein the step
c) of releasing the active material from the particles is
accomplished in the calendering of the fibrous web.

5

19. A paper or board product comprising a surface
treatment composition of claims 1-15.

20. An ink-jet or flexographic printed paper or board
10 comprising a paper or board product being surface treated
with a composition comprising particles which comprise an
active material comprising a salt of a multivalent metal and
a supporting material, wherein the supporting material is
adapted to release the active material from the particles
15 when subjected to heat and/or pressure and/or a change in pH.

INTERNATIONAL SEARCH REPORT

 International application No.
 PCT/IB2011/050578

A. CLASSIFICATION OF SUBJECT MATTER

IPC: see extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE, DK, FI, NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, PAJ, WPI data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4020210 A (GEER LOREN E), 26 April 1977 (1977-04-26); abstract; column 2, line 32 - column 2, line 59; column 3, line 1 - column 3, line 65 --	1-2, 4-6, 9, 13-15, 19
Y	US 4091130 A (SHAW MICHAEL J), 23 May 1978 (1978-05-23); abstract; column 1, line 10 - column 1, line 49; column 2, line 4 - column 2, line 10; column 4, line 27 - column 4, line 45; column 5, line 31 - column 6, line 40; claims 11, 13 --	1-2, 4-20
Y	US 6207258 B1 (VARNELL DANIEL F), 27 March 2001 (2001-03-27); abstract; column 4, line 32 - column 4, line 40; column 11, line 22 - column 11, line 33 --	1-2, 4-20



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

11-05-2011

Date of mailing of the international search report

12-05-2011

Name and mailing address of the ISA/SE

 Patent- och registreringsverket
 Box 5055
 S-102 42 STOCKHOLM
 Facsimile No. + 46 8 666 02 86

Authorized officer

Monika Bohlin

Telephone No. + 46 8 782 25 00

INTERNATIONAL SEARCH REPORT

 International application No.
 PCT/IB2011/050578

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2008048265 A1 (INT PAPER CO ET AL), 24 April 2008 (2008-04-24); abstract; page 7, line 12 - page 7, line 25; page 13, line 13 - page 13, line 19; page 14, line 24 - page 15, line 12 --	1-20
A	EP 0829374 A2 (HEWLETT PACKARD CO), 18 March 1998 (1998-03-18); abstract; claim 1 --	1-20
A	WO 2005068916 A1 (KIMBERLY-CLARK WORLDWIDE INC), 28 July 2005 (2005-07-28); abstract; page 2, line 9 - page 2, line 12; page 5, line 7 - page 5, line 12; page 5, line 30 - page 6, line 5 --	1-20
A	GB 2015611 A (MITSUBISHI PAPER MILLS LTD), 12 September 1979 (1979-09-12); abstract --	1-20
A	GB 2201171 A (LAPORTE INDUSTRIES LTD - (B) LAPORTE INDUSTRIES LTD), 24 August 1988 (1988-08-24); abstract; page 4 second paragraph; page 10 fourth paragraph --	1-20
A	US 3287154 A (HAAS HOWARD C), 22 November 1966 (1966-11-22); abstract; column 1, line 34 - column 1, line 48; column 3, line 34 - column 3, line 71 --	1-20
A	US 20020104632 A1 (JIMENEZ GRACIELA ET AL), 8 August 2002 (2002-08-08); abstract; page 4, paragraph [0046] - page 4, paragraph [0047] --	1-20
P, A	EP 2192231 A1 (CLARIANT INT LTD), 2 June 2010 (2010-06-02); abstract; claim 1 --	1-20

INTERNATIONAL SEARCH REPORT

International application No.
PCT/IB2011/050578

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, A	FR 2939442 A1 (TOULOUSE INST NAT POLYTECH ET AL), 11 June 2010 (2010-06-11); abstract; page 2, line 16 - page 2, line 19; page 3, line 1 - page 3, line 10; page 4, line 3 - page 4, line 6; page 5, line 1 - page 6, line 23; claims 2, 4 -- -----	1-20

Continuation of: second sheet

International Patent Classification (IPC)

D21H 21/54 (2006.01)

D21H 17/65 (2006.01)

D21H 17/66 (2006.01)

Download your patent documents at www.prv.se

The cited patent documents can be downloaded:

- From "Cited documents" found under our online services at www.prv.se
(English version)
- From "Anförda dokument" found under "e-tjänster" at www.prv.se
(Swedish version)

Use the application number as username. The password is **DQHOUMLKMN**.

Paper copies can be ordered at a cost of 50 SEK per copy from PRV InterPat (telephone number 08-782 28 85).

Cited literature, if any, will be enclosed in paper form.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/IB2011/050578

US	4020210 A	26/04/1977	NONE			
US	4091130 A	23/05/1978	NONE			
US	6207258 B1	27/03/2001	NONE			
WO	2008048265 A1	24/04/2008	CA	2666699 A1	24/04/2008	
EP	0829374 A2	18/03/1998	JP	10100533 A	21/04/1998	
WO	2005068916 A1	28/07/2005	AU	2004313571 B2	20/05/2010	
			BR	PI0405409 A	08/11/2005	
			EP	1706677 A1	04/10/2006	
			JP	2007520643 T	26/07/2007	
			KR	20060111604 A	27/10/2006	
			US	20050136765 A1	23/06/2005	
GB	2015611 A	12/09/1979	NONE			
GB	2201171 A	24/08/1988	NONE			
US	3287154 A	22/11/1966	NONE			
US	20020104632 A1	08/08/2002	MX	PA00012547 A	25/04/2003	
EP	2192231 A1	02/06/2010	NONE			
FR	2939442 A1	11/06/2010	NONE			