

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
7 July 2005 (07.07.2005)

PCT

(10) International Publication Number
WO 2005/061099 A1

(51) International Patent Classification⁷: **B01J 20/06**,
20/08, 20/20, 20/32, C02F 1/28, 1/62, B01D 53/04, B01J
20/28

(21) International Application Number:
PCT/US2003/039925

(22) International Filing Date:
16 December 2003 (16.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant: **CALGON CARBON CORPORATION**
[US/US]; 500 Calgon Carbon Drive, Pittsburgh, PA 15205
(US).

(72) Inventor: **VO, Toan, Phan**; 94, Jessica Lane, Niskayuna,
NY 12309 (US).

(74) Agents: **WETTACH, Thomas, C.** et al.; Cohen &
Grigsby, P.C., 15th floor, 11 Stanwix Street, Pittsburgh,
PA 15222 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- with amended claims

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ADSORBENTS FOR REMOVING HEAVY METALS AND METHODS FOR PRODUCING AND USING THE SAME

(57) Abstract: Adsorbents for removing anions of a heavy metals comprise a porous carbon in which at least one oxygen-containing compound of iron, copper, and/or aluminum is incorporated. The oxygen-containing compound may be incorporated into the porous carbon by impregnation or dispersion of a suitable precursor of such a compound. The precursor may be further treated to yield the oxygen-containing compound. Such adsorbents are particularly useful for removing arsenic and/or selenium from the environment and may be used in treating drinking water sources.

WO 2005/061099 A1

ADSORBENTS FOR REMOVING HEAVY METALS AND METHODS FOR PRODUCING AND USING THE SAME

FIELD OF INVENTION

The present invention relates to adsorbents for removing heavy metals from a medium adjacent thereto and methods for producing and using the same. In particular, the present invention relates to adsorbents for removing arsenic and/or selenium from a medium adjacent thereto and methods for producing and using the same.

BACKGROUND OF THE INVENTION

It has been known that many heavy metals, such as lead, arsenic, and selenium, are toxic to humans even at low levels. One cause for the presence of these heavy metals in the environment has been increasing industrial activities in the recent past. However, in some parts of the world, high levels of heavy metals, such as arsenic, exist naturally in underground water sources because of natural occurrence of these metals in rock formations. Recent epidemiological studies on the carcinogenicity of arsenic have triggered increasing concern about the concentration of arsenic in drinking water and have prompted reevaluation of the current United States maximum contaminant level ("MCL") of 50 µg/l for arsenic. Some recent studies on long-term human exposure show that arsenic in drinking water can be associated with liver, lung, kidney, and bladder cancer. Over exposure to selenium has been shown to have undesired effects on the nervous system and to contribute to the cause dyspnea, bronchitis, and gastrointestinal disturbance.

Many experimental techniques have been proposed or tested for removing arsenic. All of these techniques have achieved varying degrees of effectiveness when arsenic is first oxidized to As(V). Coagulation using alum or ferric sulfate has been shown to have an effect on arsenic levels at a near neutral pH in laboratory and pilot-plant tests. However, the efficiency of this process decreases sharply at low or high pHs. Moreover, the coagulant containing arsenic must be filtered, resulting in additional costs. Lime softening techniques have been shown to be effective at pH levels greater than about

10.5; and, therefore, is not likely to be applicable in drinking water applications. Adsorption treatment methods using activated alumina or ion exchange have been proposed and tested on a pilot-plant scale. However, adsorption of arsenic on alumina is seriously compromised when other ions are present, such as selenium, fluoride, chloride, and sulfate. The adsorption process using ion exchange adsorbents can remove arsenic, but sulfate, total dissolved solids ("TDS"), selenium, fluoride, and nitrate also compete with arsenic for the ion exchange capacity, thus decreasing likely effectiveness.

Therefore, there is a need to provide simple and convenient materials and methods for removing heavy metals such as arsenic and/or selenium from the environment that do not have the disadvantages of the prior-art materials and methods. It is also desirable to provide convenient materials and methods for removing arsenic and/or selenium from the environment, which materials and methods can be made widely available at low cost.

SUMMARY OF THE INVENTION

The present invention provides adsorbents and methods for removing heavy metals that exist as anions from the environment to acceptable levels. An adsorbent comprises a carbon adsorbent having at least one oxygen-containing compound incorporated therein wherein said oxygen-containing compound is of a metal selected from the group consisting of iron, copper, and aluminum. In one embodiment of the present invention, the oxygen-containing compound of a metal is selected from the group consisting of oxides and hydroxides. In another embodiment of the present invention, the oxygen-containing compound of a metal is incorporated into the carbon adsorbent by a method of impregnating or dispersing at least a compound of said metal in the carbon adsorbent.

Another embodiment of the present invention provides a method for producing a carbon adsorbent capable of removing heavy metals that exist as anions. The method comprises the steps of: (1) providing a carbon adsorbent; (2) impregnating the adsorbent with at least one compound of a metal selected from the group consisting of iron, copper, and aluminum or combinations thereof; and (3) converting said compound into at least

one oxygen-containing compound. In another embodiment, the method comprises the steps of: (1) providing a carbonaceous material; (2) mixing at least one compound of a metal selected from the group consisting of iron, copper, and aluminum or combinations thereof into the carbonaceous material to produce a mixture of said carbonaceous material and said metal; (3) forming the mixture into particles of a carbonaceous material containing said metal; and (4) converting the particles of said carbonaceous material containing said metal into particles of a carbon adsorbent containing said metal.

Alternatively, a carbon adsorbent of the present invention for use in removing metal anions from a liquid or gas medium may be made by: (1) pulverizing a carbonaceous material, a binder, and at least one compound of a metal selected from the group consisting of iron, copper, and aluminum or combinations thereof to form a powdered mixture; (2) compacting said powdered mixture into shaped objects; and (3) crushing and screening the shaped objects into a metal-containing particulate material to produce said carbon adsorbent. Preferably, in step one, the carbonaceous material, binder and metal compound is pulverized together or, alternatively, the carbonaceous material, binder and metal compound are pulverized separately before making the pulverized mixture. Preferably in step two, the compacting is accomplished by briquetting, pelletizing, densifying or extruding processes. The method may also have an additional step four comprising gasifying said metal containing particulate material to produce said carbon adsorbent. In an embodiment, the gasifying of step four is conducted under an atmosphere comprising an oxygen-containing gas at a temperature in a range from about 900⁰ C to about 1100⁰ C for a time sufficient to produce an adsorbent having a BET surface area of at least 100 m²/g. The method may also comprise the additional step of oxidizing said metal-containing particulate material before the step of gasifying.

In another preferred embodiment of the present invention the method for removing heavy metals that exist as anions comprises the steps of: (1) providing a carbon adsorbent containing a metal selected from the group consisting of iron, copper, and aluminum; and (2) contacting said carbon adsorbent containing said metal with a medium containing the heavy metal anions. In all embodiments, the medium may be a liquid or gas phase in which the metals exist as anions. Preferably, the medium is drinking water.

Other features and advantages of the present invention will be apparent from a perusal of the following detailed description of the invention.

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides an adsorbent for removing heavy metal from a medium that comprises a carbon having at least one oxygen-containing compound of a metal incorporated therein, wherein said metal is selected from the group consisting of iron, copper, and aluminum. Some heavy metals such as arsenic and selenium normally exist in the environment as anions and, thus, are soluble in water and difficult to be removed therefrom. One theory why conventional adsorption methods of water treatment using conventional solid adsorbents (such as activated carbon or alumina) are not very effective is because the adsorbents typically develop negative charges on their surfaces when immersed in water. Therefore, their surfaces tend to repulse the heavy metals anions, leading to low adsorption capacities for these anions. The present invention provides carbon adsorbents that overcome this shortcoming of traditional carbon adsorbents by incorporating at least an oxygen-containing compound of a metal selected from the group consisting of iron, copper, and aluminum into a porous carbon. It is contemplated that these and similar metals having metal oxides or hydroxides which are stable in liquid phase would work in the present invention. The carbon adsorbents of the present invention retain a substantial amount of their microporosity enabling them to remove heavy metal anions such as arsenic and selenium anions as well as organic materials from the surrounding medium such as liquid or gas. In a preferred embodiment, the medium is drinking water.

A metal-containing carbon adsorbent of the present invention is preferably a microporous carbon adsorbent, which has a large surface area as measured by the Brunauer-Emmett-Teller ("BET") method and has a substantial micropore volume for pores having diameter less than about 2 nm. As used herein, "micropore volume" is the total volume of pores having diameter less than 2 nm. Suitable carbon adsorbents for use in the present invention are those having a BET surface area greater than about 100 m²/g, preferably greater than about 200 m²/g, more preferably greater than about 400 m²/g, and

most preferably greater than about 600 m²/g. In general, it is contemplated that the higher surface areas will capture metal anions and other contaminants, especially organics. These carbon adsorbents typically have a micropore volume greater than about 20 cm³/100g. Preferably, the carbon adsorbents have a micropore volume greater than about 5 30 cm³/100g, more preferably greater than about 40 cm³/100g, and most preferably greater than about 50 cm³/100g.

Suitable carbon adsorbents for use in the present invention may be made from any of a variety of starting carbonaceous materials such as, but not limited to, coals of various ranks such as anthracite, semianthracite, bituminous, subbituminous, brown coals, or 10 lignites; nutshell; wood; vegetables such as rice hull or straw; residues or by-products from petroleum processing; and natural or synthetic polymeric materials. The carbonaceous material may be processed into carbon adsorbents by any conventional thermal or chemical method known in the art before incorporating the metal therein. They will inherently impart different surface areas and pore volumes. Generally, for 15 example, lignites can result in carbon having surface areas about 500-600 m²/g and, typically, fiber-based carbons areas are about 1200-1400 m²/g. Certain wood-based carbons may have areas in the range of about 200 m²/g, but tend to have a very large pore volume which is generally suitable for depositing large amounts of impregnates. Surface area and pore volume of coal based carbon may also be made to allow for some control of 20 surface area and pore volumes. Preferably, the carbon is an activated carbon adsorbent. Alternatively, at least one metal may be incorporated into the carbonaceous starting material, then the mixture may be processed into carbon adsorbents containing one or more of such metals.

In an embodiment, the carbon adsorbent contains metal at a concentration of up to 25 about 50% by weight of the carbon. Preferably, the metal is present at a concentration in the range from about 1% to about 40% or, more preferably, from about 2% to about 30% and, more preferably, from about 3% to about 20% by weight of the carbon.

In another embodiment of the present invention, a microporous carbon adsorbent is impregnated with at least one salt of a metal selected from the group consisting of iron,

copper, and aluminum. Examples of such salts include halides, nitrates, sulfates, chlorates, carboxylates having from one to five carbon atoms such as formates, acetates, oxalates, malonates, succinates, or glutarates of iron, copper, or aluminum. The impregnated salts are then converted to oxygen-containing compounds of iron, copper, or aluminum by either thermal decomposition or chemical reaction. Preferred forms of the oxygen-containing compounds are hydroxides and oxides.

The following examples illustrate preferred embodiments of the present invention.

EXAMPLE 1

Preparation of an iron-impregnated carbon adsorbent:

4.6 ml of an aqueous ferric chloride solution (having a concentration of 100g ferric chloride in 40 ml water) was diluted with 40.3 g of deionized water. This solution was poured slowly into 50.0 g of oven-dried 12x30 mesh (U.S. sieve series) coconut shell-based PCBTM activated carbon (Calgon Carbon Corporation, Pittsburgh, Pennsylvania) contained in a pyrex glass dish. PCBTM activated carbon has a BET surface area of about 1050 m²/g and a micropore volume of about 60 cm³/100g. The impregnated carbon was stirred thoroughly while the solution was being poured into the carbon. The wet impregnated carbon was dried in an oven at 105⁰ C for 2 hours based on the amount of ferric chloride solution used for the impregnation. The dried impregnated carbon had an iron content of about 7.9 % by weight of the carbon. The dried impregnated carbon was taken out of the oven and cooled down in a hood. A KOH solution was prepared by dissolving 12.47 g of KOH pellets in 60.02 g deionized water. The KOH solution was poured into the dried impregnated carbon. This amount of KOH was enough to completely wet the impregnated carbon without leaving an excess solution. The wet KOH-treated carbon was transferred into a 2000-ml beaker and the beaker was filled with deionized water. The water from the beaker was decanted and fresh deionized was added to wash potassium chloride from the impregnated carbon. This process of washing was repeated until the pH of the solution was about 7, as indicated by pH paper. The wet carbon was then dried in an oven at 105⁰ C overnight. It

was expected that the iron in the carbon would be in the form of ferric hydroxide. The dried ferric hydroxide-impregnated carbon was pulverized in a titanium vial containing tungsten abrading balls for testing of the removal of heavy metal anions. This impregnated carbon was identified as "3224-31-1."

5 Testing of Arsenic Removal:

An aqueous arsenic solution having an arsenic concentration of about 100 parts per billion ("ppb") by weight was prepared for testing by diluting into deionized water an appropriate amount of an arsenic standard solution of arsenic trioxide in 10 % (by weight) nitric acid.

10 Polyethylene bottles having a nominal volume of 500 ml and magnetic stirring bars were cleaned with dilute nitric acid solution and dried. An appropriate amount of the pulverized impregnated carbon adsorbent 3224-31-1, as disclosed above, was put into a cleaned and dried polyethylene bottle containing a magnetic stirring bar. An amount of about 500 g of the arsenic solution prepared as disclosed above was put into the bottle.

15 The bottle was then put on a multi-position stirring plate and the stirring continued for about 24 hours. At the end of the 24-hour period, a sample of the solution in the bottle was taken and filtered. The residual concentration of arsenic in the solution was analyzed by ICP/MS method. Many such bottles were prepared during the same experiment, each had a different amount of pulverized carbon adsorbent. In addition, a control bottle was

20 also prepared in which no carbon adsorbent was added. The results of this testing are shown in Table 1A below. The limit of detection for this method of analysis was 0.3 ppb. This carbon could reduce the level of arsenic to less than detection limit with a small dose of the carbon.

Table 1A

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with pH meter)
3208-17B	0	83.8	4
3208-17F	0.0249	19.8	4
3208-17G	0.0496	1.25	4.1
3208-17A	0.0998	< 0.3	4.2

Testing of this carbon was conducted with another aqueous arsenic solution having a targeted concentration of about 300 ppb similarly prepared. The results are shown in Table 1B.

5

Table 1B

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with pH meter)
3208-37A-6	0	331	3.4
3208-37A-2	0.05	171	3.4
3208-37A-3	0.10	54.4	No data
3208-37A-4	0.20	5.5	No data

Although a coconut shell-based carbon was used in this example it is understood that other activated carbons may be equally applicable for the present invention. An economically attractive carbon for the present invention is one made from bituminous coal in a steam gasification process. For example, activated carbons suitable for the present invention may be those made from wood chips in a chemical activation process employing phosphoric acid, or those made from phosphoric acid treatment of petroleum residue, or activated carbons made from gasification of carbonized polymeric materials, such as those derived from phenolic resins or polyesters. Activated carbons suitable for

the present invention may have the form of powder, granule, sphere, pellet, honeycomb, woven or nonwoven fiber, mat, or felt.

EXAMPLE 2

The same oven-dried PCBTM carbon was impregnated with ferric chloride to achieve a ferric ion loading of about 15.8 % by weight of the carbon using the same manufacturing method as in Example 1. An arsenic solution having a targeted concentration of about 1 part per million ("ppm") was prepared from the arsenic trioxide standard solution as above. The results of this experiment are shown in Table 2. This carbon could remove a very high level of arsenic (841 ppb) to less than detection limit with only a small dose of the carbon.

Table 2

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with pH meter)
3246-18M	0	841	6.4
3246-18O	0.50	< 0.3	6.3
3246-18Q	2.50	< 0.3	No data

EXAMPLE 3

Preparation of iron (II) impregnated carbon adsorbent:

An iron (II) impregnated activated carbon was prepared similarly to the process disclosed in Example 1, except a ferrous chloride solution was prepared for impregnation, instead of ferric chloride. 1.778g of FeCl₂·4H₂O was dissolved into 40.0 g of deionized water. The ferrous chloride solution was impregnated into 50.0 g of oven-dried 12x30 mesh PCBTM activated carbon. The dried impregnated carbon had a nominal iron (II) loading of about 1% by weight. The dried impregnated carbon was reacted with a KOH solution consisting essentially of 1.27 g of KOH pellet dissolved in 70.16 g of deionized

water. The washed and dried impregnated carbon was pulverized as above and labeled as "3224-32-1" for testing.

Testing for arsenic removal:

The arsenic solution and the method of testing were similar to those disclosed in Example 1. The results of the testing are shown in Table 3.

Table 3

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with a pH meter)
3208-18F	0	348	3.4
3208-18A	0.0253	307	No data
3208-18B	0.0500	279	No data
3208-18C	0.1001	211	3.4
3208-18D	0.2000	116	No data
3208-18E	0.5002	8.2	3.8

EXAMPLE 4

Oven-dried 12x30 PCBTM activated carbon was impregnated with aluminum chloride in the same manner as disclosed in Example 1. The aluminum chloride solution was prepared by dissolving 89.48 g of AlCl₃·6H₂O in 80.0 g of deionized water. The solution was impregnated into 100 g of oven-dried 12x30 PCBTM activated carbon. Thus, the impregnated carbon has an aluminum loading of about 10% by weight of the carbon. The aluminum chloride-impregnated carbon was reacted with a solution containing 63.17 g KOH in 120 g deionized water. The steps of washing, drying, and pulverizing were the same as those of Example 1. An arsenic solution having a targeted As concentration of about 1 ppm was prepared for testing. The arsenic removal testing was the same as that disclosed in Example 1 except different amounts of impregnated carbon were used. The results are shown in Table 4.

Table 4

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with pH meter)
3246-18A	0	851	5.6
3246-18C	0.51	333	7.6
3246-18E	2.50	4.84	No data
3246-18F	5.00	4.19	No data

EXAMPLE 5

Preparation of carbon adsorbent containing ferric oxide:

3.7325 g of $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ was dissolved into 37.70 g of deionized water. This solution was poured over a 50.02 g of oven dried 12x30 mesh PCBTM carbon in a glass dish. The impregnated carbon was mixed thoroughly and then dried in an oven at 105^o C for 3 hours. The dried impregnated carbon was charged into a quartz tube having an inner diameter of about 2.54 cm. The carbon was retained in place by a piece of glass wool at each end. The quartz tube was inserted in a horizontal tube furnace and heated from ambient temperature to about 300^o C in 30 minutes, then held at that temperature for about 20 hours. The temperature was subsequently increased to 500^o C in about 20 minutes and held for an additional 3 hours. The heating was conducted under a flow of nitrogen at substantially ambient pressure at about 300 cm³/minute. The tube with the carbon still inside was cooled down under nitrogen flow to ambient temperature. It was expected that ferric nitrate decomposed to ferric oxide under this treatment condition. A representative sample of the ferric oxide-loaded carbon was pulverized as described in Example 1 above for testing. The results of the testing are shown in Table 5. The results show that arsenic was removed even at low doses of carbon.

Table 5

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with pH meter)
3208-19F	0	326	No data
3208-19A	0.010	317	No data
3208-19B	0.026	299	No data
3208-19C	0.050	271	No data
3208-19D	0.100	222	No data
3208-19E	0.200	131	No data

EXAMPLE 6

Preparation of carbon adsorbent containing iron (III):

Meadow River bituminous coal (a bituminous coal from West Virginia, U.S.A.)

5 was pulverized with 4% (by weight of the coal) coal tar pitch and 10% (by weight of the coal) Fe_3O_4 powder so that at least 90% of the pulverized material passed through 325 mesh screen (U.S. sieve series). Alternatively, the coal, pitch binder, and the iron powder may be pulverized separately and then mixed together after pulverization. The powder mixture was compacted in a Fitzpatrick roll press at about 1.5 MPa into elongated

10 briquettes of about 1cm wide, about 0.5 cm thick, and about 3-4 cm long. Other briquette shapes and sizes also may be used. The mixture also may be extruded into pellets instead of the above pressing to briquettes. The compaction pressure may be appropriately chosen for the particular coal used. It may be higher or lower than the pressure disclosed above, but typically is in the range from about 8 MPa to about 16 MPa. The briquettes

15 were crushed and screened to produced particles having a mesh size of about 6x14. The produced particles were oxidized under an excess flow of air in an indirectly heated rotary kiln, the temperature of which was increased from ambient to about 250⁰ C at a rate of 45⁰ C per hour, and then from 250⁰ C to about 450⁰ C at a rate of 60⁰ C per hour. Other oxidizing gases also may be used, such as a mixture of oxygen and air or an inert gas,

20 which mixture has an oxygen concentration greater than about 21% by volume, or a

combustion product from a combustor containing oxygen, steam, and other gases. The resulting oxidized iron-containing coal particulate material was gasified in steam at 925-950⁰ C for about 40-45 minutes to produce an iron-containing porous carbon adsorbent of the present invention. The step of gasifying the carbon precursor, such as this coal particulate, in an oxidizing atmosphere is usually termed "activation." It should be understood that the activation temperature and time are chosen to be appropriate for the type of coal, the compaction technique, the type of activation furnace used in the process of manufacture, and the desired microporosity of the activated product. Generally, higher-rank coals and higher compaction would require a higher temperature and/or a longer time. A longer activation time produces a more porous activated carbon. Activation furnace types that provide a very intimate contact between the solid and the gas phase and a well-mixed solid therein usually require a shorter activation time. Activation temperature is typically in the range from about 900⁰ C to about 1100⁰ C, and activation time is typically in the range from about 10 minutes to about 10 hours. In addition to steam, other oxygen-containing gases may also be present. The steps of oxidizing the coal particles and of gasifying the oxidized coal particles were carried out in this example in a rotary kiln. However, other types of furnaces or kilns may also be used in which an intimate contact between the solid and the gas phase can be maintained. Suitable furnaces or kilns are fluidized-bed kilns, belt furnaces, and Herreshoff furnaces. A representative sample of this adsorbent was pulverized in titanium vials using tungsten balls as disclosed above for testing.

Testing for arsenic removal:

An arsenic solution was prepared similarly to that of Example 1, except the targeted As concentration was 1 ppm. The testing procedure was similar to that described in Example 1. The results of the testing are shown in Table 6.

Table 6

Bottle Number	Amount of Carbon Adsorbent (g)	Residual As Concentration (ppb)	pH (measured with pH meter)
3246-18G	0	837	5.9
3246-18I	0.5	685	6.4
3246-18K	2.5	20	No data
3246-18L	5.0	21.7	No data

EXAMPLE 7

Testing for selenium removal

The carbon of Example 1 was tested for selenium removal. A solution containing
5 selenium was prepared as follows.

An aqueous selenium solution having a selenium concentration of about 300 parts
per billion by weight was prepared for testing by diluting into Milli-Q water an
appropriate amount of a 1000 ppm selenium standard reference solution. The reference
solution was purchased from Fisher Scientific and is commonly used as the standard
10 solution for atomic absorption spectroscopy.

The method of testing was similar to that described in Example 1. The results of
the testing are shown in Table 7.

Table 7

Bottle Number	Amount of Carbon Adsorbent (g)	Residual Se Concentration (ppb)	pH (measured with pH meter)
Control 1	0	273	No data
3224-31-1B	0.10	39.3	6.1
3224-31-1C	0.25	15.5	6.2
3224-31-1D	0.50	9.7	6.4
3224-31-1E	1.00	8.1	6.6

EXAMPLE 8

Testing for selenium removal

- 5 The carbon of Example 5 was tested for selenium removal. The solution containing selenium was prepared as described in Example 7.

The method of testing was similar to that described in Example 1. The results of the testing are shown in Table 8.

Table 8

Bottle Number	Amount of Carbon Adsorbent (g)	Residual Se Concentration (ppb)	pH (measured with pH meter)
Control 3	0	289	No data
3129-28F-2	0.10	15.6	6.1
3129-28F-3	0.25	6.2	6.2
3129-28F-4	0.50	6.2	6.4
3129-28F-5	1.01	3.3	6.6

EXAMPLE 9

Testing for selenium removal

The carbon of Example 4 was tested for selenium removal. A solution containing selenium was prepared to have a target selenium concentration of about 300 ppb by diluting a selenium atomic absorption standard solution containing 100 ppm selenium dioxide in water.

The method of testing was similar to that described in Example 1. The results of the testing are shown in Table 9.

Table 9

Bottle Number	Amount of Carbon Adsorbent (g)	Residual Se Concentration (ppb)	pH (measured with pH meter)
Control 2	0	295	No data
3246-14B-2	0.11	23.7	6.2
3246-14B-3	0.26	4.7	6.2
3246-14B-4	0.50	2.2	6.3
3246-14B-5	1.00	1.1	6.4

The adsorbents of the present invention may be used to remove heavy metal anions from a medium adjacent thereto in many arrangements. Granular particles of the adsorbents of the present invention may be installed in a fixed bed or a fluidized bed. Granular adsorbents are particularly suitable to be packaged in small cartridges for installation at the point of use. An adsorbent in powder form may be injected into a stirred tank and then removed by filtration or settling. Adsorbents in fiber form may be inserted in a section of the water supply piping. Furthermore, in certain circumstances, it may be advantageous to include at least one other type of adsorbents in a treatment of the medium. Such other types of adsorbents are, for example, zeolites, ion exchange resins, silica gel, alumina, and unimpregnated activated carbons.

While various embodiments are described herein, it will be appreciated from the specification that various combinations of elements, variations, equivalents, or improvements therein may be made by those skilled in the art, and are still within the scope of the invention as defined in the appended claims.

WHAT IS CLAIMED IS:

1. A carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium comprising a porous carbon having a BET surface area greater than about 100 m²/g and having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of iron, copper and aluminum, or combinations thereof.
2. The adsorbent according to claim 1, wherein said oxygen-containing compound of metal is incorporated into said porous carbon by impregnation or dispersion within said adsorbent.
3. The adsorbent according to claim 1, wherein said oxygen-containing compound of metal is an oxide or hydroxide.
4. The adsorbent according to claim 1, wherein said heavy metal is selected from the group consisting of arsenic, selenium and combinations thereof.
5. The adsorbent according to claim 1, wherein said adsorbent has a micropore volume of greater than about 20 cm³/100g.
6. The adsorbent according to claim 1, wherein said metal is present at a concentration of up to about 50% by weight of said carbon.
7. An adsorbent for removing metal anions from a liquid or gas medium surrounding said adsorbent, said adsorbent comprising a porous carbon having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of iron, copper and aluminum or combinations thereof, wherein said metal is present at a concentration in the range from about 0.01 to about 50 percent by weight of said porous carbon; said oxygen-containing compound being selected from the group consisting of oxides, hydroxides and

combinations thereof; and said adsorbent having a BET surface area greater than about 100 m²/g.

8. A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium containing metal anions comprising the steps of:
 - (1) providing a porous carbonaceous adsorbent;
 - (2) impregnating said porous carbonaceous adsorbent with a solution comprising at least one compound of at least one metal selected from the group consisting of iron, copper, and aluminum or combinations thereof; and
 - (3) converting said compound into an oxygen-containing compound of said metal to produce said carbon adsorbent.
9. The method according to claim 8, wherein said porous carbonaceous adsorbent is an activated carbon.
10. The method according to claim 8, wherein said compound of said metal is selected from the group consisting of halides, nitrates, sulfates, chlorates, carboxylates having one to five carbon atoms.
11. The method according to claim 8, wherein said step of converting consists of thermal decomposition or chemical reaction.
12. The method according to claim 8, wherein said one metal is present at a concentration of up to about 50% by weight of said porous carbonaceous adsorbent.
13. The method according to claim 8, wherein said oxygen-containing compound is an oxide or hydroxide.

14. The method according to claim 9, wherein said activated carbon has a BET surface area greater than about 100 m²/g and is selected from the group consisting of coal, wood, nut shell, petroleum residue and vegetable-based activated carbons.
15. The method according to claim 9, wherein said activated carbon is selected from the group consisting of coal, wood, nut shell, petroleum residue, vegetable-based activated carbons and has a micropore volume greater than about 20 cm³/100g of adsorbent.
16. A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium, said method comprising the steps of:
 - (1) pulverizing a carbonaceous material, a binder, and at least one compound of a metal selected from the group consisting of iron, copper, and aluminum or combinations thereof to form a powdered mixture;
 - (2) compacting said powdered mixture into shaped objects;
 - (3) crushing and screening the shaped objects into a metal-containing particulate material; and
 - (4) gasifying said metal-containing particulate material to produce said carbon adsorbent.
17. The method according to claim 16, wherein said carbonaceous material, said binder, and said at least one compound of said metal are pulverized together.
18. The method according to claim 16, wherein said carbonaceous material, said binder, and said at least one compound of said metal are pulverized separately before said pulverized mixture is made.
19. The method according to claim 16, wherein said compacting is selected from the group consisting of briquetting, pelletizing, densifying, and extruding.

20. The method according to claim 16, wherein said gasifying is conducted under an atmosphere comprising an oxygen-containing gas at a temperature in a range from about 900⁰ C to about 1100⁰ C, for a time sufficient to produce an adsorbent having a BET surface area of at least 100 m²/g.
21. The method according to claim 16 further comprising the step of oxidizing said metal-containing particulate material before the step of gasifying.
22. A method for removing heavy metal anions from a fluid or gas medium containing metal anions, said method comprising the steps of:
- (1) providing an adsorbent comprising a porous carbon having a BET surface area greater than about 100 m²/g and having deposited therein at least one oxygen-containing compound of at least one metal selected from the group consisting of iron, copper, and aluminum;
 - (2) contacting a portion of said medium with said adsorbent; and
 - (3) obtaining a treated medium having a lower concentration of said heavy metal than a concentration of said heavy metal of said medium;
- wherein said anions contain oxygen; said heavy metal is selected from the group consisting of arsenic, selenium, and combinations thereof; said oxygen-containing compound is selected from the group consisting of oxides, hydroxides, and combinations thereof; said at least one metal is present at a concentration from about 0.01 to about 50 percent by weight of said porous carbon.
23. The method according to claim 22, wherein said adsorbent has a micropore volume of greater than about 20 cm³/100g of adsorbent.
24. The method according to claim 22, wherein said adsorbent has a form selected from the group consisting of granule, pellet, sphere, powder, woven fabric, non-woven fabric, mat, felt, block, and honeycomb.

25. The method according to claim 22, wherein said adsorbent is disposed at a point of use.
26. The method according claim 25, wherein said adsorbent is disposed in a fixed bed.
27. The method according claim 26, wherein said adsorbent is disposed in a section of a water supply piping of a house.
28. The method according to claim 26, wherein said fixed bed comprises a cartridge that is disposed at a water faucet.
29. The method according to claim 28, wherein said cartridge further comprises at least one adsorbent selected from the group consisting of zeolites, ion exchange resins, silica gel, alumina, and unimpregnated activated carbons.

AMENDED CLAIMS

[Received by the International Bureau on 11 April 2005 (11.04.2005)
original claims 1,3,6-8,16 amended ; new claims 30-41 added]

1. A carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium comprising a porous carbon having a BET surface area greater than about $100 \text{ m}^2/\text{g}$ and having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of iron (II) and aluminum, or combinations thereof, wherein said adsorbent is capable of interacting with said anions of said heavy metal to lower a concentration of said heavy metal in said liquid or gas.
2. The adsorbent according to claim 1, wherein said oxygen-containing compound of metal is incorporated into said porous carbon by impregnation or dispersion within said adsorbent.
3. The adsorbent according to claim 1, wherein said oxygen-containing compound of at least one metal is an oxide or hydroxide.
4. The adsorbent according to claim 1, wherein said heavy metal is selected from the group consisting of arsenic, selenium and combinations thereof.
5. The adsorbent according to claim 1, wherein said adsorbent has a micropore volume of greater than about $20 \text{ cm}^3/100\text{g}$.
6. The adsorbent according to claim 1, wherein said at least one metal selected from the group consisting of iron (II) and aluminum, or combinations thereof are present at a concentration of up to about 50% by weight of said carbon.
7. An adsorbent for removing heavy metal anions from a liquid or gas medium surrounding said adsorbent, said adsorbent comprising a porous carbon having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of iron (II) and aluminum or combinations thereof, wherein said metal is present at a concentration in the range from about 0.01 to about 50 percent by weight of said porous carbon; said oxygen-containing compound being selected from the group consisting of oxides, hydroxides and combinations thereof; and said adsorbent having a BET surface area greater than about $100 \text{ m}^2/\text{g}$, wherein said adsorbent is capable of interacting with said anions of said heavy metal to lower a concentration of said heavy metal in said liquid or gas.
8. A method for making a carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium containing said heavy metal, said method comprising the steps of:
 - (1) providing a porous carbonaceous adsorbent;

- (2) impregnating said porous carbonaceous adsorbent with a solution comprising at least one compound of at least one metal selected from the group consisting of iron (II) and aluminum or combinations thereof; and
- (3) converting said compound into an oxygen-containing compound of said metal to produce said carbon adsorbent;

wherein said adsorbent is capable of interacting with said anions of said heavy metal to lower a concentration of said heavy metal in said liquid or gas.

9. The method according to claim 8, wherein said porous carbonaceous adsorbent is an activated carbon.
10. The method according to claim 8, wherein said compound of said metal is selected from the group consisting of halides, nitrates, sulfates, chlorates, carboxylates having one to five carbon atoms.
11. The method according to claim 8, wherein said step of converting consists of thermal decomposition or chemical reaction.
12. The method according to claim 8, wherein said one metal is present at a concentration of up to about 50% by weight of said porous carbonaceous adsorbent.
13. The method according to claim 8, wherein said oxygen-containing compound is an oxide or hydroxide.
14. The method according to claim 9, wherein said activated carbon has a BET surface area greater than about $100 \text{ m}^2/\text{g}$ and is selected from the group consisting of coal, wood, nut shell, petroleum residue and vegetable-based activated carbons.
15. The method according to claim 9, wherein said activated carbon is selected from the group consisting of coal, wood, nut shell, petroleum residue, vegetable-based activated carbons and has a micropore volume greater than about $20 \text{ cm}^3/100\text{g}$ of adsorbent.
16. A method for making a carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium, said method comprising the steps of:
 - (1) pulverizing a carbonaceous material, a binder, and at least one compound of a metal selected from the group consisting of iron (II) and aluminum or combinations thereof to form a powdered mixture;
 - (2) compacting said powdered mixture into shaped objects;
 - (3) crushing and screening the shaped objects into a metal-containing particulate material; and

- (4) gasifying said metal-containing particulate material to produce said carbon adsorbent;

wherein said adsorbent is capable of interacting with said anions of said heavy metal to lower a concentration of said heavy metal in said liquid or gas.

17. The method according to claim 16, wherein said carbonaceous material, said binder, and said at least one compound of said metal are pulverized together.

18. The method according to claim 16, wherein said carbonaceous material, said binder, and said at least one compound of said metal are pulverized separately before said pulverized mixture is made.

19. The method according to claim 16, wherein said compacting is selected from the group consisting of briquetting, pelletizing, densifying, and extruding.

20. The method according to claim 16, wherein said gasifying is conducted under an atmosphere comprising an oxygen-containing gas at a temperature in a range from about 900⁰ C to about 1100⁰ C, for a time sufficient to produce an adsorbent having a BET surface area of at least 100 m²/g.

21. The method according to claim 16 further comprising the step of oxidizing said metal-containing particulate material before the step of gasifying.

22. A method for removing heavy metal anions from a fluid or gas medium containing metal anions, said method comprising the steps of:

- (1) providing an adsorbent comprising a porous carbon having a BET surface area greater than about 100 m²/g and having deposited therein at least one oxygen-containing compound of at least one metal selected from the group consisting of iron, copper, and aluminum;
- (2) contacting a portion of said medium with said adsorbent; and
- (3) obtaining a treated medium having a lower concentration of said heavy metal than a concentration of said heavy metal of said medium;

wherein said anions contain oxygen; said heavy metal is selected from the group consisting of arsenic, selenium, and combinations thereof; said oxygen-containing compound is selected from the group consisting of oxides, hydroxides, and combinations thereof; said at least one metal is present at a concentration from about 0.01 to about 50 percent by weight of said porous carbon.

23. The method according to claim 22, wherein said adsorbent has a micropore volume of greater than about 20 cm³/100g of adsorbent.

24. The method according to claim 22, wherein said adsorbent has a form selected from the group consisting of granule, pellet, sphere, powder, woven fabric, non-woven fabric, mat, felt, block, and honeycomb.
25. The method according to claim 22, wherein said adsorbent is disposed at a point of use.
26. The method according claim 25, wherein said adsorbent is disposed in a fixed bed.
27. The method according claim 26, wherein said adsorbent is disposed in a section of a water supply piping of a house.
28. The method according to claim 26, wherein said fixed bed comprises a cartridge that is disposed at a water faucet.
29. The method according to claim 28, wherein said cartridge further comprises at least one adsorbent selected from the group consisting of zeolites, ion exchange resins, silica gel, alumina, and unimpregnated activated carbons.
30. A carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium comprising a porous carbon having a BET surface area greater than about 100 m²/g and having incorporated therein iron (III) hydroxide, wherein said adsorbent is capable of interacting with said anions of said heavy metal to lower a concentration of said heavy metal in said liquid or gas.
31. The adsorbent according to claim 30, wherein said anions comprise oxygen-containing species of said heavy metal.
32. The adsorbent according to claim 31, wherein said iron (III) hydroxide is incorporated into said porous carbon by impregnation or dispersion within said adsorbent.
33. The adsorbent according to claim 31, wherein said heavy metal is selected from the group consisting of arsenic, selenium, and combinations thereof.
34. The adsorbent according to claim 31, wherein said iron (III) is present at a concentration of up to about 50% by weight of said carbon.
35. A method for making a carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium containing said heavy metal anions, said method comprising the steps of:
- (1) providing a porous carbonaceous adsorbent;
 - (2) impregnating said porous carbonaceous adsorbent with a solution comprising at least one compound of iron (III); and

- (3) converting said compound into iron (III) hydroxide to produce said carbon adsorbent;

wherein said carbon adsorbent is capable of lowering a concentration of said heavy metal anions in said liquid or gas medium.

36. The method according to claim 35, wherein said at least one compound of said iron (III) is selected from the group consisting of halides, nitrates, sulfates, chlorates, carboxylates having one to five carbon atoms.

37. A method for making a carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium, said method comprising the steps of:

- (1) pulverizing a carbonaceous material, a binder, and at least one compound of iron (III) to form a powdered mixture;
- (2) compacting said powdered mixture into shaped objects;
- (3) crushing and screening the shaped objects into an iron (III)-containing particulate material; and
- (4) gasifying said iron (III)-containing particulate material to produce said carbon adsorbent;

wherein said carbon adsorbent is capable of lowering a concentration of said heavy metal anions in said liquid or gas medium.

38. The method according to claim 37, wherein said carbonaceous material, said binder, and said at least one compound of said iron (III) are pulverized separately before said mixture is made.

39. The method according to claim 37, wherein said gasifying is conducted under an atmosphere comprising an oxygen-containing gas at a temperature in a range from about 900⁰ C to about 1100⁰C, for a time sufficient to produce an adsorbent having a BET surface area of at least 100 m²/g.

40. A carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium comprising a porous carbon having a BET surface area greater than about 100 m²/g and having incorporated therein copper hydroxide, wherein said adsorbent is capable of interacting with said anions of said heavy metal to lower a concentration of said heavy metal in said liquid or gas.

41. The adsorbent according to claim 40, wherein said anions comprise oxygen-containing species of said heavy metal.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 03/39925

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 B01J20/06 B01J20/08 B01J20/20 B01J20/32 C02F1/28
 C02F1/62 B01D53/04 B01J20/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 B01J C02F B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
 EPO-Internal, WPI Data, PAJ, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	BRIAN E. REED: "As(III), As(V), Hg, and Pb removal by Fe-oxide impregnated activated carbon" JOURNAL OF ENVIRONMENTAL ENGINEERING, vol. 126, no. 9, September 2000 (2000-09), pages 869-873, XP008035441 USA the whole document	1-7, 22-24
X	B. PETRUSEVSKI: "Adsorbent -based point-of-use system for arsenic removal in rural areas" JOURNAL OF WATER SUPPLY , RESEARCH AND TECHNOLOGY, 2002, pages 135-144, XP008035365 page 138 - page 139 page 137, left-hand column	1-7, 22-26

Further documents are listed in the continuation of box C. Patent family members are listed in annex.

° Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p>
--	--

Date of the actual completion of the international search 28 January 2005	Date of mailing of the international search report 09. 07 2005
---	--

Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Hilgenga, K
--	--

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/39925

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 369 072 A (M. M. BENJAMIN) 29 November 1994 (1994-11-29) column 6, line 64 - column 7, line 6 column 6, line 3 - line 4 column 7, line 62 - line 65 -----	8-14
A	US 6 599 429 B1 (AZIZIAN FARID) 29 July 2003 (2003-07-29) column 2, line 34 - line 45 column 2, line 66 - column 3, line 4 abstract -----	1-4,6-8, 10-13, 22,24
E	US 2004/089608 A1 (VO TOAN PHAN) 13 May 2004 (2004-05-13) the whole document -----	1-29
E	DE 103 33 824 A (FRANZ DIETRICH OESTE) 1 July 2004 (2004-07-01) page 4, paragraph 15 page 4, right-hand column, line 21 -----	1-4
X	US 4 877 920 A (LUSH ET AL) 31 October 1989 (1989-10-31) column 1, line 55 - line 59 column 1, line 5 - line 10 column 1, line 60 - column 2, line 2 -----	1-7
X	US 4 532 115 A (NISHINO ET AL) 30 July 1985 (1985-07-30) column 3, line 3 - line 13 column 1, line 47 - line 51 -----	1-3,6-14
X	EP 0 719 584 A (NORITAKE CO., LIMITED) 3 July 1996 (1996-07-03) page 4, line 3 - line 8 page 7, line 1 - line 3 page 4, line 22 - line 26 -----	16,18,19
X	US 2003/196966 A1 (HUGHES KENNETH D) 23 October 2003 (2003-10-23) paragraph '0043!; claims 1,9,15 -----	1-4,6,7, 22,24,25
A	DATABASE WPI Section Ch, Week 197537 Derwent Publications Ltd., London, GB; Class A97, AN 1975-60932W XP002315607 & JP 49 033896 A (AGENCY OF IND SCI & TECHNOLOGY) 28 March 1974 (1974-03-28) abstract -----	16,18,19
	----- -/--	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/39925

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	L.J. RAJAKOVIC: "The Sorption of Arsenic onto Activated Carbon Impregnated with Metallic Silver and Copper" SEPARATION SCIENCE AND TECHNOLOGY, vol. 27, no. 11, 1992, pages 1423-1433, XP008042154 the whole document -----	1,2, 4-10,12, 14,15, 22-24
A	DATABASE WPI Section Ch, Week 198640 Derwent Publications Ltd., London, GB; Class D15, AN 1986-260866 XP002315619 & JP 61 187931 A (ASAHI CHEM IND CO LTD) 21 August 1986 (1986-08-21) abstract -----	1-3,7-9, 13,22

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 03/39925

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:

3. Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- The additional search fees were accompanied by the applicant's protest.
- No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1 (partially)-6, 7(partially), 8(partially)-15,
22(partially)-29

A carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium comprising a porous carbon having a BET surface greater than about 100 m²/g and having incorporated therein at least one oxygen-containing compound of iron.

An adsorbent for removing metal anions from a liquid or gas medium surrounding said adsorbent, said adsorbent comprising a porous carbon having incorporated therein at least one oxygen-containing compound of iron wherein said metal is present at a concentration in the range from about 0.01 to about 50 percent by weight of said porous carbon; said oxygen-containing compound being selected from the group consisting of oxides, hydroxides and combination thereof; and said adsorbent having a BET surface area greater than about 100 m²/g.

A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium containing metal anions comprising the steps of:

- (1) providing a porous carbonaceous adsorbent;
- (2) impregnating said porous carbonaceous adsorbent with a solution comprising at least one compound of iron; and
- (3) converting said compound into an oxygen-containing compound of said metal to produce said carbon adsorbent.

A method for removing heavy metal anions from a fluid or gas medium containing metal anions, said method comprising the steps of:

- (1) providing an adsorbent comprising a porous carbon having a BET surface area greater than about 100 m²/g and having deposited therein at least one oxygen-containing compound of iron;
- (2) contacting a portion of said medium with said adsorbent; and
- (3) obtaining a treated medium having a lower concentration of said heavy metal than a concentration of said heavy metal of said medium.

2. claims: 16 (partially)-21

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium, said method comprising the steps of:

- (1) pulverizing a carbonaceous material, a binder, and at least one compound of iron to form a powdered mixture;
- (2) compacting said powdered mixture into shaped objects;
- (3) crushing and screening the shaped objects into a metal-containing particulate material; and
- (4) gasifying said metal-containing particulate material to produce said carbon adsorbent.

3. claims: 1 (partially)-6,7 (partially),8(partially)-15, 16 (partially)-21, 22(partially)-29

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

A carbon adsorbent for use inand having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of copper, a combination of copper with aluminium, a combination of copper with iron and a combination of copper, iron and aluminium.

An adsorbent for removing metal anions..... having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of copper, a combination of copper with aluminium, a combination of copper with iron and a combination of copper, iron and aluminium wherein said metal is present at a concentration in the range from about 0.01 to about 50 percent by weight of said porous carbon; said oxygen-containing compound being selected from the group consisting of oxides , hydroxides.....

A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium containing metal anions comprising the steps of :

- (1) providing a porous carbonaceous adsorbent;
- (2) impregnating said porous carbonaceous adsorbent with a solution comprising at least one compound of at least one metal selected from the group consisting of copper, a combination of copper with aluminium, a combination of copper with iron and a combination of copper, iron and aluminium

A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium, said method comprising the steps of:

- (1) pulverizing a carbonaceous material, a binder, and at least one compound of a metal selected from the group consisting of copper, a combination of copper with aluminium, a combination of copper with iron and a combination of copper, iron and aluminium to form a powdered mixture;
- (2) compacting said powdered mixture into shaped objects;
- (3) crushing and screening the shaped objects into a metal-containing particulate material.....

A method for removing heavy metal anions from a fluid or gas medium containing metal anions, said method comprising the steps of:

- (1) providing an adsorbent comprising a porous carbon having a BET surface area greater than about 100 m²/g and having deposited therein at least one oxygen-containing compound of at least one metal selected from the group consisting of copper, a combination of copper with aluminium, a combination of copper with iron and a combination of copper, iron and aluminium.....

4. claims: 1 (partially)-6,7 (partially), 8 (partially)-15
 ,16(partially)-21, 22(partially)-29

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

A carbon adsorbent for use in removing heavy metal anions from a liquid or gas medium comprising a porous carbon having a BET surface greater than about 100 m²/g and having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of aluminum or a combination of aluminum and iron.

An adsorbent for removing metal anions from a liquid or gas medium surrounding said adsorbent, said adsorbent comprising a porous carbon having incorporated therein at least one oxygen-containing compound of at least one metal selected from the group consisting of aluminum or a combination of aluminum and iron wherein said metal is present at a concentration in the range from about 0.01 to about 50 percent by weight of said porous carbon; said oxygen-containing compound being selected from the group consisting of oxides, hydroxides and combination thereof; and said adsorbent having a BET surface area greater than about 100 m²/g.

A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium containing metal anions comprising the steps of:

- (1) providing a porous carbonaceous adsorbent;
- (2) impregnating said porous carbonaceous adsorbent with a solution comprising at least one compound of at least one metal selected from the group consisting of aluminum or a combination of aluminum and iron; and
- (3) converting said compound into an oxygen-containing compound of said metal to produce said carbon adsorbent.

A method for making a carbon adsorbent for use in removing metal anions from a liquid or gas medium, said method comprising the steps of:

- (1) pulverizing a carbonaceous material, a binder, and at least one compound of a metal selected from the group consisting of aluminum and a combination of aluminum and iron to form a powdered mixture;
- (2) compacting said powdered mixture into shaped objects.....

A method for removing heavy metal anions from a fluid or gas medium containing metal anions, said method comprising the steps of:

- (1) providing an adsorbent comprising a porous carbon having a BET surface area greater than about 100 m²/g and having deposited therein at least one oxygen-containing compound of at least one metal selected from the group consisting of aluminum or a combination of aluminum and iron.....

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/39925

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5369072	A	29-11-1994	US 5911882 A	15-06-1999
US 6599429	B1	29-07-2003	AU 743349 B2	24-01-2002
			AU 3429399 A	18-10-1999
			BR 9909332 A	12-12-2000
			CA 2327087 A1	07-10-1999
			CN 1303353 T	11-07-2001
			CZ 20003435 A3	14-11-2001
			EP 1070019 A1	24-01-2001
			WO 9950182 A1	07-10-1999
			HU 0102208 A2	28-10-2001
			JP 2002509801 T	02-04-2002
			RU 2225251 C2	10-03-2004
			SK 14642000 A3	09-04-2001
			ZA 200005116 A	02-01-2002
US 2004089608	A1	13-05-2004	NONE	
DE 10333824	A	01-07-2004	DE 10333824 A1	01-07-2004
US 4877920	A	31-10-1989	NONE	
US 4532115	A	30-07-1985	JP 1736074 C	26-02-1993
			JP 4024092 B	24-04-1992
			JP 59160535 A	11-09-1984
			JP 1736087 C	26-02-1993
			JP 4024093 B	24-04-1992
			JP 60071039 A	22-04-1985
			CA 1216136 A1	06-01-1987
			DE 3467096 D1	10-12-1987
			EP 0121339 A2	10-10-1984
			HK 12290 A	23-02-1990
			SG 2290 G	06-07-1990
EP 0719584	A	03-07-1996	JP 2766459 B2	18-06-1998
			JP 8173800 A	09-07-1996
			DE 69531038 D1	17-07-2003
			DE 69531038 T2	19-02-2004
			EP 0719584 A1	03-07-1996
			US 5685986 A	11-11-1997
US 2003196966	A1	23-10-2003	WO 03089112 A1	30-10-2003
JP 49033896	A	28-03-1974	NONE	
JP 61187931	A	21-08-1986	JP 1757004 C	23-04-1993
			JP 4045213 B	24-07-1992