

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 June 2009 (04.06.2009)

PCT

(10) International Publication Number
WO 2009/068157 A1

(51) International Patent Classification:

B01J 31/18 (2006.01) **C07C 2/36** (2006.01)
B01J 31/14 (2006.01) **C07F 9/46** (2006.01)

(21) International Application Number:

PCT/EP2008/009305

(22) International Filing Date:

5 November 2008 (05.11.2008)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

07023013.1 28 November 2007 (28.11.2007) EP

(71) Applicants (for all designated States except US): **LINDE AG** [DE/DE]; Klosterhofstrasse 1, 80331 München (DE). **SAUDI BASIC INDUSTRIES CORPORATION** [SA/SA]; P.O. Box 5101, 11422 Riyadh (SA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ALIYEV, Vugar** [SA/SA]; c/o Saudi Basic Industries Corporation, P.O. Box 5101, 11422 Riyadh (SA). **AL-HAZMI, Mohammed, Hassan** [SA/SA]; c/o Saudi Basic Industries Corporation, P.O. Box 5101, 11422 Riyadh (SA). **MOSA, Fuad** [SA/SA]; c/o Saudi Basic Industries Corporation, P.O. Box 5101, 11422 Riyadh (SA). **FRITZ, Peter, M.** [DE/DE]; Truderinger Str. 21, 82008 Unterhaching (DE). **BÖLT, Heinz** [DE/DE]; Kanalstr. 21, 85515 Wolfratshausen (DE). **WÖHL, Anina** [DE/DE]; Wolfratshausener Str. 86a, 82049 Pullach (DE). **MÜLLER, Wolfgang** [DE/DE]; Jaspersallee 36, 81245 München (DE). **WINKLER,**

Florian [DE/DE]; Holzstr. 49, 80469 München (DE). **WELLENHOFER, Anton** [DE/DE]; Torriweg 33, 81247 München (DE). **ROSENTHAL, Uwe** [DE/DE]; Hahnenkamp 9, 18069 Lambrechtshagen (DE). **MÜLLER, Bernd, H.** [DE/DE]; Gellertstr. 7, 18057 Rostock (DE). **HAPKE, Marko** [DE/DE]; Thomas-Müntzer-Platz 13, 18057 Rostock (DE). **PEULECKE, Normen** [DE/DE]; Bühnenweg 3, 23968 Wismar (DE).

(74) Agents: **SCHOLZ, Volker** et al.; Boehmert & Boehmert, Hollerallee 32, 28209 Bremen (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(54) Title: CATALYST COMPOSITION AND PROCESS FOR OLIGOMERIZATION OF ETHYLENE

(57) Abstract: The present invention relates to a catalyst composition comprising: (a) a binuclear chromium(II) complex; (b) a ligand of the general structure (A) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-H$ or (B) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-PR_6R_7$, wherein $R_1, R_2, R_3, R_4, R_5, R_6$ and R_7 are independently selected from halogen, amino, trimethylsilyl, C_1-C_{10} -alkyl, aryl and substituted aryl, wherein the PNP- or PNPNP-unit is optionally part of a ring system; and (c) an activator or co-catalyst, as well as to a process for oligomerization of ethylene.

WO 2009/068157 A1

Catalyst composition and process for oligomerization of ethylene

The present invention relates to a catalyst composition and a process for the oligomerization of ethylene.

Linear alpha-olefins (LAOs) are very useful intermediates for the manufacture of detergents, synthetic lubricants, co-polymers, plasticizer alcohols and many other important products. There are several producers of such LAOs via oligomerization of ethylene, e.g. SHELL, BP, SABIC, AMOCO, CHEVRON PHILIPS etc.. An intrinsic problem of all of these metal-catalyzed ethylene oligomerization processes is the production of LAO mixtures following a mathematical distribution (Schulz-Flory or Poisson), which is difficult to separate and whose composition often does not match market demands. To solve this technical and economical unsatisfying situation, there is a deep interest to overcome the technical limitations and to transform the non-selective ethylene oligomerization reactions into more selective processes. Recently these activities are predominantly concentrated on the selective trimerization of ethylene to 1-hexene (review: D.H. Morgan et al. *J. Organomet. Chem.* 2004, 689, 3641; and refs. Cited therein) as well as the selective tetramerization of ethylene to 1-octene (recent review: D. Wass, *Dalton Trans.* 2007, 816).

Several patents for the trimerization of ethylene to 1-hexene and the tetramerization of ethylene to 1-octene are already known. In most of these cases different chromium precatalysts in combination with a broad array of different ligand systems and activating agents (like main group metal alkyl compounds) were utilized.

Prior art chromium based ethylene trimerization catalyst with chromium compounds, organoaluminum activators and different ligands are those listed e.g. in the following patent publications: US Patent 4,668,838; EP 0 668 105; US Patent 5,750,817; US Patent 6,031,145; US Patent 5,811,681; EP 537609; EP 1574492; US 2004783429; WO 2005039758; FR 2833191; US 2002035029; WO 2002004119; WO 2001083447 and EP 1110930. Here, various chelating and non-chelating donor ligands and a large number of Cr(III) precursor complexes were claimed. In WO 2003004158, Cr(II) complexes such as chromium(II)acetate were

claimed in conjunction with substituted cyclopentadienes as suitable ligand systems, in addition to the already described and utilized Cr(III) complexes. In WO 2003053891, also Cr(II) complexes such as, e.g., chromium(II)acetate are claimed. The claimed ligands are bis(2-diphenylphosphino-ethyl)amines and derivatives thereof.

Prior art ethylene tetramerization catalysts include a number of different transition metal compounds, organoaluminum activators or different ligands, that have been used in the same or slightly modified form for the trimerization process. Patents concerning the tetramerization are: US Patent No. 6,184,428; US Patent No. 3,676,523; DE Patent 14 43 927; US Patent No. 3,906,053; WO 2005/086251; WO 2006108803, WO 2006099053, WO 2007057455, WO 2007057458 and WO 2007088329. In most of these patents, the obtained mixture of olefins does not contain more than 25 weight-% 1-octene. In some of the most recent applications, different PNP- and similar chelating donor ligands were claimed in conjunction with Cr(III) complexes only (WO 2004/056478 and WO 2004/056479). These applications were the first to demonstrate that in ethylene oligomerization a high selectivity towards 1-octene (up to 70 mass-%) with significantly less simultaneous 1-hexene production can be achieved. It was pointed out that the formed nine-membered ring systems (chromacyclononane) are the reason for the selective tetramerization of ethylene to 1-octene with 70% mass selectivity.

The selective ethylene trimerization and tetramerization catalysts and processes known generally have to cope with some disadvantages. The catalysts show only low selectivities to the desired products 1-hexene and/or 1-octene due to by-products from side reaction channels. Further limited purities of the products are obtained, i.e. the selectivities within the specific C₆- or C₈-cut due to isomerization, branched olefin formation, etc.. Also wax formation, i.e. formation of heavy, long-chain, high carbon-number products is detected. This is also true for polymer formation (polyethylene, branched and/or cross-linked polyethylene) leading to considerable product yield loss and fouling of equipment. Further it has to be mentioned that prior art processes only show poor turnover rates and catalyst activity resulted in high cost per kg product. Prior art catalysts and ligands are usually to be prepared with high costs. Ligands are usually difficult to synthesize, resulting in poor availability and high catalyst cost. The catalyst performance is highly susceptible to trace impurities, and the catalyst components are often difficult to handle in technical environment. The prior art processes usually require

harsh reaction conditions, i.e. high temperatures and pressures, resulting in high invest, maintenance and energy costs. Finally, high costs are also to be expected for co-catalyst/activator.

It is therefore an object of the present invention to overcome the difficulties of the prior art and to provide a catalyst composition showing improved selectivities and purities in the oligomerization of ethylene without formation of wax or polymer, showing rather improved turnover rates with fair costs for preparing catalyst and ligand.


Additionally, a process for the oligomerization of ethylene shall be provided.


The first object is achieved by a catalyst composition comprising: (a) a binuclear chromium(II) complex; (b) a ligand of the general structure (A) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-H$ or (B) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-PR_6R_7$, wherein R_1 , R_2 , R_3 , R_4 , R_5 , R_6 and R_7 are independently selected from halogen, amino, trimethylsilyl, C_1 - C_{10} -alkyl, aryl and substituted aryl, wherein the PNP- or PNP- unit is optionally part of a ring system; and (c) an activator or co-catalyst.

As is to be understood, any cyclic derivatives of (A) and (B) can be utilized as ligand, wherein at least one of the P or N atoms of the PNP- unit (structure (A)) or PNP- unit (structure (B)) is a ring member, the ring being formed from one or more constituent compounds of structures (A) or (B) by substitution, i. e. by formally eliminating per constituent compound either two whole groups R_1 - R_7 (as defined) or H, one atom from each of two groups R_1 - R_7 (as defined) or a whole group R_1 - R_7 (as defined) or H and an atom from another group R_1 - R_7 (as defined), and joining the formally so-created valence-unsaturated sites by one covalent bond per constituent compound to provide the same valence as initially present at a given site.


Preferably, the chromium complex has a Cr-Cr-bond or two chromium centres are connected via a bridging ligand.

Most preferably, the binuclear chromium complex is selected from:






6



7



8

In one embodiment, R₁, R₂, R₃, R₄, R₅, R₆ and R₇ are selected from chloro, amino, trimethylsilyl, methyl, ethyl, isopropyl, tert-butyl, phenyl, benzyl, tolyl and xylyl.

In another embodiment, the activator or co-catalyst is selected from trimethyl aluminium, triethyl aluminium, triisopropylaluminum, triisobutyl aluminium, ethylaluminum sesquichloride, diethylaluminum chloride, ethyl aluminium dichloride, methylaluminoxane (MAO) or mixtures thereof.

The ligand may be selected from $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{CH}_3)\text{-N}(\text{i-Pr})\text{-H}$, $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{i-Pr})\text{-H}$, $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{Ph})\text{-H}$, $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{tert-butyl})\text{-H}$ and $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{CH}(\text{CH}_3)(\text{Ph}))\text{-H}$.

Preferably, the catalyst composition comprises a solvent, which may be selected from aromatic hydrocarbons, straight-chain and cyclic aliphatic hydrocarbons, straight-chain olefins and ethers, preferably toluene, benzene, ethyl benzene, cumene, xylenes, mesitylene, hexane, octane, cyclohexane, methylcyclohexane, hexene, heptene, octene, diethylether or tetrahydrofuran or mixtures thereof, most preferably toluene.

A second object of the invention is achieved by a process for oligomerization of ethylene, comprising subjecting a catalyst composition according to the invention to a gas phase of ethylene in a reactor and conducting an oligomerization.

Preferably, the oligomerization is carried at a pressure of 1 to 200 bar, preferably 10 to 50 bar.

Also preferred, the oligomerization is carried at a temperature of from 10 to 200°C, preferably 20 to 100°C.

In one embodiment, the process is carried out continuously, semi-continuously or discontinuously.


The mean residence time may be from 10 minutes to 20 hours, preferably 1 to 4 hours.

Most preferred, the process is a trimerization or tetramerization.

Surprisingly it was found that a process for oligomerization of ethylene utilizing the inventive catalyst composition avoids the broad spectrum of LAO products and allows for the selective production of the economically most desired products, namely 1-hexene and 1-octene. Unprecedented high selectivity, purity and sufficiently high active/turnover frequency are achieved.


The current invention is based on the fact that the selective tetramerization of ethylene to 1-octene and the trimerization of ethylene to 1-hexene can proceed more efficiently by using a binuclear transition metal complex, rather than a mononuclear transition metal complex, whose mechanism involves mononuclear metallocyclononanes and metallacycloheptanes, respectively.

Without wishing to be bound to any theory, it is assumed that for the binuclear chromium complexes utilized in a tetramerization reaction a mechanism is suggested wherein the reaction proceeds via metallocyclopentanes which the C₄-chain dimerizes to a saturated C₈-chain between the metal centers as illustrated in the following scheme:



The above mechanism is characterized by the novel principle of a dinuclear reductive elimination from chromium(II) via chromium(I) to chromium(0) leading to 1-octene.

The catalyst composition according to the present invention can be tuned by suitable ligands to the novel principle of dinuclear reductive elimination from chromium(0) via chromium(I) to chromium(0) (case: neutral ligands) or from chromium(I)/(II) via chromium(II)/(I) to chromium(I)/(0) (case: anionic ligands) leading selectively to 1-hexene:



Additionally, it was surprisingly found that the modification of a tridentate ligand, such as $(\text{phenyl})_2\text{P-N(isopropyl)-P(phenyl)}_2$ by an additional NH(isopropyl) unit resulted in the tetradentate ligand $((\text{phenyl})_2\text{PN(isopropyl)P(phenyl)NH(isopropyl)})$. Utilizing the former ligand in the catalyst composition resulted in a high selectivity towards the tetramerization of ethylene, whereas the latter ligand resulted in a high selectivity for the trimerization or tetramerization of ethylene depending on the substituents, as will be shown below in the examples section.

In other words, the inventive process results in the production of 1-octene and 1-hexene with high turnover rate and selectivity. An easy switchover from 1-octene to 1-hexene production by using specific ligands can be easily obtained. Further, a high reproducibility is obtained, e.g. the catalyst system is stable against interference from impurities and fluctuations in process conditions. Formation of wax and polymers is well suppressed. Additionally, in the inventive process slight reaction conditions may be employed, consequently resulting in low investment costs for technical-scale plant and low energy and operation costs.

Additional advantages and features of the present invention will become apparent from the following detailed description on the basis of examples.

A ligand to be used in the inventive catalyst composition may be prepared as follows:

Preparation of $\text{Ph}_2\text{PN}(\text{i-Pr})\text{PMeNH}(\text{i-Pr})$: 2,21 g of Ph_2PCl (10 mmol) was slowly added to a mixture of 1,62 g $\text{MeP}(\text{NH}(\text{i-Pr}))_2$ (10mmol) (Eur. J. Inorg. Chem. 1999, 12, 2355-68) and 5ml triethylamine in 15 ml toluene at 0°C . The solution was stirred for additional 2h at r.t. and then filtered to remove the amine-hydrochloride. After evaporation of the volatile compounds in vacuo a sticky oil remained. Yield: 80%

^{31}P -NMR (C_6D_6); 33.7, 57.6 (broad)

Trimerization by binuclear complexes

Example 1:

Ethylene trimerization using $\{[(\text{i-Pr})_2\text{N}]\text{Cr}[\mu\text{-(i-Pr)}_2\text{N}]\}_2$, $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{phenyl})\text{NH}(\text{isopropyl}))$ and triethylaluminum

A 300 ml pressure reactor, equipped with dip tube, thermowell, gas entrainment stirrer, cooling coil, control units for temperature, pressure and stirrer speed (all hooked up to a data acquisition system) was inertized with dry argon and filled with 100 ml anhydrous toluene. Then 81.7 mg (0.2 mmol) of $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{phenyl})\text{NH}(\text{isopropyl}))$ in 10 ml toluene was combined with 65.6 mg $\{[(\text{i-Pr})_2\text{N}]\text{Cr}[\mu\text{-(i-Pr)}_2\text{N}]\}_2$ (0.13 mmol) under an argon blanket. This catalyst solution was transferred to the reactor under constant argon flow, along with 3.6 ml of a 1.9 mol/l solution of triethylaluminium in toluene.

The reactor was sealed, pressurized with 30 bar dry ethylene and heated to 50°C . While stirring at 1200 rpm, the ethylene consumption was monitored by the data acquisition system and an electronic balance by constantly weighing the ethylene pressure cylinder. After 120 min residence time, the reaction in the liquid phase was quenched by transferring the liquid inventory by means of the ethylene pressure to a glass vessel filled with approx. 100 ml of water. The entire gas phase from the reactor's head space was quantified by a calibrated gas meter and was then collected quantitatively in a purged and evacuated gas bag.

After separation of the liquid organic phase, the total mass was determined by weighing. Subsequently, the composition of the organic phase was analyzed separately by GC/FID. Based on the measured data, the mass balance was closed and the overall yields and selectivities were determined. The product distribution of this example is summarized in Table 1.

Comparative Example 2:

Ethylene trimerization using $\text{CrCl}_3(\text{tetrahydrofuran})_3$, $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{phenyl})\text{NH}(\text{isopropyl}))$ and triethylaluminum

In analogy to Example 1 a 300 ml pressure reactor was filled with 100 ml anhydrous toluene. A solution of 81.7 mg (0.2 mmol) of $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{phenyl})\text{NH}(\text{isopropyl}))$ in 10 ml toluene was combined with 50.0 mg (0.13 mmol) $\text{CrCl}_3(\text{tetrahydrofuran})_3$ under a argon blanket. This catalyst solution was transferred to the reactor along with 3.6 ml of a 1.9 mol/l solution of triethylaluminium in toluene. The reactor was sealed, pressurized with 30 bar dry ethylene and heated to 50°C. After 120 min residence time while stirring at 1200 rpm the reaction mixture was worked up and analyzed as mentioned above. The product distribution of this example is summarized in Table 1.

The comparison shows higher activity for binuclear complexes.

Table 1. Ethylene trimerization runs

Example	Activity, kg prod./g Cr	C ₆ -Yield, wt%	C ₈ -Yield, wt%	1-hex in C ₆
1	145	88	1	99.0
2	34	89	1	99.0

Tetramerization by binuclear compounds

Example 3:

Ethylene tetramerization using $\{[(i\text{-Pr})_2\text{N}]\text{Cr}[\mu\text{-}(i\text{-Pr})_2\text{N}]\}_2$, $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{methyl})\text{NH}(\text{isopropyl}))$ and triethylaluminum

In analogy to Example 1 a 300 ml pressure reactor was filled with 100 ml anhydrous toluene and a solution of 69.3 mg of $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{methyl})\text{NH}(\text{isopropyl}))$ (0.2 mmol) in 10 ml toluene together with 65.6 mg $\{[(i\text{-Pr})_2\text{N}]\text{Cr}[\mu\text{-}(i\text{-Pr})_2\text{N}]\}_2$ (0.13 mmol). After adding 3.6 ml of a 1.9 M solution of triethylaluminum in toluene the reactor was sealed, pressurized with 30 bar dry ethylene and heated to 50°C. After 120 min residence time while stirring at 1200 rpm the reaction mixture was worked up and analyzed as mentioned above. The product distribution of this example is summarized in Table 2.

Comparative Example 4:

Ethylene oligomerization using $\text{CrCl}_3(\text{tetrahydrofuran})_3$, $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{methyl})\text{NH}(\text{isopropyl}))$ and triethylaluminum

In analogy to Example 1 a 300 ml pressure reactor was filled with 100 ml anhydrous toluene and a solution of 69.3 mg of $((\text{phenyl})_2\text{PN}(\text{isopropyl})\text{P}(\text{methyl})\text{NH}(\text{isopropyl}))$ (0.2 mmol) in 10 ml toluene together with 50.0 mg $\text{CrCl}_3(\text{tetrahydrofuran})_3$ (0.13 mmol). After adding 3.6 ml of a 1.9 M solution of triethylaluminum in toluene the reactor was sealed, pressurized with 30 bar dry ethylene and heated to 50°C. After 120 min residence time while stirring at 1200 rpm the reaction mixture was worked up and analyzed as mentioned above. The product distribution of this example is consistent with a Schulz-Flory distribution and summarized in Table 2.

Table 2. Ethylene tetramerization runs

Example	Activity, kg prod./g Cr	C ₆ -Yield, wt%	C ₈ -Yield, wt%	1-hex in C ₆	1-oct in C ₈
3	21	8	82	98.0	98.0
4	33	30	28	98.0	98.0

As can be seen from the examples, by changing the ligand utilized in the catalyst composition an easy switch from trimerization (Example 1 and 2) to tetramerization (Example 3) may be achieved. Furthermore by using binuclear chromium(II) complexes an easy switch from unselective oligomerization (Example 4) to tetramerization (Example 3) is possible.

The features disclosed in the foregoing description and in the claims may, both separately and in any combination thereof, be material for realizing the invention in diverse forms thereof.

Claims

1. Catalyst composition comprising:

(a) a binuclear chromium(II) complex;

(b) a ligand of the general structure

(A) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-H$ or


(B) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-PR_6R_7$,

wherein R_1 , R_2 , R_3 , R_4 , R_5 , R_6 and R_7 are independently selected from halogen, amino, trimethylsilyl, C_1 - C_{10} -alkyl, aryl and substituted aryl, wherein the PNP- or PNP- unit is optionally part of a ring system; and


(c) an activator or co-catalyst.

2. Catalyst composition according to claim 1, wherein the chromium complex has a Cr-Cr-bond or two chromium centers are connected via a bridging ligand.


3. Catalyst composition according to any of the preceding claims, wherein the binuclear chromium complex is selected from:




1




2




3




4




5



6



7



8

4. Catalyst composition according to any of the preceding claims, wherein R_1 , R_2 , R_3 , R_4 , R_5 , R_6 and R_7 are selected from chloro, amino, trimethylsilyl, methyl, ethyl, isopropyl, tert-butyl, phenyl, benzyl, tolyl and xylyl.

5. Catalyst composition according to any of the preceding claims, wherein the activator or co-catalyst is selected from trimethyl aluminium, triethyl aluminium, triisopropyl aluminium, triisobutyl aluminium, ethylaluminum sesquichloride, diethylaluminum chloride, ethyl aluminium dichloride, methylaluminoxane (MAO) or mixtures thereof.
6. Catalyst composition according to any of the preceding claims, wherein the ligand is selected from $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{CH}_3)\text{-N}(\text{i-Pr})\text{-H}$, $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{i-Pr})\text{-H}$, $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{Ph})\text{-H}$, $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{tert-butyl})\text{-H}$ and $(\text{Ph})_2\text{P-N}(\text{i-Pr})\text{-P}(\text{Ph})\text{-N}(\text{CH}(\text{CH}_3)(\text{Ph}))\text{-H}$.
7. Catalyst composition according to any of the preceding claims additionally comprising a solvent.
8. Catalyst composition according to claim 7, wherein the solvent is selected from aromatic hydrocarbons, straight-chain and cyclic aliphatic hydrocarbons, straight-chain olefins and ethers, preferably toluene, benzene, ethyl benzene, cumene, xylenes, mesitylene, hexane, octane, cyclohexane, methylcyclohexane, hexene, heptene, octene, diethylether or tetrahydrofuran or mixtures thereof, most preferably toluene.
9. Process for oligomerization of ethylene, comprising subjecting a catalyst composition according to any of the claims 1 to 8 to a gas phase of ethylene in a reactor and conducting an oligomerization at a temperature of from 20 to 100°C.
10. Process according to claim 9, wherein the oligomerization is carried at a pressure of 1 to 200 bar, preferably 10 to 50 bar.
11. Process according to claim 9 or 10, wherein the process is carried out continuously.

12. Process according to any of the claims 9 to 11, wherein the mean residence time is from 10 minutes to 20 hours, preferably 1 to 4 hours.

13. Catalyst composition, obtainable by combining at least:

(a) a binuclear chromium(II) complex;

(b) a ligand of the general structure

(A) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-H$ or

(B) $R_1R_2P-N(R_3)-P(R_4)-N(R_5)-PR_6R_7$,

Wherein R_1 , R_2 , R_3 , R_4 , R_5 , R_6 and R_7 are independently selected from halogen, amino, trimethylsilyl, C_1 - C_{10} -alkyl, aryl and substituted aryl, wherein the PNP- or PNPNP-unit is optionally part of a ring system; and

(c) an activator or co-catalyst.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2008/009305

A. CLASSIFICATION OF SUBJECT MATTER
 INV. B01J31/18 B01J31/14 C07C2/36 C07F9/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 B01J C07C C07F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
 EPO-Internal, CHEM ABS Data, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2006/293546 A1 (NABIKA MASAOKI [JP]) 28 December 2006 (2006-12-28) paragraphs [0015] - [0024] paragraph [0026] claims 1-7; examples 1-6, comp1, comp2	1-13
A	US 2007/027350 A1 (NABIKA MASAOKI [JP]) 1 February 2007 (2007-02-01) paragraphs [0012] - [0021] paragraph [0023] claims 1-7; examples 1-4, comp1, comp2	1-13
A	US 4 668 838 A (BRIGGS JOHN R [US]) 26 May 1987 (1987-05-26) claim 1; example II; table II	1-13
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

22 December 2008

Date of mailing of the international search report

07/01/2009

Name and mailing address of the ISA/
 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040,
 Fax: (+31-70) 340-3016

Authorized officer
 Goebel, Matthias

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2008/009305

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JABRI AMIR ET AL: "Isolation of a Cationic Chromium(II) Species in a Catalytic System for Ethylene Tri- and Tetramerization" ORGANOMETALLICS, ACS, WASHINGTON, DC, US, vol. 25, no. 3, 1 June 2006 (2006-06-01), pages 715-718, XP002457472 ISSN: 0276-7333 the whole document -----	1-13
A	COTTON F A ET AL: "Advanced inorganic chemistry" 1988, WILEY-INTERSCIENCE, NEW YORK (US), XP002482793 5th edition, pages 683-686 the whole document -----	1-3
A	WO 2007/057458 A (SHELL INT RESEARCH [NL]; DE BOER ERIC JOHANNES MARIA [NL]; VAN DER HEI) 24 May 2007 (2007-05-24) cited in the application page 8, line 17 - page 9, line 5 page 16, line 22 - page 17, line 6 claims -----	1-13
A	WO 02/04119 A (BP CHEM INT LTD [GB]; WASS DUNCAN FRANK [GB]) 17 January 2002 (2002-01-17) cited in the application page 3, line 28 - page 4, line 2 page 4, lines 13-18; claims 7,9,10,17,19,26,27,29-37,43,44 -----	1-13
A	WO 01/10876 A (BP CHEM INT LTD [GB]; WASS DUNCAN FRANK [GB]) 15 February 2001 (2001-02-15) claim 13; examples 1-5,10,11 page 4, lines 17-21; claims 1,5 -----	1-8
A	WO 97/37765 A (BP CHEM INT LTD [GB]; DOSSETT STEPHEN JOHN [GB]) 16 October 1997 (1997-10-16) claims 1-4; examples 1,5,6,9 -----	1-8
A	WRACKMEYER, BERND ET AL: "The first 1,3,2-diazaphospha-[3]ferrocenophanes" INORGANIC CHEMISTRY COMMUNICATIONS, 7(7), 884-888 CODEN: ICCOFP; ISSN: 1387-7003, 8 June 2004 (2004-06-08), XP002464832 pages 884-885; figure 1; compound 4B -----	1-13

-/--

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2008/009305

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	BURFORD, NEIL ET AL: "Sequential dehydrochloride coupling of trichlorophosphine with 2,6-di-isopropylaniline: aminophosphine precursors to phosphetidines" CANADIAN JOURNAL OF CHEMISTRY , 80(11), 1404-1409 CODEN: CJCHAG; ISSN: 0008-4042, 7 October 2002 (2002-10-07), XP002464833 page 1404 - page 1407; figures 1,2; compounds 5, 7	1-13
A	SCHERER, OTTO J. ET AL: "Synthesis and isolation of cis- and trans-1,3,2.lambda.3,4.lambda.3-diazadiphosphetidine" ANGEWANDTE CHEMIE INT. ED. ENGL., vol. 15, no. 12, 1976, pages 772-772, XP002464834 the whole document	1-13
A	KATZ, STEPHANIE A. ET AL: "Diastereoselectivity in the Formation of Skeletally Stabilized Phosphazanes" INORGANIC CHEMISTRY , 33(9), 1762-9 CODEN: INOCAJ; ISSN: 0020-1669, 1994, XP002464835 page 1762 - page 1765; compounds 2, 5, 11-13	1-13
A	HELM, MONTE L. ET AL: "Synthesis, Characterization, and Solution Properties of Skeletally Stabilized Triphosphazanes" INORGANIC CHEMISTRY , 38(13), 3167-3172 CODEN: INOCAJ; ISSN: 0020-1669, 8 June 1999 (1999-06-08), XP002464836 abstract page 3167 - page 3170; compounds 5, 6, 8	1-13
A	MUNDT, CORNELIA ET AL: "N-Phosphanylated 1,3,2-oxaza- and 1,3,2-diazaphospholanes and phosphorinanes" PHOSPHORUS, SULFUR AND SILICON AND THE RELATED ELEMENTS , 88(1-4), 75-81 CODEN: PSSLEC; ISSN: 1042-6507, 1994, XP009094587 pages 79-80 pages 75-77; compounds 3, 4, 7, 9	1-13

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2008/009305

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2006293546 A1	28-12-2006	CN 1891679 A DE 102006028935 A1	10-01-2007 11-01-2007
US 2007027350 A1	01-02-2007	CN 1903807 A DE 102006034812 A1	31-01-2007 22-02-2007
US 4668838 A	26-05-1987	AR 241012 A1 AU 594749 B2 AU 6989387 A BR 8701145 A CA 1273018 A1 CN 87101861 A DE 3763603 D1 EP 0237079 A1 FI 871125 A GR 3000913 T3 HU 44049 A2 IL 81821 A IN 168364 A1 JP 4066457 B JP 62265237 A MA 20901 A1 NO 871054 A NZ 219617 A PH 23205 A PH 24154 A PT 84481 A TR 23720 A ZA 8701859 A	30-04-1991 15-03-1990 17-09-1987 05-01-1988 21-08-1990 23-09-1987 16-08-1990 16-09-1987 15-09-1987 10-12-1991 28-01-1988 17-09-1990 23-03-1991 23-10-1992 18-11-1987 01-10-1987 15-09-1987 26-04-1989 06-06-1989 22-03-1990 01-04-1987 17-07-1990 27-04-1988
WO 2007057458 A	24-05-2007	AU 2006314445 A1 CA 2629889 A1 EP 1951645 A1 KR 20080080570 A US 2007185357 A1	24-05-2007 24-05-2007 06-08-2008 04-09-2008 09-08-2007
WO 0204119 A	17-01-2002	AR 028795 A1 AU 6774301 A BG 107539 A BR 0112470 A CA 2412990 A1 CN 1630554 A EG 22912 A EP 1299189 A1 HU 0400497 A2 JP 2004502527 T MX PA03000301 A NO 20030108 A PL 358746 A1 RU 2299096 C2 SK 172003 A3 TW 562696 B US 2003166456 A1 ZA 200210392 A	21-05-2003 21-01-2002 30-09-2003 29-07-2003 17-01-2002 22-06-2005 30-10-2003 09-04-2003 28-05-2004 29-01-2004 05-04-2004 13-02-2003 23-08-2004 20-05-2007 11-09-2003 21-11-2003 04-09-2003 05-11-2003
WO 0110876 A	15-02-2001	AU 6000100 A DE 60034795 T2 EP 1208108 A1	05-03-2001 20-09-2007 29-05-2002

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2008/009305

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0110876	A	US 2003018141 A1	23-01-2003
WO 9737765	A	16-10-1997	
		AU 2302797 A	29-10-1997
		DE 69727460 D1	11-03-2004
		DE 69727460 T2	01-07-2004
		EP 0850105 A1	01-07-1998
		ES 2216137 T3	16-10-2004
		JP 4027423 B2	26-12-2007
		JP 11506981 T	22-06-1999
		US 6018016 A	25-01-2000