

(19) **DANMARK**

(10) **DK/EP 2657734 T3**



(12)

Oversættelse af europæisk patentskrift

Patent- og
Varemærkestyrelsen

-
- (51) Int.Cl.: **G 02 B 6/028 (2006.01)** **G 02 B 6/036 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2019-12-16**
- (80) Dato for Den Europæiske Patentmyndigheds bekendtgørelse om meddelelse af patentet: **2019-10-30**
- (86) Europæisk ansøgning nr.: **13165638.1**
- (86) Europæisk indleveringsdag: **2013-04-26**
- (87) Den europæiske ansøgnings publiceringsdag: **2013-10-30**
- (30) Prioritet: **2012-04-27 WO PCT/IB2012/001174**
- (84) Designerede stater: **AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**
- (73) Patenthaver: **Draka Comteq BV, De Boelelaan 7, 1083 HJ Amsterdam, Holland**
- (72) Opfinder: **Molin, Denis, 55, Avenue Jean Jaurès, 91210 Draveil, Frankrig**
Sansonetti, Pierre, 8, avenue du Moulin de la Planche, 91120 Palaiseau, Frankrig
Sillard, Pierre, 2 Square Raphael Résidence Orsay, 78150 Le Chesnay, Frankrig
- (74) Fuldmægtig i Danmark: **Larsen & Birkeholm A/S Skandinavisk Patentbureau, Banegårdspladsen 1, 1570 København V, Danmark**
- (54) Benævnelse: **Hybrid optisk single- og multimodefiber til et hjemmenetværk**
- (56) Fremdragne publikationer:
JP-A- 2 073 203
JP-A- H01 113 708
US-A1- 2002 041 737
US-A1- 2002 114 599
US-A1- 2004 202 423
US-A1- 2005 163 449
US-A1- 2007 196 061
US-A1- 2010 158 460
US-B1- 6 393 189

DESCRIPTION

1. FIELD OF THE INVENTION

[0001] The invention relates to fiber optic transmission, and, more specifically, to an optical fiber for a home network that supports both single-mode and multimode transmissions.

2. TECHNOLOGICAL BACKGROUND

[0002] An optical fiber is conventionally constituted of an optical core, which transmits an optical signal, and of an optical cladding, which confines the optical signal within the optical core. To that end the refractive index of the core, n_c , is greater than the one of the cladding, n_g . An optical fiber is generally characterized by a refractive index profile that associates the refractive index (n) with the radius (r) of the optical fiber: the distance r with respect to the center of the optical fiber is shown on x-axis and the difference between the refractive index at radius r and the refractive index of the optical cladding is shown on y-axis.

[0003] Nowadays, two main categories of optical fibers exist: multimode fibers and single-mode fibers. In a multimode fiber, for a given wavelength, several optical modes are propagated simultaneously along the optical fiber, whereas in a single-mode fiber, the higher order modes (hereafter called HOMs) are cut-off or highly attenuated.

[0004] Single-mode fibers are commonly used for long-distance applications, such as access networks. To obtain an optical fiber capable to transmit a single-mode optical signal, a core with a relatively small diameter is required (typically between 5 μm and 11 μm). To meet requirements of high bandwidth applications for the access networks (for example 10Gbps), standard single-mode fibers require use of a modulated single-mode laser emitter tuned to work typically at a wavelength of 1550 nm.

[0005] Multimode fibers are commonly used for short-distance applications requiring a high bandwidth, such as local area networks (LANs) and multi-dwelling units (MDUs), more generally known as in-building networks. The core of a multimode fiber typically has a diameter of 50 μm , or 62,5 μm . Multimode fibers have been the subject of international standardization, which define criteria of bandwidth, of numerical aperture, and of core diameter for a given wavelength. The OM3 and OM4 standards have been adopted to meet the demands of high-bandwidth applications (typically 10Gbps) over long distances (a few tens to a few hundreds of meters), such as in the Ethernet high speed transmission networks. The OM3 standard requires, at a wavelength of 850 nm, an efficient modal bandwidth (hereafter called EMB) of at least 2 000 MHz.km to assure error-free multimode transmissions of 10 Gbps up to a distance of 300 m. The OM4 standard requires, at a wavelength of 850 nm, an EMB of at least 4 700 MHz.km to assure error-free multimode transmissions of 10 Gbps up to a distance of 400 m.

[0006] The most prevalent multimode fibers in telecommunications are the refractive graded-index profile optical fibers. Such a refractive index profile guaranties, by minimizing the intermodal dispersion (i.e. the difference between the propagation delay times or group velocity of the optical modes along the optical fiber), a high modal bandwidth for a given wavelength.

[0007] For the development of an optical home network, the choice of the category of optical fiber category is critical. Multimode fiber is a cost effective solution for optical data networks. Thanks to their wider numerical aperture and core diameter, and their low modal dispersion provided by their graded-index core profile, multimode fibers can support efficiently 10Gbps optical signals emitted by cost effective light sources based solutions (such as Vertical Cavity Surface Emitting Laser or VCSEL), whereas single-mode fibers require expensive and tolerant single-mode transceivers. In particular the connection of the light source with the single-mode fiber (launching conditions) requires tighter alignment tolerances than with the multimode fiber.

[0008] However, since the optical home network is expected to be connected to the outside access networks, which mainly use single-mode technology because of longer reach requirements, the problem of interoperability with single-mode fibers needs further considerations.

[0009] In practice, multimode fibers are not designed to be interconnected with single-mode optical transmission systems. A home network can be seen as a network of optical fibers that enables the users to connect devices at both ends of the network. Today, the devices are likely to implement multimode optical transmission based technologies that require multimode fibers, whilst tomorrow they could be designed to operate also with a single-mode based technology. Thus the installation of optical fiber, which is relatively costly, would have to be repeated once the access networks be ready to work with the optical home networks.

[0010] It is therefore desirable to provide an optical fiber for a home network that can transmit both error free multimode optical signals at an operating wavelength of the home network, for example 850 nm, and error free single-mode optical signals at an operating wavelength of an access network, for example 1550 nm.

[0011] One proposed known solution would consist of using a standard multimode fiber that has a refractive graded-index profile optimized for providing error-free transmission with a broad bandwidth at a wavelength of 850 nm. Nevertheless, when a single-mode source operating at a wavelength of 1550 nm is coupled to the standard multimode fiber, the optical signal injected in the fiber stimulates, mainly but unfortunately not only the fundamental optical mode, but also the HOMs within the optical fiber. Indeed, a part of the optical power is coupled into the fundamental mode of the standard multimode fiber and almost all the remaining power is coupled into the set of HOMs of the fiber (that corresponds to parasitic signal or an optical noise). Since the different modes have different propagation delay times and propagation constants, therefore, on the receiver side, both optical signals carried by the fundamental

mode and the HOMs interfere, leading to power fluctuations that degrade the quality of the optical transmission. Therefore, due to mode field mismatch at 1550 nm between the fundamental modes carried by a standard multimode fiber and a standard single-mode fiber, such a standard multimode fiber is not adapted to an interconnection with a single-mode optical transmission system.

[0012] In practice, to perform well in a high-bandwidth application, an optical fiber should have the highest quality of the optical transmission. For a given wavelength, this criterion may be characterized by the optical mode coupling ratio, which is given by the following equation:

$$\frac{|\gamma|^2}{\sum_i |\beta_i|^2} = \frac{|\langle E_{SMF}, E_{MMF} \rangle|^2}{\sum_i |\langle E_{SMF}, E_{MMF}^{(i)} \rangle|^2}$$

wherein:

γ is the optical power coupled into the fundamental mode;

β_i is the optical power coupled into the higher order modes (HOMs), with $i \geq 1$;

E_{SMF} is the electrical field of the fundamental mode of the single mode fiber;

E_{MMF} is the electrical field of the fundamental mode of the multimode fiber;

$$\langle E_1 | E_2 \rangle = \iint E_1^* \cdot E_2 \cdot dS$$

is the scalar product of fields E_1 and E_2 .

[0013] This equation defines the ratio of optical power coupled between the fundamental mode and the HOMs. Less the optical power is coupled into the HOMs, more the optical transmission quality of the fiber is improved.

[0014] The Australian patent document AU 2002/100296 discloses an optical fiber comprising a single-mode core part, which has a first refractive index, surrounded by a multimode core part, which has a second refractive index, finally surrounded by a cladding which has a third refractive index. Nevertheless, this document does not describe the conditions for the fiber profile to enable sufficient error free single-mode transmission at 1550 nm. The disclosed optical fiber further presents a relatively low bandwidth at 850 nm. This document does not address the problem of reduction of noise caused by the HOMs of the optical fiber.

[0015] The French patent document FR 2 441 585 discloses a single-mode or multimode optical fiber with a central single-mode core and a multimode sheath for data transmission. In particular, the disclosed optical fiber does not exhibit a refractive graded-index core profile, which is critical for high speed performances at 850nm. The latter document does not describe the conditions for the fiber profile to provide sufficient error free single-mode and multimode transmission. Nor does not address the problem of reduction of the optical power coupled into the HOMs of the optical fiber. A multimode fiber according to the state of the art is known from

US-A-20040202423.

3. GOALS OF THE INVENTION

[0016] The invention, in at least one embodiment, is aimed especially at overcoming these different drawbacks of the prior art.

[0017] More specifically, a goal of at least one embodiment of the invention is to provide a hybrid optical fiber for an optical home network that combines features of multimode (like the ability to be used with high-speed VCSEL-based sources for instance) and single-mode optical fibers with an adequate trade-off in terms of optical properties, for high-data rate applications.

[0018] In other words, a goal of the invention is to provide an optical fiber that can transmit error free multimode optical signals at an operating wavelength of the home network (typically 850 nm) and error free single-mode optical signals at an operating wavelength of an access network (typically 1550 nm).

[0019] It is also an aim of at least one embodiment of the invention to provide an optical fiber having an improved optical mode-coupling ratio for single-mode transmission, while keeping a broad bandwidth for multimode transmission over a few tens of meters.

[0020] It is also an aim of at least one embodiment of the invention to provide an optical fiber that presents a relatively low modal dispersion for the multimode transmission and that sustains a fundamental mode similar to that in a standard single-mode optical fiber.

[0021] It is also an aim of at least one embodiment of the invention to provide an optical fiber that is simple to manufacture and costs little.

4. SUMMARY OF THE INVENTION

[0022] In one particular embodiment of the invention, it is proposed an optical fiber according to claim 1.

[0023] The general principle is to propose a hybrid optical fiber that includes a multisegmented optical core exhibiting a refractive graded-index profile typically used to support multimode transmission in which a step-index is added at the center of the optical core, the profile parameters a_s and Δ_s of this step-index as well as Δ_d of the depressed area being tuned so as to provide an optical fiber that transmits both error free multimode optical signals and error free single-mode optical signals.

[0024] Indeed, the astute implementation of such a refractive index profile $n(r)$ of the optical

core, as well as the choice of an adequate value of the parameters a_s and Δ_s , lead to adapt the fundamental mode of the optical fiber such that the optical power coupled into the fundamental mode is maximized at the wavelength of the single-mode transmission (1550 nm for example), while preserving a relatively reduced modal dispersion at the wavelength of the multimode transmission (850 nm for example).

[0025] The refractive index profile of the second core region presents the typical characteristics of a multimode fiber, for example, operating at a wavelength of 850 nm.

[0026] The first core region is used to have a radial portion of the optical fiber that has a step-index profile whose characteristics with respect to the second region core enables to impose the single-mode transmission conditions when single-mode optical signals are injected inside the fiber, while keeping the multimode characteristics of the optical fiber when multimode optical signals are injected inside the fiber.

[0027] The invention is thus based on an optical mode matching that, thanks to the refractive profile $n(r)$ defined above, enables to combine both features of a multimode optical fiber and a single-mode optical fiber with an adequate trade-off in terms of optical properties.

[0028] In addition, an optical fiber according to the invention is simple to manufacture and costs little, since all that is needed is to adapt the doping of the optical core as a function of the desired refractive index profile.

[0029] It should be noted that the technical effects obtained for an optical fiber of the invention with a constant refractive index first core region are the same as those described above, for an optical fiber of the invention with a refractive graded-index first core region.

[0030] Advantageously, the non-dimensional parameter α is comprised between 1 and 5.

[0031] Advantageously, the width w_d of the depressed area is comprised between 1 and 8 μm .

[0032] Adding a depressed area at the periphery of the first core region leads to improve even more the modal bandwidth at 850 nm.

[0033] In another embodiment, the invention pertains to an optical system, such as an optical home network, comprising at least one optical fiber described here above in any of its different embodiments.

5. LIST OF FIGURES

[0034] Other features and advantages of embodiments of the invention shall appear from the following description, given by way of an indicative and non-exhaustive examples and from the

appended drawings, of which:

- Figure 1 graphically provides the refractive index profile of an optical fiber
- Figure 2 graphically depicts the optical mode coupling ratio as a function of parameters of core index profile of a first exemplary optical fiber according to the invention;
- Figure 3 graphically depicts the achievable 10GbE reach as a function of parameters of core index profile of the first exemplary optical fiber according to the invention;
- Figure 4 represents, on a same graphic, the curves obtained at figures 2 and 3;
- Figure 5 graphically depicts the optical mode coupling ratio as a function of parameters of core index profile of a second exemplary optical fiber according to the invention;
- Figure 6 graphically depicts the achievable 10GbE reach as a function of parameters of core index profile of the second exemplary optical fiber according to the invention;
- Figure 7 represents, on a same graphic, the curves obtained at figures 5 and 6;
- Figure 8 graphically depicts the optical mode coupling ratio as a function of parameters of core index profile of a third exemplary optical fiber according to the invention;
- Figure 9 graphically depicts the achievable 10GbE reach as a function of parameters of core index profile of the third exemplary optical fiber according to the invention;
- Figure 10 represents, on a same graphic, the curves obtained at figures 8 and 9;
- Figure 11 graphically provides the refractive index profile of an optical fiber according to a second embodiment of the invention.

6. DETAILED DESCRIPTION

[0035] In all of the figures of the present document, identical elements and steps are designated by the same numerical reference sign.

[0036] **Figure 1** depicts the refractive index profile of an optical fiber. It describes the relationship between the refractive index value n and the distance r from the center of the optical fiber.

[0037] The fiber of the invention is a hybrid optical fiber having a refractive index profile $n(r)$ defined by the following equation:

$$n(r) = \begin{cases} n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} + \Delta_s & r < a_s \\ n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} & a_s \leq r < a \\ n_0 \cdot \sqrt{1 - 2 \cdot \Delta} & a \leq r \end{cases}$$

wherein:

a_s is the radius of the first core region;

a is the radius of the second core region;

Δ_s is a refraction index-step defined by the refractive index difference between the first core region and the second core region at $r = a_s$;

n_0 is the maximal refractive index of the second core region;

α is a non-dimensional parameter that defines the index profile shape of the second core region, and $\alpha \geq 1$;

Δ is the normalized refractive index difference, and

$$\Delta = \frac{n_0^2 - n_1^2}{2n_0^2},$$

n_1 being the minimal refractive index of the second core region.

[0038] The optical fiber comprises an optical core for $0 < r < a$ and an optical cladding $a \leq r$ surrounding the optical core. The fiber's optical cladding has a standard constant refractive index such as:

$$n_0 \cdot \sqrt{1 - 2 \cdot \Delta}.$$

[0039] The fiber's optical core comprises a first core region having a radius a_s and a refractive step-index with respect to a second core region, with a refractive index profile such as:

$$n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} + \Delta_s \text{ for } r < a_s$$

[0040] The second core region, which have a radius a , immediately surrounds the first core region and has a refractive graded-index profile (also known as "alpha index profile") with respect to the optical cladding such as:

$$n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} \text{ for } a_s \leq r < a$$

[0041] The second core region presents the typical characteristics of a multimode fiber operating at a wavelength of 850 nm.

[0042] The first core region is used to have a radial portion of the optical fiber that has a step-index profile whose the characteristics (Δ_s and a_s) with respect to the second region core enables to impose the single-mode transmission conditions operating at a wavelength of 1550 nm, while keeping the multimode characteristics of the optical fiber at 850 nm.

[0043] Indeed, the refractive index profile depicted in figure 1 exhibits a graded-index core with a step index positioned in the center of the optical core that is tuned to provide optical mode matching at 1550 nm between the fundamental mode of the hybrid optical fiber of the invention and the fundamental mode of a standard single-mode fiber.

[0044] In this example, the first core region's radius a is about 25 μm (with a tolerance of $\pm 2 \mu\text{m}$) and the first core region's radius a_s is about 6 μm . The parameter α of the optical core's index profile is about 2. The refractive index difference Δ_s corresponding to the step-index may have a value of between about $3 \cdot 10^{-3}$ and $12 \cdot 10^{-3}$.

[0045] Generally speaking, the refractive index difference Δ_s and the radius a_s of the first core region can be optimized in order to achieve the best trade-off in terms of optical properties, i.e. a high optical mode coupling ratio

$$\left(\frac{|Y|^2}{\sum_i |\beta_i|^2} \right)$$

for single-mode transmissions at 1550 nm and a low dispersion modal (or a high bandwidth) for multimode transmissions at 850 nm.

[0046] In a particular embodiment, the refractive index difference Δ_s and the radius a_s of the first core region can be such that they satisfy the following inequality:

$$0.0549 \cdot a_s^4 - 0.9053 \cdot a_s^3 + 5.483 \cdot a_s^2 - 14.39 \cdot a_s + 13.75 < 1000 \cdot \Delta_s < 1.11 \cdot a_s^2 - 6.9145 \cdot a_s + 17.94$$

[0047] In a preferably embodiment, the refractive index difference Δ_s and the radius a_s of the first core region are such that they satisfy the following inequality:

$$0.0373 \cdot a_s^4 - 0.6145 \cdot a_s^3 + 4.0286 \cdot a_s^2 - 12.217 \cdot a_s + 14.739 < 1000 \cdot \Delta_s < 0.9821 \cdot a_s^2 - 6.5036 \cdot a_s + 16.7$$

[0048] It should be noted that these two empiric inequalities each enables to improve the fundamental mode matching at 1550 nm. These empiric inequalities have been established by the inventors assuming that the fundamental mode matching can be assessed indirectly by the comparison to the mode field diameter of the fundamental mode of the hybrid optical fiber of the invention at 1550 nm and the fundamental mode of a standard single-mode fiber. Especially, these two inequalities correspond to a mode field diameter difference of about 0,8 μm and 0,5 μm respectively. The fundamental mode diameter is smaller, the optical power coupled into the fundamental mode ($|Y|^2$) is higher (and the optical power coupled into the HOMs

$$\left(\sum_i |\beta_i|^2 \right)$$

is lower).

[0049] The advantages of the invention will be more evident by comparing optical fibers of the prior art with an exemplary optical fiber according to the invention. Table 1 below shows fiber

profile parameters of a standard multimode fiber that has a refractive graded-index profile optimized for providing error-free transmission at a wavelength of 850 nm. That prior art fiber is subjected to an optical signal of a wavelength λ of 1550 nm.

Table 1						
Examples	α	Δ	a	λ	$ V ^2$	$\sum_i \beta_i ^2$
1	2	1.0%	25 μm	1550 nm	95.3%	4.7%
2	2	2.0%	31.25 μm	1550 nm	96.8%	3.2%

[0050] Table 2 below shows fiber profile parameters of a hybrid optical fiber according to the invention. The optical fiber exhibits a refractive index profile that respects the equation $n(r)$ described above, with the refractive index difference Δ_s and the radius a_s of the first core region that comply with the first inequality:

$$0.0549 \cdot a_s^4 - 0.9053 \cdot a_s^3 + 5.483 \cdot a_s^2 - 14.39 \cdot a_s + 13.75 < 1000 \cdot \Delta_s < 1.11 \cdot a_s^2 - 6.9145 \cdot a_s + 17.94$$

Table 2							
Examples	α	a_s	Δ_s	a	λ	$ V ^2$	$\sum_i \beta_i ^2$
1	2	2 μm	6	25 μm	1550 nm	99.93%	0.07%
2	2	2 μm	5	25 μm	1550 nm	99.66%	0.34%
3	2	2 μm	7	25 μm	1550 nm	99.94%	0.06%
4	2	3 μm	3	25 μm	1550 nm	99.61%	0.39%

[0051] From these two tables, it should be noticed that, for an optical fiber's length of about 30 m, the optical power coupled in the fundamental mode of the prior art fiber does not exceed 97%, whereas the optical power coupled in the fundamental mode of the optical fiber of the invention clearly exceeds 99%.

[0052] **Figure 2** graphically depicts simulated optical mode coupling ratio (OMCR) measurements as a function of the refractive step-index difference Δ_s and the radius a_s of the first core region of an optical fiber for which the core radius is of 25 μm and the numerical aperture of 0.200.

[0053] The left-hand y-axis depicts the first core region's refractive step-index difference Δ_s and the x-axis depicts the first core region's radius a_s . The values of optical mode coupling ratio corresponding to a given pair of parameters (Δ_s , a_s) are illustrated in shades of gray in the right-hand y-axis.

[0054] The curves 10 is defined by the following inequality, assuming that the optical power

coupled into the fundamental mode is upper than 98% at the wavelength of 1550 nm (single-mode transmission):

$$\Delta_s > 0.17173 a_s^2 - 1.6926 a_s + 5.1835$$

[0055] The curves 11 is defined by the following inequality, assuming that the optical power coupled into the fundamental mode is upper than 98% at the wavelength of 1550 nm (single-mode transmission):

$$\Delta_s > 0.31742 a_s^2 - 2.9046 a_s + 8.3221$$

[0056] The values of OMCR situated above curves 10 and 11 enable to establish the values of the parameters Δ_s and a_s of the optical fiber's first core region for which the fundamental mode-matching is provided at a ratio of at least 98%, respectively 99%, at the wavelength of 1550 nm.

[0057] **Figure 3** graphically depicts simulated achievable 10GbE reach as a function of the refractive step-index difference Δ_s and the radius a_s of the first core region of an optical fiber for which the core radius is of 25 μm and the numerical aperture of 0,200.

[0058] The left-hand y-axis depicts the first core region's refractive step-index difference Δ_s and the x-axis depicts the first core region's radius a_s . The values of achievable 10GbE reach, expressed as m (meter), at the wavelength of 850 nm, corresponding to a given (Δ_s, a_s) pair are illustrated in shades of gray in the right-hand y-axis.

[0059] The term "10GbE reach" refers to the maximum guaranteed transmission distance for which an optical fiber can operate at a nominal data rate of 10Gbps with a bit error rate (or BER) of less than 10^{-12} when used with 10G-BASE-S sources (the 10G-BASE-S sources are standardized sources for 10GbE applications (see IEEE 802.3).

[0060] The curves 12 is defined by the following inequality, assuming 10GbE reach of 30m:

$$\Delta_s < 0.26184 a_s^2 - 3.1935 a_s + 10.5832$$

[0061] The curves 13 is defined by the following inequality, assuming a 10GbE reach of 50m:

$$\Delta_s < 0.21308 a_s^2 - 2.3168 a_s + 6.9690$$

[0062] The values situated below curves 12 and 13 enable to establish the values of the parameters Δ_s and a_s of the optical fiber's first core region for which the modal dispersion of the optical fiber at the wavelength of 850 nm is sufficiently low so that the optical fiber can be employed in high data rate applications (e.g. 10 GbE applications) over respectively 30 m and 50 m.

[0063] Figure 4 depicts on a same graphic the curves 10, 11, 12, 13 obtained at figures 2 and 3. This figure shows that the optical fiber has a pair of values (Δ_s , a_s) for which the corresponding point should be situated between the curves 10, 12 or between the curves 10, 13 or between the curves 11, 12 so that this optical fiber provides a satisfactory trade-off between the optical mode coupling ratio for single-mode transmissions at 1550 nm and the modal bandwidth for multimode transmissions at 850 nm. For example, an optical fiber that possesses a first core region having a refractive step-index difference Δ_s of $2,5 \cdot 10^{-3}$ and a radius of $3,5 \mu\text{m}$ will exhibit a value of OMCR of at least 99% at 1550 nm and an achievable 10GbE reach of at least 30 meters at 850 nm. In that example, the modal dispersion at 850nm is low enough to allow for an error free multimode transmission at 850nm using off-the-shelf 10Gbps transceivers (typically implementing a VCSEL technology) and an error free single-mode transmission at 1550nm.

[0064] Figure 5 graphically depicts simulated optical mode coupling ratio (OMCR) measurements as a function of the refractive step-index difference Δ_s and the radius a_s of the first core region of an optical fiber for which the core radius is of $31,25 \mu\text{m}$ and the numerical aperture of 0,275.

[0065] The curves 14 is defined by the following inequality, assuming that the optical power coupled into the fundamental mode is upper than 98% at the wavelength of 1550 nm (single-mode transmission):

$$\Delta_s > 0.13774 a_s^2 - 1.3462 a_s + 4.0572$$

[0066] The curves 15 is defined by the following inequality, assuming that the optical power coupled into the fundamental mode is upper than 98% at the wavelength of 1550 nm (single-mode transmission):

$$\Delta_s > 0.2839 a_s^2 - 2.5787 a_s + 7.2947$$

[0067] The values of OMCR situated above curves 14 and 15 enable to establish the values of the parameters Δ_s and a_s of the optical fiber's first core region for which the fundamental mode-matching is provided at a ratio of at least 98%, respectively 99%, at the wavelength of 1550 nm.

[0068] Figure 6 graphically depicts simulated achievable 10GbE reach as a function of the refractive step-index difference Δ_s and the radius a_s of the first core region of an optical fiber for which the core radius is of $31,25 \mu\text{m}$ and the numerical aperture of 0,275.

[0069] The curves 16 is defined by the following inequality, assuming a 10GbE reach of 30 m:

$$\Delta_s < 0.22044 a_s^2 - 2.7607 a_s + 9.7057$$

[0070] The curves 17 is defined by the following inequality, assuming a 10GbE reach of 50 m:

$$\Delta_s < 0.15979 a_s^2 - 1.8078 a_s + 5.9286$$

[0071] The values situated below curves 16 and 17 enable to establish the values of the parameters Δ_s and a_s of the optical fiber's first core region for which the modal dispersion of the optical fiber at the wavelength of 850 nm is sufficiently low so that the optical fiber of can be employed in high data rate applications (typically 10 GbE applications) over respectively 30 m and 50 m.

[0072] Figure 7 depicts on a same graphic the curves 14, 15, 16, 17 obtained at figures 5 and 6. This figure shows that the optical fiber has a pair of values (Δ_s , a_s) for which the corresponding point should be situated between the curves 14 and 16 or between the curves 14 and 17 or between the curves 15 and 16 or 15 and 17, so that this optical fiber provides a satisfactory trade-off between the optical mode coupling ratio at 1550 nm and the modal bandwidth at 850 nm. For example, an optical fiber that possesses a first core region having a refractive step-index difference Δ_s of $2,0 \cdot 10^{-3}$ and a radius of 4 μm will exhibit a value of OMCR of at least 99% at 1550 nm and an achievable 10GbE reach of at least 30 meters at 850 nm. In that example, the modal dispersion at 850nm is low enough to allow for an error free multimode transmission at 850nm using off-the-shelf 10Gbps transceivers (typically implementing a VCSEL technology) and an error free single-mode transmission at 1550nm.

[0073] Figure 8 graphically depicts simulated optical mode coupling ratio (OMCR) measurements as a function of the refractive step-index difference Δ_s and the radius a_s of the first core region of an optical fiber for which the core radius is of 40 μm and the numerical aperture of 0,290.

[0074] The curves 18 is defined by the following inequality, assuming that the optical power coupled into the fundamental mode is upper than 98% at the wavelength of 1550 nm (single-mode transmission):

$$\Delta_s > 0.20185 a_s^2 - 2.0205 a_s + 6.2914$$

[0075] The curves 19 is defined by the following inequality, assuming that the optical power coupled into the fundamental mode is upper than 98% at the wavelength of 1550 nm (single-mode transmission):

$$\Delta_s > 0.34616 a_s^2 - 3.211 a_s + 9.3320$$

[0076] The values of OMCR situated above curves 18 and 19 enable to establish the values of the parameters Δ_s and a_s of the optical fiber's first core region for which the fundamental mode-matching is provided at a ratio of at least 98%, respectively 99%, at the wavelength of 1550 nm.

[0077] Figure 9 graphically depicts simulated achievable 10GbE reach as a function of the

refractive step-index difference Δ_s and the radius a_s of the first core region of an optical fiber for which the core radius is of 40 μm and the numerical aperture of 0,290.

[0078] The curves 20 is defined by the following inequality, assuming a 10GbE reach of 30 m:
 $\Delta_s < 0.26946 a_s^2 - 3.5101 a_s + 12.8205$

[0079] The curves 21 is defined by the following inequality, assuming a 10GbE reach of 50 m:
 $\Delta_s < 0.20605 a_s^2 - 2.4798 a_s + 8.3655$

[0080] The values situated below curves 21 and 22 enable to establish the values of the parameters Δ_s and a_s of the optical fiber's first core region for which the modal dispersion of the optical fiber at the wavelength of 850 nm is sufficiently low so that the optical fiber can be employed in high data rate applications (e.g. 10 GbE applications) over respectively 30 m and 50 m.

[0081] **Figure 10** depicts on a same graphic the curves 18, 19, 20, 21 obtained at figures 8 and 9. This figure shows that the optical fiber has a pair of values (Δ_s , a_s) for which the corresponding point should be situated between the curves 18 and 20 or between the curves 18 and 12 or between the curves 19 and 20 or 19 and 21, so that this optical fiber provides a satisfactory trade-off between the optical mode coupling ratio at 1550 nm and the modal bandwidth at 850 nm. For example, an optical fiber that possesses a first core region having a refractive step-index difference Δ_s of $2,0 \cdot 10^{-3}$ and a radius of 4 μm will exhibit a value of OMCR of at least 99% at 1550 nm and an achievable 10GbE reach of at least 30 meters at 850 nm. In that example, the modal dispersion at 850nm is low enough to allow for an error free multimode transmission at 850nm using off-the-shelf 10Gbps transceivers (typically implementing a VCSEL technology) and an error free single-mode transmission at 1550nm.

[0082] **Figure 11** graphically provides the refractive index profile of an optical fiber according to a second embodiment of the invention. This second embodiment differs from the second embodiment of the invention in that the optical fiber comprises a depressed area positioned between the first core region and the second core region, surrounding immediately the first core region. The depressed area aims at reducing even more the dispersion modal for multimode transmissions at 850 nm.

[0083] This depressed area has a width w_d of about 4 μm and a refractive index difference Δ_d with respect to the second core region of about $-1,3 \cdot 10^{-3}$. The refractive index difference Δ_s' of the step-index first core region is about $2,5 \cdot 10^{-3}$.

[0084] More generally, the width w_d of the depressed area may have a value of between about 1 μm and 8 μm .

[0085] In practice, the refractive index difference Δ_d of the depressed area and the refractive index difference Δ_s' of the first core region may be determined using the following equation: $|\Delta_d| + \Delta_s' = \Delta_s$, wherein Δ_s satisfies at least one of the inequalities described here above in relation the first embodiment of the invention. For example, the sum of the refractive index difference $|\Delta_d|$ of the depressed area and the refractive index difference Δ_s' of the first core region may have a value of between about $3 \cdot 10^{-3}$ and $12 \cdot 10^{-3}$, with Δ_d comprised between $-4,5 \cdot 10^{-3}$ and $-0,5 \cdot 10^{-3}$.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- [AU2002100296 \[0014\]](#)
- [FR2441585 \[0015\]](#)
- [US20040202423A \[0015\]](#)

P A T E N T K R A V

1. Optisk fiber, omfattende en optisk kerne og en optisk kappe, som omgiver den optiske kerne, **kendetegnet ved, at** den optiske kerne omfatter et første kerneområde og et andet kerneområde, som omgiver det første kerneområde, hvor den optiske fiber er **kendetegnet ved, at** det første og andet kerneområde er således, at den optiske kerne har en brydningsindeksprofil $n(r)$ defineret enten af ligningen:

$$n(r) = \begin{cases} n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} + \Delta_s & r < a_s \\ n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} - \Delta_d & a_s \leq r < a_s + w_d \\ n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} & a_s + w_d \leq r < a \end{cases}$$

eller af ligningen:

$$n(r) = \begin{cases} n_0 + \Delta_s & r < a_s \\ n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} - \Delta_d & a_s \leq r < a_s + w_d \\ n_0 \cdot \sqrt{1 - 2 \cdot \Delta \cdot \left(\frac{r}{a}\right)^\alpha} & a_s + w_d \leq r < a \end{cases}$$

hvor:

a_s er radiussen af det første kerneområde, som ligger mellem 1,5 og 4,5 μm ;

a er radiussen af det andet kerneområde;

Δ_s er et trinindeks defineret af brydningsindeksforskellen mellem det første kerneområde og det andet kerneområde;

A_d er et forsænket indeksområde defineret af brydningsindeksforskellen med hensyn til det andet kerneområde;

n_0 er det maksimale brydningsindeks af det andet kerneområde;

α er en ikke-dimensional parameter, som definerer indeksprofilformen på det andet kerneområde, og $\alpha \geq 1$;

Δ er den normaliserede brydningsindeksforskel, og $\Delta = \frac{n_0^2 - n_1^2}{2n_0^2}$, hvor n_1 er det minimale brydningsindeks af det andet kerneområde,

og **ved, at** det forsænkede indeksområde er positioneret på periferien af det første kerneområde og har en given bredde w_d med en given bredde mellem 1 og 8 μm og en brydningsindeksforskel Δ_d med hensyn til det andet kerneområde, således at brydningsindeksforskellen Δ_d for det forsænkede indeksområde, brydningsindeksforskellen Δ_s mellem det første kerneområde og det andet kerneområde og radiussen for det første kerneområde a_s opfylder følgende ulighed:

$$0.0549 \cdot a_s^4 - 0.9053 \cdot a_s^3 + 5.483 \cdot a_s^2 - 14.39 \cdot a_s + 13.75 < 1000 \cdot (\Delta_s + |\Delta_d|) < 1.11 \cdot a_s^2 - 6.9145 \cdot a_s + 17.94$$

2. Optisk fiber ifølge krav 1, hvor den ikke-dimensionale parameter α ligger mellem 1 og 5.

3. Optisk system, omfattende mindst en optisk fiber ifølge et hvilket som helst af kravene 1 til 2.

DRAWINGS




Figure 1






Figure 2

**Figure 3****Figure 4**




Figure 5




Figure 6




Figure 7







Figure 8

**Figure 9****Figure 10**

**Figure 11**