



(86) Date de dépôt PCT/PCT Filing Date: 2006/06/02
(87) Date publication PCT/PCT Publication Date: 2007/01/25
(45) Date de délivrance/Issue Date: 2012/02/21
(85) Entrée phase nationale/National Entry: 2008/01/18
(86) N° demande PCT/PCT Application No.: US 2006/021231
(87) N° publication PCT/PCT Publication No.: 2007/011459
(30) Priorité/Priority: 2005/07/19 (US60/700,600)


(51) Cl.Int./Int.Cl. *C08F 210/14* (2006.01),
C10M 143/08 (2006.01)

(72) Inventeurs/Inventors:
WU, MARGARET M., US;
YANG, NORMAN, US;
BAUGH, LISA S., US;
CANICH, JO ANN M., US;
RUCKER, STEVEN P., US;
WALZER, JOHN F., JR., US;
LEE, GORDON H., US;
...

(73) Propriétaire/Owner:
EXXONMOBIL CHEMICAL PATENTS INC., US

(74) Agent: BORDEN LADNER GERVAIS LLP

(54) Titre : NOUVELLES COMPOSITIONS POLYALPHAOLEFINIQUES ET PROCEDES DE REALISATION AFFERENTS
(54) Title: POLYALPHA-OLEFIN COMPOSITIONS AND PROCESSES TO PRODUCE THE SAME



(57) Abrégé/Abstract:

This invention relates to a polyalpha-olefin (and hydrogenated analogs thereof) comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has: a) 40 mole % or more of mm triads, b) a Bromine number of Y or greater, where Y is equal to $89.92 * (V)^{0.5863}$, where V is the Kinematic Viscosity of the polyalpha-olefin measured at 100°C in cSt, and c) 1,2 disubstituted olefins present at 7 mole % or more, preferably having Z mole % or more of units represented by the formula: where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and where $Z = 8.420 * \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt. This invention also relates to process to produce such polyalpha-olefins.



(72) **Inventeurs(suite)/Inventors(continued):** LO, FREDERICK YIP-KWAI, US; JACKSON, ANDREW, US;
HAGEMEISTER, MARK, US; TIRMIZI, SHAKEEL, US; JIANG, PEIJUN, US; CHEE, CHIA S., US

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
25 January 2007 (25.01.2007)

PCT

(10) International Publication Number
WO 2007/011459 A1

(51) International Patent Classification:

C08F 210/14 (2006.01) *C10M 143/08* (2006.01)

(21) International Application Number:

PCT/US2006/021231

(22) International Filing Date: 2 June 2006 (02.06.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

60/700,600 19 July 2005 (19.07.2005) US

(71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL PATENTS INC.** [US/US]; A CORPORATION OF THE STATE OF DELAWARE, 5200 Bayway Drive, Baytown, TX 77520-2101 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **WU, Margaret, M.** [US/US]; 45 Richmond Drive, Skillman, NJ 08558 (US). **YANG, Norman** [US/US]; 2 Normandy Drive, Westfield, NJ 07090 (US). **BAUGH, Lisa, S.** [US/US]; 71 Manners Road, Ringoes, NJ 08551 (US). **CANICH, Jo Ann, M.** [US/US]; 15710 Mesa Verde Drive, Houston, TX 77059 (US). **RUCKER, Steven, P.** [US/US]; 5 Fawn Lane, Warren, NJ 07059-5558 (US). **WALZER, John, F.** [US/US]; 204 Lakeshore Drive, Seabrook, TX 77586 (US). **LEE, Gordon, H.** [US/US]; 9 Leslie Place, Newton, PA 18940 (US). **LO, Frederick, Yip-kwai** [US/US]; P.O. Box 343, Middlesex, NJ 08842 (US). **JACKSON, Andrew** [US/US]; 4 Walking Purchase Drive, Pennington, NJ 08534 (US). **HAGEMEISTER, Mark** [US/US]; 10

Turkey Hill Road, Boonton, NJ 07005 (US). **TIRMIZI, Shakeel** [US/US]; 76 Idolstone Lane, Matawan, NJ 07747 (US). **JIANG, Peijun** [CN/US]; 119 Mariner Cove Court, League City, TX 77573 (US). **CHEE, Chia, S.** [US/US]; 17118 Chapel Park Way, Houston, TX 77059 (US).

(74) Agents: **GRIFFIS, Andrew, B.** et al.; EXXONMOBIL CHEMICAL COMPANY, LAW TECHNOLOGY, P.O. Box 2149, Baytown, TX 77522-2149 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POLYALPHA-OLEFIN COMPOSITIONS AND PROCESSES TO PRODUCE THE SAME



(I)

(57) Abstract: This invention relates to a polyalpha-olefin (and hydrogenated analogs thereof) comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has: a) 40 mole % or more of mm triads, b) a Bromine number of Y or greater, where Y is equal to $89.92 * (V)^{0.5863}$, where V is the Kinematic Viscosity of the polyalpha-olefin measured at 100°C in cSt, and c) 1,2 disubstituted olefins present at 7 mole % or more, preferably having Z mole % or more of units represented by the formula: where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and where

$Z = 8.420 * \log(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 1000C in cSt This invention also relates to process to produce such polyalpha-olefins.

WO 2007/011459 A1

- 1 -

POLYALPHA-OLEFIN COMPOSITIONS AND PROCESSES TO PRODUCE THE SAME

5 Field of the Invention

 This invention relates to a process to produce a new class of poly-alpha-olefins (PAOs) with unique chemical compositions. More specifically, this invention relates to novel PAOs prepared in the presence of a metallocene catalyst with an activator and a process for making PAOs in the presence of a metallocene
10 catalyst with an activator.

Description of Related Art

 Efforts to improve upon the performance of natural mineral oil-based lubricants by the synthesis of oligomeric hydrocarbon fluids have been the subject of important research and development in the petroleum industry for at least fifty
15 years. These efforts have led to the relatively recent market introduction of a number of synthetic lubricants. In terms of lubricant property improvement, the thrust of the industrial research efforts involving synthetic lubricants have been towards fluids exhibiting useful viscosities over a wide temperature range, *i.e.*, improved viscosity index (VI), while also showing lubricities, thermal and
20 oxidative stabilities and pour points equal to or better than those for mineral oil.

 The viscosity-temperature relationship of a lubricating oil is one of the critical criteria which must be considered when selecting a lubricant for a particular application. The mineral oils commonly used as a base for single and multigraded lubricants exhibit a relatively large change in viscosity with a change
25 in temperature. Fluids exhibiting such a relatively large change in viscosity with temperature are said to have a low viscosity index. Viscosity index is an empirical number which indicates the rate of change in the viscosity of an oil within a given temperature range. A high VI oil, for example, will thin out at elevated temperatures more slowly than a low VI oil. Usually, A high VI oil is
30 more desirable because it has higher viscosity at higher temperature, which translates into better lubrication and better protection of the contacting machine

- 2 -

elements, preferably at high temperatures and or at temperatures over a wide range. VI is calculated according to ASTM method D 2270.

PAOs comprise a class of hydrocarbons manufactured by the catalytic oligomerization (polymerization to low-molecular-weight products) of linear α -olefin (LAO) monomers. These typically range from 1-octene to 1-dodecene, with 1-decene being a preferred material, although oligomeric copolymers of lower olefins such as ethylene and propylene may also be used, including copolymers of ethylene with higher olefins as described in U.S. Patent 4,956,122 and the patents referred to therein. PAO products have achieved importance in the lubricating oil market. Typically there are two classes of synthetic hydrocarbon fluids (SHF) produced from linear alpha-olefins, the two classes of SHF being denoted as PAO and HVI-PAO (high viscosity index PAO's). PAO's and HVI-PAO's of different viscosity grades are typically produced using promoted BF_3 or AlCl_3 catalysts.

Specifically, PAOs may be produced by the polymerization of olefin feed in the presence of a catalyst such as AlCl_3 , BF_3 , or BF_3 complexes. Processes for the production of PAOs are disclosed, for example, in the following patents: U.S. Patents 3,149,178; 3,382,291; 3,742,082; 3,769,363; 3,780,128; 4,172,855 and 4,956,122. PAOs are also discussed in:

Will, J.G. *Lubrication Fundamentals*, Marcel Dekker: New York, 1980. Subsequent to polymerization, the PAO lubricant range products are typically hydrogenated in order to reduce the residual unsaturation, generally to a level of greater than 90%. HVI-PAO's may also be conveniently made by the polymerization of an alpha-olefin in the presence of a polymerization catalyst such as Friedel-Crafts catalysts. These include, for example, aluminum trichloride, boron trifluoride, aluminum trichloride or boron trifluoride promoted with water, with alcohols such as ethanol, propanol, or butanol, with carboxylic acids, or with esters such as ethyl acetate or ethyl propionate or ether such as diethyl ether, diisopropyl ether, etc. For example, the methods disclosed by U.S. Patents 4,149,178 or 3,382,291 may be conveniently used herein. Other descriptions of PAO synthesis are found in the following U.S. Patents: 3,742,082 (Brennan); 3,769,363 (Brennan); 3,876,720 (Heilman); 4,239,930 (Allphin);

- 3 -

4,367,352 (Watts); 4,413,156 (Watts); 4,434,408 (Larkin); 4,910,355 (Shubkin); 4,956,122 (Watts); and 5,068,487 (Theriot).

Another class of HVI-PAOs may be prepared by the action of a supported, reduced chromium catalyst with an alpha-olefin monomer. Such PAOs are
5 described in U.S. Patents 4,827,073 (Wu); 4,827,064 (Wu); 4,967,032 (Ho et al.); 4,926,004 (Pelrine et al.); and 4,914,254 (Pelrine). Commercially available PAOs include SpectraSyn™ 2, 4, 5, 6, 8, 10, 40, 100 and SpectraSyn Ultra™ 150, SpectraSyn Ultra™ 300, SpectraSyn Ultra™ 1000, etc. (ExxonMobil Chemical Company, Houston Texas).

10 Synthetic PAOs have found wide acceptability and commercial success in the lubricant field for their superiority to mineral based lubricants. In terms of lubricant property improvement, industrial research efforts on synthetic lubricants have led to PAO fluids exhibiting useful viscosities over a wide range of temperature, *i.e.*, improved viscosity index, while also showing lubricity, thermal
15 and oxidative stability and pour point equal to or better than mineral oil. These relatively new synthetic lubricants lower mechanical friction, enhancing mechanical efficiency over the full spectrum of mechanical loads and do so over a wider range of operating conditions than mineral oil lubricants.

Performance requirements of lubricants are becoming increasingly
20 stringent. New PAOs with improved properties, such as high viscosity index (VI), low pour point, high shear stability, improved wear performance, increased thermal and oxidative stability, and or wider viscosity range, are needed to meet new performance requirements for lubricants. New methods to provide such new PAOs with improved properties are also needed.

25 Efforts have been made to prepare various PAOs using metallocene catalyst systems. Examples include US 6,706,828 (equivalent to US 2004/0147693), where PAOs are produced from *meso*-forms of certain metallocene catalysts under high hydrogen pressure. Comparative example D of US 6,706,828, however, uses *rac*-dimethylsilylbis(2-methyl-indenyl)zirconium
30 dichloride in combination with methylalumoxane (MAO) at 100°C in the presence of hydrogen to produce polydecene having a reported Kinematic Viscosity at 100 °C (KV₁₀₀) of 116 cSt, a Kinematic Viscosity at 40°C (KV₄₀) of 1039 cSt, a VI of

- 4 -

214, an iodine number of 2.8, an Mw of 7084, an Mn of 2906, an Mw/Mn of 2.4, and a Tg of -72.4°C. Likewise, WO 02/14384 discloses, among other things, in examples J and K the use of *rac*-ethyl-bis(indenyl)zirconium dichloride or *rac*-dimethylsilyl-bis(2-methyl-indenyl) zirconium dichloride in combination with
5 MAO at 40 °C (at 200 psi hydrogen or 1 mole of hydrogen) to produce isotactic polydecene reportedly having a Tg of -73.8°C, a KV₁₀₀ of 702 cSt, and a VI of 296; or to produce polydecene reportedly having a Tg of -66 °C, a KV₁₀₀ of 1624, and a VI of 341, respectively. Further WO 99/67347 discloses in example 1 the use of ethylidene bis(tetrahydroindenyl)zirconium dichloride in combination with
10 MAO at 50°C to produce a polydecene having an Mn of 11,400 and 94% vinylidene double bond content.

Others have made various PAOs, such as polydecene, using various metallocene catalysts not typically known to produce polymers or oligomers with any specific tacticity. Examples include WO 96/23751, EP 0 613 873, US
15 5,688,887, US 6,043,401, WO 03/020856 (equivalent to US 2003/0055184), US 6,548,724 (equivalent to US 2001/0041817 and US 6,548,723), US 5,087,788, US 6,414,090, US 6,414,091, US 4,704,491, US 6,133,209, and US 6,713,438.

To date however, PAO's made with metallocenes have not found wide applicability in the marketplace, particularly the lubricant marketplace, due to
20 inefficient process, cost and property deficits. The instant invention address such and other needs by providing new PAO's and or HVI-PAO's having excellent property combinations and an improved process to produce them.

Summary of Invention

25

This invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C₅ to C₂₄ alpha-olefin monomers where the polyalpha-olefin has:


- a) 40 mole % or more of mm triads,
- 30 b) a Bromine number of Y or greater, where Y is equal to $89.92 * (V)^{0.5863}$, where V is the kinematic viscosity of the polyalpha-olefin in cSt measured at 100°C, and

- 5 -

c) 1,2 disubstituted olefins present at 7 mole % or more, preferably present at Z mole % or more, where $Z = 8.420 \cdot \text{Log}(V) - 4.048$ where V is the kinematic viscosity of the polyalpha-olefin in cSt measured at 100°C.

5 Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has:

- a) 40 mole % or more of mm triads,
- b) a Bromine number of 1.8 or less, and
- 10 c) Z mole % or more of units represented by the formula:




where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22; n is an integer from 1 to 350; and where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt

20 Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has:

- a) 40 mole % or more of mm triads,
- b) a Bromine number of Y or greater, where Y is equal to $89.92 \cdot (V)^{-0.5863}$, where V is the kinematic viscosity of the polyalpha-olefin in cSt measured at 25 100°C, and
- c) 1,2 disubstituted olefins, preferably present at Z mole % or more of units represented by the formula:


- 6 -



where the olefinic 1,2-disubstituted carbons will be positioned between Ca and Cb or occasionally between Cb and Cc, and where j, k and m are each,
 5 independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22; n is an integer from 1 to 350; and
 where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt.

10 Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has:

- a) less than 40 mole % of mm triads,
- b) a Bromine number of 1.8 or less, and
- 15 c) Z mole % or more of units represented by the formula:




where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15,
 20 or 16, n is an integer from 1 to 350, and
 where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt

- 7 -

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has Z mole % or more of units represented by the formula:

5



where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and
 10 where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt

Alternatively, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the
 15 polyalpha-olefin has:

- a) 40 mole % or less of mm triads,
- b) a Bromine number of Y or greater, where Y is equal to $89.92 \cdot (V)^{0.5863}$, where V is the kinematic viscosity in cSt measured at 100°C, and
- c) 1,2 disubstituted olefins present at Z mole % or more where $Z =$
 20 $8.420 \cdot \text{Log}(V) - 4.048$ where V is the kinematic viscosity of the polyalphaolefin in cSt measured at 100°C.

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the
 25 polyalpha-olefin has 40 mole % or more of mm triads and less than 300 ppm of a Group 4 metal.

- 8 -

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has 40 mole % or more of mm triads and less than 1000 ppm of a Group 13 metal, preferably less than 1000 pm of aluminum and/or boron.

5

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has 40 mole % or more of mm triads and less than 1000 ppm of aluminum and boron.

10

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers, where the polyalpha-olefin has 40 mole % or more of mm triads and less than 100 ppm of a Group 13 metal.

15

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers, where the polyalpha-olefin has 40 mole % or more of mm triads and less than 1000 ppm of aluminum.

20

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers, where the polyalpha-olefin has 40 mole % or more of mm triads and less than 600 ppm of aluminum.

25

Alternatively, this invention relates to a hydrogenated polyalpha-olefin comprising more than 50 mole% of one or more C5 to C24 alpha-olefin monomers, where the polyalpha-olefin has mm triads ranging from 95% to 20% mm triads and less than 1000 ppm of group 13 metals, preferably less than 1000 ppm of aluminum and/or boron.

30

- 9 -

Alternatively, this invention relates to a hydrogenated polyalpha-olefin comprising more than 50 mole% of one or more C5 to C24 alpha-olefin monomers, where the polyalpha-olefin has mm triads ranging from 95% to 20% mm triads and less than 1000 ppm of group 13 metals, preferably less than 1000 ppm of aluminum and/or boron.

Alternately, this invention relates to a polyalpha-olefin comprising more than 50 mole % C5 to C24 alpha-olefin monomers and having an Mw of 100,000 or less and an Mw/Mn of greater than 1 and less than 2.5.

10

This invention also relates to process to produce such polyalpha-olefins comprising contacting the C5 to C20 monomers with a metallocene catalyst (preferably a racemic metallocene catalyst), an activator (preferably an alumoxane and or a non-coordinating anion) and, optionally an alkylaluminum compound.

15

This invention also relates to process to produce such polyalpha-olefins comprising contacting C5 to C20 monomers with a metallocene catalyst and an activator, preferably a racemic metallocene catalyst with an alumoxane or NCA as activator, or a substituted metallocene catalyst with an NCA activator, or a meso metallocene with an NCA activator. In all cases, optionally a co-activator such as an alkylaluminum compound may be used.

20

Further, these polyalpha-olefins (and any polyalpha-olefins described herein) may be hydrogenated by contacting the polyalpha-olefin with hydrogen and a hydrogenation catalyst. This hydrogenation step is often used to reduce the bromine number and/or to modify the amount of mm triads in the final poly-alpha-olefins.

25

Detailed Description of the Invention

As used herein, the new numbering scheme for the Periodic Table of the Elements is used as set out in CHEMICAL AND ENGINEERING NEWS, 63(5), 27 (1985).

- 5 For purposes of this invention and the claims thereto, when a polymer or oligomer is referred to as comprising an olefin, the olefin present in the polymer or oligomer is the polymerized or oligomerized form of the olefin, respectively. Likewise the use of the term polymer is meant to encompass homopolymers and copolymers, where copolymers include any polymer having two or more
- 10 chemically distinct monomers. Likewise the use of the term oligomer is meant to encompass homooligomers and cooligomers, where cooligomers include any oligomer or having two or more chemically distinct monomers.

- 11 -

For the purposes of this invention and the claims thereto the term "Polyalpha-olefin," "polyalphaolefin," or "PAO" includes homooligomers, cooligomers, homopolymers and copolymers of alpha-olefin monomers.

For the purposes of this invention and the claims thereto the active species
5 in a catalytic cycle may comprise the neutral or ionic forms of the catalyst.

The term "catalyst system" is defined to mean a catalyst precursor/activator pair, such as a metallocene/activator pair. When "catalyst system" is used to describe such a pair before activation, it means the unactivated catalyst (precatalyst) together with an activator and, optionally, a co-activator
10 (such as a trialkylaluminum compound). When it is used to describe such a pair after activation, it means the activated catalyst and the activator or other charge-balancing moiety. Additionally, the catalyst system may optionally comprise a co-activator and/or other charge-balancing moiety.

"Catalyst precursor" is also often referred to as precatalyst, catalyst,
15 precursor, metallocene, transition metal compound, unactivated catalyst, or transition metal complex. These words are used interchangeably. Activator and cocatalyst are also used interchangeably. A scavenger is a compound that is typically added to facilitate oligomerization or polymerization by scavenging impurities. Some scavengers may also act as activators and may be referred to as
20 co-activators. A co-activator which is not a scavenger may also be used in conjunction with an activator in order to form an active catalyst with a transition metal compound. In some embodiments, a co-activator can be pre-mixed with the transition metal compound to form an alkylated transition metal compound, also referred to as an alkylated catalyst compound or alkylated metallocene.

25 For purposes of this invention and the claims thereto noncoordinating anion (NCA) is defined to mean an anion which either does not coordinate to the catalyst metal cation or that coordinates only weakly to the metal cation. An NCA coordinates weakly enough that a neutral Lewis base, such as an olefinically or acetylenically unsaturated monomer, can displace it from the catalyst center. Any
30 metal or metalloid that can form a compatible, weakly coordinating complex with the catalyst metal cation may be used or contained in the noncoordinating anion. Suitable metals include, but are not limited to, aluminum, gold, and platinum.

- 12 -

Suitable metalloids include, but are not limited to, boron, aluminum, phosphorus, and silicon. A subclass of non-coordinating anions comprises stoichiometric activators, which can be either neutral or ionic. The terms ionic activator, and stoichiometric ionic activator can be used interchangeably. Likewise, the terms
5 neutral stoichiometric activator and Lewis acid activator can be used interchangeably.

In addition, a reactor is any container(s) in which a chemical reaction occurs.

Polyalpha-olefins

10 In a preferred embodiment, this invention relates to polyalpha-olefins (PAO's) comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers, preferably 55 mole % or more, preferably 60 mole % or more, preferably 65 mole % or more, preferably 70 mole % or more, preferably 75 mole % or more, preferably 80 mole % or more, preferably 85 mole % or more,
15 preferably 90 mole % or more, preferably 95 mole % or more, preferably 100 mole % based on the total moles of monomers present in the polyalpha-olefin, as measured by Carbon -13 NMR.

In another embodiment this invention further relates to PAO's having 40 mole % or more of mm triads, preferably 45% or more, preferably 50 % or more,
20 preferably 55% or more, preferably 60% or more, preferably 65% or more, preferably 70% or more, preferably 75% or more, preferably 80% or more, preferably 85% or more, preferably 90% or more, preferably 95% or more, as determined by Carbon-13 Nuclear Magnetic Resonance (NMR) spectroscopy according to the procedure below.

25 In another embodiment, the polyalphaolefins according to the present invention have at least about 84 mole % mm triads. In yet other embodiments, the PAO's have at least about 98 mole % mm triads. In one embodiment, the polyalphaolefins according to the present invention have a ratio of mm to mr triads ranging from about 49 to about 1.0. In one embodiment, the preferred range
30 is from 1.0 to 10.0, or from 2 to 49, or from 2 to 18, with more preferred ranges of from 1.0 to 8 or from 8 to 49, as measured by Carbon 13 NMR.

- 13 -

In another embodiment, this invention further related to hydrogenated PAO's having 90% or less mm triads, preferably 70% mm triads or less, preferably 50% mm triads or less, preferably 30% or less mm triads, or preferably 10% mm triads or less.

5 In another embodiment, the hydrogenated polyalphaolefins according to the present invention have a ratio of mm to mr triads of less than 1, with preferred range from 0.01 to 0.9.

NMR spectroscopy provides key structural information about the synthesized polymers. Proton NMR analysis of the unhydrogenated PAO gives a
10 quantitative breakdown of the olefinic structure types (viz. vinyl, 1,2-disubstituted, trisubstituted, and vinylidene). As noted above, Carbon-13 NMR is used to determine tacticity of the polyalphaolefins of the present invention – quantitatively in some cases, and qualitatively in others. Carbon-13 NMR can be used to determine the concentration of the triads, denoted mm (meso, meso), mr
15 (meso, racemic) and rr (racemic, racemic), as well as molar composition of the sample. The concentrations of these triads defines whether the polymer is isotactic, atactic or syndiotactic. Spectra for a PAO sample are acquired in the following manner. Approximately 100-1000 mg of the PAO sample is dissolved in 2-3 ml of chloroform-*d* for Carbon 13 analysis. Approximately -10 mg/ml
20 (solvent basis) of chromium acetylacetonate relaxation agent, Cr(acac)₃, is added to the sample to enhance the data acquisition rate. Analysis of the spectra is performed according to the paper by Kim, I.; Zhou, J.-M.; and Chung, H. *Journal of Polymer Science: Part A: Polymer Chemistry* 2000, 38 1687-1697, augmented by the identification and integration of end group resonances, and removal of their
25 contributions to the peaks used in the analysis. The deconvolutions are executed with Acorn NMR Inc.'s NutsPro NMR data analysis software, using an 85/15 Lorentzian/Gaussian lineshape. The component peaks are lumped together into clusters according to the *mm*, *mr*, and *rr* triad assignments, and fit with a Bernoullian distribution. The adjustable parameter for these fits is *P_r*, the fraction
30 of monomer added with racemic stereochemistry. For details of going from a set of triad measurements (such as described by Kim above) to a statistical model

- 14 -

(such as the Bernoullian) see "Polymer Sequence Determination, James C. Randall, Academic Press, New York, 1977"

In another embodiment, any of the polyalpha-olefins produced herein
5 preferably have a Bromine number of Y or greater, where Y is equal to
 $89.92 \times (V)^{-0.5863}$, where V is the Kinematic Viscosity at 100°C (KV₁₀₀) of the
polyalpha-olefin and where KV₁₀₀ is measured according to ASTM D 445,
preferably a bromine number of Y +1 or greater, preferably Y+2 or greater,
preferably Y+3 or greater, preferably Y+4 or greater, where Bromine number is
10 measured by ASTM D 1159.

In another embodiment, any of the polyalpha-olefins produced herein
preferably have 1,2 disubstituted olefins present at 7 mole % or more, based upon
the total moles of all monomers present in the poly-alpha-olefin as measured by
15 Proton NMR, preferably 8 mole % or more, preferably 9 mole % or more,
preferably 10 mole % or more, preferably 15 mole % or more.

In another embodiment, any of the polyalpha-olefins produced herein
preferably have 1,2- disubstituted olefins present at Z mole % or more as
20 measured by Proton-NMR, where $Z = 8.420 \times \text{Log}(V) - 4.048$, where V is the
kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt


In another embodiment, any of the polyalpha-olefins produced herein
preferably have a Bromine number of 1.8 or less as measured by ASTM D 1159,
25 preferably 1.7 or less, preferably 1.6 or less, preferably 1.5 or less, preferably 1.4
or less, preferably 1.3 or less, preferably 1.2 or less, preferably 1.1 or less,
preferably 1.0 or less, preferably 0.5 or less, preferably 0.1 or less.

In another embodiment, any of the polyalpha-olefins produced herein are
30 hydrogenated and have a Bromine number of 1.8 or less as measured by ASTM D
1159, preferably 1.7 or less, preferably 1.6 or less, preferably 1.5 or less,

- 15 -

preferably 1.4 or less, preferably 1.3 or less, preferably 1.2 or less, preferably 1.1 or less, preferably 1.0 or less, preferably 0.5 or less, preferably 0.1 or less.

In another embodiment, any of the polyalpha-olefins described herein
5 preferably have Z mole % or more of units represented by the formula:



where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15,
10 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350 (preferably 1 to 300, preferably 5 to 50), as measured by proton NMR and
where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the
polyalpha-olefin measured at 100°C in cSt, preferably Z is $= 0.990 \cdot V^{(0.627)}$.

15 The proton NMR analysis (used to measure 1,2-disubstitutions and the units represented by the formula above) is performed by dissolving the sample in appropriate deuterated solvent (e.g. chloroform-d), and acquiring a pulse-acquire experiment of sufficient signal-to-noise ratio to allow integration of the olefin region (approximately 6 ppm – 4.6 ppm). The spectra are acquired at a
20 temperature of 50°C, with the temperature chosen to ensure complete sample dissolution (if the sample is not completely dissolved at 50 °C, then the temperature is raised slowly until the sample is completely dissolved). The aliphatic region of the proton spectrum comprises the signal from the saturated components, and the olefinic region from the unsaturated end of the polymer. In
25 cases where multiple alphaolefins are copolymerized, it may be possible to determine the composition of the polymer from the branch methyl resonances of the differing alphaolefin branches. This composition determination can be

- 16 -

executed if the methyl peaks (resonating between 1.0 and 0.6 ppm) are sufficiently resolved to allow direct integration, or spectral deconvolution.

The olefinic region can be integrated piecewise according to the chemical shift assignments tabulated below:

Olefin type	Chemical shift range (ppm)	Number of protons
Vinyl	5.7 – 5.9	1
	4.8 – 5.3	2
1,2-disubstituted	5.3 – 5.6	2
Trisubstituted	4.8 – 5.3	1
Vinylidene (1,1-disubstituted)	4.6 – 4.8	2

5

The olefin subintegrals are corrected for the proton multiplicity of the contributing species, and for overlapping contributions (e.g. both vinyl and trisubstituted olefins in the 5.3-4.8 ppm region). The integral values resulting from this correction can then be normalized to give the mole-percentage of each olefin class. Comparison of the corrected integral values with the aliphatic integral intensity (also multiplicity-corrected) can be used to determine the olefin concentrations on an absolute basis (e.g. olefins per 1000 carbons).

10

In another embodiment, any of the polyalpha-olefins described herein preferably have less than 300 ppm of Group 4 metals (preferably Ti, Hf or Zr), preferably less than 200 ppm, preferably less than 100 ppm, preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

15

In another embodiment, any of the polyalpha-olefins described herein preferably have less than 300 ppm of Ti, preferably less than 200 ppm, preferably less than 100 ppm, preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

20

In another embodiment, any of the polyalpha-olefins described herein preferably have less than 300 ppm of Hf, preferably less than 200 ppm, preferably less than 100 ppm, preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

25

- 17 -

In another embodiment, any of the polyalpha-olefins described herein preferably have less than 300 ppm of Zr, preferably less than 200 ppm, preferably less than 100 ppm, preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

5 In another embodiment, any of the polyalpha-olefins described herein preferably have less than 100 ppm of Group 13 metals (preferably B or Al), preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

10 In another embodiment, any of the polyalpha-olefins described herein preferably have less than 100 ppm of boron, preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

In another embodiment, any of the polyalpha-olefins described herein preferably have less than 600 ppm of aluminum, preferably less than 500 ppm, preferably less than 600 ppm, preferably less than 300 ppm, preferably less than
15 300 ppm, preferably less than 10 ppm, preferably less than 50 ppm, preferably less than 10 ppm, as measured by ASTM 5185.

In another embodiment, any of the polyalpha-olefins described herein preferably have an Mw (weight average molecular weight) of 100,000 or less, preferably between 100 and 80,000, preferably between 250 and 60,000,
20 preferably between 280 and 50,000, preferably between 336 and 40,000 g/mol. (Preferred Mw's include those from 224 to 55,100, preferably from 392 to 30,000, preferably 800 to 24,000, preferably 2,000 to 37,5000 g/mol. Alternately preferred Mw's include 224 to about 6790 and 224 to about 2720).

In another embodiment, any of the polyalpha-olefins described herein
25 preferably have an Mn (number average molecular weight) of 50,000 or less, preferably between 200 and 40,000, preferably between 250 and 30,000, preferably between 500 and 20,000 g/mol. (Preferred Mn's include those from 280 to 10,000, preferably from 280 to 4000. Alternately preferred Mn's include those from 200 to 20,900, preferably 280, to 10,000, preferably 200 to 7000,
30 preferably 200 to 2000, preferably 280 to 2900, preferably 280 to 1700, preferably 200 to 500.)

- 18 -

In another embodiment, any of the polyalpha-olefins described herein preferably have an Mw/Mn of greater than 1 and less than 5, preferably less than 4, preferably less than 3, preferably less than 2.5, preferably less than 2.

Alternately any of the polyalpha-olefins described herein preferably have an
5 Mw/Mn of between 1 and 2.5, alternately between 1 and 3.5.

The Mw, Mn and Mz are measured by GPC method using a column for medium to low molecular weight polymers, tetrahydrofuran as solvent and polystyrene as calibration standard, correlated with the fluid viscosity according to a power equation.

10 This relationship of Mw vs. 100°C viscosity in cSt for fluids prepared in this invention using 1-decene as feed is as following: $Mw = 352.41 \times (100^\circ\text{C vis in cSt})^{0.5997}$. Similarly, the relationship of Mw vs. 100°C viscosity in cSt for fluids prepared in this invention using 1-hexene as feed is as following: $Mw = 234.85 * (V)^{0.6165}$ where V is the kinematic viscosity measured at 100°C in cSt. When other
15 alpha-olefins are used as feed, this Mw vs. 100°C viscosity relationship may change slightly. It is expected similar type of relationship will hold.

Unless otherwise indicated Mw values reported herein are GPC values and not calculated from KV100.

In a preferred embodiment of this invention, any PAO described herein
20 may have a pour point of less than 0 °C (as measured by ASTM D 97), preferably less than -10 °C, preferably less than -20 °C, preferably less than -25°C, preferably less than -30°C, preferably less than -35°C, preferably less than -50 °C, preferably between -10 and -80 °C, preferably between -15°C and -70°C.

In a preferred embodiment of this invention, any PAO described herein
25 may have a kinematic viscosity (at 40°C as measured by ASTM D 445) from about 4 to about 50,000 cSt, preferably from about 5 cSt to about 30,000 cSt at 40 °C, alternately from about 4 to about 100,000 cSt, preferably from about 6 cSt to about 50,000 cSt, preferably from about 10 cSt to about 30,000 cSt at 40 °C.

In another embodiment according to the present invention, any polyalpha
30 olefin described herein may have a kinematic viscosity at 100°C from about 1.5 to about 5,000 cSt, preferably from about 2 to about 3,000 cSt, preferably from about 3 cSt to about 1,000 cSt, more preferably from about 4 cSt to about 1,000 cSt, and

- 19 -

yet more preferably from about 8 cSt to about 500 cSt as measured by ASTM D445. The PAOs preferably have viscosities in the range of 2 to 500 cSt at 100°C in one embodiment, and from 2 to 3000 cSt at 100 °C in another embodiment, and from 3.2 to 300 cSt in another embodiment. Alternately, the polyalpha-olefin has
5 a KV₁₀₀ of less than 200 cSt.

In another embodiment according to the present invention any polyalpha olefin described herein may have a kinematic viscosity at 100°C from 3 to 10 cSt and a flash point of 150 °C or more, preferably 200 °C or more (as measured by ASTM D 56).

10 In another embodiment according to the present invention any polyalpha olefin described herein may have a dielectric constant of 2.5 or less (1 kHz at 23 °C as determined by ASTM D 924).

In another embodiment according to the present invention any polyalpha olefin described herein may have a specific gravity of 0.75 to 0.96 g/cm³,
15 preferably 0.80 to 0.94 g/cm³.

The PAO's prepared herein, particularly those of low viscosity (such as those with a KV₁₀₀ of 10 cSt or less), are especially suitable for high performance automotive engine oil formulations either by themselves or by blending with other fluids, such as Group II, Group II+, Group III, Group III+ or lube base stocks
20 derived from hydroisomerization of wax fractions from Fisher-Tropsch hydrocarbon synthesis from CO/H₂ syn gas, or other Group IV or Group V base stocks. PAOs having KV₁₀₀'s from 3 cSt to 8 cSt are also preferred grades for high performance automotive engine oil or industrial oil formulations. The PAO's of 40 to 1000 cSt made in this invention are desirable for use as blend stock with
25 Gr I, II, III, III+ or GTL derived lube base stocks for use in industrial and automotive engine or gear oil, especially certain high KV₁₀₀ grades of 3 to 1000 cSt which are especially desirable for use as blend stock with Gr I, II, III, III+ or GTL derived lube base stocks for use in industrial and automotive engine or gear oil. They are also suitable for use in personal care applications, such as blends
30 with soaps, detergents, other emollients, for use in personal care creams, lotions, sticks, shampoos, detergents, etc.

- 20 -

In another embodiment the PAO's have KV₁₀₀'s ranging from about 42 to about 3045 cSt. In another embodiment the PAO's have KV₁₀₀'s ranging from about 32 to about 102 cSt.

In another embodiment according to the present invention, any polyalpha olefin described herein may have a viscosity index (VI) of 100 or more, preferably 120 or more, preferably 130 or more, alternately, from 120 to 450, alternately from 100 to 400, alternately from 120 to 380, alternately from 100 to 300, alternately from 140 to 380, alternately from 180 to 306, alternately from 252 to 306, alternately the viscosity index is at least about 165, alternately at least about 187, alternately at least about 200, alternately at least about 252. For many lower viscosity fluids made from 1-decene or 1-decene equivalent feeds (KV₁₀₀ of 3 to 10 cSt), the preferred VI range is from 100 to 180. Viscosity index is determined according to ASTM Method D 2270-93 [1998].

All kinematic viscosity values reported for fluids herein are measured at 100 °C unless otherwise noted. Dynamic viscosity can then be obtained by multiplying the measured kinematic viscosity by the density of the liquid. The units for kinematic viscosity are in m^2/s , commonly converted to *cSt* or *centistokes* ($1cSt = 10^{-6} m^2/s$ or $1 cSt = 1 mm^2/sec$).

One embodiment according to the present invention is a new class of poly-alpha-olefins, which have a unique chemical composition characterized by a high percentage of unique head-to-head connections at the end position of the polymer chain and a high degree of stereo-regularity. The new poly-alpha-olefins when used by themselves or blended with other fluids have unique lubrication properties. The term "head-to-head connection" refers to a connection formed on at least one end of the PAO oligomer or polymer in which the penultimate olefin inserted 1,2 and the last olefin inserted 2,1 into the oligomer or polymer chain, as illustrated in the lower scheme in Figure 3.

Another embodiment according to the present invention is a new class of hydrogenated poly-alpha-olefins having a unique chemical composition which is characterized by a high percentage of unique head-to-head connection at the end position of the polymer and by a reduced degree tacticity compared to the product

- 21 -

before hydrogenation. The new poly-alpha-olefins when used by itself or blended with another fluid have unique lubrication properties.

The PAO's produced according to this invention are typically dimers, trimers, tetramers, or higher oligomers of one or more C5 to C24 olefin monomers, preferably one or more C5 to C24 alpha-olefin monomers, preferably one or more C5 to C24 linear alpha-olefin monomers. Alternatively, an alpha-olefin with alkyl substituent at least 2 carbons away from the olefinic double bond can also be used. Typically, the PAO's produced herein are usually a mixture of many different oligomers. The smallest oligomers from these alpha-olefins have carbon number ranging from C10 to C20. These small oligomers are usually too light for most high performance fluids application. They are usually separated from the higher oligomers with carbon number of greater than C20, for example C24 and higher which are more preferred as high performance fluids. These separated C10 to C20 oligomer olefins or the corresponding paraffins after hydrogenation can be used in specialty applications, such as drilling fluids, solvents, paint thinner, etc with excellent biodegradability, toxicity, viscosities, etc. The high performance fluid fraction in the C20, or C30 and higher fractions typically have lower viscosities making them beneficial for some applications, such as better fuel economy, better biodegradability, better low temperature flow properties, or lower volatility. The higher viscosity product, usually have much higher average degree of polymerization have very low amount of C20 or C30 component. These high viscosity fluids are excellent blend stocks for lube application to improve the viscosity. Because of their usually narrow molecular weight distribution, they have superior shear stability. Because of their unique chemical composition, they have excellent viscometrics and unexpected low traction properties. These higher viscosity PAO can be used as superior blend stocks. They can be blend stocks with any of the Gr I, II, III, III+, GTL and Gr V fluids to give the optimum viscometrics, solvency, high and low temperature lubricity, etc. When further blended with proper additives, including antioxidants, anitwear additives, friction modifiers, dispersants, detergents, corrosion inhibitors, defoamants, extreme pressure additives, seal swell additives, and optionally viscosity modifiers, etc. Description of typical additives can be found in the book

- 22 -

“Lubricant Additives” Chemistry and Applications, ed. L. R. Rudnick, Marcel Dekker, Inc., New York, 2003.

Process

One embodiment of the present invention discloses an improved process to produce a new class of poly-alpha-olefins having unique chemical compositions. This improved process employs metallocene catalysts together with one or more activators (such as an alumoxane or a non-coordinating anion). The metallocene catalyst can be a bridged or unbridged, substituted or unsubstituted cyclopentadienyl, indenyl or fluorenyl compound. One preferred class of catalysts are highly substituted metallocenes that give high catalyst productivity and higher product viscosity. Another preferred class of metallocenes are bridged and substituted cyclopentadienes. Another preferred class of metallocenes are bridged and substituted indenenes or fluorenes. One aspect of the processes described herein also includes treatment of the feed olefins to remove catalyst poisons, such as peroxides, oxygen, sulfur, nitrogen-containing organic compounds, and or acetylenic compounds. This treatment is believed to increase catalyst productivity, typically more than 5 fold, preferably more than 10 fold.


In a preferred embodiment, this invention relates to a process to produce a polyalpha-olefin comprising:

- 1) contacting at least one alpha-olefin monomer having 5 to 24 carbon atoms with a racemic metallocene compound (preferably a highly substituted compound) and an activator under polymerization conditions wherein hydrogen, if present, is present at a partial pressure of 200 psi (1379 kPa) or less, based upon the total pressure of the reactor (preferably 150 psi (1034 kPa) or less, preferably 100 psi (690 kPa) or less, preferably 50 psi (345 kPa) or less, preferably 25 psi (173 kPa) or less, preferably 10 psi (69 kPa) or less (alternately the hydrogen, if present is present in the reactor at 1000ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less), and wherein the alpha-olefin monomer having 5 to 24 carbon atoms is present at 10 volume % or more based upon the

- 23 -

total volume of the catalyst/activator/co-activator solutions, monomers, and any diluents or solvents present in the reaction; and

- 2) obtaining a polyalpha-olefin, optionally hydrogenating the PAO, and obtaining a PAO, comprising at least 50 mole% of a C5 to C24 alpha-olefin monomer, wherein the polyalpha-olefin has a kinematic viscosity at 100°C of 5000 cSt or less, and the polyalpha-olefin comprises Z mole % or more of units represented by the formula:



where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the Kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt.

In an alternate embodiment, this invention relates to a process to produce a polyalpha-olefin comprising:

- 1) contacting a feed stream comprising at least one alpha-olefin monomer having 5 to 24 carbon atoms with a metallocene catalyst compound and a non-coordinating anion activator or alkylalumoxane activator, and optionally an alkyl-aluminum compound, under polymerization conditions wherein the alpha-olefin monomer having 5 to 24 carbon atoms is present at 10 volume % or more based upon the total volume of the catalyst/activator/co-activator solution, monomers, and any diluents or solvents present in the reactor and where the feed alpha-olefin, diluent or solvent stream comprises less than 300 ppm of heteroatom containing compounds; and obtaining a polyalpha-olefin comprising at least 50 mole% of a C5 to C24 alpha-olefin monomer where the polyalpha-olefin has a kinematic viscosity at 100°C of 5000 cSt or less. Preferably, hydrogen, if present

- 24 -

is present in the reactor at 1000ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less.

5

In an alternate embodiment, this invention relates to a process to produce a polyalpha-olefin comprising:

1) contacting a feed stream comprising at least one alpha-olefin monomer having 5 to 24 carbon atoms with a metallocene catalyst compound and
10 a non-coordinating anion activator or alkylalumoxane activator, and optionally an alkyl-aluminum compound, under polymerization conditions wherein the alpha-olefin monomer having 5 to 24 carbon atoms is present at 10 volume % or more based upon the total volume of the catalyst/activator/co-activator solution, monomers, and any diluents or solvents present in the reactor and where the feed
15 alpha-olefin, diluent or solvent stream comprises less than 300 ppm of heteroatom containing compounds which; and obtaining a polyalpha-olefin comprising at least 50 mole% of a C5 to C24alpha-olefin monomer where the polyalpha-olefin has a kinematic viscosity at 100°C of 5000 cSt or less;

2) isolating the lube fraction polymers and then contacting this lube
20 fraction with hydrogen under typical hydrogenation conditions with hydrogenation catalyst to give fluid with bromine number below 1.8, or alternatively, isolating the lube fraction polymers and then contacting this lube fraction with hydrogen under more severe conditions with hydrogenation catalyst to give fluid with bromine number below 1.8 and with reduce mole% of mm
25 components than the unhydrogenated polymers.

Alternately, in any process described herein hydrogen, if present, is present in the reactor at 1000ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or
30 less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less.

- 25 -

Alternately, in any process described herein hydrogen, if present, is present in the feed at 1000 ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less.

Unless otherwise stated all pressures in psi are psig.

Metallocene Catalyst Compounds

For purposes of this invention and the claims thereto, the terms "hydrocarbyl radical," "hydrocarbyl," and hydrocarbyl group" are used interchangeably throughout this document. Likewise the terms "group," "radical," and "substituent" are also used interchangeably throughout this document. For purposes of this disclosure, "hydrocarbyl radical" is defined to be a C₁-C₁₀₀ radical and may be linear, branched, or cyclic. When cyclic, the hydrocarbon radical may be aromatic or non-aromatic. "Hydrocarbon radical" is defined to include substituted hydrocarbyl radicals, halocarbyl radicals, substituted halocarbyl radicals, silylcarbyl radicals, and germylcarbyl radicals as these terms are defined below. Substituted hydrocarbyl radicals are radicals in which at least one hydrogen atom has been substituted with at least one functional group such as NR^{*}₂, OR^{*}, SeR^{*}, TeR^{*}, PR^{*}₂, AsR^{*}₂, SbR^{*}₂, SR^{*}, BR^{*}₂, SiR^{*}₃, GeR^{*}₃, SnR^{*}₃, PbR^{*}₃ and the like or where at least one non-hydrocarbon atom or group has been inserted within the hydrocarbyl radical, such as -O-, -S-, -Se-, -Te-, -N(R^{*})-, =N-, -P(R^{*})-, =P-, -As(R^{*})-, =As-, -Sb(R^{*})-, =Sb-, -B(R^{*})-, =B-, -Si(R^{*})₂-, -Ge(R^{*})₂-, -Sn(R^{*})₂-, -Pb(R^{*})₂- and the like, where R^{*} is independently a hydrocarbyl or halocarbyl radical, and two or more R^{*} may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.

Halocarbyl radicals are radicals in which one or more hydrocarbyl hydrogen atoms have been substituted with at least one halogen (e.g. F, Cl, Br, I) or halogen-containing group (e.g. CF₃).

- 26 -

Substituted halocarbyl radicals are radicals in which at least one halocarbyl hydrogen or halogen atom has been substituted with at least one functional group such as NR^*_2 , OR^* , SeR^* , TeR^* , PR^*_2 , AsR^*_2 , SbR^*_2 , SR^* , BR^*_2 , SiR^*_3 , GeR^*_3 , SnR^*_3 , PbR^*_3 and the like or where at least one non-carbon atom or group has been inserted within the halocarbyl radical such as -O-, -S-, -Se-, -Te-, -N(R*)-, =N-, -P(R*)-, =P-, -As(R*)-, =As-, -Sb(R*)-, =Sb-, -B(R*)-, =B-, -Si(R*)₂-, -Ge(R*)₂-, -Sn(R*)₂-, -Pb(R*)₂- and the like, where R* is independently a hydrocarbyl or halocarbyl radical provided that at least one halogen atom remains on the original halocarbyl radical. Additionally, two or more R* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.

Silylcarbyl radicals (also called silylcarbyls) are groups in which the silyl functionality is bonded directly to the indicated atom or atoms. Examples include SiH_3 , SiH_2R^* , SiHR^*_2 , SiR^*_3 , $\text{SiH}_2(\text{OR}^*)$, $\text{SiH}(\text{OR}^*)_2$, $\text{Si}(\text{OR}^*)_3$, $\text{SiH}_2(\text{NR}^*_2)$, $\text{SiH}(\text{NR}^*_2)_2$, $\text{Si}(\text{NR}^*_2)_3$, and the like where R* is independently a hydrocarbyl or halocarbyl radical and two or more R* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.

Germylcarbyl radicals (also called germylcarbyls) are groups in which the germyl functionality is bonded directly to the indicated atom or atoms. Examples include GeH_3 , GeH_2R^* , GeHR^*_2 , GeR^*_3 , $\text{GeH}_2(\text{OR}^*)$, $\text{GeH}(\text{OR}^*)_2$, $\text{Ge}(\text{OR}^*)_3$, $\text{GeH}_2(\text{NR}^*_2)$, $\text{GeH}(\text{NR}^*_2)_2$, $\text{Ge}(\text{NR}^*_2)_3$, and the like where R* is independently a hydrocarbyl or halocarbyl radical and two or more R* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.

Polar radicals or polar groups are groups in which a heteroatom functionality is bonded directly to the indicated atom or atoms. They include heteroatoms of groups 1-17 of the periodic table (except carbon and hydrogen) either alone or connected to other elements by covalent bonds or other interactions such as ionic bonds, van der Waals forces, or hydrogen bonding. Examples of functional heteroatom containing groups include carboxylic acids, acid halides, carboxylic esters, carboxylic salts, carboxylic anhydrides, aldehydes and their

- 27 -

chalcogen (Group 14) analogues, alcohols and phenols, ethers, peroxides and hydroperoxides, carboxylic amides, hydrazides and imides, amidines and other nitrogen analogues of amides, nitriles, amines and imines, azos, nitros, other nitrogen compounds, sulfur acids, selenium acids, thiols, sulfides, sulfoxides, sulfones, phosphines, phosphates, other phosphorus compounds, silanes, boranes, borates, alanes, aluminates. Functional groups may also be taken broadly to include organic polymer supports or inorganic support material such as alumina, and silica. Preferred examples of polar groups include NR^*_2 , OR^* , SeR^* , TeR^* , PR^*_2 , AsR^*_2 , SbR^*_2 , SR^* , BR^*_2 , SnR^*_3 , PbR^*_3 and the like where R^* is independently a hydrocarbyl, substituted hydrocarbyl, halocarbyl or substituted halocarbyl radical as defined above and two R^* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.

In using the terms "substituted or unsubstituted cyclopentadienyl ligand", "substituted or unsubstituted indenyl ligand", and "substituted or unsubstituted tetrahydroindenyl ligand", the substitution to the aforementioned ligand may be hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, silylcarbyl, or germylcarbyl. The substitution may also be within the ring giving heterocyclopentadienyl ligands, heteroindenyl ligands or heterotetrahydroindenyl ligands, each of which can additionally be substituted or unsubstituted.


In some embodiments, the hydrocarbyl radical is independently selected from methyl, ethyl, ethenyl, and isomers of propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, heneicosyl, docosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl, triacontyl, propenyl, butenyl, pentenyl, hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl, dodecenyl, tridecenyl, tetradecenyl, pentadecenyl, hexadecenyl, heptadecenyl, octadecenyl, nonadecenyl, eicosenyl, heneicosenyl, docosenyl, tricosenyl, tetracosenyl, pentacosenyl, hexacosenyl, heptacosenyl, octacosenyl, nonacosenyl, triacontenyl, propynyl, butynyl, pentynyl, hexynyl, heptynyl, octynyl, nonynyl, decynyl, undecynyl, dodecynyl, tridecynyl, tetradecynyl,

- 28 -

pentadecynyl, hexadecynyl, heptadecynyl, octadecynyl, nonadecynyl, eicosynyl, heneicosynyl, docosynyl, tricosynyl, tetracosynyl, pentacosynyl, hexacosynyl, heptacosynyl, octacosynyl, nonacosynyl, triacontynyl, butadienyl, pentadienyl, hexadienyl, heptadienyl, octadienyl, nonadienyl, and decadienyl. Also included
5 are isomers of saturated, partially unsaturated and aromatic cyclic and polycyclic structures wherein the radical may additionally be subjected to the types of substitutions described above. Examples include phenyl, methylphenyl, dimethylphenyl, ethylphenyl, diethylphenyl, propylphenyl, dipropylphenyl, benzyl, methylbenzyl, naphthyl, anthracenyl, cyclopentyl, cyclopentenyl,
10 cyclohexyl, cyclohexenyl, methylcyclohexyl, cycloheptyl, cycloheptenyl, norbornyl, norbornenyl, adamantyl and the like. For this disclosure, when a radical is listed, it indicates that radical type and all other radicals formed when that radical type is subjected to the substitutions defined above. Alkyl, alkenyl and alkynyl radicals listed include all isomers including where appropriate cyclic
15 isomers, for example, butyl includes *n*-butyl, 2-methylpropyl, 1-methylpropyl, *tert*-butyl, and cyclobutyl (and analogous substituted cyclopropyls); pentyl includes *n*-pentyl, cyclopentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1-ethylpropyl, and neopentyl (and analogous substituted cyclobutyls and cyclopropyls); butenyl includes E and Z forms of 1-butenyl, 2-butenyl, 3-butenyl,
20 1-methyl-1-propenyl, 1-methyl-2-propenyl, 2-methyl-1-propenyl and 2-methyl-2-propenyl (and cyclobutenyls and cyclopropenyls). Cyclic compound having substitutions include all isomer forms, for example, methylphenyl would include ortho-methylphenyl, meta-methylphenyl and para-methylphenyl; dimethylphenyl would include 2,3-dimethylphenyl, 2,4-dimethylphenyl, 2,5-dimethylphenyl, 2,6-
25 diphenylmethyl, 3,4-dimethylphenyl, and 3,5-dimethylphenyl. Examples of cyclopentadienyl and indenyl ligands are illustrated below as anionic ligands.

- 29 -



The ring numbering scheme is also



illustrated. Cyclopentadienyl

Indenyl

A similar numbering and nomenclature scheme is used for heteroindenyl as illustrated below where Z and Q independently represent the heteroatoms O, S, Se, or Te, or heteroatom groups, NR', PR', AsR', or SbR' where R' is hydrogen, or a hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, silylcarbyl, or germylcarbyl substituent. The number scheme shown below is for heteroindenyl ligands that are bridged to another ligand via a bridging group.



Examples include:


Cyclopenta[*b*]thienyl (Z=S)
Cyclopenta[*b*]furanlyl (Z=O)
Cyclopenta[*b*]selenophenyl (Z=Se)
Cyclopenta[*b*]tellurophenyl (Z=Te)
6-Methyl-cyclopenta[*b*]pyrrolyl (Z=N-Me)
6-Methyl-cyclopenta[*b*]phospholylyl (Z=P-Me)
6-Methyl-cyclopenta[*b*]arsolylyl (Z=As-Me)
6-Methyl-cyclopenta[*b*]stibolylyl (Z=Sb-Me)

Examples include:

Cyclopenta[*c*]thienyl (Z=S)
Cyclopenta[*c*]furanlyl (Z=O)
Cyclopenta[*c*]selenophenyl (Z=Se)
Cyclopenta[*c*]tellurophenyl (Z=Te)
5-Methyl-cyclopenta[*c*]pyrrolyl (Z=N-Me)
5-Methyl-cyclopenta[*c*]phospholylyl (Z=P-Me)
5-Methyl-cyclopenta[*c*]arsolylyl (Z=As-Me)
5-Methyl-cyclopenta[*c*]stibolylyl (Z=Sb-Me)

A similar numbering and nomenclature scheme is used for heterocyclopentadienyl rings as illustrated below where G and J independently represent the heteroatoms N, P, As, Sb or B. For these ligands when bridged to another ligand via a bridging group, the one position is usually chosen to be the ring carbon position where the ligand is bonded to the bridging group, hence a numbering scheme is not illustrated below.

- 30 -




Examples include:

Azacyclopentadiene (G = N)
 Phosphacyclopentadiene (G = P)
 Stibacyclopentadiene (G = Sb)
 Arsacyclopentadiene (G = As)
 Boracyclopentadiene (G = B)

Depending on the position of the bridging ligand, the numbering for the following ligands will change; 1,3 and 1,2 are only used in this case to illustrate the position of the heteroatoms relative to one another.

5



Examples include:

1,3-Diazacyclopentadiene (G = J = N)
 1,3-Diphosphacyclopentadiene (G = J = P)
 1,3-Distibacyclopentadiene (G = J = Sb)
 1,3-Diarsacyclopentadiene (G = J = As)
 1,3-Diboracyclopentadiene (G = J = B)
 1,3-Azaphosphacyclopentadiene (G = N; J = P)
 1,3-Azastibacyclopentadiene (G = N; J = Sb)
 1,3-Azarsacyclopentadiene (G = N; J = As)
 1,3-Azaboracyclopentadiene (G = N; J = B)
 1,3-Arsaphosphacyclopentadiene (G = As; J = P)
 1,3-Arsastibacyclopentadiene (G = As; J = Sb)
 1,3-Arsaboracyclopentadiene (G = As; J = B)
 1,3-Boraphosphacyclopentadiene (G = B; J = P)
 1,3-Borastibacyclopentadiene (G = B; J = Sb)
 1,3-Phosphastibacyclopentadiene (G = P; J = Sb)

Examples include:

1,2-Diazacyclopentadiene (G = J = N)
 1,2-Diphosphacyclopentadiene (G = J = P)
 1,2-Distibacyclopentadiene (G = J = Sb)
 1,2-Diarsacyclopentadiene (G = J = As)
 1,2-Diboracyclopentadiene (G = J = B)
 1,2-Azaphosphacyclopentadiene (G = N; J = P)
 1,2-Azastibacyclopentadiene (G = N; J = Sb)
 1,2-Azarsacyclopentadiene (G = N; J = As)
 1,2-Azaboracyclopentadiene (G = N; J = B)
 1,2-Arsaphosphacyclopentadiene (G = As; J = P)
 1,2-Arsastibacyclopentadiene (G = As; J = Sb)
 1,2-Arsaboracyclopentadiene (G = As; J = B)
 1,2-Boraphosphacyclopentadiene (G = B; J = P)
 1,2-Borastibacyclopentadiene (G = B; J = Sb)
 1,2-Phosphastibacyclopentadiene (G = P; J = Sb)

A "ring heteroatom" is a heteroatom that is within a cyclic ring structure.


A "heteroatom substituent" is heteroatom containing group that is directly bonded to a ring structure through the heteroatom. A "bridging heteroatom substituent" is

10 a heteroatom or heteroatom group that is directly bonded to two different ring

- 31 -

structures through the heteroatom. The terms "ring heteroatom", "heteroatom substituent", and "bridging heteroatom substituent" are illustrated below where Z and R' are as defined above. It should be noted that a "heteroatom substituent" can be a "bridging heteroatom substituent" when R' is additionally defined as the

5 ligand "A".



A "ring carbon atom" is a carbon atom that is part of a cyclic ring structure. By this definition, an indenyl ligand has nine ring carbon atoms; a cyclopentadienyl ligand has five ring carbon atoms.

10 Transition metal compounds have symmetry elements and belong to symmetry groups. These elements and groups are well established and can be referenced from Chemical Applications of Group Theory (2nd Edition) by F. Albert Cotton, Wiley-Interscience, 1971. Pseudo-symmetry, such as a pseudo C_2 -axis of symmetry refers to the same symmetry operation, however, the

15 substituents on the ligand frame do not need to be identical, but of similar size and steric bulk. Substituents of similar size are typically within 4 atoms of each other, and of similar shape. For example, methyl, ethyl, *n*-propyl, *n*-butyl and *iso*-butyl substituents (e.g. C1-C4 primary bonded substituents) would be considered of similar size and steric bulk. Likewise, *iso*-propyl, *sec*-butyl, 1-methylbutyl, 1-

20 ethylbutyl and 1-methylpentyl substituents (e.g. C3-C6 secondary bonded substituents) would be considered of similar size and steric bulk. *Tert*-butyl, 1,1-


- 32 -

dimethylpropyl, 1,1-dimethylbutyl, 1,1-dimethylpentyl and 1-ethyl-1-methylpropyl (e.g. C4-C7 tertiary bonded substituents) would be considered of similar size and steric bulk. Phenyl, tolyl, xylyl, and mesityl substituents (C6-C9 aryl substituents) would be considered of similar size and steric bulk.

5 Additionally, the bridging substituents of a compound with a pseudo C₂-axis of symmetry do not have to be similar at all since they are far removed from the active site of the catalyst. Therefore, a compound with a pseudo C₂-axis of symmetry could have for example, a Me₂Si, MeEtSi or MePhSi bridging ligand, and still be considered to have a pseudo C₂-axis of symmetry given the
10 appropriate remaining ligand structure. In some embodiments, metallocenes with a C₁-axis of symmetry may also be useful herein.

For purposes of this disclosure, the term oligomer refers to compositions having 2-75 mer units and the term polymer refers to compositions having 76 or more mer units. A mer is defined as a unit of an oligomer or polymer that
15 originally corresponded to the olefin(s) used in the oligomerization or polymerization reaction. For example, the mer of polydecene would be decene.

The metallocene compounds (pre-catalysts), useful herein are preferably cyclopentadienyl derivatives of titanium, zirconium and hafnium. In general, useful titanocenes, zirconocenes and hafnocenes may be represented by the
20 following formulae:



wherein:

M is the metal center, and is a Group 4 metal preferably titanium, zirconium or
25 hafnium, preferably zirconium or hafnium;

Cp and Cp* are the same or different cyclopentadienyl rings that are each bonded to M, and substituted with from zero to four substituent groups S'' for formula (1) and zero to five substituents for formula (2), each substituent group S'' being, independently, a radical group which is a hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, silylcarbyl or germlylcarbyl, or Cp and Cp* are
30 the same or different cyclopentadienyl rings in which any two adjacent S'' groups

- 33 -

are optionally joined to form a substituted or unsubstituted, saturated, partially unsaturated, or aromatic cyclic or polycyclic substituent; A' is a bridging group; X₁ and X₂ are, independently, hydride radicals, hydrocarbyl radicals, substituted hydrocarbyl radicals, halocarbyl radicals, substituted halocarbyl radicals, silylcarbyl radicals, substituted silylcarbyl radicals, germylcarbyl radicals, or substituted germylcarbyl radicals; or both X are joined and bound to the metal atom to form a metallacycle ring containing from about 3 to about 20 carbon atoms; or both together can be an olefin, diolefin or aryne ligand; or when Lewis-acid activators, such as methylalumoxane, which are capable of donating an X ligand as described above to the transition metal component are used, both X may, independently, be a halogen, alkoxide, aryloxy, amide, phosphide or other univalent anionic ligand or both X can also be joined to form a anionic chelating ligand.

In a preferred embodiment the metallocene is racemic which means in a preferred embodiment, that the compounds represented by formula (1) [(Cp-A'-Cp*)MX₁X₂] have no plane of symmetry containing the metal center, M; and have a C₂-axis of symmetry or pseudo C₂-axis of symmetry through the metal center. Preferably in the racemic metallocenes represented by formula (1) A' is selected from R'₂C, R'₂Si, R'₂Ge, R'₂CCR'₂, R'₂CCR'₂CR'₂, R'₂CCR'₂CR'₂CR'₂, R'C=CR', R'C=CR'CR'₂, R'₂CCR'=CR'CR'₂, R'C=CR'CR'=CR', R'C=CR'CR'₂CR'₂, R'₂CSiR'₂, R'₂SiSiR'₂, R'₂CSiR'₂CR'₂, R'₂SiCR'₂SiR'₂, R'C=CR'SiR'₂, R'₂CGeR'₂, R'₂GeGeR'₂, R'₂CGeR'₂CR'₂, R'₂GeCR'₂GeR'₂, R'₂SiGeR'₂, R'C=CR'GeR'₂, R'B, R'₂C-BR', R'₂C-BR'-CR'₂, R'N, R'P, O, S, Se, R'₂C-O-CR'₂, R'₂CR'₂C-O-CR'₂CR'₂, R'₂C-O-CR'₂CR'₂, R'₂C-O-CR'=CR', R'₂C-S-CR'₂, R'₂CR'₂C-S-CR'₂CR'₂, R'₂C-S-CR'₂CR'₂, R'₂C-S-CR'=CR', R'₂C-Se-CR'₂, R'₂CR'₂C-Se-CR'₂CR'₂, R'₂C-Se-CR'₂CR'₂, R'₂C-Se-CR'=CR', R'₂C-N=CR', R'₂C-NR'-CR'₂, R'₂C-NR'-CR'₂CR'₂, R'₂C-NR'-CR'=CR', R'₂CR'₂C-NR'-CR'₂CR'₂, R'₂C-P=CR', and R'₂C-PR'-CR'₂ where when Cp is different than Cp* then R' is a C1-C5 containing hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, silylcarbyl or germylcarbyl substituent, and when Cp is the same as Cp* then R' is selected from hydrogen, C1-C20 containing hydrocarbyl, substituted hydrocarbyl, halocarbyl,

- 34 -

substituted halocarbyl, silylcarbyl or germylcarbyl substituent and optionally two or more adjacent R' may join to form a substituted or unsubstituted, saturated, partially unsaturated, cyclic or polycyclic substituent.

5 Table A depicts representative constituent moieties for the metallocene components of formula 1 and 2. The list is for illustrative purposes only and should not be construed to be limiting in any way. A number of final components may be formed by permuting all possible combinations of the constituent moieties with each other. When hydrocarbyl radicals including alkyl, alkenyl, alkynyl,
10 cycloalkyl, cycloalkenyl, cycloalkynyl and aromatic radicals are disclosed in this application the term includes all isomers. For example, butyl includes n-butyl, 2-methylpropyl, 1-methylpropyl, tert-butyl, and cyclobutyl; pentyl includes n-pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1-ethylpropyl, neopentyl, cyclopentyl and methylcyclobutyl; butenyl includes E and Z forms of 1-butenyl,
15 2-butenyl, 3-butenyl, 1-methyl-1-propenyl, 1-methyl-2-propenyl, 2-methyl-1-propenyl and 2-methyl-2-propenyl. This includes when a radical is bonded to another group, for example, propylcyclopentadienyl include n-propylcyclopentadienyl, isopropylcyclopentadienyl and cyclopropylcyclopentadienyl. In general, the ligands or groups illustrated in Table
20 A include all isomeric forms. For example, dimethylcyclopentadienyl includes 1,2-dimethylcyclopentadienyl and 1,3-dimethylcyclopentadienyl; methylindenyl includes 1-methylindenyl, 2-methylindenyl, 3-methylindenyl, 4-methylindenyl, 5-methylindenyl, 6-methylindenyl and 7-methylindenyl; methylethylphenyl includes ortho-methylethylphenyl, meta-methylethylphenyl and para-methylethylphenyl.
25 Examples of specific invention catalyst precursors take the following formula where some components are listed in Table A. To illustrate members of the transition metal component, select any combination of the species listed in Tables A. For nomenclature purposes, for the bridging group, A', the words "silyl" and "silylene" are used interchangeably, and represent a diradical species. For the
30 bridging group A', "ethylene" refers to a 1,2-ethylene linkage and is distinguished from ethene-1,1-diyl. Thus, for the bridging group A', "ethylene" and "1,2-ethylene" are used interchangeably. For compounds having a bridging group, A',

- 35 -

the bridge position on the cyclopentadienyl-type ring is always considered the 1-position. The numbering scheme previous defined for the indenyl ring is used to indicate the bridge position; if a number is not specified, it is assumed that the bridge to the indenyl ligand is in the one position.

5

TABLE A -

<u>A'</u>	Cp, Cp*
dimethylsilylene	cyclopentadienyl
diethylsilylene	methylcyclopentadienyl
dipropylsilylene	dimethylcyclopentadienyl
dibutylsilylene	trimethylcyclopentadienyl
dipentylsilylene	tetramethylcyclopentadienyl
dihexylsilylene	ethylcyclopentadienyl
diheptylsilylene	diethylcyclopentadienyl
dioctylsilylene	propylcyclopentadienyl
dinonylsilylene	dipropylcyclopentadienyl
didecylsilylene	butylcyclopentadienyl
diundecylsilylene	dibutylcyclopentadienyl
didodecylsilylene	pentylcyclopentadienyl
ditridecylsilylene	dipentylcyclopentadienyl
ditetradecylsilylene	hexylcyclopentadienyl
dipentadecylsilylene	dihexylcyclopentadienyl
dihexadecylsilylene	heptylcyclopentadienyl
diheptadecylsilylene	diheptylcyclopentadienyl
dioctadecylsilylene	octylcyclopentadienyl
dinonadecylsilylene	dioctylcyclopentadienyl
dieicosylsilylene	nonylcyclopentadienyl
diheneicosylsilylene	dinonylcyclopentadienyl
didocosylsilylene	decylcyclopentadienyl
ditricosylsilylene	didecylcyclopentadienyl
ditetracosylsilylene	undecylcyclopentadienyl
dipentacosylsilylene	dodecylcyclopentadienyl
dihexacosylsilylene	tridecylcyclopentadienyl
diheptacosylsilylene	tetradecylcyclopentadienyl
dioctacosylsilylene	pentadecylcyclopentadienyl
dinonacosylsilylene	hexadecylcyclopentadienyl
ditriacontylsilylene	heptadecylcyclopentadienyl
dicyclohexylsilylene	octadecylcyclopentadienyl
dicyclopentylsilylene	nonadecylcyclopentadienyl

- 36 -

dicycloheptylsilylene	eicosylcyclopentadienyl
dicyclooctylsilylene	heneicosylcyclopentadienyl
dicyclodecylsilylene	docosylcyclopentadienyl
dicyclododecylsilylene	tricosylcyclopentadienyl
dinapthylsilylene	tetracosylcyclopentadienyl
diphenylsilylene	pentacosylcyclopentadienyl
ditolylsilylene	hexacosylcyclopentadienyl
dibenzylsilylene	heptacosylcyclopentadienyl
diphenethylsilylene	octacosylcyclopentadienyl
di(butylphenethyl)silylene	nonacosylcyclopentadienyl
methylethylsilylene	triacontylcyclopentadienyl
methylpropylsilylene	cyclohexylcyclopentadienyl
methylbutylsilylene	phenylcyclopentadienyl
methylhexylsilylene	diphenylcyclopentadienyl
methylphenylsilylene	triphenylcyclopentadienyl
ethylphenylsilylene	tetraphenylcyclopentadienyl
ethylpropylsilylene	tolylcyclopentadienyl
ethylbutylsilylene	benzylcyclopentadienyl
propylphenylsilylene	phenethylcyclopentadienyl
dimethylgermylene	cyclohexylmethylcyclopentadienyl
diethylgermylene	napthylcyclopentadienyl
diphenylgermylene	methylphenylcyclopentadienyl
methylphenylgermylene	methyltolylcyclopentadienyl
cyclotetramethylenesilylene	methylethylcyclopentadienyl
cyclopentamethylenesilylene	methylpropylcyclopentadienyl
cyclotrimethylenesilylene	methylbutylcyclopentadienyl
cyclohexylazanediyl	methylpentylcyclopentadienyl
butylazanediyl	methylhexylcyclopentadienyl
methylazanediyl	methylheptylcyclopentadienyl
phenylazanediyl	methyloctylcyclopentadienyl
perfluorophenylazanediyl	methylnonylcyclopentadienyl
methylphosphanediyl	methyldecylcyclopentadienyl
ethylphosphanediyl	vinylcyclopentadienyl
propylphosphanediyl	propenylcyclopentadienyl
butylphosphanediyl	butenylcyclopentadienyl
cyclohexylphosphanediyl	indenyl
phenylphosphanediyl	methyindenyl
methylboranediyl	dimethyindenyl
phenylboranediyl	trimethyindenyl
methylene	tetramethyindenyl
dimethylmethylene	pentamethyindenyl

- 37 -

diethylmethylene	methylpropylindenyl
dibutylmethylene	dimethylpropylindenyl
dipropylmethylene	methyldipropylindenyl
diphenylmethylene	methylethylindenyl
ditolylmethylene	methylbutylindenyl
di(butylphenyl)methylene	ethylindenyl
di(trimethylsilylphenyl)methylene	propylindenyl
di(triethylsilylphenyl)methylene	butylindenyl
dibenzylmethylene	pentylindenyl
cyclotetramethylenemethylene	hexylindenyl
cyclopentamethylenemethylene	heptylindenyl
ethylene	octylindenyl
methylethylene	nonylindenyl
dimethylethylene	decylindenyl
trimethylethylene	phenylindenyl
tetramethylethylene	(fluorophenyl)indenyl
cyclopentylene	(methylphenyl)indenyl
cyclohexylene	biphenylindenyl
cycloheptylene	(bis(trifluoromethyl)phenyl)indenyl
cyclooctylene	napthylindenyl
propanediyl	phenanthrylindenyl
methylpropanediyl	benzylindenyl
dimethylpropanediyl	benzindenyl
trimethylpropanediyl	cyclohexylindenyl
tetramethylpropanediyl	methylphenylindenyl
pentamethylpropanediyl	ethylphenylindenyl
hexamethylpropanediyl	propylphenylindenyl
tetramethyldisiloxylene	methylnapthylindenyl
vinylene	ethylnapthylindenyl
ethene-1,1-diyl	propylnapthylindenyl
divinylsilylene	(methylphenyl)indenyl
dipropenylsilylene	(dimethylphenyl)indenyl
dibutenylsilylene	(ethylphenyl)indenyl
methylvinylsilylene	(diethylphenyl)indenyl
methylpropenylsilylene	(propylphenyl)indenyl
methylbutenylsilylene	(dipropylphenyl)indenyl
dimethylsilylmethylene	methyltetrahydroindenyl
diphenylsilylmethylene	ethyltetrahydroindenyl
dimethylsilylethylene	propyltetrahydroindenyl
diphenylsilylethylene	butyltetrahydroindenyl
dimethylsilylpropylene	phenyltetrahydroindenyl

- 38 -

diphenylsilylpropylene	(diphenylmethyl)cyclopentadienyl
dimethylstannylene	trimethylsilylcyclopentadienyl
diphenylstannylene	triethylsilylcyclopentadienyl
	trimethylgermylcyclopentadienyl
	trifluoromethylcyclopentadienyl
X₁ or X₂	cyclopenta[<i>b</i>]thienyl
chloride	cyclopenta[<i>b</i>]furanyl
bromide	cyclopenta[<i>b</i>]selenophenyl
iodide	cyclopenta[<i>b</i>]tellurophenyl
fluoride	cyclopenta[<i>b</i>]pyrrolyl
hydride	cyclopenta[<i>b</i>]phospholyl
methyl	cyclopenta[<i>b</i>]arsolyl
ethyl	cyclopenta[<i>b</i>]stibolyl
propyl	methylcyclopenta[<i>b</i>]thienyl
butyl	methylcyclopenta[<i>b</i>]furanyl
pentyl	methylcyclopenta[<i>b</i>]selenophenyl
hexyl	methylcyclopenta[<i>b</i>]tellurophenyl
heptyl	methylcyclopenta[<i>b</i>]pyrrolyl
octyl	methylcyclopenta[<i>b</i>]phospholyl
nonyl	methylcyclopenta[<i>b</i>]arsolyl
decyl	methylcyclopenta[<i>b</i>]stibolyl
undecyl	dimethylcyclopenta[<i>b</i>]thienyl
dodecyl	dimethylcyclopenta[<i>b</i>]furanyl
tridecyl	dimethylcyclopenta[<i>b</i>]pyrrolyl
tetradecyl	dimethylcyclopenta[<i>b</i>]phospholyl
pentadecyl	trimethylcyclopenta[<i>b</i>]thienyl
hexadecyl	trimethylcyclopenta[<i>b</i>]furanyl
heptadecyl	trimethylcyclopenta[<i>b</i>]pyrrolyl
octadecyl	trimethylcyclopenta[<i>b</i>]phospholyl
nonadecyl	ethylcyclopenta[<i>b</i>]thienyl
eicosyl	ethylcyclopenta[<i>b</i>]furanyl
heneicosyl	ethylcyclopenta[<i>b</i>]pyrrolyl
docosyl	ethylcyclopenta[<i>b</i>]phospholyl
tricosyl	diethylcyclopenta[<i>b</i>]thienyl
tetracosyl	diethylcyclopenta[<i>b</i>]furanyl
pentacosyl	diethylcyclopenta[<i>b</i>]pyrrolyl
hexacosyl	diethylcyclopenta[<i>b</i>]phospholyl
heptacosyl	triethylcyclopenta[<i>b</i>]thienyl
octacosyl	triethylcyclopenta[<i>b</i>]furanyl
nonacosyl	triethylcyclopenta[<i>b</i>]pyrrolyl
triacontyl	triethylcyclopenta[<i>b</i>]phospholyl

- 39 -

phenyl	propylcyclopenta[<i>b</i>]thienyl
benzyl	propylcyclopenta[<i>b</i>]furanyl
phenethyl	propylcyclopenta[<i>b</i>]pyrrolyl
tolyl	propylcyclopenta[<i>b</i>]phospholyl
methoxy	dipropylcyclopenta[<i>b</i>]thienyl
ethoxy	dipropylcyclopenta[<i>b</i>]furanyl
propoxy	dipropylcyclopenta[<i>b</i>]pyrrolyl
butoxy	dipropylcyclopenta[<i>b</i>]phospholyl
dimethylamido	tripropylcyclopenta[<i>b</i>]thienyl
diethylamido	tripropylcyclopenta[<i>b</i>]furanyl
methylethylamido	tripropylcyclopenta[<i>b</i>]pyrrolyl
phenoxy	tripropylcyclopenta[<i>b</i>]phospholyl
benzoxyl	butylcyclopenta[<i>b</i>]thienyl
allyl	butylcyclopenta[<i>b</i>]furanyl
	butylcyclopenta[<i>b</i>]pyrrolyl
	butylcyclopenta[<i>b</i>]phospholyl
X₁ and X₂ together	dibutylcyclopenta[<i>b</i>]thienyl
methylidene	dibutylcyclopenta[<i>b</i>]furanyl
ethylidene	dibutylcyclopenta[<i>b</i>]pyrrolyl
propylidene	dibutylcyclopenta[<i>b</i>]phospholyl
tetramethylene	tributylcyclopenta[<i>b</i>]thienyl
pentamethylene	tributylcyclopenta[<i>b</i>]furanyl
hexamethylene	tributylcyclopenta[<i>b</i>]pyrrolyl
ethylenedihydroxy	tributylcyclopenta[<i>b</i>]phospholyl
butadiene	ethylmethylcyclopenta[<i>b</i>]thienyl
methylbutadiene	ethylmethylcyclopenta[<i>b</i>]furanyl
dimethylbutadiene	ethylmethylcyclopenta[<i>b</i>]pyrrolyl
pentadiene	ethylmethylcyclopenta[<i>b</i>]phospholyl
methylpentadiene	methylpropylcyclopenta[<i>b</i>]thienyl
dimethylpentadiene	methylpropylcyclopenta[<i>b</i>]furanyl
hexadiene	methylpropylcyclopenta[<i>b</i>]pyrrolyl
methylhexadiene	methylpropylcyclopenta[<i>b</i>]phospholyl
dimethylhexadiene	butylmethylcyclopenta[<i>b</i>]thienyl
	butylmethylcyclopenta[<i>b</i>]furanyl
	butylmethylcyclopenta[<i>b</i>]pyrrolyl
<u>M</u>	butylmethylcyclopenta[<i>b</i>]phospholyl
titanium	cyclopenta[<i>c</i>]thienyl
zirconium	cyclopenta[<i>c</i>]furanyl
hafnium	cyclopenta[<i>c</i>]selenophenyl
	cyclopenta[<i>c</i>]tellurophenyl
	cyclopenta[<i>c</i>]pyrrolyl

- 40 -

	cyclopenta[c]phospholyl
	cyclopenta[c]arsolyl
	cyclopenta[c]stibolyl
	methylcyclopenta[c]thienyl
	methylcyclopenta[c]furanyl
	methylcyclopenta[c]selenophenyl
	methylcyclopenta[c]tellurophenyl
	methylcyclopenta[c]pyrrolyl
	methylcyclopenta[c]phospholyl
	methylcyclopenta[c]arsolyl
	methylcyclopenta[c]stibolyl
	dimethylcyclopenta[c]thienyl
	dimethylcyclopenta[c]furanyl
	dimethylcyclopenta[c]pyrrolyl
	dimethylcyclopenta[c]phospholyl
	trimethylcyclopenta[c]thienyl
	trimethylcyclopenta[c]furanyl
	trimethylcyclopenta[c]pyrrolyl
	trimethylcyclopenta[c]phospholyl
	ethylcyclopenta[c]thienyl
	ethylcyclopenta[c]furanyl
	ethylcyclopenta[c]pyrrolyl
	ethylcyclopenta[c]phospholyl
	diethylcyclopenta[c]thienyl
	diethylcyclopenta[c]furanyl
	diethylcyclopenta[c]pyrrolyl
	diethylcyclopenta[c]phospholyl
	triethylcyclopenta[c]thienyl
	triethylcyclopenta[c]furanyl
	triethylcyclopenta[c]pyrrolyl
	triethylcyclopenta[c]phospholyl
	propylcyclopenta[c]thienyl
	propylcyclopenta[c]furanyl
	propylcyclopenta[c]pyrrolyl
	propylcyclopenta[c]phospholyl
	dipropylcyclopenta[c]thienyl
	dipropylcyclopenta[c]furanyl
	dipropylcyclopenta[c]pyrrolyl
	dipropylcyclopenta[c]phospholyl
	tripropylcyclopenta[c]thienyl
	tripropylcyclopenta[c]furanyl

- 41 -

	tripropylcyclopenta[c]pyrrolyl
	tripropylcyclopenta[c]phospholyl
	butylcyclopenta[c]thienyl
	butylcyclopenta[c]furanyl
	butylcyclopenta[c]pyrrolyl
	butylcyclopenta[c]phospholyl
	dibutylcyclopenta[c]thienyl
	dibutylcyclopenta[c]furanyl
	dibutylcyclopenta[c]pyrrolyl
	dibutylcyclopenta[c]phospholyl
	tributylcyclopenta[c]thienyl
	tributylcyclopenta[c]furanyl
	tributylcyclopenta[c]pyrrolyl
	tributylcyclopenta[c]phospholyl
	ethylmethylcyclopenta[c]thienyl
	ethylmethylcyclopenta[c]furanyl
	ethylmethylcyclopenta[c]pyrrolyl
	ethylmethylcyclopenta[c]phospholyl
	methylpropylcyclopenta[c]thienyl
	methylpropylcyclopenta[c]furanyl
	methylpropylcyclopenta[c]pyrrolyl
	methylpropylcyclopenta[c]phospholyl
	butylmethylcyclopenta[c]thienyl
	butylmethylcyclopenta[c]furanyl
	butylmethylcyclopenta[c]pyrrolyl
	butylmethylcyclopenta[c]phospholyl
	pentamethylcyclopentadienyl
	tetrahydroindenyl
	mehtyltetrahydroindenyl
	dimethyltetrahydroindenyl

In a preferred embodiment of the invention, Cp is the same as Cp* and is a substituted or unsubstituted indenyl or tetrahydroindenyl ligand. Most preferred substituted indenyl or tetrahydroindenyl ligands do not have a substituent in the 2-
5 position of the indenyl or tetrahydroindenyl ring. Most preferred substituted and unsubstituted indenyl or tetrahydroindenyl ligands include indenyl, tetrahydroindenyl, 4,7-dimethylindenyl and 5,6-dimethylindenyl.

- 42 -

In another embodiment, the metallocene catalyst compound used herein is not $\text{rac-CH}_2\text{CH}_2(\text{Ind})_2\text{ZrCl}_2$ and or $\text{rac-Me}_2\text{Si}(2\text{-Me-Ind})_2\text{ZrCl}_2$. In another embodiment, the metallocene catalyst compound used herein is not $\text{rac-CH}_2\text{CH}_2(\text{Ind})_2\text{ZrCl}_2$ and or $\text{rac-Me}_2\text{Si}(2\text{-Me-Ind})_2\text{ZrCl}_2$ and the activator is not methylalumoxane, where Me is methyl and Ind is indenyl.

In a preferred embodiment of the invention, when the metallocene is used with an alumoxane, Cp is the same as Cp^* and is a substituted or unsubstituted indenyl or tetrahydroindenyl ligand. Most preferred substituted indenyl or tetrahydroindenyl ligands do not have a substituent in the 2-position of the indenyl or tetrahydroindenyl ring. Most preferred substituted and unsubstituted indenyl or tetrahydroindenyl ligands include indenyl, tetrahydroindenyl, 4,7-dimethylindenyl and 5,6-dimethylindenyl.

In another embodiment, when the metallocene is used with an alumoxane, then the metallocene catalyst compound used herein is not $\text{rac-CH}_2\text{CH}_2(\text{Ind})_2\text{ZrCl}_2$ and or $\text{rac-Me}_2\text{Si}(2\text{-Me-Ind})_2\text{ZrCl}_2$. In another embodiment, the metallocene catalyst compound used herein is not $\text{rac-CH}_2\text{CH}_2(\text{Ind})_2\text{ZrCl}_2$ and or $\text{rac-Me}_2\text{Si}(2\text{-Me-Ind})_2\text{ZrCl}_2$ and the activator is not methylalumoxane, where Me is methyl and Ind is indenyl.

In a preferred embodiment of the invention, when used with an NCA, Cp is the same as Cp^* and is a substituted or unsubstituted indenyl or tetrahydroindenyl ligand. Most preferred substituted and unsubstituted indenyl or tetrahydroindenyl ligands include having a substituent in the 2-position of the indenyl or tetrahydroindenyl ring, indenyl, tetrahydroindenyl, 4,7-dimethylindenyl and 5,6-dimethylindenyl.

In another embodiment, when used with NCA, the metallocene catalyst compound used herein is bridged, substituted or unsubstituted metallocenes of general structure as shown in formula (1) or (2)

In another embodiment, the catalyst used herein is $\text{Y}_2\text{methylidene}(\text{R}_n\text{Cp})(\text{R}_m\text{Flu})\text{ZrX}_2$ or $\text{Y}_2\text{silyl}(\text{R}_n\text{Cp})(\text{R}_m\text{Flu})\text{ZrX}_2$ where Y is independently a C1 to C20 alkyl or a substituted or unsubstituted phenyl group, X is a halogen, a substituted or unsubstituted phenyl group, or a C1 to C20 alkyl, Cp

- 43 -

is a cyclopentadienyl ring, R is a C1 to C20 alkyl group, n is a number denoting the degree of substitution of Cp and is a number from 0 to 5, Flu is a fluorenyl ring, m is a number denoting the degree of substitution of Flu and is a number from 0 to 9.

- 5 Preferred metallocene compounds (pre-catalysts) which, according to the present invention, provide catalyst systems which are specific to the production of poly- α -olefins having mm triads over 40 % include the racemic versions of:
- dimethylsilylbis(indenyl) zirconium dichloride, dimethylsilylbis(indenyl) zirconium dimethyl, diphenylsilylbis(indenyl) zirconium dichloride,
- 10 diphenylsilylbis(indenyl) zirconium dimethyl, methylphenylsilylbis(indenyl) zirconium dichloride,
- methylphenylsilylbis(indenyl) zirconium dimethyl, ethylenebis(indenyl) zirconium dichloride, ethylenebis(indenyl) zirconium dimethyl,
- 15 methylenebis(indenyl) zirconium dichloride, methylenebis(indenyl) zirconium dimethyl, dimethylsilylbis(indenyl) hafnium dichloride, dimethylsilylbis(indenyl) hafnium dimethyl, diphenylsilylbis(indenyl) hafnium dichloride,
- diphenylsilylbis(indenyl) hafnium dimethyl, methylphenylsilylbis(indenyl) hafnium dichloride, methylphenylsilylbis(indenyl) hafnium dimethyl,
- 20 ethylenebis(indenyl) hafnium dichloride, ethylenebis(indenyl) hafnium dimethyl, methylenebis(indenyl) hafnium dichloride, methylenebis(indenyl) hafnium dimethyl, dimethylsilylbis(tetrahydroindenyl) zirconium dichloride,
- dimethylsilylbis(tetrahydroindenyl) zirconium dimethyl, diphenylsilylbis(tetrahydroindenyl) zirconium dichloride,
- diphenylsilylbis(tetrahydroindenyl) zirconium dimethyl,
- 25 methylphenylsilylbis(tetrahydroindenyl) zirconium dichloride, methylphenylsilylbis(tetrahydroindenyl) zirconium dimethyl, ethylenebis(tetrahydroindenyl) zirconium dichloride,
- ethylenebis(tetrahydroindenyl) zirconium dimethyl, methylenebis(tetrahydroindenyl) zirconium dichloride,
- 30 methylenebis(tetrahydroindenyl) zirconium dimethyl, dimethylsilylbis(tetrahydroindenyl) hafnium dichloride, dimethylsilylbis(tetrahydroindenyl) hafnium dimethyl,

- 44 -

diphenylsilylbis(tetrahydroindenyl) hafnium dichloride,
diphenylsilylbis(tetrahydroindenyl) hafnium dimethyl,
methylphenylsilylbis(tetrahydroindenyl) hafnium dichloride,
methylphenylsilylbis(tetrahydroindenyl) hafnium dimethyl,
5 ethylenebis(tetrahydroindenyl) hafnium dichloride, ethylenebis(tetrahydroindenyl)
hafnium dimethyl, methylenebis(tetrahydroindenyl) hafnium dichloride,
methylenebis(tetrahydroindenyl) hafnium dimethyl, dimethylsilylbis(4,7-
dimethylindenyl) zirconium dichloride, dimethylsilylbis(4,7-dimethylindenyl)
zirconium dimethyl, diphenylsilylbis(4,7-dimethylindenyl) zirconium dichloride,
10 diphenylsilylbis(4,7-dimethylindenyl) zirconium dimethyl,
methylphenylsilylbis(4,7-dimethylindenyl) zirconium dichloride,
methylphenylsilylbis(4,7-dimethylindenyl) zirconium dimethyl, ethylenebis(4,7-
dimethylindenyl) zirconium dichloride, ethylenebis(4,7-dimethylindenyl)
zirconium dimethyl, methylenebis(4,7-dimethylindenyl) zirconium dichloride,
15 methylenebis(4,7-dimethylindenyl) zirconium dimethyl, dimethylsilylbis(4,7-
dimethylindenyl) hafnium dichloride, dimethylsilylbis(4,7-dimethylindenyl)
hafnium dimethyl, diphenylsilylbis(4,7-dimethylindenyl) hafnium dichloride,
diphenylsilylbis(4,7-dimethylindenyl) hafnium dimethyl,
methylphenylsilylbis(4,7-dimethylindenyl) hafnium dichloride,
20 methylphenylsilylbis(4,7-dimethylindenyl) hafnium dimethyl, ethylenebis(4,7-
dimethylindenyl) hafnium dichloride, ethylenebis(4,7-dimethylindenyl) hafnium
dimethyl, methylenebis(4,7-dimethylindenyl) hafnium dichloride,
methylenebis(4,7-dimethylindenyl) hafnium dimethyl, dimethylsilylbis(2-methyl-4-
naphthylindenyl) zirconium dichloride, dimethylsilylbis(2-methyl-4-
25 naphthylindenyl) zirconium dimethyl, diphenylsilylbis(2-methyl-4-naphthylindenyl)
zirconium dichloride, dimethylsilylbis(2,3-dimethylcyclopentadienyl) zirconium
dichloride, dimethylsilylbis(2,3-dimethylcyclopentadienyl) zirconium dimethyl,
diphenylsilylbis(2,3-dimethylcyclopentadienyl) zirconium dichloride,
diphenylsilylbis(2,3-dimethylcyclopentadienyl) zirconium dimethyl,
30 methylphenylsilylbis(2,3-dimethylcyclopentadienyl) zirconium dichloride,
methylphenylsilylbis(2,3-dimethylcyclopentadienyl) zirconium dimethyl,
ethylenebis(2,3-dimethylcyclopentadienyl) zirconium dichloride, ethylenebis(2,3-

- 45 -

- dimethylcyclopentadienyl) zirconium dimethyl, methylenebis(2,3-dimethylcyclopentadienyl) zirconium dichloride, methylenebis(2,3-dimethylcyclopentadienyl) zirconium dimethyl, dimethylsilylbis(2,3-dimethylcyclopentadienyl) hafnium dichloride, dimethylsilylbis(2,3-
- 5 dimethylcyclopentadienyl) hafnium dimethyl, diphenylsilylbis(2,3-dimethylcyclopentadienyl) hafnium dichloride, diphenylsilylbis(2,3-dimethylcyclopentadienyl) hafnium dimethyl, methylphenylsilylbis(2,3-dimethylcyclopentadienyl) hafnium dichloride, methylphenylsilylbis(2,3-
- 10 dimethylcyclopentadienyl) hafnium dimethyl, ethylenebis(2,3-dimethylcyclopentadienyl) hafnium dichloride, ethylenebis(2,3-dimethylcyclopentadienyl) hafnium dimethyl, methylenebis(2,3-dimethylcyclopentadienyl) hafnium dichloride, methylenebis(2,3-
- 15 dimethylcyclopentadienyl) hafnium dimethyl, dimethylsilylbis(3-trimethylsilylcyclopentadienyl) zirconium dichloride, dimethylsilylbis(3-trimethylsilylcyclopentadienyl) zirconium dimethyl, diphenylsilylbis(3-trimethylsilylcyclopentadienyl) zirconium dichloride, diphenylsilylbis(3-
- 20 trimethylsilylcyclopentadienyl) zirconium dimethyl, methylphenylsilylbis(3-trimethylsilylcyclopentadienyl) zirconium dichloride, methylphenylsilylbis(3-trimethylsilylcyclopentadienyl) zirconium dimethyl, ethylenebis(3-trimethylsilylcyclopentadienyl) zirconium dichloride, ethylenebis(3-
- 25 trimethylsilylcyclopentadienyl) zirconium dimethyl, methylenebis(3-trimethylsilylcyclopentadienyl) zirconium dichloride, methylenebis(3-trimethylsilylcyclopentadienyl) zirconium dimethyl, dimethylsilylbis(3-trimethylsilylcyclopentadienyl) hafnium dichloride, dimethylsilylbis(3-
- 30 trimethylsilylcyclopentadienyl) hafnium dimethyl, diphenylsilylbis(3-trimethylsilylcyclopentadienyl) hafnium dichloride, diphenylsilylbis(3-trimethylsilylcyclopentadienyl) hafnium dimethyl, methylphenylsilylbis(3-trimethylsilylcyclopentadienyl) hafnium dichloride, methylphenylsilylbis(3-
- trimethylsilylcyclopentadienyl) hafnium dimethyl, ethylenebis(3-trimethylsilylcyclopentadienyl) hafnium dichloride, ethylenebis(3-trimethylsilylcyclopentadienyl) hafnium dimethyl, methylenebis(3-

- 46 -

trimethylsilylcyclopentadienyl) hafnium dichloride, methylenebis(3-trimethylsilylcyclopentadienyl) hafnium dimethyl,

Particularly preferred species are the racemic versions of:

dimethylsilylbis(indenyl) zirconium dichloride, dimethylsilylbis(indenyl)
 5 zirconium dimethyl, ethylenebis(indenyl) zirconium dichloride,
 ethylenebis(indenyl) zirconium dimethyl, dimethylsilylbis(tetrahydroindenyl)
 zirconium dichloride, dimethylsilylbis(tetrahydroindenyl) zirconium dimethyl,
 ethylenebis(tetrahydroindenyl) zirconium dichloride,
 ethylenebis(tetrahydroindenyl) zirconium dimethyl, dimethylsilylbis(4,7-
 10 dimethylindenyl) zirconium dichloride, dimethylsilylbis(4,7-dimethylindenyl)
 zirconium dimethyl, ethylenebis(4,7-dimethylindenyl) zirconium dichloride,
 ethylenebis(4,7-dimethylindenyl) zirconium dimethyl, dimethylsilylbis(indenyl)
 hafnium dichloride, dimethylsilylbis(indenyl) hafnium dimethyl,
 ethylenebis(indenyl) hafnium dichloride, ethylenebis(indenyl) hafnium dimethyl,
 15 dimethylsilylbis(tetrahydroindenyl) hafnium dichloride,
 dimethylsilylbis(tetrahydroindenyl) hafnium dimethyl,
 ethylenebis(tetrahydroindenyl) hafnium dichloride, ethylenebis(tetrahydroindenyl)
 hafnium dimethyl, dimethylsilylbis(4,7-dimethylindenyl) hafnium dichloride,
 dimethylsilylbis(4,7-dimethylindenyl) hafnium dimethyl, ethylenebis(4,7-
 20 dimethylindenyl) hafnium dichloride, and ethylenebis(4,7-dimethylindenyl)
 hafnium dimethyl.

Preferred catalyst compounds also include bis(1,3-dimethylcyclopentadienyl)zirconium dichloride and
 bis(tetramethylcyclopentadienyl)zirconium dichloride

25

Activators and Catalyst Activation

The catalyst precursors, when activated by a commonly known activator such as methylalumoxane, form active catalysts for the polymerization or oligomerization of olefins. Activators that may be used include alumoxanes such
 30 as methylalumoxane, modified methylalumoxane, ethylalumoxane, *iso*-butylalumoxane and the like; Lewis acid activators include triphenylboron, tris-perfluorophenylboron, tris-perfluorophenylaluminum and the like; ionic activators

- 47 -

include dimethylanilinium tetrakis(perfluorophenyl)borate, triphenylcarboniumtetrakis(perfluorophenyl)borate, dimethylaniliniumtetrakis(perfluorophenyl)aluminate, and the like.

A co-activator is a compound capable of alkylating the transition metal complex, such that when used in combination with an activator, an active catalyst is formed. Co-activators include alumoxanes such as methylalumoxane, modified alumoxanes such as modified methylalumoxane, and aluminum alkyls such as trimethylaluminum, tri-isobutylaluminum, triethylaluminum, and tri-isopropylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, tri-n-decylaluminum or tri-n-dodecylaluminum. Co-activators are typically used in combination with Lewis acid activators and ionic activators when the pre-catalyst is not a dihydrocarbyl or dihydride complex. Sometimes co-activators are also used as scavengers to deactivate impurities in feed or reactors.

Particularly preferred co-activators include alkylaluminum compound is represented by the formula: R_3Al , where each R is, independently, a C1 to C18 alkyl group, preferably each R is, independently, selected from the group consisting of methyl, ethyl, n-propyl, iso-propyl, iso-butyl, n-butyl, t-butyl, n-pentyl, iso-pentyl, neopentyl, n-hexyl, iso-hexyl, n-heptyl, iso-heptyl, n-octyl, iso-octyl, n-nonyl, n-decyl, n-undecyl, n-dodecyl, n-tridecyl, n-tetradecyl, n-pentadecyl, n-hexadecyl, n-heptadecyl, n-octadecyl, and their iso-analogs.

The alumoxane component useful as an activator typically is preferably an oligomeric aluminum compound represented by the general formula $(R^x-Al-O)_n$, which is a cyclic compound, or $R^x(R^x-Al-O)_nAlR^x_2$, which is a linear compound. It is believed that the most common alumoxanes are a mixture of the cyclic and linear compounds. In the general alumoxane formula, R^x is independently a C₁-C₂₀ alkyl radical, for example, methyl, ethyl, propyl, butyl, pentyl, isomers thereof, and the like, and "n" is an integer from 1-50. Most preferably, R^x is methyl and "n" is at least 4. Methylalumoxane and modified methylalumoxanes are most preferred. For further descriptions see, EP 0 279 586, EP 0 594 218, EP 0 561 476, WO94/10180 and US Pat. Nos. 4,665,208, 4,874,734, 4,908,463, 4,924,018, 4,952,540, 4,968,827, 5,041,584, 5,091,352, 5,103,031, 5,157,137, 5,204,419, 5,206,199, 5,235,081, 5,248,801, 5,329,032, 5,391,793, and 5,416,229.

- 48 -

When an alumoxane or modified alumoxane is used, the catalyst-precursor-to-activator molar ratio is from about 1:3000 to 10:1; alternatively, 1:2000 to 10:1; alternatively 1:1000 to 10:1; alternatively, 1:500 to 1:1; alternatively 1:300 to 1:1; alternatively 1:250 to 1:1, alternatively 1:200 to 1:1; alternatively 1:100 to 1:1; alternatively 1:50 to 1:1; alternatively 1:10 to 1:1. When the activator is an alumoxane (modified or unmodified), some embodiments select the maximum amount of activator at a 5000-fold molar excess over the catalyst precursor (per metal catalytic site). The preferred minimum activator-to-catalyst-precursor ratio is 1:1 molar ratio.

10 Ionic activators (at times used in combination with a co-activator) may be used in the practice of this invention. Preferably, discrete ionic activators such as $[\text{Me}_2\text{PhNH}][\text{B}(\text{C}_6\text{F}_5)_4]$, $[\text{Ph}_3\text{C}][\text{B}(\text{C}_6\text{F}_5)_4]$, $[\text{Me}_2\text{PhNH}][\text{B}((\text{C}_6\text{H}_3-3,5-(\text{CF}_3)_2))_4]$, $[\text{Ph}_3\text{C}][\text{B}((\text{C}_6\text{H}_3-3,5-(\text{CF}_3)_2))_4]$, $[\text{NH}_4][\text{B}(\text{C}_6\text{H}_5)_4]$ or Lewis acidic activators such as $\text{B}(\text{C}_6\text{F}_5)_3$ or $\text{B}(\text{C}_6\text{H}_5)_3$ can be used, where Ph is phenyl and Me is methyl.

15 Preferred co-activators, when used, are alumoxanes such as methylalumoxane, modified alumoxanes such as modified methylalumoxane, and aluminum alkyls such as tri-isobutylaluminum, and trimethylaluminum, triethylaluminum, and tri-isopropylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, tri-n-decylaluminum or tri-n-dodecylaluminum.

20 It is within the scope of this invention to use an ionizing or stoichiometric activator, neutral or ionic, such as tri(n-butyl)ammoniumtetrakis(pentafluorophenyl) borate, a trisperfluorophenyl boron metalloid precursor or a trisperfluoronaphthyl boron metalloid precursor, polyhalogenated heteroborane anions (WO 98/43983), boric acid (U.S. Patent No. 25 5,942,459) or combination thereof.

Examples of neutral stoichiometric activators include tri-substituted boron, tellurium, aluminum, gallium and indium or mixtures thereof. The three substituent groups are each independently selected from alkyls, alkenyls, halogen, substituted alkyls, aryls, arylhalides, alkoxy and halides. Preferably, the three groups are independently selected from halogen, mono or multicyclic (including halosubstituted) aryls, alkyls, and alkenyl compounds and mixtures thereof, preferred are alkenyl groups having 1 to 20 carbon atoms, alkyl groups having 1

- 49 -

to 20 carbon atoms, alkoxy groups having 1 to 20 carbon atoms and aryl groups having 3 to 20 carbon atoms (including substituted aryls). More preferably, the three groups are alkyls having 1 to 4 carbon groups, phenyl, naphthyl or mixtures thereof. Even more preferably, the three groups are halogenated, preferably
5 fluorinated, aryl groups. Most preferably, the neutral stoichiometric activator is trisperfluorophenyl boron or trisperfluoronaphthyl boron.

Ionic stoichiometric activator compounds may contain an active proton, or some other cation associated with, but not coordinated to, or only loosely coordinated to, the remaining ion of the ionizing compound. Such compounds
10 and the like are described in European publications EP-A-0 570 982, EP-A-0 520 732, EP-A-0 495 375, EP-B1-0 500 944, EP-A-0 277 003 and EP-A-0 277 004, and U.S. Patent Nos. 5,153,157, 5,198,401, 5,066,741, 5,206,197, 5,241,025, 5,384,299 and 5,502,124 and U.S. Patent Application Serial No. 08/285,380, filed August 3, 1994, all of which are herein fully incorporated by reference.

15 Ionic catalysts can be prepared by reacting a transition metal compound with an activator, such as $B(C_6F_5)_3$, which upon reaction with the hydrolyzable ligand (X') of the transition metal compound forms an anion, such as $[B(C_6F_5)_3(X')]^-$, which stabilizes the cationic transition metal species generated by the reaction. The catalysts can be, and preferably are, prepared with activator
20 components which are ionic compounds or compositions. However preparation of activators utilizing neutral compounds is also contemplated by this invention.

Compounds useful as an activator component in the preparation of the ionic catalyst systems used in the process of this invention comprise a cation, which is preferably a Bronsted acid capable of donating a proton, and a
25 compatible non-coordinating anion which anion is relatively large (bulky), capable of stabilizing the active catalyst species which is formed when the two compounds are combined and said anion will be sufficiently labile to be displaced by olefinic diolefinic and acetylenically unsaturated substrates or other neutral Lewis bases such as ethers, nitriles and the like. Two classes of compatible non-
30 coordinating anions have been disclosed in EPA 277,003 and EPA 277,004 published 1988: 1) anionic coordination complexes comprising a plurality of lipophilic radicals covalently coordinated to and shielding a central charge-

- 50 -

bearing metal or metalloid core, and 2) anions comprising a plurality of boron atoms such as carboranes, metallocarboranes and boranes. In a preferred embodiment, the stoichiometric activators include a cation and an anion component, and may be represented by the following formula: $(L^{**}-H)_d^+ (A^{d-})$ wherein L^{**} is a neutral Lewis base; H is hydrogen; $(L^{**}-H)^+$ is a Bronsted acid; A^{d-} is a non-coordinating anion having the charge $d-$ d is an integer from 1 to 3.

The cation component, $(L^{**}-H)_d^+$ may include Bronsted acids such as protons or protonated Lewis bases or reducible Lewis acids capable of protonating or abstracting a moiety, such as an alkyl or aryl, from the precatalyst after alkylation.

The activating cation $(L^{**}-H)_d^+$ may be a Bronsted acid, capable of donating a proton to the alkylated transition metal catalytic precursor resulting in a transition metal cation, including ammoniums, oxoniums, phosphoniums, silyliums, and mixtures thereof, preferably ammoniums of methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, diphenylamine, trimethylamine, triethylamine, N,N-dimethylaniline, methyldiphenylamine, pyridine, p-bromo N,N-dimethylaniline, p-nitro-N,N-dimethylaniline, phosphoniums from triethylphosphine, triphenylphosphine, and diphenylphosphine, oxoniums from ethers such as dimethyl ether, diethyl ether, tetrahydrofuran and dioxane, sulfoniums from thioethers, such as diethyl thioethers and tetrahydrothiophene, and mixtures thereof. The activating cation $(L^{**}-H)_d^+$ may also be a moiety such as silver, tropylium, carbeniums, ferroceniums and mixtures, preferably carboniums and ferroceniums; most preferably triphenyl carbonium. The anion component A^{d-} include those having the formula $[M^{k+}Q_n]^{d-}$ wherein k is an integer from 1 to 3; n is an integer from 2-6; $n - k = d$; M is an element selected from Group 13 of the Periodic Table of the Elements, preferably boron or aluminum, and Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, and halosubstituted-hydrocarbyl radicals, said Q having up to 20 carbon atoms with the proviso that in not more than one occurrence is Q a halide. Preferably, each Q is a fluorinated hydrocarbyl group having 1 to 20 carbon atoms, more preferably each Q is a fluorinated aryl group, and most

- 51 -

preferably each Q is a pentafluoryl aryl group. Examples of suitable A^{d-} also include diboron compounds as disclosed in U.S. Pat. No. 5,447,895.

Illustrative, but not limiting examples of boron compounds which may be

5 used as an activating cocatalyst in combination with a co-activator in the preparation of the improved catalysts of this invention are tri-substituted ammonium salts such as: trimethylammonium tetraphenylborate, triethylammonium tetraphenylborate, tripropylammonium tetraphenylborate, tri(*n*-butyl)ammonium tetraphenylborate, tri(*tert*-butyl)ammonium

10 tetraphenylborate, N,N-dimethylanilinium tetraphenylborate, N,N-diethylanilinium tetraphenylborate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate, trimethylammonium tetrakis(pentafluorophenyl)borate, triethylammonium tetrakis(pentafluorophenyl)borate, tripropylammonium tetrakis(pentafluorophenyl)borate, tri(*n*-butyl)ammonium

15 tetrakis(pentafluorophenyl)borate, tri(*sec*-butyl)ammonium tetrakis(pentafluorophenyl)borate, N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate, N,N-diethylanilinium tetrakis(pentafluorophenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl)borate, trimethylammonium tetrakis-(2,3,4,6-

20 tetrafluorophenyl) borate, triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, tri(*n*-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, dimethyl(*tert*-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, N,N-dimethylanilinium tetrakis-(2,3,4,6-

25 tetrafluorophenyl)borate, N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate, trimethylammonium tetrakis(perfluoronaphthyl)borate, triethylammonium tetrakis(perfluoronaphthyl)borate, tripropylammonium

30 tetrakis(perfluoronaphthyl)borate, tri(*n*-butyl)ammonium tetrakis(perfluoronaphthyl)borate, tri(*tert*-butyl)ammonium tetrakis(perfluoronaphthyl)borate, N,N-dimethylanilinium

- 52 -

- tetrakis(perfluoronaphthyl)borate, N,N-diethylanilinium
 tetrakis(perfluoronaphthyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium)
 tetrakis(perfluoronaphthyl)borate, trimethylammonium
 tetrakis(perfluorobiphenyl)borate, triethylammonium
 5 tetrakis(perfluorobiphenyl)borate, tripropylammonium
 tetrakis(perfluorobiphenyl)borate, tri(*n*-butyl)ammonium
 tetrakis(perfluorobiphenyl)borate, tri(*tert*-butyl)ammonium
 tetrakis(perfluorobiphenyl)borate, N,N-dimethylanilinium
 tetrakis(perfluorobiphenyl)borate, N,N-diethylanilinium
 10 tetrakis(perfluorobiphenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium)
 tetrakis(perfluorobiphenyl)borate, trimethylammonium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, triethylammonium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, tripropylammonium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, tri(*n*-butyl)ammonium tetrakis(3,5-
 15 bis(trifluoromethyl)phenyl)borate, tri(*tert*-butyl)ammonium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, N,N-dimethylanilinium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, N,N-diethylanilinium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium)
 tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, and dialkyl ammonium salts such
 20 as: di-(*iso*-propyl)ammonium tetrakis(pentafluorophenyl)borate, and
 dicyclohexylammonium tetrakis(pentafluorophenyl)borate; and other salts such as
 tri(*o*-tolyl)phosphonium tetrakis(pentafluorophenyl)borate, tri(2,6-
 dimethylphenyl)phosphonium tetrakis(pentafluorophenyl)borate, tropillium
 tetraphenylborate, triphenylcarbenium tetraphenylborate, triphenylphosphonium
 25 tetraphenylborate, triethylsilylium tetraphenylborate,
 benzene(diazonium)tetraphenylborate, tropillium
 tetrakis(pentafluorophenyl)borate, triphenylcarbenium
 tetrakis(pentafluorophenyl)borate, triphenylphosphonium
 tetrakis(pentafluorophenyl)borate, triethylsilylium
 30 tetrakis(pentafluorophenyl)borate, benzene(diazonium)
 tetrakis(pentafluorophenyl)borate, tropillium tetrakis-(2,3,4,6-
 tetrafluorophenyl)borate, triphenylcarbenium tetrakis-(2,3,4,6-

- 53 -

tetrafluorophenyl)borate, triphenylphosphonium tetrakis-(2,3,4,6-
 tetrafluorophenyl)borate, triethylsilylium tetrakis-(2,3,4,6-
 tetrafluorophenyl)borate, benzene(diazonium) tetrakis-(2,3,4,6-
 tetrafluorophenyl)borate, tropillium tetrakis(perfluoronaphthyl)borate,
 5 triphenylcarbenium tetrakis(perfluoronaphthyl)borate, triphenylphosphonium
 tetrakis(perfluoronaphthyl)borate, triethylsilylium
 tetrakis(perfluoronaphthyl)borate, benzene(diazonium)
 tetrakis(perfluoronaphthyl)borate, tropillium tetrakis(perfluorobiphenyl)borate,
 triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylphosphonium
 10 tetrakis(perfluorobiphenyl)borate, triethylsilylium
 tetrakis(perfluorobiphenyl)borate, benzene(diazonium)
 tetrakis(perfluorobiphenyl)borate, tropillium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, triphenylphosphonium tetrakis(3,5-
 15 bis(trifluoromethyl)phenyl)borate, triethylsilylium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, and benzene(diazonium) tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate.

Most preferably, the ionic stoichiometric activator $(L^{**}-H)_d^+ (A^{d-})$ is N,N-
 dimethylanilinium tetrakis(perfluorophenyl)borate, N,N-dimethylanilinium
 20 tetrakis(perfluoronaphthyl)borate, N,N-dimethylanilinium
 tetrakis(perfluorobiphenyl)borate, N,N-dimethylanilinium tetrakis(3,5-
 bis(trifluoromethyl)phenyl)borate, triphenylcarbenium
 tetrakis(perfluoronaphthyl)borate, triphenylcarbenium
 tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-
 25 bis(trifluoromethyl)phenyl)borate, or triphenylcarbenium
 tetra(perfluorophenyl)borate.

The catalyst precursors can also be activated with cocatalysts or activators
 that comprise non-coordinating anions containing metalloid-free
 cyclopentadienide ions. These are described in U.S. Patent Publication
 30 2002/0058765 A1, published on 16 May 2002, and for the instant invention,
 require the addition of a co-activator to the catalyst pre-cursor. "Compatible" non-
 coordinating anions are those which are not degraded to neutrality when the

- 54 -

initially formed complex decomposes. Further, the anion will not transfer an anionic substituent or fragment to the cation so as to cause it to form a neutral transition metal compound and a neutral by-product from the anion. Preferred non-coordinating anions useful in accordance with this invention are those that are
5 compatible, stabilize the transition metal complex cation in the sense of balancing its ionic charge at +1, yet retain sufficient lability to permit displacement by an ethylenically or acetylenically unsaturated monomer during polymerization. These types of cocatalysts are sometimes used with scavengers such as but not limited to tri-*iso*-butylaluminum, tri-*n*-octylaluminum, tri-*n*-hexylaluminum,
10 triethylaluminum or trimethylaluminum.

Invention processes also can employ cocatalyst compounds or activator compounds that are initially neutral Lewis acids but form a cationic metal complex and a noncoordinating anion, or a zwitterionic complex upon reaction with the alkylated transition metal compounds. The alkylated metallocene
15 compound is formed from the reaction of the catalyst pre-cursor and the co-activator. For example, tris(pentafluorophenyl) boron or aluminum act to abstract a hydrocarbyl ligand to yield an invention cationic transition metal complex and stabilizing noncoordinating anion, see EP-A-0 427 697 and EP-A-0 520 732 for illustrations of analogous Group-4 metallocene compounds. Also, see the
20 methods and compounds of EP-A-0 495 375. For formation of zwitterionic complexes using analogous Group 4 compounds, see U.S. Patents 5,624,878; 5,486,632; and 5,527,929.

Additional neutral Lewis-acids are known in the art and are suitable for abstracting formal anionic ligands. See in particular the review article by E. Y.-X.
25 Chen and T.J. Marks, "Cocatalysts for Metal-Catalyzed Olefin Polymerization: Activators, Activation Processes, and Structure-Activity Relationships", *Chem. Rev.*, 100, 1391-1434 (2000).

When the cations of noncoordinating anion precursors are Bronsted acids such as protons or protonated Lewis bases (excluding water), or reducible Lewis
30 acids such as ferrocenium or silver cations, or alkali or alkaline earth metal cations such as those of sodium, magnesium or lithium, the catalyst-precursor-to-activator

- 55 -

molar ratio may be any ratio. Combinations of the described activator compounds may also be used for activation.

When an ionic or neutral stoichiometric activator (such as an NCA) is used, the catalyst-precursor-to-activator molar ratio is from 1:10 to 1:1; 1:10 to 10:1; 1:10 to 2:1; 1:10 to 3:1; 1:10 to 5:1; 1:2 to 1.2:1; 1:2 to 10:1; 1:2 to 2:1; 1:2 to 3:1; 1:2 to 5:1; 1:3 to 1.2:1; 1:3 to 10:1; 1:3 to 2:1; 1:3 to 3:1; 1:3 to 5:1; 1:5 to 1:1; 1:5 to 10:1; 1:5 to 2:1; 1:5 to 3:1; 1:5 to 5:1; 1:1 to 1.1:2. The catalyst-precursor-to-co-activator molar ratio is from 1:500 to 1:1, 1:100 to 100:1; 1:75 to 75:1; 1:50 to 50:1; 1:25 to 25:1; 1:15 to 15:1; 1:10 to 10:1; 1:5 to 5:1, 1:2 to 2:1; 1:100 to 1:1; 1:75 to 1:1; 1:50 to 1:1; 1:25 to 1:1; 1:15 to 1:1; 1:10 to 1:1; 1:5 to 1:1; 1:2 to 1:1; 1:10 to 2:1. Preferred activators and activator/co-activator combinations include methylalumoxane, modified methylalumoxane, mixtures of methylalumoxane with dimethylanilinium tetrakis(pentafluorophenyl)borate or tris(pentafluorophenyl)boron, and mixtures of trimethyl aluminum with dimethylanilinium tetrakis(pentafluorophenyl)borate or tris(pentafluorophenyl)boron. In some embodiments, scavenging compounds are used with stoichiometric activators. Typical aluminum or boron alkyl components useful as scavengers are represented by the general formula R^xJZ_2 where J is aluminum or boron, R^x is as previously defined above, and each Z is independently R^x or a different univalent anionic ligand such as halogen (Cl, Br, I), alkoxide (OR^x) and the like. Most preferred aluminum alkyls include triethylaluminum, diethylaluminum chloride, tri-*iso*-butylaluminum, tri-*n*-octylaluminum, tri-*n*-hexylaluminum, trimethylaluminum and the like. Preferred boron alkyls include triethylboron. Scavenging compounds may also be alumoxanes and modified alumoxanes including methylalumoxane and modified methylalumoxane.

Supported Catalysts

Supported catalysts and or supported catalyst systems may be used to prepare PAO's. To prepare uniform supported catalysts, the catalyst precursor preferably dissolves in the chosen solvent. The term "uniform supported catalyst" means that the catalyst precursor, the activator, and or the activated catalyst

- 56 -

approach uniform distribution upon the support's accessible surface area, including the interior pore surfaces of porous supports. Some embodiments of supported catalysts prefer uniform supported catalysts; other embodiments show no such preference.

5 Useful supported catalyst systems may be prepared by any method effective to support other coordination catalyst systems, effective meaning that the catalyst so prepared can be used for oligomerizing or polymerizing olefins in a heterogenous process. The catalyst precursor, activator, co-activator (if needed), suitable solvent, and support may be added in any order or simultaneously.

10 By one method, the activator, dissolved in an appropriate solvent such as toluene, may be stirred with the support material for 1 minute to 10 hours to prepare the supported catalyst. The total solution volume (of the catalyst solution, the activator solution or both) may be greater than the pore volume of the support, but some embodiments limit the total solution volume below that needed to form a
15 gel or slurry (about 90% to 400 %, preferably about 100-200%, of the pore volume). The mixture is optionally heated from 30-200 °C during this time. The catalyst precursor may be added to this mixture as a solid, if a suitable solvent is employed in the previous step, or as a solution. Alternatively, the mixture can be filtered, and the resulting solid mixed with a catalyst precursor solution.

20 Similarly, the mixture may be vacuum dried and mixed with a catalyst precursor solution. The resulting catalyst mixture is then stirred for 1 minute to 10 hours, and the supported catalyst is either filtered from the solution and vacuum dried or subjected to evaporation to remove the solvent.

 Alternatively, the catalyst precursor and activator may be combined in
25 solvent to form a solution. The support is then added to the solution, and the resulting mixture is stirred for 1 minute to 10 hours. The total activator/catalyst-precursor solution volume may be greater than the pore volume of the support, but some embodiments limit the total solution volume below that needed to form a gel or slurry (about 90% to 400 %, preferably about 100-200% of the pore volume).

30 After stirring, the residual solvent is removed under vacuum, typically at ambient temperature and over 10-16 hours; however, greater or lesser times and temperatures may be used.

- 57 -

The catalyst precursor may also be supported absent the activator; in this case, the activator (and co-activator if needed) is added to a the liquid phase of a slurry process. For example, a solution of catalyst precursor may be mixed with a support material for a period of about 1 minute to 10 hours. The resulting
5 precatalyst mixture may be filtered from the solution and dried under vacuum or treated with evaporation to remove the solvent. The total catalyst-precursor-solution volume may be greater than the support's pore volume, but some embodiments limit the total solution volume below that needed to form a gel or slurry (about 90% to 400 %, preferably about 100-200% of the pore volume).

10 Additionally, two or more different catalyst precursors may be placed on the same support using any of the support methods disclosed above. Likewise, two or more activators or an activator and a co-activator, may be placed on the same support. Suitable solid particle supports are typically comprised of polymeric or refractory oxide materials, each being preferably porous. Any
15 support material that has an average particle size greater than 10 μm is suitable for use in this invention. Various embodiments select a porous support material, such as for example, talc, inorganic oxides, inorganic chlorides, for example magnesium chloride and resinous support materials such as polystyrene polyolefin or polymeric compounds or any other organic support material and the like. Some
20 embodiments select inorganic oxide materials as the support material including Group-2, -3, -4, -5, -13, or -14 metal or metalloid oxides. Some embodiments select the catalyst support materials to include silica, alumina, silica-alumina, and their mixtures. Other inorganic oxides may serve either alone or in combination with the silica, alumina, or silica-alumina. These are magnesia, titania, zirconia,
25 and the like. Lewis acidic materials such as montmorillonite and similar clays may also serve as a support. In this case, the support can optionally double as an activator component. But additional activator may also be used. In some cases, a special family of solid support commonly known as MCM-41 can also be used. MCM-41 is a new class of unique crystalline support and can be prepared with
30 tunable pore size and tunable acidity when modified with a second component. A detailed description of this class of materials and their modification can be found in US 5,264,203.

- 58 -

The support material may be pretreated by any number of methods. For example, inorganic oxides may be calcined, chemically treated with dehydroxylating agents such as aluminum alkyls and the like, or both.

As stated above, polymeric carriers will also be suitable in accordance with the invention, see for example the descriptions in WO 95/15815 and U.S. patent 5,427,991. The methods disclosed may be used with the catalyst compounds, activators or catalyst systems of this invention to adsorb or absorb them on the polymeric supports, particularly if made up of porous particles, or may be chemically bound through functional groups bound to or in the polymer chains.

Useful catalyst carriers may have a surface area of from 10-700 m²/g, and or a pore volume of 0.1-4.0 cc/g and or an average particle size of 10-500 μm. Some embodiments select a surface area of 50-500 m²/g, and or a pore volume of 0.5-3.5 cc/g, and or an average particle size of 20-200 μm. Other embodiments select a surface area of 100-400 m²/g, and or a pore volume of 0.8-3.0 cc/g, and or an average particle size of 30-100 μm. Invention carriers typically have a pore size of 10-1000 Angstroms, alternatively 50-500 Angstroms, or 75-350 Angstroms.

The metallocenes and or the metallocene/activator combinations are generally deposited on the support at a loading level of 10-100 micromoles of catalyst precursor per gram of solid support; alternately 20-80 micromoles of catalyst precursor per gram of solid support; or 40-60 micromoles of catalyst precursor per gram of support. But greater or lesser values may be used provided that the total amount of solid catalyst precursor does not exceed the support's pore volume.

The metallocenes and or the metallocene/activator combinations can be supported for gas-phase, bulk, or slurry polymerization, or otherwise as needed. Numerous support methods are known for catalysts in the olefin polymerization art, particularly alumoxane-activated catalysts; all are suitable for use herein. See, for example, U.S. Patents 5,057,475 and 5,227,440. An example of supported ionic catalysts appears in WO 94/03056. U.S. Patent 5,643,847 and WO 96/04319A which describe a particularly effective method. Both polymers and inorganic oxides may serve as supports, see U.S. Patents 5,422,325, 5,427,991,

- 59 -

5,498,582 and 5,466,649, and international publications WO 93/11172 and WO 94/07928.

In another preferred embodiment, the metallocene and or activator (with or without a support) are combined with an alkylaluminum compound, preferably a trialkylaluminum compound, prior to entering the reactor. Preferably the alkylaluminum compound is represented by the formula: R_3Al , where each R is independently a C1 to C20 alkyl group; preferably the R groups are independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, isobutyl, n-butyl, pentyl, isopentyl, n-pentyl, hexyl, isohexyl, n-hexyl, heptyl, octyl, isooctyl, n-octyl, nonyl, isononyl, n-nonyl, decyl, isodecyl, n-decyl, undecyl, isoundecyl, n-undecyl, dodecyl, isododecyl, and n-dodecyl, preferably isobutyl, n-octyl, n-hexyl, and n-dodecyl. Preferably the alkylaluminum compound is selected from tri-isobutyl aluminum, tri n-octyl aluminum, tri-n-hexyl aluminum, and tri-n-dodecyl aluminum.

15

Monomers

In a preferred embodiment the catalyst compounds described herein are used to polymerize or oligomerize any unsaturated monomer or monomers. Preferred monomers include C_5 to C_{24} olefins, preferably C_6 to C_{14} olefins, more preferably C_8 to C_{12} olefins. In some embodiments preferred monomers include linear, branched or cyclic alpha-olefins, preferably C_6 to C_{20} alpha-olefins, preferably C_6 to C_{14} alpha-olefins, and more preferably C_8 to C_{12} alpha-olefins. Preferred olefin monomers may be one or more of hexene, heptene, octene, nonene, decene, dodecene, 3-methyl-1-butene, and tetradecene.

25

In a preferred embodiment, the process described herein may be used to produce homo-oligomers or co-oligomers (for the purposes of this invention and the claims thereto, a co-oligmer may comprise two, three, four, or more different monomer units). Preferred oligomers produced herein include homo-oligomers or co-oligomers of any of the above monomers. In a preferred embodiment the oligomer is a homo-oligomer of any C_8 to C_{12} alpha-olefin. Preferably the oligomer is a homo-oligomer of 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, or 1-dodecene. Preferably the oligomer is a homo-oligomer

30

- 60 -

of decene. In another embodiment the oligomer is a co-oligomer comprising decene and one or more of any of the monomers listed above.

The alpha-olefins used to make PAOs include, but are not limited to, C₅ to C₂₄ alpha-olefins, with the C₆ to C₁₄ alpha-olefins, such as 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene, 1-tridecene and 1-tetradecene being preferred. A preferred group of polyalpha-olefins are poly-1-hexene, poly-1-heptene, poly-1-octene, poly-1-nonene, poly-1-decene, poly-1-undecene, poly-1-dodecene, poly-1-tridecene, and poly-1-tetradecene, although the dimers of higher olefins in the range of C₁₂ to C₁₈ can be present in the final products. Useful PAO's are preferably dimers, trimers, tetramers, pentamers, and higher oligomers or polymers with carbon numbers starting from C₂₀ and higher made from C₄ to C₁₈ alpha-olefins in one embodiment, and oligomers or polymers with carbon number starting from C₂₀ and higher made from C₆ to C₁₄ alpha-olefins in another embodiment. Suitable olefins include 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene and 1-dodecene, 1-tridecene, 1-tetradecene. In one embodiment, the olefin is 1-decene, and the PAO is a mixture of dimers, trimers, tetramers and pentamers (and higher) of 1-decene. In another embodiment, the olefin is 1-decene, and the PAO is a mixture of trimers, tetramers and pentamers (and higher) of 1-decene. In another embodiment, the olefin is 1-octene, and the PAO is a mixture of trimers, tetramers and pentamers (and higher) of 1-octene. In another embodiment, the olefin is 1-hexene, and the PAO is a mixture of tetramers and pentamers (and higher) of 1-hexene.

In a preferred embodiment, the PAO comprises two or more monomers, preferably three or more monomers, preferably four or more monomers, preferably five or more monomers. For example, a C₈, C₁₀, C₁₂-linear alpha-olefin mixture, or a C₆, C₇, C₈, C₉, C₁₀, C₁₁, C₁₂, C₁₃, C₁₄-linear alpha-olefin mixture, or a C₄, C₆, C₈, C₁₀, C₁₂, C₁₄, C₁₆, C₁₈-linear alpha-olefin mixture can be used as a feed.

In an alternate embodiment, the PAO comprises less than 50 mole% of C₂, C₃ and C₄ monomers, preferably less than 40 mole%, preferably less than 30 mole%, preferably less than 20 mole%, preferably less than 10 mole%, preferably less

- 61 -

than 5 mole%, preferably less than 3 mole %, preferably 0%. Specifically, in an alternate embodiment, the PAO comprises less than 50 mole% of ethylene, propylene and butene, preferably less than 40 mole%, preferably less than 30 mole %, preferably less than 20 mole%, preferably less than 10 mole%, preferably less than 5 mole%, preferably less than 3 mole %, preferably 0%. In another embodiment, the PAO comprises less than 40 mole% of ethylene. In another embodiment, the PAO comprises less than 40 mole% of propylene. In another embodiment, the PAO comprises less than 40 mole% of butene. In another embodiment, the PAO comprises less than 10 mole% of ethylene. In another embodiment, the PAO comprises less than 10 mole% of propylene. In another embodiment, the PAO comprises less than 10 mole% of butene. In another embodiment, the PAO comprises less than 1 mole% of ethylene. In another embodiment, the PAO comprises less than 1 mole% of propylene. In another embodiment, the PAO comprises less than 1 mole% of butene.

15 The alpha-olefins used herein can be produced directly from ethylene growth process as practiced by several commercial production processes, or they can be produced from Fischer-Tropsch hydrocarbon synthesis from CO/H₂ syngas, or from metathesis of internal olefins with ethylene, or from cracking of petroleum or Fischer-Tropsch synthetic wax at high temperature, or any other
20 alpha-olefin synthesis routes. A preferred feed for this invention is preferably at least 80 weight % alpha-olefin (preferably linear alpha olefin), preferably at least 90 weight % alpha-olefin (preferably linear alpha olefin), more preferably 100% alpha-olefin (preferably linear alpha olefin). However, alpha-olefin mixtures can also be used as feeds in this invention, especially if the other components are
25 internal-olefins, branched olefins, paraffins, cyclic paraffins, aromatics (such as toluene and or xylenes). These components have diluent effects and are believed to not have a substantial detrimental effect on the polymerization of alpha-olefins. In other words, the process described herein can selectively convert alpha-olefins in a mixture and leave the other components unreacted. This is particularly useful
30 when ethylene is not present in the mixture. This technology can be used to separate out alpha-olefins from a mixture by selectively reacting them with polymerization or oligomerization catalyst systems completely eliminating the

- 62 -

need to separate alpha-olefins from the remainder of the components in a mixed feedstream. This is economically advantageous, for example, in a process utilizing Fisher-Tropsch synthesis olefin product streams containing alpha-olefins, internal-olefins and branched olefins. Such a mixture can be fed to the
5 oligomerization technology as described herein and to selectively react away the alpha-olefin. No separate step to isolate the alpha-olefin is needed. Another example of the utility of this process involves alpha-olefins produced by the metathesis of internal olefins with ethylene, which may contain some internal olefins. This mixed olefin base stock feed can be reacted as is in the
10 polymerization / oligomerization process of the present invention, which selectively converts the alpha-olefins into lube products. Thus one can use the alpha-olefin for the base stock synthesis without having to separate the alpha-olefin from internal olefin. This can bring a significant improvement in process economics.

15 In a preferred embodiment, the PAO's produced herein may contain monomers having branches at least 2, preferably at least 3 carbons away from the alpha-unsaturation, such 4-methyl-1-decene, 4-ethyl-1-decene, or 4-methyl-1-hexene, 4-methyl-1-pentene, etc. These olefins may be present in the linear alpha-olefins from the manufacturing process or they can be added deliberately. The
20 copolymers of slightly branched alpha-olefins with completely linear alpha-olefins have improved low temperature properties.

In a preferred embodiment, any of the PAO's described herein may comprise at least 50 mole% 5 to 24 carbon atoms and from 0.5 to 20 mole% ethylene, where at least 80% of the ethylene present in the polyalpha-olefin is
25 present in runs of 1 to 35 carbons or less as measured by Carbon 13 NMR. Preferably any of the PAO's described herein may comprise at least 60 mole% 5 to 24 carbon atoms (preferably at least 70 mole%, preferably at least 80 mole%, preferably at least 85 mole%, preferably at least 90 mole%, preferably at least 95 mole%) and from 0.5 to 20 mole% ethylene (preferably from 1 to 15 mole%,
30 preferably from 2 to 10 mole %, preferably from 2 to 5 mole%), where at least 80% (preferably at least 85%, preferably at least 90%, preferably at least 95%, preferably at least 98%, preferably 100%) of the ethylene present in the

- 63 -

polyalpha-olefin is present in runs of 1 to 35 carbons (preferably 1 to 30, preferably 1 to 25, preferably 1 to 20, preferably 1 to 15, preferably 1 to 10, preferably 1 to 5) as measured by Carbon 13 NMR.

5 **Polymerization/Oligomerization Process**

Many polymerization/oligomerization processes and reactor types used for metallocene-catalyzed polymerizations or oligomerizations such as solution, slurry, and bulk polymerization or oligomerization processed can be used in this invention. In some embodiments, if a solid or supported catalyst is used, a slurry or continuous fixed bed or plug flow process is suitable. In a preferred embodiment, the monomers are contacted with the metallocene compound and the activator in the solution phase, bulk phase, or slurry phase, preferably in a continuous stirred tank reactor, continuous tubular reactor, or a batch reactor. In a preferred embodiment, the temperature in any reactor used herein is from -10°C to 250 °C, preferably from 30°C to 220 °C, preferably from 50°C to 180 °C, preferably from 60°C to 170 °C. In a preferred embodiment, the pressure in any reactor used herein is from 0.1 to 100 atmospheres, preferably from 0.5 to 75 atmospheres, preferably from 1 to 50 atmospheres. In another embodiment, the pressure in any reactor used herein is from 1 to 50,000 atmospheres, preferably 1 to 25,000 atmospheres. In another embodiment, the monomer(s), metallocene and activator are contacted for a residence time of 1 second to 100 hours, preferably 30 seconds to 50 hours, preferably 2 minutes to 6 hours, preferably 1 minute to 4 hours. In another embodiment solvent or diluent is present in the reactor and is preferably selected from the group consisting of butanes, pentanes, hexanes, heptanes, octanes, nonanes, decanes, undecanes, dodecanes, tridecanes, tetradecanes, pentadecanes, hexadecanes, toluene, o-xylene, m-xylene, p-xylene, ethylbenzene, isopropylbenzene, and n-butylbenzene; preferably toluene and or xylenes and or ethylbenzene, normal paraffins (such as Norpar solvents available for ExxonMobil Chemical Company in Houston, Texas), or isoparaffin solvents (such as Isopar solvents available for ExxonMobil Chemical Company in Houston, Texas). These solvents or diluents are usually pre-treated in same manners as the feed olefins.

- 64 -

Typically, in the processes of this invention, one or more transition metal compounds, one or more activators, and one or more monomers are contacted to produce polymer or oligomer. These catalysts may be supported and as such will be particularly useful in the known slurry, solution, or bulk operating modes conducted in single, series, or parallel reactors. If the catalyst, activator or co-activator is a soluble compound, the reaction can be carried out in a solution mode. Even if one of the components is not completely soluble in the reaction medium or in the feed solution, either at the beginning of the reaction or during or at the later stages of the reaction, a solution or slurry type operation is still applicable. In any instance, the catalyst components, dissolved or suspended in solvents, such as toluene or other conveniently available aromatic solvents, or in aliphatic solvent, or in the feed alpha-olefin stream, are fed into the reactor under inert atmosphere (usually nitrogen or argon blanketed atmosphere) to allow the polymerization or oligomerization to take place. The polymerization or oligomerization can be run in a batch mode, where all the components are added into a reactor and allowed to react to a pre-designed degree of conversion, either to partial conversion or full conversion. Subsequently, the catalyst is deactivated by any possible means, such as exposure to air or water, or by addition of alcohols or solvents containing deactivating agents. The polymerization or oligomerization can also be carried out in a semi-continuous operation, where feeds and catalyst system components are continuously and simultaneously added to the reactor so as to maintain a constant ratio of catalyst system components to feed olefin(s). When all feeds and catalyst components are added, the reaction is allowed to proceed to a pre-determined stage. The reaction is then discontinued by catalyst deactivation in the same manner as described for batch operation. The polymerization or oligomerization can also be carried out in a continuous operation, where feeds and catalyst system components are continuously and simultaneously added to the reactor so to maintain a constant ratio of catalyst system and feed olefins. The reaction product is continuously withdrawn from the reactor, as in a typical continuous stirred tank reactor (CSTR) operation. The residence times of the reactants are controlled by a pre-determined degree of conversion. The withdrawn product is then typically quenched in the separate

- 65 -

reactor in a similar manner as other operation. In a preferred embodiment, any of the processes to prepare PAO's described herein are continuous processes.

Preferably the continuous process comprises the steps of a) continuously introducing a feed stream comprising at least 10 mole % of the one or more C5 to C24 alpha-olefins into a reactor, b) continuously introducing the metallocene compound and the activator into the reactor, and c) continuously withdrawing the polyalpha-olefin from the reactor. In another embodiment, the continuous process comprises the step of maintaining a partial pressure of hydrogen in the reactor of 200 psi (1379 kPa) or less, based upon the total pressure of the reactor, preferably 150 psi (1034 kPa) or less, preferably 100 psi (690 kPa) or less, preferably 50 psi (345 kPa) or less, preferably 25 psi (173 kPa) or less, preferably 10 psi (69 kPa) or less. Alternately the hydrogen, if present is present in the reactor at 1000ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less. Alternately the hydrogen, if present, is present in the feed at 1000ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less.

Preferred reactors range in size from 2 ml and up. Usually, it is preferable to use reactors larger than one liter in volume for commercial production. The production facility may have one single reactor or several reactors arranged in series or in parallel or in both to maximize productivity, product properties and general process efficiency. The reactors and associated equipments are usually pre-treated to ensure proper reaction rates and catalyst performance. The reaction is usually conducted under inert atmosphere, where the catalyst system and feed components will not be in contact with any catalyst deactivator or poison which is usually polar oxygen, nitrogen, sulfur or acetylenic compounds.

One or more reactors in series or in parallel may be used in the present invention. The transition metal compound, activator and when required, co-activator, may be delivered as a solution or slurry in a solvent or in the alpha-olefin feed stream, either separately to the reactor, activated in-line just prior to

- 66 -

the reactor, or preactivated and pumped as an activated solution or slurry to the reactor. Polymerizations/oligomerizations are carried out in either single reactor operation, in which monomer, or several monomers, catalyst/activator/co-activator, optional scavenger, and optional modifiers are added continuously to a single reactor or in series reactor operation, in which the above components are added to each of two or more reactors connected in series. The catalyst components can be added to the first reactor in the series. The catalyst component may also be added to both reactors, with one component being added to first reaction and another component to other reactors. In one preferred embodiment, the precatalyst is activated in the reactor in the presence of olefin. In another embodiment, the precatalyst such as the dichloride form of the metallocenes is pre-treated with alkylaluminum reagents, especially, triisobutylaluminum, tri-n-hexylaluminum and/ or tri-n-octylaluminum, followed by charging into the reactor containing other catalyst component and the feed olefins, or followed by pre-activation with the other catalyst component to give the fully activated catalyst, which is then fed into the reactor containing feed olefins. In another alternative, the pre-catalyst metallocene is mixed with the activator and/or the co-activator and this activated catalyst is then charged into reactor, together with feed olefin stream containing some scanvenger or co-activator. In another alternative, the whole or part of the co-activator is pre-mixed with the feed olefins and charged into the reactor at the same time as the other catalyst solution containing metallocene and activators and/or co-activator.

In some embodiments, a small amount of poison scavenger, such as trialkylaluminum (trimethylaluminum, triethylaluminum, triisopropylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum) or methylalumoxane is added to the feed olefin stream to further improve catalyst activity. In a preferred embodiment, the monomers are contacted with an alkylaluminum compound, preferably a trialkylaluminum compound, prior to being introduced into the reactor. In another preferred embodiment, the metallocene and or activator are combined with an alkylaluminum compound, preferably a trialkylaluminum compound, prior to entering the reactor. Preferably the alkylaluminum compound is represented by the formula: R_3Al , where each R

- 67 -

is independently a C1 to C20 alkyl group, preferably the R groups are independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, isobutyl, n-butyl, pentyl, isopentyl, n-pentyl, hexyl, isohexyl, n-hexyl, heptyl, octyl, isooctyl, n-octyl, nonyl, isononyl, n-nonyl, decyl, isodecyl, n-decyl, undecyl, isoundecyl, n-undecyl, dodecyl, isododecyl, and n-dodecyl, preferably isobutyl, n-octyl, n-hexyl, and n-dodecyl. Preferably the alkylaluminum compound is selected from tri-isobutylaluminum, tri n-octylaluminum, tri-n-hexylaluminum, and tri-n-dodecylaluminum.

In one embodiment of any of the process described herein the feed olefins and or solvents are treated to remove catalyst poisons, such as peroxides, oxygen or nitrogen-containing organic compounds or acetylenic compounds. The treatment of the linear alpha-olefin with an activated 13X molecular sieve and a de-oxygenate catalyst, i.e., a reduced copper catalyst, increased catalyst productivity more than 10-fold. Alternatively, the feed olefins and or solvents are treated with an activated molecular sieve, such as 3A, 4A, 8A or 13X molecular sieve, and/or in combination with an activated alumina or an activated de-oxygenated catalyst. Such treatment will increase catalyst productivity 2- to 10-fold or more. The improved process also includes special treatment of the feed olefins to remove catalyst poisons, such as peroxides, oxygen, sulfur or nitrogen-containing organic compounds or other trace impurities. This treatment can increase catalyst productivity substantially (typically more than 10-fold). Preferably the feed olefins are contacted with a molecular sieve, activated alumina, silica gel, oxygen removing catalyst, and or purifying clays to reduce the heteroatom-containing compounds in the feed, preferably below 50 ppm, preferably below 10 ppm.

The catalyst compositions can be used individually or can be mixed with other known polymerization catalysts to prepare polymer or oligomer blends. Monomer and catalyst selection allows polymer or oligomer blend preparation under conditions analogous to those using individual catalysts. Polymers having increased MWD are available from polymers made with mixed catalyst systems and can thus be achieved. Mixed Catalyst can comprise two or more catalyst precursors and or two or more activators.

- 68 -

Generally, when using metallocene catalysts, after pre-treatment of feed olefins, solvents, diluents and after precautions to keep the catalyst component stream(s) and reactor free of impurities, the reaction should proceed well. In some embodiments, when using metallocene catalysts, particularly when they are

5 immobilized on a support, the complete catalyst system will additionally comprise one or more scavenging compounds. Here, the term scavenging compound means a compound that removes polar impurities from the reaction environment. These impurities adversely affect catalyst activity and stability. Typically, purifying steps are usually used before introducing reaction components to a reaction vessel.

10 But such steps will rarely allow polymerization or oligomerization without using some scavenging compounds. Normally, the polymerization process will still use at least small amounts of scavenging compounds.

Typically, the scavenging compound will be an organometallic compound such as the Group-13 organometallic compounds of U.S. Patents 5,153,157,

15 5,241,025 and WO-A-91/09882, WO-A-94/03506, WO-A-93/14132, and that of WO 95/07941. Exemplary compounds include triethylaluminum, triethylborane, tri-*iso*-butylaluminum, diisobutylaluminum hydride, methylalumoxane, *iso*-butylalumoxane, and tri-*n*-octylaluminum. Those scavenging compounds having bulky or C₆-C₂₀ linear hydrocarbyl substituents connected to the metal or

20 metalloid center usually minimize adverse interaction with the active catalyst. Examples include triethylaluminum, but more preferably, bulky compounds such as tri-*iso*-butyl aluminum, tri-*iso*-prenyl aluminum, and long-chain linear alkyl-substituted aluminum compounds, such as tri-*n*-hexyl aluminum, tri-*n*-octyl aluminum, or tri-*n*-dodecyl aluminum. When alumoxane is used as the activator,

25 any excess over that needed for activation will scavenge impurities and additional scavenging compounds may be unnecessary. Alumoxanes also may be added in scavenging quantities with other activators, e.g., methylalumoxane, [Me₂HNPh]⁺[B(pfp)₄]⁻ or B(pfp)₃, where pfp is perfluorophenyl (C₆F₅), Me is methyl and Ph is phenyl.

30 In a preferred embodiment ethylene is present in the feed at 10 mole% or less, preferably 0.5 to 8 moles %, preferably 0.5 to 5 mole%, preferably from 1 to 3 mole%

- 69 -

The PAO's described herein can also be produced in homogeneous solution processes. Generally this involves polymerization or oligomerization in a continuous reactor in which the polymer formed and the starting monomer and catalyst materials supplied, are agitated to reduce or avoid concentration or temperature gradients. Temperature control in the reactor is generally obtained by balancing the heat of polymerization and with reactor cooling by reactor jackets or cooling coils or a cooled side-stream of reactant to cool the contents of the reactor, auto refrigeration, pre-chilled feeds, vaporization of liquid medium (diluent, monomers or solvent) or combinations of the above. Adiabatic reactors with pre-chilled feeds may also be used. The reactor temperature depends on the catalyst used and the product desired. Higher temperatures tend to give lower molecular weights and lower temperatures tend to give higher molecular weights, however this is not a hard and fast rule. In general, the reactor temperature preferably can vary between about 0 °C and about 300 °C, more preferably from about 10 °C to about 230 °C, and most preferably from about 25 °C to about 200 °C. Usually, it is important to control the reaction temperature as pre-determined. In order to produce fluids with narrow molecular distribution, such as to promote the highest possible shear stability, it is useful to control the reaction temperature to obtain minimum of temperature fluctuation in the reactor or over the course of the reaction time. If multiple reactors are used in series or in parallel, it is useful to keep the temperature constant in a pre-determined value to minimize any broadening of molecular weight distribution. In order to produce fluids with broad molecular weight distribution, one can adjust the reaction temperature swing or fluctuation, or as in series operation, the second reactor temperature is preferably higher than the first reactor temperature. In parallel reactor operation, the temperatures of the two reactors are independent. Or one can use two types of metallocene catalysts.

The pressure in any reactor used herein can vary from about 0.1 atmosphere to 100 atmosphere (1.5 psi to 1500 psi), preferably from 0.5 bar to 75 atm (8 psi-1125 psi), most preferably from 1.0 to 50 atm (15 psi to 750 psi). The reaction can be carried out under the atmosphere of nitrogen or with some hydrogen. Sometimes a small amount of hydrogen is added to the reactor to

- 70 -

improve the catalyst. The amount of hydrogen is preferred to keep at such a level to improve catalyst productivity, but not induce any hydrogenation of olefins, especially the feed alpha-olefins because the conversion of alpha-olefins into saturated paraffins is very detrimental to the efficiency of the process. The amount of hydrogen partial pressure is preferred to be kept low, less than 100 psi, prefer less than 50 psi, preferably less than 25 psi, preferably less than 10 psi, preferably less than 5 psi, preferably less than 1 psi. In a particularly preferred embodiment in any of the process described herein the concentration of hydrogen in the reactant phase is less than 100 ppm, preferably less than 50 ppm, preferably less than 10 ppm, preferably less than 1 ppm. In a particularly preferred embodiment in any of the process described herein the concentration of hydrogen in the reactor is kept at a partial pressure of 200 psi (1379 kPa) or less, based upon the total pressure of the reactor, preferably 150 psi (1034 kPa) or less, preferably 100 psi (690 kPa) or less, preferably 50 psi (345 kPa) or less, preferably 10 psi (69 kPa) or less. Alternately, in any process described herein hydrogen, if present, is present in the reactor and or feed at 1000 ppm or less by weight, preferably 750 ppm or less, preferably 500 ppm or less, preferably 250 ppm or less, preferably 100 ppm or less, preferably 50 ppm or less, preferably 25 ppm or less, preferably 10 ppm or less, preferably 5 ppm or less.

The reaction time or reactor residence time is usually dependent on the type of catalyst used, the amount of catalyst used, and the desired conversion level. Different metallocenes have different activities. Usually, a higher degree of alkyl substitution on the cyclopentadienyl ring, or bridging improves catalyst productivity. Catalysts such as bis(1,2,3,4-tetramethylcyclopentadienyl)zirconium dichloride or bis(1,2,4-trimethylcyclopentadienyl)zirconium dichloride, (1,2,3,4-tetramethylcyclopentadienyl)(1,3-dimethylcyclopentadienyl)zirconium dichloride or (1,2,4-trimethylcyclopentadienyl)(1,3-dimethylcyclopentadienyl)zirconium dichloride or their dialkyl analogs have desirable high productivity and stability than unsubstituted metallocenes. Certain bridged and bridged with substitution catalysts, such as the di-halides or dialkyls of dimethylsilylbis[indenyl]zirconium or dimethylsilylbis[tetrahydro-indenyl]zirconium dimethylsilylbis[1-methylindenyl]zirconium or their hafnium analogs, etc. Usually the amount of

- 71 -

catalyst components used is determinative. High amount of catalyst loading tends to gives high conversion at short reaction time. However, high amount of catalyst usage make the production process uneconomical and difficult to manage the reaction heat or to control the reaction temperature. Therefore, it is useful to
5 choose a catalyst with maximum catalyst productivity to minimize the amount of metallocene and the amount of activators needed. When the catalyst system is metallocene plus methylalumoxane, the range of methylalumoxane used is typically in the range of 0.1 milligram (mg) to 500 mg/g of alpha-olefin feed. A more preferred range is from 0.05 mg to 10 mg/g of alpha-olefin feed.

10 Furthermore, the molar ratios of the aluminum to metallocene (Al/M molar ration) range from 2 to 4000, preferably 10 to 2000, more preferably 50 to 1000, preferably 100 to 500. When the catalyst system is metallocene plus a Lewis Acid or an ionic promoter with NCA component, the metallocene use is typically in the range of 0.01 microgram to 500 micrograms of metallocene component/gram of
15 alpha-olefin feed. Usually the preferred range is from 0.1 microgram to 100 microgram of metallocene component per gram of alpha-olefin feed. Furthermore, the molar ratio of the NCA activator to metallocene is in the range from 0.1 to 10, preferably 0.5 to 5, preferably 0.5 to 3. If a co-activator of alkylaluminum compound is used, the molar ratio of the Al to metallocene is in
20 the range from 1 to 1000, preferably 2 to 500, preferably 4 to 400.

Typically one prefers to have the highest possible conversion (close to 100%) of feed alpha-olefin in shortest possible reaction time. However, in CSTR operation, sometimes it is beneficial to run the reaction at an optimum conversion, which is slightly less than 100% conversion. There are also occasions, when
25 partial conversion is more desirable when the narrowest possible MWD of the product is desirable because partial conversion can avoid a MWD broadening effect. If the reaction is conducted to less than 100% conversion of the alpha-olefin, the unreacted starting material after separation from other product and solvents/diluents can be recycled to increase the total process efficiency.

30 Desirable residence times for any process described herein are in the range from 1 minutes to 20 hours, typically 5 minutes to 10 hours.

- 72 -

Each of these processes may also be employed in single reactor, parallel or series reactor configurations. The liquid processes comprise contacting olefin monomers with the above described catalyst system in a suitable diluent or solvent and allowing said monomers to react for a sufficient time to produce the desired polymers or oligomers. Hydrocarbon solvents both aliphatic and aromatic are suitable. Aromatics such as toluene, xylenes, ethylbenzene, propylbenzene, cumene, t-butylbenzene are suitable. Alkanes, such as hexane, heptane, pentane, isopentane, and octane, Norpar or Isopar solvents from ExxonMobil Chemical Company in Houston, Texas are also suitable. Generally, toluene is most suitable to dissolve catalyst components. Norpar, Isopar solvent or hexanes are preferred as reaction diluents. Oftentimes, a mixture of toluene and Norpar or Isopar is used as diluent or solvent.

The process can be carried out in a continuous stirred tank reactor, batch reactor, or plug flow reactor, or more than one reactor operated in series or parallel. These reactors may have or may not have internal cooling and the monomer feed may or may not be refrigerated. See the general disclosure of U.S. patent 5,705,577 for general process conditions.

When a solid supported catalyst is used for the conversion, a slurry polymerization/oligomerization process generally operates in the similar temperature, pressure and residence time range as described previously. In a slurry polymerization or oligomerization, a suspension of solid catalyst, promoters, monomer and comonomers are added. The suspension including diluent is intermittently or continuously removed from the reactor. The catalyst is then separated from the product by filtration, centrifuge or settlement. The fluid is then distilled to remove solvent, any unreacted components and light product. A portion or all of the solvent and unreacted component or light components can be recycled for reuse.

If the catalyst used is un-supported, is a solution catalyst, when the reaction is complete (such as in a batch mode), or when the product is withdrawn from the reactor (such as in a CSTR), the product may still contain soluble, suspended or mixed catalyst components. These components are preferably deactivated or removed. Any of the usual catalyst deactivation methods or

- 73 -

aqueous wash methods can be used to remove the catalyst component. Typically, the reaction is deactivated by addition of stoichiometric amount or excess of air, moisture, alcohol, isopropanol, etc. The mixture is then washed with dilute sodium hydroxide or with water to remove catalyst components. The residual
5 organic layer is then subjected to distillation to remove solvent, which can be recycled for reuse. The distillation can further remove any light reaction product from C18 and less. These light components can be used as diluent for further reaction. Or they can be used as olefinic raw material for other chemical synthesis, as these light olefin product have vinylidene unsaturation, most suitable
10 for further functionalization to convert in high performance fluids. Or these light olefin products can be hydrogenated to be used as high quality paraffinic solvents.

Polymerization or oligomerization in absence of hydrogen is also advantageous to provide polymers or oligomers with high degree of unsaturated double bonds. These double bonds can be easily converted into functionalized
15 fluids with multiple performance features. Examples for converting these polymers with MW greater than 300 can be found in preparation of ashless dispersants, by reacting the polymers with maleic anhydride to give PAO-succinic anhydride which can then reacted with amines, alcohols, polyether alcohols to convert into dispersants. Examples for such conversion can be found in the book
20 "Lubricant Additives: Chemistry and Application," ed. By Leslie R. Rudnick, p. 143-170.

In another embodiment, any of polyalphaolefins produced herein is hydrogenated. In particular the polyalpha-olefin is preferably treated to reduce heteroatom containing compounds to less than 600 ppm, and then contacted with
25 hydrogen and a hydrogenation catalyst to produce a polyalpha-olefin having a bromine number less than 1.8. In a preferred embodiment, the treated polyalpha-olefin comprises 100 ppm of heteroatom containing compounds or less, preferably 10 ppm of heteroatom containing compounds or less. (A heteroatom containing compound is a compound containing at least one atom other than carbon and
30 hydrogen.) Preferably the hydrogenation catalyst is selected from the group consisting of supported Group 7, 8, 9, and 10 metals, preferably the hydrogenation catalyst selected from the group consisting of one or more of Ni, Pd, Pt, Co, Rh,

- 74 -

Fe, Ru, Os, Cr, Mo, and W, supported on silica, alumina, clay, titania, zirconia, or mixed metal oxide supports. A preferred hydrogenation catalyst is nickel supported on kieselguhr, or platinum or palladium supported on alumina, or cobalt-molybdenum supported on alumina. Usually, a high nickel content catalyst, such as 60% Ni on Kieselguhr catalyst is used, or a supported catalyst with high amount of Co-Mo loading. Alternately, the hydrogenation catalyst is nickel supported on kieselguhr, silica, alumina, clay or silica-alumina.

In a preferred embodiment the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst at a temperature from 25 to 350°C, preferably 100 to 300°C. In another preferred embodiment the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst for a time period from 5 minutes to 100 hours, preferably from 5 minutes to 24 hours. In another preferred embodiment the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst at a hydrogen pressure of from 25 psi to 2500 psi, preferably from 100 to 2000 psi. In another preferred embodiment the hydrogenation process reduces the number of mm triad groups in a polyalpha-olefin by 1 to 80%. Preferably the PAO has 10 to 80% less mm triad groups than the polyalpha-olefin prior to contact with the hydrogen and hydrogenation catalyst. For further information on hydrogenation of PAO's please see US 5,573,657 and "Lubricant Base Oil Hydrogen Refining Processes" (page 119 to 152 of **Lubricant Base Oil and Wax Processing**, by Avilino Sequeira, Jr., Marcel Dekker, Inc., NY, 1994).

This hydrogenation process can be accomplished in a slurry reactor in a batch operation or in a continuous stirred tank reactor (CSTR), where the catalyst is 0.001 wt% to 20 wt% of the PAO feed or preferably 0.01 to 10 wt%, hydrogen and the polyalpha-olefins are continuously added to the reactor to allow for certain residence time, usually 5 minutes to 10 hours to allow complete hydrogenation of the unsaturated olefins and to allow proper conversion of the mm diads. The amount of catalyst added is usually very small just to compensate for the catalyst deactivation. The catalyst and hydrogenated PAO are continuously withdrawn from the reactor. The product mixture was then filtered, centrifuged or settled to remove the solid hydrogenation catalyst. The catalyst can be regenerated and reused. The hydrogenated PAO can be used as is or further distilled or

- 75 -

fractionated to the right component if necessary. In some cases, when the hydrogenation catalyst show no catalyst deactivation over long term operation, the stir tank hydrogenation process can be carried out in a manner where a fixed amount of catalyst is maintained in the reactor, usually 0.1 wt% to 10% of the total reactant, and only hydrogen and PAO feed are continuously added at certain feed rate and only hydrogenated PAO was withdrawn from the reactor.

The hydrogenation process can also be accomplished by a fixed bed process, in which the solid catalyst is packed inside a tubular reactor and heated to reactor temperature. Hydrogen and PAO feed can be fed through the reactor simultaneously from the top or bottom or countercurrently to maximize the contact between hydrogen, PAO and catalyst and to allow best heat management. The feed rate of the PAO and hydrogen are adjusted to give proper residence to allow complete hydrogenation of the unsaturated olefins in the feed and to allow desirable conversion of mm triads in the process. The hydrogenated PAO fluid can be used as is or further distilled or fractionated to give the right component, if necessary. Usually, the finished hydrocarbon PAO fluids have bromine number less than 2 and have reduced amount of mm triads than the unhydrogenated PAO.

The new poly-alpha-olefins when used alone or blended with other fluid has unique lubrication properties.

In another embodiment, a novel lubricant of the present invention comprises the PAO's produced in this invention, together with one or more other base stocks, including Group I to Group V base stocks with viscosity range from 1.5 to 100 cSt at 100°C to formulate suitable viscosity grades. In addition, additives of one or more of: thickeners, VI improvers, antioxidants, anti-wear additives, detergent/dispersant/inhibitor (DDI) packages, and/or anti-rust additives may be added. In a preferred embodiment the PAO's produced herein are combined with one or more of dispersants, detergents, friction modifiers, traction improving additives, demulsifiers, defoamants, chromophores (dyes), and/or haze inhibitors. These fully formulated lubricants can be used in automotive crank case oil (engine oil), industrial oil, grease, or gas turbine engine oil. These are examples of additives used in finished lubricant formulations. Additional information on the use of PAO's in the formulations of full synthetic, semi-

- 76 -

synthetic or part synthetic lubricant or functional fluids can be found in "Synthetic Lubricants and High-Performance Functional Fluids", 2nd Ed. L. Rudnick, etc. Marcel Dekker, Inc., N.Y. (1999). Additional information on additives used in product formulation can be found in "Lubricants and Lubrications, Ed. By T. Mang and W. Dresel, by Wiley-VCH GmbH, Weinheim 2001.

Examples

The following examples are for purposes of illustration only and are non-limiting examples.

10 The 1-decene used for all of the experiments was purified by mixing 1 liter of untreated raw material with 20 grams of activated 13X molecular sieve, (which was activated by calcining at 200°C for at least four hours under a stream of purging dry nitrogen gas), and 10 grams of Oxi-Clear catalyst (purchased from Altech Associates, Inc of Deerfield, IL 60115) for at least two days inside a glove
15 box under a dry, inert atmosphere of nitrogen. The molecular sieve and de-oxygenation catalyst were then removed by filtration in the glove box to provide purified 1-decene. Alternatively, the feeds were purified by passing through a bed of activated 13X molecular sieve alone under nitrogen atmosphere.

 The polymerization/oligomerization reaction was carried out under
20 nitrogen (N₂) inert atmosphere or argon inert atmosphere. In a small scale screening experiment, 2.2 grams of purified 1-decene was added into a small stainless steel reactor fitted with glass liner with a total reactor volume of 5.5 ml, an agitator and a temperature controller, followed by addition of 0.668 ml of methylalumoxane (MAO) in toluene solution which was prepared by diluting 10
25 wt % MAO in toluene solution to a dilute solution containing 8.68 mg methylaluminoxane per ml of solution volume. The reactor was then heated to the desired reaction temperature and the desired amount of metallocene catalyst in toluene was added to initiate the polymerization reaction. After 3 hours, the reaction was quenched by addition of carbon dioxide (CO₂) gas of equal moles as
30 the metallocene catalyst. The polymerization / oligomerization product was isolated by stripping the reactor contents, from about room temperature to 50 °C, under high vacuum for at least 2 hours to remove solvent, unreacted starting

- 77 -

material and dimer, i.e., any component having less than thirty carbon atoms. The product properties, including molecular weight and Mw/Mn, were analyzed by gel permeation chromatography using tetrahydrofuran as the solvent and polystyrene as the calibration standard. The residual fluid viscosity was calculated by a correlation equation, which correlated the Mw by GPC to fluid viscosity. The correlation equation used was:

$$Kv@100^{\circ}C \text{ in cSt} = 0.13 + 0.005578 * Mw + 1.37 * 10^{-6} * (Mw)^2$$

Catalyst productivity was calculated as grams of product, which is usually the C30 and higher component when 1-decene is used as feed, per gram of MAO.

10 In the case when an NCA was used as co-catalyst, the catalyst productivity was calculated in gram of product (C30 and higher) per gram of metallocene catalyst (not including the NCA or co-activator).

Examples 1 through 10 were conducted generally as described above, with additional experimental details provided in Table 1 below.

Table 1 Reactions were carried out using 0.1 micromole metallocene catalyst, Al/Zr molar ratio=1000

Example number	1	2	3	4	5	6	7	8	9	10
catalyst type*	A	B	C	D	E	F	G	E	F	G
reaction temperature, °C	100	100	100	100	100	100	100	50	50	50
product yield, wt%	65	65	71	29	88	76	29	88	41	94
g product/g MAO	190	190	207	86	259	224	86	259	121	276
Mw g/mol	507	514	791	493	5860	1436	23935	12300	8280	27560
Mw/Mn	1.1	1.1	1.2	1.1	1.8	1.4	1.5	1.8	2	2
estimated 100°C vis, cSt**	3.3	3.4	5.4	3.2	80	11	918	276	140	1194

Reactions were carried out using 0.1 micromole catalyst, Al/Zr molar ratio=1000.

*Catalyst type

- A biscyclopentadienylzirconium dichloride
- B dimethylsilylbis(cyclopentadienyl)zirconium dichloride
- C bis(1,3-dimethylcyclopentadienyl)zirconium dichloride
- D iso-propylidenebis(cyclopentadienyl)zirconium dichloride
- E rac-ethylenebis(1-indenyl)zirconium dichloride
- F rac-dimethylsilylbis(tetrahydroindenyl)zirconium dichloride
- G diphenylmethylenedene(cyclopentadienyl)(9-fluorenyl)zirconium dichloride

** Viscosity was calculated based on Mw determined by GPC using the formula:
Kv@100°C in cSt = 0.13+0.005578*Mw + 1.37*10⁻⁶*(Mw)²

- 79 -

Examples 11 through 17 were conducted generally as described above, with additional experimental details provided in Table 2 below.

- 5 Table 2. Reactions were carried out at 100°C, using 0.1 micromole metallocene catalyst, Al/Zr molar ratio =250

Example number	11	12	13	14	15	16	17
Catalyst type*	H	I	J	K	C	L	B
product yield, wt%***	21.7	28.3	15.9	17.3	38.1	23.2	27.6
g product/g MAO	329	430	241	262	578	352	419
Mw (g/mol)	1715	1674	1807	1862	2305	2333	2331
Mw/Mn	1.1	1.1	1.1	1.1	1.2	1.2	1.2
Estimated 100°C vis, cSt**	4.0	3.8	4.4	4.7	6.7	6.9	6.9

Catalyst type

H bis(methylcyclopentadienyl)zirconium dichloride

I bis(ethylcyclopentadienyl)zirconium dichloride

10 J bis(n-butylcyclopentadienyl)zirconium dichloride

K bis(n-dodecylcyclopentadienyl)zirconium dichloride

L (methylcyclopentadienyl)(propylcyclopentadienyl)zirconium dichloride

** Viscosity was calculated based on Mw determined by GPC using the formula:

15 $K_v@100^\circ\text{C in cSt} = 0.13 + 0.005578 * \text{Mw} + 1.37 * 10^{-6} * (\text{Mw})^2$

*** product yield weight % = 100 (residual weight/ feed 1-decene weight)

Examples 18 through 26 were conducted generally as described above, with additional experimental details provided in Table 3 below.

Table 3: Reactions were carried out at 100°C, using 0.1 micromole metallocene catalyst, Al/Zr molar ratio =250

Sample number.	18	19	20	21	22	23	24	25	26
Catalyst type*	M	N	O	P	F	G	Q	R	S
product yield, wt%	28.5	20.6	52.3	5.5	61.9	11.3	27.4	3.2	5.1
g polymer/g MAO	433	313	793	83	939	172	415	48	77
Mw	11287	11259	19822	10214	24369	298921	15278	14431	37372
Mw/Mn	1.1	1.1	1.3	1.1	1.3	1.8	1.2	1.2	1.9
Estimated 100°C viscosity, cSt**	90	90	243	76	353	44524	153	138	781

Catalyst type:

- M bis(indenyl)zirconium dichloride
- N cyclopentadienyl(indenyl)zirconium dichloride
- O bis(1,2,4-trimethylcyclopentadienyl)zirconium dichloride
- P bis(pentamethylcyclopentadienyl)zirconium dichloride
- Q bis(1-methyl-3-n-propylcyclopentadienyl)zirconium dichloride
- R bis(cyclopentadienyl)hafnium dichloride
- S bis(indenyl)hafnium dichloride

** Viscosity was calculated based on Mw determined by GPC using the formula:

$$Kv@100^{\circ}C \text{ in cSt} = 0.13 + 0.005578 * Mw + 1.37 * 10^{-6} * (Mw)^2$$

*** product yield weight % = 100 (residual weight/ feed 1-decene weight)

- 81 -

Example 27 to 32. In this set of experiments, the reaction was carried out by adding 180 gram of purified 1-decene and a catalyst solution, prepared by dissolving 2.017 millimole methylalumoxane (1.17 gram of a 10wt% in toluene solution) and 8.07 micromole of metallocene catalyst in 58 gram of toluene solvent, into a 500 ml round bottom flask containing 180 gram purified 1-decene heated to reaction temperature and equipped with stirrer and temperature controller. The reaction mixture was maintained at proper reaction temperature. After 4-10 hours, the reaction was quenched by addition of 3-ml isopropanol, dilute HCl solution and washed with 5% NaOH solution. The organic layer was separated and distilled under full vacuum to remove any C20 and lower components. The C30 and higher components were then hydrogenated under typical hydrogenation conditions using Nickel on Kieselguhr catalyst at 200°C, 800 psi hydrogen for 4-8 hours. After hydrogenation, the bromine number of the samples were below 1. The composition of the product was then analyzed by gas chromatograph equipped with a 60 meter DB1 column (initial temperature, 70°C/0 minute, 10°C/minute to 320 °C). A typical gas chromatograph for the C₃₀H₆₂ component of example 31 is shown in Figure 4. The major components **A** and **B** were determined by comparison of the GC retention time to the known compounds. Component **A** is believed to be produced by hydrogenation of the olefin **A''** produced from simple 1,2-connections of each 1-decene molecule. Component **B** is believed to be produced by hydrogenation of olefin **B''** produced from a 1,1-connection during the chain termination process. The presence of component **B** is unexpected from this type of chemistry.

25

The amount of Component **B**, 1,1-octyldocosane, is related to product viscosity, as demonstrated in Table 4. In Table 4, the higher the lube viscosity, the higher the amount of component **B** is in the 1-decene-trimer fraction. This is quite unexpected from previously known chemistry. The presence of **B** is beneficial for fluid property. For example, a C₃₀H₆₂ **B** compound, synthesized independently from n-dodecyl aldehyde following a well-defined chemical

30

- 82 -

reaction path (final product B C₃₀H₆₂, 11-octyldocosane),
has superior viscometrics and VI (Kv at 100°C = 3.38 cSt, VI = 149), as compared
to the current low vis PAO of Kv at 100°C = 4.1 cSt and VI = 126 or the
synthesized C₃₀ A with Kv at 100°C of 3.67 and VI = 130.

5

Table 4. lube properties and amount of compound B in C30 component

Example no	27	28	29	30	31	32
catalyst type	A	B	I	F	F	F
Reaction temp., °C	50	100	70	126	100	70
Lube properties						
KV100°C, cSt	8.14	10.29	13.81	15.86	37.56	126.27
KV40°C, cSt	43.8	56.73	85.04	100.57	284.04	1132.63
Viscosity Index	162	172	167	169	183	218
pour point, °C	<-55	<-50	<-52	<-55	-48	-33
Bromine number before hydrogenation	27.0	21.5	20.2	17.5	11.1	5.6
Bromine number after hydrogenation	0	0	0	0.5	0	0
Wt% B component in C ₃₀ H ₆₂ fraction	3.6	4.9	4.9	8.4	11.3	14.6

Catalyst type:

- A biscyclopentadienylzirconium dichloride
 B dimethylsilylbis(cyclopentadienyl)zirconium dichloride
 I bis(ethylcyclopentadienyl)zirconium dichloride
 F rac-dimethylsilylbis(tetrahydroindenyl)zirconium dichloride

10

For high viscosity fluids, the quantitative presence of the 1,1-connection
can be determined by the proton NMR of the olefinic region before
hydrogenation. The olefinic carbons in component A" and B" have very different
chemical shifts. In the olefinic region, each olefin class resonates in a
characteristic region assigned according to the table below:

15

- 83 -

Olefin type	Chemical shift range (ppm)	Number of protons
Vinyl	5.7 – 5.9	1
	4.8 – 5.3	2
1,2-disubstituted	5.3 – 5.6	2
Trisubstituted	4.8 – 5.3	1
Vinylidene (1,1-disubstituted)	4.6 – 4.8	2

The total olefinic integral can be subdivided as described, and gives quantitative concentrations for each olefin type.

- 5 Examples 33 to 35. Three poly-1-decene samples were prepared using similar procedures as Example 31, except at different temperatures and the products were analyzed by proton NMR before hydrogenation. The olefin distribution was determined as described above, and a typical olefinic region of a proton NMR spectrum was seen. From this proton NMR analysis, we
- 10 calculated the mole% unhydrogenated B in total PAO product. After hydrogenation, the B" will be converted to B component. The B component varied with the product viscosities and higher viscosity fluid had higher amount of component B in the end group (Table 5).

Table 5. Amount of structure B'' in poly-1-decene lube fluid by H-NMR

Example no.	33	34	35
Catalyst	F	F	F
Reaction temp., °C	100	70	45
KV100°C, cSt	35.13	150.39	497.01
KV40°C, cSt	254.27	1374.2 7	5174.28
Viscosity Index	187	224	278
Pour point, °C	-44	-30	-22
Bromine No. before hydrogenation	11.1	4.8	2.3
Mole% of component by H-NMR			
A''	78.9	66.2	41.2
B''	15.9	30.0	53.9
Others*	5.2	3.8	4.9

The product made in Example 32 was evaluated for EHL (elastohydrodynamic lubrication) traction performance using a Mini-Traction Machine (MTM) from PCS Instruments Ltd. This device uses a ball-on-plate configuration in which each is driven independently in order to vary sliding and rolling speeds. Under the varied sliding and rolling speeds, an EHL contact is formed between the ball and plate thereby separating the surfaces. The separated surfaces allow the lubricant shear effects to be measured, while temperature and contact pressure are varied to produce a comprehensive map of the fluid's behavior. The traction coefficient is a ratio of the EHL traction force measured to the normal force applied (F_t / F_n). The results are presented in Table I.

Table I

Pressure (GPa)	0.75	1	1.25
At 80 °C			
SpectraSyn 100	0.0151	0.0246	0.0308
SpectraSyn Ultra 150	0.013	0.0227	0.0299
Hydrogenated Example 32 PAO	0.0123	0.0222	0.0291
at 100 °C			
SpectraSyn 100	0.0118	0.0201	0.0263
SpectraSyn Ultra 150	0.0111	0.0191	0.0256
Hydrogenated Example 32 PAO	0.0106	0.0187	0.025
At 120 °C			
SpectraSyn 100	0.0088	0.0149	0.0205
SpectraSyn Ultra 150	0.0084	0.0143	0.02
Hydrogenated Example 32 PAO	0.0072	0.0129	0.0186

As a comparison of the traction coefficients of conventional PAO with
 5 100 cSt viscosity (at 100°C), SpectraSyn™ 100, a SpectraSyn Ultra™ 150
 and hydrogenated polyolefin of Example 32 shows, hydrogenated
 Example 32 lube has a consistently lower traction coefficient over a wide range of
 test pressure and temperature. Lower traction coefficient is more desirable and is
 advantageous for energy efficiency (Reference - Synthetic Basics, Benefits of
 10 Synthetic Lubricants in Industrial Applications, W. R. Murphy, D. A. Blain, A. S.
 Galiano-Roth, J. Synthetic Lubrication, Jan. 2002 (18) p.301).

Examples 36 to 41. This set of experiments was carried out in a
 continuous reactor. These runs demonstrated the use of non-coordinating anion
 (NCA) as activator, high lube yields and or narrow molecular weight distribution.
 15 1-Decene and toluene used in the runs were purified through a 5Angstrom
 molecular sieve. The metallocene catalyst used was
 dimethylsilylbis[tetrahydroindenyl]zirconium dimethyl. The activator used was
 N,N-dimethylanilinium tetra(pentafluorophenyl)borate (labeled as activator-A or
 NCA-A). A catalyst solution was prepared by pre-mixing equal molar of
 20 metallocene with the activator in toluene solution to give 0.8 micromole catalyst
 per ml of solution. The experiments were conducted in a series dual-reactor
 continuous solution process. Both of the reactors were 1-liter autoclave reactors.

- 86 -

All feeds were introduced into the first reactor. Both of the reactors were controlled at the same reaction temperature. The catalyst solution of 0.8 micromole/ml, a scavenger tri-n-octylaluminum (TNOA) solution, and purified 1-decene were continuously pumped into an one-liter stainless autoclave heated to
5 reaction temperature. Reaction product was continuously withdrawn from the autoclave, quenched, and washed with water. The organic layer was further distilled at high temperature to remove any C20 and lighter components. These data demonstrated that the NCA activator gave excellent catalyst productivities, conversions and or lube yields. The residual oil was then hydrogenated using 1
10 wt% Ni-on-Kieselguhr catalyst at 200°C, 800 psi (5.5MPa) hydrogen pressure for 4 hours. The bromine numbers for all samples after hydrogenation were much below 1. The reaction conditions and the hydrogenated finished lube properties are summarized in the following Table 6. This set of data demonstrates that a wide range of viscosities can be produced at high productivities. Also, these data
15 show that a wide range of mm contents, ranging from 86% to 51%, can be produced.

Carbon-13 NMR was used to determine the tacticity of the polyalphaolefins of the present invention. Carbon-13 NMR can determine the presence and quantity of triads present, denoted mm (meso, meso), mr (meso,
20 racemic) and rr (racemic, racemic). Extensive runs of mm or rr triads correspond to isotactic and syndiotactic polyalphaolefins, respectively. The tacticity of the polydecene was examined by carbon-13 NMR. Spectra for these samples were acquired in the following manner. The polymer samples were dissolved in chloroform-*d* for carbon analysis. Approximately 10-15mg/ml of chromium
25 acetylacetonate relaxation agent, Cr(acac)₃, was added to the carbon samples to enhance the data acquisition rate. Spectra were acquired using the 10mm broadband probe on either the Varian INOVA 300 or the Varian UnityPlus 500, with 8000-12000 scans acquired for each spectrum. Three carbon chemical shifts in polydecene and polydodecene evidence tacticity dependence: the S_{αα} backbone
30 methylene, and the 8B₈ and 7B₈ methylenes (for decene) and the 10B₁₀ and 9B₁₀ methylenes (for dodecene) on the short chain branches (SCBs). A peak

- 87 -

deconvolution was performed on the 8B₈ or 10B₁₀ peaks, and assigned to monomer stereochemical triads according to the paper by I. Kim, J.-M. Zhou, and H. Chung, *Journal of Polymer Science: Part A: Polymer Chemistry* **38** (2000) 1687-1697. Figure 3 in the paper by Kim, et al. shows how the chemical shift
5 offset of the relevant branch methylene varies with branch length. Based on the trends shown, we assumed that the dodecene- and decene-based SCBs were both of sufficient length that the chemical shift assignments for the 8B₈ and 10B₁₀ methylenes would be interchangeable. It also follows from this figure, that copolymers of different α -olefins will have spectra complicated by monomer
10 sequence effects. Furthermore, several of the samples are low M_n materials, and contributions from chain end carbons overlap the region of interest. Where possible, the end group resonances were identified, integrated. Their contribution to the peaks were removed from the analysis. The deconvolutions were executed with Acorn NMR Inc.'s NutsPro NMR data analysis software, using an 85/15
15 Lorentzian/Gaussian lineshape. The component peaks were lumped together into clusters according to the *mm* (~34.65-35.4 ppm), *mr* (~34.2-34.65 ppm), and *rr* (33.8-34.2 ppm) triad assignments, and fit by least-squares minimization to a Bernoullian distribution. The probability of racemic addition, P_r, is the adjustable parameter. The exact chemical shift offset cut points for the stereo triad regions
20 may vary somewhat as a function of solvent type, temperature, sample concentration, and relaxation agent concentration. A typical spectrum of this region was shown in Figure 8.

End group-related resonances appear in the 42-45 ppm and 35-36.5 ppm regions. Visual inspection of low-M_n materials suggests that there are three endgroup
25 carbons contributing to the 8B₈ or 10B₁₀ region, with one carbon in each of the *mm*, *mr*, and *rr* triad regions. As a first-order approximation to end group correction, the end group resonances (where detected) in the 42-45 and 35-36.5 ppm regions were integrated by deconvolution. The integral values so obtained were averaged and subtracted from each of the *mm*, *mr*, and *rr* triad areas. In general, the quality of fit
30 improves upon such correction. The carbon-13 data is reported in Table 6 and is reported in mole %.

- 88 -

Branch concentrations were also determined by NMR spectroscopy. The characteristic shift ranges for the carbon spectra are methyl branch: 20-15 ppm, propyl branch: 15-14.2 ppm, butyl and longer branches: 14.2-13 ppm, ethyl branches: 12-8 ppm. In the proton spectra, the methyl protons resonate upfield of 1 ppm, and signals
5 from different branch lengths can often be resolved sufficiently to allow quantification by branch length. A typical spectrum of this region was seen. In the carbon spectra, the integrals of the branch methyl signals can be divided by the total spectral integral, and the result expressed in terms of branches per 1000 carbons. The same holds true for the proton spectrum, although the integrals need to be corrected for
10 the proton multiplicity of the relevant carbon (e.g. CH, CH₂, or CH₃).

Table 6. Reaction Conditions for Ex 36 to 41

Ex. No	36	37	38	39	40	41
Rxr Tem. (°C)	50	60	70	80	90	100
1-decene (ml/min)	40	40	40	40	40	40
Cat rate (mol/min)	2.39E-06	2.39E-06	3.73E-06	3.73E-06	3.73E-06	3.73E-06
TNOA (mol/min)	7.57E-10	7.57E-10	9.10E-10	9.10E-10	9.10E-10	9.10E-10
Yield (g/min)	21.9	24.14	25.43	28.04	29.19	na
Conversion, wt%	73.27	80.76	85.08	93.84	97.67	na
Productivity g-lube/g cat.	2.19E+04	2.41E+04	1.63E+04	1.80E+04	1.87E+04	na
KV at 100°C, cSt	295.21	169.07	79.49	26.54	14.89	11.2
KV at 40°C, cSt	3002.3	1618	696.8	197.2	99.7	70.4
Viscosity Index	249	225	197	169	155	150
Pour point, °C	-30	-30	-33	-48	-52	-57
Bromine number after hydrogenation	0.09	0.05	0.00	0.00	0.05	0.22
Mw	10732	7579	4823	2586	1760	1493
Mw/Mn	1.758	1.671	1.516	1.317	1.161	1.14
Tacticity by C13 NMR, in mole %						
mm	86	86	76	69	62	51
mr	13	14	22	28	33	41
rr	1	0.1	2	3	1	8
Pr	0.07	0.07	0.13	0.17	0.21	0.29
Ratio of mm/mr	6.6	6.1	3.5	2.5	1.9	1.2
CH3 per 1000 Carbons Measured by C13-NMR						
	1.9	2.7	3.9	8.1	13.0	16.2

The Example 36 and Example 37 products were subjected to a tapered roller bearing shear test (CEC L-45-T/C), a severe viscosity shear stability test, for 20 hours. At the end of the test, the Example 36 fluid lost only 0.77% of its original viscosity. The Example 37 fluid lost -0.20% of its original viscosity. This viscosity change is well within the experimental error of viscosity measurement. Such outstanding shear is not known for other fluids of similar viscosity range. This property can be significant for many high performance

- 90 -

application, such as in the formulation of automotive engine, industrial, gear oils and grease formulation, etc.

Example 42 demonstrates the use of the dihalide form of a metallocene catalyst with an NCA activator. The metallocene used was catalyst F. A reaction flask containing containing 50 gram purified 1-decene and 31.74 mg tri-siobutylaluminum (TIBA) was heated to 30°C. To this flask a catalyst solution containing 0.912 mg F catalyst and 0.801 mg activator-A in 20 ml toluene was added. After 20 hours of reaction at this temperature, 2 ml isopropanol was added. The reaction mixture was worked up by water wash. The product was distilled at 160°C/1 mm-Hg vacuum to remove any light ends. The residual lube oil properties are summarized in Table 7. Examples 43 to 46 are similar to Example 42 except at different reaction temperature. Example 47 is similar to Examples 42, except catalyst I was the metallocene used.

15

Table 7. 1-Decene polymerization by metallocene and NCA activator-A

Example No.	42	43	44	45	46	47
Reaction Temp, C	30-40	30-65	70	120	140	70
Solution weight in reactor						
1-decene, grams	50	50	50	50	50	50
TIBA, mg	31.74	63.6	63.6	63.6	63.6	63.6
Toluene, grams	0	0	20	20	20	20
Metallocene, mg	0.912	0.912	0.954	0.918	0.912	0.697
NCA-A activator, mg	0.801	3.205	3.205	3.205	3.205	3.205
wt% Selectivity to Lube	95.7	97.0	96.2	80.6	73.0	94.0
KV at 100°C, cSt	1095.2	194.61	72.53	8.43	6.2	40.08
Viscosity Index	310	226	191	151	145	167
Pour Point, °C		-28	-38	<-56		
Mw	25151	9094	4718	1358		
Mw/Mn	2.05	2.04	1.62	1.22		

These Examples 42 to 46 demonstrate that high quality lube can be produced in high yields. The lubes have high VI and very narrow Mw/Mn. Also, high selectivity to lube can be obtained with these catalysts.

20

- 91 -

For Example 48 and 49 in Table 8, the metallocene was catalyst F. For Example 50 in Table 8 the metallocene was catalyst I.

Table 8. 1-Decene reaction over metallocene and activator-B as activator

Example No.	48	49	50
Reaction Temp, C	70	140	70
Solution weight in reactor			
1-decene, grams	50	50	50
TIBA, mg	65	65	65
Toluene, grams	20	20	20
Metallocene, mg	0.456	0.456	0.348
NCA activator, mg	0.922	0.922	0.922
wt% Selectivity to Lube	99.4	69.1	93.6
Kinematic Viscosity at 100°C, cSt	83.71	6.76	39.03
Viscosity Index	194	162	170

- 5 Examples 51 to 63 in Table 9 demonstrate that other metallocene catalysts activated with MAO or NCA activators can produce high quality fluids in high yields. The procedures for these examples were similar to Examples 27 to 32 when MAO was the activator or similar to Example 42 when NCA was used as activator. [Note – these samples were not hydrogenated.] Examples 51 to 56
- 10 demonstrate that a wide range of catalysts can be used to produce polymers with high degree of mm triads. These catalysts include the racemic catalysts including Catalysts F, E, and T; and highly substituted catalyst U. Examples 59 to 62 demonstrate that using meso type catalysts with no hydrogen produces fluids with lower degree of mm triads (e.g. less than 40%) and bromine number of up to 6
- 15 before hydrogenation. This is unexpected when compared to US6706828.

- 92 -

Table 9. Polymer fluids from 1-decene by different metallocene catalysts –
reaction conditions, results, product properties and tacticity analysis.

Ex. no.	Catalyst*	Reaction temp. °C	% Selectivity to lube	KV@ 100 °C, cS	VI	Pour point, °C	Br. No**.	Mole% analyzed by C13-NMR				
								mm	mr	rr	Pr	mr
51	F	50	96	295.2	249	-30	2.8	87	5	9	0.05	1
52	E	50	100	1028.96	306	-19	0.8	98	2	0	0.01	
53	E	75	94	368.05	252	na	0.5	83	16	1	0.09	
54	E	100	74	92.61	200	-39	4.3	65	31	4	0.2	
55	E	125	48	41.94	187	-50	10.5	64	32	4	0.2	
56	M	70	95	32.05	170	na	10.2	42	46	13	0.36	
57	T	70	88	3044.88	165	na	na	88	12	4	0.06	
58	U	70	99	101.67	193	-38	3.9	31	49	2	0.44	1
59	V	70	99	2339.93	354	na	na	34	49	17	0.41	
60	W**	50	99	3758.42	380	na	na	34	49	17	0.41	
61	W	50	99	1383.62	323	-27	na	34	49	17	0.42	
62	W	70	98	861.34	296	-30	na	33	49	18	0.43	
63	W	125	76	117.72	206	-41	5.7	34	49	17	0.42	

*Catalyst type

T Rac-dimethylsilylbis(2-methylindenyl)ZrCl₂5 U Bis(tetramethylcyclopentadienyl)ZrCl₂V meso-dimethylsilylbis(2-methylindenyl)ZrCl₂W meso-ethylenebis(indenyl)ZrCl₂

** The samples in this Table were not hydrogenated and the Bromine numbers were measured before hydrogenation.

10 *** NCA activator A was used.

Examples 64 to 69 demonstrate the advantages of hydrogenation of the polyalpha-olefins produced from the polymerization step. In this hydrogenation reaction, the Example 52 polyalpha-olefin was charged into an autoclave together with 3 wt% of a Ni (~60%) on Kieselguhr hydrogenation catalyst, purged with

- 93 -

hydrogen to remove air and pressurized with hydrogen to 800 psi (5.5MPa) and heated to 250°C with agitation. The sample was allowed to hydrogenated for different period of reaction time. All the hydrogenated samples have bromine number less than 0.5. Other properties of the fluids are summarized in Table 10.

- 5 These data demonstrate that post-polymerization hydrogenation not only reduces the bromine number to below 1, but also we can produce polyalpha-olefins with 26 to 95 mole% of mm triads. Furthermore, comparing the DSC of the hydrogenated samples versus the unhydrogenated sample, the hydrogenated samples had reduced heat of of melting (ΔH_m , j/g) and heat of crystallization
- 10 (ΔH_c , j/g). Hydrogenation of the sample can reduce the heat of melting and crystallization as shown in Table 10.

Table 10.

Example No.	52	64	65	66	67	68	69
time, hrs	Starting PAO	1	2	4	7	12	24
Mole% diads by C13-NMR							
mm	98	95	72	57	45	36	26
mr	2	3	15	20	41	38	47
rr	0	3	13	22	14	27	26
Pr	0.01	0.02	0.13	0.21	0.33	0.43	0.5
Mole % mm change	0	3	26	41	53	62	72
DSC							
ΔH_m , j/g	25.01	22.69	21.5 8	13.9 8	2.05 1	0	0
ΔH_c , j/g	19.94	21.38	15.6 8	18.1 3	1.68 3	0	0
%Hm decrease	0.0	9.3	13.7	44.1	91.8	100	100

- 15 DSC (Differential scanning calorimetry) was measured using a Perkin Elmer DSC. 10 mg samples was heated at 10°C/minutes to 150°C and then cooled down to -100°C at 10°C per minute. The total heat of melting and crystallization during cooling was measured by integrating the heat corresponding

- 94 -

to the melting and crystallization peak using the standard software provided by Perkin Elmer.

Example 70 to 74 were carried out similarly to Ex. 31, except 1-hexene
 5 was used in each experiment. The amounts of catalyst and activators used, together with product properties are summarized in Table 11. This set of examples demonstrated that other alpha-olefins can be used to produce high quality fluids.

10 Table 11.

Example	70	71	72	73	74
temperature, °C	45	70	100	125	170
reaction time, hr	22	20	21	21	24
grams hexene feed	91	90	90	90	90
grams of MAO solution	0.117	0.0585	0.0585	0.0585	0.0585
molar ratio Al/Zr	300	250	250	250	250
KV100°C, cSt	1535.53	564.63	75.09	24.3	8.64
KV40°C, cSt	42368.3	12822.88	1086.46	253.28	59.27
Viscosity Index	239	198	132	112	108
pour point, °C					
Wt% Conversion	93	92	88	87	na

Examples 75 to 78 in Table 12 are similar to Example 42 to 46, except 1-hexene was used as starting material. These experiments demonstrated that 1-hexene can be polymerized into high quality fluids using metallocene and NCA
 15 activators and trialkylaluminum compounds as co-activator.

- 95 -

Example	75	76	77	78
Reaction Temperature, °C	31	80	100	120
Conversion, wt%	89.4	93.5	86.5	49.1
Lube Properties				
KV100 °C, cSt	269.21	53.57	25.78	12.02
KV40 °C, cSt	4900.2	661.38	269.58	96.66
Viscosity Index	176	132	115	105
Pour Point, °C	-24	-40	-32	-43
Mn	2519	1613	1211	912
Mw/Mn	3.025	1.667	1.315	1.287
Mole% Olefin Types in Unhydrogenated Polyalpha-Olefins				
Vinylidene	67.4	71.4	72.3	72.2
1,2-disubstituted	15.7	11.6	8.8	5
tri-substituted	16.9	17	18.9	22.8
vinyl	0	0	0	0

Using catalyst E (rac-ethylenebis(indenyl) ZrCl₂) at different reaction temperature and similar reaction procedures, we obtained products with useful 100°C viscosities ranging from 42 cSt to 1029 cSt (Examples 79 to 82 of Table 13) without any hydrogen.

Table 13.

Example no	Reaction Temp., °C	Kv@100 °C, cS	Kv@40 °C, cS	VI	Pour point, °C	mm	mr	rr	P
79	50	1028.96	12399	306	-19	0.98	0.02	0	0.0
80	75	368.05	4009.3	252	na	0.83	0.16	0.01	0.0
81	100	92.61	842.29	200	-39	0.65	0.31	0.04	0
82	125	41.94	316.73	187	-50	0.64	0.32	0.04	0

The product composition produced in this invention is different from the compositions produced in US6706828 and WO 02/14384. Our invention using metallocene catalysts with MAO or NCA activator optionally with co-activators in low or no hydrogen (usually less than 200 psi hydrogen preferably less than 50 psi or no hydrogen) during the polymerization step. In contrast, US6706828 and WO

- 96 -

02/14384 produced products from meso catalysts in the presence of hydrogen, as reported in Example D of US 6,706,828 or Example J and K in WO 021484. We compared the bromine number of polymers produced in our invention vs Examples 1, 2, 8, 9, 10, 11, and 12 of US 6,706,828.

5 In Comparative example 1, the reaction was conducted in the presence of 200 psi hydrogen and catalyst T (rac-dimethylsilylbis(2-methy-1-lindenyl)zirconium dichloride, similar to Example D of US6706828. The results are summarized in Table 12. The polyalpha-olefin sample was analyzed for the Z mole% of B components in C30 fraction. The amount of this Z mole% was
10 plotted in Figure 2.

Comparative Examples 2 and 3 were similar to Comparative Example 1, except the reaction hydrogen pressure was 100 and 50 psi. The polyalpha-olefin sample was then analyzed for the mole% of B components in C30 fraction. Comparative Example 4 was similar to Comparative Example 1, except the
15 reaction was carried out at 110°C.

Table 12. Comparative Examples using rac-dimethylsilyl-bis(2-methylindenyl)zirconiumdichloride

	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4
Temperature, °C	100	100	100	110
Hydrogen pressure, psi	200	100	50	200
KV@100C, cSt	89.5	466.2	598.01	59.10
% B in C30 fraction	5.7	4.3	2.2	7.5
CH ₃ per 1000 C by C13 NMR	14.2	2.7	2.5	na
Viscosity Index	194	266	281	
Pour Point, °C	-36	-21	-21	

The amount of B mole% for the Comparative Examples 1-4 versus the
20 amount of B mole% by Examples 27 to 35 was plotted.

Also, the amount of isolated CH₃ attached to a tertiary CH was analyzed by Carbon 13 NMR method and are summarized in Table 12. We compared the amount of CH₃ per 1000 Carbons of the Comparative Examples 1 to 3 produced in the presence of hydrogen during polymerization to the CH₃ per 1000

- 97 -

Carbons of Examples 36 to 41 produced without hydrogen during polymerization. The resulting graph clearly showed that the compositions of Examples 36 to 41 have much lower methyl groups per 1000 Carbons. A lower amount of methyl groups is advantageous to the lube properties, as we have shown earlier that the trimer C₃₀H₆₂ without extra methyl group (Compound B) has better viscometrics, especially VI, than trimers in current PAO which has extra short chain branches. Furthermore, less CH₃ branches imply less tertiary hydrogen in the hydrocarbon structure. This tertiary hydrogen is more susceptible toward oxidative degradation. This implies that compositions with less CH₃ branches and less tertiary hydrogen are less susceptible to oxidative degradation.

Table 13 shows that the types of unsaturation from Comparative Example 4 are very different from the types of unsaturations produced from Example 33 or 76. In Comparative Example 4 which used 200 psi hydrogen, 52% of the unsaturated double bonds were tri-substituted olefins. In contrast, in Example 33 or 76, where no hydrogen was added to the reactor, only 10 to 17% of the unsaturation double bonds are tri-substituted olefins by either MAO or NCA as co-activator.

Table 13. Comparison of unsaturation types.

	Comparative Example 4	Example 33	Example 76
KV at 100°C, cSt	59.10	35.1	53.57
Mole% trisubstituted olefins	52	10	17.0
Mole% vinylidene	41	71	71.4
Mole% 1,2-disubstituted olefins	7	19	11.6

20

In preferred embodiments, the polyalpha-olefins produced herein have higher bromine numbers, the amount of tri-substituted olefins are significantly lower than prior art, and/or the amount of vinylidene + 1,2-disubstituted olefins are higher. In further preferred embodiments the PAO's produced herein have higher amounts of B'' structures believed to be formed from head-to-head connection in the polymer product. 3. In further preferred embodiments the

25

- 98 -

PAO's produced herein have high mole% of mm content (>40%). In further preferred embodiments the PAO's produced herein have higher mole% of B'' formed by head-to-head connection. This is indicated by the higher C30-B component by GC or the un-expected higher mole% of the di-substituted olefins of the B'' structure.

These structural differences for the polyalpha-olefins persist after hydrogenation step(s) to remove the double bond, as is usually practiced to further improve lube base stock property. After hydrogenation, the examples above had lower amount of isolated CH₃ per 1000 carbons in the polymers than the Comparative Examples, even when the same polymerization catalysts were used. In our examples, we preferred to hydrogenate the sample after the polymerization. During this hydrogenation step, we can tailor the mole% of mm content in the polymer. By selection of hydrogenation condition, we can maintain the same mole% of mm content or we can reduce the mole% mm content to significantly below 40.

Exmaples 90, 91 and 92 illustrate the presence of a minor amount of ethylene in the polymerization. The procedure, catalyst, activator, and reaction conditions were the same as for Example 46, except that ethylene was present.

- 99 -


Ex. No.	90	91	92
Polymerization temperature (°C)	80	80	80
1-decene feed rate (ml/min)	40.00	40.00	40.00
Ethylene feed rate (standard liter per minute)	0.18	0.01	0.35
Catalyst/activator combination feed rate (mol/min)	3.73E-06	2.39E-06	2.39E-06
TNOA feed rate (mol/min)	9.10E-10	9.10E-10	9.10E-10
Yield (g/min)	29.5	29.0	30.5
Conversion (%)	98	97	100
Productivity (g lube/g catalyst)	1.89E+04	2.90E+04	3.05E+04
Mn (kg/mol)	1.15	1.52	1.57
Mw (kg/mol)	1.31	2.00	1.70
Mw/Mn	1.14	1.32	1.09
Wt% C2 in feed	3.63	0.21	6.87
Kv at 100 °C, cSt	11.67	22.81	15.58
Kv at 40 °C, cSt	69.94	150.44	101.19
viscosity index	151	166	153

As is apparent from the foregoing general description and the specific embodiments, while forms of the invention have been illustrated and described, various modifications can be made without departing from the spirit and scope of the invention. Accordingly, it is not intended that the invention be limited thereby.

-100-

CLAIMS:


1. A polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has:
- a) 40 mole % or more of mm triads,
 - b) a Bromine number of Y or greater, where Y is equal to $89.92 * (V)^{-0.5863}$, where V is the Kinematic Viscosity of the polyalpha-olefin measured at 100°C in cSt,
 - c) 1,2 disubstituted olefins present at 7 mole % or more, or at Z mole % or more, where $Z = 8.420 * \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt, and wherein the 1,2-disubstituted olefins are represented by the formula:



- where the olefinic 1,2-disubstituted carbons are position between Ca and Cb or occasionally between Cb and Cc, where j, k, and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and
- d) a pour point of less than 0°C or less.

2. A polyalpha-olefin comprising more than 50 mole % of one or more C5 to C24 alpha-olefin monomers where the polyalpha-olefin has:
- a) 40 mole % or more of mm triads,
 - b) a Bromine number of 1.8 or less,
 - c) comprises Z mole % or more of units represented by the formula:

-101-



where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt, and

d) a pour point of less than 0°C or less.

3. The polyalpha-olefin according to either claim 1 or 2, wherein the polyalpha-olefin has an Mw/Mn of greater than 1 to 3.5.
4. The polyalpha-olefin according to any one of claims 1 to 3, wherein the polyalpha-olefin has an Mw/Mn of greater than 1 to 2.5.
5. The polyalpha-olefin according to any one of claims 1 to 4, wherein the polyalpha-olefin has a Kinematic viscosity at 100°C of from 1.5 to 5000 cSt.
6. The polyalpha-olefin according to any one of claims 1 to 5, wherein the polyalpha-olefin has a Kinematic viscosity at 100°C of from 2 to 3000 cSt.
7. The polyalpha-olefin according to any one of claim 1 to 6, wherein the polyalpha-olefin has a Kinematic viscosity at 100°C of from 3 to 1000 cSt.
8. The polyalpha-olefin according to any one of claims 1 to 7, wherein the polyalpha-olefin has a Kinematic viscosity at 40°C of from 4 to 100,000 cSt.

-102-

9. The polyalpha-olefin according to any one of claims 1 to 8, wherein the polyalpha-olefin has a Kinematic viscosity at 40°C of from 6 to 50,000 cSt.
10. The polyalpha-olefin according to any one of claims 1 to 9, wherein the polyalpha-olefin has a Kinematic viscosity at 40°C of from 10 to 30,000 cSt.
11. The polyalpha-olefin according to any one of claims 1 to 10, wherein the polyalpha-olefin has a Viscosity Index of 100 or more.
12. The polyalpha-olefin according to any one of claims 1 to 11, wherein the polyalpha-olefin has a Viscosity Index of 120 or more.
13. The polyalpha-olefin according to any one of claims 1 to 12, wherein the polyalpha-olefin has a Viscosity Index of 130 or more.
14. The polyalpha-olefin according to any one of claims 1 to 13, wherein the polyalpha-olefin has a Viscosity Index between 120 and 450.
15. The polyalpha-olefin according to any one of claims 1 to 14, wherein the polyalpha-olefin has a pour point of -30°C or less.
16. The polyalpha-olefin according to any one of claims 1 to 15, wherein the polyalpha-olefin has a pour point between -10°C and -80°C.
17. The polyalpha-olefin according to any one of claims 1 to 16, wherein the polyalpha-olefin has a pour point between -15°C and -70°C.
18. The polyalpha-olefin according to any one of claims 1 to 17, wherein the polyalpha-olefin has a weight average molecular weight of 100,000 g/mol or less.
19. The polyalpha-olefin according to any one of claims 1 to 18, wherein the polyalpha-olefin has a weight average molecular weight of 100 to 100,000 g/mol.

-103-

20. The polyalpha-olefin according to any one of claims 1 to 19, wherein the polyalpha-olefin has a weight average molecular weight of 280 to 50,000 g/mol.
21. The polyalpha-olefin according to any one of claims 1 to 20, wherein the polyalpha-olefin has a weight average molecular weight of 336 to 40,000 g/mol.
22. The polyalpha-olefin according to any one of claims 1 to 21, wherein the monomers are selected from the group consisting of 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene, 1-tridecene, 1-tetradecene, 1-pentadecene, 1-hexadecene, 1-heptadecene, 1-octadecene, 1-nonadecene, 1-eicosene, 1-uneicosene, 1-docosene, 1-tricosene, 1-tetracosene, 1-pentacosene, 1-hexacosene, 4-methyl-1-pentene, 4-phenyl-1-butene, and 5-phenyl-1-pentene.
23. The polyalpha-olefin according to any one of claims 1 to 22, wherein the monomers are selected from the group consisting of 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene, 1-tridecene, 1-tetradecene, 1-pentadecene and 1-hexadecene.
24. The polyalpha-olefin according to any one of claims 1 to 23, wherein the monomers are selected from the group consisting of 1-hexene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene and 1-hexadecene.
25. The polyalpha-olefin according to any one of claims 1 to 24, wherein the polyalpha-olefin comprises octene, decene, and dodecene derived monomers.
26. The polyalpha-olefin according to any one of claims 1 to 25, wherein the polyalpha-olefin has a dielectric constant of 2.5 or less (1 kHz at 23 °C).
27. The polyalpha-olefin according to any one of claims 1 to 26, where ethylene, propylene and butene monomers are present at less than 1 weight %.

-104-

28. The polyalpha-olefin according to any one of claims 1 to 27, where the monomers having 5 to 24 carbon atoms are present at 60 mole% or more.
29. The polyalpha-olefin according to any one of claims 1 to 28, where the monomers having 5 to 24 carbon atoms are present at 70 mole% or more.
30. The polyalpha-olefin according to any one of claims 1 to 29, where the monomers having 5 to 24 carbon atoms are present at 80 mole% or more.
31. The polyalpha-olefin according to any one of claims 1 to 30, where the monomers having 5 to 24 carbon atoms are present at 90 mole% or more.
32. A use of the polyalpha-olefin defined in any one of claims 1 to 31, either by itself or by blending with another fluid, in a high performance automotive engine oil formulation, in an industrial oil formulation, in a personal care application, or as blend stock with a Gr I, II, III, III+ or GTL derived lube base stock in an industrial oil, an automotive engine oil, or a gear oil.
33. A lubricating composition comprising the polyalpha-olefin of any one of claims 1 to 31 and a conventional base stock.
34. A process to produce a polyalpha-olefin comprising:
- 1) contacting in a reactor at least one alpha-olefin monomer having 5 to 24 carbon atoms with a metallocene catalyst compound and an activator, and optionally an alkyl-aluminum compound, under polymerization conditions wherein hydrogen, if present, is present at a partial pressure of 1379 kPa or less, based upon the total pressure of the reactor, and wherein the alpha-olefin monomer having 5 to 24 carbon atoms is present at 10 volume % or more based upon the total volume of the catalyst, monomers, and any diluents or solvents present in the reactor;
- wherein i) the metallocene catalyst is a bridged, substituted or unsubstituted cyclopentadienyl, indenyl, or fluorenyl compound, the activator is a non-coordinating anion activator, and the feed stream comprises less than 300 ppm of heteroatom containing

-105-

compounds, or ii) the metallocene is racemic and hydrogen, if present, is present at a partial pressure of 1,379 kPa (200 psia) or less; and


2) obtaining a polyalpha-olefin comprising at least 50 mole% of a C5 to C24 alpha-olefin monomer where the polyalpha-olefin has:

a) a Kinematic viscosity at 100°C of 5000 cSt or less,

b) 40 mole % or more of mm triads,

c) a pour point of less than 0°C, and

d) 1, 2-disubstituted olefins are present at 7 mole% or more, or at Z mole% or more, wherein the 1,2-disubstituted olefins are represented by the formula:



where j, k and m are each, independently, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22, n is an integer from 1 to 350, and where $Z = 8.420 \cdot \text{Log}(V) - 4.048$, where V is the kinematic viscosity of the polyalpha-olefin measured at 100°C in cSt.

35. The process of claim 34 further comprising the following steps:

3) optionally treating the polyalpha-olefin to reduce heteroatom containing compounds, prior to contacting with a hydrogen catalyst, to less than 600 ppm,

4) optionally separating the polyalpha-olefins from solvents or diluents;

5) contacting the polyalpha-olefin with hydrogen and a hydrogenation catalyst, and

4) obtaining a polyalpha-olefin having a bromine number less than 1.8.

-106-

36. The process of claim 35 wherein the polyalpha-olefin is treated to remove heteroatom containing compounds prior to contacting with the hydrogen.
37. The process of claim 36 wherein the treated polyalpha-olefin comprises 100 ppm of heteroatom containing compounds or less.
38. The process of claim 34 or 35 further comprising a co-activator selected from the group consisting of methylalumoxane and modified methylalumoxane.
39. The process of claim 34 wherein the activator comprises one or more of N,N-dimethylanilinium tetra(pentafluorophenyl)borate, N,N-dialkylphenylanilinium tetra(pentafluorophenyl)borate (where the alkyl is a C1 to C18 alkyl group), trityl tetra(pentafluorophenyl)borate, tris(pentafluorophenyl)boron, tri-alkylammonium tetra(pentafluorophenyl)borate (where the alkyl is a C1 to C18 alkyl group), and tetra-alkylammonium tetra(pentafluorophenyl)borate (where the alkyl is a C1 to C18 alkyl group).
40. The process of any one of claims 34 to 39, wherein the metallocene comprises one or more of dimethylsilylbis(cyclopentadienyl)zirconium dichloride; isopropylidenebis(cyclopentadienyl)zirconium dichloride; rac-ethylenebis(1-indenyl)zirconium dichloride; rac-dimethylsilylbis(tetrahydroindenyl)zirconium dichloride; diphenylmethylidene(cyclopentadienyl)(9-fluorenyl)zirconium dichloride; bis(indenyl)zirconium dichloride; cyclopentadienyl(indenyl)zirconium dichloride; bis(1,2,4-trimethylcyclopentadienyl)zirconium dichloride; bis(1,3-dimethylcyclopentadienyl)zirconium dichloride; bis(tetramethylcyclopentadienyl)zirconium dichloride; and bis(pentamethylcyclopentadienyl)zirconium dichloride.
41. The process of any one of claims 34 to 40, where an alkylaluminum compound is present and the alkylaluminum compound is represented by the formula: R_3Al , where each R is, independently, selected from the group consisting of methyl, ethyle, n-propyl, iso-propyl, iso-butyl, n-butyl, t-butyl, n-pentyl, iso-pentyl, neopentyl, n-hexyl, iso-hexyl, n-

-107-

heptyl, iso-heptyl, n-octyl, iso-octyl, n-nonyl, n-decyl, n-undecyl, n-dodecyl, n-tridecyl, n-tetradecyl, n-pentadecyl, n-hexadecyl, n-heptadecyl, n-octadecyl, and their iso-analogs.

42. The process of any one of claims 34 to 41, wherein the process is a continuous process.

43. The process of claim 42 wherein the process is a continuous process comprising:

- a) continuously introducing a feed stream comprising at least 10 mole% of the one or more C5 to C24 alpha-olefins into a reactor,
- b) continuously introducing the metallocene compound and the activator into the reactor,
- c) optionally continuously introducing co-activator into the reactor, and
- d) continuously withdrawing the polyalpha-olefin from the reactor.

44. The process of claim 43 further comprising maintaining a concentration of hydrogen in the reactor of 1000 ppm or less by weight.

45. The process of claim 43 or 44 wherein the process further comprises:

- 1) optionally, continuously treating the polyalpha-olefin to reduce heteroatom containing compounds to less than 600 ppm,
- 2) continuously contacting the polyalpha-olefin with hydrogen and a hydrogenation catalyst
- 3) continuously obtaining a polyalpha-olefin having a bromine number less than 1.8.

46. The process of any one of claims 34 to 45 wherein two monomers having 5 to 18 carbon atoms are present in the polyalpha-olefin.

47. The process of any one of claims 34 to 46, wherein the temperature in the reactor is from -10°C to 250 °C.

48. The process of claim 47 wherein the temperature is from 30°C to 220 °C.

-108-

49. The process of claim 47 wherein the temperature is from 50°C to 180 °C.
50. The process of claim 47 wherein the temperature is from 70°C to 150 °C.
51. The process of any one of claims 34 to 50, wherein the pressure in the reactor is from 0.1 to 100 atmospheres.
52. The process of claim 51 wherein the pressure is from 0.5 to 75 atmospheres.
53. The process of claim 51 wherein the pressure is from 1 to 50 atmospheres.
54. The process of any one of claims 34 to 53, wherein the monomers, metallocene and activator are contacted for a residence time of 1 second to 100 hours.
55. The process of any one of claims 34 to 53 wherein the monomers, metallocene and activator are contacted for a residence time of 30 seconds to 50 hours.
56. The process of any one of claims 34 to 53 wherein the monomers, metallocene and activator are contacted for a residence time of 2 minutes to 6 hours.
57. The process of any one of claims 34 to 53 wherein the monomers, metallocene and activator are contacted for a residence time of 1 minute to 1 hour.
58. The process of any one of claims 34 to 57 wherein solvent or diluent is present.
59. The process of claim 58 wherein the solvent or diluent is selected from the group consisting of butanes, pentanes, hexanes, heptanes, octanes, nonanes, decanes, undecanes, dodecanes, tridecanes, tetradecanes, pentadecanes, hexadecanes, benzene, toluene, o-xylenes, m-xylenes, p-xylenes, ethylbenzene, isopropylbenzene, and n-butylbenzene.
60. The process of claim 58 wherein the solvent or diluent comprises toluene, xylenes, or ethylbenzene.

61. The process of any one of claims 34 to 60, wherein the reactor is a continuous stirred tank reactor.
62. The process of any one of claims 34 to 60, wherein the reactor is a continuous tubular reactor.
63. The process of any one of claims 34 to 41, wherein the reactor is a batch reactor.
64. The process of any one of claims 54 to 57 where co-activator is present where the monomers are contacted with the metallocene compound and the activator.
65. The process of any one of claims 34 to 64 where the monomers are contacted with the metallocene compound and the activator in the solution phase or in a slurry phase.
66. The process of any one of claims 34 to 65, wherein the monomers are contacted with an alkylaluminum compound prior to being introduced into the reactor.
67. The process of any one of claims 34 to 66 where the metallocene and activator are combined with an alkylaluminum compound prior to entering the reactor.
68. The process of claim 66 or 67 where the alkylaluminum compound is represented by the formula: R_3Al , where each R is independently a C1 to C20 alkyl group and can be n-alkyl or iso-alkyl group.
69. The process of claim 68 wherein the R groups are independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, isobutyl, n-butyl, pentyl, isopentyl, n-pentyl, hexyl, isohexyl, n-hexyl, heptyl, octyl, isooctyl, n-octyl, nonyl, isononyl, n-nonyl, decyl, isodecyl, n-decyl, undecyl, isoundecyl, n-undecyl, dodecyl, isododecyl, and n-dodecyl.

-110-

70. The process of any one of claims 34 to 65, where an alkylaluminum compound is present and the compound is tri-isobutylaluminum, tri-n-octylaluminum, tri-n-hexylaluminum, or tri-n-dodecylaluminum.

71. The process of any one of claims 34 to 70, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst selected from the group consisting of supported Group 7, 8, 9, and 10 metals.

72. The process of any one of claims 34 to 71, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst selected from the group consisting of one or more of Ni, Pd, Pt, Co, Rh, Fe, Ru, Os, Cr, Mo, and W, supported on silica, alumina, clay, titania, zirconia, or mixed metal oxide supports.

73. The process of claim 72 where the hydrogenation catalyst is nickel supported on keislegur, silica, alumina, clay or silica-alumina.

74. The process of any one of claims 34 to 73, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst at a temperature from 25 to 350°C.

75. The process of any one of claims 34 to 73, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst at a temperature from 100 to 300°C.

76. The process of any one of claims 34 to 73, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst for a time period from 5 minutes to 100 hours.

77. The process of any one of claims 34 to 73, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst for a time period from 5 minutes to 24 hours.

-111-

78. The process of any one of claims 34 to 77, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst at a hydrogen pressure of from 25 psi to 2500 psi.

79. The process of any one of claims 34 to 77, wherein the polyalpha-olefin is contacted with hydrogen and a hydrogenation catalyst at a hydrogen pressure of from 100 to 2000 psi.

80. The process of claim 34 where the feed olefins are contacted with molecular sieve, activated alumina, silica gel, and or purifying clays to reduce the heteroatom-containing compounds in the feed to below 100 ppm.

81. The process of claim 34 where the feed olefins are contacted with molecular sieve, activated alumina, silica gel, oxygen removing catalyst, and or purifying clays to reduce the heteroatom-containing compounds in the feed to below 50 ppm.

82. The process of claim 34 where the feed olefins are contacted with molecular sieve, activated alumina, silica gel, oxygen removing catalyst, and or purifying clays to reduce the heteroatom-containing compounds in the feed to below 10 ppm.

83. The process of claim 72 where the hydrogenation catalyst is supported Co and Mo and further comprises promoters selected from the group consisting of Ni, Pt, Pd, Rh, Fe, Ru, Os, Cr, and W.

84. The process of claim 34 where the metallocene is selected from the group consisting of rac-dimethylsilylbis(tetrahydroindenyl)ZrX₂, meso-ethylidenebis(indenyl)ZrX₂, (R_nCp)₂ZrX₂ or (R_mInd)₂ZrX₂, ethylidenebis(R_nCp)₂ZrX₂, dimethylsilylbis(R_nCp)₂ZrX₂, ethylidenebis(R_nInd)₂ZrX₂, and dimethylsilylbis(R_nInd)₂ZrX₂, where X is a halogen, a substituted or unsubstituted phenyl group, or a C1 to C20 alkyl, Cp is a cyclopentadienyl ring, R is a C1 to C20 alkyl group, n is a number denoting the degree of substitution of Cp and is a number from 0 to 5, Ind is

-112-

an indenyl ring, m is a number denoting the degree of substitution of Ind and is a number from 0 to 7.

85. The process of claim 34 where the metallocene is rac-dimethylsilylbis(tetrahydroindenyl)zirconiumdimethyl or meso-ethylidenebis(indenyl)zirconiumdimethyl.

86. The process of claim 34 where the metallocene is a $Y_2\text{methylidene}(R_n\text{Cp})(R_m\text{Flu})\text{ZrX}_2$ or $Y_2\text{silyl}(R_n\text{Cp})(R_m\text{Flu})\text{ZrX}_2$ where Y is independently a C1 to C20 alkyl or a substituted or unsubstituted phenyl group, X is a halogen, a substituted or unsubstituted phenyl group, or a C1 to C20 alkyl, Cp is a cyclopentadienyl ring, R is a C1 to C20 alkyl group, n is a number denoting the degree of substitution of Cp and is a number from 0 to 5, Flu is a fluorenyl ring, m is a number denoting the degree of substitution of Flu and is a number from 0 to 9.

87. The process of any one of claims 34 to 86, wherein the process is a bulk process.

88. The process of any one of claims 34 to 87, wherein ethylene is present in the monomer feed at from 0.5 to 10 mole%.

89. The process of any one of claims 34 to 88 wherein the feed stream comprises an alpha-olefin mixture.

**ANY REFERENCE TO FIGURES 1-10 SHALL BE
CONSIDERED NON-EXISTENT**

