

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2012/167079 A2

(43) International Publication Date
6 December 2012 (06.12.2012)

WIPO | PCT

(51) International Patent Classification:

A61K 8/67 (2006.01)

(21) International Application Number:

PCT/US2012/040459

(22) International Filing Date:

1 June 2012 (01.06.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/493,309 3 June 2011 (03.06.2011) US

(71) Applicant (for all designated States except US): **ALLERGAN, INC.** [US/US]; 2525 Dupont Drive, Irvine, California 92612 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LIU, Futian** [US/US]; 530 La Conner Drive, # 36, Sunnyvale, California 94087 (US). **MANESIS, Nicholas J.** [US/US]; 2280 Varley Street, Summerland, California 93067 (US). **YU, XiaoJie** [US/US]; 79 Legacy Way, Irvine, California 92602 (US). **CHAN, Athene Wan Chie** [US/US]; 2405 Bantry Lane, South San Francisco, California 94080 (US).

(74) Agents: **FOX, Linda A.** et al.; Allergan, Inc., 2525 Dupont Drive, Irvine, California 92612 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) Title: DERMAL FILLER COMPOSITIONS INCLUDING ANTIOXIDANTS



AA2G, (L-ascorbic acid 2-glucoside)

FIG. 1

(57) Abstract: Provided are injectable, hyaluronic acid-based hydrogel compositions including conjugated vitamins.

DERMAL FILLER COMPOSITIONS INCLUDING ANTIOXIDANTS

By Inventors: **Futian Liu, XiaoJie Yu,
Nicholas J. Manesis, Athene Wan Chie Chan**

5

RELATED APPLICATIONS

This application claims priority to and the benefit of U.S. Provisional Patent
10 Application No. 61/493,309, filed on June 3, 2011, the entire disclosure of which is
incorporated herein by this reference.

BACKGROUND

15 The present invention generally relates to dermal filler compositions, and more
specifically relates to injectable dermal filler compositions including antioxidants.

Skin aging is a progressive phenomenon, occurs over time and can be affected by
lifestyle factors, such as alcohol consumption, tobacco and sun exposure. Aging
20 of the facial skin can be characterized by atrophy, slackening, and fattening.
Atrophy corresponds to a massive reduction of the thickness of skin tissue.
Slackening of the subcutaneous tissues leads to an excess of skin and ptosis and
leads to the appearance of drooping cheeks and eye lids. Fattening refers to an
increase in excess weight by swelling of the bottom of the face and neck. These
25 changes are typically associated with dryness, loss of elasticity, and rough texture.

Hyaluronan, also known as hyaluronic acid (HA) is a non-sulfated
glycosaminoglycan that is distributed widely throughout the human body in
connective, epithelial, and neural tissues. Hyaluronan is abundant in the different
30 layers of the skin, where it has multiple functions such as, e.g., to ensure good
hydration, to assist in the organization of the extracellular matrix, to act as a filler
material; and to participate in tissue repair mechanisms. However, with age, the
quantity of hyaluronan, collagen, elastin, and other matrix polymers present in the

skin decreases. For example, repeated exposed to ultra violet light, e.g., from the sun, causes dermal cells to both decrease their production of hyaluronan as well as increase the rate of its degradation. This hyaluronan loss results in various skin conditions such as, e.g., imperfects, defects, diseases and/or disorders, and

5 the like. For instance, there is a strong correlation between the water content in the skin and levels of hyaluronan in the dermal tissue. As skin ages, the amount and quality of hyaluronan in the skin is reduced. These changes lead to drying and wrinkling of the skin.

10 Dermal fillers are useful in treating soft tissue condition and in other skin therapies because the fillers can replace lost endogenous matrix polymers, or enhance/facilitate the function of existing matrix polymers, in order to treat these skin conditions. In the past, such compositions have been used in cosmetic applications to fill wrinkles, lines, folds, scars, and to enhance dermal tissue, such

15 as, e.g., to plump thin lips, or fill-in sunken eyes or shallow cheeks. One common matrix polymer used in dermal filler compositions is hyaluronan. Because hyaluronan is natural to the human body, it is a generally well tolerated and a fairly low risk treatment for a wide variety of skin conditions.

20 Originally, compositions comprising hyaluronan were made from naturally-occurring polymers, which exist in an uncrosslinked state. Although exhibiting excellent biocompatibility and affinity for water molecules, naturally-occurring hyaluronan exhibits poor biomechanical properties as a dermal filler. One primary reason is that because this polymer is uncrosslinked, it is highly soluble and, as

25 such, is cleared rapidly when administered into a skin region. This *in vivo* clearance is primarily achieved by rapid degradation of the polymers, principally enzymatic degradation via hyaluronidase and chemical degradation via free-radicals. Thus, while still in commercial use, compositions comprising uncrosslinked hyaluronan polymers tend to degrade within a few days after

30 administration and thus require fairly frequent reinjection to maintain their skin improving effect.

To minimize the effect of these *in vivo* degradation pathways, matrix polymers are crosslinked to one another to form a stabilized hydrogel. Because hydrogels comprising crosslinked matrix polymers are a more solid substance, dermal fillers comprising such hydrogels remain in place at the implant site longer. In addition, 5 these hydrogels are more suitable as a dermal filler because the more solid nature thereof improves the mechanical properties of the filler, allowing the filler to better lift and fill a skin region. Hyaluronan polymers are typically crosslinked with a crosslinking agent to form covalent bonds between hyaluronan polymers. Such crosslinked polymers form a less water soluble hydrogel network that is more 10 resistant to degradation, and thus requires less frequent reinjection, than the non-crosslinked hyaluronan compositions.

Vitamin C, also known as ascorbic acid or AsA, is well known as an antioxidant which reduces, and thereby neutralizes, reactive oxygen species such as 15 hydrogen peroxide, thus reducing oxidative stress for various clinical benefits, including treating cardiovascular disease, hypertension, chronic inflammatory diseases, diabetes, and conditions with severe burns. For example, among other benefits, vitamin C acts as an anti-inflammatory, and promotes collagenesis and angiogenesis. Vitamin C is known to promote collagenesis and/or angiogenesis 20 by functioning as a cofactor in enzymatic reactions to promote collagen formation, develop and maintain blood vessels and cartilage. Vitamin C is known to inhibit biological functions of tyrosinase to prevent melanin formation or lightening melanin pigmentation. For these reasons, there is interest in developing dermal filler compositions containing vitamin C.

25

Vitamin C is generally unstable upon exposure to air, light and heat. It is also considered cytotoxic at certain levels. When vitamin C is physically mixed with hyaluronic acid gel and injected into the skin, the vitamin C is fully released from the mixture in less than one week.

30

It would be desirable to provide an injectable hyaluronic acid-based composition with vitamin C, or another vitamin, having a sustained release rate, that is, a

release rate over weeks or even months rather than a few days. However, it has proven difficult to develop stable, effective, sustained release dermal filler products which include vitamins. The present invention provides improved hyaluronic acid-based dermal filler compositions including conjugated vitamins, for example, 5 vitamin derivatives.

10

SUMMARY

The present invention provides novel dermal fillers useful for treating skin conditions. More specifically, the present invention provides effective, long lasting, therapeutic dermal filler compositions generally comprising a biocompatible 15 polymer, for example, hyaluronic acid, and a vitamin, for example, vitamin C, for example a vitamin C derivative.

In one aspect of the invention, the polymer is a polysaccharide, for example, hyaluronic acid. The hyaluronic acid includes a crosslinked component. The 20 vitamin may comprise vitamin C, for example, a Vitamin C derivative. More specifically, the vitamin C is at least one of L-ascorbic acid 2-glucoside (AA2G), ascorbyl 3-aminopropyl phosphate (Vitagen) and sodium ascorbyl phosphate (AA2P).

25 Vitamins are defined generally as any of a group of organic compounds that are essential for normal growth and nutrition and are required in small quantities in the diet because they cannot be synthesized by the body.

In one aspect of the invention, the vitamin is a vitamin derivative, and is covalently 30 conjugated to the polymer by a suitable reaction process, for example, etherification, amidization and esterification.

The conjugation degree is up to about 5 mol%, up to about 10 mol%, up to about 15 mol%, up to about 20 mol%, up to about 25 mol%, up to about 30 mol%, or up to about 40 mol%.

5 In another aspect of the invention, methods of making injectable dermal filler compositions including crosslinked hyaluronic acid and conjugated Vitamin C, as provided.

10 In yet another aspect of the invention, methods for treating a skin defect are provided, including introducing into the skin a composition in accordance with the invention.

BRIEF DESCRIPTION OF DRAWINGS

Figure 1 is a representation of the structure of L-ascorbic acid 2-glucoside (AA2G)

15

Figure 2 is a representation of the structure of ascorbyl 3-aminopropyl phosphate (Vitagen).

Figure 3 is a representation of the structure of sodium ascorbyl phosphate (AA2P).

20

Figure 4 is a representation of the structure of 1,4-butanediol diglycidyl ether (BDDE).

Figure 5 is a representation of the structure of pentaerythritol glycidal ether (Star-

25 PEG epoxide).

Figure 6 is a representation of the structure of pentaerythritol (3-aminopropyl) ether (Star-PEG amine).

30 Figure 7 is a Table showing conjugation degrees and G' values for various dermal filler compositions in accordance with the invention.

Figure 8 is a Table showing conjugation degrees, HA concentration and G' values for HA-AA2G (BDDE) dermal filler compositions in accordance with the invention.

Figure 9 is a Table showing the effect of α -glucosidase concentration on AsA release from AA2G –PBS solution.

Figure 10 shows a representation of a release profile of free AsA from conjugated dermal fillers in accordance with the invention (sustained release) (AA2G conversion in mol% versus reaction time).

10

Figure 11A and 11B show additional release data for various dermal fillers in accordance with the invention.

DETAILED DESCRIPTION

15 In one aspect of the invention, dermal filler compositions are provided, the compositions generally comprising a biocompatible polymer, for example, a polysaccharide such as a crosslinked hyaluronic acid, and a vitamin C derivative covalently conjugated to the polymer. The composition provides sustained release of the vitamin C for skin neocollagenesis as well as other therapeutic or
20 cosmetic benefits. When introduced into the skin, for example intradermally, the composition reacts with endogenous enzymes in the body, and over time, bioactive vitamin C is generated in vivo, via enzymatic cleavages. As vitamin C is released from the composition over a period of weeks or months, its attendant benefits are made available to the body.

25

The polymer may be selected from the group of polymers consisting of proteins, peptides and polypeptides, polylysine, collagens, pro-collagens, elastins, and laminins.

30 The polymer may be selected from the group of polymers consisting of synthetic polymers with hydroxyl, amine, and carboxyl functional groups: poly(vinyl alcohol), polyethylene glycol, polyvinyl amine, polyallylamine, deacetylated polyacrylamide,

polyacrylic acid, and polymethacrylic acid. The polymer may be selected from the group of polymers consisting of dentric or branched polymers, including dentric polyols and dentric polyamines. The polymer may be selected from the group of polymers consisting of solid surface with hydroxyl, amine, and carboxyl functional groups.

The polysaccharide may be selected from the group of polysaccharides including starch and its derivatives; dextran and its derivatives, cellulose and its derivatives; chitin and chitosan and alginate and its derivatives.

10

In an exemplary embodiment of the invention, the polymer is glycosaminoglycan. The hydrogel composition disclosed herein can further comprise two or more different glycosaminoglycan polymers. As used herein, the term "glycosaminoglycan" is synonymous with "GAG" and "mucopolysaccharide" and refers to long unbranched polysaccharides consisting of a repeating disaccharide units. The repeating unit consists of a hexose (six-carbon sugar) or a hexuronic acid, linked to a hexosamine (six-carbon sugar containing nitrogen) and pharmaceutically acceptable salts thereof. Members of the GAG family vary in the type of hexosamine, hexose or hexuronic acid unit they contain, such as, e.g., glucuronic acid, iduronic acid, galactose, galactosamine, glucosamine) and may also vary in the geometry of the glycosidic linkage. Any glycosaminoglycan polymer is useful in the hydrogel compositions disclosed herein with the proviso that the glycosaminoglycan polymer improves a condition of the skin. Non-limiting examples of glycosaminoglycans include chondroitin sulfate, dermatan sulfate, keratan sulfate, hyaluronan. Non-limiting examples of an acceptable salt of a glycosaminoglycans includes sodium salts, potassium salts, magnesium salts, calcium salts, and combinations thereof. Glycosaminoglycan and their resulting polymers useful in the hydrogel compositions and methods disclosed herein are described in, e.g., Piron and Tholin, Polysaccharide Crosslinking, Hydrogel Preparation, Resulting Polysaccharides(s) and Hydrogel(s), uses Thereof, U.S. Patent Publication 2003/0148995; Lebreton, Cross-Linking of Low and High Molecular Weight Polysaccharides Preparation of Injectable Monophase

Hydrogels; Lebreton, Viscoelastic Solutions Containing Sodium Hyaluronate and Hydroxypropyl Methyl Cellulose, Preparation and Uses, U.S. Patent Publication 2008/0089918; Lebreton, Hyaluronic Acid-Based Gels Including Lidocaine, U.S. Patent Publication 2010/0028438; and Polysaccharides and Hydrogels thus 5 Obtained, U.S. Patent Publication 2006/0194758; and Di Napoli, Composition and Method for Intradermal Soft Tissue Augmentation, International Patent Publication WO 2004/073759, each of which is hereby incorporated by reference in its entirety. GAGs useful in the hydrogel compositions and methods disclosed herein are commercially available, such as, e.g., hyaluronan-based dermal fillers 10 JUVEDERM®, JUVEDERM® 30, JUVEDERM® Ultra, JUVEDERM® Ultra Plus, JUVEDERM® Ultra XC, and JUVEDERM® Ultra Plus XC (Allergan Inc, Irvine, California). Table 1 lists representative GAGs.

Table 1. Examples of GAGs

Name	Hexuronic acid/Hexose	Hexosamine	Glycosidic linkage geometry	Unique features
Chondroitin sulfate	GlcUA or GlcUA(2S)	GalNAc or GalNAc(4S) or GalNAc(6S) or GalNAc(4S,6S)	-4GlcUA β 1-3GalNAc β 1-	Most prevalent GAG
Dermatan sulfate	GlcUA or IdoUA or IdoUA(2S)	GalNAc or GalNAc(4S) or GalNAc(6S) or GalNAc(4S,6S)	-4IdoUA β 1-3GalNAc β 1-	Distinguished from chondroitin sulfate by the presence of iduronic acid, although some hexuronic acid monosaccharides may be glucuronic acid.
Keratan sulfate	Gal or Gal(6S)	GlcNAc or GlcNAc(6S)	-3Gal(6S) β 1-4GlcNAc(6S) β 1-	Keratan sulfate type II may be fucosylated.

Heparin	GlcUA or IdoUA(2S)	GlcNAc or GlcNS or GlcNAc(6S) or GlcNS(6S)	-4IdoUA(2S) α 1- 4GlcNS(6S) α 1-	Highest negative charge density of any known biological molecule
Heparan sulfate	GlcUA or IdoUA or IdoUA(2S)	GlcNAc or GlcNS or GlcNAc(6S) or GlcNS(6S)	-4GlcUA β 1- 4GlcNAc α 1-	Highly similar in structure to heparin, however heparan sulfates disaccharide units are organized into distinct sulfated and non-sulfated domains.
Hyaluronan	GlcUA	GlcNAc	-4GlcUA β 1- 3GlcNAc β 1-	The only GAG that is exclusively non-sulfated

GlcUA = β -D-glucuronic acid
 GlcUA(2S) = 2-O-sulfo- β -D-glucuronic acid
 IdoUA = α -L-iduronic acid
 IdoUA(2S) = 2-O-sulfo- α -L-iduronic acid
 Gal = β -D-galactose
 Gal(6S) = 6-O-sulfo- β -D-galactose
 GalNAc = β -D-N-acetylgalactosamine
 GalNAc(4S) = β -D-N-acetylgalactosamine-4-O-sulfate
 GalNAc(6S) = β -D-N-acetylgalactosamine-6-O-sulfate
 GalNAc(4S,6S) = β -D-N-acetylgalactosamine-4-O, 6-O-sulfate
 GlcNAc = α -D-N-acetylglucosamine
 GlcNS = α -D-N-sulfoglucosamine
 GlcNS(6S) = α -D-N-sulfoglucosamine-6-O-sulfate

Aspects of the present invention provide, in part, a hydrogel composition comprising a chondroitin sulfate polymer. As used herein, the term "chondroitin sulfate polymer" refers to an unbranched, sulfated polymer of variable length comprising disaccharides of two alternating monosaccharides of D-glucuronic acid (GlcA) and N-acetyl-D-galactosamine (GalNAc) and pharmaceutically acceptable salts thereof. A chondroitin sulfate polymer may also include D-glucuronic acid residues that are epimerized into L-iduronic acid (IdoA), in which case the

resulting disaccharide is referred to as dermatan sulfate. A chondroitin sulfate polymer can have a chain of over 100 individual sugars, each of which can be sulfated in variable positions and quantities. Chondroitin sulfate polymers are an important structural component of cartilage and provide much of its resistance to 5 compression. Any chondroitin sulfate polymer is useful in the compositions disclosed herein with the proviso that the chondroitin sulfate polymer improves a condition of the skin. Non-limiting examples of pharmaceutically acceptable salts of chondroitin sulfate include sodium chondroitin sulfate, potassium chondroitin sulfate, magnesium chondroitin sulfate, calcium chondroitin sulfate, and 10 combinations thereof.

Aspects of the present specification provide, in part, a hydrogel composition comprising a keratan sulfate polymer. As used herein, the term "keratan sulfate polymer" refers to a polymer of variable length comprising disaccharide units, 15 which themselves include β -D-galactose and N-acetyl-D-galactosamine (GalNAc) and pharmaceutically acceptable salts thereof. Disaccharides within the repeating region of keratan sulfate may be fucosylated and N-Acetylneuraminic acid caps the end of the chains. Any keratan sulfate polymer is useful in the compositions disclosed herein with the proviso that the keratan sulfate polymer improves a 20 condition of the skin. Non-limiting examples of pharmaceutically acceptable salts of keratan sulfate include sodium keratan sulfate, potassium keratan sulfate, magnesium keratan sulfate, calcium keratan sulfate, and combinations thereof.

Aspects of the present specification provide, in part, a hydrogel composition 25 comprising a hyaluronan polymer. As used herein, the term "hyaluronic acid polymer" is synonymous with "HA polymer", "hyaluronic acid polymer", and "hyaluronate polymer" refers to an anionic, non-sulfated glycosaminoglycan polymer comprising disaccharide units, which themselves include D-glucuronic acid and D-N-acetylglucosamine monomers, linked together via alternating β -1,4 30 and β -1,3 glycosidic bonds and pharmaceutically acceptable salts thereof. Hyaluronan polymers can be purified from animal and non-animal sources. Polymers of hyaluronan can range in size from about 5,000 Da to about

20,000,000 Da. Any hyaluronan polymer is useful in the compositions disclosed herein with the proviso that the hyaluronan improves a condition of the skin. Non-limiting examples of pharmaceutically acceptable salts of hyaluronan include sodium hyaluronan, potassium hyaluronan, magnesium hyaluronan, calcium 5 hyaluronan, and combinations thereof.

Aspects of the present specification provide, in part, a hydrogel composition comprising a crosslinked glycosaminoglycan polymer. As used herein, the term "crosslinked" refers to the intermolecular bonds joining the individual polymer 10 molecules, or monomer chains, into a more stable structure like a gel. As such, a crosslinked glycosaminoglycan polymer has at least one intermolecular bond joining at least one individual polymer molecule to another one. The crosslinking of glycosaminoglycan polymers typically result in the formation of a hydrogel. Such hydrogels have high viscosity and require considerable force to extrude 15 through a fine needle. Glycosaminoglycan polymers disclosed herein may be crosslinked using dialdehydes and disulfides crosslinking agents including, without limitation, multifunctional PEG-based crosslinking agents, divinyl sulfones, diglycidyl ethers, and bis-epoxides, biscarbodiimide. Non-limiting examples of hyaluronan crosslinking agents include multifunctional PEG-based crosslinking 20 agents like pentaerythritol tetraglycidyl ether (PETGE), divinyl sulfone (DVS), 1,4-butanediol diglycidyl ether (BDDE), 1,2-bis(2,3-epoxypropoxy)ethylene (EGDGE), 1,2,7,8-diepoxyoctane (DEO), (phenylenebis-(ethyl)-carbodiimide and 1,6 hexamethylenebis (ethylcarbodiimide), adipic dihydrazide (ADH), bis(sulfosuccinimidyl)suberate (BS), hexamethylenediamine (HMDA), 1-(2,3- 25 epoxypropyl)-2,3-epoxycyclohexane, or combinations thereof. Other useful crosslinking agents are disclosed in Stroumpoulis and Tezel, Tunably Crosslinked Polysaccharide Compositions, U.S. Patent Application 12/910,466, filed October 22, 2010, which is incorporated by reference in its entirety. Non-limiting examples of methods of crosslinking glycosaminoglycan polymers are described in, e.g., 30 Glycosaminoglycan polymers useful in the compositions and methods disclosed herein are described in, e.g., Piron and Tholin, Polysaccharide Crosslinking, Hydrogel Preparation, Resulting Polysaccharides(s) and Hydrogel(s), uses

Thereof, U.S. Patent Publication 2003/0148995; Lebreton, Cross-Linking of Low and High Molecular Weight Polysaccharides Preparation of Injectable Monophase Hydrogels; Lebreton, Viscoelastic Solutions Containing Sodium Hyaluronate and Hydroxypropyl Methyl Cellulose, Preparation and Uses, U.S. Patent Publication 5 2008/0089918; Lebreton, Hyaluronic Acid-Based Gels Including Lidocaine, U.S. Patent Publication 2010/0028438; and Polysaccharides and Hydrogels thus Obtained, U.S. Patent Publication 2006/0194758; and Di Napoli, Composition and Method for Intradermal Soft Tissue Augmentation, International Patent Publication WO 2004/073759, each of which is hereby incorporated by reference in its 10 entirety.

In accordance with the present specification, “%” in a formulation is defined as weight by weight (i.e., w/w) percentage. As an example: 1% (w/w) means a concentration of 10 mg/g.

15 In an embodiment, a hydrogel composition comprises a crosslinked glycosaminoglycan polymer where the crosslinked glycosaminoglycan polymer is present in an amount sufficient to improve a skin condition as disclosed herein. In aspect of this embodiment, a composition comprises a crosslinked chondroitin 20 sulfate polymer, a crosslinked dermatan sulfate polymer, a crosslinked keratan sulfate polymer, a crosslinked heparan polymer, a crosslinked heparan sulfate polymer, or a crosslinked hyaluronan polymer. In other aspects of this embodiment, a composition comprises a crosslinked glycosaminoglycan where the crosslinked glycosaminoglycan represents, e.g., about 1% by weight, about 25 2% by weight, about 3% by weight, about 4% by weight, about 5% by weight, about 6% by weight, about 7% by weight, about 8% by weight, or about 9%, or about 10% by weight, of the total glycosaminoglycan present in the composition. In yet other aspects of this embodiment, a composition comprises a crosslinked glycosaminoglycan where the crosslinked glycosaminoglycan represents, e.g., at 30 most 1% by weight, at most 2% by weight, at most 3% by weight, at most 4% by weight, at most 5% by weight, at most 6% by weight, at most 7% by weight, at most 8% by weight, at most 9% by weight, or at most 10% by weight, of the total

glycosaminoglycan present in the composition. In still other aspects of this embodiment, a composition comprises a crosslinked glycosaminoglycan where the crosslinked glycosaminoglycan represents, e.g., about 0% to about 20% by weight, about 1% to about 17% by weight, about 3% to about 15% by weight, or 5 about 5% to about 10% by weight, for example, about 11% by weight, about 15% by weight or about 17% by weight, of the total glycosaminoglycan present in the composition.

In aspects of this embodiment, a hydrogel composition comprises a crosslinked 10 glycosaminoglycan where the crosslinked glycosaminoglycan is present at a concentration of, e.g., about 2 mg/g, about 3 mg/g, about 4 mg/g, about 5 mg/g, about 6 mg/g, about 7 mg/g, about 8 mg/g, about 9 mg/g, about 10 mg/g, about 11 mg/g, about 12 mg/g, about 13 mg/g, about 13.5 mg/g, about 14 mg/g, about 15 mg/g, about 16 mg/g, about 17 mg/g, about 18 mg/g, about 19 mg/g, or about 20 mg/g. In other aspects of this embodiment, a composition comprises a crosslinked 15 glycosaminoglycan where the crosslinked glycosaminoglycan is present at a concentration of, e.g., at least 1 mg/g, at least 2 mg/g, at least 3 mg/g, at least 4 mg/g, at least 5 mg/g, at least 10 mg/g, at least 15 mg/g, at least 20 mg/g, or at least 25 mg/g, or about 40 mg/g. In yet other aspects of this 20 embodiment, a composition comprises a crosslinked glycosaminoglycan where the crosslinked glycosaminoglycan is present at a concentration of, e.g., at most 1 mg/g, at most 2 mg/g, at most 3 mg/g, at most 4 mg/g, at most 5 mg/g, at most 10 mg/g, at most 15 mg/g, at most 20 mg/g, at most 25 mg/g, or at most 40 mg/g. In still other aspects of this embodiment, a composition comprises a crosslinked 25 glycosaminoglycan where the crosslinked glycosaminoglycan is present at a concentration of, e.g., about 7.5 mg/g to about 19.5 mg/g, about 8.5 mg/g to about 18.5 mg/g, about 9.5 mg/g to about 17.5 mg/g, about 10.5 mg/g to about 16.5 mg/g, about 11.5 mg/g to about 15.5 mg/g, or about 12.5 mg/g to about 14.5 mg/g, up to about 40 mg/g.

30

Aspects of the present specification provide, in part, a hydrogel composition comprising hyaluronan polymers of low molecular weight, hyaluronan polymers of

high molecular weight, or hyaluronan polymers of both low and high molecular weight. As used herein, the term "high molecular weight" when referring to "hyaluronan" refers to hyaluronan polymers having a mean molecular weight of 1,000,000 Da or greater. Non-limiting examples of a high molecular weight 5 hyaluronan polymers include hyaluronan polymers about 1,500,000 Da, about 2,000,000 Da, about 2,500,000 Da, about 3,000,000 Da, about 3,500,000 Da, about 4,000,000 Da, about 4,500,000 Da, and about 5,000,000 Da. As used herein, the term "low molecular weight" when referring to "hyaluronan" refers to hyaluronan polymers having a mean molecular weight of less than 1,000,000 Da.

10 Non-limiting examples of a low molecular weight hyaluronan polymers include hyaluronan polymers of about 200,000 Da, about 300,000 Da, about 400,000 Da, about 500,000 Da, about 600,000 Da, about 700,000 Da, of about 800,000 Da, and about 900,000 Da.

15 In an embodiment, a composition comprises crosslinked hyaluronan polymers of low molecular weight. In aspects of this embodiment, a composition comprises crosslinked hyaluronan polymers having a mean molecular weight of, e.g., about 100,000 Da, about 200,000 Da, about 300,000 Da, about 400,000 Da, about 500,000 Da, about 600,000 Da, about 700,000 Da, about 800,000 Da, or about 20 900,000 Da. In yet other aspects of this embodiment, a composition comprises crosslinked hyaluronan polymers having a mean molecular weight of, e.g., at most 100,000 Da, at most 200,000 Da, at most 300,000 Da, at most 400,000 Da, at most 500,000 Da, at most 600,000 Da, at most 700,000 Da, at most 800,000 Da, at most 900,000 Da, or at most 950,000. In still other aspects of this embodiment, 25 a composition comprises crosslinked hyaluronan polymers having a mean molecular weight of, e.g., about 100,000 Da to about 500,000 Da, about 200,000 Da to about 500,000 Da, about 300,000 Da to about 500,000 Da, about 400,000 Da to about 500,000 Da, about 500,000 Da to about 950,000 Da, about 600,000 Da to about 950,000 Da, about 700,000 Da to about 950,000 Da, about 800,000 30 Da to about 950,000 Da, about 300,000 Da to about 600,000 Da, about 300,000 Da to about 700,000 Da, about 300,000 Da to about 800,000 Da, or about 400,000 Da to about 700,000 Da.

In another embodiment, a composition comprises crosslinked hyaluronan polymers of high molecular weight. In aspects of this embodiment, a composition comprises a crosslinked hyaluronan polymers having a mean molecular weight of, 5 e.g., about 1,000,000 Da, about 1,500,000 Da, about 2,000,000 Da, about 2,500,000 Da, about 3,000,000 Da, about 3,500,000 Da, about 4,000,000 Da, about 4,500,000 Da, or about 5,000,000 Da. In yet other aspects of this embodiment, a composition comprises a crosslinked hyaluronan polymers having a mean molecular weight of, e.g., at least 1,000,000 Da, at least 1,500,000 Da, at 10 least 2,000,000 Da, at least 2,500,000 Da, at least 3,000,000 Da, at least 3,500,000 Da, at least 4,000,000 Da, at least 4,500,000 Da, or at least 5,000,000 Da. In still other aspects of this embodiment, a composition comprises a crosslinked hyaluronan polymers having a mean molecular weight of, e.g., about 1,000,000 Da to about 5,000,000 Da, about 1,500,000 Da to about 5,000,000 Da, 15 about 2,000,000 Da to about 5,000,000 Da, about 2,500,000 Da to about 5,000,000 Da, about 2,000,000 Da to about 3,000,000 Da, about 2,500,000 Da to about 3,500,000 Da, or about 2,000,000 Da to about 4,000,000 Da.

In yet another embodiment, a composition comprises a crosslinked hyaluronan polymers where the crosslinked hyaluronan polymers comprise a combination of both high molecular weight hyaluronan polymers and low molecular weight hyaluronan polymers, in various ratios. In aspects of this embodiment, a composition comprises a crosslinked hyaluronan polymers where the crosslinked hyaluronan polymers comprises a combination of both high molecular weight 25 hyaluronan polymers and low molecular weight hyaluronan polymers in a ratio of about 20:1, about 15:1, about 10:1, about 5:1, about 1:1, about 1:5 about 1:10, about 1:15, or about 1:20.

Aspects of the present specification provide, in part, a hydrogel composition 30 comprising a crosslinked glycosaminoglycan polymer having a degree of crosslinking. As used herein, the term “degree of crosslinking” refers to the percentage of glycosaminoglycan polymer monomeric units, such as, e.g., the

disaccharide monomer units of hyaluronan that are bound to a cross-linking agent. The degree of crosslinking is expressed as the percent weight ratio of the crosslinking agent to glycosaminoglycan.

5 Aspects of the present specification provide, in part, a hydrogel composition comprising an uncrosslinked glycosaminoglycan polymer. As used herein, the term “uncrosslinked” refers to a lack of intermolecular bonds joining the individual glycosaminoglycan polymer molecules, or monomer chains. As such, an uncrosslinked glycosaminoglycan polymer is not linked to any other

10 glycosaminoglycan polymer by an intermolecular bond. In aspects of this embodiment, a composition comprises an uncrosslinked chondroitin sulfate polymer, an uncrosslinked dermatan sulfate polymer, an uncrosslinked keratan sulfate polymer, an uncrosslinked heparan polymer, an uncrosslinked heparan sulfate polymer, or an uncrosslinked hyaluronan polymer. Uncrosslinked

15 glycosaminoglycan polymers are water soluble and generally remain fluid in nature. As such, uncross-linked glycosaminoglycan polymers are often mixed with a glycosaminoglycan polymer-based hydrogel composition as a lubricant to facilitate the extrusion process of the composition through a fine needle.

In an embodiment, a composition comprises an uncrosslinked glycosaminoglycan

20 polymer where the uncrosslinked glycosaminoglycan polymer is present in an amount sufficient to improve a skin condition as disclosed herein. In aspects of this embodiment, a composition comprises an uncrosslinked glycosaminoglycan where the uncrosslinked glycosaminoglycan is present at a concentration of, e.g., about 2 mg/g, about 3 mg/g, about 4 mg/g, about 5 mg/g, about 6 mg/g, about 7

25 mg/g, about 8 mg/g, about 9 mg/g, about 10 mg/g, about 11 mg/g, about 12 mg/g, about 13 mg/g, about 13.5 mg/g, about 14 mg/g, about 15 mg/g, about 16 mg/g, about 17 mg/g, about 18 mg/g, about 19 mg/g, about 20 mg/g, about 40 mg/g, or about 60 mg/g. In other aspects of this embodiment, a composition comprises an uncrosslinked glycosaminoglycan where the uncrosslinked glycosaminoglycan is

30 present at a concentration of, e.g., at least 1 mg/g, at least 2 mg/g, at least 3 mg/g, at least 4 mg/g, at least 5 mg/g, at least 10 mg/g, at least 15 mg/g, at least 20 mg/g, at least 25 mg/g at least 35 mg/g, or at least 40 mg/g. In yet other aspects

of this embodiment, a composition comprises an uncrosslinked glycosaminoglycan where the uncrosslinked glycosaminoglycan is present at a concentration of, e.g., at most 1 mg/g, at most 2 mg/g, at most 3 mg/g, at most 4 mg/g, at most 5 mg/g, at most 10 mg/g, at most 15 mg/g, at most 20 mg/g, or at most 25 mg/g. In still 5 other aspects of this embodiment, a composition comprises an uncrosslinked glycosaminoglycan where the uncrosslinked glycosaminoglycan is present at a concentration of, e.g., about 1 mg/g to about 60 mg/g, about 10 mg/g to about 40 mg/g, about 7.5 mg/g to about 19.5 mg/g, about 8.5 mg/g to about 18.5 mg/g, about 9.5 mg/g to about 17.5 mg/g, about 10.5 mg/g to about 16.5 mg/g, about 10 11.5 mg/g to about 15.5 mg/g, or about 12.5 mg/g to about 14.5 mg/g.

In an embodiment, a composition comprises uncrosslinked hyaluronan polymers of low molecular weight. In aspects of this embodiment, a composition comprises a uncrosslinked hyaluronan having a mean molecular weight of, e.g., about 15 100,000 Da, about 200,000 Da, about 300,000 Da, about 400,000 Da, about 500,000 Da, about 600,000 Da, about 700,000 Da, about 800,000 Da, or about 900,000 Da. In yet other aspects of this embodiment, a composition comprises uncrosslinked hyaluronan polymers having a mean molecular weight of, e.g., at most 100,000 Da, at most 200,000 Da, at most 300,000 Da, at most 400,000 Da, 20 at most 500,000 Da, at most 600,000 Da, at most 700,000 Da, at most 800,000 Da, at most 900,000 Da, or at most 950,000. In still other aspects of this embodiment, a composition comprises uncrosslinked hyaluronan polymers having a mean molecular weight of, e.g., about 100,000 Da to about 500,000 Da, about 200,000 Da to about 500,000 Da, about 300,000 Da to about 500,000 Da, about 400,000 Da to about 500,000 Da, about 500,000 Da to about 950,000 Da, about 25 600,000 Da to about 950,000 Da, about 700,000 Da to about 950,000 Da, about 800,000 Da to about 950,000 Da, about 300,000 Da to about 600,000 Da, about 300,000 Da to about 700,000 Da, about 300,000 Da to about 800,000 Da, or about 400,000 Da to about 700,000 Da.

30

In another embodiment, a composition comprises uncrosslinked hyaluronan polymers of high molecular weight. In aspects of this embodiment, a composition

comprises an uncrosslinked hyaluronan having a mean molecular weight of, e.g., about 1,000,000 Da, about 1,500,000 Da, about 2,000,000 Da, about 2,500,000 Da, about 3,000,000 Da, about 3,500,000 Da, about 4,000,000 Da, about 4,500,000 Da, or about 5,000,000 Da. In other aspects of this embodiment, a

5 composition comprises an uncrosslinked hyaluronan polymers having a mean molecular weight of, e.g., at least 1,000,000 Da, at least 1,500,000 Da, at least 2,000,000 Da, at least 2,500,000 Da, at least 3,000,000 Da, at least 3,500,000 Da, at least 4,000,000 Da, at least 4,500,000 Da, or at least 5,000,000 Da. In yet other aspects of this embodiment, a composition comprises an uncrosslinked

10 hyaluronan polymers having a mean molecular weight of, e.g., about 1,000,000 Da to about 5,000,000 Da, about 1,500,000 Da to about 5,000,000 Da, about 2,000,000 Da to about 5,000,000 Da, about 2,500,000 Da to about 5,000,000 Da, about 2,000,000 Da to about 3,000,000 Da, about 2,500,000 Da to about 3,500,000 Da, or about 2,000,000 Da to about 4,000,000 Da. In still other

15 aspects, a composition comprises an uncrosslinked hyaluronan polymers having a mean molecular weight of, e.g., greater than 2,000,000 Da and less than about 3,000,000 Da, greater than 2,000,000 Da and less than about 3,500,000 Da, greater than 2,000,000 Da and less than about 4,000,000 Da, greater than 2,000,000 Da and less than about 4,500,000 Da, greater than 2,000,000 Da and

20 less than about 5,000,000 Da.

In another embodiment, a composition comprises uncrosslinked hyaluronan polymers where the uncrosslinked hyaluronan comprises a combination of both high molecular weight hyaluronan polymers and low molecular weight hyaluronan polymers, in various ratios. In aspects of this embodiment, a composition comprises an uncrosslinked hyaluronan polymers where the uncrosslinked hyaluronan polymers comprises a combination of both high molecular weight hyaluronan polymers and low molecular weight hyaluronan polymers in a ratio of about 20:1, about 15:1, about 10:1, about 5:1, about 1:1, about 1:5 about 1:10, about 1:15, or about 1:20.

Aspects of the present specification provide, in part, a hydrogel composition comprising a substantially uncrosslinked glycosaminoglycan polymer. As used herein, the term “substantially uncrosslinked” refers to the presence of uncrosslinked glycosaminoglycan polymers in a composition disclosed herein at a 5 level of at least 90% by weight of the composition, with the remaining at most 10% by weight of the composition being comprised of other components including crosslinked glycosaminoglycan polymers. In aspects of this embodiment, a composition comprises a substantially uncrosslinked chondroitin sulfate polymer, a substantially uncrosslinked dermatan sulfate polymer, a substantially 10 uncrosslinked keratan sulfate polymer, a substantially uncrosslinked heparan polymer, a substantially uncrosslinked heparan sulfate polymer, or a substantially uncrosslinked hyaluronan polymer. In other aspects of this embodiment, a composition comprises an uncrosslinked glycosaminoglycan where the uncrosslinked glycosaminoglycan represents, e.g., about 90% or more by weight, 15 about 91% or more by weight, about 92% or more by weight, about 93% or more by weight, about 94% or more by weight, about 95% or more by weight, about 96% or more by weight, about 97% or more by weight, about 98% or more by weight, or about 99% or more, or about 100% by weight, of the total glycosaminoglycan present in the composition. In yet other aspects of this 20 embodiment, a composition comprises an uncrosslinked glycosaminoglycan where the uncrosslinked glycosaminoglycan represents, e.g., about 90% to about 100% by weight, about 93% to about 100% by weight, about 95% to about 100% by weight, or about 97% to about 100% by weight, of the total glycosaminoglycan present in the composition.

25

Aspects of the present specification provide, in part, a hydrogel composition that is essentially free of a crosslinked glycosaminoglycan polymer. As used herein, the term “essentially free” (or “consisting essentially of”) refers to a composition where only trace amounts of cross-linked matrix polymers can be detected. In an aspect 30 of this embodiment, a composition comprises a chondroitin sulfate that is essentially free of a crosslinked chondroitin sulfate polymer, a dermatan sulfate essentially free of a crosslinked dermatan sulfate polymer, a keratan sulfate

essentially free of a crosslinked keratan sulfate polymer, a heparan essentially free of a crosslinked heparan polymer, a heparan sulfate essentially free of a crosslinked heparan sulfate polymer, or a hyaluronan sulfate essentially free of a crosslinked hyaluronan polymer.

5

Aspects of the present specification provide, in part, a hydrogel composition that is entirely free of a crosslinked glycosaminoglycan polymer. As used herein, the term "entirely free" refers to a composition that within the detection range of the instrument or process being used, crosslinked glycosaminoglycan polymers

10 cannot be detected or its presence cannot be confirmed. In an aspect of this embodiment, a composition comprises a chondroitin sulfate that is entirely free of a crosslinked chondroitin sulfate polymer, a dermatan sulfate entirely free of a crosslinked dermatan sulfate polymer, a keratan sulfate entirely free of a crosslinked keratan sulfate polymer, a heparan entirely free of a crosslinked heparan polymer, a heparan sulfate entirely free of a crosslinked heparan sulfate polymer, or a hyaluronan sulfate entirely free of a crosslinked hyaluronan polymer.

Aspects of the present specification provide, in part, a hydrogel composition comprising a ratio of crosslinked glycosaminoglycan polymer and uncrosslinked

20 glycosaminoglycan polymer. This ratio of crosslinked and uncrosslinked glycosaminoglycan polymer is also known as the gel:fluid ratio. Any gel:fluid ratio is useful in making the compositions disclosed herein with the proviso that such ratio produces a composition disclosed herein that improves a skin condition as disclosed herein. Non-limiting examples of gel:fluid ratios in compositions of the 25 present invention include 100:0, 98:2, 90:10, 75:25, 70:30, 60:40, 50:50, 40:60, 30:70, 25:75, 10:90; 2:98, and 0:100.

In aspects of this embodiment, a composition comprises a crosslinked glycosaminoglycan polymer and an uncrosslinked glycosaminoglycan polymer

30 where the gel:fluid ratio is, e.g., about 0:100, about 1:99, about 2:98, about 3:97, about 4:96, about 5:95, about 6:94, about 7:93, about 8:92, about 9:91, or about 10:90. In other aspects of this embodiment, a composition comprises a

crosslinked glycosaminoglycan polymer and an uncrosslinked glycosaminoglycan polymer where the gel:fluid ratio is, e.g., at most 1:99, at most 2:98, at most 3:97, at most 4:96, at most 5:95, at most 6:94, at most 7:93, at most 8:92, at most 9:91, or at most 10:90. In yet other aspects of this embodiment, a composition 5 comprises a crosslinked glycosaminoglycan polymer and an uncrosslinked glycosaminoglycan polymer where the gel:fluid ratio is, e.g., about 0:100 to about 3:97, about 0:100 to about 5:95, or about 0:100 to about 10:90.

In other aspects of this embodiment, a composition comprises a crosslinked 10 glycosaminoglycan polymer and an uncrosslinked glycosaminoglycan polymer where the gel:fluid ratio is, e.g., about 15:85, about 20:80, about 25:75, about 30:70, about 35:65, about 40:60, about 45:55, about 50:50, about 55:45, about 60:40, about 65:35, about 70:30, about 75:25, about 80:20, about 85:15, about 90:10, about 95:5, about 98:2, or about 100:0. In yet other aspects of this 15 embodiment, a composition comprises a crosslinked glycosaminoglycan polymer and an uncrosslinked glycosaminoglycan polymer where the gel:fluid ratio is, e.g., at most 15:85, at most 20:80, at most 25:75, at most 30:70, at most 35:65, at most 40:60, at most 45:55, at most 50:50, at most 55:45, at most 60:40, at most 65:35, at most 70:30, at most 75:25, at most 80:20, at most 85:15, at most 90:10, at most 95:5, at most 98:2, or at most 100:0. In still other aspects of this embodiment, a 20 composition comprises a crosslinked glycosaminoglycan polymer and an uncrosslinked glycosaminoglycan polymer where the gel:fluid ratio is, e.g., about 10:90 to about 70:30, about 15:85 to about 70:30, about 10:90 to about 55:45, about 80:20 to about 95:5, about 90:10 to about 100:0, about 75:25 to about 25 100:0, or about 60:40 to about 100:0.

A hydrogel composition disclosed herein may further comprise another agent or combination of agents that provide a beneficial effect when the composition is administered to an individual. Such beneficial agents include, without limitation, 30 an antioxidant, an anti-itch agent, an anti-cellulite agent, an anti-scarring agent, an anti-inflammatory agent, an anesthetic agent, an anti-irritant agent, a vasoconstrictor, a vasodilator, an anti-hemorrhagic agent like a hemostatic agent

or anti-fibrinolytic agent, a desquamating agent, a tensioning agent, an anti-acne agent, a pigmentation agent, an anti-pigmentation agent, or a moisturizing agent. Aspects of the present specification provide, in part, a hydrogel composition disclosed herein that may optionally comprise an anesthetic agent. An anesthetic agent is preferably a local anesthetic agent, *i.e.*, an anesthetic agent that causes a reversible local anesthesia and a loss of nociception, such as, *e.g.*, aminoamide local anesthetics and aminoester local anesthetics. The amount of an anesthetic agent included in a composition disclosed herein is an amount effective to mitigate pain experienced by an individual upon administration of the composition. As such, the amount of an anesthetic agent included in a composition disclosed in the present specification is between about 0.1% to about 5% by weight of the total composition. Non-limiting examples of anesthetic agents include lidocaine, ambucaine, amolanone, amylocaine, benoxinate, benzocaine, betoxycaine, biphenamine, bupivacaine, butacaine, butamben, butanilicaine, butethamine, butoxycaine, carticaine, chloroprocaine, cocaethylene, cocaine, cyclomethycaine, dibucaine, dimethysoquin, dimethocaine, diperodon, dycyclonine, ecgonidine, ecgonine, ethyl chloride, etidocaine, beta-eucaine, euprocin, fenalcomine, formocaine, hexylcaine, hydroxytetracaine, isobutyl p-aminobenzoate, leucinocaine mesylate, levoxadrol, lidocaine, mepivacaine, meprylcaine, metabutoxycaine, methyl chloride, myrtecaine, naepaine, octacaine, orthocaine, oxethazaine, parethoxycaine, phenacaine, phenol, piperocaine, piridocaine, polidocanol, pramoxine, prilocaine, procaine, propanocaine, proparacaine, propipocaine, propoxycaine, psuedococaine, pyrrocaine, ropivacaine, salicyl alcohol, tetracaine, tolycaine, trimecaine, zolamine, combinations thereof, and salts thereof. Non-limiting examples of aminoester local anesthetics include procaine, chloroprocaine, cocaine, cyclomethycaine, cimethocaine (larocaine), propoxycaine, procaine (novocaine), proparacaine, tetracaine (amethocaine). Non-limiting examples of aminoamide local anesthetics include articaine, bupivacaine, cinchocaine (dibucaine), etidocaine, levobupivacaine, lidocaine (lignocaine), mepivacaine, piperocaine, prilocaine, ropivacaine, and trimecaine. A composition disclosed herein may comprise a single anesthetic agent or a plurality

of anesthetic agents. A non-limiting example of a combination local anesthetic is lidocaine/prilocaine (EMLA).

Thus in an embodiment, a composition disclosed herein comprises an anesthetic agent and salts thereof. In aspects of this embodiment, a composition disclosed herein comprises an aminoamide local anesthetic and salts thereof or an aminoester local anesthetic and salts thereof. In other aspects of this embodiment, a composition disclosed herein comprises procaine, chloroprocaine, cocaine, cyclomethycaine, cimethocaine, propoxycaine, procaine, proparacaine, tetracaine, or salts thereof, or any combination thereof. In yet other aspects of this embodiment, a composition disclosed herein comprises articaine, bupivacaine, cinchocaine, etidocaine, levobupivacaine, lidocaine, mepivacaine, piperocaine, prilocaine, ropivacaine, trimecaine, or salts thereof, or any combination thereof. In still other aspects of this embodiment, a composition disclosed herein comprises a lidocaine/prilocaine combination.

In other aspects of this embodiment, a composition disclosed herein comprises an anesthetic agent in an amount of, e.g., about 0.1%, about 0.2%, about 0.3%, about 0.4%, about 0.5%, about 0.6%, about 0.7%, about 0.8% about 0.9%, about 1.0%, about 2.0%, about 3.0%, about 4.0%, about 5.0%, about 6.0%, about 7.0%, about 8.0%, about 9.0%, or about 10% by weight of the total composition. In yet other aspects, a composition disclosed herein comprises an anesthetic agent in an amount of, e.g., at least 0.1%, at least 0.2%, at least 0.3%, at least 0.4%, at least 0.5%, at least 0.6%, at least 0.7%, at least 0.8% at least 0.9%, at least 1.0%, at least 2.0%, at least 3.0%, at least 4.0%, at least 5.0%, at least 6.0%, at least 7.0%, at least 8.0%, at least 9.0%, or at least 10% by weight of the total composition. In still other aspects, a composition disclosed herein comprises an anesthetic agent in an amount of, e.g., at most 0.1%, at most 0.2%, at most 0.3%, at most 0.4%, at most 0.5%, at most 0.6%, at most 0.7%, at most 0.8% at most 0.9%, at most 1.0%, at most 2.0%, at most 3.0%, at most 4.0%, at most 5.0%, at most 6.0%, at most 7.0%, at most 8.0%, at most 9.0%, or at most 10% by weight of the total composition. In further aspects, a composition disclosed herein

comprises an anesthetic agent in an amount of, e.g., about 0.1% to about 0.5%, about 0.1% to about 1.0%, about 0.1% to about 2.0%, about 0.1% to about 3.0%, about 0.1% to about 4.0%, about 0.1% to about 5.0%, about 0.2% to about 0.9%, about 0.2% to about 1.0%, about 0.2% to about 2.0%, about 0.5% to about 1.0%,
5 or about 0.5% to about 2.0% by weight of the total composition.

In another embodiment, a composition disclosed herein does not comprise an anesthetic agent.

- 10 In one aspect of the present invention, an injectable dermal filler is provided which comprises a polymer, for example, a glycosaminoglycan polymer, for example a hyaluronic acid polymer, for example, a hyaluronic acid at least a portion of which is crosslinked, and a beneficial agent covalently conjugated to the polymer.
- 15 The beneficial agent covalently conjugated to the polymer may comprise a vitamin, an antioxidant, a growth factor, a peptide or any other beneficial agent that can be chemically conjugated to the polymer, for example, in order to enhance extended release of the agent in the body.
- 20 The beneficial agent may comprise a vitamin. In some embodiments, the vitamin is at least one of vitamin C, a retinoid, and vitamin E.

In an especially advantageous embodiment, the beneficial agent covalently conjugated to the polymer is vitamin C, or a vitamin C derivative. The amount of
25 vitamin C in the composition is in an amount effective to provide at least one desired therapeutic or cosmetic benefit when released in the body, for example, but not limited to, neocollagenesis, anti-inflammation, promotion of cell viability, antioxidation, angiogenesis, opacity, and other benefits. The amount of vitamin C included in a composition disclosed herein is between about 0.04% to about 5.0%
30 by weight of the total composition, for example, between about 0.1% to about 4.0% by weight of the total composition, for example, between about 0.2% to about 2.0% by weight of the total composition. In one embodiment, the amount of

vitamin C included in a composition disclosed herein is between about 0.3% to about 1.2% by weight of the total composition.

Suitable vitamin C or vitamin C derivatives that are covalently conjugated to the polymer in compositions of the invention include ascorbic acid, L-ascorbic acid, L-ascorbic acid 2-sulfate (AA-2S) and L-ascorbic acid 2-phosphate (AA-2P), ascorbic acid 2-O-glucoside (AA-2G), 6-O-acyl-2-O-alpha-D-glucopyranosyl-L-ascorbic acids (6-Acyl-AA-2G), (ascobyl 3-aminopropyl phosphate, Ascorbyl palmitate), derivatives and combinations thereof. A composition disclosed herein may comprise a single vitamin C agent or a plurality of vitamin C agents.

In another aspect of the invention, the beneficial agent chemically conjugated to the polymer is a retinoid. Suitable retinoids include retinol (-hydroxyl group, -OH), tretinoin (retinoic acid-carboxyl acid group-COOH), and adapalence (carboxyl group,-COOH).

In another aspect of the invention, the beneficial agent chemically conjugated to the polymer is a vitamin E, for example, (g-Tocopherol, d-Tocopherol).

20 In another aspect of the invention, the beneficial agent chemically conjugated to the polymer is a antioxidant, for example, alpha-lipoic acid (ALA,-COOH), dimethylaminoethanol (DMAE, -OH), Catalase (-OH).

25 In another aspect of the invention, the beneficial agent chemically conjugated to the polymer is a growth factor (with amine groups), for example, an epidermal growth factor (EGF- with amine groups), a transforming growth factor (TGF-with amine groups).

30 In another aspect of the invention, the beneficial agent chemically conjugated to the polymer is a peptide (with amine groups), for example, microcollagen pentapeptides, keratin, or elastin.

In another aspect of the present invention, an injectable dermal filler is provided which comprises a glycosaminoglycan polymer, at least a portion of which is crosslinked, and an antioxidant agent in an amount effective to reduce or prevent degradation of a composition disclosed herein, such as, e.g., enzymatic

5 degradation and/or chemical degradation of the composition. As such, the amount of an anti-oxidant agent included in a composition disclosed herein is between about 0.1% to about 10% by weight of the total composition. Non-limiting examples of antioxidant agents include a polyol, a flavonoid, a phytoalexin, an ascorbic acid agent, a tocopherol, a tocotrienol, a lipoic acid, a melatonin, a

10 carotenoid, an analog or derivative thereof, and any combination thereof. A composition disclosed herein may comprise a single antioxidant agent or a plurality of antioxidant agents, a retinol, coenzyme, idebenone, allopurinol, glutathione, sodium selenite.

15 Aspects of the present specification provide, in part, a hydrogel composition comprising a polymer and vitamin C covalently conjugated to the polymer. Non-limiting examples of vitamin C include ascorbic acid and sodium, potassium, and calcium salts of ascorbic acid, fat-soluble esters of ascorbic acid with long-chain fatty acids (ascorbyl palmitate or ascorbyl stearate), magnesium ascorbyl

20 phosphate (MAP), sodium ascorbyl phosphate (SAP), and ascorbic acid 2-glucoside (AA2GTM), sodium ascorbyl phosphate (AA2P), disodium ascorbyl sulfate, and ascorbyl 3-aminopropyl phosphate (vitagen).

The ascorbic acid may be present in the composition in an amount of, e.g., about

25 0.01% about 0.1%, about 0.2%, about 0.3%, about 0.4%, about 0.5%, about 0.6%, about 0.7%, about 0.8% about 0.9%, about 1.0%, about 2.0%, about 3.0%, about 4.0%, about 5.0%, about 6.0%, about 7.0%, about 8.0%, about 9.0%, or about 10% by weight of the total composition. In yet other aspects, a composition disclosed herein comprises an ascorbic acid in an amount of, e.g., at least 0.1%,

30 at least 0.2%, at least 0.3%, at least 0.4%, at least 0.5%, at least 0.6%, at least 0.7%, at least 0.8% at least 0.9%, at least 1.0%, at least 2.0%, at least 3.0%, at least 4.0%, at least 5.0%, at least 6.0%, at least 7.0%, at least 8.0%, at least

9.0%, or at least 10% by weight of the total composition. In still other aspects, a composition disclosed herein comprises an ascorbic acid in an amount of, e.g., at most 0.1%, at most 0.2%, at most 0.3%, at most 0.4%, at most 0.5%, at most 0.6%, at most 0.7%, at most 0.8% at most 0.9%, at most 1.0%, at most 2.0%, at 5 most 3.0%, at most 4.0%, at most 5.0%, at most 6.0%, at most 7.0%, at most 8.0%, at most 9.0%, or at most 10% by weight of the total composition. In further aspects, a composition disclosed herein comprises an ascorbic acid in an amount of, e.g., about 0.1% to about 0.5%, about 0.1% to about 1.0%, about 0.1% to about 2.0%, about 0.1% to about 3.0%, about 0.1% to about 4.0%, about 0.1% to 10 about 5.0%, about 0.2% to about 0.9%, about 0.2% to about 1.0%, about 0.2% to about 2.0%, about 0.5% to about 1.0%, or about 0.5% to about 2.0% by weight of the total composition.

In one embodiment of the present invention, a hydrogel composition is provided comprising a crosslinked hyaluronic acid-based polymer and a vitamin C 15 chemically conjugated to the polymer and having a conjugation degree of up to about 3 mol%, up to about 5 mol%, up to about 10 mol%, up to about 15 mol%, up to about 20 mol%, up to about 25 mol%, up to about 30 mol%, or up to about 40 mol%.

20 In one embodiment of the invention, a dermal filler is provided wherein the hyaluronic acid is crosslinked with Star-PEG epoxide or Star PEG amide. In this embodiment, the degree of conjugation may be between about 20 mol% and about 32 mol%.

25 In another embodiment of the invention, a dermal filler is provided wherein the hyaluronic acid is crosslinked with BDDE. In this embodiment, the degree of conjugation may be between about 3 mol% and about 15 mol %, for example, between about 10 mol% and about 13 mol%.

30 In some embodiments, the dermal fillers have a sustained bioavailability. For example, dermal fillers are provided which, when introduced into the skin of a

human being, are effective to release ascorbic acid or other vitamin into the human being for at least about 1 months and up to about 20 months or more.

Aspects of the present specification provide, in part, a hydrogel composition disclosed herein that exhibits a complex modulus, an elastic modulus, a viscous modulus and/or a $\tan \delta$. The compositions as disclosed herein are viscoelastic in that the composition has an elastic component (solid-like such as, e.g., crosslinked glycosaminoglycan polymers) and a viscous component (liquid-like such as, e.g., uncrosslinked glycosaminoglycan polymers or a carrier phase) when a force is applied (stress, deformation). The rheological attribute that described this property is the complex modulus (G^*), which defines a composition's total resistance to deformation. The complex modulus is a complex number with a real and imaginary part: $G^* = G' + iG''$. The absolute value of G^* is $\text{Abs}(G^*) = \sqrt{G'^2 + G''^2}$. The complex modulus can be defined as the sum of the elastic modulus (G') and the viscous modulus (G''). Falcone, et al., *Temporary Polysaccharide Dermal Fillers: A Model for Persistence Based on Physical Properties*, Dermatol Surg. 35(8): 1238-1243 (2009); Tezel, *supra*, 2008; Kablik, *supra*, 2009; Beasley, *supra*, 2009; each of which is hereby incorporated by reference in its entirety.

Elastic modulus, or modulus of elasticity, refers to the ability of a hydrogel material to resists deformation, or, conversely, an object's tendency to be non-permanently deformed when a force is applied to it. Elastic modulus characterizes the firmness of a composition and is also known as the storage modulus because it describes the storage of energy from the motion of the composition. The elastic modulus describes the interaction between elasticity and strength ($G' = \text{stress}/\text{strain}$) and, as such, provides a quantitative measurement of a composition's hardness or softness. The elastic modulus of an object is defined as the slope of its stress-strain curve in the elastic deformation region: $\lambda = \text{stress}/\text{strain}$, where λ is the elastic modulus in Pascal's; stress is the force causing the deformation divided by the area to which the force is applied; and strain is the ratio of the change caused by the stress to the original state of the object. Although depending on the speed at which the force is applied, a stiffer composition will have a higher elastic

modulus and it will take a greater force to deform the material a given distance, such as, e.g., an injection. Specifying how stresses are to be measured, including directions, allows for many types of elastic moduli to be defined. The three primary elastic moduli are tensile modulus, shear modulus, and bulk modulus.

5

Viscous modulus is also known as the loss modulus because it describes the energy that is lost as viscous dissipation. $\tan \delta$ is the ratio of the viscous modulus and the elastic modulus, $\tan \delta = G''/G'$. Falcone, *supra*, 2009.

For $\tan \delta$ values disclosed in the present specification, a $\tan \delta$ is obtained from the dynamic modulus at a frequency of 1 Hz. A lower $\tan \delta$ corresponds to a stiffer, harder, or

10 more elastic composition.

In another embodiment, a hydrogel composition disclosed herein exhibits an elastic modulus. In aspects of this embodiment, a hydrogel composition exhibits

15 an elastic modulus of, e.g., about 25 Pa, about 50 Pa, about 75 Pa, about 100 Pa, about 125 Pa, about 150 Pa, about 175 Pa, about 200 Pa, about 250 Pa, about

300 Pa, about 350 Pa, about 400 Pa, about 450 Pa, about 500 Pa, about 550 Pa, about 600 Pa, about 650 Pa, about 700 Pa, about 750 Pa, about 800 Pa, about

850 Pa, about 900 Pa, about 950 Pa, about 1,000 Pa, about 1,200 Pa, about

1,300 Pa, about 1,400 Pa, about 1,500 Pa, about 1,600 Pa, about 1,700 Pa, about

1,800 Pa, about 1,900 Pa, about 2,000 Pa, about 2,100 Pa, about 2,200 Pa, about

2,300 Pa, about 2,400 Pa, or about 2,500 Pa. In other aspects of this

embodiment, a hydrogel composition exhibits an elastic modulus of, e.g., at least

25 25 Pa, at least 50 Pa, at least 75 Pa, at least 100 Pa, at least 125 Pa, at least 150

Pa, at least 175 Pa, at least 200 Pa, at least 250 Pa, at least 300 Pa, at least 350

Pa, at least 400 Pa, at least 450 Pa, at least 500 Pa, at least 550 Pa, at least 600

Pa, at least 650 Pa, at least 700 Pa, at least 750 Pa, at least 800 Pa, at least 850

Pa, at least 900 Pa, at least 950 Pa, at least 1,000 Pa, at least 1,200 Pa, at least

1,300 Pa, at least 1,400 Pa, at least 1,500 Pa, at least 1,600 Pa, at least 1,700 Pa,

30 at least 1,800 Pa, at least 1,900 Pa, at least 2,000 Pa, at least 2,100 Pa, at least

2,200 Pa, at least 2,300 Pa, at least 2,400 Pa, or at least 2,500 Pa. In yet other

aspects of this embodiment, a hydrogel composition exhibits an elastic modulus

of, e.g., at most 25 Pa, at most 50 Pa, at most 75 Pa, at most 100 Pa, at most 125 Pa, at most 150 Pa, at most 175 Pa, at most 200 Pa, at most 250 Pa, at most 300 Pa, at most 350 Pa, at most 400 Pa, at most 450 Pa, at most 500 Pa, at most 550 Pa, at most 600 Pa, at most 650 Pa, at most 700 Pa, at most 750 Pa, at most 800 Pa, at most 850 Pa, at most 900 Pa, at most 950 Pa, at most 1,000 Pa, at most 1,200 Pa, at most 1,300 Pa, at most 1,400 Pa, at most 1,500 Pa, or at most 1,600 Pa. In still other aspects of this embodiment, a hydrogel composition exhibits an elastic modulus of, e.g., about 25 Pa to about 150 Pa, about 25 Pa to about 300 Pa, about 25 Pa to about 500 Pa, about 25 Pa to about 800 Pa, about 125 Pa to about 300 Pa, about 125 Pa to about 500 Pa, about 125 Pa to about 800 Pa, about 500 Pa to about 1,600 Pa, about 600 Pa to about 1,600 Pa, about 700 Pa to about 1,600 Pa, about 800 Pa to about 1,600 Pa, about 900 Pa to about 1,600 Pa, about 1,000 Pa to about 1,600 Pa, about 1,100 Pa to about 1,600 Pa, about 1,200 Pa to about 1,600 Pa, about 500 Pa to about 2,500 Pa, about 1,000 Pa to about 2,500 Pa, about 1,500 Pa to about 2,500 Pa, about 2,000 Pa to about 2,500 Pa, about 1,300 Pa to about 1,600 Pa, about 1,400 Pa to about 1,700 Pa, about 1,500 Pa to about 1,800 Pa, about 1,600 Pa to about 1,900 Pa, about 1,700 Pa to about 2,000 Pa, about 1,800 Pa to about 2,100 Pa, about 1,900 Pa to about 2,200 Pa, about 2,000 Pa to about 2,300 Pa, about 2,100 Pa to about 2,400 Pa, or about 2,200 Pa to about 2,500 Pa.

In another embodiment, a hydrogel composition disclosed herein exhibits a viscous modulus. In aspects of this embodiment, a hydrogel composition exhibits a viscous modulus of, e.g., about 10 Pa, about 20 Pa, about 30 Pa, about 40 Pa, about 50 Pa, about 60 Pa, about 70 Pa, about 80 Pa, about 90 Pa, about 100 Pa, about 150 Pa, about 200 Pa, about 250 Pa, about 300 Pa, about 350 Pa, about 400 Pa, about 450 Pa, about 500 Pa, about 550 Pa, about 600 Pa, about 650 Pa, or about 700 Pa. In other aspects of this embodiment, a hydrogel composition exhibits a viscous modulus of, e.g., at most 10 Pa, at most 20 Pa, at most 30 Pa, at most 40 Pa, at most 50 Pa, at most 60 Pa, at most 70 Pa, at most 80 Pa, at most 90 Pa, at most 100 Pa, at most 150 Pa, at most 200 Pa, at most 250 Pa, at most 300 Pa, at most 350 Pa, at most 400 Pa, at most 450 Pa, at most 500 Pa, at most 550 Pa, at most 600 Pa, at most 650 Pa, or at most 700 Pa.. In yet other

aspects of this embodiment, a hydrogel composition exhibits a viscous modulus of, e.g., about 10 Pa to about 30 Pa, about 10 Pa to about 50 Pa, about 10 Pa to about 100 Pa, about 10 Pa to about 150 Pa, about 70 Pa to about 100 Pa, about 50 Pa to about 350 Pa, about 150 Pa to about 450 Pa, about 250 Pa to about 550
5 Pa, about 350 Pa to about 700 Pa, about 50 Pa to about 150 Pa, about 100 Pa to about 200 Pa, about 150 Pa to about 250 Pa, about 200 Pa to about 300 Pa, about 250 Pa to about 350 Pa, about 300 Pa to about 400 Pa, about 350 Pa to about 450 Pa, about 400 Pa to about 500 Pa, about 450 Pa to about 550 Pa, about 500 Pa to about 600 Pa, about 550 Pa to about 650 Pa, or about 600 Pa to
10 about 700 Pa.

In another embodiment, a hydrogel composition disclosed herein exhibits a tan δ . In aspects of this embodiment, a hydrogel composition exhibits a tan δ of, e.g., about 0.1, about 0.2, about 0.3, about 0.4, about 0.5, about 0.6, about 0.7, about
15 0.8, about 0.9, about 1.0, about 1.1, about 1.2, about 1.3, about 1.4, about 1.5, about 1.6, about 1.7, about 1.8, about 1.9, about 2.0, about 2.1, about 2.2, about 2.3, about 2.4, or about 2.5. In other aspects of this embodiment, a hydrogel composition exhibits a tan δ of, e.g., at most 0.1, at most 0.2, at most 0.3, at most 0.4, at most 0.5, at most 0.6, at most 0.7, at most 0.8, at most 0.9, at most 1.0, at
20 most 1.1, at most 1.2, at most 1.3, at most 1.4, at most 1.5, at most 1.6, at most 1.7, at most 1.8, at most 1.9, at most 2.0, at most 2.1, at most 2.2, at most 2.3, at most 2.4, or at most 2.5. In yet other aspects of this embodiment, a hydrogel composition exhibits a tan δ of, e.g., about 0.1 to about 0.3, about 0.3 to about 0.5, about 0.5 to about 0.8, about 1.1 to about 1.4, about 1.4 to about 1.7, about 0.3 to
25 about 0.6, about 0.1 to about 0.5, about 0.5 to about 0.9, about 0.1 to about 0.6, about 0.1 to about 1.0, about 0.5 to about 1.5, about 1.0 to about 2.0, or about 1.5 to about 2.5.

Aspects of the present specification provide, in part, a hydrogel composition
30 disclosed herein having a transparency and/or translucency. Transparency (also called pellucidity or diaphaneity) is the physical property of allowing light to pass through a material, whereas translucency (also called translucence or

translucidity) only allows light to pass through diffusely. The opposite property is opacity. Transparent materials are clear, while translucent ones cannot be seen through clearly. The silk fibroin hydrogels disclosed herein may, or may not, exhibit optical properties such as transparency and translucency. In certain cases, 5 e.g., superficial line filling, it would be an advantage to have an opaque hydrogel. In other cases such as development of a lens or a "humor" for filling the eye, it would be an advantage to have a translucent hydrogel. These properties could be modified by affecting the structural distribution of the hydrogel material. Factors used to control a hydrogel's optical properties include, without limitation, polymer 10 concentration, gel crystallinity, and hydrogel homogeneity.

When light encounters a material, it can interact with it in several different ways. These interactions depend on the nature of the light (its wavelength, frequency, energy, etc.) and the nature of the material. Light waves interact with an object by 15 some combination of reflection, and transmittance with refraction. As such, an optically transparent material allows much of the light that falls on it to be transmitted, with little light being reflected. Materials which do not allow the transmission of light are called optically opaque or simply opaque.

20 In an embodiment, a hydrogel composition disclosed herein is optically transparent. In aspects of this embodiment, a hydrogel composition transmits, e.g., about 75% of the light, about 80% of the light, about 85% of the light, about 90% of the light, about 95% of the light, or about 100% of the light. In other aspects of this embodiment, a hydrogel composition transmits, e.g., at least 75% 25 of the light, at least 80% of the light, at least 85% of the light, at least 90% of the light, or at least 95% of the light. In yet other aspects of this embodiment, a hydrogel composition transmits, e.g., about 75% to about 100% of the light, about 80% to about 100% of the light, about 85% to about 100% of the light, about 90% to about 100% of the light, or about 95% to about 100% of the light.

30

In another embodiment, a hydrogel composition disclosed herein is optically opaque. In aspects of this embodiment, a hydrogel composition transmits, e.g.,

about 5% of the light, about 10% of the light, about 15% of the light, about 20% of the light, about 25% of the light, about 30% of the light, about 35% of the light, about 40% of the light, about 45% of the light, about 50% of the light, about 55% of the light, about 60% of the light, about 65% of the light, or about 70% of the light. In other aspects of this embodiment, a hydrogel composition transmits, e.g., at most 5% of the light, at most 10% of the light, at most 15% of the light, at most 20% of the light, at most 25% of the light, at most 30% of the light, at most 35% of the light, at most 40% of the light, at most 45% of the light, at most 50% of the light, at most 55% of the light, at most 60% of the light, at most 65% of the light, at most 70% of the light, or at most 75% of the light. In other aspects of this embodiment, a hydrogel composition transmits, e.g., about 5% to about 15%, about 5% to about 20%, about 5% to about 25%, about 5% to about 30%, about 5% to about 35%, about 5% to about 40%, about 5% to about 45%, about 5% to about 50%, about 5% to about 55%, about 5% to about 60%, about 5% to about 65%, about 5% to about 70%, about 5% to about 75%, about 15% to about 20%, about 15% to about 25%, about 15% to about 30%, about 15% to about 35%, about 15% to about 40%, about 15% to about 45%, about 15% to about 50%, about 15% to about 55%, about 15% to about 60%, about 15% to about 65%, about 15% to about 70%, about 15% to about 75%, about 25% to about 35%, about 25% to about 40%, about 25% to about 45%, about 25% to about 50%, about 25% to about 55%, about 25% to about 60%, about 25% to about 65%, about 25% to about 70%, or about 25% to about 75%, of the light.

In an embodiment, a hydrogel composition disclosed herein is optically translucent. In aspects of this embodiment, a hydrogel composition diffusely transmits, e.g., about 75% of the light, about 80% of the light, about 85% of the light, about 90% of the light, about 95% of the light, or about 100% of the light. In other aspects of this embodiment, a hydrogel composition diffusely transmits, e.g., at least 75% of the light, at least 80% of the light, at least 85% of the light, at least 90% of the light, or at least 95% of the light. In yet other aspects of this embodiment, a hydrogel composition diffusely transmits, e.g., about 75% to about 100% of the light, about 80% to about 100% of the light, about 85% to about 100%

of the light, about 90% to about 100% of the light, or about 95% to about 100% of the light.

A hydrogel composition disclosed herein may be further processed by pulverizing

5 the hydrogel into particles and optionally mixed with a carrier phase such as, e.g., water or a saline solution to form an injectable or topical substance like a solution, oil, lotion, gel, ointment, cream, slurry, salve, or paste. As such, the disclosed hydrogel compositions may be monophasic or multiphasic compositions. A hydrogel may be milled to a particle size from about 10 μm to about 1000 μm in

10 diameter, such as about 15 μm to about 30 μm , about 50 μm to about 75 μm , about 100 μm to about 150 μm , about 200 μm to about 300 μm , about 450 μm to about 550 μm , about 600 μm to about 700 μm , about 750 μm to about 850 μm , or about 900 μm to about 1,000 μm .

15 Aspects of the present specification provide, in part, a composition disclosed herein is injectable. As used herein, the term "injectable" refers to a material having the properties necessary to administer the composition into a skin region of an individual using an injection device with a fine needle. As used herein, the term "fine needle" refers to a needle that is 27 gauge or smaller. Injectability of a

20 composition disclosed herein can be accomplished by sizing the hydrogel particles as discussed above.

In aspect of this embodiment, a hydrogel composition disclosed herein is injectable through a fine needle. In other aspects of this embodiment, a hydrogel

25 composition disclosed herein is injectable through a needle of, e.g., about 27 gauge, about 30 gauge, or about 32 gauge. In yet other aspects of this embodiment, a hydrogel composition disclosed herein is injectable through a needle of, e.g., 22 gauge or smaller, 27 gauge or smaller, 30 gauge or smaller, or 32 gauge or smaller. In still other aspects of this embodiment, a hydrogel

30 composition disclosed herein is injectable through a needle of, e.g., about 22 gauge to about 35 gauge, 22 gauge to about 34 gauge, 22 gauge to about 33

gauge, 22 gauge to about 32 gauge, about 22 gauge to about 27 gauge, or about 27 gauge to about 32 gauge.

In aspects of this embodiment, a hydrogel composition disclosed herein can be
5 injected with an extrusion force of about 60 N, about 55 N, about 50 N, about 45 N, about 40 N, about 35 N, about 30 N, about 25 N, about 20 N, or about 15 N at speeds of 100 mm/min. In other aspects of this embodiment, a hydrogel composition disclosed herein can be injected through a 27 gauge needle with an extrusion force of about 60 N or less, about 55 N or less, about 50 N or less, about
10 45 N or less, about 40 N or less, about 35 N or less, about 30 N or less, about 25 N or less, about 20 N or less, about 15 N or less, about 10 N or less, or about 5 N or less. In yet other aspects of this embodiment, a hydrogel composition disclosed herein can be injected through a 30 gauge needle with an extrusion force of about 60 N or less, about 55 N or less, about 50 N or less, about 45 N or less, about 40
15 N or less, about 35 N or less, about 30 N or less, about 25 N or less, about 20 N or less, about 15 N or less, about 10 N or less, or about 5 N or less. In still other aspects of this embodiment, a hydrogel composition disclosed herein can be injected through a 32 gauge needle with an extrusion force of about 60 N or less, about 55 N or less, about 50 N or less, about 45 N or less, about 40 N or less,
20 about 35 N or less, about 30 N or less, about 25 N or less, about 20 N or less, about 15 N or less, about 10 N or less, or about 5 N or less.

Aspects of the present specification provide, in part, a hydrogel composition disclosed herein that exhibits cohesivity. Cohesivity, also referred to as cohesion
25 cohesive attraction, cohesive force, or compression force is a physical property of a material, caused by the intermolecular attraction between like-molecules within the material that acts to unite the molecules. Cohesivity is expressed in terms of grams-force (gmf). Cohesiveness is affected by, among other factors, the molecular weight ratio of the initial free glycosaminoglycan polymer, the degree of
30 crosslinking of glycosaminoglycan polymers, the amount of residual free glycosaminoglycan polymers following crosslinking, and the pH of the hydrogel composition. A composition should be sufficiently cohesive as to remain localized

to a site of administration. Additionally, in certain applications, a sufficient cohesiveness is important for a composition to retain its shape, and thus functionality, in the event of mechanical load cycling. As such, in one embodiment, a hydrogel composition disclosed herein exhibits cohesivity, on par 5 with water. In yet another embodiment, a hydrogel composition disclosed herein exhibits sufficient cohesivity to remain localized to a site of administration. In still another embodiment, a hydrogel composition disclosed herein exhibits sufficient cohesivity to retain its shape. In a further embodiment, a hydrogel composition disclosed herein exhibits sufficient cohesivity to retain its shape and functionality.

10

Aspects of the present specification provide, in part, a hydrogel composition disclosed herein that exhibits a physiologically-acceptable osmolarity. As used herein, the term "osmolarity" refers to the concentration of osmotically active solutes in solution. As used herein, the term "a physiologically-acceptable 15 osmolarity" refers to an osmolarity in accord with, or characteristic of, the normal functioning of a living organism. As such, administration of a hydrogel composition as disclosed herein exhibits an osmolarity that has substantially no long term or permanent detrimental effect when administered to a mammal. Osmolarity is expressed in terms of osmoles of osmotically active solute per liter of 20 solvent (Osmol/L or Osm/L). Osmolarity is distinct from molarity because it measures moles of osmotically active solute particles rather than moles of solute. The distinction arises because some compounds can dissociate in solution, whereas others cannot. The osmolarity of a solution can be calculated from the following expression: $Osmol/L = \sum \varphi_i \eta_i C_i$, where φ is the osmotic coefficient, 25 which accounts for the degree of non-ideality of the solution; η is the number of particles (e.g. ions) into which a molecule dissociates; and C is the molar concentration of the solute; and i is the index representing the identity of a particular solute. The osmolarity of a hydrogel composition disclosed herein can be measured using a conventional method that measures solutions.

30

In an embodiment, a hydrogel composition disclosed herein exhibits a physiologically-acceptable osmolarity. In aspects of this embodiment, a hydrogel

composition exhibits an osmolarity of, e.g., about 100 mOsm/L, about 150 mOsm/L, about 200 mOsm/L, about 250 mOsm/L, about 300 mOsm/L, about 350 mOsm/L, about 400 mOsm/L, about 450 mOsm/L, or about 500 mOsm/L. In other aspects of this embodiment, a hydrogel composition exhibits an osmolarity of, e.g.,

5 at least 100 mOsm/L, at least 150 mOsm/L, at least 200 mOsm/L, at least 250 mOsm/L, at least 300 mOsm/L, at least 350 mOsm/L, at least 400 mOsm/L, at least 450 mOsm/L, or at least 500 mOsm/L. In yet other aspects of this embodiment, a hydrogel composition exhibits an osmolarity of, e.g., at most 100 mOsm/L, at most 150 mOsm/L, at most 200 mOsm/L, at most 250 mOsm/L, at

10 most 300 mOsm/L, at most 350 mOsm/L, at most 400 mOsm/L, at most 450 mOsm/L, or at most 500 mOsm/L. In still other aspects of this embodiment, a hydrogel composition exhibits an osmolarity of, e.g., about 100 mOsm/L to about 500 mOsm/L, about 200 mOsm/L to about 500 mOsm/L, about 200 mOsm/L to about 400 mOsm/L, about 300 mOsm/L to about 400 mOsm/L, about 270 mOsm/L

15 to about 390 mOsm/L, about 225 mOsm/L to about 350 mOsm/L, about 250 mOsm/L to about 325 mOsm/L, about 275 mOsm/L to about 300 mOsm/L, or about 285 mOsm/L to about 290 mOsm/L.

Aspects of the present specification provide, in part, a hydrogel composition

20 disclosed herein that exhibits a physiologically-acceptable osmolality. As used herein, the term "osmolality" refers to the concentration of osmotically active solutes per kilo of solvent in the body. As used herein, the term "a physiologically-acceptable osmolality" refers to an osmolality in accord with, or characteristic of, the normal functioning of a living organism. As such, administration of a hydrogel

25 composition disclosed herein exhibits an osmolality that has substantially no long term or permanent detrimental effect when administered to a mammal. Osmolality is expressed in terms of osmoles of osmotically active solute per kilogram of solvent (osmol/kg or Osm/kg) and is equal to the sum of the molalities of all the solutes present in that solution. The osmolality of a solution can be measured

30 using an osmometer. The most commonly used instrument in modern laboratories is a freezing point depression osmometer. This instruments measure the change in freezing point that occurs in a solution with increasing osmolality (freezing point

depression osmometer) or the change in vapor pressure that occurs in a solution with increasing osmolality (vapor pressure depression osmometer).

In an embodiment, a hydrogel composition disclosed herein exhibits a physiologically-acceptable osmolality. In aspects of this embodiment, a hydrogel 5 composition exhibits an osmolality of, e.g., about 100 mOsm/kg, about 150 mOsm/kg, about 200 mOsm/kg, about 250 mOsm/kg, about 300 mOsm/kg, about 350 mOsm/kg, about 400 mOsm/kg, about 450 mOsm/kg, or about 500 mOsm/kg. In other aspects of this embodiment, a hydrogel composition exhibits an osmolality of, e.g., at least 100 mOsm/kg, at least 150 mOsm/kg, at least 200 mOsm/kg, at 10 least 250 mOsm/kg, at least 300 mOsm/kg, at least 350 mOsm/kg, at least 400 mOsm/kg, at least 450 mOsm/kg, or at least 500 mOsm/kg. In yet other aspects of this embodiment, a hydrogel composition exhibits an osmolality of, e.g., at most 100 mOsm/kg, at most 150 mOsm/kg, at most 200 mOsm/kg, at most 250 mOsm/kg, at most 300 mOsm/kg, at most 350 mOsm/kg, at most 400 mOsm/kg, 15 at most 450 mOsm/kg, or at most 500 mOsm/kg. In still other aspects of this embodiment, a hydrogel composition exhibits an osmolality of, e.g., about 100 mOsm/kg to about 500 mOsm/kg, about 200 mOsm/kg to about 500 mOsm/kg, about 200 mOsm/kg to about 400 mOsm/kg, about 300 mOsm/kg to about 400 mOsm/kg, about 270 mOsm/kg to about 390 mOsm/kg, about 225 mOsm/kg to 20 about 350 mOsm/kg, about 250 mOsm/kg to about 325 mOsm/kg, about 275 mOsm/kg to about 300 mOsm/kg, or about 285 mOsm/kg to about 290 mOsm/kg.

Aspects of the present specification provide, in part, a hydrogel composition disclosed herein that exhibits substantial stability. As used herein, the term 25 “stability” or “stable” when referring to a hydrogel composition disclosed herein refers to a composition that is not prone to degrading, decomposing, or breaking down to any substantial or significant degree while stored before administration to an individual. As used herein, the term “substantial heat stability”, “substantially heat stable”, “autoclave stable”, or “steam sterilization stable” refers to a hydrogel 30 composition disclosed herein that is substantially stable when subjected to a heat treatment as disclosed herein.

Stability of a hydrogel composition disclosed herein can be determined by subjecting a hydrogel composition to a heat treatment, such as, e.g., steam sterilization at normal pressure or under pressure (e.g., autoclaving). Preferably the heat treatment is carried out at a temperature of at least about 100 °C for 5 between about one minute and about 10 minutes. Substantial stability of a hydrogel composition disclosed herein can be evaluated 1) by determining the change in the extrusion force (ΔF) of a hydrogel composition disclosed herein after sterilization, where the change in extrusion force less 2N is indicative of a substantially stable hydrogel composition as measured by (the extrusion force of a 10 hydrogel composition with the specified additives) minus (the extrusion force of the a hydrogel composition without the added additives); and/or 2) by determining the change in rheological properties of a hydrogel composition disclosed herein after sterilization, where the change in $\tan \delta$ 1 Hz of less than 0.1 is indicative of a substantially stable hydrogel composition as measured by ($\tan \delta$ 1 Hz of gel 15 formulation with additives) minus ($\tan \delta$ 1 Hz of gel formulation without additives). As such, a substantially stable hydrogel composition disclosed herein retains one or more of the following characteristics after sterilization: homogeneousness, extrusion force, cohesiveness, hyaluronan concentration, agent(s) concentration, osmolarity, pH, or other rheological characteristics desired by the hydrogel before 20 the heat treatment.

In an embodiment, a hydrogel composition comprising a glycosaminoglycan polymer and the at least one agent disclosed herein is processed using a heat treatment that maintains the desired hydrogel properties disclosed herein. In 25 aspects of this embodiment, a hydrogel composition comprising a glycosaminoglycan polymer and the at least one agent disclosed herein is processed using a heat treatment of, e.g., about 100 °C, about 105 °C, about 110 °C, about 115 °C, about 120 °C, about 125 °C, or about 130 °C. In other aspects of this embodiment, a hydrogel composition comprising a glycosaminoglycan 30 polymer and the at least one agent disclosed herein is processed using a heat treatment of, e.g., at least 100 °C, at least 105 °C, at least 110 °C, at least 115 °C, at least 120 °C, at least 125 °C, or at least 130 °C. In yet other aspects of this

embodiment, a hydrogel composition comprising a glycosaminoglycan polymer and the at least one agent disclosed herein is processed using a heat treatment of, e.g., about 100 °C to about 120 °C, about 100 °C to about 125 °C, about 100 °C to about 130 °C, about 100 °C to about 135 °C, about 110 °C to about 120 °C, 5 about 110 °C to about 125 °C, about 110 °C to about 130 °C, about 110 °C to about 135 °C, about 120 °C to about 125 °C, about 120 °C to about 130 °C, about 120 °C to about 135 °C, about 125 °C to about 130 °C, or about 125 °C to about 135 °C.

10 Long term stability of a hydrogel composition disclosed herein can be determined by subjecting a hydrogel composition to a heat treatment, such as, e.g., storage in an about 45 °C environment for about 60 days. Long term stability of a hydrogel composition disclosed herein can be evaluated 1) by assessing the clarity and color of a hydrogel composition after the 45 °C heat treatment, with a clear and 15 uncolored hydrogel composition being indicative of a substantially stable hydrogel composition; 2) by determining the change in the extrusion force (ΔF) of a hydrogel composition disclosed herein after the 45 °C heat treatment, where the change in extrusion force less 2N is indicative of a substantially stable hydrogel composition as measured by (the extrusion force of a hydrogel composition with 20 the specified additives before the 45 °C heat treatment) minus (the extrusion force of the a hydrogel composition with the specified additives after the 45 °C heat treatment); and/or 3) by determining the change in rheological properties of a hydrogel composition disclosed herein after sterilization, where the change in $\tan \delta$ 1 Hz of less than 0.1 is indicative of a substantially stable hydrogel composition 25 as measured by ($\tan \delta$ 1 Hz of gel formulation with the specified additives before the 45 °C heat treatment) minus ($\tan \delta$ 1 Hz of gel formulation with the specified additives after the 45 °C heat treatment). As such, a long term stability of a hydrogel composition disclosed herein is evaluated by retention of one or more of the following characteristics after the 45 °C heat treatment: clarity (transparency 30 and translucency), homogeneity, and cohesiveness.

In aspects of this embodiment, a hydrogel composition is substantially stable at room temperature for, e.g., about 3 months, about 6 months, about 9 months, about 12 months, about 15 months, about 18 months, about 21 months, about 24 months, about 27 months, about 30 months, about 33 months, or about 36 months. In other aspects of this embodiment, a hydrogel composition is substantially stable at room temperature for, e.g., at least 3 months, at least 6 months, at least 9 months, at least 12 months, at least 15 months, at least 18 months, at least 21 months, at least 24 months, at least 27 months, at least 30 months, at least 33 months, or at least 36 months. In other aspects of this embodiment, a hydrogel composition is substantially stable at room temperature for, e.g., about 3 months to about 12 months, about 3 months to about 18 months, about 3 months to about 24 months, about 3 months to about 30 months, about 3 months to about 36 months, about 6 months to about 12 months, about 6 months to about 18 months, about 6 months to about 24 months, about 6 months to about 30 months, about 6 months to about 36 months, about 9 months to about 12 months, about 9 months to about 18 months, about 9 months to about 24 months, about 9 months to about 30 months, about 9 months to about 36 months, about 12 months to about 18 months, about 12 months to about 24 months, about 12 months to about 30 months, about 12 months to about 36 months, about 18 months to about 24 months, about 18 months to about 30 months, or about 18 months to about 36 months.

Aspects of the present specification provide, in part, a hydrogel composition disclosed herein that is a pharmaceutically-acceptable composition. As used herein, the term "pharmaceutically acceptable" means any molecular entity or composition that does not produce an adverse, allergic or other untoward or unwanted reaction when administered to an individual. A pharmaceutically-acceptable hydrogel composition is useful for medical and veterinary applications. A pharmaceutically-acceptable hydrogel composition may be administered to an individual alone, or in combination with other supplementary active ingredients, agents, drugs or hormones.

Aspects of the present specification provide, in part, a hydrogel composition as disclosed herein comprising a pharmacologically acceptable excipient. As used herein, the term "pharmacologically acceptable excipient" is synonymous with "pharmacological excipient" or "excipient" and refers to any excipient that has

5 substantially no long term or permanent detrimental effect when administered to mammal and encompasses compounds such as, e.g., stabilizing agent, a bulking agent, a cryo-protectant, a lyo-protectant, an additive, a vehicle, a carrier, a diluent, or an auxiliary. An excipient generally is mixed with an active ingredient, or permitted to dilute or enclose the active ingredient and can be a solid, semi-

10 solid, or liquid agent. It is also envisioned that a pharmaceutical composition as disclosed herein can include one or more pharmaceutically acceptable excipients that facilitate processing of an active ingredient into pharmaceutically acceptable compositions. Insofar as any pharmacologically acceptable excipient is not incompatible with the active ingredient, its use in pharmaceutically acceptable

15 compositions is contemplated. Non-limiting examples of pharmacologically acceptable excipients can be found in, e.g., *Pharmaceutical Dosage Forms and Drug Delivery Systems* (Howard C. Ansel et al., eds., Lippincott Williams & Wilkins Publishers, 7th ed. 1999); *Remington: The Science and Practice of Pharmacy* (Alfonso R. Gennaro ed., Lippincott, Williams & Wilkins, 20th ed. 2000); *Goodman*

20 & *Gilman's The Pharmacological Basis of Therapeutics* (Joel G. Hardman et al., eds., McGraw-Hill Professional, 10th ed. 2001); and *Handbook of Pharmaceutical Excipients* (Raymond C. Rowe et al., APhA Publications, 4th edition 2003), each of which is hereby incorporated by reference in its entirety.

25 It is further envisioned that a hydrogel composition disclosed herein may optionally include, without limitation, other pharmaceutically acceptable components, including, without limitation, buffers, preservatives, tonicity adjusters, salts, antioxidants, osmolality adjusting agents, emulsifying agents, wetting agents, sweetening or flavoring agents, and the like.

30

A pharmaceutically acceptable buffer is a buffer that can be used to prepare a hydrogel composition disclosed herein, provided that the resulting preparation is

pharmaceutically acceptable. Non-limiting examples of pharmaceutically acceptable buffers include acetate buffers, borate buffers, citrate buffers, neutral buffered salines, phosphate buffers, and phosphate buffered salines. Any concentration of a pharmaceutically acceptable buffer can be useful in formulating

5 a pharmaceutical composition disclosed herein, with the proviso that a therapeutically effective amount of the active ingredient is recovered using this effective concentration of buffer. Non-limiting examples of concentrations of physiologically-acceptable buffers occur within the range of about 0.1 mM to about 900 mM. The pH of pharmaceutically acceptable buffers may be adjusted,

10 provided that the resulting preparation is pharmaceutically acceptable. It is understood that acids or bases can be used to adjust the pH of a pharmaceutical composition as needed. Any buffered pH level can be useful in formulating a pharmaceutical composition, with the proviso that a therapeutically effective amount of the matrix polymer active ingredient is recovered using this effective pH

15 level. Non-limiting examples of physiologically-acceptable pH occur within the range of about pH 5.0 to about pH 8.5. For example, the pH of a hydrogel composition disclosed herein can be about 5.0 to about 8.0, or about 6.5 to about 7.5, about 7.0 to about 7.4, or about 7.1 to about 7.3.

20 Pharmaceutically acceptable preservatives include, without limitation, sodium metabisulfite, sodium thiosulfate, acetylcysteine, butylated hydroxyanisole and butylated hydroxytoluene. Pharmaceutically acceptable preservatives include, without limitation, benzalkonium chloride, chlorobutanol, thimerosal, phenylmercuric acetate, phenylmercuric nitrate, a stabilized oxy chlo

25 composition, such as, e.g., PURITE[®] (Allergan, Inc. Irvine, CA) and chelants, such as, e.g., DTPA or DTPA-bisamide, calcium DTPA, and CaNaDTPA-bisamide.

Pharmaceutically acceptable tonicity adjustors useful in a hydrogel composition disclosed herein include, without limitation, salts such as, e.g., sodium chloride and potassium chloride; and glycerin. The composition may be provided as a salt and can be formed with many acids, including but not limited to, hydrochloric, sulfuric, acetic, lactic, tartaric, malic, succinic, etc. Salts tend to be more soluble in

aqueous or other protonic solvents than are the corresponding free base forms. It is understood that these and other substances known in the art of pharmacology can be included in a pharmaceutical composition disclosed herein. Other non-limiting examples of pharmacologically acceptable components can be found in, 5 e.g., Ansel, *supra*, (1999); Gennaro, *supra*, (2000); Hardman, *supra*, (2001); and Rowe, *supra*, (2003), each of which is hereby incorporated by reference in its entirety.

Aspects of the present specification provide, in part, a method of treating a soft 10 tissue condition of an individual by administering a hydrogel composition disclosed herein. As used herein, the term "treating," refers to reducing or eliminating in an individual a cosmetic or clinical symptom of a soft tissue condition characterized by a soft tissue imperfection, defect, disease, and/or disorder; or delaying or preventing in an individual the onset of a cosmetic or clinical symptom of a 15 condition characterized by a soft tissue imperfection, defect, disease, and/or disorder. For example, the term "treating" can mean reducing a symptom of a condition characterized by a soft tissue defect, disease, and/or disorder by, e.g., at least 20%, at least 30%, at least 40%, at least 50%, at least 60%, at least 70%, at least 80%, at least 90% or at least 100%. The effectiveness of a hydrogel 20 composition disclosed herein in treating a condition characterized by a soft tissue defect, disease, and/or disorder can be determined by observing one or more cosmetic, clinical symptoms, and/or physiological indicators associated with the condition. An improvement in a soft tissue defect, disease, and/or disorder also can be indicated by a reduced need for a concurrent therapy. Those of skill in the 25 art will know the appropriate symptoms or indicators associated with specific soft tissue defect, disease, and/or disorder and will know how to determine if an individual is a candidate for treatment with a compound or composition disclosed herein.

30 A hydrogel composition is administered to an individual. An individual is typically a human being of any age, gender or race. Typically, any individual who is a candidate for a conventional procedure to treat a soft tissue condition is a

candidate for a method disclosed herein. Although a subject experiencing the signs of aging skin is an adult, subjects experiencing premature aging or other skin conditions suitable for treatment (for example, a scar) can also be treated with a hydrogel composition disclosed herein. In addition, the presently disclosed 5 hydrogel compositions and methods may apply to individuals seeking a small/moderate enlargement, shape change or contour alteration of a body part or region, which may not be technically possible or aesthetically acceptable with existing soft tissue implant technology. Pre-operative evaluation typically includes routine history and physical examination in addition to thorough informed consent 10 disclosing all relevant risks and benefits of the procedure.

The hydrogel composition and methods disclosed herein are useful in treating a soft tissue condition. A soft tissue condition includes, without limitation, a soft tissue imperfection, defect, disease, and/or disorder. Non-limiting examples of a 15 soft tissue condition include breast imperfection, defect, disease and/or disorder, such as, e.g., a breast augmentation, a breast reconstruction, mastopexy, micromastia, thoracic hypoplasia, Poland's syndrome, defects due to implant complications like capsular contraction and/or rupture; a facial imperfection, defect, disease or disorder, such as, e.g., a facial augmentation, a facial 20 reconstruction, a mesotherapy, Parry-Romberg syndrome, lupus erythematosus profundus, dermal divots, scars, sunken checks, thin lips, nasal imperfections or defects, retro-orbital imperfections or defects, a facial fold, line and/or wrinkle like a glabellar line, a nasolabial line, a perioral line, and/or a marionette line, and/or other contour deformities or imperfections of the face; a neck imperfection, defect, 25 disease or disorder; a skin imperfection, defect, disease and/or disorder; other soft tissue imperfections, defects, diseases and/or disorders, such as, e.g., an augmentation or a reconstruction of the upper arm, lower arm, hand, shoulder, back, torso including abdomen, buttocks, upper leg, lower leg including calves, foot including plantar fat pad, eye, genitals, or other body part, region or area, or a 30 disease or disorder affecting these body parts, regions or areas; urinary incontinence, fecal incontinence, other forms of incontinence; and gastroesophageal reflux disease (GERD). As used herein, the term

“mesotherapy” refers to a non-surgical cosmetic treatment technique of the skin involving intra-epidermal, intra-dermal, and/or subcutaneous injection of an agent administered as small multiple droplets into the epidermis, dermo-epidermal junction, and/or the dermis.

5

The amount of a hydrogel composition used with any of the methods as disclosed herein will typically be determined based on the alteration and/or improvement desired, the reduction and/or elimination of a soft tissue condition symptom

desired, the clinical and/or cosmetic effect desired by the individual and/or 10 physician, and the body part or region being treated. The effectiveness of composition administration may be manifested by one or more of the following clinical and/or cosmetic measures: altered and/or improved soft tissue shape,

altered and/or improved soft tissue size, altered and/or improved soft tissue contour, altered and/or improved tissue function, tissue ingrowth support and/or 15

new collagen deposition, sustained engraftment of composition, improved patient satisfaction and/or quality of life, and decreased use of implantable foreign material.

For example, for breast augmentation procedures, effectiveness of the 20

compositions and methods may be manifested by one or more of the following clinical and/or cosmetic measures: increased breast size, altered breast shape, altered breast contour, sustained engraftment, reduction in the risk of capsular contraction, decreased rate of liponecrotic cyst formation, improved patient satisfaction and/or quality of life, and decreased use of breast implant.

25

As another example, effectiveness of the compositions and methods in treating a facial soft tissue may be manifested by one or more of the following clinical and/or cosmetic measures: increased size, shape, and/or contour of facial feature like increased size, shape, and/or contour of lip, cheek or eye region; altered size,

30 shape, and/or contour of facial feature like altered size, shape, and/or contour of lip, cheek or eye region shape; reduction or elimination of a wrinkle, fold or line in the skin; resistance to a wrinkle, fold or line in the skin; rehydration of the skin;

increased elasticity to the skin; reduction or elimination of skin roughness; increased and/or improved skin tautness; reduction or elimination of stretch lines or marks; increased and/or improved skin tone, shine, brightness and/or radiance; increased and/or improved skin color, reduction or elimination of skin paleness;

5 sustained engraftment of composition; decreased side effects; improved patient satisfaction and/or quality of life.

As yet another example, for urinary incontinence procedures, effectiveness of the compositions and methods for sphincter support may be manifested by one or

10 10 more of the following clinical measures: decreased frequency of incontinence, sustained engraftment, improved patient satisfaction and/or quality of life, and decreased use of implantable foreign filler.

In aspects of this embodiment, the amount of a hydrogel composition administered

15 15 is, e.g., about 0.01 g, about 0.05 g, about 0.1 g, about 0.5 g, about 1 g, about 5 g, about 10 g, about 20 g, about 30 g, about 40 g, about 50 g, about 60 g, about 70 g, about 80 g, about 90 g, about 100 g, about 150 g, or about 200 g. In other aspects of this embodiment, the amount of a hydrogel composition administered is, e.g., about 0.01 g to about 0.1 g, about 0.1 g to about 1 g, about 1 g to about

20 20 10 g, about 10 g to about 100 g, or about 50 g to about 200 g. In yet other aspects of this embodiment, the amount of a hydrogel composition administered is, e.g., about 0.01 mL, about 0.05 mL, about 0.1 mL, about 0.5 mL, about 1 mL, about 5 mL, about 10 mL, about 20 mL, about 30 mL, about 40 mL, about 50 mL, about 60 mL, about 70 g, about 80 mL, about 90 mL, about 100 mL, about 150 mL, or about 200 mL. In other aspects of this embodiment, the amount of a hydrogel composition administered is, e.g., about 0.01 mL to about 0.1 mL, about 0.1 mL to about 1 mL, about 1 mL to about 10 mL, about 10 mL to about 100 mL, or about 50 mL to about 200 mL.

25 25 30 The duration of treatment will typically be determined based on the cosmetic and/or clinical effect desired by the individual and/or physician and the body part or region being treated. In aspects of this embodiment, administration of a

hydrogel composition disclosed herein can treat a soft tissue condition for, e.g., about 6 months, about 7 months, about 8 months, about 9 months, about 10 months, about 11 months, about 12 months, about 13 months, about 14 months, about 15 months, about 18 months, or about 24 months. In other aspects of this 5 embodiment, administration of a hydrogel composition disclosed herein can treat a soft tissue condition for, e.g., at least 6 months, at least 7 months, at least 8 months, at least 9 months, at least 10 months, at least 11 months, at least 12 months, at least 13 months, at least 14 months, at least 15 months, at least 18 months, or at least 24 months. In yet aspects of this embodiment, administration 10 of a hydrogel composition disclosed herein can treat a soft tissue condition for, e.g., about 6 months to about 12 months, about 6 months to about 15 months, about 6 months to about 18 months, about 6 months to about 21 months, about 6 months to about 24 months, about 9 months to about 12 months, about 9 months to about 15 months, about 9 months to about 18 months, about 9 months to about 21 months, about 21 months, about 6 months to about 24 months, about 12 months to about 15 months, about 12 months to about 18 months, about 12 months to about 21 months, about 12 months to about 24 months, about 15 months to about 18 months, about 15 months to about 21 months, about 15 months to about 24 months, about 18 months to about 21 months, about 18 months to about 24 15 months, about 18 months to about 21 months, or about 21 months to about 24 months. 20

Aspects of the present specification provide, in part, administering a hydrogel composition disclosed herein. As used herein, the term “administering” means any delivery mechanism that provides a composition disclosed herein to an 25 individual that potentially results in a clinically, therapeutically, or experimentally beneficial result. The actual delivery mechanism used to administer a composition to an individual can be determined by a person of ordinary skill in the art by taking into account factors, including, without limitation, the type of skin condition, the location of the skin condition, the cause of the skin condition, the severity of the 30 skin condition, the degree of relief desired, the duration of relief desired, the particular composition used, the rate of excretion of the particular composition used, the pharmacodynamics of the particular composition used, the nature of the

other compounds included in the particular composition used, the particular route of administration, the particular characteristics, history and risk factors of the individual, such as, e.g., age, weight, general health and the like, or any combination thereof. In an aspect of this embodiment, a composition disclosed
5 herein is administered to a skin region of an individual by injection.

The route of administration of a hydrogel composition to an individual patient will typically be determined based on the cosmetic and/or clinical effect desired by the individual and/or physician and the body part or region being treated. A
10 composition disclosed herein may be administered by any means known to persons of ordinary skill in the art including, without limitation, syringe with needle, a pistol (for example, a hydropneumatic-compression pistol), catheter, topically, or by direct surgical implantation. The hydrogel composition disclosed herein can be administered into a skin region such as, e.g., a dermal region or a hypodermal
15 region. For example, a hydrogel composition disclosed herein can be injected utilizing needles with a diameter of about 0.26 mm to about 0.4 mm and a length ranging from about 4 mm to about 14 mm. Alternately, the needles can be 21 to 32 G and have a length of about 4 mm to about 70 mm. Preferably, the needle is a single-use needle. The needle can be combined with a syringe, catheter, and/or
20 a pistol.

In addition, a composition disclosed herein can be administered once, or over a plurality of times. Ultimately, the timing used will follow quality care standards. For example, a hydrogel composition disclosed herein can be administered once or
25 over several sessions with the sessions spaced apart by a few days, or weeks. For instance, an individual can be administered a hydrogel composition disclosed herein every 1, 2, 3, 4, 5, 6, or 7 days or every 1, 2, 3, or 4 weeks. The administration a hydrogel composition disclosed herein to an individual can be on a monthly or bi-monthly basis or administered every 3, 6, 9, or 12 months.

30

For a breast soft tissue replacement procedure, the route of administration may include axillary, periareolar, and/or inframammary routes. Alternatively or in

addition, a composition may be delivered through a transaxillary endoscopic subpectoral approach. For a facial soft tissue replacement procedure, the route of administration can be frontal, temporal, zygomatic, periocular, mandibula, perioral or chin routes. In urinary incontinence procedures, the route of administration may 5 include transurethral or periurethral routes. Alternatively or in addition, administration may be delivered via an antegrade route. The routes discussed herein do not exclude the use of multiple routes to achieve the desired clinical effect.

10 Aspects of the present specification provide, in part, a dermal region. As used herein, the term "dermal region" refers to the region of skin comprising the epidermal-dermal junction and the dermis including the superficial dermis (papillary region) and the deep dermis (reticular region). The skin is composed of three primary layers: the epidermis, which provides waterproofing and serves as a 15 barrier to infection; the dermis, which serves as a location for the appendages of skin; and the hypodermis (subcutaneous adipose layer). The epidermis contains no blood vessels, and is nourished by diffusion from the dermis. The main type of cells which make up the epidermis are keratinocytes, melanocytes, Langerhans cells and Merkels cells.

20 The dermis is the layer of skin beneath the epidermis that consists of connective tissue and cushions the body from stress and strain. The dermis is tightly connected to the epidermis by a basement membrane. It also harbors many Mechanoreceptor/nerve endings that provide the sense of touch and heat. It 25 contains the hair follicles, sweat glands, sebaceous glands, apocrine glands, lymphatic vessels and blood vessels. The blood vessels in the dermis provide nourishment and waste removal from its own cells as well as from the Stratum basale of the epidermis. The dermis is structurally divided into two areas: a superficial area adjacent to the epidermis, called the papillary region, and a deep 30 thicker area known as the reticular region.

The papillary region is composed of loose areolar connective tissue. It is named for its fingerlike projections called papillae that extend toward the epidermis. The papillae provide the dermis with a "bumpy" surface that interdigitates with the epidermis, strengthening the connection between the two layers of skin. The 5 reticular region lies deep in the papillary region and is usually much thicker. It is composed of dense irregular connective tissue, and receives its name from the dense concentration of collagenous, elastic, and reticular fibers that weave throughout it. These protein fibers give the dermis its properties of strength, extensibility, and elasticity. Also located within the reticular region are the roots of 10 the hair, sebaceous glands, sweat glands, receptors, nails, and blood vessels. Tattoo ink is held in the dermis. Stretch marks from pregnancy are also located in the dermis.

The hypodermis lies below the dermis. Its purpose is to attach the dermal region 15 of the skin to underlying bone and muscle as well as supplying it with blood vessels and nerves. It consists of loose connective tissue and elastin. The main cell types are fibroblasts, macrophages and adipocytes (the hypodermis contains 50% of body fat). Fat serves as padding and insulation for the body.

20 In an aspect of this embodiment, a hydrogel composition disclosed herein is administered to a skin region of an individual by injection into a dermal region or a hypodermal region. In aspects of this embodiment, a hydrogel composition disclosed herein is administered to a dermal region of an individual by injection into, e.g., an epidermal-dermal junction region, a papillary region, a reticular 25 region, or any combination thereof.

Other aspects of the present specification disclose, in part, a method of treating a skin condition comprises the step of administering to an individual suffering from a skin condition a hydrogel composition disclosed herein, wherein the administration 30 of the composition improves the skin condition, thereby treating the skin condition. In an aspect of this embodiment, a skin condition is a method of treating skin dehydration comprises the step of administering to an individual suffering from

skin dehydration a hydrogel composition disclosed herein, wherein the administration of the composition rehydrates the skin, thereby treating skin dehydration. In another aspect of this embodiment, a method of treating a lack of skin elasticity comprises the step of administering to an individual suffering from a

5 lack of skin elasticity a hydrogel composition disclosed herein, wherein the administration of the composition increases the elasticity of the skin, thereby treating a lack of skin elasticity. In yet another aspect of this embodiment, a method of treating skin roughness comprises the step of administering to an individual suffering from skin roughness a hydrogel composition disclosed herein,

10 wherein the administration of the composition decreases skin roughness, thereby treating skin roughness. In still another aspect of this embodiment, a method of treating a lack of skin tautness comprises the step of administering to an individual suffering from a lack of skin tautness a hydrogel composition disclosed herein, wherein the administration of the composition makes the skin tauter, thereby

15 treating a lack of skin tautness.

In a further aspect of this embodiment, a method of treating a skin stretch line or mark comprises the step of administering to an individual suffering from a skin stretch line or mark a hydrogel composition disclosed herein, wherein the

20 administration of the composition reduces or eliminates the skin stretch line or mark, thereby treating a skin stretch line or mark. In another aspect of this embodiment, a method of treating skin paleness comprises the step of administering to an individual suffering from skin paleness a hydrogel composition disclosed herein, wherein the administration of the composition increases skin

25 tone or radiance, thereby treating skin paleness. In another aspect of this embodiment, a method of treating skin wrinkles comprises the step of administering to an individual suffering from skin wrinkles a hydrogel composition disclosed herein, wherein the administration of the composition reduces or eliminates skin wrinkles, thereby treating skin wrinkles. In yet another aspect of

30 this embodiment, a method of treating skin wrinkles comprises the step of administering to an individual a hydrogel composition disclosed herein, wherein

the administration of the composition makes the skin resistant to skin wrinkles, thereby treating skin wrinkles.

The conjugated Vitamin C/HA gels in accordance with certain embodiments of the invention have shown clear advantages over physical mixing of vitamin C with HA

5 in terms of release profile. The conjugated HA gels are stable enough in simple in-vitro release condition (no enzymes involved). It is envisioned that the conjugated vitamin C gels show sustained release with aid of enzymes. In case of conjugated AA2G gels through etherification, the release of active Vitamin C is triggered by α -glucosidase and/or hyaluronidase. In terms of conjugated Vitagen or AA2P gels

10 via amidization, the release of active vitamin C is triggered by phosphatase. In case of conjugated AA2G gels, the release of active vitamin C is triggered by hydrolysis and glucosidase.

In some embodiments, the dermal fillers have a sustained bioavailability. For

15 example, dermal fillers are provided which, when introduced into the skin of a human being, (for example, intradermally or subdermally into a human being for the correction of soft tissue defects of voids in the face), release ascorbic acid (or other vitamin) into the human being for at least about 1 months and up to about 20 months or more.

20 For example, to predict a sustained Vitamin C efficacy in coordinate with filler duration, an estimation on conjugated degree is made. This estimation was based on the formulation of AA2G conjugation to HA via etherification. The formulation is stable under physiological conditions but start to release of Ascorbic acid (AsA) by

25 α -glucosidase which is attached to the cell membrane. Release of AsA happens at the filler/cell interface due to the fact that α -glucosidase is attached to cell membrane. Further release of AsA from HA-AA2G will be accompanied by HA degradation to make AA2G available to fibroblasts. The release of AsA is thus depending on AA2G conjugation degree and duration of HA. A gel with

30 conjugation degree of 5 mol% approximately could release active Vitamin C in a period of at least up to 1 month, for example, between 3 ~5 months; a gel with 10 mol % conjugation degree could release active Vitamin C in a period up to 6~8

months; a gel with 15 mol% conjugation degree could release active Vitamin C in a period up to 10~ months; 30 mol% up to one and half years.

5

Conjugation degree (mol%)	Total AsA available*(mM)	Calculated number (months)**
3	2.13	2.8
5	3.55	3.1
10	7.10	6.3
15	10.65	9.4
25	17.75	15.7
30	21.13	18.8

* Based on parameters of Gels: volume, 0.1cc; concentration, 24 mg/ml. (0.1X 24 X 3% X1000)/(338*0.1)=2.13 (mM)

10 ** Assumptions:

- AsA is released at a constant rate.
- Effective concentration of AsA is 0.05mM and maintains effective > 2 days $2.13 \text{ mM} / (0.05 \text{ mM}) = 42.6 \text{ days}$ (months)

15 In an embodiment of the invention, a dermal filler is provided comprising hyaluronic acid crosslinked with a Star-PEG epoxide and having a vitamin C derivative (for example, one of AA2G (Ascorbic acid 2-Glucoside), Vitagen (3-aminopropyl-L-ascorbyl phosphate) and SAP (sodium ascorbyl phosphate) conjugated to the hyaluronic acid with a degree of conjugation of between about 5
20 mol% and about 40 mol%.

Methods of making this dermal filler include reacting pentaerythritol glycidal ether (Star-PEG epoxide) with ascorbic acid 2-Glucoside (AA2G) at a ratio, reaction temperature and reaction time suitable for achieving a composition containing AA2G capped by 4-arm epoxides (AA2G-4 arm epoxides), unreacted 4-arm 5 epoxides and free AA2G. The 4 arm epoxide capped AA2G (AA2G-4 arm epoxides) is conjugated to hyaluronic acid via the epoxyl group. The unreacted 4 arm epoxides serves as a crosslinker to crosslink hyaluronic acid and as a conjugation agent to further conjugate AA2G.

10 In another embodiment of the invention, a dermal filler is provided comprising hyaluronic acid crosslinked with BDDE and having a vitamin C derivative (for example, one of AA2G (Ascorbic acid 2-Glucoside), Vitagen (3-aminopropyl-L-ascorbyl phosphate) and SAP (sodium ascorbyl phosphate) conjugated to the hyaluronic acid with a degree of conjugation of between about 3 mol% and about 15 15 mol%.

Methods of making this dermal filler include reacting BDDE with ascorbic acid 2-Glucoside (AA2G) at a ratio, reaction temperature and reaction time suitable for achieve a composition containing AA2G capped by BDDE (AA2G-BDDE), 20 unreacted BDDE and free AA2G. The BDDE capped AA2G (AA2G-BDDE) is conjugated to hyaluronic acid via the epoxyl group. The unreacted BDDE serves as a crosslinker to crosslink hyaluronic acid and as a conjugation agent to further conjugate AA2G.

25 Figure 9 is a Table showing the effect of α -glucosidase concentration on AsA release from AA2G-PBS solution. The conversion of AA2G to AsA depends on the concentration of α -glycosidase. AA2G converted AsA almost completely in 15 minutes when α -glycosidase concentration is 6.3 unit per gram gel. When α -glycosidase concentration is 4.7 units per gram gel, It took 30 minutes to 30 completely convert AA2G to AsA. Further decease α -glycosidase concentration resulted in slow conversion of AA2G to AsA.

Figure 10 shows a representation of a release profile of free AsA from conjugated dermal fillers in accordance with the invention (sustained release) (AA2G conversion in mol% versus reaction time). AA2G completely converted to AsA in AA2G/Juvederm mix in 40 minutes. HA-AA2G conjugates showed a time 5 dependence of AA2G conversion to AsA.

Figure 11A and 11B show additional release data for various dermal fillers in accordance with the invention. More specifically, conversion of AA2G to AsA in HA-AA2G gels is dependent on α -glycosidase concentration. High α -glycosidase 10 concentration resulted in a fast conversion of AA2G to AsA. For a given α -glycosidase concentration, different formulations showed different profiles of AA2G to AsA.

EXAMPLES

15

Example 1: AA2G conjugation to crosslinked HA Gels using BDDE as a crosslinker

400.6 mg of LMW HA was hydrated in 1802 mg of 1 wt% NaOH in a syringe for ~30min. 800.7 mg of AA2G was put in a vial, followed by 713.7 mg of BDDE and 20 1416.8 mg of 10% NaOH. The above solution (pH >12) was allowed to react in a 50 °C water bath for ~20min, before adding to the hydrated HA. After the addition, the mixture was mixed ~20 times by passing back and forth between 2 syringes. The mixed paste was put in a vial and in the 50 °C water bath for ~2.5 hours. 223.5 mg of 12M HCl was added to 9.05 g PBS, pH7.4. After ~2.5 hours, the HA- 25 AA2G gel was formed. The gel was cut into pieces, and the HCl-PBS solution was added to it. The gel was allowed to neutralize and swell overnight on an orbital shaker. The gel was sized through a ~60 μ m screen and mixed ~20 times by passing back and forth between 2 syringes. The gel was put in a 15,000 MWCO RC dialysis bag and dialyzed in PBS, pH7.4 buffer. The dialysis went on for ~185 30 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and stored in a 4 °C refrigerator.

Example 2: Determination of AA2G conjugations

The weight of gel as described in Example 1 was noted right before dialysis, and after dialysis. The assumption was made that the gel was ~1g/mL after dialysis.

- 5 The dialysis was stopped at the point where no notable AA2G was coming out per > 8 hours in 1L of PBS. The AA2G was measured at 260nm using UV/Vis spectrophotometer (Nanodrop 2000C, ThermoScientific). The calibration curve of AA2G was calculated using different concentration of AA2G in 2% HA (A@260nm = 1.4838 [AA2G(mM)]).
- 10 The weight of HA after dialysis: the starting weight of HA x (actual weight before dialysis / theoretical weight)
The mmol of AA2G after dialysis: put the absorption @ 260nm after dialysis in the equation (A@260nm = 1.4838 [AA2G(mM)]).
The conjugation @ of AA2G: (mmol of AA2G/mmol of HA)x100%
- 15 The AA2G conjugation degree in the gel as described in Example 1 is 14.7 mol%.

Example 3: Determination of gel rheological properties:

An oscillatory parallel plate rheometer (Anton Paar, Physica MCR 301) was used

- 20 to measure the properties of the gel obtained in Example 1. The diameter of plate used was 25 mm. The gap between the plates was set at 1 mm. For each measurement, a frequency sweep at a constant strain was run first, before the strain sweep at a fixed frequency. The G' (storage modulus) was obtained from the strain sweep curve at 1% strain. The value is 1450 Pa for the gel.

25

Example 4: AA2G conjugation to crosslinked HA Gels using BDDE as a crosslinker, with tunable conjugation degree and gel rheological properties.

The procedure was similar to that as described in Example 1. Conjugation degree

is modified by tuning crosslinker to HA and AA2G mol ratios. Gel properties were

- 30 measured as described in Example 3. Details are as follows:

400.8 mg of LMW HA was hydrated in 1752.1 mg of 1% NaOH in a syringe for ~30min. 800.3 mg of AA2G was put in a vial, followed by 354.1 mg of BDDE and 1402.0 mg of 10% NaOH. The above solution (pH >12) was allowed to react in a 50 °C water bath for ~20min, before adding to the hydrated HA. After the addition, 5 the mixture was mixed ~20 times by passing back and forth between 2 syringes. The mixed paste was put in a vial and in the 50 °C water bath for ~2.5 hours. 140.9 mg of 12M HCl was added to 9.0053 g PBS, pH7.4. After ~2.5 hours, the HA-AA2G gel was formed. The gel was cut into pieces, and the HCl-PBS solution was added to it. The gel was allowed to neutralize and swell overnight on an 10 orbital shaker. The gel was sized through a ~60 µm screen and mixed ~20 times by passing back and forth between 2 syringes. The gel was put in a 15,000 MWCO RC dialysis bag and dialyzed in PBS, pH7.4 buffer. The dialysis went on for ~164.5 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and stored in a 4 °C refrigerator. The conjugation degree is 15 13%. Gel storage modulus (G') is 803 Pa.

Example 5: AA2G conjugation to crosslinked HA Gels using BDDE as a crosslinker, conjugation degree is 5.3 %, G' is ~ 300 Pa.

20 400.3 mg of LMW HA was hydrated in 3002.0 mg of 1% NaOH in a syringe for ~30min. 800.5 mg of AA2G was put in a vial, followed by 264.3 mg of BDDE and 1100.0 mg of 10% NaOH. The above solution (pH >12) was allowed to react in a 50 °C water bath for ~20min, before adding to the hydrated HA. After the addition, the mixture was mixed ~20 times by passing back and forth between 2 syringes. 25 The mixed paste was put in a vial and in the 50 °C water bath for ~2.5 hours. 104.2 mg of 12M HCl was added to 8.5128 g PBS, pH7.4. After ~2.5 hours, the HA-AA2G gel was formed, and the HCl-PBS solution was added to it. The gel was allowed to neutralize and swell over the weekend (~55 hours) on an orbital shaker. The gel was sized through a ~60 µm screen and mixed ~20 times by passing back 30 and forth between 2 syringes. The gel was put in a 15,000 MWCO RC dialysis bag and dialyzed in PBS, pH7.4 buffer. The dialysis went on for ~114 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and

stored in a 4 °C refrigerator. The conjugation degree and gel rheological properties are measured in a procedure as described in Example 2 and 3. The conjugation degree is 5.3%. Gel storage modulus is ~ 300 Pa.

5 **Example 6: AA2G conjugation to crosslinked HA Gels using star-PEG epoxide as a crosslinker, conjugation degree is 29.4 %, G' is ~ 235 Pa.**

200.4 mg of LMW HA was hydrated in 2000 mg of 1% NaOH in a syringe for ~30min. 400 mg of AA2G was put in a vial, followed by 312.7 mg of star-PEG
10 epoxide and 1026.5 mg of 10% NaOH. The above solution was allowed to react in a 50 °C water bath for ~20min, before adding to the hydrated HA. After the addition, the mixture was mixed ~20 times by passing back and forth between 2 syringes. The mixed paste was put in a vial and in the 50 °C water bath for ~2.5 hours. 187.4 mg of 12M HCl was added to 3.034 g PBS, pH7.4. After ~2.5 hours,
15 the HA-AA2G gel was formed, and the HCl-PBS solution was added to it. The gel was allowed to neutralize and swell over the weekend (~68 hours) on an orbital shaker. The gel was sized through a ~60 µm screen and mixed ~20 times by passing back and forth between 2 syringes. The gel was put in a 15,000 MWCO RC dialysis bag and dialyzed in PBS, pH 7.4 buffer. The dialysis went on for ~95
20 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and stored in a 4 °C refrigerator. The conjugation degree and gel rheological properties are measured in a procedure as described in Examples 2 and 3. The conjugation degree is 29.4%. Gel storage modulus is ~ 235 Pa.

25 **Example 7: AA2G conjugation to crosslinked HA Gels using star-PEG epoxide as a crosslinker, conjugation degree is 27.8 %, G' is ~ 363 Pa.**

200.3 mg of LMW HA was hydrated in 2000 mg of 1% NaOH in a syringe for ~30min. 400.2 mg of AA2G was put in a vial, followed by 313.4 mg of star-PEG
30 epoxide and 1022.6 mg of 10% NaOH. The above solution was added to the hydrated HA. After the addition, the mixture was mixed ~20 times by passing back and forth between 2 syringes. The mixed paste was put in a vial and in the 50 °C

water bath for ~2.5 hours. 196.5 mg of 12M HCl was added to 3.016 g PBS, pH7.4. After ~2.5 hours, the HA-AA2G gel was formed, and the HCl-PBS solution was added to it. The gel was allowed to neutralize and swell overnight (~24 hours) on an orbital shaker. The gel was sized through a ~60 μm screen and mixed ~20 times by passing back and forth between 2 syringes. The gel was put in a 15,000 MWCO RC dialysis bag and dialyzed in PBS, pH7.4 buffer. The dialysis went on for ~98.5 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and stored in a 4 °C refrigerator. The conjugation degree and gel rheological properties are measured in a procedure as described in Examples 2 and 3. The conjugation degree is 27.8%. Gel storage modulus is ~ 363 Pa.

Example 8: AA2G conjugation to crosslinked HMW HA Gels using BDDE as a crosslinker, conjugation degree is 9.8 mol %, G' is ~ 238 Pa.

15 400.3 mg of HMW HA was hydrated in 2501.3 mg of 4 wt% NaOH in a syringe for ~30min. 1200 mg of AA2G was put in a vial, followed by 304.7 mg of BDDE and 1178.6 mg of 16 wt% NaOH. The above solution (pH >12) was allowed to react in a 50 °C water bath for ~20min and transferred to a 20 cc syringe, before adding to the hydrated HA. After the addition, the mixture was mixed ~20 times by passing 20 back and forth between 2 syringes. The mixed paste was put in a 20 cc vial and in the 50 °C water bath for ~2.5 hours. After ~2.5 hours, the HA-AA2G gel was formed. Then 226.6 mg of 12M HCl was added to 8492.2 mg 10X PBS, pH7.4 to get HCl-PBS solution and the HCl-PBS solution was added to neutralize and swell the gel. The gel was allowed to neutralize and swell over 48 hrs on an orbital 25 shaker. The gel was sized through a ~60 μm screen and mixed ~20 times by passing back and forth between 2 syringes. The gel was put in a 20,000 MWCO CE dialysis bag and dialyzed in PBS, pH7.4 buffer. The dialysis went on for ~114 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and stored in a 4 °C refrigerator. The conjugation degree and gel 30 rheological properties are measured in a procedure as described in Examples, 2 and 3. The conjugation degree is 5.3%. Gel storage modulus is ~ 300 Pa.

Example 9: Vitagen conjugation to crosslinked LMW HA Gels using BDDE as a crosslinker, conjugation degree is 15 mol %, G' is ~ 365 Pa.

398.2 mg of LMW HA was hydrated in 1753.24 mg of 1 wt% NaOH in a syringe for
5 ~ 40min. BDDE (311.7 mg) was added to swollen HA and continue let HA swell for another 80 min. The swollen HA/BDDE mixture was pre-reacted at 50 $^{\circ}$ C for 20 min.

801.9 mg of vitagen was separately dissolved in 1459.7 mg of 10 wt% NaOH and mixed with HA which was pre-reacted with BDDE. The mixture was continued to
10 react at 50 $^{\circ}$ C for another 2.5 hrs. After ~2.5 hours, the HA-Vitagen gel was formed. Then 195 mg of 12M HCl was added to 9004.0 mg of 10X PBS, pH7.4 to get HCl-PBS solution and the HCl-PBS solution was added to neutralize and swell the gel. The gel was allowed to neutralize and swell over 48 hrs on an orbital shaker. The gel was sized through a ~60 μ m screen and mixed ~20 times by
15 passing back and forth between 2 syringes. The gel was put in a 20,000 MWCO CE dialysis bag and dialyzed in PBS, pH7.4 buffer. The dialysis went on for ~120 hours, with frequent change of PBS buffer. After the dialysis, the gel was put in a syringe and stored in a 4 $^{\circ}$ C refrigerator. The gel rheological properties were measured in a procedure as described in Example 3. The conjugation degree is
20 calculated to ~ 15 mol% by mass balance Gel storage modulus is ~ 365 Pa.

Example 10: Vitagen conjugation to linear HA via amidization chemistry

200.3 mg of HMW HA was hydrated in 10 ml of water in 60 cc syringe. 500 mg of
25 Vitagen was dissolved in 0.5 ml of water and solution was neutralized to pH4.8. 197.7 mg of EDC and 149 mg of NHS were dissolved separately in 6 ml of water. The above solutions (solutions and EDC/NHS solutions) are added to another 60 cc syringe containing 23.5 ml of water. The two syringes are mixed 20 times by passing back and forth between 2 syringes. The mixtures was stored in one
30 syringe and soaked in 37 $^{\circ}$ C bath for 4 hrs. The solutions was finally dialyzed against PBS pH7.4 buffer until no noticeable vitagen was observed. The

conjugation degree was determined by a similar method as described Example 3. The conjugation degree is about 10 mol%.

Example 11: AA2P Conjugations to crosslinked HA gels

5

200.4 mg of LMW HA is hydrated in 1000 mg of MES 5.2 buffer in a syringe for ~30min. 292 mg of AA2P is put in a vial, followed by 300 mg of star-PEG amine added. The above solution is allowed to react at room temperature overnight. The gel was hydrated with PBS buffer and dialyzed against PBS buffer to remove 10 unreacted AA2P. The finally gel was characterized as described in Examples 2 and 3 to determine the conjugation degree and gel rheological properties. The conjugation degree is about 20 mol%. The storage modulus (G') is about 500 Pa.

Example 12

15

Formulation of a HA/BDE Dermal Filler Product with AA2G

To any of the gels described in the above Examples, after dialysis, a suitable amount of free HA gel may be added to the gel to improve of modify gel cohesivity and/or injectability. For example, free HA fibers are swollen in a phosphate buffer

20 solution, in order to obtain a homogeneous viscoelastic gel ("free" HA gel). This uncrosslinked gel is added, before the dialysis step, to the HA/BDE crosslinked gel obtained in Example 1 (for example, to obtain a composition having between about 1% to about 5%, w/w free HA). The resulting gel is then filled into Ready-to-Fill sterile syringes and autoclaved at sufficient temperatures and pressures for 25 sterilization for at least about 1 minute. After autoclaving, the final HA-AA2G product is packaged and distributed to physicians to use as a dermal filler.

Example 13

Formulation of HA-AA2G Dermal Filler including Lidocaine

30

The procedure of Example 12 is followed, but after the dialysis step and before the addition of free HA gel, lidocaine chlorhydrate (lidocaine HCl) is added to the

mixture. The (lidocaine HCl) in powder form may first be solubilized in WFI and filtered through a 0.2 μ m filter. Dilute NaOH solution is added to the cohesive HA-AA2G gel in order to reach a slightly basic pH (for example, a pH of between about 7.5 and about 8). The lidocaine HCl solution is then added to the slightly 5 basic gel to reach a final desired concentration, for example, a concentration of about 0.3% (w/w). The resulting pH of the HA-AA2G/lidocaine mixture is then about 7 and the HA concentration is about 24 mg/mL. Mechanical mixing is performed in order to obtain a proper homogeneity in a standard reactor equipped with an appropriate blender mechanism.

10

Example 14
Conjugations of additives containing
carboxyl functional group to HA hydrogels.

15 Additives such as retinoic acid (AKA, tretinooin), adapalene and alpha-lipoic acid contain carboxyl functional group (-COOH). These additives are conjugated to HA hydrogels via esterifications using EDC chemistry. An example for the conjugations in accordance with an embodiment of the invention is described as follows:

20 200 mg of HMW HA is hydrated in 10 ml of pH 4.8 MES buffer in 60 cc syringe. In another syringe, 200 mg of retinoic acid is dissolved in 5 ml of water-acetone mixture (water/acetone volume ratio 1:3). The above two syringes are mixed via a syringe connector for about 20 times. Then 197.7 mg of EDC and 149 mg of NHS are dissolved separately in 6 ml of water in a separate syringe. The 25 syringe containing EDC and NHS is connected the syringe containing with HA and retinoic acid to allow reactants to mix at least for 20 times by passing back and forth between 2 syringes. The mixtures are stored in one syringe and soaked in 37°C bath for 4 hrs. The gels are dialyzed against isopropanol to remove unconjugated Retinoic acid, and then dialyzed against PBS buffer under aseptic 30 conditions. The gels are packaged into sterilized syringes and stored at 4 °C.

Example 15

Conjugations of additives containing hydroxyl functional group to HA hydrogels.

Additives such as retinol (AKA, tretinoiin), catalase, dimethylaminoethanol and g-Tocopherol contain hydroxyl functional group (-OH). These additives are conjugated to HA hydrogels via esterifications using EDC chemistry. A typical example for the conjugations is described as follows:

200 mg of HMW HA is hydrated in 10 ml of pH 4.8 2-(N-morpholino)ethanesulfonic acid (MES) buffer in 60 cc syringe. In another syringe, 200 mg of 5 retinol acid is dissolved in 5 ml of water-acetone mixture (water/acetone volume ratio 1:3). The above two syringes are mixed via a syringe connector for about 20 times. Then 197.7 mg of EDC and 149 mg of NHS are dissolved separately in 6 ml of water in a separate syringe. The syringe containing EDC and NHS is connected 10 to the syringe containing with HA and retinol to allow reactants to mix at least for 20 times by passing back and forth between 2 syringes. The mixtures are stored in 15 one syringe and soaked in 37⁰C bath for 4 hrs. The gels are dialyzed against isopropanol to remove unconjugated retinol, and then dialyzed against PBS buffer under aspect conditions. The gels are packaged into sterilized syringes and stored at 4⁰C.

20

Example 16

Conjugations of additives containing hydroxyl functional group to HA hydrogels by post-modifications.

25 This is a two-step process. Step one: HA hydrogels, e.g. Juvederm or restylane, are treated with EDC/NHS to activate the carboxyl group of HA. Step 2: the activated HA hydrogels are treated with additives containing hydroxyl groups. Additives containing hydroxyl groups are retinol, catalase, dimethylaminoethanol and g-Tocopherol hydroxyl functional group (-OH). A typical examples for the 30 conjugation of additives to crosslinked HA gels is as follows:

2 gm of Juvederm gel is mixed with 200 gm of EDC and 150 mg of NHS at room temperature. Then 200mg of retinol in 3 ml of acetone-water mixture is added. The above mixture is reacted at 37 °C for 4 hrs. The gels are dialyzed against isopropanol to remove unconjugated Retinol, and then dialyzed against PBS 5 buffer under aseptic conditions. The gels are packaged into sterilized syringes and stored at 4 °C.

Example 17

Conjugation of growth factors, peptides, or elastin to HA Hydrogels

10

Additives such as epidermal growth factor (EGF), transforming growth factor (TGF) and peptides contain functional amine groups may be conjugated to HA to form beneficial dermal fillers. These additives are conjugated to HA via amidization chemistry. A typical example for conjugating is described as follows:

15

200.3 mg of HMW HA is hydrated in 10 ml of MES pH 5.4 buffer water. 20 mg of EGF in 100 mg of MES solution is added. To above mixture, 197.7 mg of EDC and 149 mg are added. The resulting reaction mixture is allowed to react at 37 °C for 4 hrs. After the reaction completes, the gel is further dialyzed against 20 isopropanol and then dialyzed against PBS buffer under aseptic conditions. The gels are packaged into sterilized syringes and stored at 4 °C.

25

In closing, it is to be understood that although aspects of the present specification have been described with reference to the various embodiments, one skilled in the art will readily appreciate that the specific examples disclosed are only illustrative of the principles of the subject matter disclosed herein. Therefore, it should be understood that the disclosed subject matter is in no way limited to a particular methodology, protocol, and/or reagent, etc., described herein. As such, those skilled in the art could make numerous and various modifications or changes to or 30 alternative configurations of the disclosed subject matter can be made in accordance with the teachings herein without departing from the spirit of the present specification. Changes in detail may be made without departing from the

spirit of the invention as defined in the appended claims. Lastly, the terminology used herein is for the purpose of describing particular embodiments only, and is not intended to limit the scope of the present invention, which is defined solely by the claims. In addition, it is intended that all matter contained in the above 5 description or shown in the accompanying drawings shall be interpreted as illustrative only and not limiting. Accordingly, the present invention is not limited to that precisely as shown and described.

Certain embodiments of this invention are described herein, including the best 10 mode known to the inventors for carrying out the invention. Of course, variations on these described embodiments will become apparent to those of ordinary skill in the art upon reading the foregoing description. The inventor expects skilled artisans to employ such variations as appropriate, and the inventors intend for the invention to be practiced otherwise than specifically described herein. 15 Accordingly, this invention includes all modifications and equivalents of the subject matter recited in the claims appended hereto as permitted by applicable law. Moreover, any combination of the above-described elements in all possible variations thereof is encompassed by the invention unless otherwise indicated herein or otherwise clearly contradicted by context.

20 Groupings of alternative elements or embodiments of the invention disclosed herein are not to be construed as limitations. Each group member may be referred to and claimed individually or in any combination with other members of the group or other elements found herein. It is anticipated that one or more 25 members of a group may be included in, or deleted from, a group for reasons of convenience and/or patentability. When any such inclusion or deletion occurs, the specification is deemed to contain the group as modified thus fulfilling the written description of all Markush groups used in the appended claims.

30 Unless otherwise indicated, all numbers expressing quantities of ingredients, properties such as molecular weight, reaction conditions, and so forth used in the specification and claims are to be understood as being modified in all instances by

the term “about.” As used herein, the term “about” means that the item, parameter or term so qualified encompasses a range of plus or minus ten percent above and below the value of the stated item, parameter or term. Accordingly, unless indicated to the contrary, the numerical parameters set forth in the specification 5 and attached claims are approximations that may vary depending upon the desired properties sought to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding 10 techniques. Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements.

15

The terms “a,” “an,” “the” and similar referents used in the context of describing the invention (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. Recitation of ranges of values herein is merely 20 intended to serve as a shorthand method of referring individually to each separate value falling within the range. Unless otherwise indicated herein, each individual value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use 25 of any and all examples, or exemplary language (e.g., “such as”) provided herein is intended merely to better illuminate the invention and does not pose a limitation on the scope of the invention otherwise claimed. No language in the specification should be construed as indicating any non-claimed element essential to the practice of the invention.

30

Specific embodiments disclosed herein may be further limited in the claims using consisting of or consisting essentially of language. When used in the claims,

whether as filed or added per amendment, the transition term “consisting of” excludes any element, step, or ingredient not specified in the claims. The transition term “consisting essentially of” limits the scope of a claim to the specified materials or steps and those that do not materially affect the basic and novel 5 characteristic(s). Embodiments of the invention so claimed are inherently or expressly described and enabled herein.

All patents, patent publications, and other publications referenced and identified in the present specification are individually and expressly incorporated herein by 10 reference in their entirety for the purpose of describing and disclosing, for example, the compositions and methodologies described in such publications that might be used in connection with the present invention. These publications are provided solely for their disclosure prior to the filing date of the present application. Nothing in this regard should be construed as an admission that the inventors are 15 not entitled to antedate such disclosure by virtue of prior invention or for any other reason. All statements as to the date or representation as to the contents of these documents are based on the information available to the applicants and does not constitute any admission as to the correctness of the dates or contents of these documents.


What is claimed is:

1. An injectable dermal filler comprising:
hyaluronic acid; and
a vitamin C derivative covalently conjugated to the hyaluronic acid;
wherein a degree of conjugation is between about 3 mol% and about 40 mol%.
2. The dermal filler of claim 1 wherein the hyaluronic acid is crosslinked with Star-PEG epoxide.
3. The dermal filler of claim 1 wherein the hyaluronic acid is crosslinked with Star-PEG amine.
4. The dermal filler of claim 1 wherein the hyaluronic acid is crosslinked with BDDE.
5. The dermal filler of claim 4 wherein and the degree of conjugation is between about 3 mol% and about 15 mol%.
6. The dermal filler of claim 1 wherein vitamin C derivative is AA2G.
7. The dermal filler of claim 1 wherein the vitamin C derivative is Vitagen.
8. The dermal filler of claim 1 wherein the vitamin C derivative is AA2P.
9. The dermal filler of claim 1 used in treating a skin defect wherein, when introduced into the skin of a human being, releases ascorbic acid into the human being for at least about 1 month and up to about 20 months.


10. An injectable dermal filler comprising:
hyaluronic acid crosslinked with Star PEG amine and having a degree of conjugation of between about 3 mol% and about 40 mol% ; and
AA2P covalently conjugated to the hyaluronic acid
wherein the dermal filler, when introduced into the skin of a human being, releases ascorbic acid into the human being for at least about 1 months and up to about 20 months.
11. A method of making a dermal filler comprising the steps of:
providing hyaluronic acid;
reacting a crosslinking agent with a Vitamin C derivative;
adding the reacted crosslinking agent and Vitamin C derivative to the hyaluronic acid to form a crosslinked hyaluronic acid composition including covalently conjugated Vitamin C; and
homogenizing and neutralizing the crosslinked hyaluronic acid composition to obtain an injectable gel having a conjugation degree of between about 3 mol% and about 40 mol%.
12. The method of claim 11 wherein the step of reacting comprises pre-reacting vitamin C derivatives with crosslinker to achieve a composition containing Vitamin C derivative capped by crosslinker, unreacted crosslinker and free AA2G.
- 13 . The method of claim 12 wherein the crosslinker is BDDE and vitamin C derivative is AA2G, vitagen, and SAP.
14. The method of claim 12 wherein the crosslinker is 4-arm epoxide and vitamin C derivative is AA2G, vitagen, and SAP.
15. The method of claim 11 wherein the crosslinking agent is Star-PEG epoxide
.
16. The method of claim 11 wherein the crosslinking agent is Star-PEG amine.

17. The method of claim 11 wherein vitamin C derivative is AA2G.
18. The method of claim 11 wherein the vitamin C derivative is Vitagen.
19. The method of claim 11 wherein the vitamin C derivative is AA2P.
20. A method of treating a skin condition comprising introducing the dermal filler of claim 1 into a patient.


1/7



AA2G, (L-ascorbic acid 2-glucoside)

FIG. 1


Vitagen, (ascobyl 3-aminopropyl phosphate)

FIG. 2


AA2P, sodium ascorbyl phosphate

FIG. 3


2/7



BDDE, 1,4-butanediol diglycidal ether



FIG. 4

Star-PEG epoxide, pentaerythritol glycidal ether

FIG. 5

Star-PEG amine, pentaerythritol (3-aminopropyl) ether

FIG. 6

Sample ID	Crosslinker	Conjugation degree (HA-AA2G, mol%)	G' (Pa)	
	BDDE	12	69	Soft
		9.78	291	Hard
		10.47	377	Soft
		12.44	1160	Hard
	Star Arm PEG Epoxide	32.26	132	Soft
		31.25	263	Hard
		20.48	421	Soft
		31.87	1160	Hard

HA-AA2G/Epoxy: Gel Synthesis Results


FIG. 7

Conjugation Degree (HA-AA2G, mol%)	Gel Conc. (mg/ml)	G' (Pa)	
8.0	25	42	Soft
12.0	17	69	Medium soft
11.6	24	113	Hard
12.6	24	237	
9.8	17	291	
10.5	17	377	
8.5	26	700	
13.0	22	1010	
11.9	23	1260	

HA-AA2G (BDDE)



FIG. 8




Established an enzymatic method of α -glucosidase to efficiently cleave AA2G to AsA


- Fast conversion
- Conversion of AA2G depends on enzyme conc - 100% conversion is reached within a few min at higher enzyme conc
- Reaction follows first-order kinetics:

$$C = C_0 (1 - e^{-kt})$$

FIG. 9

5/7

**FIG. 10**

**FIG. 11A**

Cross linker	Conjugation degree (AsA mole / AA2G mole)%
BDDE	9.78
BDDE	10.04
BDDE	10.49
BDDE	13.76
Star-PEG	19.30
Star-PEG	31.87

For the same formulation, the released amount increases with the increase of the enzyme concentration.

FIG. 11B