



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 41/50, B27K 3/16 // C04B 111/20, 111/27	A1	(11) International Publication Number: WO 99/31028 (43) International Publication Date: 24 June 1999 (24.06.99)
(21) International Application Number: PCT/EP98/04914 (22) International Filing Date: 6 August 1998 (06.08.98) (30) Priority Data: 97122083.5 15 December 1997 (15.12.97) EP (71)(72) Applicant and Inventor: DOUMET, Joseph, E. [CA/FR]; 1, rue Jacob, F-75006 Paris (FR). (74) Agents: TETZNER, Volkmar et al.; Van-Gogh-Strasse 3, D-81479 München (DE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: METHOD OF PRODUCING A WATER-REPELLENT PRODUCT, AND PRODUCT AND METHOD FOR WATERPROOFING A SURFACE OF A BUILDING MATERIAL (57) Abstract The invention relates to the production and use of a water-repellent and impregnating product for surfaces of building materials. In order to be able to waterproof and impregnate building material surfaces in a relatively simple, economical and yet very reliable and durable manner, a coating product is proposed which is produced from two aqueous solutions and forms an aqueous solution product which contains silicon, calcium and sodium ions, wherein the capacity for dissolving the calcium oxide is increased by a dissolving agent added to the water and the finished product, after application and drying on the building material surface, forms a glass-like surface film.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Method of producing a water-repellent product, and product and method for waterproofing a surface of a building material

The invention relates to a method of producing a product (according to the preamble to Claim 1) and to a product (according to the preamble to Claim 8) and to a method (according to the preamble to Claim 12) for water-repellent or waterproof treatment and for impregnation of a surface of solid building materials against liquids as well as against chemical and biological corrosion.

There are on the market numerous products or agents which are intended for painting or coating surfaces on solid building materials, such as for example walls, ceilings and/or floors of parts of buildings, water tanks, swimming pools or the like, in order to waterproof these surfaces and/or to impregnate them against chemical and biological corrosion. These known products may generally be rubber-based or plastic-based products (synthetic resin or epoxy resin) or also special paints. However, these known products which are available on the market have shown themselves to be frequently inadequate in their effect and in their durability, particularly when several requirements are to be met simultaneously, as is the case for example when surfaces are to be protected against liquids (particularly water) and also simultaneously against chemical and/or biological corrosion, such as occurs for example in water reservoirs, swimming pools and the like which are built in the open.

The object of the invention, therefore, is to create a method of producing a product according to the preamble to Claim 1, a product according to the preamble to Claim 8 and a method of treating surfaces of building materials according to the preamble to Claim 12 in such a way that, on the one hand, a treatment product or coating product is made available which is relatively simple and economical to produce as well as

having many uses and being reliable and durable in its effect and, on the other hand, such a product can be applied relatively simply and quickly to a surface of a building material which is to be protected.

This object is achieved by the characterising features on the one hand of Claim 1, on the other hand of Claim 8 and furthermore by the characterising features of Claim 12.

Advantageous embodiments are the subject matter of the subordinate claims.

A first aspect of the present invention concerns a method of producing or preparing a treatment product or coating product in order to make a surface of corresponding building materials water-repellent or waterproof and thereby to impregnate or protect this surface against liquids as well as against chemical and biological corrosion. According to the invention such a product is generally produced by the following steps:

- a) preparing a first aqueous solution (base solution) by dissolving calcium oxide (CaO) in a quantity of water with the aid of a dissolving agent which is admixed with this quantity of water in order to increase the dissolution or the dissolving effect of the calcium oxide in water;
- b) preparing a second aqueous solution which contains water and sodium silicate;
- c) mixing together the said first aqueous solution with the second aqueous solution so that an aqueous solution product (treatment product or coating product) is formed which contains silicon, calcium and sodium ions and which forms a glass-like surface film on the corresponding building material surface.

By means of this method of production according to the invention, a product is made available which is ready for use in the form of an aqueous solution and which can be applied in a manner which is extremely simple to handle and relatively quickly to a building material surface which is to be protected. However, in the dried state the product produces a solid and durable, insoluble surface film due to the double silicate [sodium calcium silicate] which is formed because of the silicon, calcium and sodium ions present in the prepared aqueous solvent product.

In this method of product, however, particular importance is also given to the knowledge that calcium oxide only dissolves in water in extremely small quantities. In order to be able to dissolve a sufficient quantity of calcium oxide in the given quantity of water, first of all according to the invention the first aqueous solution (base solution) referred to above under a) is prepared, in which a sufficiently large quantity of calcium oxide can be dissolved in the predetermined quantity of water because this quantity of water has a suitable dissolving agent mixed with it in order thereby to improve or to increase the dissolution of the calcium oxide. In this connection it should be mentioned that only approximately 1 g of calcium oxide can be dissolved in one litre of water; however, by the admixture of the dissolving agent a multiple of this quantity of calcium oxide can be dissolved in the same quantity of water, so that this admixture of the dissolving agent makes it possible to dissolve a correspondingly larger quantity of calcium oxide in the same quantity of water and thereby to control the ratio of calcium oxide and sodium silicate in the prepared aqueous solution product.

Basically any dissolving agent which is suitable for dissolving an increased quantity of calcium oxide in the given quantity of water can be used in the quantity of water

of the first aqueous solution. According to the present invention it is particularly preferred if sugar in the form of saccharose ($C_{12}H_{22}O_{11}$) is dissolved as dissolving agent in the first aqueous solution in order to dissolve an increased quantity of calcium oxide therein. Thus ordinary sugar can be used to a certain extent as a type of catalyst in order markedly to increase the dissolving power of the calcium oxide in water. Thus for example approximately 32 g of calcium oxide can dissolve in a litre of water in which 400 g of sugar/saccharose are dissolved, which means that 100 g of sugar/saccharose contribute to approximately 8 g of calcium oxide being dissolved in a corresponding quantity of water.

In many cases, however, it may also be favourable in the method of production according to the invention to mix glycerine ($CH_2OH-CHOH-CH_2OH$) as dissolving agent into the first aqueous solution in order to increase the dissolution of the calcium oxide therein. With this use of glycerine, however, it should be noted that an increased quantity of calcium oxide can indeed be dissolved in the water, but the capacity for dissolving calcium oxide in the water is less than when saccharose is used. In any case, however, by the admixture of glycerine to the first aqueous solution a quantity of calcium oxide of approximately 3.5% by weight of the glycerine can be dissolved, which can be sufficient for many uses of the finished product.

When the first aqueous solution is being prepared the procedure is advantageously such that first of all a quantity of water is boiled in order to degasify or to demineralise the water. Then the dissolving agent is added to this quantity of water and thereupon the calcium oxide in the form of quicklime or calcium hydrate (in the quantity required in the particular case) is admixed with the water at room temperature and thereby dissolved, so that this first aqueous solution is formed. By this degasification all carbonic acid gas is

removed from this water, since otherwise carbonic acid gas would precipitate calcium oxide as calcium carbonate (CaCO_3). Only afterwards is the dissolving agent (saccharose or glycerine) added to the quantity of water (dissolved therein or mixed in). Although this addition of the dissolving agent can basically take place into the warm water, it is preferable for the water first of all to be cooled to room temperature (approximately 20 to 25°C) after the degasification and only thereafter for the dissolving agent to be added. The coordinated quantity of calcium oxide, likewise at this room or ambient temperature, is then admixed with the water so that it can be dissolved therein.

For the production according to the invention of the treatment product or coating product, calcium oxide is advantageously added in the form of quicklime (CaO) in a ratio which depends upon the quantity of dissolving agent used, calcium hydrate (Ca(OH)_2) being formed in the first aqueous solution. However, as mentioned above, calcium hydrate (Ca(OH)_2) can be directly added instead of quicklime.

According to the invention it is also advantageous that calcium oxide and sodium silicate are added to (dissolved in) the first and second aqueous solutions in such quantities or proportions that the finished aqueous solution product, that is to say the treatment product or coating product, contains a ratio of calcium to sodium, i.e. $\text{Ca} : \text{Na}_2$ of approximately 0.1 to 1.0. The flexibility or the strength of the dried and possibly hardened finished product film on the building material surface to be protected can be controlled in the desired manner by means of this ratio of $\text{Ca} : \text{Na}_2$. In fact, the greater the ratio $\text{Ca} : \text{Na}_2$ is, the harder and less flexible the dried product film on the coated surface becomes; however, if this ratio in the finished product is too low, then the latter becomes more easily soluble in water, whilst too high a proportion of calcium (Ca) gives the finished

product film a tendency to fracture or bursting.

Amongst the various possible types of sodium silicate used here, in the tests on which the invention is based sodium metasilicate pentahydrate ($\text{Na}_2 \cdot \text{SiO}_3 \cdot 5\text{H}_2\text{O}$), which in the dissolved state can be used in the second aqueous solution, has proved very favourable. However, other formulas of sodium silicate may be used, as they are soluble in water.

The present invention is - according to a second aspect - also directed to a product or agent for water-repellent/waterproof treatment and for impregnation of a surface of building materials against liquids (particularly water and the like) as well as against chemical and biological corrosion. According to the invention this product is distinguished by an aqueous solution product which contains silicon, calcium and sodium ions, wherein calcium oxide is dissolved in water, a dissolving agent having been added to this water, and wherein this aqueous solution product, after it has been applied to the surface of the building material and dried there, forms a glass-like surface film. This product is preferably one which has been produced according to the method described above. This aqueous solution product therefore advantageously contains calcium and sodium in a ratio of Ca : Na₂ of approximately 0.1 to 1.0.

The dissolving agent used in the finished product (for increased dissolution of a sufficient quantity of calcium oxide in the water) may be of various types. Particularly preferred is sugar in the form of saccharose, which is previously dissolved in a first aqueous solution as dissolving agent for dissolving the calcium oxide. Sugar or saccharose is capable of dissolving a particularly large quantity of calcium oxide in the water, as has already been explained above. Glycerine, which in many cases can likewise be admixed as dissolving agent with the initial quantity of water or a

first aqueous solution has by comparison a somewhat reduced capacity for dissolving calcium oxide in water.

It should also be mentioned at this point that other suitable dissolving agents are also conceivable for increased dissolution of the calcium oxide in the water, even if they do not generally achieve the particularly favourable and high dissolving effect of sugar or saccharose. Phenol, an organic chemical product, may be mentioned for example as another conceivable dissolving agent to be used instead of the organic dissolving agent saccharose.

If sugar or saccharose is used as dissolving agent in the aqueous solution product according to the invention, then the finished product thus produced contains the following components in % by weight:

52.5 to 56% water (H_2O)
24 to 33% saccharose ($\text{C}_{12}\text{H}_{22}\text{O}_{11}$)
1.9 to 2.7% calcium oxide (CaO)
8.6 to 21.3% sodium metasilicate pentahydrate
($\text{Na}_2 * \text{SiO}_3 * 5\text{H}_2\text{O}$)

If, by contrast, glycerine is used as dissolving agent in the aqueous solution product, then this product contains the following components in % by weight:

55.6 to 68% water (H_2O)
31 to 36.6% glycerine ($\text{C}_2\text{OH}-\text{CHOH}-\text{CH}_2\text{OH}$)
1.1 to 1.31% calcium oxide (CaO)
4.3 to 12.3% sodium metasilicate pentahydrate
($\text{Na}_2 * \text{SiO}_3 * 5\text{H}_2\text{O}$).

Some examples of different compositions in the product according to the invention are set out below, on the one hand in the case where sugar/saccharose is used as dissolving agent

and on the other hand in the case where glycerine is used as dissolving agent, and moreover these examples of compositions differ in the different ratios of Ca : Na₂ in the particular compositions.

Example 1

With a ratio Ca: Na₂ of 0.3, individual components being listed in % by weight:

52.5 % water (H₂O)
24.27 % saccharose (C₁₂H₂₂O₁₁)
1.93 % calcium oxide (CaO)
21.3 % sodium metasilicate pentahydrate
(Na₂ * SiO₃ * 5H₂O)

100 %

Example 2

Use of saccharose as dissolving agent, with a ratio Ca : Na₂ of 0.5:

54.12 % water (H₂O)
28.56 % saccharose (C₁₂H₂₂O₁₁)
2.28 % calcium oxide (CaO)
15.04 % sodium metasilicate pentahydrate
(Na₂ * SiO₃ * 5H₂O)

100 %

Example 3

Use of saccharose as dissolving agent, with a ratio Ca : Na₂ of 1:

55.78 % water (H_2O)
32.92 % saccharose ($\text{C}_{12}\text{H}_{22}\text{O}_{11}$)
2.63 % calcium oxide (CaO)
8.67 % sodium metasilicate pentahydrate
($\text{Na}_2 * \text{SiO}_3 * 5\text{H}_2\text{O}$)

100 %

Example 4

Use of glycerine as dissolving agent, with a ratio Ca : Na_2 of 0.3:

55.63 % water (H_2O)
31.0 % glycerine ($\text{CH}_2\text{OH}-\text{CHOH}-\text{CH}_2\text{OH}$)
1.11 % calcium oxide (CaO)
12.26 % sodium metasilicate pentahydrate
($\text{Na}_2 * \text{SiO}_3 * 5\text{H}_2\text{O}$)

100 %

Example 5

Use of glycerine as dissolving agent, with a ratio Ca : Na_2 of 0.5:

55.8 % water (H_2O)
33.94 % glycerine ($\text{CH}_2\text{OH}-\text{CHOH}-\text{CH}_2\text{OH}$)
1.22 % calcium oxide (CaO)
8.04 % sodium metasilicate pentahydrate
($\text{Na}_2 * \text{SiO}_3 * 5\text{H}_2\text{O}$)

100 %

Example 6

Use of glycerine as dissolving agent, with a ratio Ca : Na₂ of 1:

57.87 %	water (H ₂ O)
36.53 %	glycerine (CH ₂ OH-CHOH-CH ₂ OH)
1.31 %	calcium oxide (CaO)
4.33 %	sodium metasilicate pentahydrate (Na ₂ * SiO ₃ * 5H ₂ O)
100	%

Generally, all these compositions forming the aqueous solution product can be diluted by water if needed or helpful for use.

According to a third aspect the present invention also relates to a method of waterproofing and impregnating a building material surface in order to protect this against liquids, particularly water and the like, as well as against chemical and biological corrosion, by the application of a coating product in its liquid or paintable state onto the surface which is to be protected. According to the invention this takes place by the following steps:

- a) preparation of a first aqueous solution by dissolving a quantity of calcium oxide in a quantity of degasified (or demineralised) water with the aid of a dissolving agent which is admixed with this quantity of water in order to increase the dissolution (dissolving capacity) of the calcium oxide;
- b) mixing together this first aqueous solution with a second aqueous solution containing sodium silicate in order to form an aqueous solution product (as coating product) which contains silicon, calcium and sodium

ions;

- c) application of this aqueous solution product onto the surface of the building material on which it dries and hardens to a glass-like surface film.

In this case the product produced by the method according to the invention as described can in particular be used as coating product. The aqueous solution product thus produced can be applied extremely simply and quickly to a building material surface which is to be protected. The product which is applied to this surface and dried and hardened to a glass-like surface film constitutes a coating product which has very many uses and acts extremely reliably and durably and which - because of the production described above and the components used therein - can also be produced very simply and economically.

In the practical application of the coating product thus produced it may be advantageous to apply this in several thin layers onto the surface of the building material to be protected in order to waterproof and impregnate this surface. This application can be carried out in particular by rolling (with paint rollers), brushing or spraying. The coats applied to a building material surface can be dried and hardened by the use of warm air and/or by natural evaporation (due to the influence of ambient air). After this drying and hardening parts of the dissolving agent can be crystallised out towards the surface. These parts of the dissolving agent which are precipitated in the surface film can be washed off in a simple manner, for example with the aid of water, but optionally also these parts which are precipitated can simply be washed off naturally by the rain. By the way, the precipitation of saccharose will be in the form of a crystallisation.

This method according to the invention can be used in particular for waterproofing and impregnation of porous surfaces on solid building material, particularly concrete, concrete-like or cement-like materials, stone materials, wood and the like.

Finally, a practical embodiment will be explained.

In the tests on which the invention is based the walls of an old swimming pool for example were waterproofed and impregnated with the coating product produced according to the invention for instance using the method of treatment described above.

In this old swimming pool the inner faces consisted of a mosaic of ceramic parts in small pieces, between which there were cement joints. Moss had grown increasingly on the inner faces or surfaces of these swimming pool walls, apart from the fact that the inner faces had in part become permeable to water.

First of all it was attempted on the one hand to waterproof the cleaned inner faces (wall surfaces) and on the other hand to impregnate them in particular against the growth of moss using a large number of various products available on the market (which had a rubber or synthetic resin base or were special paints). None of these known products could permanently eliminate the said growth of moss and at the same time create sufficient impermeability to water. The use of some of these known products even led to unwanted colour changes in the mosaic walls of the swimming pool, which brought new problems with it.

The inner faces (surfaces) of these swimming pool walls were thereupon coated by the method according to the invention with the product produced according to the invention. Accordingly

the aqueous solution product was applied to the inner faces of the walls and of the base of the swimming pool with the aid of a paint roller in a plurality of thin coats, namely five coats, sufficient time being allowed between applications to facilitate thorough drying out. The complete drying out and hardening of the finished product film on the inner faces took place through natural external drying or evaporation. Afterwards parts of the saccharose used as dissolving agent which had crystallised out on the surface were simply washed off with water.

With regard to the quality of the coating product it may also be stated that in its liquid or paintable state it had a somewhat milky quality, but after drying and hardening it formed a thin glass-like film. In this way a completely waterproof coating was produced which had moreover penetrated sufficiently deep into the pores of the building material in order reliably to prevent renewed growth of moss. In this case the further advantage was provided that due to the glass-like coating a clean unspoilt appearance of the mosaic walls of this swimming pool could be created and maintained.

Claims

1. Method of producing a product for waterproofing and impregnation of a surface of solid building materials against liquids as well as against chemical and biological corrosion, characterised by the following steps:

- a) preparing a first aqueous solution by dissolving calcium oxide in a quantity of water with the aid of a dissolving agent which is admixed with this quantity of water in order to increase the dissolution of the calcium oxide;
- b) preparing a second aqueous solution which contains water and sodium silicate;
- c) mixing together the said first aqueous solution with the second aqueous solution so that an aqueous solution product is formed which contains silicon, calcium and sodium ions and which forms a glass-like surface film on the corresponding building material surface when it is in the dried state.

2. Method as claimed in Claim 1, characterised in that sugar in the form of saccharose is dissolved as dissolving agent in the first aqueous solution in order to dissolve an increased quantity of the calcium oxide.

3. Method as claimed in Claim 1, characterised in that glycerine is admixed with the first aqueous solution as dissolving agent in order to increase the dissolution of the calcium oxide.

4. Method as claimed in Claim 1, characterised in that

- a quantity of water is boiled for degasification,

- the dissolving agent is added to this degasified water, and
- then the calcium oxide in the form of quicklime or calcium hydrate is admixed with the said water at room temperature and dissolved, so that this first aqueous solution is formed.

5. Method as claimed in Claim 4, characterised in that quicklime (CaO) is added in a ratio which depends upon the quantity of dissolving agent used, calcium hydrate ($\text{Ca}(\text{OH})_2$) being formed in the first aqueous solution.

6. Method as claimed in Claim 5, characterised in that calcium oxide and sodium silicate are added to the first and second aqueous solutions in such quantities that the finished aqueous solution product contains a ratio of $\text{Ca} : \text{Na}_2$ of approximately 0.1 to 1.0.

7. Method as claimed in Claim 1 and/or 6, characterised in that the sodium silicate is dissolved in the second aqueous solution preferably in the form of sodium metasilicate pentahydrate ($\text{Na}_2 * \text{SiO}_3 * 5\text{H}_2\text{O}$).

8. Product for waterproofing and impregnating a surface of solid building materials against liquids as well as against chemical and biological corrosion, characterised by an aqueous solution product which contains silicon, calcium and sodium ions, wherein calcium oxide is dissolved in water with the aid of a dissolving agent added to the water, and wherein this aqueous solution product, after it has been applied to the surface of the building material and dried there, forms a glass-like surface film.

9. Product as claimed in Claim 8, characterised in that the said aqueous solution product contains calcium and sodium in a

ratio of Ca : Na₂ of approximately 0.1 to 1.0.

10. Product as claimed in Claim 8, characterised in that the aqueous solution product contains the following components (in % by weight):

52.5 to 56 % water (H₂O)
24 to 33 % saccharose (C₁₂H₂₂O₁₁)
1.9 to 2.7 % calcium oxide (CaO)
8.6 to 21.3 % sodium metasilicate pentahydrate
(Na₂ * SiO₃ * 5H₂O).

11. Product as claimed in Claim 8, characterised in that the aqueous solution product contains the following components (in % by weight):

55.6 to 68 % water (H₂O)
31 to 36.6 % glycerine (CH₂OH-CHOH-CH₂OH)
1.1 to 1.31 % calcium oxide (CaO)
4.3 to 12.3 % sodium metasilicate pentahydrate
(Na₂ * SiO₃ * 5H₂O).

12. Product as claimed in Claim 10 or 11, characterised in that the aqueous solution product is dilutable for use by water.

13. Method of waterproofing and impregnating a surface of building materials against liquids as well as against chemical and biological corrosion by the application of a coating product in its liquid or paintable state onto the surface, characterised by the following steps:

- a) preparation of a first aqueous solution by dissolving a quantity of calcium oxide in a quantity of degasified water with the aid of a dissolving agent which is admixed with this quantity of water in order to increase

the dissolution of the calcium oxide;

- b) mixing together this first aqueous solution with a second aqueous solution containing sodium silicate in order to form an aqueous solution product which contains silicon, calcium and sodium ions;
- c) application of this aqueous solution product onto the surface of the building material on which it dries and hardens to a glass-like surface film.

14. Method as claimed in Claim 13, characterised in that the finished aqueous solution product is applied in several thin coats onto the surface of the building material to be made waterproof, in particular by rolling, brushing or spraying.

15. Method as claimed in Claim 14, characterised in that the coats applied to the surface are dried and hardened by warm air and/or by natural evaporation.

16. Method as claimed in Claim 15, characterised in that parts of the dissolving agent precipitated on the surface film are washed off.

17. Method as claimed in Claim 13, characterised by its use for waterproofing and impregnating porous surfaces of solid building materials, particularly of concrete, concrete-like or cement-like materials, stone materials, wood and the like.

INTERNATIONAL SEARCH REPORT

Int: ional Application No

PCT/EP 98/04914

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C04B41/50 B27K3/16 //C04B111/20,C04B111/27

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 927 059 A (ZIAK ERNA E)	1,4,5,7, 8,12-15, 17
Y	see claims 1,5 see page 1, line 67 - line 81 see page 2, line 28 - line 33 ---	2,3
Y	EP 0 237 016 A (KOCH MARMORIT GMBH) 16 September 1987	2,3
A	see claims 1,6,9,10 see column 5, line 5 - line 14 --- -/--	1,5,8, 10-13

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z" document member of the same patent family

Date of the actual completion of the international search

11 December 1998

Date of mailing of the international search report

18/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

ROSENBERGER, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/04914

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Section Ch, Week 8510 Derwent Publications Ltd., London, GB; Class J01, AN 85-059674 XP002064718 & JP 60 016878 A (NISSHIN KOGYO KK) , 28 January 1985 see abstract -----	1,3,5-9, 12,13,17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/04914

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 927059 A		NONE	
EP 0237016 A	16-09-1987	DE 3608195 A	17-09-1987