



(22) Date de dépôt/Filing Date: 1991/10/17  
(41) Mise à la disp. pub./Open to Public Insp.: 1992/04/19  
(45) Date de délivrance/Issue Date: 2002/10/15  
(30) Priorités/Priorities: 1990/10/18 (599,550) US;  
1990/10/18 (599,610) US; 1990/10/18 (599,538) US;  
1990/10/22 (600,898) US; 1990/10/22 (600,781) US

(51) Cl.Int.<sup>5</sup>/Int.Cl.<sup>5</sup> C08F 2/00, C08F 4/642, C08F 4/64  
(72) Inventeur/Inventor:  
Job, Robert Charles, US  
(73) Propriétaire/Owner:  
UNION CARBIDE CHEMICALS & PLASTICS  
TECHNOLOGY CORPORATION, US  
(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : CATALYSEUR DE POLYMERISATION D'OLEFINES  
(54) Title: OLEFIN POLYMERIZATION CATALYST

(57) Abrégé/Abstract:

High activity, stereoregular olefin polymerization catalysts are produced from an organoaluminum cocatalyst, a selectivity control agent and a procatalyst obtainable from a magnesium-containing, titanium-containing procatalyst precursor also containing at least one of alkoxide, optionally substituted phenoxide or trialkylborate moieties. The catalysts are useful in the polymerization or copolymerization of lower  $\alpha$ -olefins, particularly propylene.



2053645

ABSTRACT

High activity, stereoregular olefin polymerization catalysts are produced from an organoaluminum cocatalyst, a  
5 selectivity control agent and a procatalyst obtainable from a magnesium-containing, titanium-containing procatalyst precursor also containing at least one of alkoxide, optionally substituted phenoxide or trialkylborate moieties. The catalysts are useful in the polymerization or  
10 copolymerization of lower  $\alpha$ -olefins, particularly propylene.

OLEFIN POLYMERIZATION CATALYST

This invention relates to a magnesium-containing, titanium-containing precursor of a catalyst component which can be used to produce a high activity olefin polymerization catalyst.

The production of polymers of  $\alpha$ -olefins, particularly ethylene and propylene, has gained commercial acceptance. The products are inexpensive and exhibit a number of commercially useful properties. In the case of the polymerization of ethylene the process is uncomplicated in that the product type is not influenced by the manner in which the ethylene molecules add to the growing polymer chain and the polymeric product does not exist in stereoisomeric forms.

In the case of polymerization of propylene the presence of methyl groups provides the several types of product depending on the steric regularity with which units add to the growing polymeric chain. Most commercial polypropylene is crystalline and results from stereoregular addition of propylene units in a regular head-to-tail manner. Polypropylene in which the units add randomly is termed atactic. This amorphous form is less desirable and often must be removed as by extraction.


Also significant is the activity of the polymerization catalyst. The early trivalent titanium, chromium or vanadium catalysts were of low activity and the product contained a significant proportion of catalyst residues. Removal of such residues was required to obtain commercially satisfactory properties.

The more recent titanium-based polymerization catalysts are stereoregulating and have sufficient activity to avoid extraction and deashing steps. In terms employed conventionally, the high activity catalysts are formed from a solid procatalyst which typically contains magnesium, titanium and halide moieties, a cocatalyst which is usually an organoaluminum compound and a selectivity control agent

(SCA). Each of these components influences the catalyst and polymer produced therefrom but the procatalyst seems to have the greatest influence.

US-A-4,330,649 describes a procatalyst obtained by heating a magnesium compound with a higher alcohol and an ester to produce a solution. This solution is added to  $\text{TiCl}_4$  and an electron donor (ED) to form the procatalyst. US-A-4,472,521 describes reacting a magnesium alkoxide with a titanium alkoxide in an aromatic hydrocarbon.  $\text{TiCl}_4$  and an ED are added to form a solid which is post-treated with transition metal halide. US-A-4,540,679 describes the production of a catalyst component by contacting a suspension of  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  in ethanol with  $\text{CO}_2$ . The addition of organoaluminum in hydrocarbon produces granular particles employed as support for titanium compound upon contact with  $\text{TiCl}_4$ . US-A-4728705 describes solubilizing  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  in ethanol with  $\text{CO}_2$  and spray drying the resulting solution or using the solution to impregnate carrier particles. Either type of particle is useful in the production of procatalyst of desirable morphology.

A different catalyst is described in US-A-4,710,428, wherein a magnesium compound of the general formula



is formed wherein R is lower alkyl and A is at least one anion having a total oxidation state of -2. This complex is reacted with tetravalent titanium halide, a halohydrocarbon and an ED to form a procatalyst. The use of the above complexes has advantages in that the complexes are crystals of desirable morphology in contrast to  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  which is not. The crystals can be converted to olefin polymerization catalyst precursors and to catalysts by largely conventional technology. The catalysts are active and produce polymer products of good properties. It would be of advantage to produce improved catalyst precursors and olefin polymerization catalysts whose use results in improved

polymer product.

The invention provides complex magnesium-containing, titanium-containing compounds useful as precursors of high activity olefin polymerization catalysts and a process of polymerizing lower  $\alpha$ -olefins employing such catalysts. The polyolefins obtained by use of the catalysts have good properties and are obtained in good yield.

Accordingly the invention provides an olefin polymerization procatalyst precursor which contains moieties of magnesium and titanium and at least one of alkoxide, trialkylborate and optionally substituted phenoxide moieties and is obtainable:

- A. by contacting a magnesium alkoxide, a titanium alkoxide and a trialkylborate in an alkanol at an elevated temperature and removing alkanol from the resulting complex alkoxide compound alcoholate;
- B. by contacting magnesium, a titanium alkoxide, a trialkylborate and an alkanol in an inert reaction diluent at an elevated temperature;
- C. by contacting a magnesium alkoxide, a titanium tetraalkoxide and a phenolic compound at an elevated temperature in an inert diluent;
- D. by contacting a magnesium alkoxide, a titanium alkoxide, a titanium tetrahalide, a phenolic compound and an alkanol, and removing alkanol from the resulting mixture; or
- E. by contacting a magnesium alkoxide, a titanium tetraalkoxide and a phenolic compound, reacting the resulting product with a magnesium halide alcoholate, and removing alkanol from the resulting mixture, wherein each alkoxide moiety independently has up to 4 carbon atoms inclusive and the phenolic compound is selected from phenol and an activating group-substituted phenol. The procatalyst precursor can then be contacted with a halide of tetravalent titanium halide, an optional haloalkane and an ED to form a solid procatalyst. The procatalyst in turn can then be contacted with an organoaluminum cocatalyst and an SCA to


form a high activity olefin polymerization catalyst. The conversion of procatalyst precursor to procatalyst and of procatalyst to catalyst is largely conventional, but the procatalyst precursor can suitably be formed by a number of 5 procedures and takes various forms and compositions depending upon the method of its preparation.

In one embodiment, a complex alkoxide compound is produced from a magnesium alkoxide, wherein each alkoxide suitably has up to 4 carbon atoms inclusive, a titanium 10 alkoxide, wherein each alkoxide suitably has up to 4 carbon atoms, and a trialkylborate, wherein each alkyl suitably has up to 4 carbon atoms. The reactants are contacted at an elevated temperature and alkanol is removed from the resulting complex alkoxide compound alcoholate. The 15 alkoxide moieties within each reactant can be the same or different and the alkoxide moieties of any one reactant can be the same as or different from the alkoxide moieties of other reactants. Although alkoxide moieties such as methoxide, i-propoxide or i-butoxide are useful, the 20 preferred alkoxide moiety is ethoxide. The stoichiometry of the complex alkoxide compound is of the formula



wherein each R independently is alkyl of up to 4 carbon atoms inclusive and is preferably ethyl.

25 The contacting of the magnesium, titanium and boron compounds takes place in alkanol solution at an elevated temperature and suitably at a pressure sufficient to maintain the reaction mixture in a non-gaseous state. The alkanol preferably, but not necessarily, corresponds to the 30 alkoxide moieties of one or more of the reactants. Suitable reaction temperatures are from 20°C to 180°C, preferably from 50°C to 90°C. Contacting is conducted in a suitable reactor and can be facilitated by conventional methods such as shaking, stirring or refluxing. The initial product, 35 obtained as a crystalline alcoholate upon cooling of the product mixture, is illustrated by the formula



wherein n is a number from 0 to about 6. This process of producing a complex alkoxide requires a trialkylborate even though boron does not appear in the crystalline product.

5 The trialkylborate suitably is provided in a quantity from about 0.1 to about 2 moles, preferably from 0.5 to 1 mole, per mole of titanium. The magnesium alkoxide suitably is provided in a quantity from about 0.5 mole to about 4 moles, preferably from 0.5 to 2 moles, per mole of titanium.

10 The resulting complex alkoxide compound (formula IIa) is a solid, crystalline material of low solubility in the medium of its production and can be recovered by well known methods such as filtration or decantation. The alcoholate is converted to the complex alkoxide procatalyst  
15 precursor (formula II) by removal of alkanol by conventional procedures generally involving heat. A particularly satisfactory method is by azeotropic distillation with a hydrocarbon or halohydrocarbon solvent. Such solvents in which the complex alkoxide of formula II is soluble and with  
20 which the alkanol forms an azeotrope are useful. An illustrative hydrocarbon is isooctane and an illustrative halohydrocarbon is chlorobenzene. The azeotropic solvent is added in a quantity in excess of the alkanol present and the resulting mixture is heated to remove the alkanol  
25 azeotropically. The complex alkoxide procatalyst precursor (formula II) which results forms a clear solution in excess azeotropic solvent at the boiling point of the azeotrope as well as upon cooling to ambient temperature. The solution can serve as procatalyst precursor and can be converted to a  
30 procatalyst as described below.

In a second embodiment a complex alkoxide procatalyst precursor is produced by reaction of elemental magnesium with a titanium alkoxide, wherein each alkoxide suitably has up to 4 carbon atoms, a trialkylborate, wherein  
35 each alkyl suitably has up to 4 carbon atoms, and an alkanol, suitably of up to 4 carbon atoms, in the presence

of an inert diluent. In this embodiment also, the alkoxide moieties of any reactant or of the different reactants are the same or are dissimilar. It is generally preferred that all alkoxide moieties be the same and be ethoxide. The  
5 complex alkoxide of this embodiment is produced by contacting the reactants in an inert reaction diluent which suitably is a hydrocarbon diluent such as isopentane, isooctane, cyclohexane, toluene or even a kerosene fraction, or a halohydrocarbon such as methylene chloride or  
10 chlorobenzene. Isooctane is a preferred hydrocarbon diluent and chlorobenzene is a preferred halohydrocarbon diluent.

The structure of the complex alkoxide compound of this embodiment is somewhat variable and will in part be determined by the ratio of reactants employed. The  
15 structure can be illustrated by the formula



wherein  $0 < t \leq 2$ ,  $s$  is  $(10-t)$  and each R independently is alkyl of up to 4 carbon atoms. A preferred complex alkoxide is of the above formula III wherein  $t$  is 2 and R is ethyl.  
20 The complex alkoxide is produced by contacting the reactants at an elevated temperature and suitably at a pressure sufficient to maintain the reaction mixture in a non-gaseous state. Suitable temperatures are from about 40°C to about 100°C, preferably from about 50°C to about 80°C. The  
25 contacting is conducted in a suitable reactor and can be conventionally facilitated as by shaking, stirring or refluxing. The stoichiometry of the reaction is not simple but sufficient magnesium is usually employed to provide from about 1% to about 6% by weight of magnesium based on total  
30 solution weight. Best results are obtained if a small amount of metal surface activator such as ferric chloride is provided to initiate reaction. The complex alkoxide product mixture is a solution of variable viscosity depending in part on the diluent and the ratio of starting materials.  
35 The complex alkoxide is an olefin polymerization procatalyst precursor and can be converted to a procatalyst by methods


described below.

In a third embodiment, the complex olefin polymerization procatalyst precursor is produced by contacting a magnesium alkoxide, a titanium alkoxide and a phenolic compound in an inert diluent. In this embodiment also, the alkoxide moieties of a reactant or of the reactants are the same or different and are preferably ethoxide. The phenolic compound, characterized as producing an anion moiety X', is selected from phenol or activating group-substituted phenol whose phenolic hydroxyl group is free of steric hindrance. By "activating group" is meant a substituent on a ring carbon atom free from active hydrogens such as alkyl of up to 5 carbon atoms, e.g. methyl, ethyl or butyl; alkoxy of up to 5 carbon atoms, e.g. methoxy, ethoxy or amyloxy; halo, particularly chloro; and dialkylamino wherein each alkyl group has up to 5 carbon atoms such as dimethylamino or ethylpropylamino. Illustrative of suitable phenolic compounds are phenol, o-cresol, 3-methoxyphenol, 4-dimethylaminophenol and 2,6-dimethylphenol. Of such phenols, o-cresol is preferred.

The complex alkoxide procatalyst precursor of this embodiment can be illustrated by the formula



wherein R is as previously defined, X' is a monovalent anion of the phenolic compound,  $0.5 \leq a \leq 2$ ,  $0 \leq c \leq 2$  and b is  $(6+4a+c)$ . A preferred complex alkoxide has the formula




wherein R and X' are as previously defined. The inert diluent suitably is a hydrocarbon such as isopentane, isooctane, toluene, or even a kerosene fraction or is a halohydrocarbon such as methylene chloride or chlorobenzene.

The production of the complex alkoxide of formula IV takes place at elevated temperature and suitably at a pressure sufficient to maintain the reaction mixture in a non-gaseous state. Suitable temperatures are from about 50°C to about 110°C, preferably from about 70°C to about

100°C. The contacting is in a suitable reactor and can be conventionally facilitated as by shaking, stirring or refluxing. Sufficient magnesium alkoxide is usually employed to provide from about 1% to about 6% by weight magnesium based on total solution. The complex alkoxide olefin procatalyst precursor which results is a solution of variable viscosity depending upon the particular diluent employed and the ratio of reactants. The precursor can be converted to a procatalyst by procedures described below.

10 In a fourth embodiment, the procatalyst is a complex of indefinite stoichiometry formed from a magnesium alkoxide, wherein each alkoxide independently has up to 4 carbon atoms inclusive, a tetravalent titanium alkoxide wherein each alkoxide suitably has up to 4 carbon atoms  
15 inclusive, a halide of tetravalent titanium, a phenolic compound and an alkanol. The alkoxide moieties of one or both alkoxides can be the same as or different from other alkoxides and are preferably ethoxy, and the halide moieties suitably are chloro or bromo but preferably are chloro. The  
20 phenolic compound is selected from phenol and an activating group-substituted phenol where the activating group is as described above.

This procatalyst precursor is suitably produced by contacting the reactants in an inert reaction diluent, e.g.  
25 a hydrocarbon such as isopentane, isooctane or cyclohexane, or a halohydrocarbon such as methylene chloride or chlorobenzene. Isooctane and chlorobenzene are preferred. The formation of the procatalyst precursor does not appear to follow conventional molar stoichiometry but is  
30 illustrated by the following partial general equation employing preferred alkoxide and halide moieties:-



wherein  $0.1 \leq y < 0.8$ ,  $0.2 < (x+y) < 3$ ,  $0.05 < z < 3$  and  $0.5 < w < 9$ .


Preferably,  $0.3 < y < 0.5$ ,  $0.5 < (x+y) < 2$ ,  $0.1 < z < 2$  and  $2 < w < 5$ .

35 The initial reaction suitably takes place in a non-gaseous state at a reaction temperature from about 30°C to

about 120°C, preferably from about 35°C to about 90°C, to produce a generally clear solution. This solution can then be heated to a higher temperature sufficient to remove alkanol, typically as an azeotrope with a portion of the inert reaction diluent. The temperature of this second heating will depend in part upon the boiling point of any alkanol-containing azeotrope which is formed, e.g. temperatures from about 70°C to about 120°C, preferably from about 85°C to about 110°C. The removal of alkanol results in the production of the procatalyst precursor in the form of opaque, spheroidal particles. This olefin polymerization procatalyst precursor can be converted to a procatalyst by methods described below.

In a fifth embodiment, the olefin polymerization procatalyst is produced by a two-step synthesis initially involving reaction of a magnesium alkoxide, wherein each alkoxide suitably has up to 4 carbon atoms, a titanium alkoxide, wherein each alkoxide suitably has up to 4 carbon atoms and a phenolic compound. The alkoxide moieties of the same or different alkoxide reactants are similar or dissimilar and the phenolic compound is selected from phenol and activating group-substituted phenol wherein the activating group is as previously defined.

The initial reaction suitably takes place in an inert reaction diluent by contacting the metal alkoxides and the phenolic compound at an elevated temperature. Reaction diluents that are suitable are relatively high-boiling so as to be liquid at the temperature of the contacting. Diluents such as chlorobenzene, toluene and isooctane are suitable. The temperature of the contacting suitably is from about 60°C to about 130°C and a pressure sufficient to maintain the reaction mixture in a non-gaseous phase is desirable. The initial product is a complex of the starting materials illustrated but not limited by the formula



wherein R and X' have the previously stated meanings. This

initial product can be obtained as a solution in the reaction diluent.

This initial product is then contacted with a magnesium halide alcoholate, preferably a hexaalcoholate, in which the alcohol moieties are ROH where R has the previously stated meaning. The magnesium halide can be  $MgCl_2$  or  $MgBr_2$ , preferably  $MgCl_2$ . The initial complex and the magnesium halide alcoholate can be mixed in an inert reaction diluent which is the same as or different from the diluent used to prepare the initial complex. Preferably, the diluent is the same. The reactants are contacted and heated, for example at a temperature up to about  $100^\circ C$ , until a solution is obtained and then heated, for example from about  $110^\circ C$  to about  $140^\circ C$ , to remove alkanol from the mixture, often as an azeotrope with the inert diluent. The product, of somewhat variable composition, is obtained as opaque, spheroidal particles. This magnesium-containing, titanium-containing solid is an olefin polymerization procatalyst precursor and can be converted to a procatalyst by methods described below.

The olefin polymerization procatalyst precursor can be converted to a procatalyst by contact with a halide of tetravalent titanium, optionally with halohydrocarbon, and an ED. The halide of tetravalent titanium can be an aryloxy- or an alkoxy- di- or trihalide such as diethoxytitanium dichloride, dihexyloxytitanium dibromide, isopropoxytitanium trichloride, or phenoxytitanium tribromide, or can be a titanium tetrahalide such as  $TiCl_4$  or  $TiBr_4$ . A titanium tetrahalide is preferred, particularly  $TiCl_4$ .

The halohydrocarbon optionally employed in the production of procatalyst suitably has up to 12 carbon atoms, preferably up to 9 carbon atoms, and contains at least one halogen atom or in the case of aliphatic halohydrocarbons contains at least two halogens. Exemplary aliphatic halohydrocarbons include  $CH_2Cl_2$ ,  $CH_2Br_2$ ,  $CHCl_3$ ,

$\text{CCl}_4$ , 1,2-dibromoethane, 1,1,3-trichloropropane, 1,1,2-trichloroethane, trichlorocyclohexane, dichlorofluoromethane and trichloroisooctane. Aromatic halohydrocarbons suitably employed include chlorobenzene, bromobenzene,  
5 dichlorobenzene and chlorotoluene. Of the aliphatic halohydrocarbons  $\text{CCl}_4$  and 1,1,2-trichloroethane are preferred, but particularly preferred is chlorobenzene.

The electron donor employed in the procatalyst is an ED conventionally used in titanium-based olefin  
10 polymerization procatalyst. The ED can be free from active hydrogens. Examples of suitable electron donors include ethers, esters, ketones, amines, imines, amides, nitriles, phosphines, stibines, arsines and alcoholates. A preferred ED is an ester, particularly an alkyl ester of an aromatic  
15 monocarboxylic or dicarboxylic acid. Preferred ED's are ethyl benzoate, ethyl p-ethylbenzoate and diisobutyl phthalate. The ED can be a mixture of compounds but preferably is a single compound. Ethyl benzoate and diisobutyl phthalate are preferred.

20 The manner in which the procatalyst precursor, halide of tetravalent titanium, the halohydrocarbon when employed and the ED are contacted is material but not critical. Best results are obtained when the ED is added to the procatalyst precursor and the resulting mixture is added  
25 to at least a portion of the halide of tetravalent titanium. Alternatively, the halide of tetravalent titanium is added to a mixture of the procatalyst precursor and the ED. Other modifications are suitable but less preferred. The resulting solid is typically washed with a 50/50 mixture by  
30 volume of additional halide of tetravalent titanium and halohydrocarbon at least once and often twice or more times. This washing process, often termed a halogenation, is frequently aided by the additional presence of an acid halide, particularly an aromatic acid halide such as benzoyl  
35 chloride or phthaloyl chloride. Subsequent to contacting with a halide of tetravalent titanium and halohydrocarbon,

the resulting solid procatalyst can be washed with a light hydrocarbon to remove unreacted titanium compounds.

In the preferred modification, the initial contacting of ED and procatalyst precursor is conducted at a temperature from about ambient temperature to about 150°C. Preferably, the materials are mixed at ambient temperature. Sufficient halide of tetravalent titanium and any acid halide are used to convert a substantial portion of the anion moieties of the procatalyst precursor to halide moieties. Sufficient ED is used so that the molar ratio of ED to Mg present in the procatalyst precursor is from about 0.01:1 to about 10:1, preferably from about 0.06:1 to about 0.4:1. The final washing produces procatalyst which is stable upon drying in the absence of O<sub>2</sub> and active hydrogen compounds or useful without drying in the formation of an olefin polymerization catalyst by reaction with a cocatalyst and SCA.

The cocatalyst is an organoaluminum compound of the type normally employed with titanium-based procatalysts in the production of high-activity olefin polymerization catalysts. Suitable organoaluminum compounds are alkylaluminum compounds such as trialkylaluminum compounds, alkylaluminum halide compounds and alkylaluminum alkoxide compounds wherein each alkyl independently has 2 to 6 carbon atoms. The preferred alkylaluminum compounds are free of halide moieties and particularly preferred are trialkylaluminum compounds such as triethylaluminum, triisobutylaluminum and diethylhexylaluminum. Triethylaluminum is especially preferred. The organoaluminum compound is suitably employed in sufficient quantity to provide from about 1 mole to about 150 moles of aluminum per mole of titanium in the procatalyst, preferably from about 10 moles to about 100 moles of aluminum per mole of titanium.

The SCA employed in catalyst production can be any conventionally utilized in olefin polymerization catalysts

based on titanium. A suitable SCA is an ED such as those above for use in procatalyst production but may also be an organosilane of the formula  $R'_qSi(OR)_{4-q}$  wherein  $R'$  is alkyl or aryl of up to 10 carbon atoms,  $R$  has the previously stated meaning and  $q$  is 1 or 2. A preferred SCA is an ester of an aromatic acid, e.g. ethyl p-ethylbenzoate, diisobutyl phthalate, or ethyl p-methylbenzoate, or an alkylalkoxysilane such as diisobutyldimethoxysilane, isopropyltrimethoxysilane or  
10 cyclohexylmethyldimethoxysilane. The SCA is suitably provided to give from about 0.01 mole to about 100 moles of SCA per mole of titanium in the procatalyst, preferably from about 0.5 mole to about 20 moles per mole of titanium.

The components of the olefin polymerization  
15 catalyst are contacted by largely conventional methods. In one modification, the components are contacted outside the polymerization zone as by mixing the components and introducing the preformed catalyst into the polymerization reactor. In an alternative modification, the catalyst  
20 components are introduced separately into the polymerization reactor and the catalyst is formed in situ. The olefin polymerization catalyst is useful in the polymerization of lower  $\alpha$ -olefins under polymerization conditions and particularly in the polymerization of straight-chain  $\alpha$ -  
25 olefins of up to 4 carbon atoms, i.e ethylene, propylene and 1-butene. The procedure of the polymerization process of the invention, by virtue of its use of a catalyst produced from the complex procatalyst precursors of the invention, provides polyolefin product having good properties in  
30 quantities which reflect the high activity of the catalyst. The polymerization product can be a homopolymer, e.g. polyethylene or polypropylene, when a single  $\alpha$ -olefin monomer is supplied to the reactor. Alternatively, the product can be a copolymer (or terpolymer) such as EPR or  
35 polypropylene impact copolymer when two or more monomers are provided to the polymerization reactor.

The polymerization can be conducted as a gas-phase process employing one or more fluidized catalyst beds or can be conducted as a slurry-phase process employing as a diluent an inert material such as propane or a liquified monomer of the polymerization such as propylene. The molecular weight of the polymer product and thus to some extent the properties of the product are influenced by the provisions to the polymerization system of molecular hydrogen as is known in the art. The process can be conducted batch-wise or in a continuous or semi-continuous manner.

The catalyst productivity is often inversely related to selectivity so that highly active catalysts often afford polymer product of low stereoregularity. The catalysts of the invention exhibit good productivity while retaining a desirably high stereospecificity so that polymer is obtained in good quantities with sufficiently good properties that extraction and deashing steps are not required.

The invention will be further illustrated by reference to the following Examples. In the Examples the productivity of the catalyst (also termed "yield") is determined in kg of polymer product per gram of catalyst in a standard batch process of 1 hour. The stereospecificity of the catalyst and specifically the selectivity to isotactic product is determined by measuring the xylene solubles (XS) in accordance with the regulations of the U.S. Food and Drug Administration. The test for XS comprises dissolving a polymer sample in xylene under reflux in a flask. The flask is then placed in a water bath at 25°C for 1 hour without stirring. The precipitate formed is then removed by filtration and the solubles content is determined by evaporating an aliquot of the filtrate followed by drying and weighing the residue. The xylene solubles consist primarily of amorphous (atactic) polymer and a small amount of low molecular weight polymer. The bulk density of

polymer product (B.D.) is determined in gm/cm<sup>3</sup>.

Example I (First Procatalyst Precursor Embodiment)

A. Magnesium ethoxide (15g, 131 mmol), 15g (66 mol) of Ti(OC<sub>2</sub>H<sub>5</sub>)<sub>2</sub> and 33.3g of ethanol were stirred 5 overnight in a 100°C oil bath. Addition of an additional 33.3g of ethanol and 1 hr. heating did not produce a solution. Triethylborate (9.6 g, 66 mol) was added and a solution was obtained with a few minutes heating. The stirred solution was cooled to room temperature and a 10 precipitate formed. This precipitate was recovered by filtration, washed with ethanol and dried under flowing nitrogen. Transparent rhombic crystals, 20.8g, were obtained. Analysis: 5.7% Mg, 10.5% Ti, 0.4% B.

B. Magnesium ethoxide (60g, 524 mmol) and 78.2g 15 (275 mmol) of Ti(O-iC<sub>3</sub>H<sub>7</sub>)<sub>4</sub> were slurried overnight in the absence of diluent while heated in a 135°C oil bath. The resulting gray slush was slurried with 168g of ethanol and 18.9g (130 mmol) B(OC<sub>2</sub>H<sub>5</sub>)<sub>3</sub>. Upon heating in a 100°C oil bath for 2 hours, a nearly clear solution resulted. After 20 cooling overnight, a precipitate formed which was recovered, washed with ethanol and dried under flowing N<sub>2</sub> to yield 160g of a moist powder.

C. In a 3-litre flask were slurried 188g (1.64 mole) of Mg(OC<sub>2</sub>H<sub>5</sub>)<sub>2</sub>, 312g (1.1 mole) of Ti(O-iC<sub>3</sub>H<sub>7</sub>)<sub>4</sub>, 572g 25 of ethanol and 447g of a 3% solution of Mg(OC<sub>2</sub>H<sub>5</sub>)<sub>2</sub>.1.2B(OC<sub>2</sub>H<sub>5</sub>)<sub>3</sub> in ethanol (0.55 mole Mg, 0.66 mole B). After stirring overnight at 70°C the solution was cooled to form a precipitate. The precipitate was collected by filtration, rinsed with ethanol and dried briefly under 30 flowing N<sub>2</sub> to produce about 600g of a moist, crystalline solid.

D. Rhombic crystals (37.8g) prepared according to the procedure of Example I.A were slurried into 170g of chlorobenzene and then boiled to a weight of 50g. The 35 resulting solution was clear and stable.

E. An ethanol-moist powder (160g) prepared by the

procedure of Example I.B was slurried in about 500g of isooctane and the resulting solution was boiled to a weight of 319g. The resulting slightly cloudy solution was filtered through a medium porosity frit to produce a 5 solution of about 3% magnesium.

F. An ethanol-moist powder (600g) prepared according to Example I.C was slurried in 1800 ml of isooctane. The resulting mixture was distilled at a head temperature of from about 69°C to about 93°C until about 10 1600 ml of solvent were collected. The slightly cloudy solution was filtered through a medium porosity frit to produce 963g of a clear solution. Analysis: Mg = 1.24 mmol/ml, Ti = 0.835 mmol/ml and B = <0.1 mmol/ml.

G. Procatalysts were produced from the 15 procatalyst precursor solutions of Examples I.D-F by employing a digest at 110°C for 60 minutes in 150 ml of TiCl<sub>4</sub>, utilizing sufficient solution to provide 30-50 mmol magnesium. Sufficient diisobutyl phthalate was also present to provide a concentration of about 40 mmol/litre. The 20 resulting solid product was washed at 110°C with 150 ml of a 50/50 by volume mixture of chlorobenzene and TiCl<sub>4</sub> containing 6 mmol/litre of phthaloyl chloride. This was followed by a 30 minute wash at 110°C with the 50/50 mixture. The resulting solid procatalyst was washed twice 25 with isooctane at room temperature and dried under N<sub>2</sub> at 50°C.

The contacting of the precursor solutions and the first wash solution was accomplished by two methods. In method 1, the diisobutyl phthalate was added to the 30 precursor solution and the mixture was added dropwise to 150 ml of stirred TiCl<sub>4</sub> mixture at room temperature. After 20 minutes, the mixture was heated to 110°C for the remainder of the digest period. Method 2 is similar, except the precursor solution and ED were held overnight at room 35 temperature before being added to the TiCl<sub>4</sub> mixture.

H. Polymerization catalysts were produced from

the procatalysts of Example I.G. Triethylaluminum was used as cocatalyst and diisobutyl phthalate as SCA. Using these catalysts, propylene was polymerized in a slurry-phase process in liquid propylene. The results are shown in Table 5 I where "Source" indicates the particular procedure of Example I employed to produce the procatalyst precursor solution and "Method" indicates the method of Example I.G by which the procatalyst was formed. Also shown are results using a catalyst produced from  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  rather than a 10 procatalyst of the invention.

TABLE I

Run	Source	Method	Ti in catalyst, %	Yield	XS	BD
1	$\text{Mg}(\text{OC}_2\text{H}_5)_2$	-	2.28	26.6	2.7	0.33
2	E	2	2.43	26.1	3.5	0.363
3	D	2	2.42	30.8	3.5	0.38
4	E	2	2.34	31.2	3.6	0.374

Example II (Second Procatalyst Precursor Embodiment)

A. Magnesium turnings (2.44g, 100 mmol),  $\text{Ti}(\text{OC}_2\text{H}_5)_4$  (8.8g of 95%, 33 mmol) and  $\text{B}(\text{OC}_2\text{H}_5)_3$  (4.86g, 33 mmol) were slurried in 71.3g of chlorobenzene in a 0.23 15 litre (8 oz) bottle and 3.5g of 3.5%  $\text{FeCl}_3$  in ethanol were added. A balloon was attached to the bottle and the mixture was stirred while heated in a 65°C oil bath. After 40 minutes, the volume of the balloon was about 200 ml. Additional ethanol, 3.7 g, was added and the evolution of  $\text{H}_2$  20 became more vigorous, providing 200 ml of gas in about 4 minutes. After 30 more minutes the evolution of gas had ceased and another 2.5g of ethanol was added. After a total of 4 hours, nearly all the Mg had reacted to give a solution. An additional 0.5g of  $\text{FeCl}_3$  solution was added 25 and the mixture was stirred overnight when all the Mg had reacted. The solution had a magnesium content of 2.2% and a molar B/Mg/Ti ratio of 1/3/1.

B. To 49g of a solution produced according to

Example II.A, 1.32g (54 mmol) of Mg turnings, 4g of 95%  $\text{TiCl}_4$  (17 mmol) and 5g of the 3%  $\text{FeCl}_3$  in ethanol were added. After stirring overnight while placed in a 65°C oil bath, a slightly cloudy solution resulted. About 0.1g of Mg had not reacted. The solution had a molar B/Mg/Ti ratio of 0.5/3/1.

C. Magnesium turnings (62.9g, 2.59 moles),  $\text{Ti}(\text{OC}_2\text{H}_5)_4$ , 200g of 95%, 0.83 mmol,  $\text{B}(\text{OC}_2\text{H}_5)_3$ , 60.7g, 0.42 mole and 96g of 2%  $\text{FeCl}_3$  in ethanol were mixed in 750g of isooctane in a 2-litre, 3-neck flask equipped with a reflux condenser. The flask and contents were heated to about 65°C and hydrogen evolved. After about 2 hours, 95g of ethanol was added and after 2 more hours 49g of ethanol was added. After stirring for a total of 36 hours at 60°C the solution which resulted was filtered while warm to recover 2.73g of magnesium. The filtrate was 1297g of a clear, olive drab solution having a magnesium content of 4.6% and a molar B/Mg/Ti ratio of 0.5/3/1.

D. Using the solutions of Examples II.A-C, olefin polymerization procatalysts were produced by the method of Example I.G. A third method of mixing the precursor solution was also employed. In method 3, the solution of procatalyst precursor was added to the  $\text{TiCl}_4$  digestion solution at 110°C and diisobutyl phthalate was added to the resulting mixture.

E. The procatalysts of Example II.D were converted to catalysts and evaluated in the polymerization of propylene according to the procedure of Example I.H. The results are shown in Table II where "Ratio" indicates the molar B/Mg/Ti ratio and "Procedure" indicates the method used to produce the procatalysts as well as the solvent employed.

TABLE II

Run	Ratio	Procedure	Ti, %	Yield	XS	B.D.
1	Mg(OC <sub>2</sub> H <sub>5</sub> ) <sub>2</sub>	--	2.28	26.6	2.7	0.33
2	0.5/3/1	A, chlorobenzene	3.17	36.7	3.6	0.37
3	0.5/3/1	B, chlorobenzene	2.55	23.5	3.4	0.373
4	1/3/1	A, chlorobenzene	3.04	25.8	4.3	--
5	0.5/3/1	A, chlorobenzene	2.77	27.1	3.8	0.349
6	0.5/3/1	C, chlorobenzene	2.74	25.5	3.6	0.393
7	0.5/3/1	A, isooctane	3.11	32.6	3.3	0.368

Run 5 was repeated except that the SCA was tetramethylpiperidine. The yield was 38.6 kg polymer/g cat and the XS was 7.3%.

Example III (Third Procatalyst Precursor Embodiment)

5 A. Olefin polymerization procatalyst precursors were prepared by contacting Mg(OC<sub>2</sub>H<sub>5</sub>)<sub>2</sub>, Ti(OC<sub>2</sub>H<sub>5</sub>)<sub>4</sub> and o-cresol in varying proportions in various solvents and the resulting mixtures were heated at temperatures from about 50°C to about 110°C. By way of illustration, in a flask  
 10 equipped with a reflux condenser, 116g (0.01 mole) of Mg(OC<sub>2</sub>H<sub>5</sub>)<sub>2</sub>, 81.2g (0.34 mole) of Ti(OC<sub>2</sub>H<sub>5</sub>)<sub>4</sub> and 73g (0.67 mole) of o-cresol were slurried in 276g of isooctane. After stirring for over 1 hour at 85°C, a relatively non-viscous solution resulted which contained 4.5% Mg by weight. The  
 15 molar ratio of cresol/Ti/Mg was 2/3/1. Solutions of similar concentrations were prepared using various molar ratios of reactants. A number of these solutions are described in Table III where the proportions of reactants are indicated and viscosity of the solution is estimated between 1  
 20 (similar to water) and 5 (similar to jelly). The solvents employed are listed where CB is chlorobenzene, iC<sub>8</sub> is isooctane, CH is cyclohexane and DCM is dichloromethane.

TABLE III

o-cresol	Mg(OC <sub>2</sub> H <sub>5</sub> ) <sub>2</sub>	Ti(OC <sub>2</sub> H <sub>5</sub> ) <sub>4</sub>	Solvent	Viscosity
0.5	3	1.75	CB,CH	1
0.5	3	1	CB,CH	5
0.75	3	1	CB	4
1	3	1	CB	2
1	3	1.5	CB,iC <sub>4</sub>	1
2	3	0.5	iC <sub>4</sub>	2
2	3	1	CB	2
2	4	1	iC <sub>4</sub> ,DCM	3
2	4.5	1	CB	5

B. The solutions of Example III.A were used in the production of procatalysts by the general procedure of Example I.G. Methods 1 of mixing and 2 of mixing were the same as in Example I.G. but a third method, method 3', was also used in which the TiCl<sub>4</sub> solution was added dropwise to the mixture of diisobutyl phthalate and the precursor solution.

C. The procatalysts of Example III.B were converted to catalysts by the general procedures of Example 10 I.H. Evaluations of these catalysts by the procedure of Example I.H are shown in Table IV. The "ratio" column indicates the molar proportions of reactants as well as the solvent used.

TABLE IV

Run	Ratio	Method	% Ti	Yield	XS	BD
--	Mg(OC <sub>2</sub> H <sub>5</sub> ) <sub>2</sub>	--	2.28	26.6	2.7	0.33
1	1/3/1.5,CB	3'	1.89	7.4	4.5	0.407
2	1/3/1.5,CB	1	3.43	38.3	5.0	0.335
3	1/3/1.5,iC <sub>4</sub>	1	3.13	26.5	4.1	0.347
4	2/3/1,CB	1	2.66	22.5	4.4	0.358
5	2/4.5/1,CB	2	3.32	20.3	3.9	0.338
6	0.5/3/1,CB	2	2.24	30.8	2.1	0.434
7	1/3/1,CB	2	2.69	30.4	3.4	0.405
8	0.5/3/1.5,CB	1	3.39	41.2	4.4	0.368

Example IV (Fourth Procatalyst Precursor Embodiment)

A. In a 0.23 litre (8 oz) bottle, 2.0g (10.5 mmol) of  $\text{TiCl}_4$ , 3.76g (15.7 mmol) of 95%  $\text{Ti}(\text{OC}_2\text{H}_5)_4$ , 8.12g (71 mmol) of  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  and 94g (8.7 mmol) of o-cresol were slurried in 100g of chlorobenzene and 5.4g of ethanol were added while the mixture was stirred at 440 rpm. The bottle was capped and immersed in an oil bath at 105°C. The  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  quickly dissolved but the solution remained murky. After about 1 hour the cap was removed and the mixture was stirred for 2 more hours and filtered while hot. The solids thus obtained were washed with warm chlorobenzene, with isooctane and dried under flowing  $\text{N}_2$ . The solids, 9.2g, were nearly white, opaque spheroids.

B. In a flask equipped with a polytetrafluoroethylene stir paddle were slurried 39.6g (165 mmol) of 95%  $\text{Ti}(\text{OC}_2\text{H}_5)_4$ , 8.12g (710 mmol) of  $\text{Mg}(\text{OC}_2\text{H}_5)_2$  and 9.4g (86.7 mmol) of o-cresol, 52.5g (1.14 mole) of ethanol and 800g of chlorobenzene. While the mixture was stirred at 300 rpm under a  $\text{N}_2$  blanket, a solution of 18g (95 mmol) of  $\text{TiCl}_4$  in 200g of chlorobenzene was rapidly added. The flask was heated to 60°C-65°C and nearly all solids dissolved after 2 hours. The mixture was then heated to 92°C and a stream of  $\text{N}_2$  was passed over the surface of the flask contents and the evolved ethanol was collected. After stirring overnight, the volume had decreased by about 5% and a musky solution resulted. The slurry was filtered while hot and the recovered solids were washed with chlorobenzene, twice with isooctane and dried under flowing nitrogen. A yield of 110.4g of primarily opaque spheroids in the 15-70 micron size range was obtained. The particles analyzed contained 13.6% by weight Mg and 8.1% by weight Ti.

C. The procatalyst precursors of Example IV.A and B were converted to procatalysts by a procedure substantially similar to that of Example I.G. The procatalyst obtained from the Example IV.A precursor contained 2.4% wt. Ti, 18.7% wt. Mg and 60% wt. Cl. The

- 22 -

procatalyst obtained from the precursor of Example IV.B contained 2.89% wt. Ti, 19.4% wt. Mg and 59.8% wt. Cl.

D. The procatalysts of Examples IV.C were converted to catalysts by mixing with triethylaluminum cocatalyst and diisobutyldimethoxysilane SCA. The quantities of components gave a molar Al/Si/Ti ratio of 70/20/1. The components were mixed prior to injection into a 1-litre autoclave containing propylene and the resulting polymerization using liquid propylene diluent took place at 67°C for 1 hour. Molecular hydrogen (43 mmol) was also added. The results of the polymerizations are shown in Table V which shows the precursor origin of the catalyst. The term "H" indicates that the catalyst was injected into the autoclave with contents heated to 67°C. The term "R" indicates that the catalyst was injected into the autoclave at room temperature and the total contents heated to 67°C over a 15-minute period. In each case, the final polymer was obtained as essentially spheroidal particles.

TABLE V

Precursor,	Injection	Yield	XS	BD
IV.A	H	35.4	3.3	0.390
	R	36.6	3.2	0.447
IV.B	H	33.1	3.5	0.413
	R	50.0	3.2	0.471

20 Example V (Fifth Procatalyst Precursor Embodiment)

A. A solution containing about 1% wt. Mg was prepared by mixing 36g (0.31 mole) of  $Mg(OC_2H_5)_2$ , 25.2g of 95%  $Ti(OC_2H_5)_4$  (0.105 mole) and 22.7g (0.21 mole) of o-cresol in 670g of chlorobenzene in a sealed container and stirred overnight while the container was in a 130°C oil bath. The molar ratio of o-cresol/Mg/Ti was 2/3/1.

In a 0.23 litre (8 oz) bottle, 128.6g of this solution was mixed with 7.3g of  $MgCl_2 \cdot 6C_2H_5OH$  (19.6 mmol) and 86g of chlorobenzene. The bottle and contents were heated in a 95°C oil bath and the contents were stirred for

2 hours at 450 rpm. The oil bath was heated to 105°C and the mixture stirred overnight. The resulting slurry was filtered while warm and the recovered solids were washed with chlorobenzene and isooctane and dried under flowing N<sub>2</sub>.  
5 A yield of 6.8g of solid spheroids was obtained.

B. Employing the procedure of Example V.A. a solution of a molar cresol/Mg/Ti ratio of 1/3/1 was prepared. A 43.55g portion of this solution was mixed with 7.3g (19.6 mmol) of MgCl<sub>2</sub>·6C<sub>2</sub>H<sub>5</sub>OH and 86g of chlorobenzene.  
10 The bottle was capped and placed in a 90°C oil bath as the contents were stirred at 450 rpm. After 2 hours the bottle was uncapped and some foaming was observed as the oil bath temperature was raised to 93°C. After stirring overnight, the resulting slurry was filtered while warm and the  
15 recovered solids washed with chlorobenzene (warm and then cool), twice with isooctane and dried under flowing N<sub>2</sub>. Cream colored, rough spheroids (9.2g) were obtained.

C. The procatalyst precursors of Example V.A. and B were converted to procatalysts by the general procedures  
20 of Example I.G. The procatalyst from Example V.A. contained 2.4% wt. Ti, 18.7% wt. Mg and 60.0% wt. Cl. The procatalyst from Example V.B contained 2.25% wt. Ti, 16.0% wt. Mg and 57.7% wt. Cl.

D. The procatalysts of Example V.C. were  
25 converted to catalysts and employed to polymerize propylene by procedures substantially similar to those of Example IV.D except that the polymerization temperature was 65°C and only the H type of catalyst addition was used. The evaluation of the polymers is shown in Table VI.

TABLE VI

Source of Precursor	Yield	XS	BD
V.A	41.3	3.3	0.348
V.B	38.8	3.2	0.366

30

A similar polymerization using a catalyst produced

2053645

- 24 -

and evaluated by the general methods of Example V.A, C and D but using the R type of catalyst addition gave a yield of 37.8%, an XS value of 3.9% and the polymer had B.D. of 0.407.

**CLAIMS:**

1. A process for preparing a compound useful as a solid olefin polymerization procatalyst precursor which contains moieties of magnesium, titanium, a titanium oxide, and chloride, characterized by contacting at an elevated temperature from 60 to 130°C in a solvent, a magnesium alkoxide, a titanium tetraalkoxide and a phenolic compound, reacting the resulting product with a magnesium halide alcoholate, removing alcohol and recovering the resulted solid precursor, wherein each alkoxide is a C<sub>1-4</sub> alkoxide and the phenolic compound is a phenol or a C<sub>1-5</sub> alkyl, C<sub>1-5</sub> alkoxy-, halo-, or a di(C<sub>1-5</sub> alkyl)amino-substituted phenol.
2. The process of claim 1, wherein the magnesium halide alcoholate is MgCl<sub>2</sub>-6C<sub>2</sub>H<sub>5</sub>OH.
3. The process of claim 2, wherein the magnesium alkoxide is magnesium diethoxide.
4. The process of claim 1 wherein the phenol is o-cresol.
5. The process of claim 1, wherein the solvent is isooctane, cyclohexane, chlorobenzene or dichloromethane.
6. A compound useful as a solid olefin polymerization procatalyst precursor prepared according to the process of any one of claims 1-5.
7. A solid olefin polymerization procatalyst characterized in that it is obtained by contacting the compound of claim 6 with a titanium tetrahalide, an electron donor, and optionally a halohydrocarbon.
8. The procatalyst of claim 7, wherein the titanium tetrahalide is titanium tetrachloride.

9. The procatalyst of claim 7, wherein the electron donor is an alkyl ester of an aromatic monocarboxylic- or dicarboxylic- acid.
10. The procatalyst of claim 8, wherein the electron donor is an alkyl ester of an aromatic monocarboxylic- or dicarboxylic- acid.
11. The procatalyst of claim 7, wherein the halohydrocarbon is present and is chlorobenzene.
12. An olefin polymerization catalyst obtained by contacting a procatalyst as claimed in claim 7 with an organoaluminum compound cocatalyst and a selectivity control agent.
13. The olefin polymerization catalyst of claim 12, wherein the cocatalyst is a trialkylaluminum compound.
14. The olefin polymerization catalyst of claim 12, wherein the selectivity control agent is an organosilane of the formula  $R'_qSi(OR)_{4-q}$ , where  $R'$  is alkyl or aryl of up to 10 carbon atoms,  $R$  is alkyl of up to 4 carbon atoms, and  $q$  is 1 or 2.
15. A process for polymerizing a lower  $\alpha$ -olefin having up to 4 carbons, said process comprising contacting at least one said lower  $\alpha$ -olefin under polymerization conditions with a catalyst as claimed in claim 12.