



US011848377B2

(12) **United States Patent**
Mauder et al.

(10) **Patent No.:** **US 11,848,377 B2**
(45) **Date of Patent:** **Dec. 19, 2023**

(54) **SEMICONDUCTOR COMPONENT WITH
EDGE TERMINATION REGION**

(71) Applicant: **Infineon Technologies AG**, Neubiberg (DE)

(72) Inventors: **Anton Mauder**, Kolbermoor (DE); **Hans-Joachim Schulze**, Taufkirchen (DE); **Matteo Dainese**, Villach (AT); **Elmar Falck**, Hohenbrunn (DE); **Franz-Josef Niedernostheide**, Hagen a. T.W. (DE); **Manfred Pfaffenlehner**, Munich (DE)

(73) Assignee: **Infineon Technologies AG**, Neubiberg (DE)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 258 days.

(21) Appl. No.: **17/307,632**

(22) Filed: **May 4, 2021**

(65) **Prior Publication Data**

US 2021/0257489 A1 Aug. 19, 2021

Related U.S. Application Data

(62) Division of application No. 16/263,244, filed on Jan. 31, 2019, now Pat. No. 11,018,249.

(30) **Foreign Application Priority Data**

Feb. 1, 2018 (DE) 102018102279.4

(51) **Int. Cl.**

H01L 29/78 (2006.01)
H01L 29/06 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 29/7811** (2013.01); **H01L 29/0619** (2013.01); **H01L 29/1095** (2013.01); **H01L 29/402** (2013.01)

(58) **Field of Classification Search**

CPC H01L 29/0619; H01L 29/061; H01L 29/7811; H01L 23/3185; H01L 29/408; H01L 23/318; H01L 29/3171
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,374,389 A 2/1983 Temple
8,264,047 B2 9/2012 Schmidt
(Continued)

FOREIGN PATENT DOCUMENTS

DE 10057612 A1 5/2002
DE 102004037153 A1 3/2006
(Continued)

OTHER PUBLICATIONS

Schmidt, Gerhard et al., "Vertikaler Randabschluss mit drainseitiger Feldplatte", Siemens AG, 2005, pp. 1-7.


Primary Examiner — Alia Sabur

(74) *Attorney, Agent, or Firm* — Murphy, Bilak & Homiller, PLLC

(57) **ABSTRACT**

A semiconductor component includes a semiconductor body having opposing first surface and second surfaces, and a side surface surrounding the semiconductor body. The semiconductor component also includes an active region including a first semiconductor region of a first conductivity type, which is electrically contacted via the first surface, and a second semiconductor region of a second conductivity type, which is electrically contacted via the second surface. The semiconductor component further includes an edge termination region arranged in a lateral direction between the first semiconductor region of the active region and the side surface, and includes a first edge termination structure and a second edge termination structure. The second edge termination structure is arranged in the lateral direction between the first edge termination structure and the side

(Continued)



surface and extends from the first surface in a vertical direction more deeply into the semiconductor body than the first edge termination structure.

9 Claims, 7 Drawing Sheets

(51) **Int. Cl.**

H01L 29/10 (2006.01)
H01L 29/40 (2006.01)

(56)

References Cited

U.S. PATENT DOCUMENTS

9,178,013 B2 11/2015 Schmidt
 9,570,542 B2 2/2017 Breymesser et al.
 2006/0267091 A1 11/2006 Takahashi
 2007/0007592 A1* 1/2007 Barthelmess H01L 29/7395
 257/E29.198
 2007/0222023 A1* 9/2007 Schmidt H01L 29/0619
 257/E29.198

2010/0078775 A1* 4/2010 Mauder H01L 29/1095
 438/495
 2014/0001528 A1* 1/2014 Pfirsch H01L 29/7813
 257/300
 2014/0167143 A1 6/2014 Schmidt
 2014/0167209 A1 6/2014 Meiser et al.
 2014/0197422 A1* 7/2014 Wada H01L 29/0619
 257/77
 2014/0246697 A1 9/2014 Schulze et al.
 2016/0027866 A1 1/2016 Yoshikawa
 2016/0163800 A1* 6/2016 Sakai H01L 29/0657
 257/77
 2016/0336396 A1* 11/2016 Konrath H01L 21/0475
 2017/0271439 A1* 9/2017 Katano H01L 21/26513
 2017/0294526 A1 10/2017 Storasta et al.

FOREIGN PATENT DOCUMENTS

DE 10240107 B4 3/2008
 DE 102007030755 B3 2/2009
 DE 102009031316 A1 3/2010
 DE 102009036930 A1 3/2010
 DE 102015121100 A1 6/2017

* cited by examiner

FIG 1




FIG 2A




FIG 2B




FIG 2C




FIG 3A




FIG 3B




FIG 3C




FIG 3D




FIG 3E




FIG 3F




FIG 4A




FIG 4B




FIG 4C




FIG 4D




FIG 4E




FIG 4F





FIG 5



1

SEMICONDUCTOR COMPONENT WITH EDGE TERMINATION REGION

RELATED APPLICATIONS

The application is a divisional of and claims priority to U.S. Pat. No. 16,263,244 filed on Jan. 31, 2019, the content of which is incorporated by reference herein in its entirety.

TECHNICAL FIELD

The application is devoted to semiconductor components comprising an edge termination region.

BACKGROUND

In semiconductor components having requirements in respect of the voltage blocking strength, the edge termination constitutes a key component part with regard to costs and reliability. On the one hand, the area requirement of the edge termination is intended to be as small as possible in order to allow cost-effective fabrication. On the other hand, the edge termination is intended to be well defined in order that the component does not undergo uncontrolled premature breakdown in the edge region when a reverse voltage is applied. Furthermore, the edge termination is intended to have a stability in stress tests under moisture and with high voltage present and also be robust vis-à-vis external positive as well as negative charges that may deposit—whether owing to production or in the course of operation—for example on a passivation layer applied on the semiconductor surface.

Semiconductor components having an improved edge termination region are thus desirable.

SUMMARY

The present disclosure relates to a semiconductor component comprising a semiconductor body having a first surface, a second surface opposite the first surface, and a side surface surrounding the semiconductor body. The semiconductor component additionally comprises an active region comprising a first semiconductor region of a first conductivity type, which is electrically contacted via the first surface, and a second semiconductor region of a second conductivity type, which is electrically contacted via the second surface. The semiconductor component additionally comprises an edge termination region, which is arranged in a lateral direction between the first semiconductor region of the active region and the side surface and comprises a first edge termination structure and a second edge termination structure, wherein the second edge termination structure is arranged in the lateral direction between the first edge termination structure and the side surface and extends from the first surface in a vertical direction more deeply into the semiconductor body than the first edge termination structure.

The first semiconductor region can be for example a body region of a field effect transistor (FET) or insulated gate bipolar transistor (IGBT) or else an anode or cathode region of a diode or of a thyristor. The second semiconductor region can be for example a drift zone of a FET or of an IGBT or else a cathode or anode region, respectively, of a diode or of a thyristor. The semiconductor component is for example a power semiconductor component suitable for conducting currents of greater than 1 A or else suitable for blocking voltages in the range of a few hundred to a few thousand

2

volts, e.g. 650 V, 1.2 kV, 1.7 kV, 3.3 kV, 4.5 kV, 5.5 kV, 6 kV, 6.5 kV. The reverse voltage can correspond for example to the voltage class of the component as specified in the data sheet.

The subdivision of the edge termination region into a first edge termination structure and into a second edge termination structure, which lies further outward with respect to the first edge termination structure and which additionally extends into the semiconductor body more deeply than the first edge termination structure, enables a technically advantageous edge termination. The first edge termination structure makes it possible to achieve advantages with regard to reliability, e.g. on account of metal field plates not being necessary, which entail the risk of corrosion under the influence of moisture. The second edge termination structure enables advantages with regard to a reduced space requirement. The combination of the first and second edge termination structures additionally makes it possible to reduce the electric field strength in an insulator surrounding the semiconductor body, e.g. a polymer-based insulator such as a silicone potting compound or a molding compound and thus to prevent a failure in reliability tests such as a stress test under moisture, e.g. an HV-H3TRB (High Voltage, High Humidity, High Temperature reverse biased) test. The first edge termination structure is for example different from a body region of a FET or of an IGBT.

In accordance with one embodiment, the second edge termination structure comprises a dielectric, which adjoins the first side surface and extends along the vertical direction from at least one part of the side surface. The dielectric at the side surface serves for electric field reduction in the surrounding insulator and enables a space-saving design of the edge termination region.

In accordance with one embodiment, a thickness of the dielectric at the first surface lies in a range of 100 nm to 10 μ m. The thickness can be dimensioned for example taking account of the voltage differences occurring between first and second surfaces.

In accordance with one embodiment, the dielectric extends at the side surface along the vertical direction from the first surface as far as at least one third of a thickness of the semiconductor body. The extension can be dimensioned for example taking account of the voltage drop between a specific depth of the semiconductor body and the second surface.

The thickness of the semiconductor body, more precisely the electrically active thickness or effective thickness of the semiconductor body, is defined herein by that region of the semiconductor body in the vertical direction in which a space charge zone forms when the nominal reverse voltage is applied. In particular in a direction toward the second surface, a highly doped semiconductor region, e.g. a highly doped substrate, which can primarily serve as a carrier or low-impedance terminal doping and is not assigned to the electrically active thickness of the semiconductor body can extend between an electrical terminal of the semiconductor and the region of the space charge zone.

Alternatively, the extension can for example also be dimensioned taking account of the profile of an electric field strength along the side surface of the semiconductor body over the depth of the semiconductor body.

In accordance with one embodiment, a thickness of the dielectric at the side surface decreases along the vertical direction from the first surface toward the second surface.

The present disclosure additionally relates to a semiconductor component comprising a semiconductor body having a first surface, a second surface opposite the first surface, and

a side surface surrounding the semiconductor body. The semiconductor component additionally comprises an active region comprising a first semiconductor region of a first conductivity type, which is electrically contacted via the first surface, and a second semiconductor region of a second conductivity type, which is electrically contacted via the second surface. The semiconductor component additionally comprises an edge termination region, which is arranged in a lateral direction between the first semiconductor region of the active region and the side surface and comprises a first edge termination structure and a second edge termination structure, the first edge termination structure is arranged in the lateral direction between the second edge termination structure and the side surface and the second edge termination structure extends from the first surface in a vertical direction more deeply into the semiconductor body than the first edge termination structure.

The subdivision of the edge termination region into a first edge termination structure and into a second edge termination structure, which lies further inward with respect to the first edge termination structure and which additionally extends into the semiconductor body more deeply than the first edge termination structure, enables a technically advantageous edge termination which, in view of the first edge termination structure, affords advantages with regard to the reliability, e.g. on account of metal field plates not being necessary, which entail a risk of corrosion under the influence of moisture, and, in view of the second edge termination structure, enables the advantages of a reduced space requirement.

In accordance with one embodiment, the first edge termination structure comprises one or more of the elements field rings, field plates, junction termination extension, JTE, variation of lateral doping, VLD. The JTE or VLD structures extend for example outside a body region formed in the cell zone of a FET or of an IGBT and are more lightly doped than the body region.

In accordance with one embodiment, an extent of the first edge termination structure in the lateral direction lies in a range of 5 μm to 500 μm . In accordance with a further embodiment, the extent of the first edge termination structure for Si components in the lateral direction lies in a range of 50 μm to 300 μm . For SiC-based components, the required extent of the first edge termination structure is significantly smaller and lies e.g. between 5 μm and 80 μm . In accordance with a further embodiment, the extent of the first edge termination structure in the lateral direction lies in a range of at least 50% of the thickness of the semiconductor body. The exact value of the lateral extent of the first edge termination structure can be defined for example taking account of the desired blocking capability of the component.

In accordance with one embodiment, the first edge termination structure is a JTE structure or a VLD structure and comprises a third semiconductor region, wherein a dopant dose of the third semiconductor region along at least 10%, at least 20% or at least 30% of its lateral extent is smaller than a breakdown charge in the semiconductor body divided by the elementary charge. In this case, the lateral extent extends for example perpendicular to an edge of the semiconductor body. The breakdown charge in a semiconductor body formed with silicon is approximately 1.3×10^{12} e/cm², wherein e corresponds to the elementary charge. The value of the breakdown charge is higher approximately by a factor of 10 in the case of SiC.

In accordance with one embodiment, the first edge termination structure is a JTE structure or a VLD structure and comprises a third semiconductor region, wherein a dopant

dose of the third semiconductor region along at least 80% of its extent in the lateral direction is less than a dopant dose of the first semiconductor region. In this case, the lateral direction extends for example perpendicular to an edge of the semiconductor body. Consequently, the dopant dose of the third semiconductor region for example along at least 80% of its extent in the lateral direction is less than the dopant dose of the body region of a FET or of an IGBT or else less than the dopant dose of an anode region of a diode. The lower dopant dose of the third semiconductor region in comparison with the first semiconductor region has an advantageous effect for example with regard to the electric field reduction in the edge termination region.

In accordance with one embodiment, the second edge termination structure extends into the semiconductor body from the first surface to at least double the depth, at least five times the depth or at least ten times the depth, of the first edge termination structure. This enables the technical advantage of a reduced space requirement for the edge termination structure in comparison with a planar edge termination based exclusively on the first edge termination structure, e.g. a JTE structure or a VLD structure.

In accordance with one embodiment, the second edge termination structure comprises a fourth semiconductor region of the first conductivity type, which extends into the semiconductor body from the first surface more deeply than the first semiconductor region in the active region. The fourth semiconductor region can be produced for example with a multiplicity of dopant implantations of differing energy, wherein the profiles of the individual implantations overlap in the vertical direction after the implantation as a result of the thermal budget and thus form the fourth semiconductor region that is deeper than the first semiconductor region in the active region. Particularly in the case of SiC-based semiconductor components, the dopants used diffuse only very little, such that in this case the projected ranges of the individual ion implantations are so close together that a continuous doping profile results. Moreover, the fourth semiconductor region can be produced by means of a masked implantation into different planes of an epitaxy deposition interrupted once or a number of times. Alternatively or supplementary, the fourth semiconductor region can be produced by means of a trench, e.g. a gate trench or—in the case of trench-based compensation components—a compensation trench, into which the dopants are implanted for example into the bottom of the trench and are outdiffused toward the front side and toward the rear side after the epitaxial filling of the trench. Alternatively or supplementary, the dopants of the fourth semiconductor region can also be set by means of a deep diffusion of implanted dopants to give the desired dopant profile. The implantations mentioned above can optionally be carried out with the aid of the so-called channeling effect in order to maximize the penetration depth resulting after the implantation for a specific implantation energy and thus to optimize the depth distribution of these dopants. Acceptor atoms or donor atoms are appropriate as dopants, depending on the conductivity type of the fourth semiconductor region. Exemplary acceptor atoms for a semiconductor body formed with silicon are e.g. boron, gallium or aluminum atoms. The comparatively deep formation of the fourth semiconductor region enables the technical advantage of an improved blocking capability of the semiconductor component. This is attributable inter alia to the fact that the maximum of the electric field strength is far below the surface of the semi-

conductor body, with the result that surface charges on said surface do not influence the breakdown voltage or influence it only slightly.

In accordance with a further embodiment, a plurality of the fourth semiconductor regions are arranged along the lateral direction at a distance from one another. This makes it possible to achieve a gradual field reduction toward the outside. By way of example, a further structure serving for field reduction, such as a JTE structure, for instance, can be arranged between two fourth semiconductor regions that are adjacent in a lateral direction.

In accordance with one embodiment, the fourth semiconductor region extends into the semiconductor body in the vertical direction from the first surface to a depth of 5 μm to 50 μm or else 8 μm to 30 μm . In accordance with a further embodiment, the fourth semiconductor region extends in the vertical direction from the first surface down to a depth of at least 10% of the thickness of the semiconductor body. As a result, the maximum of the electric field strength during off-state operation of the semiconductor component can be positioned into the depth of the semiconductor body. This has an advantageous effect on the voltage blocking strength of the semiconductor component, as explained above.

In accordance with one embodiment, a dimension of the fourth semiconductor region in the lateral direction at the first surface lies in a range of 30 μm to 150 μm . In accordance with a further embodiment, the dimension of the fourth semiconductor region in the lateral direction at the first surface lies in a range of at least 50% of the effective thickness of the semiconductor body. The fourth semiconductor region can enclose the active region at the first surface for example in an uninterrupted manner or else surround it in the form of a juxtaposition of laterally spaced segments.

In accordance with one embodiment, a dopant dose of the fourth semiconductor region lies in a range of 30% to 150%, or else in a range of 50% to 100%, of a breakdown charge in the semiconductor body. The breakdown charge in a semiconductor body formed with silicon is approximately $1.3 \times 10^{12} \text{ e/cm}^2$, wherein e corresponds to the elementary charge. The dopant dose corresponds to the integral of the dopant concentration of the fourth semiconductor region along the vertical extension thereof. The vertical extension of the fourth semiconductor region proceeds for example from the first surface of the semiconductor body and ends in the semiconductor body at the deepest point of the fourth semiconductor region relative to the first surface. The fourth semiconductor region can for example also extend into the semiconductor body from below the first surface.

In accordance with one embodiment, a maximum of a dopant concentration in the fourth semiconductor region along the vertical direction lies in a range of 30% to 70% or else of 45% to 55% of a penetration depth of the fourth semiconductor region into the semiconductor body. The maximum can be established for example by setting the implantation energy in the case of a single implantation or else coordinating implantation energies and doses in the case of a plurality of implantations.

In accordance with a further embodiment, a maximum of a dopant concentration in the fourth semiconductor region in the vertical direction lies in a range of 0% to 10% of a penetration depth of the fourth semiconductor region into the semiconductor body. The maximum can be established for example by setting the implantation energy in the case of a single implantation or else coordinating implantation energies and doses in the case of a plurality of implantations.

In accordance with one embodiment, the semiconductor component is a vertical power semiconductor component suitable for conducting a load current of more than 1 A between a first load terminal at the first surface and a second load terminal at the second surface.

In accordance with one embodiment, the semiconductor component is a vertical power semiconductor component suitable for blocking a voltage of more than 500 V between a first load terminal at the first surface and a second load terminal at the second surface. The semiconductor component is configured for example as a power semiconductor diode or as a power semiconductor FET, or as a thyristor (e.g. SCR, silicon controlled rectifier) or else a power semiconductor IGBT. The voltage blocking strength specified in the data sheet of the semiconductor component can be for example 650 V, 1.2 kV, 1.7 kV, 3.3 kV, 4.5 kV, 5.5 kV, 6 kV, 6.5 kV.

BRIEF DESCRIPTION OF THE FIGURES

The accompanying drawings serve to afford an understanding of exemplary embodiments of the invention, are included in the disclosure and form part thereof. The drawings merely illustrate exemplary embodiments and serve together with the description to elucidate same. Further exemplary embodiments and numerous advantages from among those intended are directly evident from the following detailed description. The elements and structures shown in the drawings are not necessarily illustrated in a manner true to scale with respect to one another. Identical reference signs refer to identical or mutually corresponding elements and structures.

FIG. 1 is a schematic cross-sectional view of a semiconductor body of a semiconductor component comprising an active region and an edge termination region, wherein a first edge termination structure and a comparatively deeper second edge termination structure are formed in the edge termination region.

FIG. 2A is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a first edge termination structure formed as a JTE structure.

FIG. 2B is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a first edge termination structure formed as a VLD structure.

FIG. 2C is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a first edge termination structure formed with field rings or floating potential rings.

FIG. 3A is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a second edge termination structure formed as a deep semiconductor region.

FIG. 3B is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a second edge termination structure having laterally overlapping deep semiconductor regions.

FIG. 3C is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a second edge termination structure having laterally spaced deep semiconductor regions.

FIG. 3D is a schematic cross-sectional view of the semiconductor body from FIG. 1 with a second edge termination structure comprising a dielectric formed at a side surface of the semiconductor body.

FIG. 3E is a schematic cross-sectional view of the semiconductor body from FIG. 3D in which the dielectric at the side surface has a thickness that decreases with increasing distance from the first surface.

FIG. 3F is a schematic cross-sectional view of the semiconductor body from FIG. 3D with a semiconductor region which is depletable of free charge carriers and which adjoins the dielectric at the side surface of the semiconductor body.

FIGS. 4A to 4F are schematic cross-sectional views of a semiconductor wafer for elucidating a method for producing a semiconductor component as shown in FIG. 3D, for example, with a dielectric at the side surface.

FIG. 5 is a schematic cross-sectional view of a semiconductor body of a semiconductor component comprising an active region and an edge termination region comprising a first edge termination structure and a comparatively deeper second edge termination structure, which are arranged in an interchanged manner in comparison with the view from FIG. 1.

DETAILED DESCRIPTION

In the following detailed description, reference is made to the accompanying drawings, which form part of the disclosure and show specific exemplary embodiments for illustration purposes. In this context, a direction terminology such as “upper side”, “bottom”, “front side”, “rear side”, “at the front”, “at the back”, etc. is related to the orientation of the figures currently being described. Since the component parts of the exemplary embodiments can be positioned in different orientations, the direction terminology serves only for elucidation and should in no way be interpreted as limiting.

It goes without saying that further exemplary embodiments exist and structural or logical changes can be made to the exemplary embodiments, without departing in the process from what is defined by the patent claims. The description of the exemplary embodiments is non-limiting in this respect. In particular, elements from exemplary embodiments described below can be combined with elements from other exemplary embodiments from among those described, unless something different is evident from the context.

The terms “have”, “contain”, “encompass”, “comprise” and the like hereinafter are open terms which on the one hand indicate the presence of the stated elements or features, and on the other hand do not exclude the presence of further elements or features. The indefinite articles and the definite articles encompass both the plural and the singular, unless something different is unambiguously evident from the context.

The terms “have”, “contain”, “encompass”, “comprise” and similar terms are open terms, and the terms indicate the presence of the stated structures, elements or features, but do not exclude additional elements or features. The indefinite articles and the definite articles are intended to encompass both the plural and the singular, unless something different is clearly evident from the context.

The term “electrically connected” describes a permanent low-impedance connection between electrically connected elements, for example a direct contact between the relevant elements or a low-impedance connection via a metal and/or a highly doped semiconductor. The term “electrically coupled” encompasses the fact that one or more intervening elements suitable for signal transmission can be present between the electrically coupled elements, for example elements which are controllable in order to provide at times a low-impedance connection in a first state and a high-impedance electrical decoupling in a second state.

The semiconductor regions can be of a first or of a second conductivity type. In this case, the first (second) conductivity type can be a p-type (n-type) or the first (second) conductivity type can be an n-type (p-type).

FIG. 1 illustrates a semiconductor component 100 in a schematic cross-sectional view.

The semiconductor component 100 comprises a semiconductor body 101 having a first surface 102, a second surface 104 opposite the first surface 102, and a side surface 106 surrounding the semiconductor body 101. The semiconductor component 100 additionally comprises an active region AB comprising a first semiconductor region 108 of a first conductivity type, e.g. p-type, which is electrically contacted via the first surface 102, cf. e.g. the first contact K1 illustrated schematically in FIG. 1, which first contact can consist of one or a multiplicity of conductive materials formed in a wiring region formed above the first surface 102. The semiconductor component 100 additionally comprises a second semiconductor region 110 of a second conductivity type, e.g. n-type, which is electrically coupled to the second surface, cf. e.g. the second contact K2 illustrated schematically in FIG. 1, which second contact can consist of one or a multiplicity of conductive materials formed in a wiring region formed above the first surface. The first semiconductor region can be for example a body region of a field effect transistor (FET) or insulated gate bipolar transistor (IGBT) or else an anode or cathode region of a diode or a thyristor. The second semiconductor region can be for example a drift zone of a FET or of an IGBT or else a cathode or anode region, respectively, of a diode.

The semiconductor body 101 can be based on various semiconductor materials, such as, for instance, silicon, silicon-on-insulator (SOI), silicon-on-sapphire (SOS), silicon-germanium, germanium, gallium arsenide, silicon carbide, gallium nitride, or else further compound semiconductor materials. The semiconductor body can be based on a semiconductor substrate such as a semiconductor wafer, for instance, and comprise one or more epitaxial layers deposited thereon or else be thinned back.

Besides the semiconductor regions illustrated, a multiplicity of further semiconductor regions can be formed in the semiconductor body 101 depending on the type of semiconductor component 100, e.g. source regions, drain regions, field stop zones, highly doped contact terminal regions, etc. Regions of this type are not illustrated in the simplified cross-sectional view in FIG. 1, which is not restricted to a semiconductor component of a specific type.

The semiconductor component 100 additionally comprises an edge termination region RB, which is arranged in a lateral direction x between the first semiconductor region 108 of the active region AB and the side surface 106 and comprises a first edge termination structure 112 in a first region 113 illustrated in a dashed manner, and also a second edge termination structure 114 in a dash-dotted region 115, wherein the second edge termination structure 114 is arranged in the lateral direction x between the first edge termination structure 112 and the side surface 106 and extends into the semiconductor body 101 from the first surface 102 in a vertical direction z more deeply than the first edge termination structure 112. The extension depths of the first and second edge termination structures are identified by t1 and t2 in a simplified manner in FIG. 1, such that the relation $t_2 > t_1$ holds true. In the schematic cross-sectional view in FIG. 1, by way of example, the extension depth t1 of the first edge termination structure 112 is illustrated as less than an extension depth t3 of the first semiconductor region 108. It goes without saying that the extension depth t3 of the first semiconductor region 108 can also be greater than the extension depth t1 of the first edge termination structure 112.

In accordance with one embodiment, an extent **11** of the first edge termination structure **112** in the lateral direction x lies in a range of $5\ \mu\text{m}$ to $500\ \mu\text{m}$. In accordance with a further embodiment, the extent **11** of the first edge termination structure **112** in the lateral direction x lies in a range of $50\ \mu\text{m}$ to $300\ \mu\text{m}$.

In accordance with a further embodiment, the extent **11** of the first edge termination structure in the lateral direction x lies in a range of at least 50% of an electrically active thickness or effective thickness of the semiconductor body **dd**.

The exact value of the lateral extent of the first edge termination structure can be defined for example taking account of the desired blocking capability of the component **100**.

The first edge termination structure **112** can be constructed from one or a plurality of edge termination elements.

The schematic cross-sectional view in FIG. 2A illustrates the first edge termination structure **112** for example as a JTE structure. An exemplary dopant concentration profile along the line AA', i.e. along the lateral direction x through the first semiconductor region **108** and through a third semiconductor region **1121** of the first edge termination structure **112**, is shown in the right-hand part of FIG. 2A. In this case, the dopant concentration decreases from the level in the first semiconductor region **108** to the comparatively lower dopant concentration in the third semiconductor region **1121** of the JTE structure.

The schematic cross-sectional view in FIG. 2B illustrates the first edge termination structure **112** for example as a VLD structure. An exemplary dopant concentration profile along the line AA', i.e. along the lateral direction x through the first semiconductor region **108** and through a third semiconductor region **1122** of the first edge termination structure **112**, is shown in the right-hand part of FIG. 2B. In this case, the dopant concentration decreases from the level in the first semiconductor region **108** to the comparatively lower dopant concentration of the third semiconductor region **1122** of the VLD structure. Within the VLD structure, the dopant concentration decreases along the lateral direction in the third semiconductor region **1122** toward the outside, i.e. in the direction toward the side surface **106**. Alternatively, an outwardly decreasing dopant dose within the VLD structure can also be achieved for example by virtue of the extension depth of the VLD structure decreasing toward the outside.

In accordance with one exemplary embodiment, a dopant dose of the third semiconductor region **1121**, **1122** along at least 30% of its extent in the lateral direction x is set such that it is less than a breakdown charge in the semiconductor body **101** divided by the elementary charge e .

In accordance with one exemplary embodiment, a dopant dose of the third semiconductor region along at least 80% of its extent in the lateral direction x is less than a dopant dose of the first semiconductor region **108**. The lower dopant dose of the third semiconductor region **1121**, **1122** in comparison with the first semiconductor region **108** has an advantageous effect for example with regard to the electric field reduction in the edge termination region **RB**.

The schematic cross-sectional view in FIG. 2C illustrates the first edge termination structure **112** for example as a structure **1123** having field rings or floating potential rings.

The schematic cross-sectional view in FIG. 3A illustrates the second edge termination structure **114** for example as a fourth semiconductor region **118**.

In accordance with one exemplary embodiment, the fourth semiconductor region **118** of the second edge termination structure **114** extends into the semiconductor body **101** from the first surface **102** at least to double the depth of the first edge termination structure **112**, i.e. $t_2 > 2 \times t_1$. Moreover, the fourth semiconductor region **118** can extend into the semiconductor body **110** from the first surface **102** more deeply than the first semiconductor region **108** in the active region **AB**.

The extension depth t_2 of the fourth semiconductor region into the semiconductor body **101** from the first surface **102** is for example $5\ \mu\text{m}$ to $50\ \mu\text{m}$ or else $8\ \mu\text{m}$ to $30\ \mu\text{m}$. In the case of SiC-based components, the extension depth t_2 is typically between $2\ \mu\text{m}$ and $20\ \mu\text{m}$ or between $3\ \mu\text{m}$ and $10\ \mu\text{m}$. In accordance with a further embodiment, the extension depth t_2 of the fourth semiconductor region into the semiconductor body **101** from the first surface **102** is at least 10% of the effective thickness of the semiconductor body **dd**. This makes it possible to keep the maximum of the electric field strength during off-state operation of the semiconductor component away from the first surface **102** and deep in the semiconductor body **101**. This has an advantageous effect on the voltage blocking strength of the semiconductor component, as explained above.

As is illustrated in the schematic cross-sectional views in FIGS. 3B and 3C, a plurality of the fourth semiconductor regions **118** can be arranged in a laterally overlapping manner (cf. FIG. 3B) or else in a laterally spaced manner (cf. FIG. 3C). In the case of the lateral spacing shown in FIG. 3C, further edge termination elements, e.g. VLD or JTE structures, can be arranged between adjacent fourth semiconductor regions.

A dimension **12** of the fourth semiconductor region **118** in the lateral direction x at the first surface lies for example in a range of $30\ \mu\text{m}$ to $150\ \mu\text{m}$. In accordance with a further embodiment, the dimension **12** of the fourth semiconductor region **118** in the lateral direction x at the first surface lies for example in a range of at least 50% of the effective thickness of the semiconductor body **dd**.

A dopant dose of the fourth semiconductor region **118** lies for example in a range of 30% to 150% of a breakdown charge in the semiconductor body divided by the elementary charge e .

As described further above, the fourth semiconductor region **118** can be produced in diverse ways. This makes it possible to place a dopant maximum of this region along the vertical direction z at different positions in order thus to optimize the electric field profile during off-state operation within the edge termination region **RB**. By way of example, a maximum of a dopant concentration in the fourth semiconductor region **118** along the vertical direction z lies in a first range **B1** of 45% to 55% of a penetration depth of the fourth semiconductor region **118** into the semiconductor body **101** (cf. FIG. 3A). In accordance with a further configuration, the maximum of a dopant concentration in the fourth semiconductor region in the vertical direction lies in a second range **B2** of 0% to 10% of a penetration depth of the fourth semiconductor region **118** into the semiconductor body **101**.

In the schematic cross-sectional view in FIG. 3D, the second edge termination structure **114** is formed for example as a dielectric **120**, which adjoins the first side surface **106** and extends along the vertical direction z of at least one part of the side surface **106**. The dielectric **120** is for example a dielectric of high quality such as, for instance, a dielectric composed of inorganic materials such as SiO_2 , Si_3N_4 or similar materials. A further dielectric **121** can be formed on

11

the first surface **102**, too, which further dielectric can correspond to or else deviate from the dielectric **120** at the side surface **106** with regard to the material composition. This makes it possible to achieve the technical advantage of a better tolerance vis-à-vis an electric field line concentration at the corner E. By way of example, a thickness d of the dielectric **120** at the first surface **102** lies in a range of 100 nm to 10 μ m. The further dielectric **121** at the first surface **102** can be fabricated for example by processes that are used elsewhere to produce a dielectric in the course of the method for producing the semiconductor component **100**, e.g. a LOCOS (Local oxidation of silicon) process for defining a cell region in the active region AB.

Although the dielectric **120** adjoining the side surface **106** can extend from the first surface **102** as far as the second surface, an extension that ends above the second surface **104**, as shown in FIG. 3D, for instance, is likewise suitable for improving the blocking strength of the component. Since the highest potential difference with respect to the second surface **104**, which can be applied on a leadframe, occurs near the first surface **102**, the dielectric **120** should be made sufficiently thick and with sufficient quality in the upper and uppermost region.

By way of example, the dielectric **120** extends at the side surface **106** along the vertical direction z from the first surface **102** as far as at least one third of a thickness d_0 of the semiconductor body **101**. If the vertical extension of the dielectric is designated by t_3 , then $d_0/3 \leq t_3 \leq d_0$ holds true, for example. By way of example, the vertical extension of the dielectric **120** proceeding from the first surface **102** can be dimensioned such that the dielectric **120** covers a depth range at the side surface **106** in which electric field strengths in the insulator surrounding the dielectric **120** above a threshold value, e.g. 100 kV/cm, can occur. Moreover, the dielectric **120** can extend at the side surface **106** as far as a depth of the semiconductor body **101** at which a functional semiconductor layer, e.g. a field stop layer, is formed in the semiconductor body **101**.

The schematic cross-sectional view in FIG. 3D illustrates the dielectric **120** at the side surface **106** for example with a constant thickness. As is illustrated in the schematic cross-sectional view in FIG. 3E, a thickness d_l of the dielectric **120** at the side surface **106** can also decrease along the vertical direction z from the first surface **102** toward the second surface, since the potential differences during off-state operation of the component decrease from the first surface **102** toward the second surface **104** and the requirements made of the dielectric strength of the dielectric **120** thus likewise decrease with increasing distance from the first surface **102**. By way of example, the thickness d_l decreases in a stepped fashion, cf. outer edge **1201** in FIG. 3E, or else linearly, cf. outer edge **1202** in FIG. 3E. It goes without saying that a thickness profile of the dielectric **120** at the side surface **106** which decreases toward the second surface **104** can also deviate from the profiles shown by way of example.

In the schematic cross-sectional view in FIG. 3F, the semiconductor component **100** comprises a fifth semiconductor region **122** of the first conductivity type, which adjoins the dielectric **120** at the side surface **106**. The fifth semiconductor region **122** can be configured for example such that it partly or completely covers the dielectric **120** at the side surface **106**. By way of example, the fifth semiconductor region **122** is configured with regard to the dimensions and dopant concentration such that it is depletable of free charge carriers during off-state operation of the semiconductor component **100**. The formation of the fifth semiconductor region **122** makes it possible to reduce the influ-

12

ence of fixed charges in the dielectric on the blocking ability of the semiconductor component **100** and thus contributes to an improvement in reliability.

A method for producing a semiconductor component **100** comprising a dielectric **120** as shown by way of example in FIG. 3D is elucidated in the schematic cross-sectional views in FIGS. 4A to 4F.

Referring to the cross-sectional view in FIG. 4A, a semiconductor wafer **1011** with a mask layer **124**, e.g. a hard or resist mask, on the first surface **102** is provided.

Referring to the cross-sectional view in FIG. 4B, a trench **126** is formed from the first surface **102** in the semiconductor wafer **1011**, e.g. by means of an etching process such as a dry etching process with prior photolithographic patterning of the mask layer **124**. The trench **126** lies for example between a kerf region SB and the edge termination region RB.

Referring to the cross-sectional views in FIGS. 4C, 4D, the trench is lined with a first dielectric **128** and a second dielectric **130**. It is possible to dispense with forming the first dielectric **128** and/or the second dielectric **130** provided that filling the trench with a dielectric satisfies requirements in respect of quality and reliability which are made of the dielectric **120** in FIG. 3D. By way of example, the first dielectric **128** is formed as a thermal oxide in order to achieve an interface of high quality toward the semiconductor body **101**. The second dielectric can be a nitride, for example.

Referring to the cross-sectional view in FIG. 4E, the trench is filled with a third dielectric **132**, e.g. an oxide such as SiO₂, BPSG (borophosphosilicate glass), PSG (phosphosilicate glass) or some other dielectric such as, for instance, a nitride, a low-k or high-k dielectric. The dielectrics can be produced by suitable production methods such as, for instance, chemical vapor deposition (CVD), plasma-enhanced CVD (PECVD) or else low-pressure CVD (LPCVD).

Referring to the cross-sectional view in FIG. 4F, the dielectrics **128**, **130**, **132** are removed again on the first surface **102**, e.g. by means of an etching and/or polishing process such as chemical mechanical polishing (CMP).

Dividing the semiconductor wafer **1011** in the kerf region SB by means of a suitable separating process such as e.g. sawing or laser cutting can then follow in such a way that the wafer **1011** is divided such that the cut edge in the kerf region extends as far as or into the dielectrics **128**, **130**, **132**, such that after dividing the side surfaces of the semiconductor bodies are at least partly covered with a dielectric, and a structure as shown for example in FIG. 3D results.

The schematic cross-sectional view in FIG. 5 shows a semiconductor body of a semiconductor component **100** in which the arrangement of the first edge termination structure **112** and of the comparatively deeper second edge termination structure **114** is opposite to the arrangement of the embodiment from FIG. 1. A space-saving and advantageous edge termination region can be fashioned with this arrangement, too. The indications given in association with FIGS. 1 to 3C can be applied to the semiconductor component in FIG. 5.

Although specific embodiments have been illustrated and described herein, those skilled in the art will recognize that the specific embodiments shown and described can be replaced by a multiplicity of alternative and/or equivalent configurations, without departing from the scope of protection of the invention. The application is intended to cover any adaptations or variations of the specific embodiments

13

discussed herein. Therefore, the invention is restricted only by the claims and the equivalents thereof.

The invention claimed is:

1. A semiconductor component, comprising:
a semiconductor body having a first surface, a second surface opposite the first surface, and a side surface surrounding the semiconductor body;

an active region comprising a first semiconductor region of a first conductivity type, which is electrically contacted via the first surface, and a second semiconductor region of a second conductivity type, which is electrically contacted via the second surface;

an edge termination region arranged in a lateral direction between the first semiconductor region of the active region and the side surface, and comprising a first edge termination structure and a second edge termination structure,

wherein the second edge termination structure is arranged laterally adjacent to the first edge termination structure and extends from the first surface in a vertical direction more deeply into the semiconductor body than the first edge termination structure,

wherein the second edge termination structure comprises a dielectric adjoining the first side surface and extending along the vertical direction from at least one part of the side surface,

wherein a thickness of the dielectric at the side surface decreases along the vertical direction from the first surface toward the second surface.

2. The semiconductor component of claim 1, further comprising a fifth semiconductor region of the first conductivity type adjoining the dielectric at the side surface.

3. The semiconductor component of claim 1, wherein the first edge termination structure comprises one or more of

14

field rings, field plates, junction termination extension (JTE), and/or variation of lateral doping (VLD).

4. The semiconductor component of claim 1, wherein an extent of the first edge termination structure in the lateral direction lies in a range of at least 50% of an electrically active thickness of the semiconductor body.

5. The semiconductor component of claim 1, wherein the first edge termination structure is a JTE structure or a VLD structure and comprises a third semiconductor region of the first conductivity type, and wherein a dopant dose of the third semiconductor region along at least 10% of its extent in the lateral direction is less than a breakdown charge in the semiconductor body.

6. The semiconductor component of claim 1, wherein the first edge termination structure is a JTE structure or a VLD structure and comprises a third semiconductor region, and wherein a dopant dose of the third semiconductor region along at least 80% of its extent in the lateral direction is less than a dopant dose of the first semiconductor region.

7. The semiconductor component of claim 1, wherein a plurality of the fourth regions is arranged along the lateral direction at a distance from one another or in a manner overlapping one another.

8. The semiconductor component of claim 1, wherein the semiconductor component is a vertical power semiconductor component configured to conduct a load current of more than 1 A between a first load terminal at the first surface and a second load terminal at the second surface.

9. The semiconductor component of claim 1, wherein the semiconductor component is a vertical power semiconductor component suitable for blocking a voltage of more than 500 V between a first load terminal at the first surface and a second load terminal at the second surface.

* * * * *