

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 1 196 299 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**27.10.2004 Bulletin 2004/44**

(51) Int Cl.7: **B60C 19/00, G01M 1/32**

(21) Application number: **00938582.4**

(86) International application number:  
**PCT/DK2000/000331**

(22) Date of filing: **21.06.2000**

(87) International publication number:  
**WO 2001/000430 (04.01.2001 Gazette 2001/01)**

**(54) TYRE BALANCING COMPOSITIONS**

**AUSWUCHTMASSEN FÜR FAHRZEUGREIFEN**

**COMPOSITIONS D'EQUILIBRAGE POUR PNEUS**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**

(72) Inventor: **RONLAN, Alvin**  
**Hillsboro Shores, FL 33062 (US)**

(30) Priority: **24.06.1999 EP 99112199**

(74) Representative: **Andersen, Henrik Rastrup**  
**Plougmann & Vingtoft A/S,**  
**Sundkrogsgade 9**  
**P.O. Box 831**  
**2100 Copenhagen O (DK)**

(43) Date of publication of application:  
**17.04.2002 Bulletin 2002/16**

(73) Proprietor: **Carnehammar, Lars Bertil**  
**London SW6 6AE (GB)**

(56) References cited:  
**GB-A- 1 209 696**                      **GB-A- 2 074 955**  
**US-A- 5 073 217**                      **US-A- 5 083 596**  
**US-A- 5 431 726**

**EP 1 196 299 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

### FIELD OF THE INVENTION

**[0001]** The present invention relates to tyre balancing compositions for use in eliminating/reducing vibrations in motor vehicle wheel assemblies related to tyre and rim imperfections, as well as to the use of such compositions.

### BACKGROUND OF THE INVENTION.

**[0002]** Vibrations in rolling wheel assemblies (tyre + rim) are caused by several, different types of tyre imperfections, the most important being:

- Non-homogeneous mass distribution
- Stiffness variations
- Geometric variations
- Radial and lateral run outs
- Eccentricity

**[0003]** Similarly, imperfections in the rim will also induce vibrations.

**[0004]** The at present most common method for elimination of wheel assembly derived vibrations is still the attachment of lead weights to the tyre rim. However, quite apart from giving rise to a diffuse lead pollution in the environment through the weights falling off, this method can only compensate (and even at best only partially) for vibrations caused by non-homogeneous mass distribution in the wheel assembly, and since the other imperfections mentioned above are just as important sources of vibrations, lead weight balancing is not a satisfactory method for balancing of modern quality tyres.

**[0005]** European Patent No. 0557365 which discloses a tyre balancing composition according to the preamble of claim 1 describes a different approach to reduction of vibrations induced by wheel assembly imperfections, comprising introduction of a visco-plastic gel into the tyre cavity. The principle behind the action of such gels is that they are able to flow under the stresses induced by vibrations and therefore spontaneously distribute themselves in a rolling tyre in such a way that the vibrations are reduced irrespective of what type of imperfections they are induced by. The efficiency of these balancing gels as compared to lead weight balancing can be demonstrated experimentally by measuring vertical accelerations on the spring leg of a front axle with its wheels running under load against a rotating drum. Typical results have shown that lead weight balancing actually increases vertical accelerations which clearly demonstrates that other sources of vibrations than non-homogeneous mass distribution are more important in this case. However, such balancing gels cannot completely eliminate vibrations caused by wheel assembly imperfections, because the centrifugal stress induced in

a balancing gel by localised thickening (which occurs to diminish vibrations) will eventually be as strong as the residual vibrational forces caused by the imperfections, and therefore an equilibrium is established where a certain level of vertical accelerations will remain.

**[0006]** Also, a drawback with gel compositions in general is that a fairly large amount of gel must be employed per tyre since a gel is not able to form localized "lumps" in the manner of a lead weight but must instead form a film layer with a continuously and gradually changing depth in order to provide the required balancing.

### SUMMARY OF THE INVENTION.

**[0007]** The object of the present invention is to eliminate or substantially reduce the above mentioned remaining level of vertical accelerations as well as provide a significant reduction of the amount of composition needed per tyre. It has now been found that by incorporating or imbedding into the gel layer a certain amount of solid masses or bodies of a certain size, said size being at least sufficiently large to enable the bodies to move through the gel layer under the influence of acceleration forces induced by imbalances, but not so large so as to themselves begin to induce vibrations, greatly enhances and expands the ability of the composition to reduce vibration and to balance wheel assemblies.

**[0008]** The invention therefore concerns a tyre balancing composition according to claim 1 which comprises on the one hand a visco-plastic gel and on the other hand solid bodies having an average smallest dimension in the range of 0.5-5 mm.

**[0009]** In the present context, the term "solid" as applied to the bodies is intended to mean particles having a continuous and fairly smooth surface, but not necessarily having no voids or cavities. Thus, a solid body within the meaning of the present invention may be hollow or have internal porosities, although a truly solid body, i.e. one having a continuous material phase all through and no cavities or porosities, is preferred.

**[0010]** The invention also relates to a tyre balancing composition kit according to claim 9, a balancing composition according to the invention contained in a wheel assembly, as well as a method for balancing motor vehicle wheel assemblies according to claim 12.

**[0011]** The gels in which the solid bodies are present or imbedded to form the compositions of the invention will in the following be known as DFC (Dynamic Force Compensation) gels.

### DETAILED DESCRIPTION OF THE INVENTION

**[0012]** The solid bodies imbedded in the gels to act as moving masses may be any type of solid bodies of the specified dimensions which are able to be dispersed discretely in a visco-plastic gel. In a preferred embodiment, the bodies have an average ratio  $\alpha$  between their smallest and their largest dimension of  $\alpha \leq 2$  since par-

ticles with larger such aspect ratios tend only to move with ease in the longitudinal direction,  $\alpha$  preferably being  $\leq 1.5$ , in particular around 1.

[0013] Due to the increasing importance with decreasing particle size of molecular interactions (hydrogen bonding, van der Waals forces, electrostatic interactions, etc.) between the solid masses and the visco-plastic gel in relation to the vibrational and centrifugal forces acting on the masses, masses with an average diameter below 0.1 mm do not seem to contribute to the balancing efficiency of the gel-particle composition. Consequently, the smallest dimension of the bodies is, as stated above, in the range 0.5-5 mm. In a preferred embodiment, the average smallest dimension of the bodies is in the range of 1-4 mm, in particular around 3 mm.

[0014] Suitable visco-plastic gels that will enable imbedded masses move in order to compensate vibrational forces to a smaller or larger degree can be defined in rheological (as measured with a Stress Tech Rheometer from Rheologica AB, Lund, Sweden) by the following characteristics:

Storage Modulus $^3$  (G'): Between 1000 Pa and 25000 Pa at 22°C

Loss Modulus $^3$  (G''): Smaller than the Storage Modulus

Critical Yield Stress : Exceeding 3 Pa at 22°C.

[0015] In a preferred embodiment, the Storage Modulus is around 9000 Pa at 22°C. The Critical Yield Stress is preferably around 30 Pa at 22°C.

[0016] In order to interact in a suitable manner with the tyre and the imbedded solid bodies, the composition of the invention should preferably also exhibit suitable adhesive properties ("stickiness") with respect to the tyre and the bodies. Thus, the adhesion between tyre inner lining and the visco-plastic gels as well as the adhesion between imbedded masses and the visco-plastic gels may be evaluated in the following two step practical test:

Step 1:

[0017] A two mm thick, 100x100 mm square of the visco-plastic gel to be tested is applied to the middle of a sheet (200x200 mm) of chloro-butyl rubber glued onto a stiff support (metal plate) as well as to the middle of a similar sheet of butyl rubber. The two sheets are raised into a vertical position and left standing for 24 hours at 22°C and 65% R. H. If the displacement of the upper rim of the gel-square is less than 3 mm on both test surfaces, the adhesion of the gel component to tyre inner linings is deemed satisfactory.

Step 2:

[0018] A two mm thick, 100x100 mm square of a vis-

co-plastic gel that conforms to the requirements of Step 1 of this test is applied to the middle of a sheet (200x200 mm) of chloro-butyl rubber glued onto a stiff support (metal plate), and 10 HD polyethylene disk-shaped pellets (specific weight 0.9; disk average diameter: 4.5 mm, disk average height 3 mm) are inserted randomly into the gel. The sheet is raised into a vertical position and left standing for 24 hours at 22°C and 65% R.H. If the average displacement of the pellets is less than 2 mm, the adhesion of the gel component to solid masses is deemed satisfactory.

Visco-plastic gels that conform to both step both Step 1 and Step 2 of this test are considered suitable with respect to adhesive properties.

[0019] Apart from the rheological and adhesive criteria defined above, visco plastic gels suitable for use in this invention should preferably also satisfy certain other physical and chemical criteria that will ensure optimum function under the operating conditions and environment of this particular application, such as:

- compatibility with tyre inner liners,
- proper response and displacement under the action of combined centrifugal and vibrational shear stresses,
- constancy of response over a broad temperature range,
- stability of material properties and response over many years in use,
- chemical inertia of the gel components vis a vis tyre inner liner rubber,
- stability of the gel composition and properties under high g-stress and shear stresses,
- little change in material properties and behaviour upon ageing in normal operating conditions.

[0020] The visco-plastic gels, in which the solid bodies are imbedded to form the balancing compositions of the invention, may be of any chemical composition which provides the visco-plastic properties required, preferably as defined above as well as with the other physical and chemical properties enumerated above. Such visco-plastic gels will typically be composed from on the one hand one or more organic base oils having a suitably low viscosity index and on the other hand a gel former. Non-limiting examples of base oils are mineral oil, polyol esters of fatty acids derived from synthetic or naturally occurring polyols and fatty acids, synthetic hydrocarbon oils such as polypropylene oils, poly-alpha-olefins, polybutenes, polyglycols such as liquid polyethylene glycol or liquid polypropylene glycol, or ethylene oxide/propylene oxide copolymers, as well as mixtures thereof. Non-limiting examples of gel formers are colloidal silicas, polyacrylic acids, bentonite clay and metal soaps.

[0021] One suitable type of gels are those described in the above mentioned European Patent 0557365.

[0022] The solid bodies may suitably be shaped as

prolate or oblate ellipsoids, cylinders, rectangular parallelepipeds, or spheres, or mixtures of such bodies. They may be prepared through any method known in the art such as emulsion polymerisation of polymers or cutting rectangular or circular cross-section extrudates into suitable lengths.

**[0023]** In order that the solid bodies do not interact unduly with the inside of the tyre when under the influence of centrifugal forces, it is preferred that the apparent specific gravity of the solid bodies is in the range of 500-3000 kg/m<sup>3</sup>, more preferably 600-2000 kg/m<sup>3</sup>, in particular 700-1000 kg/m<sup>3</sup>, especially 800-900 kg/m<sup>3</sup>. The term "apparent specific gravity" as applied to the solid bodies refers to the ratio between the weight of each individual solid body and the volume enclosed by the outer, continuous surface. Thus, it will be clear that if the bodies are hollow or otherwise include voids or are porous, the apparent specific gravity may lower than the nominal specific gravity of the material from which the bodies are made.

**[0024]** The solid bodies should preferably be made from a material which does not interact unsuitably with the visco-plastic gel. Non-limiting examples of suitable materials for the solid bodies are various polymers such as polyolefins, e.g. polyethylene (either high or low density) or polypropylene; polystyrene; polyvinyl chloride; polyamides, e.g. nylons; rubbers such as butyl rubber or latex; or glass.

**[0025]** The content of solid bodies in the composition of the invention may vary within fairly wide limits since the purpose of the bodies is to be able to move in the gel layer in order to establish zones with a high concentration of solid bodies to act as balancing elements. The weight ratio between the solid bodies and the gel is preferably from 10:1 to 1:10, more preferably from 5:1 to 1:5, in particular from 2:1 to 3:1, such as from 1:1 to 1:2.

**[0026]** It will be evident that in order to work the invention, imbedding the solid bodies in the visco-plastic gel to form the composition of the invention need not take place outside the tyre. Thus, when applying the teaching of the present invention, it will also be possible to instead first distribute a suitable amount of a visco-plastic gel on the inside of a tyre and subsequently distribute a suitable amount of solid bodies on the gel layer, thereby forming a composition of the invention.

**[0027]** Consequently, the invention further concerns a tyre balancing composition kit comprising

- i) a first container containing a visco-plastic gel, and
- ii) a second container containing solid bodies having their average smallest dimension in the range of 0.5-5 mm.

**[0028]** The visco-plastic gel and the solid bodies, respectively, preferably are defined as and/or exhibit the properties and attributes listed above.

**[0029]** In a preferred embodiment of the balancing kit of the invention, the weight ratio between the amount of

visco-plastic gel in the first container and the amount of solid bodies in the second container is from 10:1 to 1:10, preferably from 5:1 to 1:5, in particular from 2:1 to 3:1, such as from 1:1 to 1:2.

**[0030]** In a particularly preferred embodiment, and in order to eliminate or reduce any errors in applying them in the correct amounts, the amounts of the visco-plastic gel and the solid bodies in the first and second containers, respectively, of the balancing kit according to the invention are adapted to be applied to one single automobile tyre, whether a passenger automobile tyre, a truck tyre or the like. Such amounts will typically be from 50 to 400 g per tyre for passenger vehicle tyres, and 300-1000 g per tyre for truck tyres.

**[0031]** Due to the above described possibility of not combining the visco-plastic gel and solid bodies until in the tyre, the present invention likewise further relates to a tyre balancing composition according to the invention as defined above contained within the air cavity of a motor vehicle tyre.

**[0032]** Finally, the invention also relates to a method for balancing a motor vehicle wheel assembly, said method comprising the steps of applying to the inner surface of the tyre

- i) a tyre balancing composition as defined above, or
- ii) the components of a tyre balancing kit as defined above;

mounting the tyre on a tyre rim to form a wheel assembly; and

mounting the wheel assembly on a motor vehicle and driving the vehicle for a distance sufficient to allow the balancing composition to balance the wheel assembly, or

mounting the wheel assembly in a device that allows the wheel assembly to be rotated under load conditions similar to those experienced during actual road driving and at a speed where resonance occurs in the wheel assembly, and rotating the wheel for a time sufficient to allow the balancing composition to reduce vibrations to a stable minimum.

**[0033]** The amount of visco-plastic gel applied to the inside of the tyre should preferably be in the range of 0.01-1 grams per cm<sup>2</sup>, more preferably 0.02-0.5 grams, in particular 0.02-0.1 grams per cm<sup>2</sup>, of the inner lining surface of the tyre adjacent the part of the tyre that actually contacts the road (the tyre tread). The amount of solid masses in the tyre balancing kit of the invention applied to the inside of the tyre should preferably be between 10 and 200 g for car tyres and between 50 and 500 g for truck tyres, more preferably between 10 and 100 g for car tyres and between 50 and 300 g for truck tyres, in particular 20-80 g and 80-150 g, respectively.

**[0034]** The invention is further illustrated by the following non-limiting examples.

## EXAMPLE 1

[0035] A DFC-gel (250 g) consisting of 1 weight part of HD polyethylene disks (specific weight 0.9, disk average diameter: 4.5 mm, disk average height 3 mm), and 2 weight parts of a visco-plastic gel according to European patent no. 0557365 and consisting of an ethylene oxide (EO)/propylene oxide (PO) copolymer (UCON 50-HB-5100 from Union Carbide, theoretical molecular weight equal to 4000) and fumed silica (Aerosil 202 from Degussa), was introduced into the cavity of a Michelin 175/65/R14 tyre. The tyre was mounted on a car and driven until all vibrations disappeared. The wheel assembly was dismantled from the car, and measurement in a spin-balancing machine showed only insignificant residual weight imbalance. Inspection of the inner tyre wall showed an uneven distribution of the polyethylene pellets as would be expected if balancing is to take place.

## EXAMPLE 2

[0036] 100 g of a visco-plastic gel according to European patent no. 0557365 and consisting of an ethylene oxide/propylene oxide copolymer (L1 from Lyondell Chemical Worldwide, Inc., EO to PO ratio equal to 1:1 and theoretical molecular weight (Mw) equal to 6500) (74.0%), castor oil No. 1 (18.5%) and fumed silica (Aerosil A300 from Degussa) (7.5%) was introduced into the cavity of a Michelin 175/65/R14 tyre and spread around the inner perimeter. HD polyethylene disks (specific weight 0.9, disk average diameter: 4.5 mm, disk average height 3 mm) were then sprinkled evenly on top of the gel layer. The tyre was mounted on a car and driven until all vibrations disappeared. The wheel assembly was dismantled from the car, and measurement in a spin-balancing machine showed only insignificant residual weight imbalance. Inspection of the inner tyre wall showed a distribution of the polyethylene pellets as would be expected if balancing is to take place.

## EXAMPLE 3

[0037] 250 g of a visco-plastic gel according to European patent no. 0557365 and consisting of 93% of a 4:1 mixture of two ethylene oxide/propylene oxide copolymers (L1 from Lyondell Chemical Worldwide, Inc., EO to PO ratio equal to 1:1 and theoretical molecular weight (Mw) equal to 6500 (4 parts), and L1-Diol from Lyondell Chemical Worldwide, Inc., EO to PO ratio equal to 1:1 and theoretical molecular weight (Mw) equal to 13000 (1 part)) and 7% of fumed silica (Cab-O-Sil TS720 from Cabot Corporation) was introduced into the cavity of a Michelin XH4 235/75/15 tyre and spread around the inner perimeter. LD polyethylene spheres (specific weight 0.85, sphere average diameter: 4 mm) were then sprinkled evenly on top the gel layer. The tyre was mounted on a sports utility vehicle and driven until all vibrations

disappeared. The wheel assembly was dismantled from the vehicle, and measurement in a spin-balancing machine showed only insignificant residual weight imbalance. Inspection of the inner tyre wall showed a distribution of the polyethylene spheres as would be expected if balancing is to take place.

## Claims

1. A tyre balancing composition, which comprises a visco-plastic gel **characterised in that** it further comprises solid bodies having an average smallest dimension in the range of 0.5-5 mm.
2. A tyre balancing composition according to claim 1, wherein the solid bodies have an average ratio  $\alpha$  between their smallest and their largest dimension of  $\alpha \leq 2$ , preferably  $\alpha \leq 1.5$ , especially around 1.
3. A tyre balancing composition according to claim 1 or 2, wherein the average smallest dimension of the solid bodies is in the range of 1-4 mm, preferably around 3 mm.
4. A tyre balancing composition according to any of claims 1-3, wherein the visco-plastic gel has a storage modulus (G') between 1000 Pa and 25000 Pa at 22°C, preferably around 9000 Pa at 22°C, a loss modulus (G'') smaller than the storage modulus, and a critical yield stress above 3 Pa at 22°C, preferably around 30 Pa at 22°C.
5. A tyre balancing composition according to any of claims 1-4 wherein the solid bodies are shaped as prolate or oblate ellipsoids, cylinders, rectangular parallelepipeds, or spheres, or mixtures of such bodies.
6. A tyre balancing composition according to any of claims 1-5 wherein the apparent specific gravity of the solid bodies is in the range of 500-3000 kg/m<sup>3</sup>, preferably 600-2000 kg/m<sup>3</sup>, in particular 700-1000 kg/m<sup>3</sup>, especially 800-900 kg/m<sup>3</sup>.
7. A tyre balancing composition according to any of claims 1-6 wherein the solid bodies are made from polyolefins, polystyrene, polyvinyl chloride, polyamide, rubber or glass.
8. A tyre balancing composition according to any of claims 1-7 wherein the weight ratio between the solid bodies and the gel is from 10:1 to 1:10, preferably from 5:1 to 1:5, in particular from 2:1 to 3:1, such as from 1:1 to 1:2.
9. A tyre balancing composition kit comprising

- i) a first container containing a visco-plastic gel, preferably a visco-plastic gel as defined in claim 4, and  
 ii) a second container containing solid bodies having their average smallest dimension in the range of 0.5-5 mm, preferably solid bodies as defined in any of claims 2, 3 or 5-7.
10. A tyre balancing composition kit according to claim 9 wherein the weight ratio between the amount of visco-plastic gel in the first container and the amount of solid bodies in the second container is from 10:1 to 1:10, preferably from 5:1 to 1:5, in particular from 2:1 to 3:1, such as from 1:1 to 1:2.
11. A tyre balancing composition according to any of claims 1-8 contained within the air cavity of a motor vehicle tyre.
12. A method for balancing a motor vehicle wheel assembly comprising applying to the inner surface of the tyre i) a tyre balancing composition according to any of claims 1-8, or ii) the components of a kit according to claim 9 or 10, mounting the tyre on a tyre rim to form a wheel assembly, and  
 mounting the wheel assembly on a motor vehicle and driving the vehicle for a distance sufficient to allow the balancing composition to balance the wheel assembly, or  
 mounting the wheel assembly in a device that allows the wheel assembly to be rotated under load conditions similar to those experienced during actual road driving and at a speed where resonance occurs in the wheel assembly, and rotating the wheel for a time sufficient to allow the balancing composition to reduce vibrations to a stable minimum.
- Patentansprüche**
1. Zusammensetzung zum Auswuchten von Reifen, welche ein viskoses Kunststoffgel umfasst, **dadurch gekennzeichnet, dass** sie weiterhin feste Körper mit einer durchschnittlichen kleinsten Abmessung im Bereich von 0,5-5 mm umfasst.
2. Zusammensetzung zum Auswuchten von Reifen nach Anspruch 1, wobei die festen Körper ein durchschnittliches Verhältnis  $\alpha$  zwischen ihrer kleinsten und ihrer größten Abmessung von  $\alpha \leq 2$ , bevorzugt  $\alpha \leq 1,5$ , insbesondere um 1 herum, aufweisen.
3. Zusammensetzung zum Auswuchten von Reifen gemäß Anspruch 1 oder 2, wobei die durchschnittliche kleinste Abmessung der festen Körper im Bereich von 1-4 mm, bevorzugt um 3 mm, ist.
4. Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-3, wobei das viskose Kunststoffgel einen Speichermodul ( $G'$ ) zwischen 1000 Pa und 25000 Pa bei 22°C, bevorzugt um 9000 Pa bei 22°C, einen Verlustmodul ( $G''$ ) kleiner als der Speichermodul, und eine kritische Nachgebefestigkeit über 3 Pa bei 22°C, bevorzugt um 30 PA bei 22°C, aufweist.
5. Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-4, wobei die festen Körper als gestreckte oder abgeplattete Ellipsoiden, Zylinder, rechteckige Parallelepipeden oder Kugeln oder als Mischung derartiger Körper geformt sind.
6. Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-5, wobei die scheinbare spezifische Schwerkraft der festen Körper im Bereich von 500 bis 3000 kg/m<sup>3</sup>, bevorzugt 600 bis 2000 kg/m<sup>3</sup>, insbesondere 700-1000 kg/m<sup>3</sup>, besonders 800-900 kg/m<sup>3</sup> liegt.
7. Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-6, wobei die festen Körper aus Polyolefinen, Polystyrol, Polyvinylchlorid, Polyamid, Gummi oder Glas gefertigt sind.
8. Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-7, wobei das Gewichtsverhältnis zwischen den festen Körpern und dem Gel zwischen 10:1 und 1:10, bevorzugt zwischen 5:1 und 1:5, insbesondere zwischen 2:1 und 3:1, beispielsweise zwischen 1:1 und 1:2 liegt.
9. Bausatz für eine Zusammensetzung zum Auswuchten von Reifen umfassend  
 i) einen ersten Behälter, welcher ein viskoses Kunststoffgel, bevorzugt ein viskoses Kunststoffgel nach Anspruch 4, beinhaltet und  
 ii) einen zweiten Behälter, welcher feste Körper mit einer durchschnittlichen kleinsten Abmessung im Bereich von 0,5-5 mm, bevorzugt feste Körper gemäß einem der Ansprüche 2, 3 oder 5-7, beinhaltet.
10. Bausatz für eine Zusammensetzung zum Auswuchten von Reifen nach Anspruch 9, wobei das Gewichtsverhältnis zwischen der Menge des viskosen Kunststoffgels in dem ersten Container und der Menge von festen Körpern in dem zweiten Container zwischen 10:1 und 1:10, bevorzugt zwischen 5:1 und 1:5, insbesondere zwischen 2:1 und 3:1, beispielsweise zwischen 1:1 und 1:2 liegt.
11. Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-8, welche in dem Luft-

hohlraum eines Reifens eines Motorfahrzeugs enthalten ist.

12. Verfahren zum Auswuchten einer Motorfahrzeugreifenanordnung, welches umfasst; auf die innere Oberfläche des Rades i) eine Zusammensetzung zum Auswuchten von Reifen nach einem der Ansprüche 1-8 oder ii) die Komponenten eines Bauesatzes nach Anspruch 9 oder 10 aufzubringen, den Reifen auf eine Reifenfelge anzubringen, um eine Reifenanordnung zu bilden, und  
 die Reifenanordnung an einem Motorfahrzeug anzubringen und das Motorfahrzeug über eine Strecke zu fahren, welche ausreichend ist, es der Zusammensetzung zum Auswuchten zu ermöglichen, die Reifenanordnung auszuwuchten, oder  
 die Reifenanordnung an einem Gerät anzubringen, welches es ermöglicht, die Reifenanordnung unter Lastbedingungen zu drehen, welche ähnlich denen sind, welchen die Reifenanordnung beim tatsächlichen Fahren auf der Straße ausgesetzt ist, und bei einer Geschwindigkeit, bei welcher eine Resonanz in der Reifenanordnung auftritt, und Drehen des Reifens für einen Zeitraum, welcher ausreichend ist, es der Zusammensetzung zum Auswuchten zu ermöglichen, Vibrationen auf ein stabiles Minimum zu verringern.

#### Revendications

1. Composition d'équilibrage pour pneumatiques qui comprend un gel viscoplastique, **caractérisée en ce qu'elle** comprend en outre des corps solides ayant une plus petite dimension moyenne dans la plage comprise entre 0,5 mm et 5 mm. 35
2. Composition d'équilibrage pour pneumatiques selon la revendication 1, dans laquelle les corps solides ont un rapport moyen  $\alpha$ , entre leur plus petite et leur plus grande dimension, de  $\alpha \leq 2$ , de préférence de  $\alpha \leq 1,5$ , notamment autour de 1. 40
3. Composition d'équilibrage pour pneumatiques selon la revendication 1 ou 2, dans laquelle la plus petite dimension moyenne des corps solides est dans la plage comprise entre 1 mm et 4 mm, de préférence autour de 3 mm. 45
4. Composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 3, dans laquelle le gel viscoplastique a un module de stockage ( $G'$ ) compris entre 1000 Pa et 25 000 Pa à 22°C, de préférence autour de 9000 Pa à 22°C, un module de perte ( $G''$ ) plus petit que le module de stockage, et une limite élastique critique supérieure à 3 Pa à 22°C, de préférence autour de 30 Pa à 22°C. 55
5. Composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 4, dans laquelle les corps solides sont conformés comme des ellipsoïdes allongés ou aplatis, des cylindres, des parallélépipèdes rectangulaires ou des sphères ou des mélanges de tels corps. 5
6. Composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 5, dans laquelle le poids volumique apparent des corps solides est dans la plage comprise entre 500 kg/m<sup>3</sup> et 3000 kg/m<sup>3</sup>, de préférence entre 600 kg/m<sup>3</sup> et 2000 kg/m<sup>3</sup>, en particulier entre 700 kg/m<sup>3</sup> et 1000 kg/m<sup>3</sup>, notamment entre 800 kg/m<sup>3</sup> et 900 kg/m<sup>3</sup>. 10
7. Composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 6, dans laquelle les corps solides sont fabriqués à partir de polyoléfinés, de polystyrène, de chlorure de polyvinyle, de polyamide, de caoutchouc ou de verre. 15
8. Composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 7, dans laquelle le rapport de poids entre les corps solides et le gel varie entre 10 : 1 et 1 : 10, de préférence entre 5 : 1 et 1 : 5, en particulier entre 2 : 1 et 3 : 1, tel qu'un rapport variant entre 1 : 1 et 1 : 2. 20
9. Kit de composition d'équilibrage pour pneumatiques comprenant : 30
  - i) un premier conteneur contenant un gel viscoplastique, de préférence un gel viscoplastique tel qu'il est défini dans la revendication 4, et
  - ii) un second conteneur contenant des corps solides ayant leur plus petite dimension moyenne dans la plage comprise entre 0,5 mm et 5 mm, de préférence des corps solides tels qu'ils sont définis dans l'une quelconque des revendications 2, 3 ou 5 à 7.
10. Kit de composition d'équilibrage pour pneumatiques selon la revendication 9, dans laquelle le rapport de poids entre la quantité de gel viscoplastique dans le premier conteneur et la quantité de corps solides dans le second conteneur varie entre 10 : 1 et 1 : 10, de préférence entre 5 : 1 et 1 : 5, en particulier entre 2 : 1 et 3 : 1, tel qu'un rapport variant entre 1 : 1 et 1 : 2. 40
11. Composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 8, contenue à l'intérieur de la cavité d'air d'un pneumatique de véhicule automobile. 50
12. Procédé permettant d'équilibrer un ensemble de roue d'un véhicule automobile consistant : 55

- à appliquer sur la surface intérieure du pneumatique :
  - i) une composition d'équilibrage pour pneumatiques selon l'une quelconque des revendications 1 à 8 ou 5
  - ii) les composants d'un kit selon la revendication 9 ou 10,
- à monter le pneumatique sur une jante de pneumatique pour former un ensemble de roue, et 10
- à monter l'ensemble de roue sur un véhicule automobile et à conduire le véhicule sur une distance suffisante pour permettre à la composition d'équilibrage d'équilibrer l'ensemble de roue, ou 15
- à monter l'ensemble de roue dans un dispositif qui permet à l'ensemble de roue d'être en-rotation dans des conditions de charge analogues à celles rencontrées au cours d'une conduite réelle sur route et à une vitesse où un phénomène de résonance se produit dans l'ensemble de roue, et à faire tourner la roue pendant un temps suffisant pour permettre à la composition d'équilibrage de réduire les vibrations à un minimum stable. 25

30

35

40

45

50

55