

(19) **DANMARK**

(10) **DK/EP 2626730 T3**



(12)

Oversættelse af
europæisk patentskrift

Patent- og
Varemærkestyrelsen

-
- (51) Int.Cl.: **G 02 B 6/024 (2006.01)** **G 02 B 6/036 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2021-10-11**
- (80) Dato for Den Europæiske Patentmyndigheds bekendtgørelse om meddelelse af patentet: **2021-08-18**
- (86) Europæisk ansøgning nr.: **11830628.1**
- (86) Europæisk indleveringsdag: **2011-10-03**
- (87) Den europæiske ansøgnings publiceringsdag: **2013-08-14**
- (86) International ansøgning nr.: **JP2011072787**
- (87) Internationalt publikationsnr.: **WO2012046696**
- (30) Prioritet: **2010-10-05 JP 2010225797**
- (84) Designerede stater: **AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**
- (73) Patenthaver: **Fujikura Ltd., 1-5-1, Kiba, Koto-ku, Tokyo 135-8512, Japan**
- (72) Opfinder: **HAYASHI Kazuyuki, c/o Fujikura Ltd., Sakura Works, 1440 Mutsuzaki, Sakura-shi, Chiba 285-8550, Japan**
IZOE Katsuaki, c/o Fujikura Ltd., Sakura Works, 1440 Mutsuzaki, Sakura-shi, Chiba 285-8550, Japan
ENDOH Yutaka, c/o Fujikura Ltd., Sakura Works, 1440 Mutsuzaki, Sakura-shi, Chiba 285-8550, Japan
AIKAWA Kazuhiko, c/o Fujikura Ltd., Sakura Works, 1440 Mutsuzaki, Sakura-shi, Chiba 285-8550, Japan
KUDOH Manabu, c/o Fujikura Ltd., Sakura Works, 1440 Mutsuzaki, Sakura-shi, Chiba 285-8550, Japan
- (74) Fuldmægtig i Danmark: **Plougmann Vingtoft A/S, Strandvejen 70, 2900 Hellerup, Danmark**
- (54) Benævnelse: **POLARISERINGSOPRETHOLDENDE OPTISK FIBER**
- (56) Fremdragne publikationer:
JP-A- 63 189 809
JP-A- 2008 076 655
US-A1- 2005 008 311
US-A1- 2009 060 435
US-A1- 2009 080 843

DESCRIPTION

TECHNICAL FIELD

[0001] The present invention relates to a polarization-maintaining optical fiber suitable for an optical transmission system using a laser diode or the like mainly used in the visible wavelength range, and in particular, a polarization-maintaining optical fiber which can be used in the entire wavelength range of 400 to 680 nm and has reduced bending polarization crosstalk and bending loss in the entire wavelength range.

[0002] Priority is claimed on Japanese Patent Application No. 2010-225797, filed October 5, 2010.

BACKGROUND ART

[0003] Polarization-maintaining optical fiber is a single-mode optical waveguide (single-mode fiber) capable of holding and transmitting a linearly polarized wave.

[0004] The polarization-maintaining optical fiber has a schematic configuration including a core, a pair of stress-applying parts provided on both sides of the core, and a cladding surrounding the core and the stress-applying parts.

[0005] The stress-applying parts serve to induce birefringence in the core to which light is guided and are a pair of glass regions that are disposed in the cladding so as to be separated from each other with the core interposed therebetween and face each other in the diameter direction of the polarization-maintaining optical fiber.

[0006] In addition, the stress-applying part is provided over the entire length in the longitudinal direction of the polarization-maintaining optical fiber.

[0007] The thermal expansion coefficient of the glass regions which form the stress-applying parts is different from the thermal expansion coefficient of glass which forms the cladding.

[0008] In addition, a polarization-maintaining optical fiber is known in which the dimension (diameter) of a cross section perpendicular to the longitudinal direction in at least one of the glass regions that form stress-applying parts is larger than the diameter of the core.

[0009] The polarization-maintaining optical fiber having such a structure is called PANDA (Polarization-maintaining and absorption reducing) type polarization-maintaining optical fiber.

[0010] The polarization-maintaining optical fiber is used not only for optical communication but

also for connection between optical components having a polarization dependence or optical components for optical transmission, such as an optical fiber grating or an optical fiber coupler.

[0011] Taking into consideration the ease of manufacturing, stability of quality, connectivity with a common silica-based optical waveguide fiber, and the like, the polarization-maintaining optical fiber used as an optical component for optical transmission is designed so as to have a single-mode optical waveguide structure in a narrow wavelength range near the wavelength of the light used (for example, refer to Patent Document 1, Patent Document 2, Patent Document 3,

[0012] Non-Patent Document 1, and Non-Patent Document 2).

PRIOR ART DOCUMENT

PATENT DOCUMENTS

[0013]

[Patent Document 1] Japanese Unexamined Patent Application, First Publication No. 2003-337238

[Patent Document 2] JP 2008 076655 A, Japanese Unexamined Patent Application, First Publication No. 2008-76655 describing a polarization maintaining optical fiber that includes a core that contains a hydroxyl group with a concentration of 600-1,400 ppm, a clad surrounding the core, and a pair of stress imparting parts that penetrate a part of the clad and that are placed symmetrically about the core and in parallel in the longitudinal direction of the core.

[Patent Document 3] JP 63 189809 A, describing a single mode optical fiber having a low transmission loss and bending loss via coating the circumference of a central SiO₂ core with F-SiO₂ and further, coating the same with SiO₂ of a specific thickness.

NON-PATENT DOCUMENTS

[0014]

[Non-Patent Document 1] Fujikura Technology Vol. 85, p. 1-9, issued October, 1993

[Non-Patent Document 2] Introduction of Fujikura PANDA fiber and Basis of polarization-maintaining fiber (URL:http://www.fujikura.co.jp/products/tele/o_device/data/16pnb04j.pdf)

DISCLOSURE OF INVENTION

PROBLEMS TO BE SOLVED BY INVENTION

[0015] Conventional polarization-maintaining optical fibers have been designed so as to have a single-mode optical waveguide structure in a narrow wavelength range near the wavelength used taking into consideration the ease of manufacturing, stability of quality, connectivity with a common silica-based optical waveguide fiber, and the like.

[0016] That is, an optical fiber structure which is satisfactory in terms of bending loss and bending polarization crosstalk in the entire wavelength range of 400 to 680 nm is not yet available.

[0017] For example, when a conventional polarization-maintaining optical fiber for 400 nm is used at a wavelength (for example, 680 nm) away from the cut-off wavelength to the longer wavelength, if this polarization-maintaining optical fiber is wound 10 times with a small bending diameter (for example, with a diameter of 60 mm), there has been a problem in that the loss or the polarization crosstalk increases.

[0018] In addition, in the conventional polarization-maintaining optical fiber, the diameter of the stress-applying part is increased or the distance between the stress-applying parts is decreased so that polarization crosstalk is not increased when the bending diameter is reduced. However, if the diameter is too large, the rate of non-circularity of the cladding is increased.

[0019] Then, when the polarization-maintaining optical fiber is connected with a connector or when the polarization-maintaining optical fiber is connected with other optical fibers or optical components, positioning becomes difficult. As a result, there has been a problem in that working efficiency becomes poor.

[0020] If the distance between the stress-applying parts is narrowed, a mode field becomes non-circular. As a result, loss of connection with other optical fibers is increased, or the loss of the optical fiber itself is increased due to the influence of the stress-applying parts.

[0021] The present invention has been made in view of the above-described situation, and it is an object of the present invention to provide a polarization-maintaining optical fiber capable of suppressing an increase of bending loss and polarization crosstalk.

MEANS FOR SOLVING THE PROBLEMS

[0022] A polarization-maintaining optical fiber of the present invention is a polarization-maintaining optical fiber according to claim 1.

EFFECTS OF THE INVENTION

[0023] According to the aspect of the polarization-maintaining optical fiber of the present embodiment, after applying a bending of 60 mm in diameter 10 times, a loss increase in the wavelength range of 400 to 680 nm can be less than or equal to 0.1 dB and polarization crosstalk in the wavelength range of 400 to 680 nm can be less than or equal to -30 dB.

BRIEF DESCRIPTION OF DRAWINGS

[0024]

FIG. 1 is a schematic cross-sectional diagram showing an embodiment of a polarization-maintaining optical fiber not forming part of the present invention.

FIG. 2 is a schematic cross-sectional diagram showing an embodiment of the polarization-maintaining optical fiber of the present invention.

FIG. 3 is a graph showing a result when a polarization-maintaining optical fiber of a first example of the present invention is wound around bobbins having different external diameters and the bending loss in the wavelength range of 400 to 680 nm is measured for each bending diameter.

EMBODIMENTS FOR CARRYING OUT THE INVENTION

[0025] Hereinafter, embodiments of a polarization-maintaining optical fiber of the present invention will be described.

[0026] In addition, the present embodiment is intended to explain the summary of the invention in detail for better understanding, and does not limit the present invention unless otherwise specified.

[0027] FIG. 1 is a schematic cross-sectional diagram showing an embodiment of a polarization-maintaining optical fiber not forming part of the present invention.

[0028] A polarization-maintaining optical fiber 10 of the present embodiment has a schematic

configuration including a core 11, a pair of stress-applying parts 12 provided on both sides of the core 11 and at point-symmetrical positions with respect to the core 11, and a cladding 13 surrounding the core 11 and the stress-applying parts 12.

[0029] This polarization-maintaining optical fiber 10 is an optical fiber of which a cross-sectional shape perpendicular to the longitudinal direction, that is, a cross-sectional shape in the diameter direction is circular.

[0030] A material with higher refractive index than the cladding 13 is used as the core 11, and a material with a larger thermal expansion coefficient than the cladding 13 is used as the stress-applying part 12.

[0031] As these materials, any material may be used as long as it is a material used for the conventional PANDA type polarization-maintaining optical fiber.

[0032] For example, silica glass added (doped) with germanium is used as a material of the core 11.

[0033] As a material of the stress-applying part 12, B_2O_3 - SiO_2 glass obtained by adding (doping) boron of about 17 to 21 mol% in cross-sectional weight concentration of boron oxide (B_2O_3) is used.

[0034] Pure silica glass is used as a material of the cladding 13.

[0035] The refractive index of the core 11 is 1.462 to 1.464.

[0036] In addition, the thermal expansion coefficient of the core 11 is $21 \times 10^{-7} / ^\circ C$ to $22 \times 10^{-7} / ^\circ C$.

[0037] The thermal expansion coefficient of the stress-applying part 12 is $14 \times 10^{-7} / ^\circ C$ to $15 \times 10^{-7} / ^\circ C$.

[0038] The refractive index of the cladding 13 is 1.456 to 1.458.

[0039] In addition, the thermal expansion coefficient of the cladding 13 is $4 \times 10^{-7} / ^\circ C$ to $6 \times 10^{-7} / ^\circ C$.

[0040] The relative refractive index difference between the core 11 and the cladding 13 is 0.35 to 0.45%, and is preferably 0.37 to 0.43%.

[0041] By setting the relative refractive index difference within the above range, the effect of confinement of light to the core 11 becomes strong. Accordingly, even if the polarization-maintaining optical fiber 10 is bent with a small bending diameter, the loss does not increase.

[0042] When the relative refractive index difference is less than 0.35%, the effect of confinement of light to the core 11 becomes weak. Accordingly, if the polarization-maintaining optical fiber 10 is bent with a small bending diameter, the loss increases.

[0043] As the relative refractive index difference becomes larger, the effect of confinement of light to the core 11 becomes stronger. Accordingly, even if the polarization-maintaining optical fiber 10 is bent with a small bending diameter, the loss does not increase.

[0044] However, if the relative refractive index difference exceeds 0.45%, a mode field diameter (MFD) is reduced. As a result, connectivity with other optical fibers or optical components is reduced.

[0045] The core 11 forms the center of the polarization-maintaining optical fiber 10, and the cross-sectional shape of the polarization-maintaining optical fiber 10 in the diameter direction is circular.

[0046] Preferably, the diameter of the core 11 is 1.5 to 3.5 μm . More preferably, the diameter of the core 11 is 2 μm to 3 μm .

[0047] When the diameter of the core 11 is less than 2 μm , it is necessary to increase the refractive index difference between the core 11 and the cladding 13. In this case, since the MFD is also reduced, connection with other optical fibers, incidence of light from other optical components, and the like become difficult.

[0048] On the other hand, if the diameter of the core 11 exceeds 3 μm , it is necessary to reduce the refractive index difference between the core 11 and the cladding 13. Accordingly, loss due to the bending of the polarization-maintaining optical fiber 10 is increased.

[0049] The diameter of the cladding 13 is 125 μm .

[0050] The stress-applying parts 12 are disposed so as to be separated from each other with the core 11 interposed therebetween, and the cross-sectional shape of the polarization-maintaining optical fiber 10 in the diameter direction is circular.

[0051] The diameter D of the stress-applying part 12 is 33 to 37 μm , and is preferably 34 μm to 36 μm .

[0052] When the diameter D of the stress-applying part 12 is less than 33 μm , stress applied to the core 11 is reduced. As a result, the polarization crosstalk characteristic is degraded.

[0053] On the other hand, if the diameter D of the stress-applying part 12 exceeds 37 μm , the cladding 13 becomes non-circular. As a result, workability for a connector is degraded.

[0054] In addition, a distance R between the two stress-applying parts 12 is 8.6 to 15.4 μm , and is preferably 10 to 14 μm .

[0055] When the distance R between the stress-applying parts 12 is less than 8.6 μm , a distance between the stress-applying part 12 and the core 11 is too small. In this case, there is a possibility that the mode field will become non-circular and the connection loss will increase accordingly. Therefore, this is not desirable.

[0056] In addition, if the stress-applying part 12 overlaps the mode field, the loss is increased.

[0057] On the other hand, if the distance R between the stress-applying parts 12 exceeds 15.4 μm , the polarization maintaining characteristic is degraded. Therefore, this is not desirable.

[0058] Hereinafter, the reason why the above-described structural parameters of the polarization-maintaining optical fiber of the present invention are set to be within the above-described ranges will be described.

[0059] By calculating the diameter of the stress-applying part 12 and the distance between the stress-applying parts 12 using the method proposed in Patent Document 1 described above, the modal birefringence which determines the characteristics of the optimal polarization crosstalk can be calculated without increasing the rate of non-circularity of the core 11.

[0060] In addition, the diameter of the stress-applying part determined by this method was 38.75 μm .

[0061] Here, when a polarization-maintaining optical fiber was manufactured in which the diameter of the stress-applying part was 38.75 μm and other structural parameters were within the above-described ranges, the rate of non-circularity of the cladding exceeded the specification (2% or less).

[0062] Therefore, when the inventors and the like manufactured a polarization-maintaining optical fiber by changing the diameter of the stress-applying part, they found out that optimal polarization crosstalk characteristics were obtained and the rate of non-circularity of the cladding satisfied the specification if the diameter of the stress-applying part was in a range of 33 to 37 μm .

[0063] In addition, since the polarization-maintaining optical fiber 10 can be used in the entire wavelength range of 400 to 680 nm, the cut-off wavelength is less than or equal to 400 nm.

[0064] According to the polarization-maintaining optical fiber 10 of the present embodiment, after applying a bending of 60 mm in diameter 10 times, a loss increase in the wavelength range of 400 to 680 nm becomes less than or equal to 0.1 dB and polarization crosstalk in the wavelength range of 400 to 680 nm becomes less than or equal to -30 dB.

[0065] Therefore, by using the polarization-maintaining optical fiber 10 as an optical fiber for connection that is used for optical components for optical transmission, such as an optical fiber amplifier, a semiconductor laser, and a modulator, and optical measurement equipment, one type of optical fiber is required for each wavelength although about three types of optical fibers were required for each wavelength in the related art.

[0066] FIG. 2 is a schematic cross-sectional diagram showing an embodiment of the polarization-maintaining optical fiber of the present invention.

[0067] A polarization-maintaining optical fiber 20 of the present embodiment has a schematic configuration including a core 21, a pair of stress-applying parts 22 provided on both sides of the core 21 and at point-symmetrical positions with respect to the core 21, and a cladding 23 surrounding the core 21 and the stress-applying parts 22.

[0068] In addition, the cladding 23 is configured to include a first cladding 23A, which directly surrounds the core 21 and the stress-applying parts 22, and a second cladding 23B provided on the outer periphery of the first cladding 23A.

[0069] This polarization-maintaining optical fiber 20 is an optical fiber of which a cross-sectional shape perpendicular to the longitudinal direction, that is, a cross-sectional shape in the diameter direction is circular.

[0070] A material with higher refractive index than the cladding 23 is used as the core 21, and a material with a larger thermal expansion coefficient than the cladding 23 is used as the stress-applying part 22.

[0071] As these materials, any material may be used as long as it is a material used for the conventional PANDA type polarization-maintaining optical fiber.

[0072] As a material of the stress-applying part 22, B_2O_3 - SiO_2 glass obtained by adding (doping) boron of about 17 to 21 mol% in cross-sectional weight concentration of boron oxide (B_2O_3) is used.

[0073] Fluorine-doped silica glass is used as a material of the first cladding 23A, and pure silica glass is used as a material of the second cladding 23B.

[0074] The refractive index of the core 21 is 1.456 to 1.458.

[0075] In addition, the thermal expansion coefficient of the core 21 is $4 \times 10^{-7} / ^\circ C$ to $6 \times 10^{-7} / ^\circ C$.

[0076] The thermal expansion coefficient of the stress-applying part 22 is $14 \times 10^{-7} / ^\circ C$ to $15 \times 10^{-7} / ^\circ C$.

[0077] The refractive index of the first cladding 23A is 1.450 to 1.452.

[0078] In addition, the thermal expansion coefficient of the first cladding 23A is $4 \times 10^{-7} / ^\circ\text{C}$ to $6 \times 10^{-7} / ^\circ\text{C}$.

[0079] The refractive index of the second cladding 23B is 1.456 to 1.458.

[0080] In addition, the thermal expansion coefficient of the second cladding 23B is $4 \times 10^{-7} / ^\circ\text{C}$ to $6 \times 10^{-7} / ^\circ\text{C}$.

[0081] The relative refractive index difference between the core 21 and the cladding 23 is 0.35 to 0.45%, and is preferably 0.37 to 0.43%.

[0082] By setting the relative refractive index difference within the above range, the effect of confinement of light to the core 21 becomes strong. Accordingly, even if the polarization-maintaining optical fiber 20 is bent with a small bending diameter at a wavelength away from the cut-off wavelength to the longer wavelength, the loss does not increase.

[0083] When the relative refractive index difference is less than 0.35%, the effect of confinement of light to the core 21 becomes weak. Accordingly, if the polarization-maintaining optical fiber 20 is bent with a small bending diameter, the loss increases.

[0084] As the relative refractive index difference becomes larger, the effect of confinement of light to the core 21 becomes stronger. Accordingly, even if the polarization-maintaining optical fiber 20 is bent with a small bending diameter, the loss does not increase.

[0085] However, if the relative refractive index difference exceeds 0.45%, the mode field diameter (MFD) is reduced. As a result, connectivity with other optical fibers or optical components is reduced.

[0086] The core 21 forms the center of the polarization-maintaining optical fiber 20, and the cross-sectional shape of the polarization-maintaining optical fiber 20 in the diameter direction is circular.

[0087] Preferably, the diameter of the core 21 is 1.5 to 3.5 μm . More preferably, the diameter of the core 21 is 2 to 3 μm .

[0088] When the diameter of the core 21 is less than 2 μm , it is necessary to increase the refractive index difference between the core 21 and the cladding 23. In this case, since the MFD is also reduced, connection with other optical fibers, incidence of light using a lens, and the like become difficult.

[0089] On the other hand, if the diameter of the core 21 exceeds 3 μm , it is necessary to reduce the refractive index difference between the core 21 and the cladding 213. Accordingly, loss due to the bending of the polarization-maintaining optical fiber 20 is increased.

[0090] Preferably, the diameter of the first cladding 23A is 30 to 95 μm . More preferably, the diameter of the first cladding 23A is 60 to 90 μm .

[0091] The diameter of the second cladding 23B is 125 μm .

[0092] The thickness of the second cladding 23B is 15 to 32.5 μm . More preferably, the thickness of the second cladding 23B is 17.5 μm to 32.5 μm .

[0093] The reason why the second cladding 23B is provided is that the melting point of the cladding 23 is low if the core 21 is pure silica glass and the cladding 23 is fluorine-doped silica glass and tension is applied to the core 21 at the time of drawing, and as a result, the optical properties are no longer stable.

[0094] The reason why the thickness of the first cladding 23A is greater than or equal to 30 μm is that the light propagating through the core 21 leaks to the second cladding 23B if the second cladding 23B having the same refractive index as the core 21 is close to the core 21.

[0095] In addition, if the thickness of the second cladding 23B is less than or equal to 15 μm , tension applied to the core 21 is increased. As a result, the optical properties are no longer stable.

[0096] The stress-applying parts 22 are disposed so as to be separated from each other with the core 21 interposed therebetween, and the cross-sectional shape of the polarization-maintaining optical fiber 20 in the diameter direction is circular.

[0097] The diameter D of the stress-applying part 22 is 33 to 37 μm , and is preferably 34 to 36 μm .

[0098] When the diameter D of the stress-applying part 22 is less than 33 μm , stress applied to the core 21 is reduced. As a result, the polarization crosstalk characteristic is degraded.

[0099] On the other hand, if the diameter D of the stress-applying part 22 exceeds 37 μm , the cladding 23 becomes non-circular. As a result, workability for a connector is degraded.

[0100] In addition, a distance R between the two stress-applying parts 22 is 8.6 to 15.4 μm , and is preferably 10 to 14 μm .

[0101] When the distance R between the stress-applying parts 22 is less than 8.6 μm , a distance between the stress-applying part 22 and the core 21 is too small. In this case, there is a possibility that the mode field will become non-circular and the connection loss will increase

accordingly. Therefore, this is not desirable.

[0102] On the other hand, if the distance R between the stress-applying parts 22 exceeds 15.4 μm , the polarization maintaining characteristic is degraded. Therefore, this is not desirable.

[0103] In addition, since the polarization-maintaining optical fiber 20 can be used in the entire wavelength range of 400 to 680 nm, the cut-off wavelength is less than or equal to 400 nm.

[0104] According to the polarization-maintaining optical fiber 20 of the present embodiment, after applying a bending of 60 mm in diameter 10 times, a loss increase in the wavelength range of 400 to 680 nm becomes less than or equal to 0.1 dB and polarization crosstalk in the wavelength range of 400 to 680 nm becomes less than or equal to -30 dB.

[0105] Therefore, by using the polarization-maintaining optical fiber 20 as an optical fiber for connection that is used for optical components for optical transmission, such as an optical fiber amplifier, a semiconductor laser, and a modulator, and optical measurement equipment, one type of optical fiber is required for each wavelength although about three types of optical fibers were required for each wavelength in the related art.

[Examples]

[0106] Hereinafter, the present invention will be described more specifically through examples and comparative examples. However, the present invention is not limited to the following examples.

[First to third examples]

[0107] In manufacturing of a polarization-maintaining optical fiber, a core rod as a core region formed of pure silica glass was prepared first.

[0108] Then, particles of pure silica glass were deposited on the outer periphery of the core rod in order to obtain a predetermined cut-off wavelength. Then, this deposition member was sintered in an atmosphere of a predetermined concentration of fluorine gas so that the relative refractive index difference Δ of 0.35% (second example), 0.40% (first example), and 0.45% (third embodiment) was obtained.

[0109] Then, particles of silica glass were deposited on the outer periphery of the sintered body and were then sintered so as to become pure silica glass. As a result, a core cladding preform of PANDA type polarization-maintaining optical fiber was obtained.

[0110] Then, a drilled preform was manufactured by drilling a hole at predetermined positions

on both sides of the core region of the core cladding preform so as to have a predetermined diameter using an ultrasonic drill and making the mirror surface by grinding and polishing the inner surface of the hole.

[0111] Apart from this, using an modified chemical vapor deposition method, a stress-applying member as a stress-applying part was obtained by depositing silica glass, which was obtained by adding boron (B) of about 21 mol% in cross-sectional weight concentration of boron oxide (B_2O_3), on the inside of the silica glass tube.

[0112] Then, a stress-applying member as a stress-applying part of the polarization-maintaining optical fiber was obtained by grinding and removing the silica tube of the outer periphery of the original preform and then polishing the outer surface until the outer surface becomes a mirror surface.

[0113] The diameter of the stress-applying member is smaller than the diameter of the hole of the drilled preform.

[0114] This stress-applying member was inserted into the drilled preform, and was heated in the drawing furnace to perform drawing so that the diameter of the cladding becomes 125 μm .

[0115] On the optical fiber after drawing, two-layered ultraviolet curable acrylate resin was coated. As a result, polarization-maintaining optical fibers of the first to third examples were obtained.

[0116] In this case, the coating diameter of the first layer was set to about 185 μm , and the coating diameter of the second layer was set to about 250 μm .

[0117] For the polarization-maintaining optical fibers of the first to third examples obtained as described above, transmission loss, bending loss, and polarization crosstalk and bending polarization crosstalk when the polarization-maintaining optical fibers were wound around a bobbin having a diameter of 160 mm were evaluated.

[0118] In addition, the connectivity was evaluated by fusion splice using the external diameter alignment of the optical fibers.

[0119] These results are shown in Table 1 together with structural parameters of the polarization-maintaining optical fibers.

[Table 1]

	First example	Second example	Third example
Relative refractive index difference (%)	0.40	0.35	0.45
Core diameter (μm)	2.6	2.5	2.2
Diameter of stress-applying part (μm)	35	35	35

	First example	Second example	Third example
Distance between stress-applying parts (μm)	11	11	11
Cladding diameter (μm)	125	125	125
Coating diameter (μm)	250	250	250
MFD [405 nm] (μm)	2.3	2.7	2.4
Bead length [405 nm] (mm)	0.69	0.7	0.65
Modal birefringence ($\times 10^{-4}$)	0.59	0.58	0.62
Cut-off wavelength (nm)	390	390	390
Loss [400 nm] (dB/km)	38	38	38
Bending loss [680 nm] (dB/f60mm 10 times)	0.005	0.005	0.005
Polarization crosstalk [680 nm] (dB)	-42	-42	-42
Bending Polarization crosstalk [680 nm] (dB/f60mm 10 times)	-42	-42	-42
Connection characteristic	good	good	good

[0120] From the result of Table 1, in the polarization-maintaining optical fibers of the first to third examples, the cut-off wavelength measured at 2 m in length was 390 nm.

[0121] In addition, when the polarization-maintaining optical fibers of the first to third examples were wound 10 times around a bobbin having a diameter of 60 mm, the loss and polarization crosstalk at the wavelength of 680 nm were 0.005 dB and -42 dB, respectively. Accordingly, a satisfactory result was obtained.

[0122] In addition, the polarization-maintaining optical fiber of the first example was wound around bobbins having different diameters, and the bending loss and polarization crosstalk in the wavelength range of 400 to 680 nm were evaluated for each bending diameter.

[0123] The result is shown in Table 2 and FIG. 3.

[Table 2]

		Unit: dB			
wavelength \ Bending diameter		406 nm	480 nm	633 nm	676 nm
ϕ 280mm		-44.01	-44.65	-45.12	-43.85
ϕ 60mm		-42.65	-43.80	-45.84	-41.77
ϕ 40mm		-43.08	-43.48	-44.53	-44.08
ϕ 30mm		-44.73	-43.44	-46.09	-43.35
ϕ 20mm		-41.07	-41.01	-42.72	-43.18

The number of windings: 10 times

[0124] From the result of Table 2, when the bending diameter was 20 to 60 mm, the polarization crosstalk in the wavelength range of 400 to 680 nm was less than or equal to -41 dB.

[0125] From the result shown in FIG. 3, when the bending diameter was 20 to 60 mm, the bending loss in the wavelength range of 400 to 680 nm was less than or equal to 0.1 dB.

[First comparative example]

[0126] A polarization-maintaining optical fiber of a first comparative example was obtained in the same conditions as in the first embodiment except that the relative refractive index difference Δ was set to 0.23%.

[0127] For the polarization-maintaining optical fiber of the first comparative example obtained as described above, transmission loss, bending loss, and polarization crosstalk and bending polarization crosstalk when the polarization-maintaining optical fiber was wound around a bobbin having a diameter of 160 mm were evaluated.

[0128] In addition, connectivity was evaluated.

[0129] These results are shown in Table 3 together with structural parameters of each polarization-maintaining optical fiber.

[Table 3]

	First comparative example	Second comparative example	Third comparative example
Relative refractive index difference (%)	0.23	0.6	0.4
Core diameter (μm)	3	1.9	2.3
Diameter of stress-applying part (μm)	35	35	38.75
Distance between stress-applying parts (μm)	15.4	11	11
Cladding diameter (μm)	125	125	125
Coating diameter (μm)	250	250	250
MFD [405 nm] (μm)	3.3	2.07	2.6
Bead length [405 nm] (mm)	0.75	0.58	0.68
Modal birefringence ($\times 10^{-4}$)	0.54	0.7	0.59
Cut-off wavelength (nm)	370	390	390

	First comparative example	Second comparative example	Third comparative example
Loss [400 nm] (dB/km)	32	46	38
Bending loss [680 nm] (dB/φ 60mm 10 times)	7	0.001	0.005
Polarization crosstalk [680 nm] (dB)	-35	-42	-42
Bending Polarization crosstalk [680 nm] (dB/φ 60mm 10 times)	Immeasurable	-42	-42
Connection characteristic	good	bad	good
Non-circularity of cladding	good	good	bad

[0130] From the result of Table 3, in the polarization-maintaining optical fiber of the first comparative example, the cut-off wavelength measured at 2 m in length was 370 nm.

[0131] In addition, when the polarization-maintaining optical fiber of the first comparative example was wound 10 times around a bobbin having a diameter of 60 mm, the loss at the wavelength of 680 nm was 7 dB and the polarization crosstalk was poor and immeasurable.

[Second comparative example]

[0132] A polarization-maintaining optical fiber of a second comparative example was obtained in the same conditions as in the first embodiment except that the relative refractive index difference Δ was set to 0.60%.

[0133] For the polarization-maintaining optical fiber of the second comparative example obtained as described above, transmission loss, bending loss, and polarization crosstalk and bending polarization crosstalk when the polarization-maintaining optical fiber was wound around a bobbin having a diameter of 160 mm were evaluated.

[0134] In addition, connectivity was evaluated.

[0135] These results are shown in Table 3 together with structural parameters of each polarization-maintaining optical fiber.

[0136] From the result of Table 3, in the polarization-maintaining optical fiber of the second comparative example, the cut-off wavelength measured at 2 m in length was 390 nm.

[0137] In addition, when the polarization-maintaining optical fiber of the second comparative example was wound 10 times around a bobbin having a diameter of 60 mm, the loss and

polarization crosstalk at the wavelength of 680 nm were 0.005 dB and -42 dB, respectively. Accordingly, a satisfactory result was obtained.

[0138] However, since the diameter of the mode field diameter (MFD) is small, loss of connection with other optical fibers is increased if the axis deviation is large.

[Third comparative example]

[0139] A polarization-maintaining optical fiber of a third comparative example was obtained in the same conditions as in the first embodiment except that the relative refractive index difference Δ was set to 0.40%.

[0140] For the polarization-maintaining optical fiber of the third comparative example obtained as described above, transmission loss, bending loss, and polarization crosstalk and bending polarization crosstalk when the polarization-maintaining optical fiber was wound around a bobbin having a diameter of 160 mm were evaluated.

[0141] In addition, connectivity was evaluated.

[0142] These results are shown in Table 3 together with structural parameters of each polarization-maintaining optical fiber.

[0143] From the result of Table 3, in the polarization-maintaining optical fiber of the third comparative example, the cut-off wavelength measured at 2 m in length was 390 nm.

[0144] In addition, when the polarization-maintaining optical fiber of the third comparative example was wound 10 times around a bobbin having a diameter of 60 mm, the loss and polarization crosstalk at the wavelength of 680 nm were 0.005 dB and -42 dB, respectively. Accordingly, a satisfactory result was obtained.

[0145] However, although the diameter of the stress-applying part was 38.75 μm and other structural parameters were almost equal to those in the first example, the modal birefringence was the same as that in the first example and the rate of non-circularity of the cladding was large.

INDUSTRIAL APPLICABILITY

[0146] According to the polarization-maintaining optical fiber of the present invention, it is possible to suppress an increase of bending loss and polarization crosstalk.

DESCRIPTION OF THE REFERENCE SYMBOLS

[0147]

- 10, 20:
 polarization-maintaining optical fiber
- 11, 21:
 core
- 12, 22:
 stress-applying part
- 13, 23:
 cladding
- 23A:
 first cladding
- 23B:
 second cladding

REFERENCES CITED IN THE DESCRIPTION

Cited references

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- [JP2010225797A \[0002\]](#)
- [JP2003337238A \[0013\]](#)
- [JP2008076655A \[0013\] \[0013\]](#)
- [JP63189809A \[0013\]](#)

Non-patent literature cited in the description

- Fujikura Technology, 1993, vol. 85, 1-9 [0014]
- Introduction of Fujikura PANDA fiber and Basis of polarization-maintaining fiber, [0014]

Patentkrav**1.** Polariseringsopretholdende optisk fiber (20), omfattende:

en kerne (21);

5 et par af spændingspåførende dele (22) tilvejebragt på begge sider af kernen (21) og ved punktsymmetriske positioner i forhold til kernen (21);
og

en beklædning (23) der omgiver kernen (21) og de spændingspåførende dele (22), hvor

10 en diameter af beklædningen (23) er 125 μm , en diameter af hver af de spændingspåførende dele (22) er 33 til 37 μm , en afstand mellem parret af spændingspåførende dele (22) er 8,6 til 15,4 μm , og en grænsebølgelængde er mindre end eller lig med 400 nm;

kendetegnet ved, at:

brydningsindekset af kernen (21) er 1,456 til 1,458;

15 beklædningen (23) omfatter en første beklædning (23A), som direkte omgiver kernen (21) og de spændingspåførende dele (22) og er dannet af fluordoteret silikaglas og en anden beklædning (23B), som er tilvejebragt på en udvendig periferi af den første beklædning (23A) og er dannet af ren silikaglas;

20 en relativ brydningsindeksforskel mellem kernen (21) og den første beklædning (23A) er 0,35 til 0,45 %;

den første beklædning har brydningsindeks på 1,450 til 1,452;

den anden beklædning har en tykkelse på 15 til 32,5 μm og brydningsindeks på 1,456 til 1,458, og

25 efter påføring af en bøjning på 60 mm i diameter 10 gange, en tabsøgning i et bølgelængdeområde på 400 til 680 nm er mindre end eller lig med 0,1 dB og polariseringskrydstale i bølgelængdeområdet af 400 til 680 nm er mindre end eller lig med -30 dB.

30 **2.** Den polariseringsopretholdende optiske fiber (20) ifølge krav 1, hvor afstanden mellem parret af spændingspåførende dele (22) er 10 til 14 μm .

DRAWINGS

FIG. 1




FIG. 2




FIG. 3

