



HU000031793T2

(19) **HU**(11) Lajstromszám: **E 031 793**(13) **T2****MAGYARORSZÁG****Szellemi Tulajdon Nemzeti Hivatala**

EURÓPAI SZABADALOM SZÖVEGÉNEK FORDÍTÁSA

(21) Magyar ügyszám: **E 10 812082**(22) A bejelentés napja: **2010. 08. 31.**

(96) Az európai bejelentés bejelentési száma:

EP 20100812082

(97) Az európai bejelentés közzétételi adatai:

EP 2474306 A1 **2012. 07. 11.**

(97) Az európai szabadalom megadásának meghirdetési adatai:

EP 2474306 B1 **2016. 11. 09.**(51) Int. Cl.: **A61K 9/10** (2006.01)**A61K 31/7088** (2006.01)**A61K 47/44** (2006.01)**A61K 38/00** (2006.01)**A61K 47/34** (2006.01)**A61K 9/16** (2006.01)**A61K 31/715** (2006.01)

(86) A nemzetközi (PCT) bejelentési szám:

PCT/JP 10/064816

(87) A nemzetközi közzétételi szám:

WO 11025036

(30) Elsőbbségi adatok:

2009200681**2009. 08. 31.****JP**

(72) Feltaláló(k):

KATO, Yasuki, Kashiwa-shi Chiba 277-0882 (JP)**ISHII, Atsushi, Kashiwa-shi Chiba 277-0882 (JP)**

(73) Jogosult(ak):

NanoCarrier Co., Ltd., 226-39 Wakashiba**Kashiwa Chiba 277-0871 (JP)**

(74) Képviselő:

Gödölle, Kékes, Mészáros & Szabó**Szabadalmi és Védjegy Iroda, Budapest**

(54)

Részecskekompozíció és illet tartalmazó gyógyszerkészítmény

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmat az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 474 306 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:

09.11.2016 Bulletin 2016/45

(21) Application number: **10812082.5**

(22) Date of filing: **31.08.2010**

(51) Int Cl.:

A61K 9/10 ^(2006.01) **A61K 9/16** ^(2006.01)
A61K 31/7088 ^(2006.01) **A61K 31/715** ^(2006.01)
A61K 38/00 ^(2006.01) **A61K 47/34** ^(2006.01)
A61K 47/44 ^(2006.01)

(86) International application number:

PCT/JP2010/064816

(87) International publication number:

WO 2011/025036 (03.03.2011 Gazette 2011/09)

(54) **PARTICLE COMPOSITION AND MEDICINAL COMPOSITION COMPRISING SAME**

PARTIKELZUSAMMENSETZUNG UND MEDIZINISCHE VORRICHTUNG DAMIT

**COMPOSITION PARTICULAIRE ET COMPOSITION MÉDICAMENTEUSE COMPRENANT
CELLE-CI**

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO SE SI SK SM TR**

(30) Priority: **31.08.2009 JP 2009200681**

(43) Date of publication of application:

11.07.2012 Bulletin 2012/28

(73) Proprietor: **NanoCarrier Co., Ltd.**

226-39 Wakashiba

Kashiwa

Chiba 277-0871 (JP)

(72) Inventors:

• **KATO, Yasuki**

Kashiwa-shi

Chiba 277-0882 (JP)

• **ISHII, Atsushi**

Kashiwa-shi

Chiba 277-0882 (JP)

(74) Representative: **Thurston, Joanna et al**

Withers & Rogers LLP

4 More London Riverside

London SE1 2AU (GB)

(56) References cited:

EP-A1- 1 230 934 WO-A1-99/33489
WO-A1-2005/026372 WO-A1-2006/002538
WO-A1-2006/085664 WO-A1-2007/043486
WO-A1-2007/136134 WO-A1-2007/136134
WO-A1-2008/010341 WO-A1-2008/047948
WO-A1-2008/047948 WO-A1-2008/143339
WO-A2-2005/007196 WO-A2-2008/042973
WO-A2-2008/042973 JP-A- 6 107 565
JP-A- 2001 510 786 JP-A- 2005 519 063
JP-A- 2006 056 864 JP-A- 2006 056 864
JP-A- 2008 504 827

- **READ M L ET AL: "A versatile reducible polycation-based system for efficient delivery of a broad range of nucleic acids", NUCLEIC ACIDS RESEARCH, INFORMATION RETRIEVAL LTD, vol. 33, no. 9, 1 May 2005 (2005-05-01), pages e86-1, XP002447464, ISSN: 0305-1048, DOI: 10.1093/NAR/GNI085 [retrieved on 2005-05-24]**

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

TECHNICAL FIELD

5 **[0001]** The present invention relates to a particulate composition (such as a polymeric micelle) applicable for a carrier of a drug delivery system (DDS), and to a pharmaceutical composition (such as a polymeric micelle formulation) containing a drug encapsulated in the particulate composition.

BACKGROUND ART

10 **[0002]** Biotechnology-based pharmaceuticals, which utilize biomacromolecules such as proteins and nucleic acids, are more susceptible to enzymatic degradation or immune elimination, compared with conventional pharmaceuticals based on low-molecular compounds. Patent Documents 1 to 4 disclose a DDS which contains a biomacromolecule within a liposome made of a lipid bilayer membrane, which intends to improve the *in vivo* stability of biotechnology-based
15 pharmaceuticals.

PRIOR ART REFERENCES

PATENT DOCUMENTS

20 **[0003]**

Patent Document 1: WO2001/034115
 Patent Document 2: WO1998/5863
 25 Patent Document 3: WO2005/09238
 Patent Document 4: JP2001-504093W
 Patent Document 5: WO2006/002538 A1 discloses siRNA molecules and methods of using such siRNA molecules to modulate an immune response and to silence expression of a target gene.
 Patent Document 6: JP2006-056864 A discloses in-vivo stable polymer-modified liposomes for carrying hydrophobic
30 and hydrophilic compounds.
 Patent Document 7: WO2005/00719 discloses compositions and methods for silencing gene expression by delivering nucleic acid-lipid particles comprising siRNA molecules to a cell.

DISCLOSURE OF THE INVENTION

35 PROBLEMS TO BE SOLVED BY THE INVENTION

[0004] The conventional DDSs described in Patent Documents 1 to 3, in which the biomacromolecule drug is protected with a lipid bilayer membrane, are superior in *in vivo* stability of the drug, but are inferior in drug releasability from the carrier. In addition, due to the large particle size and also due to the electrical charge of the lipid which constitutes the
40 lipid bilayer membrane, the conventional DDSs are likely to be captured by the reticuloendothelial system, such as the lungs, liver and spleen, and thereby removed from blood before reaching to the administration target. The DDS described in Patent Document 4 is a "stealth" liposome and prevented from being captured by the reticuloendothelial system, but tends to have difficulty in releasing the drug from the carrier.

45 **[0005]** A polymeric micelle formed with a block copolymer unit having a hydrophobic polymer-chain segment and a hydrophilic polymer-chain segment can be used as a DDS carrier, and the resultant DDS can be much smaller in particle size (e.g., the average particle size can be 100nm or smaller) than the conventional DDSs using a liposome. However, such a DDS using a polymeric micelle as the carrier still has difficulty, in some cases, in delivering the drug to the administration target, due to lack of sufficient encapsulation force to maintain the biomacromolecule within the DDS
50 particle as shown in the Comparative Examples, which will be explained later. In addition, such a DDS may sometimes cause the drug to disengage from the carrier during the storage period after production.

MEANS TO SOLVE THE PROBLEMS

55 **[0006]** The present invention provides a particulate composition containing: a block copolymer unit having a hydrophobic polymer-chain segment and a hydrophilic polymer-chain segment, a plurality of the block copolymer units being arranged radially with the hydrophobic polymer-chain segments radially inside and the hydrophilic polymer-chain segments radially outside; and a charged lipid which carries a charge opposite to the charge of a drug to be encapsulated

in the composition such that the drug is to be retained within the particle via electrostatic binding with the charged lipid, the charged lipid being attracted to the hydrophobic polymer-chain segment, whereby the outer surface of the particle is prevented from being charged to attract a substance which has a charge opposite to the charge of the charged lipid wherein the particulate composition is applied to a drug selected from the group consisting of proteins and nucleic acids and wherein the charged lipids are not arranged contiguously to one another along the circumference of the particulate composition, but are arranged to intervene between the adjacent block copolymer units along the circumference of the particulate composition, whereby the adjacent charged lipids along the circumference of the particulate composition are separated by the block copolymer units and prevented from being in contact with one another.

[0007] In another aspect, the present invention provides a pharmaceutical composition containing the particulate composition and a drug which carries a charge opposite to the charge of the charged lipid and is encapsulated in the particulate composition. The invention is as described in the claims.

EFFECTS OF THE INVENTION

[0008] The present invention provides a drug carrier which has improved drug encapsulation stability and is prevented from adhesion of a biomolecule onto the carrier surface, which may obstruct delivery of a drug to a desired target, being suitable for DDS, as well as a pharmaceutical composition using the drug carrier. The drug carrier and pharmaceutical composition can deliver the drug more reliably than the conventional DDSs.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009]

FIGs. 1(a) to 1(c) illustrate structural examples for a particulate composition and a pharmaceutical composition according to the present invention;

FIG. 2 is a graph showing the relationship between the absolute values of zeta potentials of particulate compositions measured in Evaluation 1b and the aggregability of the particulate compositions in blood measured in Evaluation 1c;

FIG. 3 is a graph showing fluorescence intensities of albumin-FITC measured in Evaluation 2b;

FIG. 4 illustrates the results of electrophoresis in Evaluation 5a;

FIG. 5 indicates graphs for explaining anti-cancer activities of particulate compositions determined in Evaluation 5c;

FIG. 6 is a graph for explaining the aggregability of particulate compositions in serum determined in Evaluation 5d;

FIG. 7 is a graph showing the relationship between the absolute values of zeta potentials of particulate compositions measured in Evaluation 5b and the aggregability of particulate compositions in blood measured in Evaluation 5d; and

FIG. 8 indicates graphs for explaining drug migration to organs determined in Evaluation 5f.

DESCRIPTION OF EMBODIMENTS

[0010] FIG. 1(a) illustrates a structural example of a particulate composition according to the present invention (hereinafter also referred to as "particulate composition"), and FIG. 1(b) is a partial enlarged view thereof. The particulate composition 1 contains a block copolymer unit 2 and a charged lipid 3. The block copolymer unit 2 has a hydrophilic polymer-chain segment 2a and a hydrophobic polymer-chain segment 2b. The block copolymer units 2 are arranged radially in the particulate composition 1 with the hydrophobic polymer-chain segments 2b radially inside and the hydrophilic polymer-chain segments 2a radially outside. The charged lipid 3 carries a charge opposite to the charge of a drug to be encapsulated, and is being attracted to the hydrophobic polymer-chain segments 2b. FIG. 1(c) illustrates a structural example of a particulate pharmaceutical composition according to the present invention (hereinafter also referred to as "pharmaceutical composition"). A pharmaceutical composition 1' includes a particulate composition 1 and a drug 4, which carries a charge opposite to the charge of a charged lipid 3 and is retained within the particulate composition 1 via electrostatic binding with the charged lipid 3.

[0011] The term "charged lipid" as used herein means either an anionic lipid, which has more negative charges than positive charges in an aqueous medium, or a cationic lipid, which has more positive charges than negative charges in an aqueous medium. Amphoteric lipids, which have both cationic groups and anionic groups, are judged by the aforementioned criteria.

[0012] The charged lipid 3 retains the drug 4 to be encapsulated within the particulate composition 1 via electrostatic binding. The charged lipid 3 only needs to have an electrical charge opposite to the charge of the drug 4 to be encapsulated at least under storage environment of the pharmaceutical composition 1' formed from the particulate composition 1. This will allow the drug 4 to be retained more securely in the particulate composition 1 during the storage period after production. The charged lipid 3 and the drug 4 should preferably have charges opposite to each other even under physiological environments, such as in blood (e.g., pH 7.4). This will enable more secure prevention of the drug 4 from disengaging

from the particulate composition 1 during transport to the administration target.

[0013] The charged lipids 3 are being attracted to the hydrophobic polymer-chain segments 2b by the following mechanism. The particulate composition 1 is formed by a method including the step of suspending the block copolymer units 2 and the charged lipids 3 into an aqueous solution. The hydrophobic polymer-chain segments 2b of the block copolymer units 2 cannot disperse, but form an aggregate, in the aqueous solution due to their hydrophobicity, while the hydrophilic polymer-chain segments 2a can disperse, and move freely, in the aqueous solution. Thus, the block copolymer units 2 are arranged radially in the aqueous solution, with the hydrophobic polymer-chain segments 2b radially inside and the hydrophilic polymer-chain segments 2a radially outside. The charged lipids 3 are being attracted to the hydrophobic polymer-chain segments 2b, since they are highly hydrophobic and have higher affinity for the hydrophobic polymer-chain segments 2b than for water or the hydrophilic polymer-chain segments 2a. Thus, the charged lipids 3 are arranged away from the outer surface of the particulate composition 1. Thus, the outer surfaces of the particulate composition 1 and the pharmaceutical composition 1' are prevented from being charged to attract a substance which has a charge opposite to that of the charged lipids 3 (e.g., blood proteins).

[0014] When the charged lipids 3 and the block copolymer units 2 are suspended in the aqueous solution, they form particles in a mixture state, so that the charged lipids 3 adjacent to one another along the circumference of the particulate composition 1 are not contiguous with one another, but intervene between the adjacent block copolymer units 2 along the circumference of the particulate composition 1, as shown in FIG. 1 (b). Thus, the adjacent charged lipids 3 along the circumference of the particulate composition 1 are separated by the block copolymer units 2, and prevented from being in contact with one another. Accordingly, in the particulate composition 1, gaps G sufficiently large to accommodate block copolymer units 2 are formed in between the adjacent charged lipids 3 along the circumference of the particulate composition 1. In other words, gaps G are formed in between the adjacent charged lipids 3, and the block copolymer units 2 are positioned within the gaps G. The binding force between the charged lipid 3 and the block copolymer unit 2 is smaller than that between the charged lipids 3. Therefore, compared to the conventional DDSs (liposomes) in which the lipids are arranged contiguously to each other along the circumference of the particle, the particulate composition 1 can disintegrate its particular shape easily due to disengagement of the charged lipids 3. As a result, the drug 4 encapsulated in the particles (carriers) is prevented from being retained excessively. On the other hand, stealth liposomes, represented by the DDSs described in Patent Document 4, are prepared by first forming liposomes with lipid bilayers and then attaching diblock copolymers to the surface of the liposomes, whereby the adjacent lipids along the circumference of the particle are not separated from one another by, e.g., the block copolymers, but are arranged contiguously to one another.

[0015] The state in which the outer surface of the particulate composition 1 or the pharmaceutical composition 1' is prevented from being charged to attract a charged substance can be confirmed based on, i.e., whether the absolute value of zeta potential of the particulate composition 1 or the pharmaceutical composition 1' is lower than a predetermined value. Specifically, the absolute value of zeta potential of the pharmaceutical composition 1' should preferably be 10mV or lower, e.g. 5mV or lower, or 3mV or lower, more preferably 2mV or lower, still more preferably 1mV or lower. Incorporation of the drug 4 into the particulate composition 1 tends to reduce the absolute value of zeta potential of the resultant pharmaceutical composition 1' to be lower than the absolute value of zeta potential of the particulate composition 1. Accordingly, the absolute value of zeta potential of the particulate composition 1 should preferably be 15mV or lower, e.g. 12mV or lower, or 6mV or lower, more preferably 3mV or lower, preferably 2mV or lower, still more preferably 1mV or lower. The zeta potential can be measured by adding the particulate composition 1 or the pharmaceutical composition 1' to 10mM HEPES buffer solution (pH 7.4) in such an amount that the ratio of the total charged lipids 3 to the buffer solution is 0.1mg/mL.

[0016] Note that the absolute values of zeta potential mentioned herein may be rounded off to the nearest whole numbers. For example, the absolute value of zeta potential of "2mV or lower" should cover values of less than 2.5mV.

[0017] As demonstrated in the Examples below, aggregation of the particulate composition 1 or the pharmaceutical composition 1' in blood can be prevented by controlling the absolute value of zeta potential of the particulate composition 1 or the pharmaceutical composition 1' to a low level. Specifically, if the absolute value of zeta potential of the particulate composition 1 is controlled to be lower than a predetermined value, aggregation in blood can be prevented to such a degree that the aggregability of the particulate composition 1 in blood should preferably be, e.g., 0.2 or lower, or 0.18 or lower, or 0.15 or lower, more preferably 0.1 or lower, or in some cases 0.05 or lower. Alternatively, by controlling the absolute value of zeta potential of the pharmaceutical composition 1' to be lower than a predetermined value, aggregation in blood can be prevented to such a degree that the aggregability of the pharmaceutical composition 1' in blood should preferably be, e.g., 0.2 or lower, or 0.16 or lower, more preferably 0.1 or lower, or in some cases 0.05 or lower.

[0018] The aggregability in blood can be calculated as follows:

- (i) Sample A is prepared by adding an object composition (particulate composition 1 or pharmaceutical composition 1') to 10mM HEPES buffer solution (pH 7.4) in such an amount that the ratio of the total charged lipids 3 to the buffer solution is 2.2mg/mL, followed by addition of 9mL of FBS (fetal bovine serum) per mL of the buffer solution.

(ii) Sample B is prepared in a similar manner to step (i) above, except that the FBS (fetal bovine serum) is replaced with 10mM HEPES buffer solution (pH 7.4).

(iii) Samples A and B are let stand at 37°C for 24 hours, after which the absorbance at a wavelength of 700nm is measured for each sample.

(iv) The "absorbance for Sample B" is subtracted from the "absorbance for Sample A," and the resultant value is determined as the aggregability in blood. The smaller the value is, the less likely to aggregate in blood the object composition is.

[0019] The ratio by weight of the amount of the block copolymer units 2 to the amount of the charged lipids 3 should preferably be 1.0 or higher, more preferably 1.5 or higher, still more preferably 2.0 or higher, and preferably 50 or lower, more preferably 20 or lower, still more preferably 10 or lower. The higher the ratio, the lower the absolute value of zeta potential of the particulate composition 1 or the pharmaceutical composition 1'. Drugs 4 can be encapsulated more actively into the particle as the ratio of the charged lipids 3 becomes higher, for which reason the ratio should preferably be limited to 50 or lower, as mentioned above.


[0020] The lipids 3 may be a simple lipid, a conjugated lipid or a derived lipid. Examples thereof include phospholipids, glycolipids, glucosphingolipids, sphingoids and sterols. Specifically, examples of cationic lipids include 1,2-dioleoyl-3-trimethylammonio propane (DOTAP), N-(2,3-dioleoyloxypropyl)-N,N,N-trimethylammonium chloride (DOTMA), 2,3-dioleoyloxy-N-[2-(sperminecarboxamide)ethyl]-N,N-dimethyl-1-propanaminium trifluoroacetate (DOSPA), 1,2-dimyristyloxypropyl-3-dimethylhydroxyethylammonium bromide (DMRIE), 1,2-dioleoyloxypropyl-3-diethylhydroxyethylammonium bromide (DORIE), and 3β-[N-(N',N'-dimethylaminoethyl)carbamoyl]cholesterol (DC-Chol). Examples of anionic lipids include cardiolipin, diacylphosphatidylserine, diacylphosphatidic acid, N-succinyl phosphatidylethanolamine (N-succinyl PE), phosphatidic acid, phosphatidylinositol, phosphatidylglycerol, phosphatidylethylene glycol, and cholesterol succinate.

[0021] The hydrophilic polymer-chain segment 2a should preferably be a water-soluble polymer-chain segment made of polyethyleneglycol or polyoxyethylene. The molecular weight of the hydrophilic polymer-chain segment 2a should preferably be 2,500Da or higher, more preferably 5,000Da or higher, still more preferably 8,000Da or higher, and preferably 200,000Da or lower, more preferably 20,000Da or lower, still more preferably 15,000Da or lower. The hydrophobic polymer-chain segment 2b should preferably be a segment derived from a polyamino acid chain. The number of repeating units in the hydrophobic polymer-chain segment 2b should preferably be 10 or higher, more preferably 20 or higher, and preferably 200 or lower, more preferably 100 or lower, still more preferably 60 or lower. In order to reduce the absolute value of zeta potential of the particulate composition 1, i.e., to reduce the surface charge of the pharmaceutical composition 1' (to be closer to neutral), the size of the hydrophilic polymer-chain segment 2a (molecular weight) should preferably be larger than the size of the hydrophobic polymer-chain segment 2b (the number of repeating units) in the block copolymer unit 2.


[0022] The hydrophilic polymer-chain segment 2a and the hydrophobic polymer-chain segment 2b may also have a charged substituent such as an amino group and carboxy group, as long as the outer surface of the particulate composition 1 or the pharmaceutical composition 1' does not bear a charge which can attract a charged substance.

[0023] The hydrophilic polymer-chain segment 2a and the hydrophobic polymer-chain segment 2b can be linked to each other by covalently binding the termini of their main chains. Specifically, examples of the block copolymer unit 2 are the compounds represented by general formulae (I) and (II). The particulate composition 1 may contain two or more kinds of the block copolymer units 2.

[Formula 1]



[Formula 2]



[0024] In formulae (I) and (II),

R¹ and R³, independently of each other, is either hydrogen atom or a group represented by R⁸ (R⁹) CH(CH₂)_q-, where R⁸ and R⁹ (i) independently of each other, is hydrogen atom, C₁₋₆ alkoxy group, aryloxy group, aryl-C₁₋₃-oxy group, cyano group, carboxy group, amino group, C₁₋₆-alkoxy carbonyl group, C₂₋₇-acylamide group, tri-C₁₋₆-alkyl siloxy group, siloxy group, or silylamino group, (ii) together with each other, form ethylene dioxy group or propylene dioxy group, which are either unsubstituted or substituted with C₁₋₃-alkyl group, or (iii) together with CH group to which they are bound, form formyl group, and q is an integer of from 0 to 10;

R² is hydrogen atom, saturated or unsaturated C₁-C₂₉ aliphatic carbonyl group, or arylcarbonyl group;

R⁴ is hydroxy group, saturated or unsaturated C₁-C₃₀-aliphatic oxy group, or aryl-lower-alkyloxy group;

R⁵ is -O- or -NH-;

R⁶ is hydrogen atom, phenyl group, benzyl group, -(CH₂)₄-phenyl group, C₄-C₁₆ alkyl group which is either unsubstituted or substituted with amino group or carbonyl group, or sterol derivative residue;

R⁷ is methylene group;

n is an integer of from 55 to 4,600;

x is an integer of from 10 to 200;

m is an integer of from 0 to 200, wherein when m is one or more, the (COCHNH) units and the (COR⁷CHNH) unit(s) may be arranged in a random order in the block copolymer, and when m is two or more, R⁶ is selected for each amino acid unit independently of each other and may be arranged in a random order in the block copolymer, provided that hydrogen atoms must not exceed 75% of R⁶;

y is 1 or 2;

L¹ is a linking group selected from -NH-, -O-, -O-Z-NH-, -CO-, -CH₂-, and -O-Z-S-Z-NH-, where Z, independently of each other, is C₁-C₆ alkylene group; and

L² is a linking group selected from -OCO-Z-CO- and -NHCO-Z-CO-, where Z is C₁-C₆ alkylene group.

[0025] In formulae (I) and (II),

n is an integer of preferably 110 or larger, more preferably 180 or larger, and preferably 460 or smaller, more preferably 340 or smaller;

x is an integer of preferably 20 or larger, and preferably 100 or smaller, more preferably 60 or smaller; and

m is an integer of preferably 100 or smaller, more preferably 60 or smaller.

[0026] The block copolymer unit 2 may preferably be an anionic polymer. Use of an anionic polymer as the block copolymer unit 2 together with a cationic lipid as the charged lipid 3 makes it easier to control the absolute value of zeta potential of the particulate composition 1 and the pharmaceutical composition 1' at 3mV or less, preferably 2mV or less, and more preferably 1mV or less. Also, as demonstrated in the Examples below, use of an anionic polymer as the block copolymer unit 2 makes it possible to prevent aggregation in blood more markedly, compared to the case where a neutral polymer having a similar absolute value of zeta potential is used. As used herein, polymers which have more negative charges than positive charges in an aqueous medium with a physiological pH (e.g., pH7.4) are regarded as anionic, polymers which have more positive charges than negative charges in the aqueous medium are regarded as cationic, and polymers which have substantially equal amounts of positive charges and negative charges in the aqueous medium are regarded as neutral.

[0027] Preferred examples of the anionic block copolymer unit 2 are compounds represented by general formulae (I) and (II) in which R⁵ is -O-, R⁶ is benzyl group, -(CH₂)₄-phenyl group, or C₄-C₁₆ alkyl group which is either unsubstituted or substituted with amino group or carbonyl group.

[0028] The block copolymer unit 2 can be formed, e.g., by coupling a polymer having a hydrophilic polymer chain with a polymer having a polyamino acid chain in a known manner, optionally after purifying, if necessary, the polymers to restrict the molecular weight distribution. The block copolymer unit 2 according to formula (I) also can be formed, e.g., by the steps of: performing anion living polymerization using an initiator which can add R¹ to form a polyethyleneglycol chain; introducing an amino group to the growing end; and polymerizing, at the amino end, an N-carboxy anhydride (NCA) of a protected amino acid, such as Nε-Z-L-lysine, β-benzyl-L-aspartate, or γ-benzyl-L-glutamate.

[0029] The particulate composition 1 can be formed, e.g., as follows. First, a block copolymer unit 2 and a charged lipid 3, optionally together with a neutral lipid, are fully dissolved or dispersed into a forming solution containing an organic solvent, after which the organic solvent is removed by evaporation. Examples of organic solvents include acetone, dichloromethane, dimethylformamide, dimethylsulfoxide, acetonitrile, tetrahydrofuran, and methanol. The forming solution may contain two or more organic solvents, and also may contain a small amount of water. The resultant solid or paste is combined with water or an aqueous solution containing an additive such as an appropriate salt or stabilizer, followed by stirring to disperse the block copolymer unit and the lipid(s). The resultant product is further dispersed/pulverized by means of, e.g., ultrasonic irradiation, high-pressure emulsification or extruder to thereby form the particulate composition 1.

[0030] The present invention can provide a pharmaceutical composition 1' having the above particulate composition 1 and a drug 4 carrying a charge opposite to the charge of the charged lipid 3 contained in the particulate composition 1. The drug 4 is retained in the particulate composition 1 via electrostatic binding with the charged lipid 3. Thus, the binding between the charged lipid 3 and the drug 4 is reversible, and does not involve any chemical structural change. The drug 4 can be encapsulated into the carrier composition either by adding the drug 4 to the forming solution in the production of the carrier composition, or by adding the carrier composition to a solution of the drug 4.

[0031] Examples of the drug 4 include: anionic compounds, which have more negative charges than positive charges in an aqueous medium with a physiological pH (e.g., pH7.4); and cationic compounds, which have more positive charges than negative charges in the aqueous medium. The compounds should preferably be macromolecular compounds.

[0032] Examples of the macromolecular compounds that can be used as the drug 4 include peptides, proteins, sugar chains, and nucleic acids.

[0033] In order to prevent the drug 4 either from disengaging from the particulate composition 1 in blood too early or from being encapsulated in the particulate composition 1 for too long a time, the charge ratio between the charged lipid 3 and the drug 4 in the pharmaceutical composition 1' should preferably be controlled to be within a particular range. When the drug 4 is, e.g., a nucleic acid, the charge ratio can be defined as [the mol concentration of cationic groups of the charged lipid 3 contained in the particulate composition]/[the mol concentration of phosphoric groups in the nucleic acid]. On the other hand, when the drug is a compound which has both anionic and cationic groups, e.g., a protein, the charge ratio can be defined as [the mol concentration of charged groups of the charged lipid contained in the particulate composition]/([the mol concentration of groups in the drug which are charged oppositely to the charged lipid] - [the mol concentration of groups in the drug which are charged similarly to the charged lipid]). The charge ratio should preferably be 0.5 or higher, more preferably one or higher, still more preferably 2 or higher, and preferably 50 or lower, more preferably 20 or lower, still more preferably 10 or lower.

[0034] The average particle sizes of the particulate composition 1 and the pharmaceutical composition 1' should preferably be 10nm or larger, more preferably 30nm or larger, and preferably 300nm or smaller, more preferably 200nm or smaller.

EXAMPLES

[0035] The present invention will be explained in more detail below by referring to Examples. Measurement of the average particle sizes of particulate compositions by means of dynamic light scattering (DLS) mentioned in the following explanation was carried out using the light-scattering analyzer Zetasizer Nano ZS (Malvern


Instruments).

[Example Group 1: Particulate Composition]

[Example 1-1]

[0037] Five grams of α -methoxy- ω -amino-polyethyleneglycol (hereinafter also referred to as "PEG") having a weight-average molecular weight (Mw) of 10000 (Manufactured by NOF Corp.) was dissolved into 50mL of dimethyl sulfoxide, which was reacted with 5.5g (42 parts with respect to polyethyleneglycol) of N-carboxy anhydride (NCA) of γ -benzyl-L-glutamate (hereinafter also referred to as "PBLG") at 40°C for 24 hours. The reaction solution was dropped into 1L of a mixture solvent of hexane and ethyl acetate (volume ratio 1:1) to cause precipitation of a polymer, which was recovered by filtration under reduced pressure and then dried to yield 8.6g of a solid product. This product was dissolved into 86mL of DMF, with which 432 μ L of acetic anhydride was mixed and reacted at 40°C for 24 hours. The reaction solution was dropped into 1L of a mixture solvent of hexane and ethyl acetate (volume ratio 1:1) to cause precipitation of a polymer, which was recovered by filtration under reduced pressure and then further dried to yield 8.1g of polyethyleneglycol-poly(γ -benzyl-L-glutamate)-Ac block copolymer (hereinafter also referred to as "PEG-PBLG"), which is a neutral polymer. The structural formula of PEG-PBLG is shown below. ¹H-NMR analysis revealed that the degree of polymerization of the PBLG block was 40.

[Formula 3]



[0038] Four mL of the PEG-PBLG solution in chloroform (50mg/mL) was mixed with 0.5mL of 1,2-dioleoyl-3-trimethylammonio propane (hereinafter also referred to as "DOTAP") (Avant Polar Lipid) solution in chloroform (40mg/mL), the solvent was evaporated on a rotary evaporator, and was further dried overnight under reduced pressure. To the resulting solid, 10mL of 20mM HEPES buffer (pH7.4) was added, and stirred at room temperature for 3 hours to suspend the solid. The suspension was pulverized by ultrasonic irradiation (130W, 1 second pulse, 20 minutes). The solution was passed through a 0.2 μ m filter (Millex GP, Millipore) to thereby yield the particulate composition 1. The particulate com-

position 1 is formed with the hydrophobic polymer-chain segments arranged radially inside and the hydrophilic polymer-chain segments arranged radially outside. The particulate compositions 2 to 6 described below are also in a similar state.

[Example 1-2]

[0039] The particulate composition 2 was prepared in the same manner as in Example 1-1 except that DOTAP was replaced with phosphatidic acid (anionic charged lipid; hereinafter also referred to as "PA").

[Example 1-3]

[0040] Four mL of the PEG-PBLG solution in chloroform (50mg/mL) prepared in Example 1-1 was mixed with 0.5mL of the DOTAP (cationic lipid; Avant Polar Lipid) solution in chloroform (40mg/mL) and 0.5mL of dioleoylphosphatidylethanolamine (hereinafter also referred to as "DOPE"; Avant Polar Lipid) (neutral lipid; Avant Polar Lipid) solution in chloroform (40mg/mL), the solvent was evaporated on a rotary evaporator, and was further dried overnight under reduced pressure. To the resulting solid, 5mL of 20mM HEPES buffer (pH7.4) was added, and stirred at room temperature for 3 hours to suspend the solid. The suspension was pulverized by ultrasonic irradiation (130W, 1 second pulse, 20 minutes). The solution was passed through a 0.2 μ m filter (Millex GP, Millipore) to thereby yield the particulate composition 3.

[Example 1-4]

[0041] The particulate composition 4 was prepared in the same manner as in Example 1-3 except that the amount of the chloroform solution of PEG-PBLG was changed to 2mL.

[Example 1-5]

[0042] The particulate composition 5 was prepared in the same manner as in Example 1-3 except that the amount of the chloroform solution of PEG-PBLG was changed to 1.33mL.


[Example 1-6]

[0043] The particulate composition 6 was prepared in the same manner as in Example 1-3 except that the amount of the chloroform solution of PEG-PBLG was changed to 1mL.

[Example 1-7]

[0044] PEG-PBLG prepared in Example 1-1 was alkali-treated to deprotect the benzyl groups of the glutamic acid side chains, whereby polyethyleneglycol/poly(L-glutamic acid) block copolymer (PEG-pGlu) was prepared. The glutamic acid side chains of PEG-pGlu were partially modified with octyl groups (C₈H₁₇) via condensation reaction using octyl alcohol to thereby yield PEG-pGlu(C8) polymer, which is an anionic polymer. ¹H-NMR analysis revealed that the number of octyl groups introduced was 33 per polymer. The structural formula of PEG-pGlu(C8) is shown below.

[Formula 4]


 R^{10} : H (7 units), C_8H_{17} (33 units)

[0045] One milliliter of a methanol solution (50mg/mL) of the resultant PEG-pGlu(C8) was mixed with 0.5mL of a methanol solution (40mg/mL) of DOTAP (cationic charged lipid; Avanti Polar Lipid) and 0.5mL of a methanol solution (40mg/mL) of dioleoylphosphatidylethanolamine (hereinafter also referred to as "DOPE") (neutral lipid; Avanti Polar Lipid), and then the solvent was evaporated on a rotary evaporator and dried overnight under reduced pressure. The resultant solid was combined with 2.5mL of 100mM sodium phosphate buffer (pH7.4), stirred for three hours at room temperature to obtain a suspension. The suspension was pulverized by ultrasonic irradiation (130W, 1 second pulse, 10 minutes), and passed through a 0.2 μ m filter (Millex GP, Millipore) to thereby yield the particulate composition 7.


[Example 1-8]

[0046] The particulate composition 8 was prepared in the same manner as in Example 1-7 except that the amount of the methanol solution (50mg/mL) of PEG-pGlu (C8) was changed to 0.5mL.

[Example 1-9]

[0047] PEG-PBLG prepared in Example 1-1 was alkali-treated to deprotect the benzyl groups of the glutamic acid side chains, whereby polyethyleneglycol/poly(L-glutamic acid) block copolymer (PEG-pGlu) was prepared. The glutamic acid side chains of PEG-pGlu were partially modified with benzyl groups (PhCH_2) via condensation reaction using benzyl alcohol to thereby yield PEG-pGlu(Bn), which is an anionic polymer. $^1\text{H-NMR}$ analysis revealed that the number of benzyl groups introduced was 34 per polymer. The structural formula of PEG-pGlu(Bn) is shown below.

[Formula 5]

R¹⁰ : H (6 units), PhCH₂ (34 units)

[0048] One milliliter of an acetone solution (50mg/mL) of PEG-pGlu(C8) was mixed with 0.5mL of a methanol solution (40mg/mL) of DOTAP (cationic charged lipid; Avanti Polar Lipid) and 0.5mL of a methanol solution (40mg/mL) of dioleoylphosphatidylethanolamine (hereinafter also referred to as "DOPE") (neutral lipid; Avanti Polar Lipid), and then the solvent was evaporated on a rotary evaporator and dried overnight under reduced pressure. The resultant solid was combined with 2.5mL of 100mM sodium phosphate buffer (pH7.4), stirred for three hours at room temperature to obtain a suspension. The suspension was pulverized by ultrasonic irradiation (130W, 1 second pulse, 10 minutes), and passed through a 0.2μm filter (Millex GP, Millipore) to thereby yield the particulate composition 9.

[Example 1-10]

[0049] The particulate composition 10 was prepared in the same manner as in Example 1-7 except that the amount of the methanol solution of PEG-pGlu (C8) was changed to 0.5mL.

[Comparative Example 1-1]

[0050] The comparative composition C1 was prepared in the same manner as in Example 1-1 except that no DOTAP was used.

[Comparative Example 1-2]

[0051] The comparative composition C2 was prepared in the same manner as in Example 1-3 except that no DOTAP was used.

[Comparative Example 1-3]

[0052] The comparative composition C3 was prepared in the same manner as in Example 1-3 except that no PEG-PBLG was used. The composition C3 does not contain a block copolymer but only contains DOTAP (charged lipid) and DOPE (neutral lipid).

[Evaluation 1a]

[0053] The average particle sizes of the particulate compositions 1 to 10 and the comparative particulate compositions C1 to C3 were measured using dynamic light scattering. The results are shown in Table 1.

[Table 1]

	Particulate composition	Weight ratio of polymer and lipid	Particle size (nm)
Example 1-1	1	PEG-PBLG:DOTAP=10:1	64.7
Example 1-2	2	PEG-PBLG:PA=10:1	73.2
Example 1-3	3	PEG-PBLG:DOTAP:DOPE=10:1:1	88.7
Example 1-4	4	PEG-PBLG:DOTAP:DOPE=5:1:1	90.3
Example 1-5	5	PEG-PBLG:DOTAP:DOPE=3.3:1:1	87.7
Example 1-6	6	PEG-PBLG:DOTAP:DOPE=2.5:1:1	88.1
Example 1-7	7	PEG-pGlu(C8):DOTAP:DOPE=2.5:1:1	167.7
Example 1-8	8	PEG-pGlu(C8):DOTAP:DOPE=1.25:1:1	158.1
Example 1-9	9	PEG-pGlu(Bn):DOTAP:DOPE=2.5:1:1	137.1
Example 1-10	10	PEG-pGlu(Bn):DOTAP:DOPE=1.25:1:1	158.1
Comparative Example 1-1	C1	-	94.2
Comparative Example 1-2	C2	PEG-PBLG:DOPE=10:1	87.3
Comparative Example 1-3	C3	DOTAP:DOPE=1:1	61.7

[Evaluation 1b]

[0054] To the particulate compositions 3 to 10 and the comparative particulate composition C3, 10mM HEPES buffer (pH 7.4) was added to prepare samples having a charged lipid concentration of 0.1mg/mL. Using the light-scattering analyzer Zetasizer Nano ZS (Malvern Instruments), the zeta potential for each sample (800 μ L) was determined. Disposable capillary cells (DTS1060, Malvern Instruments) were used for measurement, and the temperature during measurement was set at 25°C.

[Table 2]

Particulate composition	Weight ratio of polymer and lipid	Zeta potential (mV)
3	PEG-PBLG:DOTAP:DOPE=10:1:1	2.04
4	PEG-PBLG:DOTAP:DOPE=5:1:1	5.38
5	PEG-PBLG:DOTAP:DOPE=3.3:1:1	7.80
6	PEG-PBLG:DOTAP:DOPE=2.5:1:1	11.0
7	PEG-pGlu(C8):DOTAP:DOPE=2.5:1:1	1.63
8	PEG-pGlu(C8):DOTAP:DOPE=1.25:1:1	1.09
9	PEG-pGlu(Bn):DOTAP:DOPE=2.5:1:1	0.26
10	PEG-pGlu(Bn):DOTAP:DOPE=1.25:1:1	2.06
C3	DOTAP:DOPE=1:1	60.7

[0055] As shown in Table 2, the particulate compositions 3 to 10 had smaller absolute values of the zeta potential compared to the comparative particulate composition C3 which contained no block copolymer units. In the particulate compositions 3 to 10, the absolute values of the zeta potential became smaller as the weight ratio of the block copolymer units to the charged lipid became higher. This result means that the outer surface of the particulate compositions 3 to 10 were prevented from carrying charges resulting from the charged lipid. Assuming that the content of the charged lipids in the particulate compositions is constant, this result also means that the outer surface of the particles become less likely to carry charges resulting from the charged lipids, as the density of the area constituted by the hydrophilic polymer-chain segments becomes higher.

[Evaluation 1c: Evaluation of aggregation in blood]

[00556] Using the particulate compositions 3 to 10 and the comparative particulate composition C3 as the particulate compositions, the absorbance of the samples A and B prepared as described above at a wavelength of 700nm was determined using a plate reader (POWERSCAN HT, Dainippon Sumitomo Pharma Co., Ltd.) to calculate the aggregability in blood. When the calculated value was 0 or less, the aggregability in blood was set at 0. Table 3 shows this data and the absolute values of the zeta potential determined in Evaluation 1b, while FIG. 2 shows the relationship between the absolute value of zeta potential and the aggregability in blood.

[Table 3]

Particulate composition	Degree of aggregation in blood	Zeta potential (mV)
None	0.118	-
3	0.093	2.04
4	0.177	5.38
5	0.185	7.80
6	0.198	11.0
7	0	1.63
8	0	1.09
9	0.012	0.26
10	0.073	2.06
C3	0.375	60.7

[00557] As can be seen from FIG. 2 and Table 3, the aggregability in blood was low when the absolute value of zeta potential of the particulate composition was 10mV or lower, preferably 6mV or lower, more preferably 3mV or lower.

[Example Group 2: Albumin (pH 7.4)-encapsulating particulate composition]

[Example 2]

[00558] Albumin-FITC (Sigma Aldrich), bovine-derived albumin labeled with FITC (fluorescein 5-isothiocyanate), was dissolved in 20mM HEPES buffer (pH 7.4) to prepare a 10mg/mL solution. 0.2mL of this albumin solution was mixed with 0.5mL of the particulate composition 1 (containing 40mg/mL of PEG-PBLG and 4mg/mL of DOTAP) and 0.5mL of 20mM HEPES buffer (pH 7.4), and allowed to stand overnight at 4°C to thereby prepare an albumin-encapsulating particulate composition. The average particle size of the particulate composition measured by dynamic light scattering was 98.7nm. Albumin is a biomacromolecule that has an isoelectric point (PI) of about 4.8 and thus exhibits an anionic character at pH 7.4.

[Comparative Example 2-1]

[00559] An albumin-encapsulating particulate composition was prepared in the same manner as in Example 2 except that the particulate composition 1 was replaced with the particulate composition 2 (containing 40mg/mL of PEG-PBLG and 4mg/mL of PA). The average particle size of the particulate composition measured by dynamic light scattering was 91.6nm.

[Comparative Example 2-2]

[00600] An albumin-encapsulating particulate composition was prepared in the same manner as in Example 2 except that the particulate composition 1 was replaced with the comparative particulate composition C1 (containing 40mg/mL of PEG-PBLG). The average particle size of the particulate composition measured by dynamic light scattering was 118nm.

EP 2 474 306 B1

[Comparative Example 2-3]

[0061] An albumin-encapsulating particulate composition was prepared in the same manner as in Example 2 except that the particulate composition 1 was replaced with the comparative particulate composition C2 (containing 40mg/mL of PEG-PBLG and 2mg/mL of DOPE). The average particle size of the particulate composition measured by dynamic light scattering was 119nm.

[Evaluation 2a: Evaluation of retention of albumin by ultracentrifugation]

[0062] Forty μ L each of the solutions of the albumin-encapsulating particulate compositions prepared in Example 2 and Comparative Examples 2-1 to 2-3 mixed with 360 μ L of 10mM HEPES buffer (pH 7.4) was ultracentrifuged at 100,000xg, 4°C with an ultracentrifuge (Optima MAX Ultracentrifuge, Beckman Coulter). The fluorescence intensity of albumin-FITC in the supernatant was measured using a plate reader (POWERSCAN HT, manufactured by Dainippon Sumitomo Pharma Co., Ltd.) (excitation wavelength: 485nm; fluorescence wavelength: 528nm) to determine the retaining rate of albumin in the particulate composition based on the following equation (1).

$$(\text{Retaining rate}) = (A-B) \times 100 / A \quad \text{Equation (1)}$$

A: Fluorescence intensity of albumin-FITC added to the particulate composition
B: Fluorescence intensity of albumin-FITC in the supernatant

[Table 4]

	Particulate composition used	pH	Retaining rate of albumin-FITC (%)
Example 2	1	7.4	94.0
Comparative Example 2-1	2	7.4	0
Comparative Example 2-2	C1	7.4	0
Comparative Example 2-3	C2	7.4	0

[0063] As shown in Table 4, as much as 94% of albumin was retained in the particles after centrifugation in Example 2, whereas in Comparative Examples 2-1 to 2-3 almost no albumin was present in the particles after centrifugation.

[Evaluation 2b: Evaluation of albumin retention by gel filtration chromatography]

[0064] One mL each of the solutions of the albumin-encapsulating particles prepared in Example 2 and Comparative Example 2-1 was analyzed by gel filtration chromatography using Sepharose CL-4B. The eluate was collected in fractions, and the fluorescence intensity of the albumin-FITC contained in each fraction was measured using a plate reader (POWERSCAN HT, manufactured by Dainippon Sumitomo Pharma Co., Ltd.) (excitation wavelength: 485nm; fluorescence wavelength: 528nm). As the eluent, 10mM HEPES buffer (pH 7.4) to which 150mM sodium chloride has been added was used.

[0065] FIG. 3 is a graph showing the results of measurement. As shown in FIG. 3, elution peaks were observed in albumin per se and in fractions around fraction 20 in Comparative Example 2-1, whereas in Example 2 elution peaks were observed in fractions around fraction 10. This means that Example 2 has a better ability of retaining albumin in the particles compared to Comparative Example 2-1.

[Example Group 3: Dextran-encapsulating particulate composition]

[Example 3]

[0066] Dextran-FITC (Sigma Aldrich), which is FITC-labelled dextran with an average molecular weight of 20000, was dissolved in 20mM HEPES buffer (pH 7.4) to prepare a 10mg/mL solution. 0.2mL of this dextran solution was mixed with 0.5mL of the particulate composition 1 (containing 40mg/mL of PEG-PBLG and 4mg/mL of DOTAP) and 0.5mL of 20mM HEPES buffer (pH 7.4), and allowed to stand overnight at 4°C to thereby prepare a dextran-encapsulating particulate composition. The average particle size of the particulate composition measured by dynamic light scattering was 77.6nm.

Dextran is a biomacromolecule that exhibits an anionic character at pH 7.4.

[Comparative Example 3-1]

[0067] A dextran-encapsulating particulate composition was prepared in the same manner as in Example 3 except that the particulate composition 1 was replaced with the particulate composition 2 (containing 40mg/mL of PEG-PBLG and 4mg/mL of PA). The average particle size of the particulate composition measured by dynamic light scattering was 95.4nm.

[Comparative Example 3-2]

[0068] A dextran-encapsulating particulate composition was prepared in the same manner as in Example 3 except that the particulate composition 1 was replaced with the comparative particulate composition C1 (containing 40mg/mL of PEG-PBLG). The average particle size of the particulate composition measured by dynamic light scattering was 119nm.

[Comparative Example 3-3]

[0069] A dextran-encapsulating particulate composition was prepared in the same manner as in Example 3 except that the particulate composition 1 was replaced with the comparative particulate composition C2 (containing 40mg/mL of PEG-PBLG and 4mg/mL of DOPE). The average particle size of the particulate composition measured by dynamic light scattering was 119nm.

[Evaluation 3: Evaluation of retention of dextran by ultracentrifugation]

[0070] For 40μL each of the solutions of the dextran-encapsulating particulate compositions prepared in Example 3 and Comparative Examples 3-1 to 3-3, the fluorescence intensity of dextran-FITC in the supernatant was measured in a similar manner to the Evaluation 2a to determine the retaining rate of albumin of the particulate composition based on the following equation (2).

$$(\text{Retaining rate}) = (A' - B') \times 100 / A' \quad \text{Equation (2)}$$

A': Fluorescence intensity of dextran-FITC added to the particulate composition

B: Fluorescence intensity of dextran-FITC in the supernatant

[Table 5]

	Particulate composition used	pH	Retaining rate of dextran-FITC (%)
Example 3	1	7.4	38.67
Comparative Example 3-1	2	7.4	6.24
Comparative Example 3-2	C1	7.4	2.39
Comparative Example 3-3	C2	7.4	4.03

[0071] As shown in Table 5, nearly 40% of dextran was retained in the particles after centrifugation in Example 3, whereas in Comparative Example 3-1 and 3-3 almost no albumin was present in the particles after centrifugation.

[Example Group 4: Albumin (pH 3.3)-encapsulating particulate composition]

[Example 4]

[0072] Albumin (bovine-derived, Sigma Aldrich) was dissolved in 50mM glycine buffer (pH 3) to prepare a 1mg/mL solution. Two mL of this albumin solution was mixed with 0.5mL of the particulate composition 2 (containing 40mg/mL of PEG-PBLG and 4mg/mL of PA) and 0.5mL of 20mM HEPES buffer (pH 7.4), and allowed to stand overnight at 4°C, pH 3.3 to thereby prepare an albumin-encapsulating particulate composition. The average particle size of the particulate composition measured by dynamic light scattering was 78.8nm. Albumin exhibits a cationic character at pH 3.3.

[Comparative Example 4-1]

[0073] An albumin-encapsulating particulate composition was prepared in the same manner as in Example 4 except that the particulate composition 2 was replaced with the particulate composition 1 (containing 40mg/mL of PEG-PBLG and 4mg/mL of DOTAP). The average particle size of the particulate composition measured by dynamic light scattering was 95.1nm.

[Comparative Example 4-2]

[0074] An albumin-encapsulating particulate composition was prepared in the same manner as in Example 4 except that the particulate composition 2 was replaced with the comparative particulate composition C1 (containing 40mg/mL of PEG-PBLG). The average particle size of the particulate composition measured by dynamic light scattering was 115nm.

[Comparative Example 4-3]

[0075] An albumin-encapsulating particulate composition was prepared in the same manner as in Example 4 except that the particulate composition 2 was replaced with the comparative particulate composition C2 (containing 40mg/mL of PEG-PBLG and 1mg/mL of DOPE). The average particle size of the particulate composition measured by dynamic light scattering was 120nm.

[Evaluation 4: Evaluation of albumin retention by ultracentrifugation]

[0076] 400 μ L each of the solutions of the albumin-encapsulating particulate compositions prepared in Example 4 and Comparative Examples 4-1 to 4-3 was ultracentrifuged for 1 hour at 100,000xg, 4°C with an ultracentrifuge (Optima MAX Ultracentrifuge, Beckman Coulter). The concentration of albumin in the supernatant was determined using the protein determination kit BCA Protein Assay (Pierce) to determine the retaining rate of albumin in the particulate composition based on the following Equation (3).

$$(\text{Retaining rate}) = (A'' - B'') \times 100 / A'' \quad \text{Equation (3)}$$

A'': Concentration of albumin added to the particulate composition

B'': Concentration of albumin in the supernatant

[Table 6]

	Particulate composition used	pH	Retaining rate of albumin (%)
Example 4	2	3.3	94.75
Comparative Example 4-1	1	3.3	49.85
Comparative Example 4-2	C1	3.3	42.86
Comparative Example 4-3	C2	3.3	55.39

[0077] As shown in Table 6, over 94% of albumin was retained in the particles after centrifugation in Example 4, whereas in Comparative Examples 4-1 and 4-3 the retaining rate of albumin after centrifugation was not as high as in Example 4.

[Example Group 5: siRNA-encapsulating particulate composition]

[Example 5]

[0078] According to the procedure shown below, each particulate composition was subjected to encapsulation treatment of siRNA.

[0079] For the particulate compositions 3 to 6 and the comparative particulate composition C3, encapsulation treatment was carried out as follows. siRNA was dissolved into 10mM HEPES buffer (pH7.4) to prepare 20 μ M siRNA solution. To 250 μ L of this siRNA solution, 250 μ L of the particulate composition of which concentration has been adjusted so as to

satisfy the charge ratio (+/-) of interest was added, and after mixing, it was allowed to stand at 4°C for 2 hours to effect the encapsulation treatment of siRNA into the particulate composition. The "charge ratio (+/-)" indicates [the concentration of cationic groups of the cationic lipid contained in the particulate composition]/[the concentration of the phosphoric group in the nucleic acid]. For the particulate compositions 7 to 10, 279 μ L of the particulate composition was added to 100 μ L of 100 μ M aqueous siRNA solution, and after mixing, it was allowed to stand at 4°C for 2 hours to carry out the encapsulation treatment of siRNA into the particulate composition. The charge ratio (+/-) of the siRNA-encapsulating particulate composition thus prepared is 8. The siRNA-encapsulated particulate compositions prepared from the particulate compositions 7 to 10 were subjected to the freezing-drying operation in a conventional manner to form a stock, and then dissolved into water again, and subjected to the measurements explained below.

[0080] In each of the Examples described in the present description, siRNA was selected from the ones explained below, all of which are available from Nippon EGT Co., Ltd.

*siRNA(Luc): Designed to target a sea firefly luciferase gene, this siRNA is composed of a sense strand of 5'-CUUACGCUGAGUACUUCGAdTdT-3' (SEQ ID NO:1) and an antisense strand of 5'-UCGAAGUACUCAGCGUAAGdTdT-3' (SEQ ID NO:2) double-stranded in a conventional manner.

*siRNA(Plk1): Designed to target the human Plk1 (Polo-like kinase 1) gene, this siRNA is composed of a sense strand of 5'-CCAUAACGAGCUGCUUAAAdTdT-3' (SEQ ID NO:3) and an antisense strand of 5'-UUAAGCAGCUCGUAAUGGdTdT-3' (SEQ ID NO:4) double-stranded in a conventional manner. The Plk1 gene is a kinase which plays a role in the M phase of cell division. siRNA(Plk1) induces apoptosis when transfected into the cell.

*F-siRNA(Luc): This siRNA is formed in the same manner as siRNA(Luc) except that the antisense strand of SEQ ID NO:2 is Cy3-labeled at the 5' end (5'-Cy3-UCGAAGUACUCAGCGUAAGdTdT-3').

[Evaluation 5a]

[0081] In Evaluation 5a, the particulate composition 4 and the particulate composition 6 as the particulate composition and siRNA(Luc) as the siRNA were used, and were subjected to the siRNA-encapsulation treatment so as to obtain the charge ratio of 0.5, 1, 2, 4 and 8 in the method described in Example 5. The encapsulation rate of siRNA in each particulate composition after the encapsulation treatment was analyzed by electrophoresis as described below. Each particulate composition containing 100ng of siRNA was loaded to a polyacrylamide gel (Novex 20% TBE Gel, Invitrogen), which was then subjected to electrophoresis using the TBE solution as the electrophoresis buffer under the condition of an applied voltage of 100 V and a migration time of 1 hour. As the control, 100ng of siRNA was run simultaneously. After the electrophoresis was complete, the gel was stained with a development reagent SYBR (TM) Green II (Invitrogen), and imaged using an image analyzing instrument Molecular Imager FX (Bio-Rad).

[0082] FIG.4 shows the result of the electrophoresis in Evaluation 5a, in which a charge ratio of 0 means the control. As shown in FIG. 4, when the charge ratio was 2 or more, no bands derived from free siRNA were observed. This indicates that when the particulate composition 4 and the particulate composition 6 were used and the charge ratio was 2 or more, almost all siRNA could be encapsulated into the particulate compositions. Since the siRNA-encapsulated particulate compositions have a smaller degree of migration in electrophoresis compared to siRNA, bands derived from free siRNA cannot be detected in the corresponding migration lanes when siRNA is appropriately encapsulated.

[Evaluation 5b]

[0083] In Evaluation 5b, the particulate compositions 3 to 10 and the comparative particulate composition C3 as the particulate composition and siRNA(Luc) as the siRNA were used, and were subjected to the encapsulation treatment so as to obtain the charge ratio of 8 in the method described in Example 5. To the particulate compositions after the encapsulation treatment, 10mM HEPES buffer (pH 7.4) was added to adjust the concentration of the charged lipid at 0.1mg/mL. Using the light-scattering analyzer Zetasizer Nano ZS (Malvern Instruments), the zeta potential for these samples (800 μ L) was determined. In the measurement, disposable capillary cells (DTS1060, Malvern Instruments) were used, and the temperature during measurement was set at 25°C.

[Table 7]

Particulate composition used	Charge ratio (+/-)	Zeta potential (mV)	Zeta potential before treatment (mV)
3	8	1.93	2.04
4	8	2.63	5.38
5	8	4.67	7.80

(continued)

Particulate composition used	Charge ratio (+/-)	Zeta potential (mV)	Zeta potential before treatment (mV)
6	8	6.17	11.0
7	8	0.37	1.63
8	8	0.95	1.09
9	8	0.567	0.26
10	8	0.96	2.06
C3	8	55.1	60.7

[0084] As shown in Table 7, the encapsulation-treated particulate compositions prepared using the particulate compositions 3 to 10 had markedly low absolute values of the zeta potential, suggesting that a lot of siRNA was encapsulated. Also as shown in Table 7, the degree of reduction of the zeta potential after the siRNA-encapsulation treatment was greater as the addition ratio of the charged lipid relative to the block copolymer units increased. This means that the greater the addition rate of the charged lipid is, the more siRNA can be encapsulated.

[Evaluation 5c: Evaluation of activity on MDA-MB-231 cells]

[0085] In Evaluation 5c, the particulate compositions 3 to 6 as the particulate composition and siRNA(Plk1) as the siRNA were used, and were subjected to the encapsulation treatment so as to obtain the charge ratio of 8 in the method described in Example 5. Using the siRNA-encapsulated particulate compositions, the following evaluation of activity on the MDA-MB-231 cells was carried out. As the inactive control sequence, siRNA(Luc) was used and run in a similar experiment.

[Activity evaluation]

[0086] 10mM HEPES buffer (pH 7.4) was added to the siRNA-encapsulated particulate compositions to adjust the concentration of siRNA at 3 μ M/mL. MDA-MB-231 cells derived from human breast cancer were plated in a 96-well plate at 2000 cells/well. Twenty four hours later, each siRNA-encapsulated particulate composition was added to the culture medium. The final concentration of siRNA in the medium was adjusted to be 300nM, 100nM, 33nM and 11nM. After further culturing for 96 hours, cell viability was evaluated using the Cell Counting Kit-8 (Dojindo Co., Ltd.).

[0087] FIG. 5 indicates graphs for explaining the result of this activity evaluation. As shown in FIG. 5, in the siRNA(Plk1)-encapsulating particulate compositions, cell counts were markedly reduced compared to the siRNA(Luc)-encapsulating particulate compositions.

[Evaluation 5d: Evaluation of aggregation in blood]

[0088] In Evaluation 5d, the particulate compositions 3 to 10 and the comparative particulate composition C3 as the particulate composition and siRNA(Luc) as the siRNA were used, and were subjected to the encapsulation treatment so as to obtain the charge ratio of 8 in the method described in Example 5. The absorbances of the samples A and B prepared as described above at a wavelength of 700nm were determined using a plate reader (POWERSCAN HT, Dainippon Sumitomo Pharma Co., Ltd.) to calculate the aggregability in blood. When the calculated value was 0 or less, the aggregability in blood was set at 0.

[0089] FIG. 6 is a graph showing the absorbances of Measurement sample A (with FBS) and Measurement sample B (without FBS) for the encapsulation-treated particulate composition that used the particulate composition 4 and the encapsulation-treated particulate composition that used the comparative particulate composition C3. As shown in FIG. 6, the FBS treatment caused a significant increase in the absorbance in the encapsulation-treated particulate composition that used the comparative particulate composition C3. This indicates the occurrence of aggregation due to interactions with blood components. In the encapsulation-treated particulate composition (siRNA-encapsulated particulate composition) that used the particulate composition 4, almost no increase in absorbance due to the FBS treatment was observed.

[0090] The graph of FIG. 7 and Table 8 (shown below) show the relationship between the absolute values of zeta potential of the encapsulation-treated particulate compositions measured in Evaluation 5b and the aggregability in blood of the encapsulation-treated particulate compositions measured in Evaluation 5d.

[Table 8]

Particulate composition used	Aggregation in blood	Zeta potential (mV)
None	0.118	-
3	0.092	1.93
4	0.132	2.63
5	0.142	4.67
6	0.153	6.17
7	0	0.37
8	0	0.95
9	0	0.57
10	0	0.96
C3	0.292	55.1

[0091] As shown in Fig. 7 and Table 8, the encapsulation-treated particulate compositions had a markedly low aggregability in blood when the absolute values of the zeta potential thereof were 5mV or lower, 3mV or lower, furthermore 2mV or lower, and specifically 1mV or lower.

[Evaluation 5e: Evaluation of remaining rate in blood]

[0092] In Evaluation 5e, the particulate compositions 3 to 10 as the particulate composition and F-siRNA(Luc) as the siRNA were used, and were subjected to the encapsulation treatment of siRNA so as to obtain the charge ratio of 8 in the method described in Example 5. For the particulate composition 4, the encapsulation-treated of siRNA was also carried out so as to obtain the charge ratio of 1, 2 and 4. To the siRNA-encapsulated particulate compositions thus prepared, 3M aqueous sodium chloride solution was added at a volume ratio of 1/20 to prepare an isotonic solution (siRNA encapsulation-treated particulate composition sample) containing 150mM sodium chloride. As the control, to a 10 μ M siRNA solution prepared by dissolving F-siRNA(Luc) into a 10mM HEPES buffer (pH 7.4), a 3M aqueous sodium chloride solution was added at a volume ratio of 1/20 to prepare an isotonic solution (siRNA single sample) containing 150mM sodium chloride. The siRNA-encapsulated particulate composition samples and the siRNA single sample were administered to Balb/c mice (prepared from Charles River Laboratories Japan, Inc.) via the tail vein, and 200 μ L of blood was collected via the inferior vena cava one hour after. The dosage of each sample for each mouse was determined so as for the ratio of F-siRNA to the weight of the mouse to be 1mg/kg.

[0093] The blood collected from each of the individuals that received a sample derived from the particulate compositions 3 to 6 was centrifuged with 2000xg at 4°C for 10 minutes, and 80 μ L of plasma was collected from the supernatant. The plasma was measured for fluorescence intensity using a plate reader (POWERSCAN HT, manufactured by Dainippon Sumitomo Pharma Co., Ltd.) (excitation wavelength: 485nm; fluorescence wavelength: 528nm) to determine the quantity of F-siRNA circulating in blood. The blood collected from each of the individuals that received a sample derived from the particulate compositions 7 to 10 was centrifuged with 2000xg at 4°C for 10 minutes, and 100 μ L of plasma was collected from the supernatant. To the plasma, one mL of Sepasol RNA I (Nakalai Tesque) was added, vortex-mixed, and allowed to stand for 5 minutes. 200 μ L of chloroform was added thereto, mixed by inversion, and allowed to stand for 3 minutes. The solution was centrifuged with 2000xg at 4°C for 10 minutes, and 300 μ L of the supernatant prepared was measured for fluorescence intensity using a plate reader (POWERSCAN HT, manufactured by Dainippon Sumitomo Pharma Co., Ltd.) (excitation wavelength: 485nm; fluorescence wavelength: 528nm) to determine the quantity of F-siRNA circulating in blood.

[Table 9]

Particulate composition used	Charge ratio (+/-)	Zeta potential (mV)	Remaining rate in blood relative to the dosage of F-siRNA (%)
None (single F-siRNA)	-	-	<0.4
3	8	1.93	5.2
4	8	2.63	4.3

(continued)

Particulate composition used	Charge ratio (+/-)	Zeta potential (mV)	Remaining rate in blood relative to the dosage of F-siRNA (%)
5	8	4.67	3.0
6	8	6.17	2.3
7	8	0.37	37.9
8	8	0.95	0.9
9	8	0.57	15.5
10	8	0.96	2.8

[Table 10]

Particulate composition used	Charge ratio (+/-)	Remaining rate in blood relative to the dosage of F-siRNA (%)
4	1	0.46
4	2	1.2
4	4	3.6
4	8	4.3

[0094] As shown in Table 9, 0.9% or more of F-siRNA remained in blood for the siRNA-encapsulated particulate compositions prepared using the particulate compositions 3 to 10. The remaining rate of F-siRNA was higher as the weight ratio of the block copolymer units to the charged lipid becomes greater in the siRNA-encapsulated particulate compositions. This means that when the content of the charged lipid in the particulate composition is assumed to be constant, the period of retaining the drug in blood becomes longer as the density of the region formed by the hydrophilic polymer-chain segments becomes increased. Also, the lower the absolute value of zeta potential of the sample, the remaining rate of F-siRNA becomes higher. For example, the remaining rate of F-siRNA of a sample prepared by using the particulate composition 7 having the absolute value of zeta potential of 0.37mV was 37.9%, while the remaining rate of F-siRNA of a sample prepared by using the particulate composition 9 having the absolute value of zeta potential of 0.57mV was 15.5%. As shown in Table 10, the remaining rate of F-siRNA was higher as the charge ratio in the siRNA-encapsulated particulate compositions became higher. This means that the more the amount of the charged lipid added is, the longer the period becomes in which the particles can retain the drug in blood.

[0095] For a sample prepared by carrying out the encapsulation treatment so as to obtain the charge ratio of 1.5 using the particulate composition 6 as the particulate composition and siRNA(Luc) as the siRNA in the method described in Example 5, the zeta potential was measured in the method described in Evaluation 5b. The absolute value was 0.36mV, which was almost equal to the sample prepared using the particulate composition 7. However, for a sample (zeta potential: 0.36mV) prepared by carrying out the encapsulation treatment on the particulate composition 6 using F-siRNA(Luc) as the siRNA in the method described in Evaluation 5e, the remaining rate in blood was evaluated, and the amount of F-siRNA remaining in blood was found to be 0.91%. Thus, while the sample prepared using the particulate composition 7 had about the same absolute value of the zeta potential as the sample prepared using the particulate composition 6, it had a markedly excellent retaining rate of the encapsulated drug in blood. Therefore, by forming the particulate composition with anionic polymers, the retaining rate of the encapsulated drug in blood can be significantly enhanced compared to when the particulate composition was formed with neutral polymers.

[Evaluation 5f: Evaluation of organ migration]

[0096] In Evaluation 5f, the encapsulation treatment of siRNA was carried out using the particulate composition 3 and the comparative particulate composition 3 as the particulate composition and F-siRNA(Luc) as the siRNA so as to obtain the charge ratio of 8 in the method described in Example 5. To the encapsulation-treated particulate compositions thus prepared, a 3M aqueous sodium chloride solution was added at a volume ratio of 1/20 to prepare an isotonic solution (encapsulation-treated particulate composition sample) containing 150mM sodium chloride. MDA-MB-231 cells derived from human breast cancer were transplanted to Balb/c nude mice (female, 5 week-old, prepared from Charles River Laboratories Japan, Inc.). To mice of which tumor size became 200 mm² or greater four weeks later, the encapsulation-

treated particulate composition sample was administered. The amount of F-siRNA given was adjusted to be 1mg/kg of mouse body weight. At 10, 60 and 180 minutes after the administration, 50 to 100 μ g of each organ was collected, to which one mL each of the RNA extraction reagent Sepasol RNA I (Nakalai Tesque) was added, and homogenized. To 500 μ L of each homogenate, 100 μ L of chloroform was added, and centrifuged at 4°C, 5200G for 10 minutes. Then, 200 μ L of the supernatant prepared was measured for fluorescence intensity using a plate reader (POWERSCAN HT, manufactured by Daiippon Sumitomo Pharma Co., Ltd.) (excitation wavelength: 485nm; fluorescence wavelength: 528nm) to determine the quantity of F-siRNA that migrated into each organ.

[Table 11]

Particulate composition used	Time after administration (min)	Migration rate (%)					
		Blood	Tumor	Liver	Lung	Kidney	Spleen
4	10	10.8	0.3	8.1	15.0	2.3	19.0
	60	0.9	n.d.	3.8	0.7	0.6	9.9
	180	0.8	n.d.	0.7	0.3	0.1	1.7
C3	10	0.3	n.d.	0.6	178.9	0.7	0.5
	60	0.3	n.d.	1.2	103.1	0.2	0.4
	180	0.2	n.d.	0.5	56.7	n.d.	n.d.
* The migration rate indicates the ratio (%) of the determined value of F-siRNA per g of the organ to the amount administered of F-siRNA per each mouse. "n.d." stands for "not detected".							

[0097] FIG. 8 indicates graphs for explaining the drug migration into organs investigated in Evaluation 5f. As shown in FIG. 7 and Table 11, the encapsulation-treated particulate composition prepared using the comparative particulate composition C3 rapidly disappeared from blood, and its significant accumulation in the lung was observed. On the other hand, the siRNA-encapsulated particulate composition prepared using the particulate composition 4 remained in blood for a much longer period of time, and its migration into the tumor was also observed.

INDUSTRIAL APPLICABILITY

[0098] The particulate composition of the present invention can be used as a drug carrier for preparing a drug-encapsulated pharmaceutical composition, whereby the drug (specifically a polymer compound) can more effectively be retained *in vivo* and protected against decomposition or excretion, and the drug can be delivered to the affected area while maintaining its activity. Furthermore, aggregation of the drug carrier due to interaction with blood components can be avoided. These features would highly improve the drug availability and thereby serve to reduce the dosage significantly, leading to improvement in medicoeconomics and effective expression of physiological effects. The reduction in the dosage would also be useful for controlling side effects, such as induction of immune responses to, e.g., proteins and nucleic acids, as well as adverse effects on the blood coagulation system.

SEQUENCE LISTING

[0099]

<110> NanoCarrier Co., Ltd.

<120> PARTICULE COMPOSITION AND PHARMACEUTICAL COMPOSITION COMPRISING THE SAME

<130> Y660-PCT

<150> JP2009-200681

<151> 2009-08-31

<160> 4

<170> PatentIn version 3.1

<210> 1

<211> 21

<212> RNA

<213> Artificial

<220>

<223> a sense strand of a double-strand siRNA designed to target Firefly luciferase gene

<220>

<221> misc_feature

<222> (20)..(20)

<223> n stands for deoxythymidine

<220>

<221> misc_feature

<222> (21)..(21)

<223> n stands for deoxythymidine

<400> 1

cuuacgcuga guacuucgan n 21

<210> 2

<211> 21

<212> RNA

<213> Artificial

<220>

<223> an antisense strand of a double-strand siRNA designed to target firefly luciferase gene

<220>

<221> misc_feature

<222> (20)..(20)

<223> n stands for deoxythymidine

<220>

<221> misc_feature

<222> (21)..(21)

<223> n stands for deoxythymidine

<400> 2

ucgaaguacu cagcguaagn n 21

<210> 3

<211> 21

<212> RNA

<213> Artificial

<220>

<223> a sense strand of a double-strand siRNA designed to target Human Polo-like kinase 1 gene

<220>

<221> misc_feature

<222> (20)..(20)

<223> n stands for deoxythymidine

<220>

<221> misc_feature

<222> (21)..(21)

<223> n stands for deoxythymidine

5 <400> 3
ccauuaacga gcugcuuaan n 21

<210> 4

<211> 21

10 <212> RNA

<213> Artificial

<220>

15 <223> an antisense strand of a double-strand siRNA designed to target H uman Polo-like kinase 1 gene

<220>

<221> misc_feature

<222> (20)..(20)

20 <223> n stands for deoxythymidine

<220>

<221> misc_feature

<222> (21)..(21)

25 <223> n stands for deoxythymidine

<400> 4

uuaagcagcu cguuaauggn n 21

30 **Claims**

1. A particulate composition for encapsulating a drug therein, comprising:

35 a block copolymer unit having a hydrophobic polymer-chain segment and a hydrophilic polymer-chain segment, a plurality of the block copolymer units being arranged radially with the hydrophobic polymer-chain segments radially inside and the hydrophilic polymer-chain segments radially outside; and
40 a charged lipid which carries a charge opposite to the charge of the drug to be encapsulated in the composition such that the drug is to be retained within the particle via electrostatic binding with the charged lipid, the charged lipid being attracted to the hydrophobic polymer-chain segment, whereby the outer surface of the particle is prevented from being charged to attract a substance which has a charge opposite to the charge of the charged lipid,



wherein the particulate composition is applied to a drug selected from peptides, proteins, sugar chains and nucleic acids; and

45 wherein the charged lipids are not arranged contiguously to one another along the circumference of the particulate composition, but are arranged to intervene between the adjacent block copolymer units along the circumference of the particulate composition, whereby the adjacent charged lipids along the circumference of the particulate composition are separated by the block copolymer units and prevented from being in contact with one another.

50 2. The particulate composition according to claim 1, wherein the hydrophilic polymer-chain segment is a polyethylene glycol chain and the hydrophobic polymer-chain segment is a polyamino acid chain.

55 3. The particulate composition according to claim 1 or 2, wherein the hydrophobic polymer-chain segment is an anionic polymer-chain segment.

4. The particulate composition according to any one of claims 1 to 3, wherein the hydrophobic polymer-chain segment is represented by general formula (I) or (II) :



wherein

R^1 and R^3 , independently of each other, is either hydrogen atom or a group represented by $R^8(R^9)CH(CH_2)_q-$, where R^8 and R^9 (i) independently of each other, is hydrogen atom, C_{1-6} alkoxy group, aryloxy group, aryl- C_{1-3} -oxy group, cyano group, carboxy group, amino group, C_{1-6} -alkoxy carbonyl group, C_{2-7} -acylamide group, tri- C_{1-6} -alkyl siloxy group, siloxy group, or silylamino group, (ii) together with each other, form ethylene dioxy group or propylene dioxy group, which are either unsubstituted or substituted with C_{1-3} -alkyl group, or (iii) together with CH group to which they are bound, form formyl group, and q is an integer of from 0 to 10;

R^2 is hydrogen atom, saturated or unsaturated C_1 - C_{29} aliphatic carbonyl group, or arylcarbonyl group;

R^4 is hydroxy group, saturated or unsaturated C_1 - C_{30} -aliphatic oxy group, or aryl-lower-alkyloxy group;

R^5 is -O- or -NH-;

R^6 is hydrogen atom, phenyl group, benzyl group, $-(CH_2)_4$ -phenyl group, C_4 - C_{16} alkyl group which is either unsubstituted or substituted with amino group or carbonyl group, or sterol derivative residue;

R^7 is methylene group;

n is an integer of from 55 to 4,600;

x is an integer of from 10 to 200;

m is an integer of from 0 to 200, wherein when m is one or more, the $(COCHNH)$ units and the (COR^7CHNH) unit(s) may be arranged in a random order in the block copolymer, and when m is two or more, R^6 is selected for each amino acid unit independently of each other and may be arranged in a random order in the block copolymer, provided that hydrogen atoms must not exceed 75% of R^6 ;

y is 1 or 2;

L^1 is a linking group selected from -NH-, -O-, -O-Z-NH-, -CO-, -CH₂-, and -O-Z-S-Z-NH-, where Z, independently of each other, is C_1 - C_6 alkylene group; and

L^2 is a linking group selected from -OCO-Z-CO- and -NHCO-Z-CO-, where Z is C_1 - C_6 alkylene group.

5. The particulate composition according to claim 4, wherein in general formulae (I) and (II), R^5 is -O- and R^6 is benzyl group, $-(CH_2)_4$ -phenyl group, or C_4 - C_{16} alkyl group which is either unsubstituted or substituted with amino group

or carbonyl group.



6. The particulate composition according to any one of claims 1 to 5, wherein the absolute value of zeta potential of the particulate composition is limited to 15mV or lower whereby the composition is prevented from aggregating in blood, the zeta potential being measured when the composition is added to 10mM HEPES buffer (pH 7.4) in such an amount that the ratio of the total charged lipids to the buffer solution is 0.1mg/ml.
7. The particulate composition according to claim 6, wherein the absolute value of zeta potential of the particulate composition is limited to 3mV or lower whereby the composition is further prevented from aggregating in blood.
8. A pharmaceutical composition comprising: a particulate composition according to any one of claims 1 to 7; and a drug which is encapsulated in the particulate composition and carries a charge opposite to the charge of the charged lipid, wherein the drug is selected from peptides, proteins, sugar chains and nucleic acids.
9. The pharmaceutical composition according to claim 8, wherein the absolute value of zeta potential of the particulate composition is limited to 10mV or lower whereby the composition is prevented from aggregating in blood, the zeta potential being measured when the composition is added to 10mM HEPES buffer (pH 7.4) in such an amount that the ratio of the total charged lipids to the buffer solution is 0.1mg/ml.
10. The pharmaceutical composition according to claim 9, wherein the absolute value of zeta potential of the particulate composition is limited to 2mV or lower whereby the composition is further prevented from aggregating in blood.
11. The pharmaceutical composition according to any one of claims 8 to 10, wherein the hydrophobic polymer-chain segment is formed with an anionic polymer-chain segment whereby the retaining rate of the drug is enhanced.

Patentansprüche

1. Eine teilchenförmige Zusammensetzung zum Verkapseln eines Arzneimittels, umfassend:

- eine Blockcopolymereinheit mit einem hydrophoben Polymerkettensegment und einem hydrophilen Polymerkettensegment, wobei eine Vielzahl aus den Blockcopolymereinheiten mit den hydrophoben Polymerkettensegmenten radial angeordnet ist und sich letztere radial innen und die hydrophilen Polymerkettensegmente radial außen befinden, und
- ein geladenes Lipid, das eine Ladung trägt, die zu der Ladung des in der Zusammensetzung zu verkapselnden Arzneimittels entgegengesetzt ist, so dass das Arzneimittel in dem Teilchen über eine elektrostatische Bindung an das geladene Lipid zurückgehalten wird, wobei das geladene Lipid von dem hydrophoben Polymerkettensegment angezogen wird, wodurch verhindert wird, dass die Oberfläche des Teilchens geladen ist und eine Substanz anzieht, deren Ladung entgegengesetzt zu derjenigen des geladenen Lipids ist, wobei
- die teilchenförmige Zusammensetzung für ein Arzneimittel, ausgewählt aus Peptiden, Proteinen, Zuckerketten und Nucleinsäuren verwendet wird, , und wobei
- die geladenen Lipide entlang des Umfangs der teilchenförmigen Zusammensetzung nicht aneinander angrenzend angeordnet sind, sondern so angeordnet sind, dass sie sich entlang des Umfangs der teilchenförmigen Zusammensetzung zwischen die einander benachbarten Blockcopolymereinheiten einlagern, wodurch die einander benachbarten geladenen Lipide entlang des Umfangs der teilchenförmigen Zusammensetzung durch die Blockcopolymereinheiten getrennt und daran gehindert sind, miteinander in Berührung zu stehen.

2. Teilchenförmige Zusammensetzung nach Anspruch 1, wobei das hydrophile Polymerkettensegment eine Polyethylenglykolkette und das hydrophobe Polymerkettensegment eine Polyaminosäurekette ist.
3. Teilchenförmige Zusammensetzung nach Anspruch 1 oder 2, wobei das hydrophobe Polymerkettensegment ein anionisches Polymerkettensegment ist.
4. Teilchenförmige Zusammensetzung nach einem der Ansprüche 1 bis 3, wobei das hydrophobe Polymerkettensegment die allgemeine Formel (I) oder (II):



besitzt, wobei:

- R^1 und R^3 sind unabhängig voneinander entweder ein Wasserstoffatom oder eine von $R^8(R^9)CH(CH_2)_q$ -repräsentierte Gruppe, worin R^8 und R^9

(i) unabhängig voneinander ein Wasserstoffatom, eine C_{1-6} -Alkoxygruppe, Aryloxygruppe, Aryl- C_{1-3} -oxygruppe, Cyanogruppe, Carboxygruppe, Aminogruppe, C_1 -Alkoxy-carbonylgruppe, C_{2-7} -Acylamidgruppe, Tri- C_{1-6} -alkylsiloxylgruppe, Siloxylgruppe oder Silylaminogruppe bedeuten,

(ii) zusammen eine Ethylendioxygruppe oder Propylendioxygruppe bilden, die entweder unsubstituiert oder mit einer C_{1-3} -Alkylgruppe substituiert ist, oder

(iii) zusammen mit der CH-Gruppe, an welche sie gebunden sind, eine Formylgruppe bilden, und q eine ganze Zahl von 0 bis 10 ist,

- R^2 ist ein Wasserstoffatom, eine gesättigte oder ungesättigte C_1 - C_2 -aliphatische Carbonylgruppe oder Aryl-carbonylgruppe,

- R^4 ist eine Hydroxygruppe, eine gesättigte oder ungesättigte C_1 - C_{30} -aliphatische Oxygruppe oder Aryl-Niederalkyloxy-Gruppe,

- R^5 ist -O- oder -NH-,

- R^6 ist ein Wasserstoffatom, eine Phenylgruppe, Benzylgruppe, $-(CH_2)_4$ -Phenylgruppe, C_4 - C_{16} -Alkylgruppe, die entweder unsubstituiert oder mit einer Aminogruppe oder Carbonylgruppe substituiert ist, oder einen Sterolderivatrest,

- R^7 ist eine Methylengruppe,

- n ist eine ganze Zahl von 55 bis 4600,

- x ist eine ganze Zahl von 10 bis 200,

- m ist eine ganze Zahl von 0 bis 200, wobei, wenn m eins oder mehr ist, die $(COCHNH)$ -Einheiten und die (COR^7CHNH) -Einheit(en) in dem Blockcopolymer auf zufällige Weise angeordnet sein können, und, wenn m zwei oder mehr ist, R^6 für jede Aminosäureeinheit unabhängig voneinander ausgewählt ist und in dem Blockcopolymer auf zufällige Weise angeordnet sein kann, vorausgesetzt, dass die Wasserstoffatome nicht mehr als 75 % von R^6 ausmachen dürfen,

- y ist 1 oder 2,

- L¹ ist eine Verbindungsgruppe, ausgewählt aus -NH-, -O-, -O-Z-NH-, -CO-, -CH₂- und -O-Z-S-Z-NH-, worin Z unabhängig voneinander eine C₁-C₆-Alkylengruppe ist, ausgewählt ist, und
 - L² ist eine Verbindungsgruppe, die aus -OCO-Z-CO- und -NHCO-Z-CO-, worin Z eine C₁-C₆-Alkylengruppe ist.



- 5 5. Teilchenförmige Zusammensetzung nach Anspruch 4, wobei in den allgemeinen Formeln (I) und (II) R⁵ -O- und R⁶ eine Benzylgruppe, -(CH₂)₄-Phenylgruppe oder C₄-C₁₆-Alkylgruppe ist, die entweder unsubstituiert oder mit einer Aminogruppe oder Carbonylgruppe substituiert ist.
- 10 6. Teilchenförmige Zusammensetzung nach einem der Ansprüche 1 bis 5, wobei der absolute Wert des Zeta-Potentials der teilchenförmigen Zusammensetzung auf 15 mV oder kleiner begrenzt ist, wodurch die Zusammensetzung gehindert wird, in Blut zu aggregieren, wobei das Zeta-Potential gemessen wird, nachdem die Zusammensetzung mit einem solchen Anteil zu einem 10 mM HEPES-Puffer (pH-Wert 7,4) zugegeben worden ist, dass das Verhältnis von sämtlichen geladenen Lipiden zur Pufferlösung 0,1 mg/ml beträgt.
- 15 7. Teilchenförmige Zusammensetzung nach Anspruch 6, wobei der absolute Wert des Zeta-Potentials der teilchenförmigen Zusammensetzung auf 3 mV oder darunter begrenzt ist, wodurch die Zusammensetzung weiter daran gehindert wird, in Blut zu aggregieren.
- 20 8. Pharmazeutische Zubereitung, umfassend: eine teilchenförmige Zusammensetzung nach einem der Ansprüche 1 bis 7 und ein Arzneimittel, das in der teilchenförmigen Zusammensetzung verkapselt ist und eine Ladung trägt, die entgegengesetzt zu derjenigen des geladenen Lipids ist, wobei das Arzneimittel ausgewählt ist aus Peptiden, Proteinen, Zuckerketten und Nucleinsäuren.
- 25 9. Pharmazeutische Zubereitung nach Anspruch 8, wobei der absolute Wert des Zeta-Potentials der teilchenförmigen Zusammensetzung auf 10 mV oder darunter begrenzt ist, wodurch die Zubereitung daran gehindert wird, in Blut zu aggregieren, wobei das Zeta-Potential gemessen wird, nachdem die Zusammensetzung mit einem solchen Anteil zu einem 10 mM HEPES-Puffer (pH-Wert 7,4) zugegeben worden ist, dass das Verhältnis von sämtlichen geladenen Lipiden zur Pufferlösung 0,1 mg/ml beträgt.
- 30 10. Pharmazeutische Zubereitung nach Anspruch 9, wobei der absolute Wert des Zeta-Potentials der teilchenförmigen Zusammensetzung auf 2 mV oder darunter begrenzt ist, wodurch die Zubereitung weiter daran gehindert wird, in Blut zu aggregieren.
- 35 11. Pharmazeutische Zubereitung nach einem der Ansprüche 8 bis 10, wobei das hydrophobe Polymerkettensegment aus einem anionischen Polymerkettensegment gebildet worden ist, wodurch die Retentionsrate des Arzneimittels erhöht wird.

Revendications

- 40 1. Composition particulière pour encapsuler un médicament dans celle-ci, comprenant :
 un motif copolymère séquencé ayant un segment de chaîne polymère hydrophobe et un segment de chaîne polymère hydrophile, une pluralité des motifs copolymères séquencés étant agencés radialement avec les
 45 segments de chaîne polymère hydrophobes radialement à l'intérieur et les segments de chaîne polymère hydrophiles radialement à l'extérieur ; et
 un lipide chargé qui porte une charge opposée à la charge du médicament devant être encapsulé dans la composition de façon que le médicament soit retenu à l'intérieur de la particule par liaison électrostatique avec
 le lipide chargé, le lipide chargé étant attiré vers le segment de chaîne polymère hydrophobe, en conséquence
 50 de quoi la surface extérieure de la particule est empêchée d'être chargée pour attirer une substance qui a une charge opposée à la charge du lipide chargé,
 laquelle composition particulière est appliquée à un médicament choisi parmi les peptides, les protéines, les chaînes
 de sucre et les acides nucléiques ; et
 55 dans laquelle les lipides chargés ne sont pas disposés de façon contiguë les uns par rapport aux autres le long de la circonférence de la composition particulière, mais sont agencés de façon à s'interposer entre les motifs copolymères séquencés adjacents le long de la circonférence de la composition particulière, en conséquence de quoi les lipides chargés adjacents le long de la circonférence de la composition particulière sont séparés par les motifs

copolymères séquencés et sont empêchés d'être en contact les uns avec les autres.

2. Composition particulière selon la revendication 1, dans laquelle le segment de chaîne polymère hydrophile est une chaîne de polyéthylèneglycol et le segment de chaîne polymère hydrophobe est une chaîne de poly(acide aminé).
3. Composition particulière selon la revendication 1 ou 2, dans laquelle le segment de chaîne polymère hydrophobe est un segment de chaîne polymère anionique.
4. Composition particulière selon l'une quelconque des revendications 1 à 3, dans laquelle le segment de chaîne polymère hydrophobe est représenté par la formule générale (I) ou (II) :



où

R^1 et R^3 , indépendamment l'un de l'autre, sont soit un atome d'hydrogène soit un groupe représenté par $R^8(R^9)CH(CH_2)_q-$, où R^8 et R^9 (i) indépendamment l'un de l'autre, sont un atome d'hydrogène, un groupe alcoxy en C_1 à C_6 , un groupe aryloxy, un groupe aryl- $(C_1$ à $C_3)$ -oxy, un groupe cyano, un groupe carboxy, un groupe amino, un groupe (alcoxy en C_1 à C_6)carbonyle, un groupe acylamido en C_2 à C_7 , un groupe tri(alkyle en C_1 à C_6)siloxy, un groupe siloxy, ou un groupe silylamino, (ii) forment ensemble un groupe éthylènedioxy ou un groupe propylènedioxy, qui est soit non substitué soit substitué par un groupe alkyle en C_1 à C_3 , ou (iii) conjointement avec le groupe CH auquel il sont rattachés, forment ensemble un groupe formyle, et q est un entier de 0 à 10 ;

R^2 est un atome d'hydrogène, un groupe carbonyle aliphatique en C_1 à C_{29} saturé ou insaturé, ou un groupe arylcarbonyle ;

R^4 est un groupe hydroxy, un groupe oxyaliphatique en C_1 à C_{30} , ou un groupe aryl-alkyloxy inférieur ;

R^5 est -O- ou -NH- ;

R^6 est un atome d'hydrogène, un groupe phényle, un groupe benzyle, un groupe $-(CH_2)_4$ -phényle, un groupe alkyle en C_4 à C_{16} qui est soit non substitué soit substitué par un groupe amino ou un groupe carbonyle, ou un résidu dérivé de stérol ;

R^7 est un groupe méthylène ;

n est un entier de 55 à 4600 ;

x est un entier de 10 à 200 ;

m est un entier de 0 à 200 et, quand m vaut un ou plus, les motifs (COCHNH) et le ou les motifs (COR⁷CHNH) peuvent être disposés de façon statistique dans le copolymère séquencé, et quand m vaut deux ou plus, R⁶ est choisi pour chaque motif acide aminé indépendamment et peut être disposé de façon statistique dans le copolymère séquencé, sous réserve que les atomes d'hydrogène ne dépassent pas 75% de R⁶;

y vaut 1 ou 2 ;

L¹ est un groupe de liaison choisi parmi -NH-, -O-, -O-Z-NH-, -CO-, -CH₂-, et -O-Z-S-Z-NH-, où Z est indépendamment un groupe alkylène en C₁ à C₆ ; et

L² est un groupe de liaison choisi parmi -OCO-Z-CO- et -NHCO-Z-CO- où Z est un groupe alkylène en C₁ à C₆.

5. Composition particulière selon la revendication 4, dans laquelle, dans les formules générales (I) et (II), R⁵ est -O- et R⁶ est un groupe benzyle, un groupe-(CH₂)₄-phényle ou un groupe alkyle en C₄ à C₁₆ qui est soit non substitué soit substitué par un groupe amino ou un groupe carbonyle.

6. Composition particulière selon l'une quelconque des revendications 1 à 5, dans lequel la valeur absolue du potentiel zêta de la composition particulière est limitée à 15 mV ou moins, en conséquence de quoi la composition est empêchée de s'agréger dans le sang, le potentiel zêta étant mesuré quand la composition est ajoutée à du tampon HEPES 10 mM (pH 7,4) en une quantité telle que le rapport des lipides chargés totaux à la solution tampon soit de 0,1 mg/ml.

7. Composition particulière selon la revendication 6, dans laquelle la valeur absolue du potentiel zêta de la composition particulière est limitée à 3 mV ou moins, en conséquence de quoi la composition est davantage empêchée de s'agréger dans le sang.

8. Composition pharmaceutique comprenant : une composition particulière selon l'une quelconque des revendications 1 à 7 ; et un médicament qui est encapsulé dans la composition particulière et qui porte une charge opposée à la charge du lipide chargé, dans laquelle le médicament est choisi parmi les peptides, les protéines, les chaînes de sucre et les acides nucléiques.

9. Composition pharmaceutique selon la revendication 8, dans lequel la valeur absolue du potentiel zêta de la composition particulière est limitée à 10 mV ou moins, en conséquence de quoi la composition est empêchée de s'agréger dans le sang, le potentiel zêta étant mesuré quand la composition est ajoutée à du tampon HEPES 10 mM (pH 7,4) en une quantité telle que le rapport des lipides chargés totaux à la solution tampon soit de 0,1 mg/ml.

10. Composition pharmaceutique selon la revendication 9, dans lequel la valeur absolue du potentiel zêta de la composition particulière est limitée à 2 mV ou moins, en conséquence de quoi la composition est empêchée de s'agréger dans le sang.

11. Composition pharmaceutique selon l'une quelconque des revendications 8 à 10, dans laquelle le segment de chaîne polymère hydrophobe est formé avec un segment de chaîne polymère anionique, en conséquence de quoi le taux de retenue du médicament est amplifié.

Fig.1




Fig.2




Fig.3




Fig.4




Fig.5




Fig.6




Fig.7





Fig.8



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 2001034115 A [0003]
- WO 19985863 A [0003]
- WO 200509238 A [0003]
- JP 2001504093 W [0003]
- WO 2006002538 A1 [0003]
- JP 2006056864 A [0003]
- WO 200500719 A [0003]
- JP 2009200681 A [0099]

RÉSZECSEKOMPOZÍCIÓ ÉS ILYET TARTALMAZÓ GYÓGYSZERKÉSZÍTMÉNY

Szabadalmi igénypontok:

1. Részecsekompozíció hatóanyag kapszulázásához, amely tartalmaz:

blokk-kopolimer egységet, amelynek van hidrofób polimer-lánc-szegmense és hidrofil polimer-lánc szegmense, több blokk kopolimer egység sugárirányban van elrendezve a hidrofób polimer-lánc szegmenssel sugárirányban befelé, és a hidrofil polimer-lánc szegmenssel sugárirányban kifelé; és

töltéssel rendelkező lipidet, amely a kompozícióba kapszulázandó hatóanyag töltésével ellentétes töltést hordoz, így a hatóanyag visszatartódik a részecskében a töltéssel rendelkező lipiddel képezett elektrosztatikus kötés révén, a töltéssel rendelkező lipidet vonzza a hidrofób polimer-lánc szegmens, ezáltal megakadályozzuk, hogy a részecske külső felülete töltéssel rendelkezzen és vonzzon egy olyan anyagot, amelynek a töltése ellentétes a töltéssel rendelkező lipid töltésével,

ahol a részecsekompozíciót a peptidek, proteinek, cukorláncok és nukleinsavak közül választott hatóanyagra visszük fel; és



ahol a töltéssel rendelkező lipidek nem egymással összefüggő módon vannak elrendezve a részecsekompozíció kerülete mentén, hanem úgy vannak elrendezve, hogy a szomszédos blokk-kopolimer egységek közé ékelődnek be a részecsekompozíció kerülete mentén, ezáltal a szomszédos, töltéssel rendelkező lipidek a részecsekompozíció kerülete mentén el vannak választva a blokk-kopolimer egységekkel, és meg van akadályozva, hogy egymással érintkezzenek.

2. Az 1. igénypont szerinti részecsekompozíció, ahol a hidrofil polimer-lánc szegmens polietilén-glikol lánc, és a hidrofób polimer-lánc szegmens poliaminosav-lánc.



3. Az 1. vagy 2. igénypont szerinti részecskekompozíció, ahol a hidrofób polimer-lánc szegmens anionos polimer-lánc szegmens.

4. Az 1-3. igénypontok bármelyike szerinti részecskekompozíció, ahol a hidrofób polimer-lánc szegmenst az (I) vagy (II) általános képlet mutatja be:



ahol

R^1 és R^3 jelentése egymástól függetlenül hidrogénatom vagy $R^8(R^9)CH(CH_2)_q$ -képletű csoport, ahol R^8 és R^9 jelentése (i) egymástól függetlenül hidrogénatom, C_{1-6} alkoxicsoport (azaz 1-6 szénatomos alkoxicsoport), ariloxicsoport, aril- C_{1-3} -oxicsoport, cianocsoport, karboxicsoport, aminocsoport, C_{1-6} -alkoxi-karbonil-csoport, C_{2-7} -acilamid-csoport, tri(C_{1-6} -alkil)-sziloxi-csoport, sziloxicsoport vagy szililaminocsoport, (ii) együtt etilén-dioxi-csoportot vagy propilén-dioxi-csoportot képez, amelyek vagy helyettesítetlenek vagy C_{1-3} -alkil-csoporttal helyettesítettek, vagy (iii) együtt a CH csoporttal, amelyhez kapcsolódnak, formilcsoportot képeznek, és q jelentése egész szám, értéke 0 - 10;

R^2 jelentése hidrogénatom, telített vagy telítetlen C_1 - C_{29} alifás karbonilcsoport, vagy arilkarbonilcsoport;

R^4 jelentése hidroxicsoport, telített vagy telítetlen C_1 - C_{30} alifás oxicsoport vagy aril- (kevés szénatomos)alkiloxi-csoport;

R^5 jelentése -O- vagy -NH-;

R^6 jelentése hidrogénatom, fenilcsoport, benzilcsoport, $-(CH_2)_4$ -fenil csoport, C_4 - C_{16} alkilcsoport, amely helyettesítetlen vagy helyettesített aminocsoporttal vagy karbonilcsoporttal, vagy szterin-származék maradék;

R^7 jelentése metilencsoport;

n jelentése egész szám, értéke 55 - 4600;

x jelentése egész szám, értéke 10 - 200;

m jelentése egész szám, értéke 0 - 200, ahol amikor m jelentése egy vagy több, a (COCHNH) egységek és a (COR⁷CHNH) egység(ek) lehetnek véletlenszerűen elrendezve a blokk kopolimerben, és amikor m jelentése kettő vagy több, R^6 jelentését mindegyik aminosav-egységre egymástól függetlenül választjuk, és lehetnek véletlenszerűen elrendezve a blokk kopolimerben, feltéve, hogy a hidrogénatomok nem haladhatják meg R^6 75 %-át;

y jelentése 1 vagy 2;

L^1 jelentése kapcsolócsoport, amelyet az -NH-, -O-, -O-Z-NH-, -CO-, -CH₂- és az -O-Z-S-Z-NH- közül választunk, ahol Z jelentése egymástól függetlenül C_1 - C_6 alkilencsoport; és

L^2 jelentése kapcsolócsoport, amelyet az -OCO-Z-CO és az -NHCO-Z-CO- közül választunk, ahol Z jelentése C_1 - C_6 alkilencsoport.

5. A 4. igénypont szerinti részecskekompozíció, ahol az (I) és (II) általános képletben R^5 jelentése -O-, és R^6 jelentése benzilcsoport, $-(CH_2)_4$ -fenil csoport vagy C_4 - C_{16} alkilcsoport, amely helyettesítetlen vagy helyettesített aminocsoporttal vagy karbonilcsoporttal.

6. Az 1-5. igénypontok bármelyike szerinti részecskekompozíció, ahol a részecskekompozíció zéta-potenciáljának abszolút értéke 15 mV-ra vagy alacsonyabbra van korlátozva, ez megakadályozza a kompozíció vérben való aggregálódását, a zéta-potenciált úgy mérjük, hogy a kompozíciót 10 mM HEPES pufferhez (pH 7,4) adjuk olyan mennyiségben, hogy az összes töltéssel rendelkező lipid és a puffer-oldat aránya 0,1 mg/ml.

7. A 6. igénypont szerinti részecskekompozíció, ahol a részecskekompozíció zéta-potenciáljának abszolút értékét 3mV-ra vagy alacsonyabb értékre korlátozzuk, ez még inkább megakadályozza a kompozíció vérben való aggregálódását.

8. Gyógyszerkészítmény, amely tartalmaz az 1-7. igénypontok bármelyike szerinti részecskekompozíciót és hatóanyagot, amely a részecskekompozícióba van kapszulázva és a töltéssel rendelkező lipid töltésével ellentétes töltést hordoz, ahol a hatóanyagot peptidek, proteinek, cukorláncok és nukleinsavak közül választjuk.

9. A 8. igénypont szerinti gyógyszerkészítmény, ahol a részecskekompozíció zéta-potenciáljának abszolút értékét 10 mV-ra vagy kisebb értékre korlátozzuk, ez megakadályozza a kompozíció vérben való aggregálódását, a zéta-potenciált úgy mérjük, hogy a kompozíciót 10 mM HEPES pufferhez (pH 7,4) adjuk olyan mennyiségben, hogy az összes töltéssel rendelkező lipid és a puffer-oldat aránya 0,1 mg/ml.

10. A 9. igénypont szerinti gyógyszerkészítmény, ahol a részecskekompozíció zéta-potenciáljának abszolút értékét 2 mV-ra vagy alacsonyabb értékre korlátozzuk, ez még inkább megakadályozza a kompozíció vérben való aggregálódását.

11. A 8-10. igénypontok bármelyike szerinti gyógyszerkészítmény, ahol a hidrofób polimer-lánc-szegmens anionos polimer-lánc szegmenssel van kialakítva, ezáltal a hatóanyag visszatartási aránya fokozott.