

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 March 2010 (18.03.2010)

PCT

(10) International Publication Number
WO 2010/030771 A1

(51) International Patent Classification:

B05D 5/00 (2006.01) **C09D 4/00** (2006.01)
C08G 18/00 (2006.01)

(21) International Application Number:

PCT/US2009/056502

(22) International Filing Date:

10 September 2009 (10.09.2009)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

12/209,296 12 September 2008 (12.09.2008) US

(71) Applicant (for all designated States except US): **PPG INDUSTRIES OHIO, INC.** [US/US]; 3800 West 143rd Street, Cleveland, Ohio 44111 (US).

(72) Inventor: **BOWMAN, Mark, P.**; 220 Frontenac Drive, New Kensington, Pennsylvania 15068 (US).

(74) Agents: **MEYERS, Diane, R.** et al.; PPG Industries, Inc., One PPG Place - 39th Floor, Pittsburgh, Pennsylvania 15272 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

— with international search report (Art. 21(3))



WO 2010/030771 A1

(54) Title: MICHAEL ADDITION CURING USING PHOSPHINE CATALYST

(57) Abstract: A method of applying a curable composition to a substrate is disclosed. The composition comprises a polyene and a active hydrogen-containing compound that are capable of undergoing a Michael Addition reaction. The reaction is conducted in the presence of a tertiary phosphine catalyst. The components of the composition are sprayed in separate streams whereby the streams overlap prior to contacting the substrate and the composition cures quickly on the substrate.

MICHAEL ADDITION CURING USING PHOSPHINE CATALYST

FIELD OF THE INVENTION

[0001] The present invention relates to the use of phosphines as catalysts for the Michael addition of active hydrogen containing materials to polyenes.

BACKGROUND OF THE INVENTION

[0002] The Michael addition reaction is well known as a curing mechanism for decorative and protective coatings. Typically, the reaction is catalyzed by strong base such as primary or secondary amines that cause yellowing and can also reduce the hydrolytic stability of coatings formulated with polymers that have linkages susceptible to hydrolysis such as polyesters.

[0003] Tertiary phosphines are known to catalyze Michael addition reactions. However, they are used under conditions where curing is through exposure to UV light or under conditions with extended pot lives and/or curing at elevated temperatures. See for example U.S. 3,729,484; 5,084,536; 5,496,896 and 2006/0094804.

[0004] For certain applications it would be desirable to catalyze Michael addition reactions with tertiary phosphines where cure occurs rapidly, that is within a few seconds after a coating containing the Michael addition reactants are applied to a substrate. For example, in the coating of large vertically disposed substrates such as bridges or buildings it would be desirable to apply the coating composition and have it cure immediately at ambient temperature.

SUMMARY OF THE INVENTION

[0005] The present invention provides a method for applying to a substrate a curable composition comprising:

- A. a polyene,
- B. an active hydrogen containing compound,
- C. a tertiary phosphine

[0006] wherein A and B are capable of Michael addition reaction in the presence of the tertiary phosphine; the method comprising spraying the curable composition in separate streams wherein the components A, B, and C are drawn from two or more separate containers to form the separate streams. The streams overlap prior to contacting the substrate and the composition is cured on the substrate.

DETAILED DESCRIPTION OF EMBODIMENTS OF THE INVENTION

[0007] For purposes of the following detailed description, it is to be understood that the invention may assume various alternative variations and step sequences, except where expressly specified to the contrary. Moreover, other than in any operating examples, or where otherwise indicated, all numbers expressing, for example, quantities of ingredients used in the specification and claims are to be understood as being modified in all instances by the term "about". Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification and attached claims are approximations that may vary depending upon the desired properties to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard variation found in their respective testing measurements.

[0008] Also, it should be understood that any numerical range recited herein is intended to include all sub-ranges subsumed therein. For example, a range of "1 to 10" is intended to include all sub-ranges between (and including) the recited minimum value of 1 and the recited maximum value of 10, that is, having a minimum value equal to or greater than 1 and a maximum value of equal to or less than 10.


[0009] In this application, the use of the singular includes the plural and plural encompasses singular, unless specifically stated otherwise. In addition, in this application, the use of "or" means "and/or" unless specifically stated otherwise, even though "and/or" may be explicitly used in certain instances.

[0010] The term "polymer" is also meant to include copolymer and oligomer.


[0011] Acrylic and methacrylic are designated as (meth)acrylic.

[0012] Aliphatic and cycloaliphatic are designated as (cyclo)aliphatic.

[0013] Suitable polyenes for use in the present invention are numerous and can vary widely. Such polyenes can include those that are known in the art. Non-limiting examples of suitable polyenes can include those that are represented by the formula:



wherein A is an organic moiety, m is an integer of at least 2, and X is an olefinically unsaturated moiety and m is at least 2, typically 2 to 4. Examples of X are groups of the following structure:



wherein each R is a radical selected from H and methyl.

[0014] The polyenes (Michael acceptors) are compounds or polymers having in the molecule olefinic double bonds that are reactive with active hydrogen-containing compounds. Examples of such materials are (meth)acrylic-functional (meth)acrylic copolymers, epoxy resin (meth)acrylates, polyester (meth)acrylates, polyether (meth)acrylates, polyurethane (meth)acrylates, amino (meth)acrylates, silicone (meth)acrylates, and melamine (meth)acrylates. The number average molar mass (M_n) of these compounds is preferably around 200 to 10,000. The molecule preferably contains on average 2 to 20 olefinic double bonds that are polymerizable by exposure to radiation. (Cyclo)aliphatic (meth)acrylates in each case are preferably used. (Cyclo)aliphatic polyurethane (meth)acrylates and (cyclo)aliphatic polyester (meth)acrylates are particularly preferred. The binders may be used singly or in mixture.

[0015] Specific examples of polyurethane (meth)acrylates are reaction products of the polyisocyanates such as 1,6-hexamethylene diisocyanate and/or isophorone diisocyanate including isocyanurate and biuret derivatives thereof with hydroxyalkyl (meth)acrylates such as hydroxyethyl (meth)acrylate and/or hydroxypropyl (meth)acrylate. The polyisocyanate can be reacted with the hydroxyalkyl (meth)acrylate in a 1:1 equivalent ratio or can be reacted with and NCO/OH equivalent ration greater than 1 to form an NCO-containing reaction product that can then be chain extended with a polyol such as a diol or triol, for example 1,4-butane diol, 1,6-hexane diol and/or trimethylol propane. Examples of polyester (meth)acrylates are the reaction products of (meth)acrylic acid or anhydride with polyols, such as diols, triols and tetraols, including alkylated polyols, such as propoxylated diols and triols. Examples of polyols include 1,4-butane diol, 1,6-hexane diol, neopentyl glycol, trimethylol propane, pentaerythritol and propoxylated 1,6-hexane diol. Specific examples of polyester (meth)acrylate are glycerol tri(meth)acrylate, trimethylolpropane tri(meth)acrylate, pentaerythritol tri(meth)acrylate and pentaerythritol tetra(meth)acrylate.

[0016] By active hydrogen containing compound (Michael donor) is meant (a) compounds containing at

least two $\begin{array}{c} | \\ -C- \\ | \end{array} H$ groups that are located in the alpha position with respect to electron


withdrawing groups such as methylene groups having two (2) carbonyl groups in the alpha position; and (b) polythiol compounds.

[0017] Examples of compound (a) are acetoacetate and malonate materials such as polyesters of malonic acid and polyesters of acetoacetic acid which are formed from reacting the malonic acid or the acetoacetic acid with polyols.

[0018] Examples of polyols that are suitable for the esterification of the malonic and acetoacetic acid are those having from 1 to 20 carbon atoms such as ethylene glycol, glycerol and trimethylol propane. Specific polyesters are ethanediol, bisacetoacetate, glycerol trismalonate and trimethylolpropane triacetate.


[0019] As used herein the term "polythiol functional material" refers to polyfunctional materials containing two or more thiol functional groups (SH). Suitable polythiol functional materials for use in forming the radiation curable topcoat composition are numerous and can vary widely. Such polythiol functional materials can include those that are known in the art. Non-limiting examples of suitable polythiol functional materials can include, but are not limited to, polythiols having at least two thiol groups including compounds and polymers. The polythiol can have ether linkages (-O-), sulfide linkages (-S-), including polysulfide linkages (-S_x-), wherein x is at least 2, such as from 2 to 4, and combinations of such linkages.

[0020] The polythiols for use in the present invention include, but are not limited to, materials of the formula:



wherein R₁ is a polyvalent organic moiety and n is an integer of at least 2, typically 2 to 6.

[0021] Non-limiting examples of suitable polythiols include, but are not limited to, esters of thiol-containing acids of the formula HS-R₂-COOH wherein R₂ is an organic moiety with polyhydroxy compounds of the structure R₃-(OH)_n wherein R₃ is an organic moiety and n is at least 2, typically 2 to 6. These components can be reacted under suitable conditions to give polythiols having the general structure:




wherein R₂, R₃ and n are as defined above.

[0022] Examples of thiol-containing acids are thioglycolic acid (HS-CH₂COOH), α -mercaptopropionic acid (HS-CH(CH₃)-COOH) and β -mercaptopropionic acid (HS-CH₂CH₂COOH) with polyhydroxy compounds such as glycols, triols, tetraols, pentaols, hexaols, and mixtures thereof. Other non-limiting examples of suitable polythiols include, but are not limited to, ethylene glycol bis (thioglycolate), ethylene glycol bis(β -mercaptopropionate), trimethylolpropane tris (thioglycolate), trimethylolpropane tris (β -mercaptopropionate), pentaerythritol tetrakis (thioglycolate) and pentaerythritol tetrakis (β -mercaptopropionate), and mixtures thereof.

[0023] Typically, the polyene is present in the clear topcoat composition in amounts of 80 to 98, more typically 90 to 95 percent by weight, and the polythiol material is typically present in amounts of 2 to 20, more usually 5 to 10 percent by weight. The percentages by weight are based on total weight of polyene and polythiol.

[0024] The phosphine catalyst is a tertiary phosphine that may be (cyclo)aliphatic, aromatic or mixed (cyclo)aliphatic aromatic, (cyclo)alkyl, aryl, alkaryl, and acalkyl. The phosphine is of the structure



where R₁, R₂, and R₃ are each independently selected from (cyclo)aliphatic and aromatic groups containing from one to twelve carbon atoms such as (cyclo)alkyl and (cyclo)alkyl groups and aromatic groups containing 6-12 carbons such as aryl and aryl (cycloalkyl).

[0025] Suitable examples include tributylphosphine, triisobutylphosphine, tri-tertiary-butylphosphine, trioctyl phosphine, tris(2,4,4-trimethylpentyl)phosphine, tricyclopentylphosphine, tricyclohexylphosphine, tri-n-octylphosphine, tri-n-dodecylphosphine, triphenyl phosphine, and dimethyl phenyl phosphine.

[0026] The equivalent ratio of a Michael receptor to the Michael donor is from 4:1 to 1:4, preferably 1.5:1 to 1:1.5. The phosphine catalyst is present in amounts of 0.1 to 5, preferably 0.2 to 2 percent by weight based on weight of Michael acceptor and Michael donor.

[0027] The curable compositions may be water borne or solvent borne or it can be diluent-free compositions. The compositions may contain additives that are commonly used in protective and decorative coatings such as pigments, ultra-violet absorbers, hindered amine stabilizers, adhesion promoters, and flow additives.

[0028] The curable compositions are in the form of multi-packaged systems where the polyene, active hydrogen containing compound and tertiary phosphine are in separate packages prior to application to the substrate. Alternatively, the composition can be in two

(2) packages with the polyene and the active hydrogen containing compound being present in one package and the tertiary phosphine being present in the second package. Alternatively, the polyene and the tertiary phosphine can be present in one package and the active hydrogen compound present in the second package or the active hydrogen containing compound and the tertiary phosphine can be present in one package and the polyene present in a separate package. The additives can be present in any of the packages.

[0029] Because of rapid curing times, the compositions are typically applied to a substrate by spraying via a nozzle assembly using an external spraying apparatus. Whereby the components of the composition are drawn in separate streams from their respective packages or containers whereby the streams intermingle and mix prior to contacting the substrates and the composition cures immediately on the substrate,

[0030] Typically, intermingling and mixing of the streams occur after they leave the external spraying device but before being applied to the substrate using a multi-nozzle spraying apparatus. For example, two adjacent atomizing nozzles are positioned so that separate streams are atomized and expelled from the spraying apparatus as separate atomized streams. Atomization occurs by applying pressurized air to the nozzles. The nozzles are positioned so that the separate atomized streams overlap prior to reaching the substrate. A typical spraying apparatus is as described in U.S. 5,713,519. The application and curing occurs at ambient conditions, typically 15-30°C.

Examples

[0031] The following examples are intended to illustrate the invention, and should not be construed as limiting the invention in any way. All parts and percentages are by weight unless otherwise indicated.

Example A
Polyene
Urethane acrylate, (NCO – Free)

[0032] A urethane acrylate was prepared by stirring a room temperature mixture of isophorone diisocyanate, DESMODUR Z 4470 from Bayer Material Science (1895 grams), a free radical inhibitor, Ionol (2.67 grams), dibutyltin dilaurate (5.35 grams), and triphenyl phosphite (9.8 grams) under nitrogen. Then, 2-hydroxyethyl acrylate (581.8 grams) was added drop wise over the course of 20 minutes while maintaining the reaction temperature at

62 °C. Then, 1,4-butanediol (25 grams) was added dropwise over 20 minutes, with the reaction temperature maintained at 60 °C. The reaction mixture was stirred for an additional 30 minutes at 60 °C. Finally, butyl acetate was added (403.3 grams), and the mixture briefly stirred.

Example B
Urethane Acrylate
(NCO – containing)

[0033] A urethane acrylate was prepared by stirring a room temperature mixture of 1,6-hexamethylene diisocyanate, DESMODUR N 3600 from Bayer Material Science (515.3 grams), a free radical inhibitor, hydroquinone monomethyl ether (0.28 grams), dibutyltin dilaurate (0.25 grams), and butyl acetate (140.8 grams) under nitrogen. Then, 4-hydroxybutyl acrylate (284.2 grams) was added drop wise over the course of 60 minutes while maintaining the reaction temperature at 70 °C. Butyl acetate was added (59.2 grams), and the mixture was then maintained at 60-65 °C for two hours. The reaction product had NCO equivalent of The reaction product had NCO equivalent weight of 884 based on weight of resin solids.

Example C
Hydroxy-Containing Acrylic Polymer

[0034] A mixture of n-amyl propionate (178.25 grams) and triphenyl phosphite (1.46 grams) was heated under nitrogen to reflux (157-158 °C). Then a mixture of 2-ethylhexyl acrylate (176.92 grams), hydroxyethyl methacrylate (336.98 grams), isobornyl methacrylate (98.57 grams), acrylic acid (12.64 grams), styrene (217.35 grams), tert-dodecyl mercaptan (4.19 grams), n-amyl propionate (49.63 grams) and LUPEROX DTA (29.38 grams, [Di-t-amyl peroxide, available from Arkema Inc.]) was added drop wise over four hours while holding the reaction mixture at reflux temperatures (169-175 °C). An additional 11.38 grams of n-amyl propionate was added and a mixture of LUPEROX DTA (4.12 grams) and n-amyl propionate (5.37 grams) was added over 30 minutes while maintaining the reaction mixture at 175 °C. An additional 11.38 grams of n-amyl propionate was added and the reaction was refluxed (173 °C) for an additional hour. The product was then cooled under a nitrogen atmosphere and had the following properties:

GPC [in THF, polystyrene standards] (Mw 4471, Mn 1457, Mz 10017)

%Solids 77.85%

OH value 128.7

Acid value 7.54

Example D
Polyene

[0035] The acrylic resin of Example C (694.4 grams) was heated to 65 °C under nitrogen. Then urethane acrylate resin of Example B (470.8 grams) was added drop wise over one hour while maintaining a temperature of 60-65 °C. Then, butyl acetate was added (136.4 grams) and the mixture was stirred at 65 °C for an additional two hours.

Example E
Polythiol

[0036] Pentaerythritol tetrakis (3-mercapto propionate)

Example 1
Primer Formulation

[0037]

Pack A

Description	Formula Weight (grams)
Urethane acrylate of Example A	104.77
SR-9003 (Diacylate)	8.42
Iron Oxide	0.31
Talc	26.14
Barium Sulfate	7.61
Calcium carbonate	22.93
Titanium dioxide	2.60
Acetone	70.12

¹ Propoxylated neopentyl glycol diacrylate available from Sartomer, Inc.

Pack B

Pentaerythritol tetrakis(3-mercaptopropionate) of Example E	29.3
---	------

[0038] The above Pack A and Pack B were mixed together and placed in one container. A 10% by weight solution of trioctyl phosphine in butyl acetate was placed in a second

container. The formulation was sprayed onto cold rolled steel panels in separate streams drawn from the two separate containers. Spraying was done with a Binks Model 2001 GW gun that is available from ITW Industrial Finishing, Glendale Heights, Illinois. The spray gun is a lightweight, hand-held, plural component spray gun for spraying two-component materials. The spray gun is operated in the conventional manner. The trigger action starts, and stops, the spray of both materials simultaneously. The two materials exit separately as an atomized spray from their respective nozzles and impinge on each other approximately 6" in front of the gun (resin) nozzle. Here, the resulting turbulence insures intimate mixing.

[0039]

Cure Time (dry to touch)	Amount of Pack A + B	10% Trioctyl phosphine solution
Less than 15 seconds	53.8 grams	11.5 grams
Less than 15 seconds	51.9 grams	2.82 grams

Example 2
Clearcoat Formulation

[0040]

Pack A

Description	Formula Weight (grams)
Byk 300 ¹	0.5
Amyl propionate	19.0
Methyl isobutyl ketone	23.0
Urethane acrylate of Example D	73.1
SR-9003 (diacrylate)	15.0

¹Polysiloxane flow control agent available from BYK Chemical.

Pack B

Pentaerythritol tetrakis(3-mercaptopropionate) of Example E	27.2
---	------

[0041] The above Pack A and Pack B were mixed together and placed in one container. A 10% by weight solution of dimethyl phenyl phosphine in butyl acetate was placed in a second container. The formulation was sprayed onto cold rolled steel panels using a Binks

Model 2001 GW spray gun, as described in Example 1. The clear coat was dry to the touch in less than 15 seconds.

Example 3
Clearcoat Formulation

[0042]

Pack A

Description	Formula Weight (grams)
Byk 300	0.5
Amyl propionate	19.0
Methyl isobutyl ketone	23.0
Urethane acrylate acrylic I	128.6
SR-9003 (diacrylate)	20.0

Pack B

Pentaerythritol tetrakis(3-mercaptopropionate)	27.3
--	------

[0043] The above Pack A and Pack B were combined, a catalyst solution added as shown in the table below. The mixture was stirred and then drawn down with a 2-mil draw down bar onto a steel panel or placed in a 20 ml scintillation vial. Tack-free time is recorded.

[0044]

Pack A	Pack B grams	Catalyst	Catalyst amount	Observations
10 grams	2.1	Dimethylphenyl phosphine	0.6	vial gelled within 1 minute, drawdown took 7 minutes to be tack free
10 grams	2.1	Methyldiphenyl phosphine	0.06	takes 3 drops (0.06g) to gel clear
10 grams	2.1	Methyldiphenyl phosphine	0.4	bulk gelled within 1/2 minute, drawdown tack free in 1 minute
10 grams	0.0	Methyldiphenyl phosphine	0.4	Did not gel. [No thiol]

Example 4
(Acetoacetate as Michael Donor)

[0045] A mixture of Setalux 17-7202 (10.0 grams, an acetoacetate functional acrylic resin, available from Nuplex Industries Ltd., Auckland, New Zealand and propoxylated trimethylolpropane triacrylate (0.69 grams, SR-492 available from Sartomer Inc., Exton, Pennsylvania) were treated with 0.5 grams of either trioctyl phosphine or triethylamine.

No Catalyst – No change in viscosity

Triethylamine – No change in viscosity after 4 hours

Trioctyl phosphine – Gel within 10 minutes

Example 5
Clearcoat Formulation

[0046]

Pack A

Description	Formula Weight (grams)
Byk 300	0.5
Amyl propionate	19.0
Methyl isobutyl ketone	23.0
Urethane acrylate acrylic of Example D	128.6
SR-9003 (diacrylate)	20.0

Pack B

Pentaerythritol tetrakis(3-mercaptopropionate) of Example E	27.3


[0047] The above Pack A & B were mixed together and placed in one container. A 10% solution of trioctyl phosphine in butyl acetate was placed in a second container. The formulation was sprayed onto cold rolled steel panels using a Binks Model 2001 GW spray gun as described in Example 1. The clear coat dried to the touch in less than 15 seconds.

WHAT IS CLAIMED IS:

1. A method of applying to a substrate a curable composition comprising;
 - A. a polyene,
 - B. an active hydrogen containing compound,
 - C. a tertiary phosphine


wherein A and B are capable of Michael addition reaction in the presence of the tertiary phosphine; the method comprising spraying the curable composition in separate streams wherein the components A, B, and C are drawn from two or more separate containers to form the separate streams whereby the streams overlap prior to contacting the substrate and curing the composition on the substrate.

2. The method of Claim 1 in which the separate streams are separately atomized.
3. The method of Claim 2 in which the separate streams are expelled from a spray gun as separate atomized streams through a nozzle assembly.
4. The method of Claim 3 in which pressurized air is applied to the nozzle assembly.
5. The method of Claim 4 in which the nozzle assemble comprises a plurality of adjacent nozzles positioned so that the separate atomized streams intermingle and mix prior to reaching the substrate.
6. The method of Claim 1 in which (B) is a polythiol.
7. The method of Claim 1 in which the polyene is of the structure $A - (x)_m$ where A is an organic moiety, m is at least 2 and x is a group of the structure



where R is H or methyl.

8. The method of Claim 1 in which the phosphine is of the structure



where R₁, R₂, and R₃ are each independently selected from the group consisting of (cyclo)alkyl, alkaryl and aralkyl.

9. The method of Claim 8 in which R₁, R₂, and R₃ are each independently selected from alkyl having from 1 to 12 carbon atoms and aryl having 6 to 12 carbon atoms.

10. The method of Claim 1 in which (C) is present in the composition in amounts of 0.1 to 5% by weight based on weight of (A) and (B).

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2009/056502A. CLASSIFICATION OF SUBJECT MATTER
INV. B05D5/00 C08G18/00 C09D4/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B05D C08G C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 371 689 A1 (DAINIPPON INK & CHEMICALS [JP]) 17 December 2003 (2003-12-17) abstract; claims 1-12 page 4, line 14	1,8-10
X	US 5 169 979 A (KUBILLUS UWE [DE] ET AL) 8 December 1992 (1992-12-08) abstract; claims 1-5 column 9, line 54	1,6-10
X	EP 1 321 494 A1 (DAINIPPON INK & CHEMICALS [JP]) 25 June 2003 (2003-06-25) the whole document	1
	----- -/--	

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

12 October 2009

Date of mailing of the international search report

16/10/2009

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Bergmans, Koen

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2009/056502

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 2005/012394 A2 (ASHLAND INC [US]; NARAYAN-SARATHY SRIDEVI [US]; GOULD MICHAEL [US]) 10 February 2005 (2005-02-10) abstract; claims 1-58 page 5	1-10
Y	----- GIMBERT C ET AL: "Michael additions catalyzed by phosphines. An overlooked synthetic method" TETRAHEDRON, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL, vol. 61, no. 36, 5 September 2005 (2005-09-05), pages 8598-8605, XP025384019 ISSN: 0040-4020 [retrieved on 2005-09-05] the whole document	1-10
A	----- EP 1 593 728 A2 (ROHM & HAAS [US]) 9 November 2005 (2005-11-09) the whole document	1-4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2009/056502

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
EP 1371689	A1	17-12-2003	CN 1659242 A	24-08-2005
			DE 60303513 T2	28-09-2006
			ES 2254940 T3	16-06-2006
			WO 03106570 A1	24-12-2003
			JP 2004018859 A	22-01-2004
			US 2006094804 A1	04-05-2006
US 5169979	A	08-12-1992	NONE	
EP 1321494	A1	25-06-2003	CA 2414729 A1	21-06-2003
			CN 1427032 A	02-07-2003
			ES 2241946 T3	01-11-2005
			JP 2003212976 A	30-07-2003
			KR 20030053018 A	27-06-2003
			US 2003195317 A1	16-10-2003
WO 2005012394	A2	10-02-2005	BR PI0413016 A	17-10-2006
			CA 2533599 A1	10-02-2005
			CN 1856518 A	01-11-2006
			EP 1660549 A2	31-05-2006
			JP 2007500767 T	18-01-2007
			KR 20060052928 A	19-05-2006
			US 2005027082 A1	03-02-2005
EP 1593728	A2	09-11-2005	BR PI0501449 A	10-01-2006
			CN 1757655 A	12-04-2006
			JP 4218898 B2	04-02-2009
			JP 2005320539 A	17-11-2005
			US 2005245721 A1	03-11-2005