WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISH	HED I	JNDER THE PATENT COOPERATION TREATY (PCT)
(51) International Patent Classification ⁶ :		(11) International Publication Number: WO 97/29165
C09K 11/79, 11/80	A1	(43) International Publication Date: 14 August 1997 (14.08.97)
(21) International Application Number: PCT/IB9 (22) International Filing Date: 27 January 1997 (2)		DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
(30) Priority Data: 96200281.2 8 February 1996 (08.02.96) (34) Countries for which the regional or international application was filed:	E AT et a	
(71) Applicant: PHILIPS ELECTRONICS N.V. [NL/NL] newoudseweg 1, NL-5621 BA Eindhoven (NL).]; Gro	:-
(71) Applicant (for DE only): PHILIPS PATENTVERWAL GMBH [DE/DE]; Röntgenstrasse 24, D-22335 F (DE).		= (
(71) Applicant (for SE only): PHILIPS NORDEN AB [Kottbygatan 7, Kista, S-164 85 Stockholm (SE).	SE/SE	
(72) Inventors: KYNAST, Ulrich, Hermann; Prof. Holstlaar 5656 AA Eindhoven (NL). WEILER, Volker, Ulric Holstlaan 6, NL-5656 AA Eindhoven (NL).	n 6, NL :h; Pro	
(74) Agent: EVERS, Johannes, H., M.; Internationaal Octrod B.V., P.O. Box 220, NL-5600 AE Eindhoven (NL).	oiburea	1

(54) Title: LUMINESCENT SCREEN

(57) Abstract

The invention relates to a luminescent screen comprising a bearer provided with a luminescent material comprising a luminescing zeolite containing rare earth ions. According to the invention the zeolite also comprises a transition metal oxide. The absorbability for exciting UV-radiation and thereby the overall efficiency of the luminescent screen are thereby strongly enhanced.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
ΑU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
ВJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic	SD	Sudan
CF	Central African Republic		of Korea	SE	Sweden
CG	Congo	KR	Republic of Korea	SG	Singapore
СН	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LR	Liberia	SZ	Swaziland
CS	Czechoslovakia	LT	Lithuania	TD	Chad
CZ	Czech Republic	LU	Luxembourg	TG	Togo
DE	Germany	LV	Latvia	TJ	Tajikistan
DK	Denmark	MC	Monaco	TT	Trinidad and Tobago
EE	Estonia	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	UG	Uganda
FI	Finland	ML	Mali	US	United States of America
FR	France	MN	Mongolia	UZ	Uzbekistan
GA	Gabon	MR	Mauritania	VN	Viet Nam

20

25

Luminescent screen

The invention relates to a luminescent screen comprising a bearer provided with a luminescent material comprising a luminescent zeolite containing rare earth ions.

The invention also relates to luminescent zeolites for use in such a luminescent screen and a method for preparing such zeolites as well as to a low pressure mercury discharge lamp comprising such a luminescent screen.

A luminescent screen as described in the opening paragraph is known from international patent application WO 95/16759. In general a luminescent screen is used to 10 convert excitation energy into radiation with a certain range of wavelengths. The excitation energy can for instance consist of an electron beam, X-rays or UV- radiation of relatively short wavelengths. Among many other applications luminescent screens find application in lamps, particularly in low pressure mercury discharge lamps or fluorescent lamps. The excitation energy then mainly comprises UV-radiation of approximately 254 nm generated by mercury present in the plasma of the fluorescent lamp. The composition of the luminescent screen is chosen in dependence on the desired spectral composition of the light radiated by the fluorescent lamp. In the known luminescent screen the rare earth ions contained in the zeolite are Ce3+ ions. When the known luminescent screen is excited by UV radiation with a wavelength of 254 nm it emits light having an emission maximum at a wavelength between 300 and 400 nm. Such a luminescent screen can for instance be used very effectively in low pressure mercury discharge lamps for use in photochemical processes, such as polymerization, lacquer hardening, drying, curing, medical irradiation purposes or suntanning. The quantum efficiency of the zeolite in the known luminescent screen is very high. Because the rare earth ions are enclosed by the zeolite structure the known luminescent screen is also very stable in different chemical environments and within a wide temperature range. Zeolites are also generally very cheap and environment-friendly. Most of the time, however, it will be desirable that the fluorescent lamp radiates light in the visible part of the spectrum. Such an emission in the visible part of the spectrum can be realized by the incorporation of other rare earth ions in the zeolite such as e.g. Tb³⁺ ions. When a

PCT/IB97/00056 WO 97/29165 2

luminescent screen provided with a luminescent material comprising a zeolite containing Tb3+ ions is excited by means of UV-radiation with a wavelength of 254 nm, visible radiation with wavelengths within the range 450 - 650 nm is emitted by the luminescent screen. A problem, however, that is associated with many zeolites containing rare earth ions emitting visible light 5 upon excitation with UV-radiation with a wavelength of 254 nm, is that the absorption of the exciting radiation is very low so that the amount of visible light that is generated out of the exciting radiation is relatively low.

10

It is an object of the present invention to provide a luminescent screen that emits visible light upon excitation by UV-radiation with a wavelength of 254 nm, that is stable and generates a relatively large amount of visible radiation out of the exciting radiation.

15

A luminescent screen as mentioned in the opening paragraph is therefore according to the invention characterized in that the zeolite further comprises a transition metal oxide. It has been found that a luminescent screen according to the invention generates visible radiation with a relatively high efficiency when excited by UV-radiation with a 20 wavelength of 254 nm.

It has been found that relatively good results were obtained in case the number of rare earth ions per unit cell of the zeolite is at least 1. Similarly relatively good results were obtained in case the number of transition metal ions per unit cell of the zeolite is at least 1.

25

More in particular the luminescent screen had a comparably high efficiency, in case the zeolite is of the Faujasite type.

Very good results were obtained for luminescent screens wherein the rare earth metal ions comprise Tb3+ ions and/or Eu3+ ions.

Very good results were also obtained for luminescent screens wherein the transition metal oxide comprises one or more oxides chosen from the group formed by 30 molybdenum oxide, tungsten oxide, niobium oxide and tantalum oxide.

It has been observed that the luminescent screen had a comparatively high efficiency in case the zeolite was prepared by a method comprising the successive steps:

- incorporating rare earth ions into a zeolite by means of ion ex

change,

- heat treatment of the zeolite,
- incorporating a transition metal compound into the zeolite, and
- conversion of the transition metal compound into transition metal oxide.
- The incorporation of the transition metal compound can be carried out in a solution or from the gas phase. Suitable precursors of e.g. tungsten oxide are volatile or soluble species, or instance chlorides, oxychlorides or carbonyls (WCl₆, WOCl₄, W(CO)₆ and the like).

The following is a typical example of the preparation of a zeolite according to the invention.

Na_{86.9}(Al_{86.9}Si_{105.1}O₃₈₄)*264 H₂O is suspended in 18.24 ml H₂O, and the pH is adjusted to ca. 5 using 0.1 n HCl. 1.76 ml of aqueous TbCl₃ (1M) are added. The resulting solution is refluxed for 24 hours. The solid is then filtered off, washed with H₂O (3 x 20 ml) and dried at 120°C in vacuo. The resulting powder is calcined under oxygen at 400°C for 1 hour (heating-up rate 1°C/minute). The resulting first product was of the approximate formula Tb₁₆Na_{38.9}(Al_{86.9}Si_{105.1}O₃₈₄)*264 H₂O. This corresponds to approximately 16 Tb³⁺ ions per unit cell.

1 gram of the powder is brought into an evacuable glass frit, the bottom of which holds a small container with 0.5 gram W(CO)₆. The container is then held in a

20 warming bath from which W(CO)₆ is sublimed through the frit into the zeolite at a pressure lower than 0.01 mbar. The temperature can range from room temperature to 90°C. When all the W(CO)₆ has vanished from the container, the zeolite is taken from the frit and placed into a soxhlet to be extracted with THF for up to 24 hours. A white material is obtained, which is suspended in 25 ml of water and mixed with 5 ml of 30% H₂O₂ and refluxed for one hour.

25 After filtering off, the powder is heated at 600°C for two hours under an oxygen stream, which was bubbled through water before contacting the phosphor. The resulting second product was of the approximate formula Tb₁₆(WO_x)₆Na_{38.9}(Al_{86.9}Si_{105.1}O₃₈₄)*264 H₂O, wherein the value of x is not known.

It was found that the zeolite containing both Tb³⁺ ions and tungsten oxide

(second product) had an absorbability that was approximately 60 times as high as that of the zeolite containing only Tb³⁺ ions (first product). Under identical excitation conditions the amount of visible light in the spectral range between 400 and 650 nm generated by the second product is approximately 20 times as high as that generated by the first product. A relatively small amount of tungsten oxide thus raises the efficiency of the luminescing zeolite

WO 97/29165 PCT/IB97/00056

4

surprisingly much. The emission spectra of the first and the second product are practically the same.

CLAIMS:

- 1. Luminescent screen comprising a bearer provided with a luminescent material comprising a luminescent zeolite containing rare earth ions, characterized in that the zeolite further comprises a transition metal oxide.
- 2. Luminescent screen according to claim 1, wherein the rare earth ions comprise 5 Tb³⁺ ions.
 - 3. Luminescent screen according to claim 1 or 2, wherein the rare earth ions comprise Eu³⁺ ions.
- 4. Luminescent screen according to claim 1, 2 or 3, wherein the transition metal oxide comprises one or more oxides chosen from the group formed by molybdenum oxide, 10 tungsten oxide, niobium oxide and tantalum oxide.
 - 5. Luminescent screen according to one or more of the previous claims, wherein the zeolite is of the Faujasite-type.
 - 6. Luminescent screen according to one or more of the previous claims, wherein the number of rare earth ions per unit cell of the zeolite is at least 1.
- 15 7. Luminescent screen according to one or more of the previous claims, wherein the number of transition metal ions per unit cell of the zeolite is at least 1.
 - 8. Low pressure mercury discharge lamp comprising a luminescent screen according to one or more of the previous claims.
 - 9. Luminescent zeolite for use in a luminescent screen according to claim 3 or 4.
- 20 10. Method for preparing a luminescent zeolite containing rare earth ions and a transition metal oxide comprising the successive steps:
 - incorporating rare earth ions into a zeolite by means of ion exchange,
 - heat treatment of the zeolite,
 - incorporating a transition metal compound into the zeolite, and
- conversion of the transition metal compound into transition metal oxide.

INTERNATIONAL SEARCH REPORT

International application No. PCT/IB 97/00056

	101/18 3//	00000
A. CLASSIFICATION OF SUBJECT MATTER		
IPC6: C09K 11/79, C09K 11/80 According to International Patent Classification (IPC) or to bo	th national classification and IPC	
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed)	ed by classification symbols)	
IPC6: CO9K		
Documentation searched other than minimum documentation to	the extent that such documents are included	in the fields searched
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (n	arme of data base and, where practicable, sear	ch terms used)
DIALOG: WPI, CLAIMS		
C. DOCUMENTS CONSIDERED TO BE RELEVAN	T	
Category* Citation of document, with indication, where	appropriate, of the relevant passages	Relevant to claim No.
WO 9516759 A1 (PHILIPS ELECTRO 22 June 1995 (22.06.95), a		1-10
İ		
1		
Further documents are listed in the continuation of B	ox C. X See patent family annex	
Special categories of cited documents:	"T" later document published after the inter	mational filing date or priority
'A" document defining the general state of the art which is not considered to be of particular relevance	date and not in conflict with the applic the principle or theory underlying the i	ation but cited to understand
'E" ertier document but published on or after the international filing date	"X" document of particular relevance: the c	laimed invention cannot be
L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other	considered novel or cannot be consider step when the document is taken alone	ed to involve an inventive
special reason (as specified)	"Y" document of particular relevance: the c	laimed invention cannot be
means	considered to involve an inventive step combined with one or more other such	when the document is documents, such combination
P" document published prior to the international filing date but later that the priority date claimed	n being obvious to a person skilled in the "&" document member of the same patent fi	art
Date of the actual completion of the international search	Date of mailing of the international se	
	25 -05-	· · · · · · · · · · · · · · · · · · ·
7 May 1997		
lame and mailing address of the ISA/ wedish Patent Office	Authorized officer	
ox 5055, S-102 42 STOCKHOLM	 May Hallne	
acsimile No. +46 8 666 02 86	Telephone No. +46 8 782 25 00	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

02/04/97

PCT/IB 97/00056

cited	atent document in search repor	ւ	Publication date		Patent family member(s)		Publication date
WO	9516759	A1	22/06/95	EP JP US	0684975 8506854 5574332	A T A	06/12/95 23/07/96 12/11/96