



US 20160007561A9

(19) **United States**  
(12) **Patent Application Publication**  
**Lipscomb**

(10) **Pub. No.: US 2016/0007561 A9**  
(48) **Pub. Date: Jan. 14, 2016**  
**CORRECTED PUBLICATION**

(54) **EXTRUDED SELF-CLUMPING CAT LITTER**  
(71) Applicant: **Pioneer Pet Products, LLC**, Cedarburg, WI (US)  
(72) Inventor: **John M. Lipscomb**, Cedarburg, WI (US)  
(21) Appl. No.: **14/668,975**  
(22) Filed: **Mar. 25, 2015**

Sep. 11, 2012, provisional application No. 61/775,707, filed on Mar. 11, 2013, provisional application No. 61/699,858, filed on Sep. 11, 2012, provisional application No. 61/931,609, filed on Jan. 25, 2014, provisional application No. 61/952,133, filed on Mar. 12, 2014, provisional application No. 61/931,609, filed on Jan. 25, 2014, provisional application No. 61/952,133, filed on Mar. 12, 2014.

**Publication Classification**

**Prior Publication Data**  
(15) Correction of US 2015/0196005 A1 Jul. 16, 2015  
See (60) Related U.S. Application Data.  
(65) US 2015/0196005 A1 Jul. 16, 2015

(51) **Int. Cl.**  
**A01K 1/015** (2006.01)  
(52) **U.S. Cl.**  
CPC ..... **A01K 1/0152** (2013.01)

**Related U.S. Application Data**

(63) Continuation-in-part of application No. 13/868,084, filed on Apr. 22, 2013, Continuation-in-part of application No. 13/868,073, filed on Apr. 22, 2013, Continuation-in-part of application No. 13/842,534, filed on Mar. 15, 2013, Continuation-in-part of application No. 14/656,692, filed on Mar. 12, 2015, Continuation-in-part of application No. 14/605,045, filed on Jan. 26, 2015.  
(60) Provisional application No. 61/931,609, filed on Jan. 25, 2014, provisional application No. 61/952,133, filed on Mar. 12, 2014, provisional application No. 61/775,707, filed on Mar. 11, 2013, provisional application No. 61/699,858, filed on Sep. 11, 2012, provisional application No. 61/775,707, filed on Mar. 11, 2013, provisional application No. 61/699,858, filed on

(57) **ABSTRACT**  
Litter formed of extruded pellets containing water soluble binder sufficient to self-clump when wetted producing pellet clumps having a clump retention rate of at least 90% and which shrink after clump formation during drying producing a clump pulls away from any contacting solid surface minimizing adhesion therebetween. Such clumps preferably also have a crush strength of at least 15 PSI when dry. Pellets preferably contain water-soluble binder formed of starch physically modified during extrusion that solubilizes when wetted to facilitate clumping while opening the interior of the pellet improving absorption capacity. A preferred litter is formed of a mixture of extruded pellets of different sizes producing litter composed of extruded pellets falling within a plurality of different size ranges with the smaller sized pellets being fines that cause horizontally extending clumps to form on top of the litter.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7

## EXTRUDED SELF-CLUMPING CAT LITTER

### CROSS REFERENCE

**[0001]** This application claims priority in U.S. Provisional Patent Application Nos. 61/931,609 filed Jan. 25, 2014 and 61/952,133 filed Mar. 12, 2014 under 35 U.S.C. §119(e), is a continuation-in-part of each of U.S. patent application Ser. No. 14/656,692 filed Mar. 12, 2015, U.S. patent application Ser. No. 14/605,045 filed Jan. 26, 2015, each of which also claims priority in U.S. Provisional Patent Application No. 61/931,609 filed Jan. 25, 2014 and in U.S. Provisional Patent Application No. Mar. 12, 2014 under 35 U.S.C. §119(e), and is a continuation-in-part of each of U.S. patent application Ser. No. 13/868,084 filed Apr. 22, 2013, U.S. patent application Ser. No. 13/868,073 filed Apr. 22, 2013, and U.S. patent application Ser. No. 13/842,534 filed Mar. 15, 2013, each of which claims priority in U.S. Provisional Patent Application No. 61/775,707 filed Mar. 11, 2013 and in U.S. Provisional Patent Application No. 61/699,858 filed Sep. 11, 2012 under 35 U.S.C. §119(e), the entire disclosures of each of which is hereby expressly incorporated herein by reference.

### FIELD

**[0002]** The present invention is directed to cat or animal litter, and more particularly to an extruded self-clumping cat litter.

### BACKGROUND

**[0003]** Many attempts have been made in the past to try to make lightweight cat or animal litter. One type of sorbent commonly used in cat or animal litter is clay-based, typically made of bentonite granules. Conventional clay-based cat or animal litters typically have a density greater than 40 pounds per cubic feet, making them not only relatively costly to ship but relatively challenging to carry because litter containers tend to be rather heavy.

**[0004]** Conventional clay-based litter is typically made of granules of smectite, typically smectite or swelling clay(s), like bentonite clay(s), which frequently includes other components like calcium carbonate, silica, fragrances or scents, and odor controllers. While many attempts have been made in the past to produce lighter weight clay-based litters having bulk densities less than 40 pounds per cubic feet, these attempts have had limited success. Quite often litter performance is either adversely impacted or the weight reduction not all that significant.

**[0005]** While many attempts to produce lighter weight clay-based litter by adding lighter weight components are limited by the fact that such litters still require at least 70% swelling clays, typically bentonite, to still perform adequately as litter. This typically is because the lighter weight components added to reduce weight and bulk density are nothing more than fillers as they typically are not absorbent nor facilitate clumping. Because such litter still requires so much bentonite to adequately perform as a result, there is a limit to how much its weight and bulk density can be reduced.

**[0006]** One problem with a clay-based litters and clay-based sorbents in general is the fact that clay is not biodegradable. This requires spent clay-based litters to be put in the garbage for landfill disposal. For clay-based and other similar mineral or inorganic-based sorbents used to pick up oil, remediate chemical spills on land and in water, as well as treat oil

spills on land and in water, disposal is a lot more complicated and costly. Expensive high temperature treatment in a kiln is typically required, which even then does not completely dispose of everything. While ash, pebbles and rocks leftover can be used in small percentages in concrete, it still needs to be handled and transported adding to overall disposal costs.

**[0007]** Other attempts have been made to produce litter from extruded pellets. Unfortunately past attempts have been heretofore unsuccessful as such extruded pellets were poorly absorbent, needed to be crushed in order to work, needed bentonite in the admixture, would not stick or clump when wetted, and/or would not form clumps that stay together among other deficiencies.

**[0008]** What is needed is an improved lightweight cat litter that does not suffer from at least one or more of these drawbacks.

### SUMMARY

**[0009]** The present invention is directed to self-clumping litter formed of extruded sorbent litter pellets extruded from a starch-containing admixture at an extruder temperature and extruder pressure and/or extruder die pressure high enough to form water-soluble binder from starch in the admixture sufficient for pellets in a litter box to self-clump together when wetted. In a preferred litter, each pellet is extruded an admixture containing one or more cereal grains, with water-soluble binder formed in the extruded pellet from starch in the admixture during pellet extrusion sufficient to solubilize when wetted and at least become tacky enough to stick wetted pellets together forming clumps of pellets having a relatively high clump retention rate and which possess high crush strength.

**[0010]** In a preferred litter, extruded pellets have sufficient water soluble binder that pellet wetting solubilizes enough binder to at least make a portion of each wetted pellet tacky enough to stick to at least a plurality of other pellets clumping them together. In one such preferred litter, extruded pellets have sufficient water soluble binder that pellet wetting solubilizes enough binder to cause at least some of the binder to form a flowable adhesive with the wetting liquid, e.g., water or urine, which flows from the wetted pellet and around a plurality of pellets clumping them together. Where flowable adhesive is formed by wetting of extruded litter pellets with liquid, such as water, e.g., 2% saline solution, or urine, the flowable adhesive rapidly increases in viscosity after wetting from a viscosity of at least 200 centipoise within one second after wetting, increases to at least 300 centipoise after one second and within five seconds after wetting, increases to at least 400 centipoise after five seconds and within 10 seconds of wetting, and increases to at least 1000 centipoise after 10 seconds and within 30 seconds of wetting such that the liquid, e.g., water, in solubilizing water-soluble binder forms a relatively high viscosity flowable adhesive gel that relatively rapidly adheres together the at least plurality of pairs of wetted pellet forming a clump having a desirably high clump retention rate of at least 90% and which is preferably at least 92%.

**[0011]** Such a preferred litter is formed of extruded litter pellets each having a sufficient amount of water-soluble binder formed in each pellet during extrusion to self-clump when wetted. In one preferred extruded self-clumping, pellets are extruded having a water soluble content of at least 15% by pellet weight and a water soluble binder content of at least 7.5% by pellet weight. In another preferred extruded self-clumping litter, pellets are extruded having a water soluble

content of at least 15% by pellet weight and a water soluble binder content of at least 10% by pellet weight. In still another preferred extruded self-clumping litter, pellets are extruded with a water soluble binder content of at least 15% by pellet weight. In another preferred extruded granular absorbent, pellets are extruded having a water soluble content of at least 20% by pellet weight and a water soluble binder content of at least 10% by pellet weight. In a further preferred extruded self-clumping litter, pellets are extruded having a water soluble content of at least 20% by pellet weight and a water soluble binder content of at least 15% by pellet weight. Such water soluble binder preferably is a cold water soluble binder, preferably a cold water soluble amylopectin binder, and more preferably an amorphous cold water soluble amylopectin binder, formed by physical modification of starch or starches, preferably by physical modification of amylopectin, in their original form in the admixture extruded to form each self-clumping litter pellet.

**[0012]** Litter formed of such extruded pellets advantageously self-clump when wetted forming clumps each having a desirably high clump retention rate of at least 90% and which is preferably at least 92%. Litter formed of such extruded pellets advantageously self-clump when wetted forming clumps each having a clump crush strength of at least 15 pounds per square inch, preferably at least 20 pounds per square inch, and more preferably at least 25 pounds per square inch when each clump is dried.

**[0013]** Extruded litter pellets of extruded self-clumping litter form clumps that shrink after formation at least 3%, preferably at least 5%, and more preferably at least 10% helping to produce clumps having such a high clump retention rate and/or high crush strength. Litter formed of such extruded pellets of the present invention produce clumps when the cat litter is wetted that shrink and advantageously condense through absorption and drying thereby causing the clump to pull away from any solid surface in contact with the clump minimizing clump adhesion with the solid surface helping prevent any portion of the clump from sticking thereto. As a result, such cat litter formed of extruded litter pellets of the present invention form clumps that shrink when wetted also thereby produce clumps that are of nonstick construction advantageously forming "clean" "non-stick" litter clumps in accordance with another aspect of the invention.

**[0014]** In addition to litter composed of extruded litter pellets of the present invention forming clean clumps when wetted, such litter composed of at least a plurality of extruded litter pellets per cubic inch volume of the litter used in their as extruded form advantageously produce de-dusting litter by each extruded pellet used in its as-extruded form acting as a dust magnet. Without being wetted, each extruded pellet used in extruded form in litter of the present invention has sufficient water-soluble material on and in an exterior surface of each pellet to cause dust in the litter to adhere to the water-soluble material of an outer pellet surface contacting the dust preventing such dust from becoming airborne. In a preferred embodiment, without being wetted, water soluble binder present in the outer surface of each extruded pellet used in extruded form in such a low-dust litter of the invention is dust attracting causing dust in the litter to stick to the water-soluble binder of extruded uncoated pellets in the litter, while the binder is dry, preventing such dust from becoming airborne. Such de-dusting extruded self-clumping litter composed of uncoated extruded litter pellet dust-magnets in accordance with the present invention enable retail bags or containers

filled with such litter to contain less than 5% dust, preferably less than 3% dust and preferably less than 1% dust by litter weight.

**[0015]** In one preferred extruded self-clumping cat litter, the litter is formed of a mixture of extruded pellets having a plurality of different sizes that prevent liquid, e.g., water or urine, being absorbed from channeling downwardly between pellets thereby forming clumps on top of the litter which are generally horizontally oriented making such clumps easy to scoop out of the litter and dispose of. In such a preferred extruded litter, the litter has at least a plurality of pairs, i.e., at least three, of larger sized extruded litter pellets per cubic inch of litter volume of a first size range, and at least another plurality of pairs, i.e. at least three, of more finely sized extruded litter pellets per cubic inch of litter volume, e.g. fines, of a second size range smaller than the first size range. A preferred extruded self-clumping litter has at least 15% fines, preferably has at least 20% fines, with the remainder of the extruded pellets being larger sized pellets. Another preferred extruded self-clumping litter has at least 5% fines and preferably has between 5% and 40% fines, with the remainder of the extruded pellets being larger sized pellets. Still another preferred extruded self-clumping litter has at least 5% fines and preferably has between 10% fines and preferably has between 10% and 30% fines, with the remainder of the extruded pellets being larger sized pellets.

**[0016]** In one such preferred extruded self-clumping cat litter, the litter is formed of a mixture of at least a plurality of pairs, i.e., at least three, of larger sized extruded pellets per cubic inch of litter volume of a first size range, and at least another plurality of pairs, i.e. at least three, of more finely sized extruded pellets per cubic inch of litter volume, e.g. fines, of a second size range smaller than the first size range. Such fines preferably are formed of smaller sized extruded pellets having a size falling within the second size "fines" range but also can be formed of pieces of extruded pellets having a size falling within the second size "fines" range. Such an extruded self-clumping litter formed of a mixture of differently sized pellets has at least 5% fines, preferably at least 10% fines, more preferably at least 15% fines, with the remainder of the pellets of the litter being larger sized extruded pellets. Another preferred extruded self-clumping litter has at least 5% fines and preferably has between 5% and 40% fines, with the remainder of the extruded pellets being larger sized pellets. Still another preferred extruded self-clumping litter has at least 5% fines, preferably has between 5% fines and 35% fines, and more preferably has between 10% and 30% fines, with the remainder of the extruded pellets being larger sized pellets.

**[0017]** In a preferred litter embodiment, each litter pellet is extruded from an admixture not containing any smectite nor any binder additive and is used in uncoated form. In another preferred litter embodiment, each litter pellet is extruded from an admixture not containing any smectite nor any binder additive and is used without any smectite, e.g., bentonite, coating. In still another preferred litter embodiment, each litter pellet is extruded from an admixture not containing any smectite nor any binder additive and is used in its as-extruded form.

**[0018]** These and other objects, features and advantages of this invention will become apparent from the following detailed description of the invention and accompanying drawings.

## DRAWING DESCRIPTION

**[0019]** FIG. 1 is an enlarged color microscope photo of a preferred extruded granular sorbent formulated for use as cat litter of the present invention;

**[0020]** FIG. 2 is an enlarged color microscope photo of a preferred but exemplary extruded sorbent granule of the extruded granular sorbent of the present invention that is an extruded pellet used substantially in its as extruded form;

**[0021]** FIG. 3 is an enlarged color microscope photo of a second preferred but exemplary extruded sorbent granule of the extruded granular sorbent of the present invention that is an extruded pellet used substantially in its as extruded form;

**[0022]** FIG. 4 is an enlarged color photo of extruded granular sorbent formed of a plurality of pairs of extruded sorbent granules in a litter box being wetted and beginning to form a clump where the extruded sorbent granules have a plurality of different granule size ranges causing the clump to form on top of the granules making scooping of the formed clump easy;

**[0023]** FIG. 5 is an enlarged color photo of the clump of FIG. 4 after being formed during scooping of the clump using a perforate litter scoop;

**[0024]** FIG. 6 is an enlarged color photo of the clump of FIG. 4 after being lifted by the scoop from the unused sorbent granules in the litter box;

**[0025]** FIG. 7 is an enlarged color photo of the clump of FIG. 4 after all of the unused sorbent granules have been removed.

**[0026]** Before explaining one or more embodiments of the invention in detail, it is to be understood that the invention is not limited in its application to the details of construction and the arrangement of the components set forth in the following description or illustrated in the drawings. The invention is capable of other embodiments, which can be practiced or carried out in various ways. Also, it is to be understood that the phraseology and terminology employed herein is for the purpose of description and should not be regarded as limiting.

## DETAILED DESCRIPTION

**[0027]** FIGS. 1-7 illustrates a preferred embodiment of a scoopable or pourable self-clumping cat or animal litter 30 of the present invention which preferably is composed of at least a plurality of pairs, i.e., at least three, of sorbent granules 32 each formed of an extruded water soluble binder containing litter pellet 34 in accordance with the invention that preferably is extruded from starch containing material, e.g., starch-containing admixture, forming water-soluble binder during extrusion from at least some of the starch in the starch-containing material in an amount sufficient for at least one extruded litter pellet 34 to self-clump by agglutinating with a plurality of other extruded litter pellets 34 when the extruded litter pellets 34 are wetted forming a clump 36 of the extruded litter pellets 34 as depicted in FIGS. 4-7. Each litter pellet 34 is extruded from a starch-containing material, preferably starch-containing admixture, using a method of making self-clumping litter in accordance with the present invention producing extruded litter pellets 34 each containing at least 10% water soluble material, e.g., water solubles, preferably at least 15% water soluble material, and at least 7% water soluble binder, preferably at least 10% water soluble binder, by pellet weight.

**[0028]** As discussed in more detail below, litter 30 made in accordance with the present invention is relatively lightweight having a bulk density less than about 35 pounds per

cubic foot, fast absorbing being able to rapidly absorb at least one times unused or unspent litter weight in water, e.g., 2% saline solution, within sixty seconds of being wetted with the water, highly absorbent being able to absorb at least 3.5 times, preferably at least 4.5 times unused or unspent litter weight in water, e.g., 2% saline solution, which form clumps 36 having at least a 92% clump retention rate, which form clumps 36 that shrink at least 3%, preferably at least 5%, when dried, e.g., in a litter box, to a moisture content of no greater than 20% moisture by clump weight, and which form clumps 36 that are biodegradable. In a preferred litter embodiment, litter 30 made in accordance with the present invention is relatively lightweight having a bulk density less than about 35 pounds per cubic foot, fast absorbing being able to rapidly absorb at least one times unused or unspent litter weight in water, e.g., 2% saline solution, within sixty seconds of being wetted with the water, highly absorbent being able to absorb at least 3.5 times, preferably at least 4.5 times unused or unspent litter weight in water, e.g., 2% saline solution, which form clumps 36 having at least a 95% clump retention rate, which form clumps 36 that shrink at least 3%, preferably at least 5%, when dried, e.g., in a litter box, to a moisture content of no greater than 20% moisture by clump weight, and which form clumps 36 each having a crush-strength of at least 15 pounds per square inch, preferably at least 20 pounds per square inch.

**[0029]** The starch-containing material preferably is a starch-containing admixture composed of one or more cereal grains, such as one or more of corn, wheat and/or sorghum, which can be in whole grain form, de-hulled or de-corticated form, de-germed form, and/or comminuted or ground form. The starch-containing material or starch-containing admixture preferably is extruded from a single screw extruder, preferably a 50 horsepower or 100 horsepower single screw extruder, at a residency time or cooking time of no greater than 12 seconds, preferably between 4-11 seconds, and more preferably between 5-10 seconds, at an extruder pressure and/or extruder die pressure of at least 1000 pounds per square inch, and at an extruder temperature of at least 125 degrees Celsius. The starch-containing material or starch-containing admixture extruded by the extruder in accordance with such extruder operating parameters preferably has a moisture content no greater than 30%, preferably no greater than 28%, more preferably no greater than 25%, by admixture weight such that dextrinization occurs during litter pellet extrusion. In one preferred method and admixture, the admixture preferably has a moisture content no greater than 28%, preferably no greater than 25%, by admixture weight with no additional water added to the extruder during extrusion.

**[0030]** In one preferred admixture formulation, the starch-containing admixture is composed of at least 50% whole grain de-hulled or de-corticated sorghum, can be composed of as much as 40% cellulose, e.g., cellulosic fiber, and can be composed of at least 10% of other constituents including scents or fragrances, dyes or colorants, surfactant(s), antibacterial agents, anti-fungal agents, anti-parasitic agents, and the like, with the admixture having a moisture content no greater than 25%, preferably no greater than 20%, by admixture weight. In one preferred sorghum-based admixture formulation, the starch-containing admixture is composed substantially completely of whole grain de-hulled or de-corticated sorghum, preferably white sorghum, with the admixture having a moisture content no greater than 20%, preferably no greater than 18%, more preferably no greater than 15%, by admixture weight. No additional water or moisture preferably

is added to the extruder during extruder operation. In one such preferred sorghum-based admixture formulation, the starch-containing admixture is composed substantially completely of whole grain de-hulled or de-corticated sorghum, preferably white sorghum, with the admixture having a moisture content no greater than 20%, preferably no greater than 18%, more preferably no greater than 15%, by admixture weight with no water added to the admixture prior to or during extruder operation.

[0031] In a preferred litter embodiment, the litter 30 has at least a plurality of pairs of litter pellets 34 per cubic inch of the litter 30 extruded from such a starch-containing material, e.g., starch-containing admixture, which contains no smectite, e.g., contains no bentonite, and which is used in its substantially as-extruded form such that each extruded litter pellet 34 is not coated with any smectite, e.g., not coated with any bentonite. In one such preferred litter embodiment, the litter 30 is substantially completely composed of litter pellets 34 each extruded from a starch-containing material or starch-containing admixture that contains no smectite, e.g., contains no bentonite, with each litter pellet 34 used in its substantially as-extruded form in that each extruded litter pellet 34 is not coated with any smectite, e.g., not coated with any bentonite.

[0032] Each extruded litter pellet 34 preferably contains at least 7.5% of a water-soluble binder by as-extruded pellet weight formed from starch of the starch-containing material during pellet extrusion that is sufficient for wetted pellets 34 to self-clump together by agglutination where at least some water-soluble binder solubilizes when wetted causing at least an outer surface of each wetted pellet 34 to become sufficiently tacky for the wetted pellet 34 to stick to one or more adjacent pellets 34 in contact therewith. In a preferred embodiment, each extruded litter pellet 34 preferably contains at least 10% of a water-soluble binder by as-extruded pellet weight formed from starch of the starch containing material during pellet extrusion that is sufficient for wetted pellets 34 to self-clump together by agglutination where at least some water-soluble binder solubilizes when wetted causing (a) at least an outer surface of each wetted pellet 34 to become sufficiently tacky for the wetted pellet 34 to stick to one or more adjacent pellets 34 in contact therewith and/or (b) at least some of the water-soluble binder of each wetted pellet 34 to solubilize and form a flowable adhesive that flows from the wetted pellet 34 onto one or more adjacent pellets 34 adhesively gluing them together.

[0033] In one preferred embodiment, each extruded litter pellet 34 preferably contains at least 15% of a water-soluble binder by as-extruded pellet weight formed from starch of the starch containing material during pellet extrusion that is sufficient for wetted pellets 34 to self-clump together by agglutination where at least some water-soluble binder solubilizes when wetted causing (a) at least an outer surface of each wetted pellet 34 to become sufficiently tacky for the wetted pellet 34 to stick to one or more adjacent pellets 34 in contact therewith and/or (b) at least some of the water-soluble binder of each wetted pellet 34 to solubilize and form a flowable adhesive that flows from the wetted pellet 34 onto one or more adjacent pellets 34 adhesively gluing them together. In one such preferred embodiment, each extruded litter pellet 34 preferably contains at least 15% of a water-soluble binder by as-extruded pellet weight formed from starch of the starch containing material during pellet extrusion that is sufficient for wetted pellets 34 to self-clump together by agglutination where at least some water-soluble binder solubilizes when

wetted causing (a) at least an outer surface of each wetted pellet 34 to become sufficiently tacky for the wetted pellet 34 to stick to one or more adjacent pellets 34 in contact therewith and (b) at least some of the water-soluble binder of each wetted pellet 34 to solubilize and form a flowable adhesive that flows from the wetted pellet 34 onto one or more adjacent pellets 34 adhesively gluing them together.

[0034] In one preferred embodiment, each extruded litter pellet 34 preferably contains at least 20% of a water-soluble binder by as-extruded pellet weight formed from starch of the starch containing material during pellet extrusion that is sufficient for wetted pellets 34 to self-clump together by agglutination where at least some water-soluble binder solubilizes when wetted causing (a) at least an outer surface of each wetted pellet 34 to become sufficiently tacky for the wetted pellet 34 to stick to one or more adjacent pellets 34 in contact therewith and/or (b) at least some of the water-soluble binder of each wetted pellet 34 to solubilize and form a flowable adhesive that flows from the wetted pellet 34 onto one or more adjacent pellets 34 adhesively gluing them together. In one such preferred embodiment, each extruded litter pellet 34 preferably contains at least 20% of a water-soluble binder by as-extruded pellet weight formed from starch of the starch containing material during pellet extrusion that is sufficient for wetted pellets 34 to self-clump together by agglutination where at least some water-soluble binder solubilizes when wetted causing (a) at least an outer surface of each wetted pellet 34 to become sufficiently tacky for the wetted pellet 34 to stick to one or more adjacent pellets 34 in contact therewith and (b) at least some of the water-soluble binder of each wetted pellet 34 to solubilize and form a flowable adhesive that flows from the wetted pellet 34 onto one or more adjacent pellets 34 adhesively gluing them together.

[0035] The water-soluble binder formed in each extruded litter pellet 34 from starch in the admixture during extrusion preferably is a cold-water soluble binder that is water soluble at temperatures below the gelatinization temperature of the type of starch in the admixture from which the binder is formed during extrusion. In a preferred method and embodiment, the water-soluble binder formed in each extruded litter pellet 34 from starch in the admixture during extrusion preferably is a cold-water soluble binder that is water soluble at temperatures below 60 degrees Celsius or 140 degrees Fahrenheit. In one preferred method and embodiment, the water-soluble binder formed in each extruded litter pellet 34 from sorghum starch in a sorghum-containing admixture during extrusion preferably is a cold-water soluble binder that is water soluble at temperatures below the gelatinization temperature of sorghum starch and preferably is water soluble at temperatures below 60 degrees Celsius or 140 degrees Fahrenheit. In one preferred method and embodiment, the water-soluble binder formed in each extruded litter pellet 34 from corn starch in a corn-containing admixture during extrusion preferably is a cold-water soluble binder that is water soluble at temperatures below the gelatinization temperature of maize or corn starch and preferably is water soluble at temperatures below 60 degrees Celsius or 140 degrees Fahrenheit.

[0036] The cold water-soluble binder formed in each extruded litter pellet 34 from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble binder formed of starch in the admixture modified,





extrusion is a cold-water soluble modified starch binder that preferably is a cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced degree of polymerization of no greater than 2,000 glucose units, preferably has a degree of polymerization of no greater than 1,000 glucose units, and more preferably has a degree of polymerization of no greater than 500 glucose units. In one such preferred method and embodiment, the cold-water soluble binder formed in each pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that preferably is a cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have (a) a reduced molecular weight of no greater than  $10^5$ , e.g., no greater than  $10^5$  g/mol, which preferably has a molecular weight no greater than  $10^4$ , e.g., no greater than  $10^4$  g/mol, and (b) a reduced degree of polymerization of no greater than 2,000 glucose units, preferably has a degree of polymerization of no greater than 1,000 glucose units, and more preferably has a degree of polymerization of no greater than 500 glucose units.

**[0043]** In still another preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight of no greater than  $10^6$ , e.g., no greater than  $10^6$  g/mol, which preferably has a molecular weight no greater than  $10^5$ , e.g., no greater than  $10^5$  g/mol. In a preferred method and extruded litter pellet embodiment in accordance with the present invention, the cold-water soluble binder formed in each pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that preferably is a cold water soluble amylopectin binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a lesser degree of polymerization of between 6,000 glucose units and 10 glucose units, preferably between 3,000 glucose units and 10 glucose units, and more preferably between 1,000 glucose units and 10 glucose units. In one such preferred method and embodiment, the cold-water soluble binder formed in each pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that preferably is a cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have (a) a lesser molecular weight of no greater than  $10^6$ , e.g., no greater than  $10^6$  g/mol, and (b) a lesser degree of polymerization of between 6,000 glucose units and 10 glucose units. In another such preferred method and embodiment, the cold-water soluble binder formed in each pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that preferably is a cold water soluble amylopectin-based binder formed of amylopectin starch in the

admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have (a) a lower molecular weight of no greater than  $10^6$ , e.g., no greater than  $10^6$  g/mol, and (b) a lower degree of polymerization of between 3,000 glucose units and 10 glucose units. In still another such preferred method and embodiment, the cold-water soluble binder formed in each pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that preferably is a cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have (a) a molecular weight of no greater than  $10^6$ , e.g., no greater than  $10^6$  g/mol, and (b) a degree of polymerization of no greater than 1,000 glucose units, preferably between 1,000 glucose units and 10 glucose units.

**[0044]** In another preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble binder having a molecular weight of within  $\pm 75\%$  of the molecular weight of dextrin, preferably having a molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having a molecular weight of within  $\pm 75\%$  of 504.43708 g/mol. In one such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble binder having a mean molecular weight of within  $\pm 75\%$  of the mean molecular weight of dextrin, preferably having a mean molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having a mean molecular weight of within  $\pm 75\%$  of 504.43708 g/mol. In another such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble binder having an average molecular weight of within  $\pm 75\%$  of the average molecular weight of dextrin, preferably having an average molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having an average molecular weight of within  $\pm 75\%$  of 504.43708 g/mol.

**[0045]** In yet another such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble binder formed of starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight of within  $\pm 75\%$  of the molecular weight of dextrin, preferably having a molecular weight of within  $\pm 75\%$  of 504.43708,

e.g., having a molecular weight of within  $\pm 75\%$  of 504.43708 g/mol. In one such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble binder formed of starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight possessing a mean molecular weight that is within  $\pm 75\%$  of the mean molecular weight of dextrin, preferably having a mean molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having a mean molecular weight of within  $\pm 75\%$  of 504.43708 g/mol. In another such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble binder formed of starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight possessing an average molecular weight of within  $\pm 75\%$  of the average molecular weight of dextrin, preferably having an average molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having an average molecular weight of within  $\pm 75\%$  of 504.43708 g/mol.

**[0046]** In a further such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight that is within  $\pm 75\%$  of the molecular weight of dextrin, preferably having a molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having a molecular weight of within  $\pm 75\%$  of 504.43708 g/mol. In one such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight and a mean molecular weight within  $\pm 75\%$  of the mean molecular weight of dextrin, preferably having a mean molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having a mean molecular weight of within  $\pm 75\%$  of 504.43708 g/mol. In another such preferred method and extruded litter pellet embodiment, the cold water-soluble binder formed in each extruded litter pellet **34** from starch in the admixture during extrusion is a cold-

water soluble modified starch binder that possesses adhesive properties, e.g., functions as a glue, when wetted, e.g., solubilized, which preferably is a cold water soluble dextrin binder, i.e., dextrin, or dextrin-like cold water soluble amylopectin-based binder formed of amylopectin starch in the admixture modified, preferably physically modified, preferably dextrinized, e.g., physically modified via dextrinization, during extrusion to have a reduced molecular weight possessing an average molecular weight of within  $\pm 75\%$  of the average molecular weight of dextrin, preferably having an average molecular weight of within  $\pm 75\%$  of 504.43708, e.g., having an average molecular weight of within  $\pm 75\%$  of 504.43708 g/mol.

**[0047]** With reference to FIGS. **2** and **3**, each litter pellet **34** is extruded with (a) an outer surface **40** that is at least partially formed of water soluble material enabling at least a portion of the outer litter pellet surface **40** to solubilize or dissolve when wetted with liquid, such as water, e.g., 2% saline solution, urine and/or fecal matter during litter use, and (b) an interior (not shown) that also is at least partially formed of water soluble material enabling at least a portion of the outer litter pellet surface **40** to solubilize or dissolve when wetted with liquid, such as water, e.g., 2% saline solution, urine and/or fecal matter during litter use. Each extruded litter pellet **34** can have, and preferably does have a plurality of pores **42**, preferably at least a plurality of pairs, i.e., at least three, of the pores **42**, in its outer pellet surface **40** preferably formed during pellet extrusion. Each extruded litter pellet **34** can have, and preferably does have at least a plurality of voids or pockets **44**, e.g., air pockets **44**, formed in the interior of the pellet **34** preferably also formed during pellet extrusion. In a preferred extruded litter pellet embodiment, at least one and preferably at least a plurality of the pores **42** formed in the outer surface **40** of each extruded pellet **34** communicates with, e.g., is in fluid or liquid communication with, at least one of the internal voids or pockets **44** inside the pellet **34**.

**[0048]** Such a partially dissolving extruded litter pellet **34** of the present invention is not only of self-clumping construction, each such partially dissolving extruded litter pellet **34** facilitates rapid absorption of liquid when wetted substantially completely absorbing at least one times the weight of unspent or unused litter pellets **34** in water, e.g., 2% saline solution, urine and/or liquid fecal matter within ninety seconds, preferably within sixty seconds, such that all of the water, urine and/or liquid fecal matter is retained by the resultant clump **36** of wetted pellets **34** that forms. Such a partially dissolving extruded litter pellet **34** of the present invention facilitates more rapid and more complete liquid absorption by having pores **42** in the outer surface **40** of each pellet **34** through which water, urine and/or liquid fecal matter is drawn into each wetted pellet **34** during litter use including via wicking, surface tension and/or capillary action. Such a partially dissolving extruded litter pellet **34** of the present invention also facilitates more rapid and more complete liquid absorption by having at least a plurality pores **42** in the outer surface **40** of each pellet **34** each being in fluid-flow or liquid-flow communication with at least one inner void or pocket **44** enabling water, urine and/or liquid fecal matter drawn into each one of the plurality of pores **42** to be relatively rapidly channeled through the pores **42** into a corresponding inner void or pocket **44** including via wicking, surface tension and/or capillary action. This channeling

action enables a greater volume of water, urine and/or liquid fecal matter to be more rapidly absorbed into each extruded litter pellet **34**.

[0049] In addition, the partially dissolving construction of each extruded litter pellet **34** of the present invention further facilitates more rapid absorption as water soluble portions of the pellet outer surface **40** and interior substantially instantaneously solubilize within two seconds, preferably within one second, of being wetted increasing the absorption volume of and within each pellet **34** within two seconds, preferably within one second, of being wetted. Water soluble material of the outer surface **40** of each wetted pellet **34** not only solubilizes or dissolves producing flowable adhesive that self-clumps wetted pellets **34** together but also creates at least a plurality of pores in addition to the pores **42** originally formed during pellet extrusion providing additional liquid-absorbing pathways or channels into the interior of each wetted pellet **34**. The water soluble material of the outer surface **40** of each wetted pellet **34** also enlarges at least one and preferably enlarges at least a plurality of the pre-existing pores **42** enabling each liquid-solubilized enlarged pore **42** to allow a greater volume of liquid to enter not only increasing wetted pellet absorption capacity but also increasing the rate of liquid absorption. Water soluble material of the interior of each wetted pellet **34** not only solubilizes or dissolves producing flowable adhesive that self-clumps wetted pellets **34** together but also creates one or more voids or pockets (not shown) within each wetted pellet **34** that provides additional liquid-absorbing pathways or channels into the interior of each wetted pellet **34** thereby advantageously increasing the amount or volume of liquid each partially dissolved wetted pellet **42** absorbs during litter use.

[0050] Such a partially dissolving extruded litter pellet construction formed during extrusion results in extruded litter pellets **34** of the present invention being able to rapidly absorb one times its weight in water, e.g., 2% saline solution, in less than ninety seconds, preferably less than sixty seconds, absorbs at least 3.5 times litter pellet weight in water, e.g., 2% saline solution, and preferably is capable of absorbing more than 4.5 times litter pellet weight in water, e.g., 2% saline solution, during litter use.

[0051] With additional reference to FIGS. 4-7, when a liquid, such as the stream of water **50**, e.g., 2% saline solution, or urine, shown in FIG. 4 being poured onto unspent or unused litter pellets **34** of litter **30** of the present invention, the litter pellets **34** wetted by the water **50** not only substantially completely absorb the water **50** but solubilize water-soluble binder in each pellet **34** causing a clump **36** (FIGS. 5-6) of at least a plurality of pairs, i.e. at least three, of wetted granules **32** to form. As a result of the partially dissolving enhanced liquid absorption extruded litter pellet construction of the present invention, the result clump **36** formed is produced by unspent or unused extruded litter pellets **34** rapidly absorbing between one time and four times unspent or unused extruded litter pellet weight in water, e.g., 2% saline solution, or urine within three minutes, preferably within two minutes, of pellet wetting relatively rapidly forming a scoopable clump within three minutes, preferably within two minutes of pellet wetting.

[0052] With reference to FIG. 5, when clump formation is complete in as little as 30 seconds to three minutes, a discrete clump **36** of litter pellets **34** of spent litter **38** is formed that can be removed using a perforate litter scoop **48** from the unspent litter **30** remaining in the litter box **46** (FIG. 6). What

remains after scooping is a fully formed clump **36** of spent litter **38** that can be easily disposed of. In a preferred embodiment, such a clump **36** formed of pellets **34** of spent litter **38** is biodegradable and preferably toilet flushable.

[0053] With continued reference to FIGS. 1-7, a preferred embodiment of litter **30** in accordance with the present invention is composed of at least a plurality of differently sized extruded litter pellets **34**, **34'** which facilitate absorption of liquid during litter use by more quickly and efficiently absorbing liquid wetting the pellets **34**, **34'** by wetting and being absorbed by the pellets **34**, **34'** while also minimizing how deeply the liquid flows downwardly into the litter **30** before being completely absorbed by the pellets **34**, **34'**. The use of at least a plurality of differently sized extruded litter pellets **34**, **34'** produces litter **30** that clumps when wetted producing a clump **36** of a plurality of wetted extruded litter pellets **34**, **34'** that forms on top of the litter **30** with the clump **36** being generally horizontally oriented on top of the litter **30** making the clump **36** easy to scoop from the rest of the unspent litter **30**.

[0054] Such a preferred litter **30** of the present invention has at least a plurality of pairs of larger extruded litter pellets **34** per cubic inch of litter **30** falling within a first size range and at least a plurality of pairs of more finely sized extruded litter pellets **34'**, e.g., fines, per cubic inch of litter **30** falling within a second size range that is smaller than the larger extruded litter pellets **34**. In a preferred embodiment, the larger sized pellets **34** have a size falling within a first size range each having a size no greater than 3 mm in length, width and/or diameter and no smaller than 1 mm in length, width and/or diameter. The smaller sized pellets **34'**, also referred to as fines **34'**, have a size smaller than 1 mm in length, width and/or diameter filling in the spaces or voids between the larger pellets **34** in a resultant litter **30** formed of a mixture thereof. In one such preferred embodiment, extruded litter pellets **34** having a size larger than 3 mm in length, width and/or diameter are not included in the resultant litter mixture of the present invention such as by filtering, screening or sieving such unwanted extruded pellets that are too large. In another such preferred embodiment, extruded litter pellets **34'** having a size smaller than 0.5 mm in length, width and/or diameter are not included in the resultant litter mixture of the present invention such as by filtering, screening or sieving to eliminate or otherwise remove such unwanted extruded pellets that are too small. In still another such preferred embodiment, extruded litter pellets **34** having a size larger than 3 mm in length, width and/or diameter and extruded litter pellets **34'** having a size smaller than 0.5 mm in length, width and/or diameter are not included in the resultant litter mixture of the present invention.

[0055] In another preferred embodiment, the larger sized pellets **34** have a size falling within a first size range each having a size no greater than about 2.8 mm in length, width and/or diameter and no smaller than 1.2 mm, preferably no smaller than about 1.18 mm, in length, width and/or diameter. The smaller sized pellets **34'**, also referred to as fines **34'**, have a size smaller than 1.2 mm, preferably smaller than about 1.180 mm, in length, width and/or diameter filling in the spaces or voids between the larger pellets **34** in a resultant litter **30** formed of a mixture thereof. In one such preferred embodiment, extruded litter pellets **34** having a size larger than about 2.8 mm in length, width and/or diameter are not included in the resultant litter mixture of the present invention such as by filtering, screening or sieving such unwanted

extruded pellets that are too large. In another such preferred embodiment, extruded litter pellets **34'** having a size smaller than about 0.8 mm, preferably smaller than about 0.710 mm in in length, width and/or diameter are not included in the resultant litter mixture of the present invention such as by filtering, screening or sieving to eliminate or otherwise remove such unwanted extruded pellets that are too small. In still another such preferred embodiment, extruded litter pellets **34** having a size larger than about 2.8 mm in in length, width and/or diameter and extruded litter pellets **34'** having a size smaller than about 0.710 mm in in length, width and/or diameter are not included in the resultant litter mixture of the present invention.

**[0056]** In still another preferred embodiment, the larger sized pellets **34** have a size falling within a first size range each having a size no greater than 2.9 mm, preferably no greater than about 2.8 mm, in length, width and/or diameter and no smaller than 1.2 mm, preferably no smaller than about 1.18 mm, in length, width and/or diameter. The smaller sized pellets **34'**, also referred to as fines **34'**, have a size smaller than 1.2 mm, preferably smaller than about 1.180 mm, in length, width and/or diameter and have a size larger than 0.5 mm, preferably larger than about 0.710 mm, in length, width and/or diameter thereby filling in the spaces or voids between the larger pellets **34** in a resultant litter **30** formed of a mixture thereof.

**[0057]** A preferred extruded self-clumping litter **30** has at least 15% fines **34'**, preferably has at least 20% fines **34'**, with the remainder of the extruded pellets of the litter **30** being larger sized pellets **34**. Another preferred extruded self-clumping litter **30** has at least 5% fines **34'** and preferably has between 5% and 40% fines **34'**, with the remainder of the extruded pellets **34** being larger sized extruded pellets. Still another preferred extruded self-clumping litter **30** has at least 5% fines **34'** and preferably has between 10% fines **34'** and preferably has between 10% and 30% fines **34'**, with the remainder of the pellets of the litter **30** being larger sized pellets **34**. Still preferred extruded self-clumping litter **30** has at least 5% fines **34'** and preferably has between 5% and 40% fines **34'**, with the remainder of the extruded pellets being larger sized pellets **34**. Still another preferred extruded self-clumping litter **30** has at least 5% fines **34'**, preferably has between 10% and 25% fines **34'**, and more preferably has between 15% and 35% fines **34'**, with the remainder of the extruded pellets being larger sized pellets **34**.

**[0058]** As a result, liquid wetting the extruded litter pellets **34, 34'** during litter use is more rapidly absorbed at or close to the surface of the litter **30** preventing the liquid from flowing deeper producing clumps **36** on top of the surface of the litter **30** that are generally horizontally oriented. As a result, such clumps **36** lie on top of the surface of the litter **30** making them quick and easy to scoop out of the rest of the unspent litter remaining in the litter box and dispose of.

**[0059]** Each extruded litter pellet **34** and/or **34'** preferably is extruded using a single screw extruder from a starch-containing admixture formed of one or more cereal grains, such as one or more of corn, wheat, sorghum, rice or another cereal grain, which can be ground or otherwise comminuted prior to extrusion, extruding pellets **34** and/or **34'** each having enough water soluble binder to cause litter **30** composed of a mixture of medium sized pellets **34** and more finely sized pellets **34'** of the present invention to self-clump when wetted with water, e.g., 2% saline solution, urine, and/or liquid fecal matter. In a preferred method of making such extruded pellets **34** and/or

**34'** each pellet **34** and/or **34'** is extruded from such a starch-containing admixture that preferably is composed of one or more cereal grains under an extruder pressure and temperature operating parameters and conditions that produce extruded pellets **34** and/or **34'** each containing at least 15% water solubles, e.g., at least 15% water soluble content, by extruded pellet weight and each containing at least 7.5% water soluble binder, preferably at least 10% water soluble binder, by extruded pellet weight with at least the water soluble binder preferably formed by physical modification of starch in the admixture during pellet extrusion in accordance with that discussed hereinabove.

**[0060]** In one preferred method, the admixture extruded to form the pellets **34** and/or **34'** has a moisture content of no greater than 30%, preferably no more than 25%, by admixture weight before entering the extruder. In one such preferred method, no water or other moisture is added during extrusion. In one preferred admixture, the admixture is formed of at least 60% corn, preferably at least 70% corn, preferably commmeal, by admixture weight, e.g., dry admixture weight, which can be de-germed, having a moisture content of no greater than 30%, preferably no greater than 25%, by admixture weight when entering the extruder. Such an admixture can include as much as 40%, preferably no greater than 30% cellulosic material, such as in the form of plant fiber, pine fiber, oat fiber, wheat fiber, alfalfa, sawdust, recycled newsprint, or another type of cellulosic material. In another preferred admixture, the admixture preferably is formed of at least 60% sorghum, preferably at least 70% sorghum, by admixture weight, e.g., dry admixture weight, which can be and preferably is whole grain sorghum, which can be de-hulled or de-corticated, having a moisture content no greater than 20%, preferably no greater than 15%, by admixture weight when entering the extruder. Such an admixture can also include as much as 40%, preferably no greater than 30% cellulosic material, such as in the form of plant fiber, pine fiber, oat fiber, wheat fiber, alfalfa, sawdust, recycled newsprint, or another type of cellulosic material.

**[0061]** Another such preferred admixture from which extruded pellets **34** and/or **34'** are formed includes one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, can include a gray or black dye or colorant, preferably carbon black, preferably no more than 5% carbon black, more preferably no more than 1% carbon black (by admixture weight), and can include cellulose, such as in the form of one or more cellulosic materials and/or cellulose-containing fibers. A preferred admixture contains at least 50% starch containing material in the form of one or more cereal grains and preferably contains no more than 50% cellulose by admixture weight. A preferred starch containing material is formed of at least 50% corn, preferably at least 60%, and more preferably at least 70% by dry admixture weight (before any water is added to the admixture) preferably in comminuted form, such as preferably in the form of commmeal that can include and preferably does include de-germed commmeal. Where the admixture includes cellulose or cellulosic material, the remainder of the admixture can be composed of preferred cellulose and cellulosic materials that include one or more of sawdust, pine shavings or fibers, other types of wood shavings or fibers, oat fiber, alfalfa, rice fiber, beet fiber or another type of cellulose or cellulosic fiber. Such an admixture preferably contains no separate binder additive like guar gum, smectite, e.g., bentonite, or the like added specifically to facilitate clumping. One such preferred admixture contains

no more than 40% cellulose or cellulosic material, e.g., fiber, with the remainder of the admixture composed substantially completely of one or more cereal grains with no more than 5%, preferably no more than 1% carbon black, by admixture weight.

**[0062]** In a preferred method of extruding pellets **34** and/or **34'** from such admixtures, the admixture is extruded using a single screw extruder at an extruder pressure of at least 900 pounds per square inch and at a temperature of at least 100° Celsius extruding at least a plurality of pairs of extruded pellets **34**, **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 15%, preferably at least 20%, by extruded pellet weight containing at least 7.5%, preferably at least 10%, water soluble binder by extruded pellet weight. In another preferred method of extruding pellets **34** and/or **34'** from such admixtures, the admixture is extruded using a single screw extruder at an extruder pressure of at least 1,000 pounds per square inch and at a temperature of at least 120° Celsius extruding at least a plurality of pairs of extruded pellets **34** and/or **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 15%, preferably at least 18%, by pellet weight containing at least 7.5%, preferably at least 10%, more preferably at least 12%, water soluble binder by pellet weight. In still another preferred method of extruding pellets **34** from such admixtures, the admixture is extruded using a single screw extruder at an extruder pressure of at least 1,100 pounds per square inch and at a temperature of at least 130° Celsius extruding at least a plurality of pairs of extruded pellets **34** and/or **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 15%, preferably at least 18%, more preferably at least 20% by pellet weight containing at least 7.5%, preferably at least 10%, more preferably at least 15%, water soluble binder by pellet weight. In a further preferred method of extruding pellets **34** and/or **34'** from such admixtures, the admixture is extruded using a single screw extruder at an extruder pressure of at least 1,200 pounds per square inch and at a temperature of at least 135° Celsius extruding at least a plurality of pairs of extruded pellets **34** and/or **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 18%, preferably at least 20%, more preferably at least 25% by pellet weight containing at least 8%, preferably at least 12%, more preferably at least 18%, water soluble binder by pellet weight.

**[0063]** The water soluble binder formed in each pellet **34** and/or **34'** during extrusion preferably is a cold water soluble binder formed from starches in a starch containing admixture preferably forming at least 7.5% cold water soluble binder, preferably at least 10% cold water soluble binder, and more preferably at least 15% cold water soluble binder in each pellet **34** and/or **34'** by pellet weight. Where cold water soluble binder is formed in each pellet **34** and/or **34'** during extrusion, cold water soluble amylopectin binder preferably is formed from amylopectin starch in such a starch containing admixture preferably forming at least 7.5% cold water soluble amylopectin binder, preferably at least 10% cold water soluble amylopectin binder, and more preferably at least 15% cold water soluble amylopectin binder in each pellet **34** and/or **34'** by pellet weight. In at least one preferred extruded pellet embodiment, each extruded pellet **34** and/or

**34'** has at least 15%, preferably at least 18%, and more preferably at least 20% cold water soluble amylopectin binder by pellet weight.

**[0064]** Where cold water soluble amylopectin-based binder is formed in each pellet **34** and/or **34'** during extrusion, the cold water soluble amylopectin binder can be or include amorphous cold water soluble amylopectin binder formed from amylopectin starch in such a starch containing admixture preferably forming at least 7.5% amorphous cold water soluble amylopectin binder, preferably at least 10% amorphous cold water soluble amylopectin binder, and more preferably at least 15% amorphous cold water soluble amylopectin binder in each pellet **34** and/or **34'** by pellet weight. In one such preferred extruded pellet embodiment where amorphous cold water soluble amylopectin binder is formed during pellet extrusion, each pellet **34** and/or **34'** has at least 15%, preferably at least 18%, and more preferably has at least 20%, amorphous cold water soluble amylopectin binder by pellet weight.

**[0065]** The amount of water solubles or water soluble content of each extruded pellet **34** and/or **34'** is specified in terms of a percentage of the extruded pellet weight indicating what weight percentage of the pellet **34** and/or **34'** is composed of modified starch, preferably starch modified during pellet extrusion, more preferably physically modified during extrusion, which is water soluble when wetted with water, e.g., 2% saline solution, and/or urine at a temperature below which it is cold water soluble as known in the field of starch chemistry. In a preferred embodiment, the amount of water solubles or water soluble content of each extruded pellet **34** and/or **34'** is specified in terms of a percentage of the extruded pellet weight indicating what weight percentage of the pellet **34** and/or **34'** is composed of modified starch, preferably starch modified during pellet extrusion, more preferably physically modified during extrusion, which is water soluble when wetted with water, e.g., 2% saline solution, and/or urine at a temperature below 160 degrees Celsius such that it is cold water soluble as known in the field of starch chemistry.

**[0066]** The cold water soluble binder present in the extruded pellets **34** and/or **34'** of litter **30** of the present invention advantageously therefore remains cold water soluble at temperatures below 110° Fahrenheit providing real world urine solubility by dissolving in liquid at temperatures as high as 110° Fahrenheit, including dissolving when wetted with or by cat urine that typically has a temperature no higher than about 108° Fahrenheit. The cold water soluble content of each extruded pellet **34** and/or **34'** includes starch from the one or more cereal grains in the admixture modified during extrusion, preferably by being physically modified during extrusion, to become water-soluble, preferably cold water soluble, and includes amylopectin in the admixture modified during extrusion into cold water soluble amylopectin. The water soluble content of each extruded pellet **34** and/or **34'** is inclusive of any water soluble binder present in the extruded pellet **34** and/or **34'**.

**[0067]** During granular sorbent use, wetting of at least a plurality of pairs, i.e. at least three, of extruded litter pellets **34**, **34'** of a preferred mixture of litter **30** of the present invention with water, preferably 2% saline solution at room temperature e.g. between 68° F. and 74° F., forms a clump **36**, such as shown in FIGS. 6 and 7, containing at least a plurality of pairs, i.e., at least three, of wetted pellets **34** and wetted pellets **34'** that self-clump together as a result of water soluble binder in each of the wetted pellets **34**, **34'** solubilizing and

making each wetted pellet **34** and **34'** tacky enough to stick to one or more pellets **34** and/or **34'** in contact therewith. In a preferred litter embodiment, the litter **30** is formed of at least a plurality of pairs of extruded pellets **34** and of at least a plurality of pairs of extruded pellets **34'** each having water-soluble binder in an amount sufficient for at least some of the binder to solubilize and flow from the wetted pellets **34** and **34'** in between and around at least a plurality of adjacent pellets **34** and/or **34'**. Water-soluble binder of a plurality of wetted pellets **34** and a plurality of wetted pellets **34'** that has solubilized and formed flowable adhesive with water, e.g. 2% saline solution, wets the pellets **34** and pellets **34'** relatively rapidly forming clump **36** as the flowable adhesive formed by the water in solubilize binder rapidly increases in viscosity immediately upon the pellets **34** and **34'** being wetted with the water.

[0068] In a preferred embodiment, during wetting of such a plurality of pairs of pellets **34** and **34'** where 400 grams of extruded pellets **34** and **34'** are wetted with 200 grams of water, e.g., 2% saline solution, at room temperature, e.g., between 68° F. and 74° F., the viscosity at pellet wetting or at the beginning of pellet wetting as measured with a Brookfield DV3T viscometer at a spindle rotation of 50 RPM rapidly increases from about 1 centipoise at wetting as the water solubilizes water-soluble binder in each wetted pellet **34** and **34'** forming a flowable adhesive whose viscosity increases to at least 200 centipoise within one second after pellet wetting, increases to at least 300 centipoise after one second and within five seconds after pellet wetting, increases to at least 400 centipoise after five seconds and within 10 seconds of pellet wetting such that the water in solubilizing water-soluble binder forms a relatively high viscosity flowable adhesive gel that relatively rapidly adheres together the at least plurality of pairs of wetted pellets **34** and **34'** forming clump **36**. In another preferred embodiment, during wetting of such a plurality of pairs of pellets **34** and **34'** where 200 grams of extruded pellets **34** and **34'** are wetted with 200 grams of water, e.g., 2% saline solution, at room temperature, the viscosity at pellet wetting or at the beginning of pellet wetting as measured with a Brookfield DV3T viscometer at a spindle rotation of 50 RPM rapidly increases from about 1 centipoise at the time of initial pellet wetting as the water solubilizes water-soluble binder in each wetted pellet **34** and **34'** forming a flowable adhesive whose viscosity increases to at least 400 centipoise within one second after pellet wetting, increases to at least 500 centipoise after one second and within five seconds after pellet wetting, increases to at least 700 centipoise after five seconds and within 10 seconds of pellet wetting, increases to at least 1000 centipoise after 10 seconds and within 20 seconds of pellet wetting, increases to at least 1800 centipoise after 20 seconds and within 25 seconds of pellet wetting, increases to at least 2500 centipoise after 25 seconds and within 30 seconds of pellet wetting, increases to at least 5000 centipoise after 30 seconds and within 40 seconds of pellet wetting such that the water in solubilizing water-soluble binder forms a relatively high viscosity flowable adhesive gel that relatively rapidly adheres together the at least plurality of pairs of wetted pellets **34** and **34'** forming clump **36**.

[0069] A preferred extruded pellet **34** and/or **34'** is formed by extruding an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, without any separate binder additive or smectite in the admixture, at such aforementioned extruder pressures and/or

temperatures with such extruder pressures and/or temperatures extruding pellets **34** and/or **34'** that are dextrinized and which can be expanded or puffed with each pellet **34** and/or **34'** having at least 15% water soluble content by pellet weight and at least 7.5% water soluble binder content by pellet weight sufficient to not only facilitate liquid absorption when wetted during sorbent use but which also self-clump together forming clumps, e.g. clump **36**, when wetted during sorbent use. Another preferred extruded pellet **34** and/or **34'** is formed by extruding such an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, without any separate binder additive or smectite such as bentonite in the admixture, at an extruder temperature and pressure at or above which it is sufficient to extrude pellets **34** and/or **34'** each having at least 15% water soluble content by pellet weight and at least 7.5%, preferably at least 10%, water soluble binder content by pellet weight. Still another preferred extruded pellet **34** and/or **34'** is formed by extruding such an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, without any separate binder additive or smectite, including bentonite, in the admixture, at an extruder temperature and pressure at or above which it is sufficient to extrude pellets **34** and/or **34'** each having at least 18% water soluble content by pellet weight and at least 10%, preferably at least 12%, water soluble binder content by pellet weight. A further preferred extruded pellet **34** and/or **34'** is formed by extruding such an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, without any separate binder additive or smectite, such as bentonite, in the admixture, at an extruder temperature and pressure at or above which it is sufficient to extrude pellets **34** and/or **34'** each having at least 20% water soluble content by pellet weight and at least 12%, preferably at least 15%, water soluble binder content by pellet weight. A still further preferred extruded pellet **34** and/or **34'** is formed by extruding an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, without any separate binder additive or smectite, including bentonite, in the admixture, at an extruder temperature and pressure at or above which it is sufficient to extrude pellets **34** and/or **34'** each having at least 25% water soluble content by pellet weight and at least 10%, preferably at least 15%, and more preferably at least 18%, water soluble binder content by pellet weight. Yet another preferred extruded pellet **34** and/or **34'** is formed by extruding an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, without any separate binder additive or smectite in the admixture, at an extruder temperature and pressure at or above which it is sufficient to extrude pellets **34** and/or **34'** each having at least 25% water soluble content by pellet weight and at least 15%, preferably at least 18%, and more preferably at least 20%, water soluble binder content by pellet weight.

[0070] The water soluble content of each extruded pellet **34** and/or **34'** preferably is composed of amorphous cold water soluble amylopectin material and the water soluble binder content of each extruded pellet **34** and/or **34'** preferably is formed of amorphous cold water soluble amylopectin binder having a molecular weight less than that of the unmodified amylopectin starch of the cereal grain or cereal grains of the admixture from which each pellet **34** and/or **34'** was extruded. In a preferred extruded pellet embodiment, the water soluble content of each extruded pellet **34** and/or **34'** preferably is

composed of amorphous cold water soluble amylopectin material and the water soluble binder content of each extruded pellet **34** and/or **34'** preferably is formed of amorphous cold water soluble amylopectin binder having a molecular weight less than that of the unmodified amylopectin starch of the cereal grain or cereal grains of the admixture from which each pellet **34** and/or **34'** was extruded and preferably a mean molecular weight within  $\pm 80\%$  of the mean molecular weight of the unmodified amylose starch of the cereal grain or cereal grains of the admixture from which each pellet **34** and/or **34'** was extruded.

**[0071]** Each extruded pellet **34** and/or **34'** can and does have at least 3%, preferably at least 5%, of a dextrin-like water soluble adhesive binder by pellet weight that preferably is a cold water soluble adhesive binder having a mean molecular weight within  $\pm 90\%$  of the mean or average molecular weight of dextrin. In a preferred extruded pellet embodiment, each pellet **34** and/or **34'** has at least 3%, preferably at least 5%, of a dextrin-like cold water soluble binder, i.e., dextrin, by pellet weight that has a molecular weight within  $\pm 90\%$  of 504,43708 g/mol, which is the CAS molecular weight of dextrin. In another preferred extruded pellet embodiment, each pellet **34** and/or **34'** has at least 3% dextrin and preferably has at least 5% dextrin by pellet weight.

**[0072]** A preferred extruded pellet **34** and/or **34'** is formed by extruding an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and/or wheat, at an admixture moisture content of no greater than 30%, preferably with no water added in the extruder during extrusion from a single screw extruder at an extruder temperature of at least 100° Celsius and an extruder pressure of at least 900 pounds per square inch to extrude a plurality of extruded pellets **34** and/or **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 15% by pellet weight containing at least 7.5% water soluble binder by pellet weight. Another preferred extruded pellet **34** and/or **34'** is formed by extruding an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and wheat, at an admixture moisture content of no greater than 25%, preferably with no water added in the extruder during extrusion at an extruder temperature of at least 120° Celsius and an extruder pressure of at least 1,000 pounds per square inch to extrude a plurality of extruded pellets **34** and/or **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 18% by pellet weight containing at least 10% water soluble binder by pellet weight. Still another preferred extruded pellet **34** and/or **34'** is formed by extruding an admixture containing one or more cereal grains, preferably one or more of corn, sorghum and wheat, at an admixture moisture content of no greater than 23%, preferably with no water added in the extruder during extrusion at an extruder temperature of at least 125° Celsius and an extruder pressure of at least 1,100 pounds per square inch to extrude a plurality of extruded pellets **34** and/or **34'** per second of extruder operation with each extruded pellet **34** and/or **34'** having a water soluble content of at least 20% by pellet weight containing at least 13%, preferably at least 15%, and more preferably at least 18%, water soluble binder by pellet weight.

**[0073]** Each extruded pellet **34** and/or **34'** can be and preferably is composed of or with at least 3%, preferably at least 5%, more preferably at least 7.5%, of a dextrin-like water soluble adhesive binder by pellet weight that preferably is a cold water soluble adhesive binder having a mean molecular

weight within  $\pm 90\%$  of the mean or average molecular weight of dextrin. In a preferred extruded pellet embodiment, each pellet **34** and/or **34'** has at least 3%, preferably at least 5%, more preferably at least 7.5%, of a dextrin-like cold water soluble binder having a molecular weight within  $\pm 90\%$  of 504.43708 g/mol. In another preferred extruded pellet embodiment, each pellet **34** and/or **34'** has at least 3% dextrin by pellet weight, preferably has at least 5% dextrin by pellet weight, and more preferably has at least 7.5% dextrin by pellet weight.

**[0074]** A preferred extruded pellet **34** and/or **34'** used as or in making litter **30** of the present invention is extruded from one or more cereal grains and has at least 15% cold water soluble content by pellet weight and preferably has at least 7.5%, preferably at least 10%, more preferably at least 13%, cold water soluble binder content by pellet weight with the water soluble binder content present in each pellet **34** and/or **34'** preferably being cold water soluble modified amylopectin starch binder that preferably is an amorphous cold water soluble amylopectin starch binder. Preferably, each pellet **34** and/or **34'** has at least 15% cold water solubles by pellet weight and at least 7.5%, preferably at least 10%, more preferably at least 13%, cold water soluble binder formed of cold water soluble amylopectin starch binder, preferably cold water soluble amorphous amylopectin starch binder, formed of amylopectin starch modified so its molecular weight has been reduced to a molecular weight below  $10^6$ , e.g.,  $10^6$  g/mol. In another preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 15% by pellet weight and a cold water soluble amylopectin starch binder content of at least 7.5%, preferably at least 10%, more preferably at least 13%, formed of reduced molecular weight physically modified amylopectin having a degree of polymerization of less than 6,000 glucose units, preferably less than 3,000 glucose units, more preferably less than 1,000 glucose units. In yet another such preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 15% by pellet weight and a cold water soluble amylopectin starch binder content of at least 7.5%, preferably at least 10%, more preferably at least 13%, formed of reduced molecular weight physically modified amylopectin having a degree of polymerization falling between 6,000 and 10 glucose units. In a further such preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 15% by pellet weight and a cold water soluble amylopectin starch binder content of at least 7.5%, preferably at least 10%, more preferably at least 13%, formed of reduced molecular weight physically modified amylopectin having a degree of polymerization falling between 500 and 10 glucose units. In one such preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 15% by pellet weight and a cold water soluble amylopectin starch binder content of at least 7.5%, preferably at least 10%, more preferably at least 13%, formed of reduced molecular weight modified amylopectin having a molecular weight no greater than  $10^6$  g/mol and a degree of polymerization falling between 10 and 6,000 glucose units. In another such preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 15% by pellet weight and a cold water soluble amylopectin starch binder content of at least 7.5%, preferably at least 10%, more preferably at least 13%, formed of reduced molecular weight modified amylopectin having a molecular weight no greater than  $10^5$  g/mol and a degree of polymerization falling between 10 and 500 glucose units.

[0075] Another preferred extruded pellet **34** and/or **34'** is extruded from one or more cereal grains and has at least 20% cold water soluble content by pellet weight and preferably has at least 15%, preferably at least 18%, more preferably at least 20%, cold water soluble binder content by pellet weight with the water soluble binder content present in each pellet **34** and/or **34'** preferably being cold water soluble modified amylopectin starch binder that preferably is an amorphous cold water soluble amylopectin starch binder. Preferably, each pellet **34** and/or **34'** has at least 25% cold water solubles by pellet weight and at least 15%, preferably at least 18%, more preferably at least 23%, cold water soluble binder formed of cold water soluble amylopectin starch binder, preferably cold water soluble amorphous amylopectin starch binder, formed of amylopectin starch modified so its molecular weight has been reduced to a molecular weight no greater than  $10^6$ , e.g.,  $10^6$  g/mol. In another preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 20% by pellet weight and a cold water soluble amylopectin starch binder content of at least 15%, preferably at least 18%, more preferably at least 20%, formed of reduced molecular weight modified amylopectin having a degree of polymerization falling between 10 and 6,000 glucose units. In yet another preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 20% by pellet weight and a cold water soluble amylopectin starch binder content of at least 15%, preferably at least 18%, more preferably at least 20%, formed of reduced molecular weight modified amylopectin having a degree of polymerization falling between 10 and 500 glucose units. In one such preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 25% by pellet weight and a cold water soluble amylopectin starch binder content of at least 15%, preferably at least 18%, more preferably at least 23%, formed of reduced molecular weight modified amylopectin having a molecular weight no greater than  $10^6$ , e.g.,  $10^6$  g/mol, and a degree of polymerization falling between 10 and 6,000 glucose units. In another such preferred embodiment, each pellet **34** and/or **34'** has a cold water soluble content of at least 25% by pellet weight and a cold water soluble amylopectin starch binder content of at least 15%, preferably at least 18%, more preferably at least 23%, formed of reduced molecular weight modified amylopectin having a molecular weight no greater than  $10^6$ , e.g.,  $10^6$  g/mol, and a degree of polymerization falling between 10 and 500 glucose units.

[0076] In at least one preferred method of making such extruded pellets **34** and/or **34'** in producing extruded litter **30** in accordance with the present invention, such pellets **34** and/or **34'** are extruded from an admixture of one or more starch-containing cereal grains contain starch damage in an amount of at least 40%, preferably at least 50%, and more preferably at least 60%, as measured in accordance with AOAC: 2002.02, as substantially all of the cold water soluble amylopectin binder, preferably cold water soluble amorphous amylopectin binder, formed in each extruded pellet **34** and/or **34'** is physically modified cold water soluble amylopectin starch binder formed by physically modifying unmodified amylopectin starch present in the cereal grain admixture whose molecular weight is reduced to no greater than  $10^6$  forming at least 7.5%, preferably at least 10%, and more preferably at least 13%, of such physically modified cold water soluble amylopectin starch binder that preferably is physically modified amorphous cold water soluble amylopectin starch binder in each pellet **34** and/or **34'**. In one such

preferred extruded pellet embodiment, each extruded pellet **34** and/or **34'** has starch damage in an amount of at least 40%, preferably at least 55%, and more preferably at least 70%, as measured in accordance with AOAC: 2002.02, as the water soluble binder formed in each pellet **34** and/or **34'** during pellet extrusion is cold water soluble amylopectin binder, preferably cold water soluble amorphous amylopectin binder, formed in formed of physically modified cold water soluble amylopectin starch binder by physically modifying unmodified amylopectin starch present in the cereal grain admixture whose molecular weight is reduced to no greater than  $10^6$  and/or has a degree of a degree of polymerization falling between 10 and 6,000 glucose units, preferably between 10 and 500 glucose units, forming at least 7.5%, preferably at least 10%, and more preferably at least 13%, of such physically modified cold water soluble amylopectin starch binder by pellet weight that preferably is physically modified amorphous cold water soluble amylopectin starch binder.

[0077] Each such extruded pellet **34** and/or **34'** preferably also has a water activity level of no greater than 0.4, and preferably no greater than 0.35, as such a water activity level is indicative of the advantageous water absorption properties each pellet **34** and/or **34'** possesses. In addition, such a lower water activity level is also indicative not only of the long shelf life sorbent granules **32** and/or **34'** possess but also its advantageously long useful sorbent life after being applied or used. This is because litter **30** composed of extruded pellets **34** and/or **34'** of the present invention possess desirably high bacterial and fungal resistance as a result of each extruded pellet **34** and/or **34'** having such a low water activity level.

[0078] Such extruded pellets **34** and/or **34'** used in litter **30** of the present invention readily self-clump when wetted producing clumps **36** having a desirably high clump retention rate. In one preferred extruded granular sorbent embodiment, litter **30** formed of such extruded litter pellets **34** and/or **34'** of the present invention form clumps **36** of the pellets **34** and/or **34'** wetted with ten milliliters of 2% saline solution that each possess a clump retention rate of at least 92%, preferably at least 95%, and more preferably at least 97%, which is greater than the maximum 80%-90% clump retention rate of clumps formed of conventional bentonite-based cat litter (not shown) formed of conventional litter granules (not shown) each made of solid sodium bentonite. In one preferred extruded cat litter **30**, extruded litter pellets **34** and/or **34'** wetted with ten milliliters of 2% saline solution form clumps **36** that each possess a clump retention rate of at least 98% and which preferably possess a clump retention rate of at least 99%.

[0079] In determining such clump retention rates, clump **36** was formed by wetting litter **30** formed of extruded litter pellets **34** and **34'** with 10 milliliters of 2% saline solution before allowing the clump **36** to set for 10 minutes. The removed clump **36** is weighed to obtain a pre-drop clump weight before dropping the clump **36** eighteen inches onto a  $\frac{3}{4}$  inch U.S. Standard Sieve. The clump that remains is weighed a second time to obtain a post-drop clump weight that is then divided by the pre-drop clump weight and multiplied by 100 to obtain the clump retention rate. The aforementioned clump retention rate test is also known as a drop cohesion clump strength test.

[0080] In one preferred extruded granular sorbent embodiment where a mixture of extruded pellets **34** and **34'** are used as litter **30**, the extruded pellets **34** and **34'** of the mixture of litter **30** readily self-clump when wetted producing clumps **36** having a desirably high retention rate. In one preferred litter

**30** formed of a mixture of such extruded pellets **34** and **34'** form clumps **36** of pellets **34** and **34'** wetted with ten milliliters of 2% saline solution that each possess a clump retention rate of at least 92%, preferably at least 95%, and more preferably at least 97%, which is greater than the maximum 80%-90% clump retention rate of clumps formed of conventional bentonite-based cat litter (not shown) formed of conventional smectite granules (not shown) each made of solid sodium bentonite. In one preferred cat litter **30**, litter **30** formed substantially completely of a mixture such extruded pellets **34** and **34'** wetted with ten milliliters of 2% saline solution form clumps **36** that each possess a clump retention rate of at least 98% and which preferably possess a clump retention rate of at least 99%.

**[0081]** Such a mixture of extruded pellets **34** and **34'** forming cat litter **30** of the present invention readily self-clump when wetted producing clumps **36** also having a desirably high clump crush strength when dry. In addition to forming clumps **38** having such a desirably high retention rate, clumps **38** formed of litter **30** composed of a mixture of pellets **34** and **34'** wetted with ten milliliters of 2% saline solution are also advantageously strong and crush-resistant having a crush strength of at least 15 pounds per square inch (PSI), preferably at least 20 PSI, and more preferably at least 25 PSI, when air dried for at least 5 days to a moisture content of no more than 20% by dried clump weight. One preferred mixture of extruded pellets **34** and **34'** used as scoopable self-clumping lightweight litter **30** of the present invention forms clumps **36** of litter pellets **34** and **34'** wetted with 2% saline solution that each possess a crush strength of at least 28 pounds per square inch (PSI), preferably at least 30 PSI, and more preferably at least 35 PSI, when air dried for at least 5 days to a moisture content of no more than 20% by dried clump weight.

**[0082]** In one preferred litter embodiment where the litter **30** is formed substantially completely of such extruded pellets **34** and/or **34'**, the extruded pellets **34** and/or **34'** readily self-clump when wetted producing clumps **36** also having a desirably high crush strength. In one preferred extruded litter embodiment, litter **30** formed of such extruded pellets **34** and/or **34'** form clumps **36** of pellets **34** and/or **34'** wetted with ten milliliters of 2% saline solution that each possess a crush strength of at least 15 pounds per square inch (PSI), preferably at least 20 PSI, and more preferably at least 25 PSI, when air dried to a moisture content of no more than 20% by dried clump weight. One preferred cat litter **38** formed substantially completely of such extruded pellets **34** and/or **34'** wetted with ten milliliters of 2% saline solution form clumps **36** that each possess a crush strength of at least 30 pounds per square inch (PSI), preferably at least 35 PSI, and more preferably at least 40 PSI, when the clump **36** is dried to a moisture content of no more than 20% by dried clump weight.

**[0083]** Clumps **36** with such a desirably high clump retention rate produced from wetted extruded litter pellets **34** and/or **34'** of the present invention retain more of the wetted or spent extruded pellets **34** and/or **34'** of spent litter **38'** (FIGS. 5 and 6) in the clump **36** thereby advantageously leaving behind less spent or used sorbent granules in litter box **46** (FIG. 6). As a result, litter **30** of the present invention formed of such extruded litter pellets **34** and/or **34'** advantageously has a least a 93% litter efficiency, preferably at least a 95% litter efficiency, and more preferably at least a 97% litter efficiency by leaving behind virtually no litter pellets **34** and/or **34'** that have been wetted or spent from the clump **36** as virtually all of the spent or wetted pellets **34** and/or **34'** are

retained by or in the clump **36**. This causes a given amount or volume of litter **30** of the present invention to last longer and have less un-clumped wetted or spent litter pellets **34** and/or **34'** remaining in the litter **30** after clumping and clump removal, which thereby advantageously maximizes litter freshness, extends useful litter life, and minimizes odor.

**[0084]** Such a litter **30** formed of extruded litter pellets **34** and/or **34'** of the present invention advantageously form a "clean" clump **36** during litter use because the water soluble binder from wetted pellets **34** and/or **34'** that facilitates clumping by helping wetted pellets **34** and/or **34'** stick to one another also shrinks the clump **36** as the clump **36** air dries before being scooped out. By causing each clump **36** to shrink as the wetted lightweight litter pellets **34** and/or **34'** dry, clump shrinkage causes the clump **36** to condense in size and create voids between the clump **36** and surrounding unspent pellets **34** and/or **34'** of the remaining litter **30** producing a self-separating clump **36** in accordance with the present invention that reduces contamination of unused or un-spent pellets **34** and/or **34'** adjacent to and surrounding the clump **36**. Where a clump **36** forms adjacent to, on or against a solid surface, such as against a wall or on the bottom of a granular sorbent container, e.g., litter pan or litter box **46**, the clump **36** can condense and begin to pull away from the solid surface with which the clump **36** is in contact with. With reference to FIGS. 6 and 7, each clump **36** preferably shrinks at least 3% after being formed from wetted pellets **34** and/or **34'** such that each clump **36** shrinks and preferably thereby also condensing the clump **36**. When this happens during drying of the clump **36**, the clump **36** can condense and pull away from any wall or bottom (not shown) of a granular sorbent container, preferably litter box **46**, containing litter **30** of the invention as the clump **36** shrinks which can reduce the surface area of contact between the clump **36** and litter box **46**, which in certain instances can reduce clump sticking and can facilitate easier clump removal.

**[0085]** Litter **30** formed of a mixture of extruded litter pellets **34** and **34'** of the present invention forms clumps **36** that each preferably shrink at least 5% after formation as the clump **36** dries forming a dried clump **36** that possesses at least 93% clump retention rate, preferably at least 95% clump retention rate, and more preferably at least 97% clump retention rate when dried in accordance with that discussed above pertaining to clump retention rates advantageously producing a "clean" clump **36** which minimizes adherence to any litter box **46** filled with the litter **30** and which also minimizes adherence to any litter scoop **48** used to scoop out any clump **36** formed in the litter **30** in the litter box **46**. In one such preferred cat litter **38** of the present invention, each clump **36** formed of a mixture of pellets **34** and **34'** preferably shrinks at least 8% while possessing at least 93% clump retention, preferably at least 95% clump retention, and more preferably at least 97% clump retention, producing such a "clean" "non-stick" clump **36** that minimizes adherence to any part of the litter box or even the litter scoop during clump removal. In another preferred cat litter **38** of the present invention, each clump **36** formed of a mixture extruded pellets **34** and **34'** preferably shrinks at least 10% while possessing at least 93% clump retention, preferably at least 95% clump retention, and more preferably at least 97% clump retention, producing such a "clean" "non-stick" clump **36** that minimizes adherence to any part of the litter box or even the litter scoop during clump removal. In yet another such preferred cat litter **38** of the invention, each clump **36** formed of a mixture of extruded

pellets **34** and **34'**, each clump **36** preferably shrinks at least 12% while possessing at least 93% clump retention, preferably at least 95% clump retention, and more preferably at least 97% clump retention, producing such a “clean” “non-stick” clump **36** maximizing the removal of dirty litter through higher spent litter granule retention and minimizing adherence to unspent litter pellets **34** and **34'** and contacting solid surfaces.

**[0086]** Litter **30** made of or with a mixture of extruded pellets **34** and **34'** of the present invention produces litter **30** that advantageously also is lightweight having a bulk density preferably no greater than 40 lbs/ft<sup>3</sup> and which is at least 40% less than conventional clay-based sorbent, i.e., bentonite-based cat litter. In a preferred litter embodiment, litter **30** made of a mixture of extruded litter pellets **34** and **34'** in accordance with the present invention has a bulk density of no greater than 45 lbs/ft<sup>3</sup> that preferably is between 20 lbs/ft<sup>3</sup> and 40 lbs/ft<sup>3</sup>, which more preferably is between 25 lbs/ft<sup>3</sup> and 35 lbs/ft<sup>3</sup>, and which more preferably is between 27 lbs/ft<sup>3</sup> and 33 lbs/ft<sup>3</sup>. In one preferred granular sorbent embodiment, litter **30** made in accordance with the present invention has extruded litter pellets **34** and **34'** with a bulk density of no greater than 45 lbs/ft<sup>3</sup> that preferably is between 20 lbs/ft<sup>3</sup> and 40 lbs/ft<sup>3</sup>, which more preferably is between 25 lbs/ft<sup>3</sup> and 35 lbs/ft<sup>3</sup>, and which more preferably is between 27 lbs/ft<sup>3</sup> and 33 lbs/ft<sup>3</sup>.

**[0087]** In a further preferred litter embodiment, litter **30** of the present invention is made substantially completely of such extruded pellets **34** and/or **34'** with the extruded pellets **34** and/or **34'** having a bulk density of between 15 lbs/ft<sup>3</sup> and 45 lbs/ft<sup>3</sup>, which preferably is between 20 lbs/ft<sup>3</sup> and 40 lbs/ft<sup>3</sup>, which more preferably is between 25 lbs/ft<sup>3</sup> and 35 lbs/ft<sup>3</sup>, and which further preferably is between 27 lbs/ft<sup>3</sup> and 33 lbs/ft<sup>3</sup>. In one such preferred litter embodiment, litter **30** of the present invention is composed of a mixture of extruded pellets **34** and **34'** produce a litter **30** having a bulk density of no greater than 45 lbs/ft<sup>3</sup> that preferably is between 20 lbs/ft<sup>3</sup> and 40 lbs/ft<sup>3</sup>, which more preferably is between 25 lbs/ft<sup>3</sup> and 35 lbs/ft<sup>3</sup>, and which more preferably is between 27 lbs/ft<sup>3</sup> and 33 lbs/ft<sup>3</sup>. In another such preferred litter embodiment, litter **30** of the present invention is substantially completely made of a mixture of such extruded pellets **34** and **34'** producing litter **38** having a bulk density of no greater than 45 lbs/ft<sup>3</sup> that preferably is between 20 lbs/ft<sup>3</sup> and 40 lbs/ft<sup>3</sup>, which more preferably is between 25 lbs/ft<sup>3</sup> and 35 lbs/ft<sup>3</sup>, and which more preferably is between 27 lbs/ft<sup>3</sup> and 33 lbs/ft<sup>3</sup>. In still another such preferred litter embodiment, litter **30** of the present invention is substantially completely composed of such extruded pellets **34** and/or **34'** is composed of extruded pellets **34** and/or **34'** having a bulk density of between 15 lbs/ft<sup>3</sup> and 45 lbs/ft<sup>3</sup>, which preferably is between 20 lbs/ft<sup>3</sup> and 40 lbs/ft<sup>3</sup>, which more preferably is between 25 lbs/ft<sup>3</sup> and 35 lbs/ft<sup>3</sup>, and which further preferably is between 27 lbs/ft<sup>3</sup> and 33 lbs/ft<sup>3</sup>.

**[0088]** In addition to litter **30** composed of extruded litter pellets **34** and/or **34'** or a mixture of extruded litter pellets **34** and/or **34'** forming clean clumps when wetted, such extruded pellets **34** and/or **34'** are advantageously de-dusting pellets that each act as a dust magnet. Without being wetted, each extruded pellet **34** and/or **34'** used in litter **30** of the present invention has sufficient water-soluble material in an outer surface **40** of each pellet **34** and/or **34'** to cause dust in the litter **30** to adhere to the water-soluble material of the outer pellet surface **40** advantageously preventing such dust from becoming

airborne. In a preferred embodiment, without being wetted, water soluble binder present in the outer surface **40** of each extruded pellet **34** and/or **34'** of litter **30** of the present invention is a dust attracting pellet **34** and/or **34'** or dust-magnet pellet **34** and/or **34'** causing dust in the litter **30** to stick to water-soluble binder of the outer surface **40** of each pellet **34** and/or **34'** coming into contact with the dust, while the binder is dry, preventing such dust from becoming airborne. Such de-dusting extruded litter pellets **34** in accordance with the present invention is well suited for use as cat litter **30** with retail bags or containers filled with such cat litter **30** composed of extruded pellets **34** and/or **34'** or a mixture of extruded pellets **34** and **34'** containing less than 5% dust, preferably less than 3% dust and preferably less than 1% dust by litter weight.

**[0089]** In a preferred litter embodiment, each litter pellet **34** and/or **34'** is extruded from an admixture not containing any smectite nor any binder additive with each extruded pellet **34** and/or **34'** used in the litter **30** in uncoated form. In another preferred litter embodiment, each litter pellet **34** and/or **34'** is extruded from an admixture not containing any smectite nor any binder additive and is used in the litter **30** without any smectite, e.g., bentonite, coating. In still another preferred litter embodiment, each litter pellet **34** and/or **34'** is extruded from an admixture not containing any smectite nor any binder additive and is used in the litter **30** in its as-extruded form.

**[0090]** Understandably, the present invention has been described above in terms of one or more preferred embodiments and methods. It is recognized that various alternatives and modifications may be made to these embodiments and methods that are within the scope of the present invention. Various alternatives are contemplated as being within the scope of the present invention. It is also to be understood that, although the foregoing description and drawings describe and illustrate in detail one or more preferred embodiments of the present invention, to those skilled in the art to which the present invention relates, the present disclosure will suggest many modifications and constructions, as well as widely differing embodiments and applications without thereby departing from the spirit and scope of the invention.

What is claimed is:

1. An extruded cat litter formed of a plurality of pellets extruded from a starch containing material having sufficient water soluble adhesive formed from starches modified during extrusion to self-clump together when wetted forming clumps comprised of at least a plurality of pairs of the extruded pellets bonded together by the water soluble adhesive.

2. The extruded cat litter of claim 1 wherein each extruded pellet is comprised of at least 7.5% water soluble binder formed of modified starches modified during pellet extrusion.

3. The extruded cat litter of claim 2 wherein the water soluble binder comprises cold water soluble binder.

4. The extruded cat litter of claim 3 wherein the cold water soluble binder comprises cold water soluble amylopectin binder.

5. The extruded cat litter of claim 1 wherein a clump formed of a plurality of pairs of the extruded pellets wetted with 2% saline solution has a clump retention rate of at least 93%.

6. The extruded cat litter of claim 5 wherein the clump formed of the plurality of pairs of the wetted extruded pellets has a clump crush strength of at least 15 pounds per square inch.

7. The extruded cat litter of claim 1 wherein a clump formed of a plurality of pairs of the extruded pellets wetted with 2% saline solution has a clump crush strength of at least 15 pounds per square inch.

8. The extruded cat litter of claim 7 wherein the clump formed of the plurality of pairs of the wetted extruded pellets has a clump retention rate of at least 93%.

9. The extruded cat litter of claim 1 wherein each extruded pellet is comprised of at least 50% starch by pellet weight.

10. The extruded cat litter of claim 9 wherein each extruded pellet is comprised of no more than 50% cellulose by pellet weight.

11. The extruded cat litter of claim 1 wherein the cat litter is comprised of:

(a) at least a plurality of pairs of finely sized extruded pellets each having a size smaller than 1.2 mm in length, width and/or diameter; and

(b) at least a plurality of pairs of larger sized extruded pellet formed of extruded pellets having a size (i) no greater than 3 mm in length, width and/or diameter, and (ii) no smaller than 1 mm in length, width and/or diameter; and wherein a clump formed of (i) a plurality of pairs of the finely sized extruded pellets, and (ii) a plurality of pairs of the larger sized extruded pellets wetted with 2% saline solution forms in a generally horizontal direction.

12. The extruded cat litter of claim 11 wherein the plurality of pairs of the wetted finely sized extruded pellets and the plurality of pairs of the wetted larger sized extruded pellets forming the clump absorb at least the weight of the wetted extruded pellets in 2% saline solution within three minutes of being wetted with the 2% saline solution in forming the clump.

13. The extruded cat litter of claim 11 wherein the clump has a clump retention rate of at least 93%.

14. The extruded cat litter of claim 13 wherein the clump has a clump crush strength of at least 15 pounds per square inch.

15. The extruded cat litter of claim 11 wherein the clump has a clump crush strength of at least 15 pounds per square inch.

16. The extruded cat litter of claim 11 wherein the extruded granular sorbent is comprised of at least 15% of the finely sized sorbent granules by weight of the extruded granular sorbent.

17. The extruded cat litter of claim 16 wherein the clump has a clump retention rate of at least 93%.

18. The extruded cat litter of claim 17 wherein the clump has a clump crush strength of at least 15 pounds per square inch.

19. The extruded cat litter of claim 11 wherein the extruded granular sorbent is comprised of at least 10% and no greater than 40% of the finely sized sorbent granules by weight of the

extruded granular sorbent with the remainder of the extruded granular sorbent comprised substantially of the larger sized sorbent granules.

20. The extruded cat litter of claim 19 wherein the clump has a clump retention rate of at least 93%.

21. The extruded cat litter of claim 19 wherein the clump has a clump crush strength of at least 15 pounds per square inch.

22. The extruded cat litter of claim 1 wherein the extruded granular sorbent is comprised of:

(a) at least a plurality of pairs of finely sized sorbent granules formed of extruded pellets having a size smaller than 2 mm in length, width and/or diameter; and

(b) at least a plurality of pairs of larger sized sorbent granules formed of extruded pellets having a size (i) no greater than 4 mm in length, width and/or diameter, and (ii) no smaller than 2 mm in length, width and/or diameter; and

wherein (i) a plurality of pairs of the finely sized sorbent granules, and (ii) a plurality of pairs of the larger sized sorbent granules wetted with 2% saline solution forms a clump of the wetted plurality of pairs of the finely sized sorbent granules and wetted plurality of pairs of the larger sized sorbent granules forms on top of a plurality of pairs of the finely sized sorbent granules and on top of a plurality of pairs of the larger sized sorbent granules not wetted by the 2% saline solution.

23. The extruded cat litter of claim 22 wherein the clump has a clump crush strength of at least 15 pounds per square inch.

24. The extruded cat litter of claim 22 wherein the clump formed of the plurality of pairs of the wetted sorbent granules has a clump retention rate of at least 92%.

25. The extruded cat litter of claim 22 wherein the extruded granular sorbent is comprised of at least 10% and no greater than 40% of the finely sized sorbent granules by weight of the extruded granular sorbent.

26. The extruded cat litter of claim 22 wherein the extruded granular sorbent is comprised of at least 10% and no greater than 40% of the finely sized sorbent granules by weight of the extruded granular sorbent with the remainder of the extruded granular sorbent comprised of the larger sized sorbent granules.

27. The extruded cat litter of claim 1 wherein a clump formed of a plurality of pairs of the sorbent granules wetted with 2% saline solution shrinks at least 5% after clump formation when the clump is dried for a period of five days to a moisture content of no greater than 20% by clump weight.

\* \* \* \* \*