



(51) International Patent Classification:

C08F 210/16 (2006.01) *C08L 23/06* (2006.01)
C08F 4/655 (2006.01) *F16L 9/12* (2006.01)

(21) International Application Number:

PCT/EP2016/065346

(22) International Filing Date:

30 June 2016 (30.06.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15177052.6 16 July 2015 (16.07.2015) EP

(71) Applicant: **SABIC GLOBAL TECHNOLOGIES B.V.**
[NL/NL]; Plasticslaan 1, 4612 PX Bergen op Zoom (NL).

(72) Inventors: **GARG, M Priya**; P/O SABIC Intellectual
Property Group P.O. Box 3008, 6160 GA Geleen (NL).
FRIEDERICHS, Nicolaas, Hendrika; c/o SABIC Intel-
lectual Property Group, P.O. Box 3008, 6160 GA Geleen
(NL). **SCHOFFELEN, Tom**; c/o SABIC Intellectual
Property Group, P.O. Box 3008, 6160 GA Geleen (NL).

(74) Agent: **SABIC INTELLECTUAL PROPERTY
GROUP**; P.O. Box 3008, 6160 GA Geleen (NL).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: BIMODAL HIGH DENSITY POLYETHYLENE

(57) Abstract: The invention is directed to bimodal polyethylene having a flow ratio FRR ranging between ≥ 30 and ≤ 40 , a density ranging between ≥ 949.0 and ≤ 952.0 kg/m³, an MFR_{190/5} ranging between ≥ 0.1 and ≤ 0.2 g/10min and comprising from 50 to 54 % by weight of an ethylene homopolymer A and from 46-50 % by weight of an ethylene-butene copolymer B, where all percentages are based on the total weight of the composition and wherein ethylene homopolymer A has a viscosity number ≥ 70 and ≤ 100 cm³/g and a density between ≥ 968 and ≤ 972 kg/m³. The polyethylene is suitable to be applied in the production of pipes.



Bimodal high density polyethylene

The present invention relates to bimodal high density polyethylene and a pressure pipe comprising the bimodal polyethylene.

5 The production processes for bimodal high density polyethylene (HDPE) are summarised at pages 16-20 of "PE 100 Pipe systems" (edited by Brömstrup; second edition, ISBN 3-8027-2728-2).

10 The production of bimodal high density polyethylene (HDPE) via a low pressure slurry process is described by Alt et al. in "Bimodal polyethylene-Interplay of catalyst and process" (Macromol.Symp. 2001, 163, 135-143). In a two stage cascade process the reactors may be fed continuously with a mixture of monomers, hydrogen, catalyst/
15 co-catalyst and diluent recycled from the process. In the reactors, polymerisation of ethylene occurs as an exothermic reaction at pressures in the range between for example 0.2 MPa (2 bar) and 1MPa (10 bar) and at temperatures in the range between
15 for example 75 °C and 85 °C. The heat from the polymerisation reaction is removed by means of external cooling. The characteristics of the polyethylene are determined amongst others by the catalyst system and by the concentrations of catalyst, co monomer and hydrogen.

20 The concept of the two stage cascade process is elucidated at pages 137-138 by Alt et al. "Bimodal polyethylene-Interplay of catalyst and process" (Macromol.Symp. 2001, 163). The reactors are set up in cascade with different conditions in each reactor including for example a high hydrogen content in the first reactor and a low hydrogen content in the second reactor. This allows for the production of HDPE with a bimodal
25 molecular mass distribution and desired co monomer content in the polyethylene chains. For reasons of monomer efficiency, it is common practise that the polymer suspension or "slurry" obtained after the second reactor flows into a so-called post reactor. In this reactor the final polymerisation takes place, resulting in a conversion rate of more than 99% of the monomers used. The suspension then flows to a
30 suspension receiver and the suspension leaving the receiver is separated, for example via a decanter centrifuge. The resulting wet polymer is fed to a fluidised bed dryer and the liquid part goes back to the reactors. After drying the extrusion step takes place. The solvent coming from the drying of the polymer is recycled after purification by amongst other distillation.

35 For the reliable supply of modern infrastructure with natural gas or water, buried pipes play an important role to maintain high living standards. In the field of pressurized pipes, polymer pipes made of bimodal polyethylene have been used for many years.

- 2 -

Initially, PE pipes were applied in the low-pressure regime up to 4 (gas) and 6 bar (water), respectively, today they are typically operated at pressure levels of up to 10 (gas) and 16 bar (water) and even higher. Pressurized PE pipes are designed to fulfill operating times of at least 50 years. The material classification of PE pipe grades is based on the long-term failure behavior using internal pipe pressure tests at different temperatures and extrapolation methods as described in EN ISO 9080 or ASTM D2837. Based on these tests, the minimum required strength (MRS) to ensure pipe lifetimes of at least 50 years is determined and leads to a classification of the materials as for example PE 80 (MRS = 8 MPa) or PE 100 (MRS = 10 MPa).

It is the object of the present invention to provide a HDPE grade having an improved hydrostatic strength while other properties such as for example slow crack growth resistance and impact resistance have values which are preferably higher than the values for PE 100 grade.

The bimodal polyethylene according to the invention has a flow ratio FRR ranging between ≥ 30 and ≤ 40 , a density ranging between ≥ 949.0 and ≤ 952.0 kg/m³, an MFR_{190/5} ranging between ≥ 0.1 and ≤ 0.2 g/10min and comprising from 50 to 54 % by weight of an ethylene homopolymer A and from 46 to 50 % by weight of an ethylene-butene copolymer B, where all percentages are based on the total weight of the composition and wherein ethylene homopolymer A has a viscosity number ≥ 70 and ≤ 100 cm³/g and a density between ≥ 968 and ≤ 972 kg/m³ and wherein the bimodal polyethylene has

- impact resistance (according to notched Charpy measurements at 23°C ; ISO 179) ≥ 30 kJ/m² and ≤ 40 kJ/m²

- impact resistance (notched Charpy measurements at -30°C; ISO 179) ≥ 15 kJ/m² and ≤ 20 kJ/m²

- strain hardening (measured according to the strain hardening method, based on the publication by Kurelec, L. *et al* in *Polymer* 2005, 46, p 6369-6379) ≥ 40 MPa and ≤ 50 MPa and

- shear thinning index ≥ 65 and ≤ 80 .

The density of polyethylene and copolymer A is determined according to ISO 1183.

The viscosity number of polyethylene and homopolymer A is determined according to ISO 1628-3.

The Flow Rate Ratio (FRR) is calculated as $\text{MFR}_{190/21.6} / \text{MFR}_{190/5}$. FRR is indicative for the rheological broadness of the material.

- 3 -

The melt-indices MFR_{190/5} and MFR_{190/21.6} are measured according to method ASTM D-1238 under a load of 5 and 21.6 kg respectively at 190°C.

The MWD of the polyethylene ranges between 25 and 55, preferably between 30 and 40.

5 According to a preferred embodiment of the invention the density of ethylene homopolymer A ranges between ≥ 969 and ≤ 971 kg/m³.

According to a preferred embodiment of the invention the viscosity number of ethylene homopolymer A ranges between ≥ 75 and ≤ 90 cm³/g.

10 The density of the bimodal polyethylene ranging between ≥ 949.0 and ≤ 952.0 kg/m³ is based on base polymer without colourants such as carbon black.

According to a preferred embodiment of the invention, the density of the bimodal polyethylene ranges between ≥ 949 and ≤ 951 kg/m³.

15 Preferably, the bimodal polyethylene comprises from 50 to 52 % by weight of an ethylene homopolymer A and from 48 to 50 % by weight of an ethylene-butene copolymer B.

The pipe tests based on this polyethylene shows excellent results as shown in the examples.

20 The pipes show an excellent pressure resistance at 20°C, 12 Mpa (measured according to ISO 1167 with pipe dimensions 32x3mm) >8000 hours, preferably >9000 hours, more preferably >10000 hours.

It is the advantage of the present invention that the ethylene butene copolymer has a higher hydrostatic strength (pressure resistance) than a PE 100 grade and furthermore improved mechanical properties such as for example impact resistance and strain hardening.

25 Furthermore, the polymer according to the invention has a good low sagging performance and good processability.

30 It is surprising that the bimodal polyethylene having a Flow Rate Ratio ranging between ≥ 30 and ≤ 40 , a density ranging between ≥ 949.0 and ≤ 952.0 kg/m³ and being based on an ethylene homopolymer A having a density between ≥ 968 and ≤ 972 kg/m³ results in a polyethylene having a higher hydrostatic strength than a PE100 grade.

The amount of butene incorporated in the ethylene-butene copolymer B ranges from ≥ 0.1 to ≤ 5 % by weight.

35 The bimodal polyethylene according to the invention is a polyethylene obtained with a polymerisation in the presence of a Ziegler-Natta catalyst system.

- 4 -

According to a preferred embodiment of the invention the high density polyethylene is produced with a two-step slurry polymerisation process using cascaded reactors in the presence of a Ziegler Natta catalyst system.

According to a further preferred embodiment of the invention the high density ethylene copolymer is produced with a two-step slurry polymerisation process using cascaded reactors in the presence of a catalyst system comprising

(I) the solid reaction product obtained by reaction of:

a) a hydrocarbon solution containing

1) an organic oxygen containing magnesium compound or a halogen containing magnesium compound and

2) an organic oxygen containing titanium compound and

b) an aluminium halogenide having the formula $AlR_n X_{3-n}$ in which R is a hydrocarbon moiety containing 1 – 10 carbon atoms, X is halogen and $0 < n < 3$ and

(II) an aluminium compound having the formula AlR_3 in which R is a hydrocarbon moiety containing 1 – 10 carbon atom.

During the reaction of the hydrocarbon solution comprising the organic oxygen containing magnesium compound and the organic oxygen containing titanium compound with component (I b) a solid catalyst precursor precipitates and after the precipitation reaction the resulting mixture is heated to finish the reaction.

The aluminium compound (II) is dosed prior to or during the polymerization and may be referred to as a cocatalyst.

Suitable organic oxygen containing magnesium compounds include for example magnesium alkoxides such as magnesium methyllate, magnesium ethyllate and magnesium isopropylate and alkylalkoxides such as magnesium ethylethyllate and so called carbonized magnesiumalkoxide such as magnesium ethyl carbonate.

Preferably, the organic oxygen containing magnesium compound is a magnesium alkoxide. Preferably the magnesium alkoxide is magnesium ethoxide $Mg(OC_2H_5)_2$.

Suitable halogen containing magnesium compounds include for example magnesium dihalides and magnesium dihalide complexes wherein the halide is preferably chlorine.

Preferably the hydrocarbon solution comprises an organic oxygen containing magnesium compound as (I) (a) (1).

- 5 -

Suitable organic oxygen containing titanium compound may be represented by the general formula $[\text{TiO}_x (\text{OR})_{4-2x}]_n$ in which R represents an organic moiety, x ranges between 0 and 1 and n ranges between 1 and 6.

5 Suitable examples of organic oxygen containing titanium compounds include alkoxides, phenoxides, oxyalkoxides, condensed alkoxides, carboxylates and enolates. Preferably the organic oxygen containing titanium compounds is a titanium alkoxide. Suitable alkoxides include for example $\text{Ti} (\text{OC}_2\text{H}_5)_4$, $\text{Ti} (\text{OC}_3\text{H}_7)_4$, $\text{TiOC}_4\text{H}_9)_4$ and $\text{Ti}(\text{OC}_8\text{H}_{17})_4$. Preferably the organic oxygen containing titanium compound is $\text{Ti} (\text{OC}_4\text{H}_9)_4$.

10 Preferably the aluminium halogenide is a compound having the formula $\text{AlR}_n\text{X}_{3-n}$ in which R is a hydrocarbon moiety containing 1 – 10 carbon atoms, X is halogen and $0.5 < n < 2$. Suitable examples of the aluminium halogenide in (I) b having the formula $\text{AlR}_n\text{X}_{3-n}$ include ethyl aluminium dibromide, ethyl aluminium dichloride, propyl aluminium dichloride, n- butyl aluminium dichloride, iso butyl aluminium dichloride, diethyl aluminium chloride, diisobutyl aluminium chloride,.
15 Preferably X is Cl. Preferably the organo aluminium halogenide in (I) b) is an organo aluminium chloride, more preferably the organo aluminium halogenide in (I) b) is chosen from ethyl aluminium dichloride, diethyl aluminium dichloride, isobutyl aluminium dichloride, diisobutyl aluminium chloride or mixtures thereof.

20 Generally the molar ratio of Al from I b): Ti from I a) 2 ranges between 3:1 and 16:1. According to a preferred embodiment of the invention the molar ratio of Al from I b): Ti from I a) 2 ranges between 6:1 and 10:1.

Suitable examples of the cocatalyst of the formula AlR_3 include tri ethyl aluminium, tri isobutyl aluminium, tri-n-hexyl aluminium and tri octyl aluminium.
25 Preferably the aluminium compound in (II) of the formula AlR_3 is tri ethyl aluminium or tri isobutyl aluminium.

The hydrocarbon solution of organic oxygen containing magnesium compound and organic oxygen containing titanium compound can be prepared according to procedures as disclosed for example in US 4178300 and EP0876318.
30 The solutions are in general clear liquids. In case there are any solid particles, these can be removed via filtration prior to the use of the solution in the catalyst synthesis.

Generally the molar ratio of magnesium: titanium is lower than 3:1 and preferably the molar ratio magnesium: titanium ranges between 0, 2:1 and 3:1.

- 6 -

Generally the molar ratio of aluminium from (II): titanium from (a) ranges between 1:1 and 300:1 and preferably the molar ratio of aluminium from (II): titanium from (a) ranges between 3:1 and 100:1.

5 The catalyst may be obtained by a first reaction between a magnesium alkoxide and a titanium alkoxide, followed by dilution with a hydrocarbon solvent, resulting in a soluble complex consisting of a magnesium alkoxide and a titanium alkoxide and thereafter a reaction between a hydrocarbon solution of said complex and the organo aluminium halogenide having the formula AlR_nX_{3-n}

10 Generally, the aluminium halogenide having the formula AlR_nX_{3-n} is used as a solution in a hydrocarbon. Any hydrocarbon that does not react with the organo aluminium halogenide is suitable to be applied as the hydrocarbon.

The sequence of the addition can be either adding the hydrocarbon solution containing the organic oxygen containing magnesium compound and organic oxygen containing titanium compound to the compound having the formula AlR_nX_{3-n} or the reversed.

15 The temperature for this reaction can be any temperature below the boiling point of the used hydrocarbon. Generally the duration of the addition is preferably shorter than 1 hour.

20 In the reaction of the hydrocarbon solution of the organic oxygen containing magnesium compound and the organic oxygen containing titanium compound with the organo aluminium halogenide of formula AlR_nX_{3-n} , the solid catalyst precursor precipitates. After the precipitation reaction the resulting mixture is heated for a certain period of time to finish the reaction. After the reaction the precipitate is filtered and washed with a hydrocarbon. Other means of separation of the solids from the diluents and subsequent washings can also be applied, like for example multiple decantation steps. All steps should be performed in an inert atmosphere of nitrogen or another suitable inert gas.

25 The polymerization can be carried out in the presence of an anti-static agent or anti fouling agent in an amount ranging between for example 1 and 500 ppm related to the total amount of reactor contents.

The polyethylene is suitable to be applied in the production of pipes, pipe fittings, films, blow molding applications and injection molding.

Preferably the polymer according to the invention is applied in the production of pipes for transport of drinking water.

35 EP1460105 discloses a bimodal polyethylene having a density greater than or equal to 953.0 kg/m^3 and SHI of 70 or more to reach a PE125 type of pipe material.

- 7 -

EP1146079 discloses a polyethylene resin having a FRR greater than 38 and overall density greater than 953 kg/m³.

US6225421 discloses bimodal polyethylene having a density 948.7 kg/m³, an MFR_{190/5} 0.3 g/10min and comprising from 50.8 % by weight of an ethylene homopolymer A and from 49.2% by weight of an ethylene-butene copolymer B wherein ethylene homopolymer A has a density 972 kg/m³. The differences between the present invention and US6225421 will result in different pipe properties.

WO2013087167 is directed to a process in the presence of donors and the bimodal polyethylene has a flow ratio FRR 34, a density 948.0, a MFR_{190/5} 0.21 g/10min and comprising from 51 % by weight of an ethylene homopolymer A and 49 % by weight of an ethylene-butene copolymer B and wherein the bimodal polyethylene granules have impact resistance (notched Charpy measurements at -30°C; ISO 179) 10 kJ/m² and strain hardening (measured according to the strain hardening method, based on the publication by Kurelec, L. *et al* in *Polymer* 2005, 46, p 6369-6379) 55 MPa. The differences between the present invention and WO2013087167 will result in different pipe properties.

EP1719788 discloses bimodal polyethylene having a flow ratio FRR ranging between 27 and 30, a density ranging between 950 and 955 kg/m³, an MFR_{190/5} ranging between 0.25 and 0.35 g/10min and comprising 50 % by weight of an ethylene homopolymer A and 50 % by weight of an ethylene-butene copolymer B, wherein ethylene homopolymer A has a density 970 kg/m³. The differences between the present invention and EP1719788 will result in different pipe properties.

The invention will be elucidated by means of the following non-restrictive examples.

25

Examples

The solids content in the catalyst suspension was determined in triplo by drying 5 ml of a catalyst suspension under a stream of nitrogen, followed by evacuating for 1 hour and subsequently weighing the obtained amount of dry catalyst.

30

The density of the polymers is measured according to ISO1183.

The viscosity number is determined according to ISO 1628-3.

The melt-indices MFR_{190/5} and MFR_{190/21.6} are measured according to method ASTM D-1238 under a load of 5 and 21.6 kg at 190°C.

35

The Flow Rate Ratio (FRR) being calculated as $MFR_{190/21.6} / MFR_{190/5}$ is indicative for the rheological broadness of the material.

- 8 -

The split of the bimodal polymer is defined as the weight fraction of the lower molecular weight material in the overall polymer. For the semi-batch process as described in the following polymerization examples, this translates into the cumulative ethylene consumption from the first polymerization step compared to the cumulative ethylene consumption in the combined first and second step.

The elemental compositions of the catalysts were analysed using Neutron Activation Analysis.

The alkoxide content in the final catalyst was determined by GC analysis of a water-quenched catalyst sample.

The tensile tests were performed according to ISO 527-2.

Notched Charpy measurements were performed according to ISO 179

The resistance to so called slow crack growth was measured using the strain hardening method, based on the publication by Kurelec, L. *et al* in *Polymer* 2005, 46, p 6369-6379.

Shear thinning index SHI(2.7/210) is the ratio of the viscosity of the polyethylene composition at different shear stresses. In the present invention, the shear stresses at 2.7 kPa and 210 kPa are used for calculating the SHI(2.7/210) which may serve as a measure of the broadness of the molecular weight distribution.

Rheological parameters such as Shear Thinning Index SHI and DMS parameters are determined by using a rheometer. The definition and measurement conditions for SHI are described in detail on page 8 line 29 to page 11, line 25 of WO 00/22040.

DMS parameters indicate the frequency (ω) at which a pre-defined/reference complex modulus value is reached for a polymer in a frequency sweep experiment. The DMS parameters are suffixed with a number (e.g. DMS_n) where 'n' denotes the reference G^* value in the format $n \cdot 10^4$ Pa. Different DMS values as typically calculated at different reference G^* are:

DMS2 indicates ω (rad/s) at $G^* = 2 \cdot 10^4$ Pa

DMS5 indicates ω (rad/s) at $G^* = 5 \cdot 10^4$ Pa

DMS10 indicates ω (rad/s) at $G^* = 10 \cdot 10^4$ Pa

DMS21 indicates ω (rad/s) at $G^* = 21 \cdot 10^4$ Pa

The calculation of DMS values takes into account the entire range of ω and G^* data of a frequency sweep experiment ($\omega = 100$ rad/s to $\omega = 0.01$ rad/s). The plot of $\log \omega$ vs $\log G^*$ is used for DMS calculation. A 3rd order polynomial is used to fit the data such that the R^2 value of the fit is more than 0.99. The values of $\log \omega$ was calculated using the trend line equation at different reference G^* values and consequently, values

- 9 -

of DMS2, DMS5, DMS10 and DMS21 were evaluated. DMS 21/2 is a ratio of the DMS21 and DMS 2 values.

The molecular weight distribution is measured by using size exclusion chromatography (SEC). In the examples this was done by using a Polymer Laboratories PL-GPC220 instrument equipped with 3 columns (Polymer Laboratories 13 µm PLgel Olexis, 300 x 7.5 mm) at an oven temperature of 140°C. A refractive index (RI) detector, a viscosity detector (Polymer Laboratories PL BV-400 viscometer) and an IR detector (Polymer Char IR5) were used. The instrument was calibrated with linear PE standards.

The pressure resistance at all temperatures and hoop stress values is measured according to ISO 1167 with pipe dimensions 32x3mm.

Experiment I

Preparation of a hydrocarbon solution comprising the organic oxygen containing magnesium compound and the organic oxygen containing titanium compound

100 grams of granular $\text{Mg}(\text{OC}_2\text{H}_5)_2$ and 150 millilitres of $\text{Ti}(\text{OC}_4\text{H}_9)_4$ were brought in a 2 litre round bottomed flask equipped with a reflux condensor and stirrer. While gently stirring, the mixture was heated to 180°C and subsequently stirred for 1.5 hours. During this, a clear liquid was obtained. The mixture was cooled down to 120°C and subsequently diluted with 1480 ml of hexane. Upon addition of the hexane, the mixture cooled further down to 67°C. The mixture was kept at this temperature for 2 hours and subsequently cooled down to room temperature. The resulting clear solution was stored under nitrogen atmosphere and was used as obtained. Analyses on the solution showed a titanium concentration of 0.25 mol/l.

Experiment II

Preparation of the catalyst

In a 0.8 liters glass reactor, equipped with baffles, reflux condenser and stirrer, 424 ml hexanes and 160 ml of the complex from Example I were dosed. The stirrer was set at 1200 RPM. In a separate flask, 100 ml of 50% ethyl aluminum dichloride (EADC) solution was added to 55 mL of hexanes. The resulting EADC solution was dosed into the reactor in 15 minutes using a peristaltic pump. Subsequently, the mixture was refluxed for 2 hours. After cooling down to ambient temperature, the obtained red/brown suspension was transferred to a glass P4 filter and the solids were separated. The solids were washed 3 times using 500 ml of hexanes. The

- 10 -

solids were taken up in 0.5 L of hexanes and the resulting slurry was stored under nitrogen. The solid content was 64 g ml⁻¹

Catalyst analysis results:

Ti 10.8 wt%; Mg 11.2 wt%; Al 5.0 wt%; Cl 65 wt%; OEt 3.2 wt% and OBu 2.6 wt%.

5

Example I and Comparative Examples A and B

The polymerization was carried out in a continuous installation, consisting of 2 equally sized CSTR polymerization reactors in series using hexanes as diluent. The reactors contain a headspace that is continuously analyzed on the composition using an on-line analyzer. In the first reactor, a lower molecular weight polyethylene homopolymer is produced, followed by the production of a high molecular weight ethylene-butene copolymer.

10

Between the first reactor and the second reactor, a flash step was applied, primarily aimed at removing the hydrogen coming out from the first reactor by means of reducing the pressure.

15

The applied catalyst was prepared in a 400L reactor, using a recipe analogous the one described in Experiment II. The catalyst flow to the first reactor was adjusted to reach the desired ethylene partial pressure in this first reactor as is indicated in the Table 1. The applied cocatalst was tri-isobutyl aluminium (TiBAI).

20

The applied recipes of Example I and Comparative Examples A and B are described in Table 1.

Table 1

	Example I	Comparative Example A	Comparative Example B
Reactor 1			
Temperature [°C]	88	88	88
Ethylene partial pressure [bar]	1.7	1.5	1.7
H ₂ /C ₂ ratio in headspace [v/v]	4.1	5.4	3.8
C ₂ /hexane feed [kg/kg]	0.663	0.649	0.648
Viscosity number [cm ³ /g]	80	60	90
Density [kg/m ³]	971	973	970
[TiBAI] mmol/L	1.1	1.1	1.1
Split %	51	55	57
Reactor 2			
Temperature [°C]	78	78	78
Ethylene partial pressure [bar]	2.96	2.1	2.1
H ₂ /C ₂ ratio in headspace [v/v]	0.013	0.010	0.003
C ₄ /C ₂ in headspace [v/v]	0.04	0.02	0.05
C ₂ /hexane feed [kg/kg]	0.29	0.28	0.27
Bimodal grade (powder)			
MFI5 (g/10min)	0.11	0.10	0.10
Density (kg/m ³)	951	956	953

Results black compound

The bimodal grade PE powder was stabilised by adding 2000 ppm of calcium stearate, 2000 ppm of Irganox 1010 and 1000 ppm of Irgafos 168. To this, 2-2.5 wt% carbon black (grade Printex PA from Degussa, Germany) was added. The stabilised powder mixture was extruded into pellets using a commercial NT extruder from Coperion, Germany comprising of 2 extruders in series (ZSK 250 and ZSK 350). The pellets were used for the mentioned analyses.

10

Table 2: Overview of polymer characteristics

	MFR ₅ g/10min	MFR ₂₁ g/10min	FRR	Density kg/m ³	Mn (kg/mol)	Mw (kg/mol)	Mw/Mn
Example I	0.11	3.8	34	961	10	350	34.0
Comparative Example A	0.10	5.1	51	965	8	380	47.5
Comparative Example B	0.10	4.6	46	963	8	350	43.7

Table 3: Overview of mechanical properties

	Notched Charpy 23°C (kJ/m ²)	Notched Charpy - 30°C (kJ/m ²)	Strain hardening modulus (MPa)	E-modulus (MPa)	Yield stress (MPa)
Example I	32.0 ± 3.1	17.1 ± 0.9	46.2 ± 1.1	1106 ± 52.8	27.1 ± 0.4
Comparative Example A	38.3 ± 2.5	19.1 ± 0.8	38.7 ± 0.9	1152 ± 38.3	29.2 ± 0.3
Comparative Example B	23.7 ± 0.7	12.3 ± 0.8	42.9 ± 0.7	1192 ± 66.0	28.1 ± 0.1

15

Table 4: Overview of rheological properties

	DMS2	DMS5	DMS10	DMS21	DMS 21/2	SHI
Example I	0.0890	0.4836	2.3779	20.7667	233	73.54
Comparative Example A	0.0507	0.2883	1.5157	16.0856	317	120.73
Comparative Example B	0.0745	0.4389	2.3682	24.3607	326	122.45

Pipe tests

The pressure tests have been performed on pipe specimens with the dimension 32 x 3.0 mm. Dimensions and tolerances of the specimens comply with ISO 4427-2 provisions. A geometric mean was only calculated when minimum 2 specimens failed.

- 5 Several different stress levels were selected. The results are summarized in Table 5.

The pressure resistance at all temperatures and hoop stress values is measured according to ISO 1167 with pipe dimensions 32x3mm.

10

Table 5: Pipe tests

Product	Unit	Example I	Comparative Example A	Comparative Example B	Required Minimum PE 100 reference according to DIN 8075
Pressure tests at 20 °C					
Hoop stress					
12.0 MPa	h	>8000	8000	> 8000	100
11.7 MPa	h	> 8000	1700	> 8000	2500
11.05 MPa	h	> 5000	> 5000	> 5000	4380
Pressure tests at 80 °C					
Hoop Stress					
4.9 MPa	h	>8800	1720	5300	2500
5.4 MPa	h	4170	270	3800	165
5.7 MPa	h	5900	1320	2190	1000

Example I shows significant improvement of all mechanical properties (such as impact and strain hardening modulus) for a rheologically narrower material.

The pressure resistance is significantly higher than PE100. Example I shows the

- 15 best performance regarding the combination of pressure resistance, impact resistance and other mechanical properties.

CLAIMS

1. Bimodal polyethylene having a flow ratio FRR ranging between ≥ 30 and ≤ 40 , a density ranging between ≥ 949.0 and ≤ 952.0 kg/m³, an MFR_{190/5} ranging between ≥ 0.1 and ≤ 0.2 g/10min and comprising from 50 to 54 % by weight of an ethylene homopolymer A and from 46 to 50 % by weight of an ethylene-butene copolymer B, where all percentages are based on the total weight of the composition and wherein ethylene homopolymer A has a viscosity number ≥ 70 and ≤ 100 cm³/g and a density between ≥ 968 and ≤ 972 kg/m³ and wherein the bimodal polyethylene has
 - impact resistance (according to notched Charpy measurements at 23°C ; ISO 179) ≥ 30 kJ/m² and ≤ 40 kJ/m²
 - impact resistance (notched Charpy measurements at -30°C; ISO 179) ≥ 15 kJ/m² and ≤ 20 kJ/m²
 - strain hardening (measured according to the strain hardening method, based on the publication by Kurelec, L. *et al* in *Polymer* 2005, 46, p 6369-6379) ≥ 40 MPa and ≤ 50 MPa and
 - shear thinning index ≥ 65 and ≤ 80 .
2. Polyethylene according to Claim 1 characterized in that the density of ethylene homopolymer A ranges between ≥ 969 and ≤ 971 kg/m³.
3. Polyethylene according to any one of Claims 1-2 characterized in that the viscosity number of ethylene homopolymer A ranges between ≥ 77 and ≤ 90 cm³/g.
4. Polyethylene according to any one of Claims 1-3 characterized in that the density of the bimodal polyethylene ranges between ≥ 949.0 and ≤ 951.0 kg/m³.
5. A process for the preparation of polyethylene according to any one of Claims 1-4 with a two-step slurry polymerisation process in the presence of a catalyst system comprising
 - (I) the solid reaction product obtained from the reaction of:
 - a) a hydrocarbon solution containing
 - 1) an organic oxygen containing magnesium compound or a halogen containing magnesium compound and
 - 2) an organic oxygen containing titanium compound and
 - b) an aluminium halogenide having the formula AlR_nX_{3-n} in which R is a hydrocarbon moiety containing 1 – 10 carbon atoms, X is halogen and $0 < n < 3$ and

- 14 -

(II) an aluminium compound having the formula AlR_3 in which R is a hydrocarbon moiety containing 1 – 10 carbon atoms .

6. Article comprising polyethylene according to any one of Claims 1- 4 or polyethylene obtained with the process according to Claim 5.
- 5 7. Pipe having a pressure resistance at 20°C, 12 Mpa (measured according to ISO 1167 with pipe dimensions 32x3mm) >8000 hours comprising polyethylene according to any one of Claims 1- 4 or polyethylene obtained with the process according to any one of Claim 5.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/065346

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F210/16 C08F4/655 C08L23/06 F16L9/12
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F C08L F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 897 934 A1 (SOLVAY [BE]) 24 February 1999 (1999-02-24)	5-7
A	examples 1,2,3R,4,5R,6R,7,8,9R paragraph [0045] - paragraph [0047] abstract	1-4
X	WO 2013/087167 A2 (SAUDI BASIC IND CORP [SA]; BATINAS-GEURTS AURORA ALEXANDRA [NL]; FRIED) 20 June 2013 (2013-06-20)	5-7
A	page 2, line 5 - line 10 examples I,II comparative examples F,G,H	1-4
A	WO 97/22633 A1 (BOREALIS AS [DK]; PALMQVIST ULF [SE]; JOHANSSON SOLVEIG [SE]; THORN LA) 26 June 1997 (1997-06-26) example 2; table II	1-4
	----- -/-	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

27 September 2016

Date of mailing of the international search report

07/10/2016

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Gamb, Véronique

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2016/065346

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 1 719 788 A1 (BOREALIS TECH OY [FI]) 8 November 2006 (2006-11-08) example 4; table 1 -----	1-7

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/065346

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0897934	A1	24-02-1999	AR 016842 A1 01-08-2001
		AT 313569 T 15-01-2006	
		AU 747084 B2 09-05-2002	
		BE 1011333 A3 06-07-1999	
		BR 9803186 A 14-12-1999	
		CA 2243614 A1 20-02-1999	
		CN 1208744 A 24-02-1999	
		CZ 9802661 A3 17-03-1999	
		DE 69832856 T2 13-07-2006	
		EP 0897934 A1 24-02-1999	
		EP 1405875 A2 07-04-2004	
		EP 2275483 A1 19-01-2011	
		ES 2255126 T3 16-06-2006	
		ES 2536111 T3 20-05-2015	
		HU 9801897 A2 28-05-1999	
		JP 4805430 B2 02-11-2011	
		JP H11147919 A 02-06-1999	
		MY 128257 A 31-01-2007	
		NO 983790 A 22-02-1999	
		PL 328048 A1 01-03-1999	
		RU 2207347 C2 27-06-2003	
		US 6225421 B1 01-05-2001	
		US 2001014724 A1 16-08-2001	
		ZA 9807330 B 14-02-2000	
WO 2013087167	A2	20-06-2013	CN 103998471 A 20-08-2014
			EA 201400692 A1 28-11-2014
			EP 2791188 A2 22-10-2014
			KR 20140107367 A 04-09-2014
			US 2014350200 A1 27-11-2014
			WO 2013087167 A2 20-06-2013
WO 9722633	A1	26-06-1997	AR 005144 A1 14-04-1999
			AT 195537 T 15-09-2000
			AU 705479 B2 20-05-1999
			AU 1216697 A 14-07-1997
			BR 9612067 A 17-02-1999
			CA 2240170 A1 26-06-1997
			CZ 9801914 A3 14-10-1998
			DE 69609865 D1 21-09-2000
			DE 69609865 T2 04-01-2001
			EP 0869978 A1 14-10-1998
			HU 9901352 A2 30-08-1999
			JP 2000502143 A 22-02-2000
			TW 418216 B 11-01-2001
			US 6225420 B1 01-05-2001
			WO 9722633 A1 26-06-1997
			ZA 9610637 B 24-06-1997
EP 1719788	A1	08-11-2006	AT 401357 T 15-08-2008
			AU 2006246039 A1 16-11-2006
			BR PI0610424 A2 22-06-2010
			CN 101171275 A 30-04-2008
			EA 200702170 A1 28-04-2008
			EP 1719788 A1 08-11-2006
			ES 2309613 T3 16-12-2008
			KR 20080005258 A 10-01-2008
			PT 1719788 E 28-10-2008

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/065346

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		US 2008241510 A1	02-10-2008
		WO 2006119875 A1	16-11-2006
