



(51) International Patent Classification:

D04H 1/4274 (2012.01) **D04H 1/435** (2012.01)
D04H 1/4291 (2012.01) **D04H 1/56** (2006.01)

(21) International Application Number:

PCT/US2015/012658

(22) International Filing Date:

23 January 2015 (23.01.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/931,101 24 January 2014 (24.01.2014) US

(71) Applicants: **FITESA SIMPSONVILLE, INC.** [US/US];
840 S.E. Main Street, Simpsonville, South Carolina 29681
(US). **FITESA GERMANY GMBH** [DE/DE]; Woltorfer
Strasse 124, 31224 Peine (DE).

(72) Inventors: **NOVARINO, Elena**; Brabeckstrasse 165,
30539 Hannover (DE). **NEWKIRK, David D.**; 107 Glad-
stone Way, Greer, South Carolina 29650 (US). **HARTL,**
Helmut; Bischofsburgweg 4, 38124 Braunschweig (DE).
STREICH, Stefanie; Weidenweg 8, 31234 Edemissen
(DE).

(74) Agents: **BALTS, Timothy, J.** et al.; Alston & Bird LLP,
Bank of America Plaza, 101 South Tryon Street, Suite
4000, Charlotte, North Carolina 28280-4000 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii))
- of inventorship (Rule 4.17(iv))

Published:

- with international search report (Art. 21(3))

(54) Title: MELTBLOWN NONWOVEN WEB COMPRISING RECLAIMED POLYPROPYLENE COMPONENT AND RE-
CLAIMED SUSTAINABLE POLYMER COMPONENT AND METHOD OF MAKING SAME FIELD

(57) Abstract: Process of preparing meltblown fibers that are reclaimed from a starting material of a polypropylene component and a sustainable polymer component is provided. In one aspect, the method includes blending starting fibers of a polypropylene component and a sustainable polymer component under heat to form a molten stream, and then vis-breaking the components to obtain a polymeric blend that is suitable for use in meltblowing applications. The molten stream of the vis-broken polymer components are extruded through a meltblowing die to form a stream of meltblown fibers that is then collected on a collection surface to form a co-herent meltblown web. The starting material may be bicomponent filaments having a sheath-core configuration in which the polypropylene component is oriented in the sheath and the sustainable polymer component is oriented in the core of the filaments. The invention is also directed to meltblown fibers and webs prepared from the process.



MELTBLOWN NONWOVEN WEB COMPRISING RECLAIMED
POLYPROPYLENE COMPONENT AND RECLAIMED SUSTAINABLE
POLYMER COMPONENT AND METHOD OF
MAKING SAME FIELD

The present invention relates to nonwoven webs, and more particularly to a meltblown web prepared from fibers comprising a blend reclaimed polypropylene component and a reclaimed sustainable polymer component.

BACKGROUND

5 Traditionally, many materials used in the production of nonwovens are prepared from thermoplastic polymers, such as polyester, polystyrene, polyethylene, and polypropylene. These polymers are generally very stable and can remain in the environment for a long time. Recently, however, there has been a trend to develop articles and products that are considered environmentally friendly and sustainable. As
10 part of this trend, there has been a desire to produce ecologically friendly products comprised of increased sustainable content in order to reduce the content of petroleum based materials.

One promising polymer that may meet this desire is polylactic acid (PLA). Polylactic acid, also known as polylactide, is a renewable thermoplastic, aliphatic
15 polyester derived from renewable resources, such as sugar, starch, or cellulose. PLA is promising because it is manufactured from natural substances, such as corn, and therefore may provide a sustainable alternative to petrochemical-derived products.

However, PLA does not necessarily have the same strength and elongation properties that may be associated with synthetic polymers, such as polyethylenes and
20 polypropylenes. As a result, composite products have been developed that include a PLA component and a synthetic polymer component. One such product is a nonwoven sheet material comprising bicomponent filaments having a PLA core and a polypropylene sheath. Such products have found use in the diaper industry where it is a goal to increase the level of sustainable components in the consumer products.

25 However, the use of such composite material may also present disadvantages. One such disadvantage is due to the difficulty in reclaiming or recycling materials that are

a composite of synthetic and sustainable polymers. As a result, the use of such materials has led to increased costs, which in turn, has limited the use of such materials in commercial products.

Accordingly, a need still exists for improved methods and products for
5 incorporating sustainable polymers, such as PLA, into commercial products.

SUMMARY

Embodiments of the invention are directed to methods of preparing meltblown fibers that are reclaimed from a starting material of a polypropylene component and a
10 sustainable polymer component. In one embodiment, the invention provides a method of preparing a meltblown web in which starting fibers comprised of a polypropylene component and a sustainable polymer component are blended under heat to form a molten stream comprising a blend of the polypropylene component and the sustainable polymer component. The molten stream is then subjected to vis-breaking in which the
15 polypropylene component and the sustainable polymer component are vis-broken so that the vis-broken components are suitable for use in meltblowing applications. The molten stream of the vis-broken polymer components are extruded through a meltblowing die to form a stream of meltblown fibers that is then collected on a collection surface to form a coherent meltblown web. In some embodiments, the meltblown web may be thermally
20 bonded, such as passing the web through a calender roll.

In one embodiment, the starting material comprises bicomponent filaments having a sheath-core configuration in which the polypropylene component is oriented in the sheath and the sustainable polymer component is oriented in the core of the filaments. In some embodiments, the starting material comprises a spunbond web, such as a
25 spunbond web comprising bicomponent filaments.

In some embodiments, vis-breaking is accomplished by blending a vis-breaking agent into the molten stream. In some embodiments, the vis-breaking agent may comprise a peroxide, hydroxylamine ester composition or thio composition. In a preferred embodiment, the vis-breaking agent comprises a hydroxylamine ester.

30 Aspects of the invention are also directed to meltblown webs comprising the meltblown fibers that are a blend of the reclaimed polypropylene component and the reclaimed sustainable polymer component. In one embodiment, the meltblown web comprises a blend of a reclaimed polypropylene component and a reclaimed polylactic acid component. The invention is also directed to composite sheet structures comprising
35 the meltblown web, such as meltblown/spunbond (MS) laminates, spunbond/meltblown/spunbond (SMS) laminates, and spunbond/meltblown/meltblown/spunbond (SMMS) laminates.

DETAILED DESCRIPTION

The present invention now will be described more fully hereinafter with reference to the accompanying drawings, in which some, but not all embodiments of the inventions are shown. Indeed, these inventions may be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these
5 embodiments are provided so that this disclosure will satisfy applicable legal requirements.

For the purposes of the present application, the following terms shall have the following meanings:

10 The term "fiber" can refer to a fiber of finite length or a filament of infinite length.

As used herein the term "nonwoven web" means a structure or a web of material which has been formed without use of weaving or knitting processes to produce a structure of individual fibers or threads which are intermeshed, but not in an identifiable, repeating manner. Nonwoven webs have been, in the past, formed by a variety of
15 conventional processes such as, for example, meltblown processes, spunbond processes, and staple fiber carding processes.

As used herein, the term "meltblown" refers to a process in which fibers are formed by extruding a molten thermoplastic material through a plurality of fine, usually circular, die capillaries into a high velocity gas (e.g. air) stream which attenuates the
20 molten thermoplastic material and forms fibers, which can be to microfiber diameter, such as less than 10 microns in diameter. Thereafter, the meltblown fibers are carried by the gas stream and are deposited on a collecting surface to form a web of random meltblown fibers. Such a process is disclosed, for example, in U.S. Pat. Nos. 3,849,241 to Butin, et al.; 4,307,143 to Meitner, et al.; and 4,707,398 to Wisneski, et al., which are incorporated
25 herein in their entirety by reference. Meltblown fibers in accordance with embodiments of the present invention may have circular and non-circular cross sections.

As used herein, the term "spunbond" refers to a process involving extruding a molten thermoplastic material as filaments from a plurality of fine, usually circular, capillaries of a spinneret, with the filaments then being attenuated and drawn
30 mechanically or pneumatically. Based on the configuration of the spinneret orifice, fibers of various cross-section shapes can be produced including circular and non-circular, such as tri-lobal, delta, and the like shaped fibers. The filaments are deposited on a collecting surface to form a web of randomly arranged substantially continuous filaments which can thereafter be bonded together to form a coherent nonwoven fabric. The production of
35 spunbond non-woven webs is illustrated in patents such as, for example, U.S. Pat. Nos. 3,338,992; 3,692,613, 3,802,817; 4,405,297 and 5,665,300. In general, these spunbond processes include extruding the filaments from a spinneret, quenching the filaments with

a flow of air to hasten the solidification of the molten filaments, attenuating the filaments by applying a draw tension, either by pneumatically entraining the filaments in an air stream or mechanically by wrapping them around mechanical draw rolls, depositing the drawn filaments onto a collection surface to form a web, and bonding the web of loose
5 filaments into a nonwoven fabric. The bonding can be any thermal or chemical bonding treatment, with thermal point bonding being typical. Other methods such a mechanical and hydroentanglement may also be used.

As used herein "thermal point bonding" involves passing a material such as two or more webs of fibers to be bonded between a heated calender roll and an anvil roll. The
10 calender roll is typically patterned so that the fabric is bonded in discrete point bond sites rather than being bonded across its entire surface.

As used herein the term "polymer" generally includes, but is not limited to, homopolymers, copolymers, such as, for example, block, graft, random and alternating copolymers, terpolymers, etc. and blends and modifications thereof. Furthermore, unless
15 otherwise specifically limited, the term "polymer" shall include all possible geometrical configurations of the material, including isotactic, syndiotactic and random symmetries.

As used herein the term "reclaimed", also known as recycled polymer, refers to a polymeric material that was previously extruded once into some product form, such as a fiber, film, or solid plastic component, but then reprocessed back into a form such as a
20 pellet that can be reextruded a second time into a useful fiber, film or solid plastic part.

In many recycle processes significant effort is made to minimize reduction in molecular weight. In other cases a purposeful reduction in molecular weight may be made to convert the recycled polymer into a new molecular weight useful for a specific new purpose.

One example of a process for reclaiming a polymeric material, such as polypropylene, is vis-breaking. In vis-breaking, the previously extruded polymer (e.g., starting material) is subject to a treatment process, chemical, mechanical, or thermal, in which the polymer chains are broken or fractured to produce a reclaimed polymer composition having a molecular weight and melt flow rate that is different than that of the
25 starting material. For instance, in the case of polypropylene, the polypropylene prior to extrusion may have a molecular weight and melt flow rate (MFR) so that the polypropylene polymer was suitable for use in spunbond processes. Following extrusion this polypropylene may then be subject to vis-breaking so as to produce a vis-broken polypropylene component having a molecular weight and MFR that is suitable for use in
30 meltblowing processes. In the present invention, the polymer material that is to be
35 "reclaimed" is subjected to a vis-breaking process.

Embodiments of the present invention are directed to processes for preparing a meltblown fabric comprised of composite meltblown fibers that have been reclaimed from a starting material comprised of a polypropylene component and a sustainable polymer component.

5 In the context of the present invention, the term "sustainable" refers to a material derived from natural processes such as agriculture or forestry that are renewed or replenished to remain available for future generations. Sustainable polymers can thus be contrasted with petroleum sourced polymers where the supply of petroleum is not naturally replenished in a reasonable length of time. Sustainable polymers suitable for
10 embodiments of the present invention typically have a sustainable content that is at least 25 weight percent on the weight percent of the sustainable polymer content, and more typically at least 50 weight percent, with a weight percent of at least 75%, and at least 90% being somewhat more typical. In a preferred embodiment, the sustainable polymer component comprises from 90 to 100 weight percent of sustainable content.

15 In some embodiments, the sustainable polymer component may comprise biodegradable polymer materials. "Biodegradable" refers to a material or product which degrades or decomposes under environmental conditions that include the action of microorganisms. Thus a material is considered as biodegradable if a specified reduction of tensile strength and/or of peak elongation of the material or other critical physical or
20 mechanical property is observed after exposure to a defined biological environment for a defined time. Depending on the defined biological conditions, a product comprised of sustainable polymer component might or might not be considered biodegradable.

A special class of biodegradable product made with sustainable content might be considered as compostable if it can be degraded in a composting environment. The
25 European standard EN 13432, "Proof of Compostability of Plastic Products" may be used to determine if a fabric or film comprised of sustainable content could be classified as compostable.

In one embodiment, the starting material comprises multicomponent fibers in which the polypropylene component and sustainable polymer component define distinct
30 regions in the fibers. For example, the starting material may comprise bicomponent filaments or fibers which have been formed from at least two polymers extruded from separate extruders but spun together to form one fiber. The polymer components in bicomponent fibers are generally arranged in substantially constantly positioned distinct zones across the cross-section of the bicomponent fibers and extend continuously along
35 the length of the bicomponent fibers. The configuration of such a bicomponent fiber may be, for example, a sheath/core arrangement wherein one polymer is surrounded by another or may be a side-by-side arrangement or an "islands-in-the-sea" arrangement.

Examples of bicomponent fibers are described in U.S. Pat. No. 5,108,820 to Kaneko et al., U.S. Pat. No. 5,336,552 to Strack et al., and U.S. Pat. No. 5,382,400 to Pike et al., each of which is incorporated herein in its entirety by reference. Multicomponent fibers may include conventional additives, such as pigments and surfactants that may be incorporated into one or both polymer streams, or applied to the filament surfaces.

In a preferred embodiment, the starting material comprises a bicomponent fiber having a polypropylene sheath and a core comprised of a sustainable polymer component. The ratio of the polypropylene to the sustainable polymer component may range from about 10 % polypropylene to 90 % sustainable polymer component to 80 % polypropylene to 20 % sustainable polymer component, and more preferably from 30% polypropylene to 70% sustainable polymer component to 70% polypropylene to 30% sustainable polymer component.

In some embodiments, the sustainable polymer component may be derived from an aliphatic component possessing one carboxylic acid group (or a polyester forming derivative thereof, such as an ester group) and one hydroxyl group (or a polyester forming derivative thereof, such as an ether group) or may be derived from a combination of an aliphatic component possessing two carboxylic acid groups (or a polyester forming derivative thereof, such as an ester group) with an aliphatic component possessing two hydroxyl groups (or a polyester forming derivative thereof, such as an ether group).

The term "aliphatic polyester" covers - besides polyesters which are made from aliphatic and/or cycloaliphatic components exclusively also polyesters which contain besides aliphatic and/or cycloaliphatic units aromatic units, as long as the polyester has substantial sustainable content. As noted above, the sustainable content is typically at least 25 weight %, and more preferably 75 weight % and even more preferably at least 90 weight %.

Polymers derived from an aliphatic component possessing one carboxylic acid group and one hydroxyl group are alternatively called polyhydroxyalkanoates (PHA). Examples thereof are polyhydroxybutyrate (PHB), poly- (hydroxybutyrate-co-hydroxyvalerate) (PHBV), poly- (hydroxybutyrate-co- polyhydroxyhexanoate) (PHBH), polyglycolic acid (PGA), poly- (epsilon-caprolactone) (PCL) and preferably polylactic acid (PLA).

Examples of polymers derived from a combination of an aliphatic component possessing two carboxylic acid groups with an aliphatic component possessing two hydroxyl groups are polyesters derived from aliphatic diols and from aliphatic dicarboxylic acids, such as polybutylene succinate (PBSU), polyethylene succinate (PESU), polybutylene adipate (PBA), polyethylene adipate (PEA), polytetramethylene adipate/terephthalate (PTMAT).

In the case of polyesters derived from a combination of an aliphatic component processing two caboxylated acid groups with an aliphatic component possessing two hydroxyl groups either the diacid or the diol or both the diacid and the diol could be comprised of substantial sustainable content. Any of the above polyesters can be used
5 as long as they contain substantial sustainable content.

In the context of the present invention, the PLA grade of the starting material should have proper molecular properties to be spun in spunbond processes. Examples of suitable include PLA grades supplied from NatureWorks LLC, of Minnetonka, MN 55345 such as, grade 6752D, 6100D, and 6202D believed to be produced as generally
10 following the teaching of US 5,525,706 and 6,807,973 both to Gruber et al..

A wide variety of polypropylene polymers may be used in the starting material including both polypropylene homopolymers and polypropylene copolymers. In one embodiment, the polypropylene of the starting material may comprise a metallocene or Ziegler Natta catalyzed propylene polymers.

15 Examples of Ziegler Natta polypropylenes that may be used in embodiments of the present invention include TOTAL®3866 polypropylene from Total Petrochemicals USA, INC of Houston, TX; Braskem CP 360H polypropylene from Braskem America of Philadelphia, PA; ExxonMobil PD 3445 from ExxonMobil of Houston, TX; Sabic 511A from Sabic of Sittard, The Netherlands; and Pro-fax PH 835 from Basell Polyolefins of
20 Wilmington, DE. Examples of suitable metallocene polypropylenes may include TOTAL® M3766 polypropylene from Total Petrochemicals USA, INC of Houston, TX; TOTAL® MR 2001 polypropylene from Total S.A. of Courbevoie, France; ACHIEVE® 3754 polypropylene from ExxonMobil of Houston, TX; and ACHIEVE® 3825 polypropylene from ExxonMobil of Houston, TX.

25 The starting material is subjected to a vis-breaking process in which the polypropylene component and sustainable polymer component are visbroken to reduce their average molecular weight. In one embodiment, the vis-breaking of both components may be accomplished under typical vis-breaking conditions and using a propylene vis-breaking agent. However, the sustainable polymer component, for
30 example, PLA, may not require a vis-breaking agent and depolymerization may occur via hydrolysis during the vis-breaking process. Accordingly, it is important to control the moisture content of the starting material so that PLA depolymerization does not proceed to too low a molecular weight such that the combination of PLA and visbroken polypropylene are no longer useful as raw material for the production of meltblown
35 fabrics.

In some embodiments, the vis-breaking may be accomplished using a vis-breaking agent to facilitate molecular scission of the propylene molecules. In some

embodiments, the vis-breaking may also be accomplished using heat (often 300-400° C.), radiation, shear (e.g., using an extruder), combinations of the foregoing techniques, or any other technique which accomplishes the desired level of molecular scission in the propylene molecules and the molecules of the sustainable polymer. It is important to control the moisture level in such processes to insure the hydrolysis and thus depolymerization of the PLA or other polyester does not progress so far that the sustainable polymer component in combination with the vis-broken polypropylene is no longer fit for use in the production of meltblown fabric.

A wide variety of vis-breaking agents may be used in embodiments of the invention. Suitable catalysts may include, for instance, alkyl hydroperoxides and dialkyl peroxides, as disclosed in U.S. Pat. No. 4,282,076, issued to Boynton. One suitable peroxide is 2,5-dimethyl-2,5-bis(t-butylperoxy)hexane. Another suitable peroxide is 2,5-dimethyl-2,5-bis(t-butylperoxy)hexane-3. These peroxides are available under the trade name LUPERSOL® from Pennwalt Corporation.

In a preferred embodiment, the vis-breaking agent comprises a hydroxylamine ester composition or thio composition, such as those described in U.S. Patent No. 7,956,109, the contents of which are hereby incorporated by reference. An example of a particularly preferred vis-breaking agent is a hydroxylamine ester composition available from BASF under the tradename IRGATEC® CR 76. Advantageously, the vis-breaking agents are peroxide free and do not adversely affect the properties of the resulting vis-broken sustainable polymer component.

The vis-breaking agent may be added to the starting material while the components of the starting material are in a molten state. For instance, the vis-breaking agent may be introduced into the starting material while the components are in a molten state at a temperature from about 180-340° C. For example, the starting material may be heated to a temperature from about 240-340° C, and preferably from about 260-320° C, and more preferably, from about 290-310° C. In some embodiments, the vis-breaking agent may be introduced into the starting material in an extruder, for example. In general, the amount of heat affects the rate and extent of the vis-breaking.

As discussed previously, the level of moisture present in the combination of sustainable polymer component, for example, PLA, and the polypropylene must be controlled to achieve some hydrolysis of the PLA to achieve some reduction in molecular weight but not depolymerization such that the combination of PLA and polypropylene is no longer fit for use in making a meltblown fabric. The moisture level as measured by methods well known in the art, such as the Karl Fischer method, should be less than about 200 ppm, and in particular, less than about 100 ppm, and more particularly, approximately 50 ppm.

The amount of vis-breaking agent will generally depend on the amount of propylene in the starting material and the desired final melt flow rate of the resulting vis-broken product. In one embodiment, the amount of vis-breaking agent, for example, in embodiments in which the vis-breaking agent comprises a hydroxylamine ester, may be from about 0.5-3% by weight of the propylene polymer, preferably about 0.75-2.5% by weight of the polymer, more preferably about 0.8-1% by weight of the propylene polymer. The desired addition level is generally dependent on temperature during the vis-breaking thus these ranges assume an operating temperature in the range of 270° to 290° C with the most preferred extruder temperature in the range of 270° to 285°C.

In the case of a vis-breaking agent comprising a peroxide, the amount of peroxide added may be about 0.001-2.0% by weight of the propylene polymer, preferably about 0.1-1.0% by weight of the polymer, more preferably about 0.2-0.7% by weight of the propylene polymer.

The vis-breaking conditions should be selected and controlled so that the vis-broken propylene polymer exhibits sufficient degradation to be useful in processes for preparing a meltblown nonwoven web. In some embodiments, the vis-broken propylene polymer should have a melt flow rate (MFR) in the range of approximately 400 to 2,500 or more preferred from approximately 500 to 2,000, and most preferred from about 700 to 1,800.

The resulting vis-broken starting material results in a blend of the vis-broken polypropylene component and vis-broken and/or hydrolyzed sustainable polymer component. Preferably, the vis-broken blend has an MFR to make it useful for preparation of meltblown nonwoven webs. In one embodiment, the resulting vis-broken blend has an MFR of at least about 400 to 2,500, and preferably from about 500 to 2,000, and more preferably about 700 to 1,800.

The resulting vis-broken starting material, also referred to as reclaimed polymer may be pelletized for future use in the manufacture of meltblown webs, or in a continuous process wherein the reclaimed starting material is immediately extruded and spun into meltblown fibers using conventional techniques.

In some embodiments, the reclaimed blend comprising the polypropylene component and the sustainable polymer component may be blended with virgin polymer (never used) to form meltblown fibers.

Meltblown webs prepared in accordance with embodiments of the present invention comprise a blend of the polypropylene component and the sustainable polymer component that have been reclaimed from the starting material. The meltblown fibers generally have diameters of less than 10 microns, and in particular, diameters of less than 8 microns. In one embodiment, the meltblown fibers have diameters from about 3

to 0.5 microns, and in particular, from about 1 to 2 microns. In some embodiments, the meltblown fibers may have diameters from about 3 to less than 0.5 microns, and in particular from about 1 to 3 microns.

Meltblown webs prepared in accordance with embodiments of the present invention may have a wide variety of basis weight ranges depending on the desired application. For example, meltblown webs and laminates incorporating such meltblown webs may have basis weights ranging from about 0.25 to 20 g/m², and in particular, from about 1.5 to 3 g/m². In some embodiments, the meltblown webs may have basis weights ranging from 1 to 400 g/m², for example, from about 15 to 400 g/m².

Meltblown webs prepared in accordance with embodiments of the present invention may be used in wide variety of applications. For example, embodiments of the invention may be used for personal care applications, for example products for baby care (diapers, wipes), for fem care (pads, sanitary towels, tampons), for adult care (incontinence products), or for cosmetic applications (pads). In these applications, the meltblown web may be incorporated into a multilayered structure. For example, meltblown webs prepared in accordance with embodiments of the present invention may be used in the production in a variety of different multilayer structures including meltblown/spunbond (MS) laminates, spunbond/meltblown/spunbond (SMS) laminates, and spunbond/meltblown/meltblown/spunbond (SMMS) laminates, for example. In these multilayer structures, the basis weight may range from as low as 0.25 g/m² and up to 20 g/m².

In some embodiments in which the meltblown layer is a part of a multilayer structure (e.g., MS, SMS, and SMMS), the amount of the meltblown in the structure may range from about 5 to 20%, and in particular, from about 10 to 15% of the structure as a percentage of the structure as a whole.

In addition, meltblown webs in accordance with embodiments of the present invention may also be used in industrial applications including filters, cleaning products, "pigs" to absorb spilt oil or (if treated with surfactant) to absorb contaminated materials from water, and the like. In these applications, the meltblown webs may have higher basis weight ranges that may range from about 15 to 400 g/m².

Multilayer structures in accordance with embodiments can be prepared in a variety of manners including continuous in-line processes where each layer is prepared in successive order on the same line, or depositing the meltblown layer on a previously formed spunbond layer. The layers of the multilayer structure can be bonded together to form a multilayer composite sheet material using thermal bonding, mechanical bonding, adhesive bonding, hydroentangling, or combinations of these. In a preferred

embodiment, the layers are thermally point bonded to each other by passing the multilayer structure through a pair of calender rolls.

EXAMPLES

5 Pellets comprised of a blend of PP/PLA are subjected to a vis-breaking process to obtain a molecular weight and MFR suitable for meltblown fiber production. The pellets are obtained from Fitesa's Washougal spunbond plant. In the course of making a polypropylene/ polylactic acid (PP/PLA) bicomponent spunbond fabric, waste material is made, such as from slitting the web into rolls or from the start-up of the process. The
10 waste is converted into pellets via heat and pressure via the use of an EREMA Plastic Recycling Machine as available from EREMA North America of Ipswich, MA 01938. The resulting pellets have a composition of approximately 50% PLA and 50% PP mixed generally homogenously within the resin pellet. The PLA is a spunbond grade supplied by NatureWorks LLC, of Minnetonka, MN 55345; believed made by generally following
15 the teaching of Gruber et al. in US 5,525,706 and 5,807,973. The polypropylene is a 35 MFR Ziegler Natta type as commonly used for spunbond applications.

A 500 Kg box of the above described PP/PLA pellets is obtained from Fitesa Washougal, and is subjected to a vis-breaking process to form a meltblown web. This step is carried out at Fitesa's pilot line in Peine, Germany. Before the vis-breaking
20 operation, the PP/PLA pellets are dried overnight via exposure to dry hot air until a moisture level as measured by the Karl Fischer method shows a moisture level of approximately 50 ppm.

Example 1

The Peine pilot line is configured with a Reicofil meltblown spin beam line. The
25 line is initially run with a 35 MFR Spunbond grade polypropylene (PP) resin to which IRGATEC® CR76 is metered into the extruder at a ratio of 0.9 parts CR76 to 99.1 parts PP pellets while increasing the extruder temperature to 275 – 280° C. The pilot line speed is adjusted with extruder output so a web of PP meltblown at basis weight of 32 GSM is achieved.

30 The 35 MFR spunbond resin is now replaced with the above described PP/PLA pellets and the level of CR 76 is slowly lowered so the ratio of CD 76 to PP in the pellets (50/50 PP/PLA) is carefully maintained to yield a meltblown web of 32 GSM. During this operation extrusion pressure is monitored to maintain values similar to those seen when processing meltblown grade PP. The pilot line speed is adjusted to match extruder
35 output so a web of PP/PLA meltblown fibers at basis weight of 32 GSM is achieved.

The resulting meltblown web has meltblown fibers comprised of a blend of reclaimed PP and PLA. This new meltblown composition shows surprising and

unexpected absorptive and filtration properties. While not bound by theory, the inventors believe that these properties may result from the intimate mixture of hydrophobic PP and slightly hydrophilic PLA polymers within the fibers of the meltblown web.

Example 2

5 In Example 2 a SMS laminate is made using the meltblown web prepared in Example 1. The pilot line has only one spunbond beam production of in-line made SMS laminates must be simulated by the steps of spinning a web of PP spunbond (at 8 GSM) then spinning the meltblown fibers of Example 1 onto the spunbond layer to make in-line SM followed by laying an previously prepared spunbond web on top of the SM webs. The
10 resulting SMS structure is calendered to produce a thermally bonded SMS laminate. The inventors observe an unexpected and surprising improvement in resistant to delamination of the layers of spunbond PP from the middle layer of the PP/PLA meltblown web. While not being bound by theory, the inventors believe this improvement comes from the intimate mixture of PP and PLA in the meltblown layer which improves
15 and promotes bonding of all layers of the SMS laminate together.

Comparative Example

In this example, a SMS web comprising polypropylene spunbond layers and a meltblown layer of PLA was prepared. The PLA was a meltblown grade available from NatureWorks, PLA Grade 6252D. As in Example 2, a meltblown layer was deposited
20 onto a spunbond polypropylene layer followed be positioning a previously prepared spunbond polypropylene layer. The resulting laminate was then thermally bonded via calendering by passing the laminate through a pair of calendering rolls at a temperature of 130° C. The inventors observed that the resulting SMS laminate exhibited poor lamination strength and that the spunbond layers were easily delaminated from the
25 meltblown layer. At higher bonding temperatures it was observed that the PLA in the meltblown layer migrated through the spunbond layers, which resulted in undesirable adhesion of the nonwoven layers to the surface of the calender roll.

As briefly discussed above, the inventors believe that the blend of the polypropylene and PLA in the reclaimed starting material significantly improves bonding
30 between the layers due to the intimate mixture of PP and PLA in the meltblown layer. This intimate mixture improves and promotes bonding of all layers of the SMS laminate together.

Example 3

In this example, the effects of blending a vis-breaking agent with previously spun
35 polymeric materials comprised of a polypropylene component and a sustainable polymer component on the melt flow rate of the resulting reclaimed polymer blend is

characterized. Recycled pellets comprising a composition of approximately 50% PLA and 50% PP as described above were used as the starting material.

5 The recycled pellets were blended with 5 wt. % Irgatec CR76 as the vis-breaking agent and the melt flow rate was determined in accordance with DIN EN ISO 1133 (230° C, 4 minute heating time at 2.16 KG load). In addition, the melt flow rate of the recycled pellets with no vis-breaking agent, and the melt flow of virgin polypropylene with 5 wt. % of the vis-breaking agent was also evaluated for comparison. The starting melt flow rate of the virgin polypropylene (Sabic Type 519A) is 35 g/10min at 230°C per the reported specification of the manufacturer. The results are summarized in the Table below.

Sample No	Polymer compositions	Amount Vis-breaking agent (wt. %)	MFR (g/10min at 230°C)
1	PLA/PP Recycle	0	128
2	PLA/PP Recycle	5	169
3	Polypropylene	5	101

10

From the above Table, it can be seen that the addition of the vis-breaking agent to the blend of recycled pellets results in an increase in the MFR of the reclaimed blend. This demonstrates that the inventive process is useful in altering the polymer chemistry of the previously spun blend of propylene and PLA such that the melt flow rate is increased and thus should be of increased utility for meltblown applications.

15

Many modifications and other embodiments of the inventions set forth herein will come to mind to one skilled in the art to which these inventions pertain having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. Therefore, it is to be understood that the inventions are not to be limited to the specific
20 embodiments disclosed and that modifications and other embodiments are intended to be included within the scope of the appended claims. Although specific terms are employed herein, they are used in a generic and descriptive sense only and not for purposes of limitation.

20

THAT WHICH IS CLAIMED:

1. Process for preparing a meltblown web comprising:
providing starting fibers comprised of a polypropylene component and a
5 sustainable polymer component, wherein each of the components are disposed in distinct
regions of the fibers;
blending the polypropylene component and the sustainable polymer component
under heat to form a molten stream;
vis-breaking the polypropylene polymer component in the molten stream;
10 degrading the sustainable polymer component in the molten stream;
extruding the molten stream through a meltblowing die to form a stream of
meltblown fibers, wherein the meltblown fibers comprise a blend of reclaimed
polypropylene component and the sustainable polymer component; and
collecting the meltblown fibers on a collection surface to form a coherent web.
- 15 2. The process of claim 1, wherein the step of vis-breaking comprises
blending a vis-breaking agent with the molten stream.
3. The process of claim 2, wherein the vis-breaking agent comprises a
hydroxylamine ester composition or thio composition.
4. The process of claim 2, wherein the vis-breaking agent comprises a
20 hydroxylamine ester.
5. The process of any one of the preceding claims, wherein the amount of
vis-breaking agent is from about 0.5 to 3% by weight based on the total weight of the
propylene component.
6. The process of any one of the preceding claims, wherein the amount of
25 vis-breaking agent is from about 0.75 to 2.5% by weight based on the total weight of the
propylene component.
7. The process of claim 1, wherein the sustainable polymer component
comprises polylactic acid.
8. The process of claim 1, wherein the sustainable content in the sustainable
30 polymer component is from 90 to 100% by weight.
9. The process of claim 1, wherein the sustainable polymer component is
degraded via hydrolysis.

10. The process of claim 1, wherein the sustainable polymer component is degraded via vis-breaking.

11. The process of claim 9, wherein the steps of vis-breaking and degrading occur at substantially the same time.

5 12. The process of claim 1, wherein the starting fibers comprise bicomponent spunbond filaments wherein the polypropylene component is oriented in a sheath of the filaments and the sustainable polymer component is oriented in a core of the filaments.

10 13. The process of claim 12, wherein the ratio of the polypropylene component to the sustainable polymer component is from about 10 weight % polypropylene to 90 weight % sustainable polymer component to 80% polypropylene to 20% sustainable polymer component.

15 14. The process of claim 12, wherein the ratio of the polypropylene component to the sustainable polymer component is from about 30 weight % polypropylene to 70 weight % sustainable polymer component to 70% polypropylene to 30% sustainable polymer component.

15. The process of claim 1, wherein prior to the step of vis-breaking, the blended molten stream of the polypropylene component and the sustainable polymer component are subjected to a step of extruding the blend into a pellet.

20 16. The process of claim 6, further comprising the step of drying the pellets and then melting the pellets to form a molten stream.

17. The process of claim 7, wherein the moisture content of the pellets is less than 200 ppm.

25 18. A meltblown web comprising a coherent matrix of fibers comprised of a blend of a reclaimed polypropylene component and a reclaimed sustainable polymer component.

19. The meltblown web of claim 18, wherein the sustainable polymer component comprises polylactic acid.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2015/012658

A. CLASSIFICATION OF SUBJECT MATTER
INV. D04H1/4274 D04H1/4291 D04H1/435 D04H1/56
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2012/020336 A2 (KIMBERLY CLARK CO [US]; TOPOLKARAEV VASILY A [US]; ZHOU PEIGUANG [US];) 16 February 2012 (2012-02-16)	18,19
A	page 4, paragraph 2 - paragraph 3 page 13, paragraph 2 - paragraph 3 page 26, paragraph 2 - page 27, paragraph 1; claims 1,7,8,14,16; examples 5-10, 16	1-17
A	US 2012/123374 A1 (RICHESON GALEN C [US] ET AL) 17 May 2012 (2012-05-17) paragraph [0018] paragraph [0061] - paragraph [0070]; claims 1,5-8, 11-16	1-19
	----- -/-	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

28 April 2015

Date of mailing of the international search report

08/05/2015

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Demay, Stéphane

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2015/012658

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2010/012769 A1 (TOTAL PETROCHEMICALS RES FELUY [BE]; HAUBRUGE HUGUES [BE]; PAVY GUILLA) 4 February 2010 (2010-02-04) page 6, line 11 - page 7, line 25 page 12, line 16 - line 25; claims 1-15 -----	1-19
A	WO 2009/152349 A1 (3M INNOVATIVE PROPERTIES CO [US]; MOORE ERIC M [US]; SCHOLZ MATTHEW T) 17 December 2009 (2009-12-17) page 1, line 9 - line 32 page 9, line 4 - line 27 page 10, line 30 - page 11, line 16; claims 1,2,19,26 -----	1-19
A	US 2003/032357 A1 (GILLESPIE JAY DARRELL [US] ET AL) 13 February 2003 (2003-02-13) paragraph [0002] - paragraph [0007]; claims 1-5 -----	1-19
A	WO 2009/100732 A1 (FIBERWEB COROVIN GMBH [DE]; FIBERWEB SIMPSONVILLE INC [US]; CHESTER ST) 20 August 2009 (2009-08-20) page 14, line 26 - page 16, line 2; claims 1-16 -----	1-19
A	WO 2006/027327 A1 (CIBA SC HOLDING AG [CH]; ROTH MICHAEL [DE]; NESVADBA PETER [CH]; HORST) 16 March 2006 (2006-03-16) cited in the application the whole document -----	1-19

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2015/012658

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2012020336 A2	16-02-2012	AU 2011288213 A1 CN 103069059 A EP 2603623 A2 KR 20130097152 A RU 2013109177 A US 2012040185 A1 WO 2012020336 A2	31-01-2013 24-04-2013 19-06-2013 02-09-2013 20-09-2014 16-02-2012 16-02-2012
US 2012123374 A1	17-05-2012	US 2012123374 A1 WO 2012064468 A2	17-05-2012 18-05-2012
WO 2010012769 A1	04-02-2010	EP 2154275 A1 EP 2307595 A1 US 2011189916 A1 WO 2010012769 A1	17-02-2010 13-04-2011 04-08-2011 04-02-2010
WO 2009152349 A1	17-12-2009	AU 2009257365 A1 CA 2727427 A1 CN 102105625 A EP 2291558 A1 JP 5485988 B2 JP 2011524475 A US 2011189463 A1 WO 2009152349 A1	17-12-2009 17-12-2009 22-06-2011 09-03-2011 07-05-2014 01-09-2011 04-08-2011 17-12-2009
US 2003032357 A1	13-02-2003	AT 305530 T CN 1564885 A DE 60206400 T2 EP 1425445 A1 KR 20040030913 A MX PA04001019 A US 2003032357 A1 US 2003203698 A1 WO 03014440 A1	15-10-2005 12-01-2005 06-07-2006 09-06-2004 09-04-2004 27-05-2004 13-02-2003 30-10-2003 20-02-2003
WO 2009100732 A1	20-08-2009	CN 101952491 A EP 2245222 A1 JP 2011514450 A US 2011028062 A1 WO 2009100732 A1	19-01-2011 03-11-2010 06-05-2011 03-02-2011 20-08-2009
WO 2006027327 A1	16-03-2006	AT 420137 T CA 2577500 A1 CN 101014656 A EP 1786861 A1 JP 4884391 B2 JP 2008512533 A MY 143966 A TW I391434 B US 2008045662 A1 US 2011207892 A1 WO 2006027327 A1	15-01-2009 16-03-2006 08-08-2007 23-05-2007 29-02-2012 24-04-2008 29-07-2011 01-04-2013 21-02-2008 25-08-2011 16-03-2006