



— *of inventorship (Rule 4.17(iv))*

Published:

— *with international search report (Art. 21(3))*

— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

Field of the invention

The present invention relates to a reflective optical element for reflecting light in a wavelength range less than 50 nm in an EUV-lithographic projection exposure system. Further, it relates to an EUV projection lens of an EUV-lithographic projection exposure system and to a method to configure an EUV projection lens.

Background art – The EUV-lithographic projection exposure system

To reduce the size of micro-structured devices like semiconductor circuits (e.g. integrated, analogue, digital or memory circuits, thin-film magnetic heads) with the technique of optical lithography the optical resolution limit of optical microlithographic projection exposure systems must be further improved. Due to diffraction, the resolution limit in a first order approximation is inverse proportional to the numerical aperture of the projection lens of the microlithographic projection exposure system, with which structures are projected from a mask onto a substrate by a projection beam, to form the micro-structured devices there, e.g., by exposure of a light sensitive resist (which covers the substrate) with at least parts of the projection beam. For this reason, one focus is to increase the numerical aperture of the projection lens. Another focus is to reduce the used wavelength for the projection process, since the optical resolution limit is also proportional to this wavelength. For this reason the historical development of optical lithography systems was such that the wavelength of the used light in the projection process was reduced from visible light to ultraviolet light and now to Very Deep Ultra Violet light (VUV light, like 193 nm which is produced e.g. by an advanced ArF excimer laser). Now VUV lithography is broadly used in mass production of semiconductor circuits. Today, mass production of high integrated circuits is mostly done on microlithographic projection exposure systems with a projection light of the mentioned wavelength of 193 nm, whereas the numerical aperture NA of the projection system which projects the structures on a mask (or structured object) onto a substrate, is much more than

1.0, even more than 1.3. Such high numerical apertures only can be achieved by the use of immersion systems. The principles of such systems are already described e.g. in DD 221563 A1 or in US 2006092533 A1.

5 For an onward reduction of the size of the micro-structured devices, a further reduction of the wavelength of the projection light is necessary. Since in the very deep ultraviolet wavelength range almost all optical materials become opaque, there are no suitable materials for optical lenses for wavelength below about 157 nm. Using even shorter wavelengths for the projection light, the projection lenses can only work with reflective
10 optical elements like mirrors or like diffractive optical elements. During the last years, enormous efforts were done to develop optical microlithographic projection exposure systems, which use for the projection process wavelengths less than 50 nm. Systems working with a projection wavelength between 10 nm and 14 nm are described e.g. in EP 1533832 A1 or in US 20040179192 A1. Depending on the light sources which are available for the
15 projection light of such short wavelengths, the wavelengths for the projection light may be even 5 nm or less. At such short wavelengths of less than 50 nm or even much shorter, the projection lenses of the optical microlithographic projection systems comprise only reflective optical elements like mirrors and/or diffractive structures like reflective diffractive structures. Projection systems which are working at a wavelength of less than about 50 nm
20 are known as EUV (Extreme Ultra Violet) lithographic projection exposure systems.

A simplified EUV lithographic projection exposure system 100 is schematically shown in Fig. 1. The system comprises an EUV light source 1, producing EUV light with a significant energy density in the extreme ultraviolet or EUV spectral region, especially in the wavelength range
25 less than 50 nm, preferably in a range between 5 nm and 15 nm. Discharged-produced or laser-produced plasma light sources are used as EUV light sources, making use of e.g. xenon, tin or lithium plasma which generates the extreme ultraviolet light. Such sources irradiate unpolarized light under about 4π solid angle. Other sources generate a spatially more directed and a more polarized beam of extreme ultraviolet light like e.g. synchrotron

radiation sources. Dependent on the EUV light source 1, especially if an EUV plasma light source is used, a collector mirror 2 may be used to collect the EUV light of the light source 1 to increase the energy density or irradiance of the EUV radiation and form an illumination beam 3. The illumination beam 3 illuminates via an illumination system¹⁰ a structured object M. The structured object M is e.g. a reflective mask, comprising reflective and non-reflective or at least minor reflective regions to form at least one structure on it. Alternatively or additionally, the structured object comprises or consists of a plurality of mirrors which are arranged about side by side in at least one dimension to form a mirror arrangement like a mirror array. Advantageously the mirrors of the mirror array are adjustable around at least one axis to adjust the incidence angle of the illumination beam 3 which is irradiated on the respective mirror.

It shall be understood that the terms reflective, minor reflective and non-reflective relates to the reflectivity of EUV light of the illumination beam 3. Due to the very short wavelength of the EUV light, the reflective surfaces are usually coated if the angle of incidence for the EUV light is less than about 45°. The coatings preferably comprise a multilayer of predetermined layer materials with predetermined layer thicknesses. Such mirrors are usually used for incidence angles less or far less than 45° down to about 0°. For such mirrors a reflectivity of more than 60% can be achieved due to a constructive interference of the reflected EUV light which is partially reflected at the various material boundaries of the individual layers of the multilayer. A further advantage of such multilayer-coated reflective mirrors or surfaces is their property to work as a spectral filter, to make e.g. an illumination and/or projection beam of the EUV lithographic projection system more monochromatic. In an EUV lithographic projection exposure system coated mirrors are sometimes also designated as normal incidence mirrors.

For larger incidence angles than about 45°, especially for much larger incidence angles like angles of about 70° and even more, it is sufficient if the reflective surface comprises a metal or a metal layer like Ruthenium, or if the reflective surface consists of a metal or a metal

layer, comprising e.g. Ruthenium. At such high incidence angles, the reflectivity can be increased up to 60% and more without the necessity of a multilayer as mentioned above. As a general rule the reflectivity increases with increasing angle of incidence, which is why these mirrors are also called grazing incidence mirrors. EUV lithographic projection exposure systems often use plasma light sources. In this case, the collector mirror 2 can be a grazing incidence mirror as described e.g. in WO 2002/065482 A2 or US 2004/0130809 A1.

The structured object M reflects parts of the illumination beam 3 into a light path which forms a projection beam 4. The structured object M structures the illumination beam 3 after being reflected on it, depending on the structure on the mask M. This projection beam 4 is carrying the information of the structure of the structured object and is irradiated into a projection lens 20 such that at least two diffraction orders of the structure or the structures of the structured object M pass the projection lens 20 and form a kind of an image of the structure or the structures of the structured object M on a substrate W. The substrate W, e.g. a wafer, comprising a semiconductor material like silicon, is arranged on a substrate stage WS which is also called wafer stage.

In addition to the information about the structure of the structured object M, the projection beam also comprises information about the illumination condition of how the structured object M is illuminated regarding angular, polarization and intensity (or radiation power per unit area) in an object point OP of the structured object M, and of how these parameters are distributed over the illuminated surface of the structured object M. The kind of illumination is expressed by the term "setting". This means a predefined angular and/or polarization and/or intensity distribution with which an object point OP on the structured object M is illuminated, and how these distributions depend on the spatial position on the structured object M. The setting also influences the optical resolution of the projection process which is done by the projection lens 20. In general, the optical resolution can be increased if the setting is adapted to the shape of the structure on the structured object M. Advanced illumination techniques which use adapted settings for the illumination of a structured

object are described e.g. in "Resolution Enhancement Techniques in Optical Lithography" by Wong, Alfred Kwok-Kit; ISBN 0-8194-3995-9". The kind of illumination, the setting, can be adjusted with the illumination system 10 (see Fig. 1), which comprises a plurality of mirrors 12, 13, 14, 15, 16.

5

In Fig. 1, as an example, the projection lens 20 schematically shows four mirrors 21, 22, 23 and 24 as reflective optical elements to form a kind of an image of the structure of the structured object M on the wafer W. Such EUV projection lenses 20 typically comprise 4 to 8 mirrors. However, projection lenses with only two mirrors may also be used. These mirrors
10 are made with highest precision regarding surface figure (or regarding their geometrical form) and surface roughness. Each deviation from the desired specification results in a degradation of the image quality on the substrate or wafer W. Usually the specification is such that a deviation from the surface figure (the required or specified dimensions of the shape of the surface) of less than one tenth of the used projection wavelength is required.
15 Depending on the used wavelength the surface figures of the mirrors 21, 22, 23 and 24 must be made with a precision of even better than 1 nm, for some mirrors the precision requirements are even a factor of 5 to 20 higher, ending up at precision ranges of much smaller than one atom layer, which means better than 0.1 nm. To project structures from a mask to a substrate with the EUV lithographic projection technique in such a way that the
20 image on the substrate comprises structures down to about 10 nm of lateral dimension or even structures with smaller lateral dimensions the optical aberration of the projection lens 20 must be smaller than 1 nm, even smaller than 0.1 nm or smaller than 50 pm (picometer) of RMS value. This means that the root-mean-square (RMS) value of the deviation of the real wavefront from the ideal wavefront is smaller than the mentioned values. This very high
25 precision regarding the surface shape (surface figure or geometrical form) must be kept over a mirror dimension of more than 10 cm. Modern EUV projections lenses comprise mirrors of a diameter of 30 cm or even more with such a high requirement regarding the surface figure. This very high mechanical precision is necessary to form an image point IP on the substrate W from an illuminated object point OP on the structured object M by illuminating the object
30 point OP with a well configured illumination beam according to a predetermined setting.

Further, to project the illuminated object point OP with the projection lens 20 with at least parts of the projection beam 4 onto the substrate W, the projection beam 4 is generated by the illumination beam 3 and the diffracting properties of the structured object M. One necessary condition to form an image on the substrate W is that the diffracted wave fronts, which are coming from an object point OP, interfere in the image point IP on the substrate or wafer W. To get a good image quality the interfering wave fronts must have a relative phase shift of far less than one wavelength of the projection beam light. Due to the various illumination settings, of how the structured object M can be illuminated by the illumination beam 3, the light path of the light passing one object point OP on the structured object M can vary within the projection lens 20 in such a way that light bundles of the projection beam 4 are reflected by the mirrors 21, 22, 23, 24 of the projection lens 20 at different surface areas with different sizes. This variation depends on the illumination settings and the position of the mirrors 21, 22, 23, 24 within the projection lens 20. To make sure that the image quality is achieved under all illumination settings it is necessary that the above-mentioned surface figure is achieved with the mentioned high mechanical precision.

Apart from the high mechanical precision of the surface figure of the mirrors 21, 22, 23, 24 in the projection lens 20, also the position and orientation of these mirrors 21, 22, 23, 24 relative to each other, relative to the structured object M and relative to the substrate W must be in the same range of accuracy. This means that position and orientation of these objects (mirrors 21, 22, 23, 24, structured object M and substrate W) must be adjusted also in the nanometer range or even below. In addition, a metrology is necessary to allow the manufacturing of such precise mirror surfaces, the assembling of the projection lens of the EUV lithographic projection system, the integration of the assembled projection lens into the projection system, and to allow any in-situ monitoring and control of the system during the operation of the system.

To achieve the above mentioned mechanical precisions, one further problem is the absorption of the projection beam 4 by the mirrors 21, 22, 23, 24. This absorption which

could be in a range of up to 30% heats the mirrors. Depending on the absorbed heat each mirror may be deformed due to thermal expansion of the mirror. One method to reduce such thermal effects during the projection step, when a certain amount of the projection beam 4 is absorbed, is to use a temperature control system to keep the very high mechanical precision data as mentioned above, especially for the surface figure of the mirrors. Another or an additional method is to use as a mirror material or as a support structure for the mirror a low thermal expansion material with such a small coefficient of thermal expansion (CTE) like 5 ppb/K (or less) to reduce deformations of the mirror, if the temperature changes e.g. due to partial absorption of the projection beam 4. This method and the selection of appropriate materials with the respective small CTE and the control of the mirror temperature is described e.g. in US 7,295,284 B2.

EUV lithographic projection exposure systems like shown in Fig. 1 are usually operated under vacuum conditions. The projection lens 20 and/or the illumination system 10 are operated under reduced pressure or vacuum. Usually the pressure conditions in the illumination system and the projection lens are different. The reduced pressure or vacuum conditions significantly reduce the technical solutions for the above mentioned problems regarding the deformation of mirrors and their active or passive position control. Especially temperature control systems for controlling a temperature of components inside the EUV lithographic projection exposure system are quite often limited to certain technical solutions which are not essentially based on thermal convection principles.

Summary of the invention

The present invention is directed to an improved EUV-projection lens to further reduce the influence of any temperature variation to deformations and/or position variations of the reflective optical elements or mirrors inside such a projection lens.

A projection lens of an EUV lithographic projection exposure system in accordance to this invention comprises mirrors and a supports structure to support or suspend the mirrors. In the vicinity of a mirror the support structure is at a reference temperature. Preferably the reference temperature is the same for all support structure parts which are close to the mirrors, and the mirrors are also at this reference temperature if they are not subjected to any radiation like EUV light. Further, the projection lens comprises a heater and temperature control system to control the temperature of at least one heatable mirror. Without heating the heater the mirrors warm up from the reference temperature by an average temperature if the projection lens is exposed with the exposure power of the EUV light which is used to project an object field onto an image field. More precisely, during such an exposure a temperature distribution is formed out on the mirror which differs from the constant temperature of the reference temperature. This temperature distribution is characterized e.g. by the average temperature or by a maximum temperature. Further, in the projection lens of this invention the at least one heatable mirror comprises a body which comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a temperature T_{0k} (called zero cross temperature). The zero cross temperature is selected such that it is higher than the reference temperature. According to this invention the heatable mirror is heated and controlled to a temperature selected from a group of determined temperatures before the formation of the temperature distribution which is caused by the exposure power of the EUV light. This has the advantage that the warm up time (if the mirror is exposed with the exposure power of the EUV light) of the heatable mirror is significantly reduced. Further, the determined temperatures are selected such that the average temperature of the mirror after the warm up is close to or at the zero cross temperature. This means the in a steady state condition the at least one heatable mirror has a temperature at or close to the zero cross temperature. Preferably more than one mirror of the projection lens is heatable.

A further projection lens, called first projection lens, of this invention comprises at least two mirrors with mirror bodies wherein each body comprise a material with a temperature dependent coefficient of thermal expansion which is zero at respective zero cross

temperatures T_{0m} , T_{0n} . The absolute value of the difference between these zero cross temperatures T_{0m} , T_{0n} is more than 6K and the lens is designed to be exposed with an exposure power of more than 8W of EUV light with a wavelength in a wavelength range of less than 50 nm. The selection of materials which widely differ regarding their respective

5 zero cross temperatures advantageously offer the possibility to make projection lenses for higher exposure powers without the drawback that the thermal induced aberration of the mirrors is increasing. This offers the possibility to manufacture EUV projection lenses with minimal aberration and high exposure power.

10 In a further projection lens, called second projection lens, according to this invention the materials of the mirror bodies or substrates are selected according to a rule which is also part of this invention. At least one material is selected in such a way that its zero cross temperature is above the largest temperature value which the mirror can get under operation. With an additional heater the mirror is warmed up to the zero cross temperature

15 or close to it which results in minimal thermal aberration. The advantage of the second projection lens is that the lens is very insensitive regarding the selected exposure power, any manufacturing tolerances of the zero cross temperature, any selected illumination settings and any mask patterns.

20 In a further projection lens, called third projection lens, according to this invention for at least two mirrors one material for the mirror bodies is selected. This material has a temperature dependent coefficient of thermal expansion which is zero at least two zero cross temperatures T_{0mn}^1 and T_{0mn}^2 . The projection lens is designed such that one of the two mirrors is operated at or close to the first zero cross temperature T_{0mn}^1 and the other mirror

25 is operated at or close to the second zero cross temperature T_{0mn}^2 , if the projection lens is subjected to the EUV exposure power which is necessary for the projection process in mass production. The advantage of the third projection lens is that the lens needs fewer different substrate materials for its mirrors.

Further, the present invention relates to a method to configure a EUV projection lens. Especially the method focuses on the selection of suitable materials for the mirror bodies such that the thermal aberration of the lens can be minimized.

5 Further aspects of the invention are to provide various heating means or tempering means with which the mirrors in an EUV projection lens can be heated or cooled. These means also comprise mirror bodies with characteristic features like coatings or shapes which improve the temperature control of the respective mirror during its operation in the projection lens.

10 In general the above mentioned mirrors of the EUV projection lens shall also comprise any reflective elements like reflective diffractive structures, since the teachings of the present invention are not limited to mirrors.

Further features and advantages of the present invention and further improvements will become apparent from the following detailed description of exemplary embodiments with
15 reference to the following figures in which like reference characters designate the same or similar parts. However, the following description of the invention by exemplary embodiments is merely illustrative and in no way intended to limit the invention and its applications. As shown in this description, features of different embodiments can be exchanged and/or combined to get additional embodiments of the present invention.

20

Brief description of the Drawings

Figure 1 schematically shows a simplified EUV lithographic projection exposure system with an illumination system and an EUV projection lens which comprises four mirrors.

25 Figure 2a linear expansion coefficient (CTE) for various materials as a function of temperature. The materials have a zero cross temperature for which this

coefficient is zero. (from Critical Reviews of Optical Science and Technology, Vol. CR43, p 183, article from S. F. Jacobs "Variable invariables – dimensional instability with time and temperature"; ISBN 0-8194-0953-7; 1992)

- Figure 2b Linear expansion coefficient for various Zerodur® materials as a function of temperature with various zero cross temperatures where this coefficient is zero. (from Critical Reviews of Optical Science and Technology, Vol. CR43, p 186, article from S. F. Jacobs "Variable invariables – dimensional instability with time and temperature"; ISBN 0-8194-0953-7; 1992)
- Figure 3a schematically shows a side view of a reflective optical element like a mirror at two different temperatures.
- Figure 3b schematically shows a deformation of a mirror surface due to temperature variations along the x-axis of the mirror.
- Figure 3c schematically shows a relative change of a length $\Delta L/L_0$ of a body with a length L_0 as a function of temperature in units of ppb for Zerodur® and ULE®.
- Figure 3d show a temperature distribution on the 4th mirror of the EUV projection lens of Fig. 6 together with the mirror size.
- Figure 3e shows the temperature profile of the mirror of Fig. 3d along the x-direction through the temperature maximum. The temperature difference to the reference temperature is given.
- Figure 3f shows the temperature profile of the mirror of Fig. 3d along the y-direction through the temperature maximum. The temperature difference to the reference temperature is given.
- Figure 3g shows values of the Zernike-coefficients for the mirror M₄ of Fig. 3d to Fig. 3f in relative units.
- Figure 3h show a temperature distribution on the 6th mirror of the EUV projection lens of Fig. 6 together with the mirror size.

Figure 3i shows the temperature profile of the mirror of Fig. 3h along the x-direction through the temperature maxima. The temperature difference to the reference temperature is given.

Figure 3k shows the temperature profile of the mirror of Fig. 3h along the y-direction through the minimum temperature between the maxima in the x-direction. The temperature difference to the reference temperature is given.

Figure 3l shows values of the Zernike-coefficients for the mirror M_6 of Fig. 3h to 3k in relative units.

Figure 4 schematically shows a mirror mounting assembly with a mirror as used in a projection lens of an EUV-lithographic projection exposure system as described in e.g. in WO 2005/026801 A2.

Figure 5 schematically shows the mirror mounting assembly of Fig. 4 with a heater for heating the mirror and a temperature control system for controlling the temperature of the mirror.

Figure 6 schematically shows an EUV projection lens which comprises 6 mirrors, a heater and a temperature or aberration control system for the sixth mirror.

Figure 7 shows an example for a warming-up of the six mirrors of the projection lens shown in Fig. 6, if such a lens is exposed with an EUV projection beam which has a power of 16 W after the reticle M.

Figure 8 shows the aberration for each mirror of the projection lens of Fig. 6 expressed by the Zernike-coefficient Z5. Z5 is given by its RMS (root mean square) value as a function of the zero cross temperature when each mirror of the projection lens is in the steady state as described in Fig. 7.

Figure 9 shows the optimized zero cross temperature as a function of the EUV light power P after the reticle M to which the EUV lens of Fig. 6 is subjected during a projection process.

Figure 10 schematically shows a side view of a reflective optical element M_k like a mirror of an EUV projection lens as shown in Fig. 4 and Fig. 6. Further, a heater and a cooler are arranged nearby the mirror which is supported by supporting elements.

- 5 Figure 11 schematically shows a side view of a reflective optical element as shown in Fig. 10 but without the heater. The temperature of the reflective optical element or mirror M_k , 421 is controlled by a pressure control of the pressure within the direct surrounding area or volume of the reflective element or mirror.

10 Figure 12a shows the transmission of Zerodur® for a transmission path of 5 mm and of 25 mm.

Figure 12b schematically shows a reflective optical element or a mirror M_k , 421 which is coated with a coating C on almost its entire surface to make the mirror heatable with IR radiation.

15 Figure 12c schematically shows a reflective optical element or a mirror M_k , 421 which is at least partly coated with a coating C2 on its surface to make the mirror heatable. The coating C2 is selected such that it will have a certain electrical resistance.

Figure 12d schematically shows a reflective optical element or a mirror M_k , 421 which is at least partly heated by a multi-zone wire grid 1050 which is arranged nearby the reflective surface MS_k .

- 20 Figure 13 schematically shows several embodiments of heaters or tempering means 300 in relation with a reflective element or mirror M_k , 421.

Detailed description of the embodiments

25 To reduce deformation or position variation of the mirrors or the reflective optical elements inside a projection lens 20 (see Fig. 1 as described above) and to achieve the surface figure accuracy and position accuracy in the range of 0.1 nm or even better, any thermal expansion

must be minimized. This means that the actual surface data regarding the surface shape of a mirror and its actual position data must be within the specified range relative to a required or specified dimension of the shape of the surface of the mirror and relative to its required or specified position. With such optical elements in a projection lens image structures down to about 10 nm of lateral dimension or even structures with smaller lateral dimensions can be generated. Further, for such optical elements (mirrors) or for the projection lens the optical aberration is smaller than 1 nm, even smaller than 0.1 nm or smaller than 50 pm (picometer) of RMS value. This means that the root-mean-square (RMS) value of the deviation of the real wavefront from the ideal wavefront is smaller than the mentioned values. To minimize thermal expansion of the optical element which result in a reduction of the thermal induced optical aberration, the body MB_k of at least one mirror or reflective optical element k of the plurality of reflective optical elements M_i of the projection lens is made of a material or comprises a material with a temperature dependent coefficient of thermal expansion (CTE) which is zero at a temperature T_{0k} . This temperature T_{0k} is called zero cross temperature. Examples of such materials are shown in Fig. 2a and 2b. The application of such materials in EUV lithographic projection exposure systems is e.g. described in WO 2004/015477 A1. Depending on the operation temperature of the lithographic projection exposure system 100, or the operation temperature of the reflective optical elements of such a system, there are different materials available which have at least one zero cross temperature T_0 . Since the usual operation temperature of the reflective optical elements is in the range of about 0°C up to about 100°C, preferably in the range of about 10°C to about 60°C, better in a range of about 20°C to about 40°C, the number of available materials is very restricted.

According to Fig. 2a Superinvar (an alloy of Fe-Ni-Co) or ULE® (a registered trademark of Corning Inc.) are suitable materials, or according to Fig. 2b a material made of a Zerodur® (a registered trademark of Schott AG) type may be chosen which is made of a glass ceramic. ULE® is a Titania silicate glass, which is a vitreous mixture of SiO_2 and TiO_2 . In a first order approximation the CTE-value of ULE® and Zerodur® near by the respective zero cross temperatures can be approximated by the equation $CTE(T) = a_1 (T - T_0)$, see e.g. Fig. 2a and

Fig. 2b. For ULE® the constant or slope a_1 is positive. This means that the material shrinks with increasing temperature if the temperature T of the material (made of ULE®) is below T_0 , and the material expands if its temperature T is above T_0 . For Zerodur® the constant or slope a_1 is negative in the range of room temperature, as it is shown in Fig. 2b. This means that the material expands with increasing temperature if the temperature T is below T_0 , and the material shrinks if the temperature is above T_0 . At higher temperatures there is a second zero cross temperature T_0^2 with a positive constant or slope a_2 in the approximation $CTE(T) = a_2 (T - T_0^2)$. This means that the material behaves similar like ULE® regarding thermal shrinkage and thermal expansion. In a certain temperature range around the zero cross temperature ULE® and Zerodur® have a CTE-value in the range of ppb/K ($10^{-9}/K$) down to zero. This means that a body of e.g. about 100 mm thickness which is made of a material with a CTE-value of about 1 ppb/K expands or shrinks of about 0.1 nm if the temperature changes by one Kelvin (1K). For Superinvar the temperature range around the zero cross temperature must be much smaller to achieve an effective CTE-value of 1 ppb/K. This result in extra efforts regarding the temperature control system which is one aspect why Superinvar is less preferred than ULE® and/or Zerodur® to use it as a substrate material for reflective optical elements in EUV lithography, especially in a projection lens 20 of an EUV lithography exposure system 100.

In general, thermal or temperature variations influence the aberration or image defects of an optical imaging system. However, an overall change or homogenous change in temperature, e.g. by a temperature offset ΔT of the spatial temperature distribution which changes the temperature from $T(x,y,z)$ to $T(x,y,z) + \Delta T$ (x , y and z designate the spatial coordinates), has only a small impact to refractive lens elements, which are used in VUV lithography. This is because the refractive power changes overall in the lens element and the changes of the surface figures of the refractive lens is negligible due to the almost constant coefficient of thermal expansion (CTE) of the refractive material.

In an EUV-lithographic projection system in which reflective optical elements like mirrors are made of materials, as e.g. shown in Fig. 2a and Fig. 2b, which comprise a coefficient of thermal expansion $CTE(T)$ which strongly depends on the temperature T , even a homogeneous change in temperature as mentioned has a strong influence onto the aberration values of the optical system. This is schematically explained in more detail with Fig. 3a and Fig. 3b on the basis of the inventors' analyses.

Fig. 3a schematically shows a side view of a reflective optical element like a mirror M_k with a body MB_k and a reflective surface MS_k . The mirror M_k has a spatial temperature distribution $T(x,y,z)$. If the mirror body MB_k comprises material with a zero cross temperature then usually the temperature distribution $T(x,y,z)$ is different from the zero cross temperature. If the temperature distribution is changed by a constant value ΔT , then, if e.g. the temperature is raised closer to the zero cross temperature, the mirror will expand to the mirror M_k^* with body MB_k^* , if e.g. Zerodur® is used in a temperature regime in which the slope a_2 (in the approximation $CTE(T) = a_2 (T - T_0^2)$) is negative. However, despite the expansion in a first approximation the surface figure of the surface MS_k does not change its shape, but the surface MS_k^* of the expanded mirror M_k^* changes its position. It is shifted e.g. into the z -direction by a value Δz as shown. This change in position of the reflective surface can be easily corrected by a translational movement of the heated mirror M_k^* . In this case the image defects or the optical aberration is almost unchanged.

Fig. 3b schematically shows the situation of the mirror M_k with a temperature distribution $T(x,y,z) = T_{Ref}$ (which is called reference temperature). Further, as an example, the mirror is locally heated in a surface area from x_1 to x_2 along the x -dimension of the mirror body MB_k , as shown by the temperature profile or temperature distribution $\Delta T(x)$ which is added to the reference temperature T_{Ref} , having a maximum temperature ΔT_{max} . In this case the reference temperature T_{Ref} means that at this temperature the mirror has reference shapes, also its reflective surface MS_k has a reference surface figure. Any deviation due to thermal expansion is related to these reference shapes and the surface figure. It is further assumed

that the interval $[x1, x2]$ is small compared to the dimension of the mirror body in the x-direction. If the mirror body is heated up from the reference temperature T_{Ref} by the temperature profile $\Delta T(x)$, and if it is made of a material with a temperature dependent coefficient of thermal expansion which is zero at a temperature T_0 , like Zerodur® or ULE® as shown in Fig. 2a and Fig. 2b, and if the maximum temperature of the mirror body, given as $T_{Ref} + \Delta T_{max}$, as an example is below the zero cross temperature T_0 and above the reference temperature T_{Ref} due to the heating, then the reflective surface of the mirror between the coordinates $x1$ and $x2$ will shrink compared with the surface at the reference temperature. This is the case if e.g. ULE® is used. In Fig. 3b the change in surface figure is schematically shown by MS_k^* which can be compared with the reference surface figure MS_k at the reference temperature T_{Ref} . L1 and L2 designate the coordinates of the body at the reference temperature $T(x,y,z) = T_{Ref}$ which result in a length of the body $L_0(T_{Ref}) = (L2-L1)$ in the x-direction. To explain this deformation in more detail reference is made to Fig. 3c.

Fig. 3c schematically shows the relative change of a length of the body MB_k $\Delta L/L_0$ with a length L_0 (like the one mentioned in connection with Fig. 3b) as a function of temperature in units of ppb (parts per billion, meaning in values of 10^{-9}). As a reference temperature $T_{Ref} = 22^\circ\text{C}$ is chosen. This means that the length L_0 is the length at 22°C . The zero cross temperature T_{0k} is, as an example, set to 25°C which is 3K higher than the reference temperature. Curve 301 schematically shows the relative length changes for ULE®, and curve 302 schematically shows the situation for a Zerodur® material, selected such to also have a zero cross temperature T_0 at about 25°C and to have a negative slope $a1$ for the CTE approximation $CTE(T) = a1 * (T - T_0)$. If e.g. the mirror body MB_k is made of ULE® and the temperature of the mirror body is selected within the temperature interval T_{Ref} and $(2T_{0k} - T_{Ref})$ then the mirror body will shrink relative to the mirror body at the reference temperature. In the case that the mirror body is made of Zerodur®, see curve 302, then the mirror body will expand relative to the body at the reference temperature, as can be seen from Fig. 3c. If the mirror surface has a temperature profile similar like shown in Fig. 3b then (in a first approximation) the mirror surface regions between L1 and $x1$ are not changed due to thermal expansion. Also the region between $x2$ and L2, since there the temperature is at

the reference temperature or close to it. In the region between x_1 and x_2 the mirror body will expand or shrink because the temperature is different from the reference temperature. Whether expansion or shrinkage occurs in this region depends on the material and on the relative position of the absolute temperature profile $\Delta T(x) + T_{\text{Ref}}$ and the zero cross temperature T_{0k} to each other. The average temperature ΔT_{av} of the temperature profile is given as $\Delta T_{\text{av}} = (\int \Delta T(x) dx \Big|_{x_1}^{x_2}) / (x_2 - x_1)$ with the integration limits x_1 and x_2 . Is the absolute temperature profile $\Delta T(x) + T_{\text{Ref}}$ about equal to the zero cross temperature T_{0k} then there is no expansion or shrinkage of the interval $[x_1, x_2]$. However, within this interval there is still surface deformation (not shown in Fig. 3b) possible on a scale lower than this interval, if there are local temperature variation of the temperature profile $\Delta T(x)$. In the case $T_{\text{av}} + T_{\text{Ref}} = T_{0k}$ the surface figure deformation is minimized and on the scale of the interval $[x_1, x_2]$ it can be neglected. In this case the aberration or image defects are minimized. In the other case if the average temperature is not the zero cross temperature and if the mirror body MB_k shrinks within the interval $[x_1, x_2]$ then the surface figure of the reflective surface changes as schematically shown in Fig. 3b, designated as MS_k^* . In the case of expansion the reflective surface changes to MS_k^{**} which also results in a change of surface figure. In both cases aberration and imaging defects will increase. In Fig. 3b, as an example, the absolute average temperature is below the zero cross temperature but within the reference temperature T_{Ref} and a temperature given by $2T_0 - T_{\text{Ref}}$, resulting in a surface deformation MS_k^* for ULE® and a surface deformation MS_k^{**} for Zerodur® for the mirror body MB_k of Fig. 3a. It shall be mentioned that if the mirror is homogenously heated to about the temperature $T = (2T_0 - T_{\text{Ref}})$ then the mirror has the same dimensions and surface figures as at the reference temperature T_{Ref} which results in no additional aberration or image errors caused by the heating. In the above simplified explanation of the influence of the thermal expansion to aberrations there are various simplifications like the special temperature profile, the assumption that there is only a temperature variation in x-direction and the other dimensions remain at the reference temperature T_{Ref} , and that the mirror body is made of a material which has no variations in the zero cross temperature which means that the zero cross temperature does not vary in the x-, y- and z-direction of the mirror. For practical designs more complex simulation calculations or finite element calculations are necessary to optimize a reflective surface and other mirror parameters like the zero cross temperature or the operation temperature of the mirror which is operated under a given thermal load.

According to the present invention the operation temperature of the mirror and the zero cross temperature shall be selected such that the absolute temperature profile $\Delta T(x,y,z) + T_{\text{Ref}}$ which differs from the reference temperature $T_{\text{Ref}}(x,y,z)$ of the mirror or reflective optical element should be symmetric about the zero cross temperature T_0 . For one dimension, e.g. in x-direction, this means as $\Delta T_{\text{av}} + T_{\text{Ref}} = (\int \Delta T(x) dx \Big|_{x_1}^{x_2}) / (x_2 - x_1) + T_{\text{Ref}} = T_0$.

If the temperature profile ΔT varies in more than one dimension, e.g. if $\Delta T = \Delta T(x,y,z)$, then the integration is done in each dimension to get the average temperature, meaning $T_{\text{av}} = (\iiint \Delta T(x,y,z) dx dy dz \Big|_{x_1}^{x_2} \Big|_{y_1}^{y_2} \Big|_{z_1}^{z_2}) / (x_2 - x_1) / (y_2 - y_1) / (z_2 - z_1)$ in which y_1 , y_2 and z_1 , z_2 are the respective mirror edges in the y- and z-direction. Alternative, an average temperature for each dimension is separately calculated. In this case the optimization to the zero cross temperature can be done to an individual average temperature or to two individual average temperatures, which are related to the dimension or to the dimensions which are most relevant for the aberration.

15

Further, in accordance with the invention the optimization of the zero cross temperature may be adapted to the expected absolute average temperatures $\Delta T_{\text{av}} + T_{\text{Ref}} = T_0$ for each mirror of the EUV projection lens which has a zero cross temperature. Alternative, the expected absolute average temperatures are homogenously raised to the zero cross temperature of the mirror material by e.g. homogenously heating the mirror body in at least one dimension with a heating means. Since the last method offers more flexibility it will be discussed below, this method is preferred.

Fig. 3d to 3f show a more realistic temperature distribution of an EUV mirror as used in the projection lens 20 (Fig. 1). In Fig. 3d a mirror M_k with its dimensions is shown from the top. For the simulation of the temperature distribution of this mirror and also the respective aberration a EUV-projection lens with 6 mirrors ($k=1$ to 6) was used, as it is shown in Fig. 6. The results for mirror 24 (see Fig. 6) or M_4 are shown in Fig. 3d to 3f which is the fourth

25

mirror after the reticle, counted in the direction of the projection beam. The EUV-lens with the 6 mirrors is shown and explained below. In Fig. 3d the temperature distribution is shown with a grey shading pattern. The temperature increases from the mirror periphery from 22°C which is the reference temperature T_{Ref} , up to about $T_{\text{Ref}} + \Delta T_{\text{max}}(x) = 24^\circ\text{C}$ in the middle black spot. Fig. 3e shows the temperature difference to the reference temperature as a temperature profile $\Delta T(x)$ of the mirror along the x-direction through the temperature maximum ΔT_{max} . Fig. 3f shows the temperature difference to the reference temperature as a temperature profile $\Delta T(y)$ of the mirror along the y-direction through the maximum temperature ΔT_{max} . The inhomogeneous temperature profile of the mirror results in deformations of the mirror surface as explained above. These deformations result in aberrations which cause image errors or defects. This is shown in Fig. 3g in which the values of the Zernike-coefficients for the mirror M_4 are given. These coefficients are a quantity or measure for the deviation of an ideal spherical wavefront in the image plane which generate an image point IP (see Fig. 1).

To get the Zernike-coefficients a wavefront is expanded in a series of Zernike functions. An ideal spherical wave has just a first Zernike coefficient and all other coefficients are zero. So the values of the Zernike-coefficients higher than 2 are a measure for various imaging errors, and the larger these coefficients are the larger is the optical aberration of the optical imaging system.

In Fig. 3g for each Zernike coefficient two values are given. The left value (bar) is the value without additional heating of the mirror. The right value, given by the right bar, is the value with an additional homogenous heating of the mirror. This is now explained in more detail. The mirror M_4 in this example has a mirror body made of ULE® with a zero cross temperature of 25°C. The reference temperature is $T_{\text{Ref}} = 22^\circ\text{C}$. This means that without EUV light the temperature of the mirror is at 22°C. Preferably the aberration is minimized at this temperature. If the EUV light is switched on to project an object point OP to an image point IP then the mirror heats up and aberration occurs as shown by the respective left bars in Fig.

3g. If the mirror M_4 is additionally homogenously heated by 2°C to be at 24°C before the EUV light is switched on then the aberration after switching on the EUV light results in the right bars which are significantly lower than the left ones. This means that the aberration of the EUV lens can be significantly reduced by the homogenous heating of at least one lens mirror.

5

Fig. 3h to 3l show a further realistic temperature distribution of an EUV mirror as used in the projection lens 20 (Fig. 1). In Fig. 3h the mirror M_6 of the EUV projection lens of Fig. 6 is shown similar to Fig. 3d. For the simulation of the temperature distribution of this mirror and also the respective aberration the EUV-projection lens with the 6 mirrors was used as for Fig. 3d to 3g and as shown in Fig. 6. The results are shown in Fig. 3h to 3l for mirror 26 (see Fig. 6) or M_6 , meaning the sixth mirror after the reticle, counted in the direction of the projection beam. The temperature increases from the mirror periphery from 22°C , which is the reference temperature T_{Ref} , up to about 1.2°C in the middle of the left and right black spots. Fig. 3i shows the temperature profile along the x-direction of the mirror trough the temperature maximums where the temperature difference $\Delta T(x) = T(x) - T_{\text{Ref}}$ to the reference temperature is given. Fig. 3k shows the temperature difference to the reference temperature $\Delta T(y) = T(y) - T_{\text{Ref}}$ in the y-direction through the minimum temperature between the maxima in x-direction. The inhomogeneous temperature profile of the mirror results again in deformations of the mirror surface. The values for the Zernike-coefficients for this mirror are given in Fig. 3l. The left value (bar) again is the value without additional heating of the mirror. The right value is the value with an additional heating of the mirror. The mirror M_6 also has a mirror body made of ULE[®] with a zero cross temperature of 25°C . The reference temperature is also $T_{\text{Ref}} = 22^\circ\text{C}$. This means again that without EUV light the temperature of the mirror is at 22°C . Preferably the aberration is minimized at this temperature. If the EUV light is switched on to e.g. project an object point OP to an image point IP then the mirror heats up and aberration occurs as shown by the respective left bars in Fig. 3l. If the mirror M_6 is additionally homogenously heated up by 3.8°C from the reference temperature T_{Ref} to be at 25.8°C before the EUV light is switched on, then the aberration, after switching on the EUV light, results in the right bars which are significantly lower than the left ones. This means again that the aberration of the EUV lens can be

30

significantly reduced by the homogenous heating of at least one lens mirror of the projection lens.

With reference to Fig. 4 a more detailed description of the mirror with the mirror mounting and the meaning of the reference temperature T_{Ref} is given. The projection lens 20 as described above with reference to Fig. 1 or Fig. 6 comprises mirrors 21, 22, 23, 24 (25, 26) or in general a plurality of reflective optical elements M_i , each comprising a body MB_i and a reflective surface MS_i to project at least one object point OP of an object field on a reticle or on a structured object M onto an image point IP in an image field on a substrate or wafer W if the projection lens 20 is exposed with an exposure power of EUV light with a wavelength in a wavelength range less than 50 nm. Preferably a wavelength of about 13 nm is used. The EUV light is reflected from the reticle M after its illumination by an illumination system 10 of an EUV-lithographic projection exposure system 100. Further, the projection lens 20 comprises a support structure for passively or actively supporting the reflective optical elements M_i (e.g. mirrors 21, 22, 23, 24). The temperature of the support structure or of at least a part of the support structure is at a reference temperature T_{Ref} . This is shown in more detail in Fig. 4 which schematically shows a mirror mounting assembly 400 for the mirror 421, representing one reflective optical element M_k from the plurality of the reflective optical elements M_i which are used in an EUV-lithographic projection exposure system 100 (Fig. 1), and as described e.g. in WO 2005/026801 A2. The mirror 421 comprises a mirror body MB_k made of Zerodur® or ULE®, or made of a material comprising e.g. one of the materials Zerodur® or ULE®, or made of a material having at least one zero cross temperature. The mirror 421 also comprises a reflective surface 450 with an optional multilayer of predetermined layer materials with predetermined layer thicknesses to improve the reflectivity of the projection beam 4 (Fig. 1) of EUV light. The mirror body MB_k is supported by a support element 480. As an example, the mirror 421 is supported or suspended by three mounting or linking points 451, 452, 453. At each of these mounting points the mirror body MB_k is connected with linking elements 471, 472, 473 with a bipod structure 461, 462, 463 to achieve a kinematic mount which holds the mirror 421 such that almost no parasitic forces and/or moments are transferred from the support element 480 to

the mirror. Usually but not necessarily at least one of these bipod structures may comprise an actuation device. The support element 480 is fixed at a housing structure 481 of the projection lens 20. The housing structure is sometimes also called projection optical box or POB. In accordance with the present invention, as a support structure with a defined or controlled reference temperature T_{Ref} one of the following elements is preferably selected:
5 The linking points 451, 452, 453, the linking elements 471, 472, 473, the bipod structures 461, 462, 463, the support element 480 or the housing structure 481. The selected support structure depends among other things also on the temperature control system which is used in the EUV lithographic exposure system. For this reason in Fig. 4 all these elements are
10 designated with T_{Ref} which does not necessarily mean that all these elements have the same temperature during the operation of the projection system 100.

According to the present invention the reference temperature T_{Ref} is the temperature of the selected support element which supports the reflective optical element 421 in an operation
15 mode of the EUV lithographic exposure system in which the EUV light is switched off, or in an operation mode in which the power of the EUV light is less than about 10% of the exposure power which is usually used for the projection of the object field on a reticle onto the image field on the substrate in a mass production operation mode of the EUV lithographic exposure system. This reference temperature T_{Ref} is usually selected close to the
20 room temperature of the clean room in which the projection lens 20 is operated, meaning that the reference temperature is in the range of about 20°C to 24°C, preferably 22°C. In most EUV lithographic projection exposure systems an additional temperature control system controls the reference temperature T_{Ref} such that this temperature is constant also during the operation of the projection lens 20. Usually this is the temperature of the housing
25 structure 481 and/or the support element 480 (Fig. 4), being e.g. at 22°C as it was chosen in Figures 3. According to this invention, preferably the temperatures are selected such that the zero cross temperature T_{0k} is higher than the reference temperature. This has the advantage that the mirrors or reflective optical elements have not to be cooled to a temperature below the reference temperature T_{Ref} to operate the mirror nearby the zero
30 cross temperature. To avoid the cooling of the mirrors in an EUV projection lens is an

advantage because the lens is operated in vacuum in which a cooling of the mirrors is technically difficult or expensive.

Further, in accordance to the present invention the projection lens 20 comprises a heater 300 to heat at least one optical element M_k , and it comprises a temperature control system 200 to control the temperature of the at least one optical element M_k to a temperature T_k as shown in Fig. 5 in which like references designate the same or similar parts as in Fig. 4. On the heatable optical element M_k a spatial temperature distribution $\Delta T(x,y,z) = (T(x,y,z) - T_{Ref})$ relative to the reference temperature is formed out when the projection lens is exposed with the exposure power and if the heater 300 is not activated or heated. This distribution has an average temperature ΔT_{av} as defined above.

The at last one heated optical element M_k may be connected to a support structure in the same way as shown in Fig. 4. In addition the mirror body MB_k of the at least one heated reflective optical element M_k comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a temperature T_{Ok} (this temperature is also called zero cross temperature) which is higher than the reference temperature T_{Ref} . Due to the preferred reference temperature of $T_{Ref} = 22^\circ\text{C}$ the preferred zero cross temperature T_{Ok} is between 22°C and about 70°C . As already mentioned such materials are e.g. Zerodur® or ULE®. The relation of the temperature T_k of the at least one temperature controlled or heatable optical element M_k to the zero cross temperature T_{Ok} and to the reference temperature T_{Ref} is such that T_k is selected from the group consisting of $T_k = T_{Ok} - \Delta T_{av}$; $T_k = 2 * T_{Ok} - T_{Ref} - \Delta T_{av}$; $T_k = T_{Ref} + 3 * (T_{Ok} - T_{Ref}) / 2 - \Delta T_{av}$; $T_k = T_{Ok} - \Delta T_{max}$; $T_k = 2 * T_{Ok} - T_{Ref} - \Delta T_{max}$; $T_k = T_{Ref} + 3 * (T_{Ok} - T_{Ref}) / 2 - \Delta T_{max}$. This temperature T_k preferably is achieved before the formation of the temperature distribution $\Delta T(x,y,z)$ on the optical element M_k , whereas the temperature distribution results from the heating when the optical element is subjected to the EUV light during the operation mode of the projection system. This has the advantage that the reflective element M_k is such close to the zero cross temperature that the EUV light of the projection beam which is absorbed by the mirror or reflective element M_k will heat it up to about the zero cross temperature. The advantage of the invention is that the zero cross temperature can be selected quite free, since the application of the heater 300 allows

that the mirror can be operated at the favorable zero cross temperature during the projection process. As an alternative, if ΔT_{av} is small like about 1K than T_k can also be the zero cross temperature T_0 .

- 5 This means that the temperature T_k is controlled by the temperature control system 200 to such a temperature with the heater 300 (see Fig. 5). Preferably the heater heats the mirror M_k homogenously to such a constant temperature value. The temperature T_k is the operation temperature of the mirror M_k in an operation mode of the EUV lithographic exposure system in which the power of the EUV light off. Switching the power of the EUV
- 10 light to an exposure power which is usually used for the projection of the object field on a reticle onto an the image field on the substrate in an mass production operation mode of the lithographic exposure system then the temperature of the reflective optical element or mirror M_k is increasing by the average temperature ΔT_{av} to or close to the zero cross temperature T_0 . As mentioned, preferably the temperature T_k is already controlled to its
- 15 value before the EUV light is switched on. In a preferred embodiment the heater is controlled such that the thermal energy to which the mirror M_k is subjected is constant. This means that if e.g. the mirror absorbs some other energy, e.g. some EUV light, then the heater reduces its heating power such that the total input of thermal energy onto the mirror is constant in time. This results in that the average temperature of the mirror is also constant
- 20 or almost constant in time. A more detailed description of the various preferred values of T_k will be given below.

The temperature T_k may be controlled at the reflective surface MS_k or at the mirror body MB_k . The above given relations between the temperatures T_{0k} (the zero cross temperature),

25 the operation temperature T_k of mirror M_k (or in general the reflective optical element) and the reference temperature T_{ref} of the support structure as well as the average temperature ΔT_{av} result in very small length variations or surface figure variations of the reflective optical element M_k for most practical cases, and the aberration or image errors are significantly

reduced, as shown in Fig. 3g and 3l, in which the temperature T_k is controlled to about $T_k = T_{0k} - \Delta T_{av}$ and $T_k = T_{Ref} + 3*(T_{0k} - T_{Ref})/2 - \Delta T_{av}$.

The equation $T_k = T_{Ref} + 3*(T_{0k} - T_{Ref})/2 - \Delta T_{av}$ is also considering that there is also a
 5 temperature distribution in the thickness- or z-direction of the mirror and not only on the surface of the mirror. If it is assumed that on the side of the reflective surface there is the temperature T_k , e.g. at the periphery of the mirror, and if at the backside of the mirror there is the reference temperature T_{Ref} due to any thermal conduction e.g. of the support structure which is at this temperature, then a good temperature for T_k is given by $T_k = 2*T_{0k} - T_{Ref} - \Delta T_{av}$. However, the accuracy of the temperature control system or the accuracy with
 10 which the temperature T_k is controllable will also influence the aberration or imaging errors. If the accuracy of the temperature of the body MB_k of the reflective optical element M_k is within $\pm 1K$ due to the temperature control and other system variations then the relative change of the length is normally less than about 10 ppb as it can be schematically seen by reference numeral 303 in Fig. 3c. However, this assumes that the operation temperature can be chosen between about $T_{Ref} + (T_{0k} - T_{Ref})/2$ and $T_{Ref} + 3*(T_{0k} - T_{Ref})/2$. As it can be seen from Fig. 3c, if the operation temperature is too close to the reference temperature T_{Ref} , or in general too far from the zero cross temperature T_{0k} , then the relative change of the length is much more than 10 ppb as shown by the reference numerals 304 and 305. In such cases
 15 there is significant risk of mirror deformation due to deformation of the body MB_k , resulting in a deterioration of the optical performance of the system. For these reason the operation temperatures $T_k = T_{0k} - \Delta T_{av}$ and $T_k = T_{Ref} + 3*(T_{0k} - T_{Ref})/2 - \Delta T_{av}$ are preferred, especially if they are within the interval $[T_{Ref} + T_0)/2 ; T_{Ref} + 3*(T_{0k} - T_{Ref})/2]$.

25 Further it is advantageous to select a material such that the zero cross temperature of the material for the mirror body MB_k is higher than according to any design calculations or simulations which are used for the design of the projection lens. In these calculations any fluctuations of the surrounding temperature, variations in design assumptions for the lens design, the EUV light source and also the variations of reticle reflections may be considered

which results in the calculation of the maximum or average temperature of the mirror M_k when the EUV projection lens is designed. If the zero cross temperature is selected several Kelvin higher than the calculated values then the EUV lens can be operated under all conditions at the preferred temperature close to the zero cross temperature at which the aberration is minimized. This operation temperature of the mirror may be achieved by a homogenous and controlled heating with the heater 300 and the controller 200. For the heater 300 various embodiments can be used. Examples are heating elements formed out as metal plates and arranged close to the mirror, preferably close to the backside of the mirror. Such plates are electrically heated. Alternative or in addition electrical heating elements are in direct contact with the mirror body. A further alternative or additional heater comprises an infrared source with which the mirror or reflective element is illuminated.

Further, the temperature control system 200 may comprise a sensor which directly measures the mirror temperature T_k at one or several positions. In further embodiments of the invention the temperature T_k of the at least one optical element M_k which is controlled by the temperature control system can be a temperature T_{MSk} of the reflective surface MS_k (Fig. 5) of the optical element M_k or a temperature T_{MBk} of the body MB_k of the optical element M_k . Alternative T_k can be a temperature given by a function of the temperature T_{MBk} of the body MB_k and/or the temperature of the reflective surface MS_k . Further, the temperature of the reflective surface T_{MSk} can be an average surface temperature. Such averaging can e.g. be done by measuring the surface temperature with an infrared camera or by a space-resolving pyrometer. Also the temperature of the body T_{MBk} can be an average temperature of a plurality of temperatures measured at a plurality of spatial positions at the body MB_k . Preferably the spatial positions or a subset of the spatial positions at which the temperature of the mirror body is measured is arranged close to the reflective surface. By the controller 200 a temperature value or control parameter can be calculated from the measurements of the temperature or the temperatures of the reflective surface and/or the body. As a further alternative, as mentioned above, the temperature T_k for the control system is selected from a spatial temperature distribution of the body MB_k or the reflective

surface T_{MSk} . Depending on whether the temperature of the optical element M_k is measured at one or several locations and whether the temperature control system comprises one or more input channels for the temperature signals, one of the mentioned temperature control option is selected. As an alternative or in addition, the optical aberration can be determined and the temperature controller 200 controls the mirror temperature such that the aberration becomes a minimum. For the temperature control or the control of the aberration the temperature T_k not necessarily explicitly has to be determined. Also a model based controller can be used to control the temperature of the mirror or the heat of the heater which is transferred to the mirror. The model may consider parameters like the power of EUV light to which the lens is exposed, illumination settings with which a reticle is illuminated, the structures on the reticle and the optical aberration of the lens.

In a further embodiment the EUV light of the illuminated reticle comprises a spatial distribution of angular, polarization and intensity in accordance with an illumination setting. This usually results in a spatial temperature distribution $\Delta T(x,y,z) = (T(x,y,z) - T_{Ref})$ relative to the reference temperature T_{Ref} . This temperature distribution usually has an average temperature ΔT_{kav} and a maximum temperature $\Delta T_{kmax} = (T_{Ref} + \Delta T_{kmax})$. It should be mentioned that this temperature distribution is formed out on the reflective surface MS_k of the heatable optical element M_k when the projection lens is exposed with the exposure power without heating the heater.

As an alternative to the above described selections of the temperature T_k , the temperature T_k is selected as $T_k = (T_{0k} + T_{Ref} + \Delta T_{kmax})/2$ after the determination of the temperature distribution. Depending on ΔT_{kmax} this selection has the advantage that the heated optical element is heated closer to the zero cross temperature in cases if the zero cross temperature is higher than the maximum temperature $T_{kmax} = T_{Ref} + \Delta T_{kmax}$. As mentioned above T_k may be the temperature T_{MBk} of the body MB_k of the optical element M_k , the temperature given by a function of the temperature T_{MBk} of the body MB_k and the temperature T_{MSk} of the reflective surface MS_k or the temperature selected from a spatial temperature distribution of the body MB_k or the reflective surface T_{MSk} , before the power of the EUV light of the projection beam 4 is switched on.

In a further embodiment of the projection lens in accordance with this invention the temperature T_k of the optical element M_k is controlled to its value by heating the heater with a first heating power at a time before the projection lens is subjected to the exposure power of the EUV light. This has the advantage that the operation temperature of the optical element T_k before the exposure with EUV light is very close to the operation temperature during the exposure. This results in that the changes of aberration errors as a function of exposure time can be significantly reduced and the projection system is much quicker in a steady state working condition in which the imaging quality will almost not change. Preferably during exposure (during the time subjecting the projection lens to the exposure power of the EUV light) the heating power of the heater is less than the first heating power. This is to prevent a warming up of the optical element M_k .

In a further embodiment of the projection lens according to this invention a second heater for the heating of a second optical element M_{2k} to a temperature T_{2k} is used, wherein the body MB_{2k} of the second optical element M_{2k} also comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a temperature T_{02k} higher than the reference temperature. On the second optical element a second spatial temperature distribution $\Delta T_2(x,y,z) = (T_2(x,y,z) - T_{Ref})$ relative to the reference temperature T_{Ref} is formed out when the projection lens is exposed with the exposure power without heating the second heater, having an average temperature ΔT_{2av} and a maximum temperature ΔT_{2max} . Analogous to the embodiment described above, also in connection with Fig. 3c, the temperature T_{2k} of the second optical element M_{2k} is selected according to the same relations as described above for the operation temperature T_k of the first heated mirror M_k . This means that the operation temperature T_{2k} of the second optical element M_{2k} is preferably selected from the group consisting of: $T_{2k} = T_{02k} - \Delta T_{2av}$; $T_{2k} = 2 * T_{02k} - T_{Ref} - \Delta T_{2av}$; $T_{2k} = T_{Ref} + 3 * (T_{02k} - T_{Ref}) / 2 - \Delta T_{2av}$; $T_{2k} = T_{02k} - \Delta T_{2max}$; $T_{2k} = 2 * T_{02k} - T_{Ref} - \Delta T_{2max}$; $T_{2k} = T_{Ref} + 3 * (T_{02k} - T_{Ref}) / 2 - \Delta T_{2max}$. Then the optical element or mirror M_{2k} is, or preferably is heated to such a temperature T_{2k} before the power of the EUV light of the projection beam 4 is switched on. In this embodiment the material of the body MB_{2k} may be the same or

different from the material of the body MB_k of the first optical element. In the first case of the same material, preferably the material has a different zero cross temperature than for the first reflective element M_k may be selected such that the CTE(T)-function (see e.g. Fig. 2b) has different algebraic signs for the slopes at the respective zero cross temperatures.

5 This requires that the material comprises at least two zero cross temperatures T_0 and T_{02} , as shown in Fig. 2b for a Zerodur® material. An example for different materials is the usage of ULE® for one optical element and Zerodur® for the other. Also in this case preferably the algebraic signs for the slopes at the respective zero cross temperatures are different. This advantageously can be used as a further measure to reduce aberration, as is described e.g.
10 in WO 2005/040924 A1.

Fig. 6 shows an additional schematic arrangement of an EUV-projection lens which comprise 6 mirrors as reflective optical elements M_1 to M_6 which are respectively designated with reference numerals 21, 22, 23, 24, 25 and 26. In Fig. 6 like references designate the same or
15 similar parts as in Fig. 1. Further, the mirrors are numbered as they are arranged in the downstream direction of the projection beam 4 which goes from the reticle M to the wafer W. If such a EUV projection lens 20 as shown e.g. in Fig. 1 or Fig. 6 is exposed with EUV light to project an object point OP to an image point IP on the wafer W then the individual mirrors are warmed up. Preferably, before the EUV light is switched on, these mirrors are at the
20 reference temperature T_{Ref} of e.g. 22°C. Fig. 7 shows an example for a warming of the six mirror of the projection lens 20 of Fig. 6, if such a lens is exposed with a projection beam 4 which has a power of 16 W after the reticle M. For the generation of this power a light source power of more than 1kW is necessary for the light source 1 (see Fig. 1). The shown diagram is a simulation calculation in which the reticle is illuminated with a dipole
25 illumination setting which gives a temperature distribution on the last mirror M_6 similar as shown in Fig. 3h. The dipole can be seen on the mirror, since this mirror is arranged nearby or at a pupil plane of the projection lens 20.

In Fig. 7 for each of the 6 mirrors the average temperature ΔT_{av} , which is the respective lower curve, is shown as a function of time. The average temperatures are calculated as defined above. Also for each mirror the maximum temperature ΔT_{max} of the temperature distribution $\Delta T(x,y,z)$ is shown as a function of time which is represented by the respective upper curve for each mirror. It can be seen that the thermal load for the mirrors M_5 , M_3 and M_2 is such that these mirrors warm up of about 4.5K, 4.0K and 3.5K respectively. M_1 warms up of about 2K and M_4 , M_6 warm up of about 0.5K. Further, it can be seen that the mirrors need about 150 minutes or more to reach an almost constant steady state temperature. During this time the effective position of the reflective surfaces and the surface figures of these surfaces will change, as explained with Fig. 3a to 3c. This results in optical aberration as described above, since the average temperatures are changing in time relative to the respective zero cross temperatures. However, the lens 20 may be optimized for the steady state condition. This means that the zero cross temperature for the mirrors is selected such that it is the steady state temperature or almost the steady state temperature, meaning $T_{0i} = (T_{av\ i} + T_{Ref})$ for the i-th mirror ($i = 1$ to 6). In this case the aberration is minimized as described in connection with Fig. 3a to 3c. If the mirror is fabricated regarding its surface figure at a temperature of about 22°C (or in general at or close to a reference temperature) then this surface figure remains almost the same even if the mirror is homogenously heated to the such selected zero cross temperature as it was explained in connection with Fig. 3a. Further, if the mirror has a spatial temperature distribution $T(x,y,z)$ due to the absorbed power of the projection beam 4 then the aberration generated by this absorption is also minimized as explained in Fig. 3b and 3c. Practically the suggested optimization (by material selection) of the zero cross temperatures has the following **drawbacks**:

1. The steady state temperature depends on the power of the light source, on the illuminated reticle and the used illumination setting with which the reticle is illuminated.
2. The manufacturing of the mirror material with a specified zero cross temperature is very expensive. In addition, there are manufacturing tolerances such that the specified zero cross temperature only can be achieved by selecting out the required material from a larger set of materials, having the manufacturing tolerances. This would be extremely expensive. In US 2003/0125184 A1 the difficulties of the production of Zerodur® with certain predefined zero

cross temperatures are described. Further, also the difficulties concerning the determination of the zero cross temperature is shown.

3. There will be unacceptable aberration during the warm up phase within the about first 2 to 3 hours in which the EUV-lens could not be used for mass production of micro-structured objects.

The influence of the above drawbacks on aberration can be seen in Fig. 8. Fig. 8 shows the aberration in form of the Zernike-coefficient Z5. For Z5 its RMS (root mean square) value is given for each of the 6 mirrors of the lens which is shown in Fig. 6. Z5 is shown as a function of the zero cross temperature if each mirror of the projection lens is in the steady state as described in Fig. 7. The bars for each mirror show how the aberration increases if the zero cross temperature is selected higher or lower. The calculations were done in 1K steps for zero cross temperatures from 18°C (left most bar) to 34°C (right most bar). For M_2 , which has a steady state temperature of about 25.5°C ($T_{av,2} = 3.5K$ with $T_{Ref} = 22^\circ C$), the aberration values for various zero cross temperatures are shown e.g. by the shown arrows with the respective zero cross temperature data. The best zero cross temperature in accordance to Fig. 8 should be between 26°C and 27°C which is in good agreement that lowest aberration should be achieved if the steady state temperature (25.5°C) corresponds to the zero cross temperature. Fig. 8 clearly shows that if the steady state temperature of a mirror does not match with the zero cross temperature within about $\pm 1K$ then the aberration will increase. Since the steady state temperature $T_{Ref} + \Delta T_{av}$ depends on the power of the EUV light source, on the used illumination setting, the used reticle and some other aspects, it seems impossible to construct an EUV-lens such that under all the mentioned working conditions the aberration can be brought to a minimum, since if the mirror materials are selected then the zero cross temperatures are fixed.

Also in Fig. 8 the influence of the manufacturing tolerances regarding the zero cross temperatures T_{0k} can be seen. If e.g. for mirror M_2 a zero cross temperature of 27°C would minimize aberration, and if the produced material has a zero cross temperature $T_{02} = 29^\circ C$ this will almost double the aberration. For mirror M_1 a deviation of 2K from the best zero

cross temperature will result in even higher aberrations, as shown with the arrows 81 and 82.

Fig. 9 shows the optimized zero cross temperature as a function of the EUV light power P after the reticle M to which the EUV lens 20 is subjected during projection. The calculation is done for settings which produce the largest aberrations. It can be seen that the optimized zero cross temperature T_{0i} for all mirrors increase in good approximation linearly with power P . The calculation was done up to 16W and ULE® was chosen as mirror material for all 6 mirrors as for the calculations of Fig. 7 and Fig. 8. Further, it can be seen that the variation of the zero cross temperatures within one EUV lens also increases with power, if the manufactured lens 20 shall be optimized regarding optical aberration. This means that different materials have to be used for the production of the mirrors, having different zero cross temperatures with a broad variation. This makes the manufacturing also very expensive. Further, the inventors realize for the first time that for higher exposure powers the zero cross temperatures within a projection lens must differ more than 6K, even more than 8K, if the EUV lens is optimized to the EUV light power and aberration. For this reason preferably in a further embodiment of the above described embodiments of the inventive projection lens the absolute value of the difference between the zero cross temperatures T_{0k} , T_{02k} of the heatable optical element and the second heatable optical element is selected such that it is more than 6K, expresses as $\text{abs}(T_{0k} - T_{02k}) > 6K$. With such a projection lens advantageously the optical aberration (caused by thermal effects due to absorption of EUV light at the optical elements) can be reduced even at higher EUV light powers. In a further embodiment of the above described inventive projection lenses the zero cross temperature T_{0k} of the at least one heatable optical element M_k is higher than the maximum of the highest reference temperature T_{Ref} and the average or maximum temperature $\Delta T_{\text{av}} + T_{\text{Ref}}$ or $\Delta T_{\text{max}} + T_{\text{Ref}}$, based on the respective spatial temperature distribution $\Delta T(x,y,z)$, expressed as $T_{0k} > \max(T_{\text{Ref}}, \Delta T_{\text{av}} + T_{\text{Ref}})$ or $T_{0k} > \max(T_{\text{Ref}}, \Delta T_{\text{max}} + T_{\text{Ref}})$. This has the advantage that with the heater 300 the at least one heatable optical element can be heated up to the zero cross temperature independently of the EUV light power (and the reference temperature) used during the projection process. Such the optical aberration can be minimized for all operation

conditions of the projection lens 20. The teaching of the inventive embodiments described above is independent of the number of mirrors. It can be applied e.g. to a projection lens 20 as shown in Fig. 1, having 4 mirrors 21, 22, 23 and 24, or to a projection lens 20 as shown in Fig. 6, comprising 6 mirrors 21, 22, 23, 24, 25 and 26.

5

Further, to minimize the optical aberration especially in projection lenses 20 in which at least one mirror or optical element M_k is heated by a heater 300, it is advantageous to connect the at least one heated optical element M_k to an actuator for its translational movement. This allows to shift the mirror M_k to compensate a homogeneous heating of the mirror M_k as it was described in connection with Fig. 3a. Further, the heater 300 for heating the mirror or optical element M_k advantageously comprises heating elements selected from the group consisting of IR light emitting diodes, Peltier elements, optical fibers, light guide rods and IR lasers, as will be described in more detail below with the description of Fig. 13. Further, such heating elements are optionally arranged in one dimension or in two dimensions at predefined spatial coordinates, forming a grid structure. Advantageously in the embodiments in which the heating elements are emitting or guiding IR radiation, these embodiments comprise an optical arrangement to configure the IR radiation, the optical arrangement comprises arrangement elements selected from the group consisting of collimator, focusing lens, adjustable lens, mirror and diffractive optical element, wherein the arrangement elements may be tiltable around at least on axis. Examples of such optical arrangements are shown in Fig. 13.

Further, in an alternative embodiment of the above described projection lenses the at least one optical element M_k comprises a modification in or on the mirror body MB_k . The modification is selected from the group consisting of recess, blind hole, defined surface roughness, diffractive structure, spherical protrusion, spherical recess and surface curvature. The modification, which is described in more detail below in connection with Fig. 13, advantageously is used to guide e.g. IR radiation to heat the optical element locally.

25

Due to the above finding that for higher exposure powers the zero cross temperatures of the mirrors within a projection lens must differ by 6K or more, the present invention also relates to a further, projection lens, in the following called **first projection lens**, which is designed to be exposed with an exposure power of more than 8W of EUV light with a wavelength in a wavelength range of less than 50 nm, preferably with a wavelength of 13 nm. The calculations for Fig. 7, Fig. 8 and Fig. 9 were done with 13 nm and for a lens 20 with 6 mirrors, as shown in Fig. 6. Generally such a lens comprises at least two reflective optical elements M_i like mirrors. Each mirror or reflective optical element comprises a body MB_i and a reflective surface MS_i to project an object field on a reticle onto an image field on a substrate if the projection lens is exposed with the exposure power of the EUV light. This light is reflected from the reticle after the reticle is illuminated by an illumination system of an EUV-lithographic projection exposure system. Further, the bodies MB_m , MB_n of at least two reflective optical elements comprise a material with a temperature dependent coefficient of thermal expansion which is zero at respective zero cross temperatures T_{0m} , T_{0n} , wherein the absolute value of the difference between the zero cross temperatures T_{0m} , T_{0n} in this first projection lens is more than 6K, expresses as $\text{abs}(T_{0m} - T_{0n}) > 6K$. This is e.g. the case for mirror M_5 and mirrors M_4 or M_6 if the lens is subjected an exposure power of 8W or more, as can be seen from Fig. 8.

As a further second embodiment of such a first projection lens the lens can comprise four or six reflective optical elements M_i or mirrors (as e.g. shown in Fig. 1 and in Fig. 6) and preferably the projection lens is designed to be exposed with an exposure power of more than 10W. In this case the absolute value of the difference between the zero cross temperatures T_{0m} , T_{0n} is more than 8K, expresses as $\text{abs}(T_{0m} - T_{0n}) > 8K$. For the 6-mirror lens 20 of Fig. 6, Fig. 9 clearly shows this for the mirrors M_5 and M_4 or M_6 . The zero cross temperatures of these mirrors differ by more than 8 K if the exposure power goes above 10 W.

The first projection lens and its previous embodiments in a third embodiment may comprise a support structure for passively or actively supporting the reflective optical elements M_i , as it was described in connection with Fig. 4 and Fig. 5. The temperature of at least a part of the support structure is at a reference temperature T_{Ref} , which is e.g. selected as 22°C. Further,

the lens in accordance with an embodiment of the first lens comprises a heater 300 for heating at least one of the mirror bodies MB_n , MB_m which comprise the materials with the different zero cross temperatures. A temperature control system 200 controls the temperature of the at least one heated mirror body MB_n , MB_m to a temperature T_k .

5 Preferably the heater 300 is made such that the body can be homogenously heated. This means that the body MB_n , MB_m is homogenously heated in at least one dimension of the body. Various types of heaters 300 will be described below in this description.

In an further fourth embodiment of the first lens (and its previous embodiments), there,

10 without the operation of the just mentioned heater 300, the exposure of the reflective surfaces MS_m and MS_n of the bodies MB_n , MB_m with EUV light, results in temperature distributions $\Delta T_n(x,y,z) = (T_n(x,y,z) - T_{Ref})$, $\Delta T_m(x,y,z) = (T_m(x,y,z) - T_{Ref})$ of the bodies MB_n , MB_m relative to the reference temperature T_{Ref} with respective average and maximum temperatures ΔT_{nav} , ΔT_{mav} and ΔT_{nmax} and ΔT_{mmax} . The EUV light with which the reflective

15 surfaces MS_m and MS_n are exposed is reflected by the illuminated reticle and comprises a spatial distribution of angular, polarization and intensity parameters in accordance with an illumination setting. In this embodiment at least one zero cross temperatures T_{Om} , T_{On} is selected higher than the maximum of the highest reference temperature T_{Ref} and the respective average or maximum temperature $\Delta T_{mav} + T_{ref}$ or $\Delta T_{mmax} + T_{ref}$, $\Delta T_{nav} + T_{ref}$ or

20 $\Delta T_{nmax} + T_{ref}$, based on the respective spatial temperature distribution $\Delta T_m(x,y,z)$, $\Delta T_n(x,y,z)$, expressed as $T_{Om} > \max(T_{Ref}, \Delta T_{mav} + T_{ref})$, $T_{Om} > \max(T_{Ref}, \Delta T_{mmax} + T_{ref})$ or $T_{On} > \max(T_{Ref}, \Delta T_{nav} + T_{ref})$, $T_{On} > \max(T_{Ref}, \Delta T_{nmax} + T_{ref})$.

Usually the reference temperature is constant and is chosen as the temperature of the

25 support element 480 or the housing structure 481 (see Fig. 4 and 5). Often the backside of the mirror also has this temperature even if the lens is subjected to the exposure power of the EUV light. The advantage of this selection of the zero cross temperature is that with the usage of the heater 300 the respective mirror always can be brought to the zero cross temperature by heating. This is because usually, without the application of the heater 300,

30 the mirror only heats to an average temperature as explained with Fig. 7. If the zero cross

temperature is adapted to this temperature then the optical aberration becomes minimal, as it was described in connection with Fig. 3a and Fig. 3b. However, if the zero cross temperature is selected higher than the absolute average temperature $T_{\text{Ref}} + \Delta T_{\text{mav}}$ or $T_{\text{Ref}} + \Delta T_{\text{nav}}$ then by heating the mirror with the additional heater 300 it can be heated to or close to the selected zero cross temperature to minimize aberration.

In a further 5th embodiment of the first projection lens (and its previous embodiments) also the manufacturing tolerances of the zero cross temperature is taken into account. This means that if the materials of the first projection lens according to this invention, which comprises materials with the zero cross temperatures T_{0m} , T_{0n} , vary regarding their real values of the zero cross temperature due to the manufacturing process, resulting in manufacturing tolerances ΔT_{0m} , ΔT_{0n} , then the respective real values are within the temperature intervals $T_{0m} \pm \Delta T_{0m}$ and $T_{0n} \pm \Delta T_{0n}$. In this case advantageously at least one zero cross temperatures T_{0m} , T_{0n} is selected higher than the maximum of the highest reference temperature T_{Ref} and the respective absolute average or maximum temperature $\Delta T_{\text{mav}} + T_{\text{Ref}}$ or $\Delta T_{\text{mmax}} + T_{\text{Ref}}$, $\Delta T_{\text{nav}} + T_{\text{Ref}}$ or $\Delta T_{\text{nmax}} + T_{\text{Ref}}$, based on the respective spatial temperature distribution $\Delta T_m(x,y,z)$, $\Delta T_n(x,y,z)$, but in addition, these values are increased by the absolute value of the respective manufacturing tolerances ΔT_{0m} , ΔT_{0n} , expressed as $T_{0m} > \max(T_{\text{Ref}}, \Delta T_{\text{mav}} + T_{\text{Ref}}) + |\Delta T_{0m}|$, $T_{0m} > \max(T_{\text{Ref}}, \Delta T_{\text{mmax}} + T_{\text{Ref}}) + |\Delta T_{0m}|$ or $T_{0n} > \max(T_{\text{Ref}}, \Delta T_{\text{nav}} + T_{\text{Ref}}) + |\Delta T_{0n}|$, $T_{0n} > \max(T_{\text{Ref}}, \Delta T_{\text{nmax}} + T_{\text{Ref}}) + |\Delta T_{0n}|$. Such a material selection regarding the zero cross material has the big advantage that the specification regarding the zero cross temperature can be relaxed, because the heater 300 guaranties that the respective heatable reflective optical element with the selected zero cross temperature can be heated to or close to the zero cross temperature by additional heating and such the aberration can be minimized. Preferably but not necessarily, the heating is done such that the mirror is homogenously heated. This simplification regarding the material selection results in enormous cost savings. If the maximum temperatures ΔT_{nmax} and ΔT_{mmax} instead of the average temperatures ΔT_{nav} , ΔT_{mav} are chosen for the election of the zero cross temperature, then in the selection process the system is more robust, e.g. regarding changes in exposure powers to higher values.

In a further 6th preferred embodiment of the first lens (and its previous embodiments) the temperature of the heated mirror bodies or the heated mirror body MB_n , MB_m is controlled to values of the temperature T_k which are within an interval of $\pm 5K$, better $\pm 2K$ centered around the respective zero cross temperature T_{0m} , T_{0n} to minimize any thermal induced optical aberration.

The above mentioned item 3 of the drawbacks that the system cannot be used in the warm-up phase if the zero cross temperatures are optimized to the steady state, as e.g. shown in Fig. 7, can be solved by the 3rd to 6th embodiments of the first EUV lens of this invention, due to the usage of the heater 300. To also solve this drawback, in a 7th embodiment of the first lens in accordance to one of its 3rd to 6th embodiments the projection lens 20 is heated at a time before the projection lens is exposed with the exposure power of the EUV light. There the temperature T_k of the at least one heated body MB_n , MB_m of the reflective optical elements M_n , M_m is controlled to its value by heating the heater 300 with a first heating power. Preferably the temperature T_k is selected from the values of the above 3rd to 6th embodiment of the first projection lens. Depending on the values of the zero cross temperatures and the power of the exposure light to which the EUV lens is subjected, in a 8th embodiment of the first lens the heating power of the heater is selected lower than the first heating power, as mentioned in the 7th embodiment, during the time of exposure of the projection lens 20 with the exposure power of the EUV light. In a preferred 9th embodiment of the first lens the temperature control system 200 controls the temperature T_k such that the heating power of the heater 300, which heats the at least one body MB_n , MB_m of the reflective optical elements M_n , M_m , and the exposure power of the EUV light which is absorbed by the at least one heated body MB_n , MB_m is constant or is almost constant in time. Advantageously this will result in minimal temperature fluctuations of the mirror body and such the thermal induced optical aberration is minimized too.

The first lens and its various embodiments essentially make use of materials for the reflective optical elements or mirrors which differ significantly regarding their zero-cross temperature. It shall be mentioned that the present invention of the first lens and its various embodiments are not limited to EUV projection lenses with 4 or 6 reflective optical elements in form of mirrors, as described in Fig. 4 and Fig. 6. It is assumed that the number of mirrors of an EUV projection lens of a lithographic projection exposure apparatus increases to more than 6 if the EUV power of the EUV exposure light also increases. The EUV light power will depend on the EUV light sources which will be available in future. Generally the number of mirrors may vary in accordance to the requirements, and the principles of the teaching in connection with the first projection lens may be applied to each mirror or to each reflective optical element, especially if used in an EUV lithographic projection exposure apparatus.

Further, to minimize the optical aberration especially in projection lenses according to the first lens of this invention in which at least one mirror or optical element M_k is heated by a heater 300, it is advantageous to connect the at least one heated optical element M_k to an actuator for its translational movement. This allows to shift the mirror M_k to compensate a homogeneous heating of the mirror M_k as it was described in connection with Fig. 3a. Further, the heater 300 for heating the mirror or optical element M_k advantageously comprises heating elements selected from the group consisting of IR light emitting diodes, Peltier elements, optical fibers, light guide rods and IR lasers, as will be described in more detail below with the description of Fig. 13. Further, such heating elements are optionally arranged in one dimension or in two dimensions at predefined spatial coordinates, forming a grid structure. Advantageously in the embodiments in which the heating elements are emitting or guiding IR radiation, these embodiments comprise an optical arrangement to configure the IR radiation, the optical arrangement comprises arrangement elements selected from the group consisting of collimator, focusing lens, adjustable lens, mirror and diffractive optical element, wherein the arrangement elements may be tiltable around at least on axis. Examples of such optical arrangements are shown in Fig. 13.

Further, in an alternative embodiment of the above described first projection lenses the at least one optical element M_k comprises a modification in or on the mirror body MB_k . The

modification is selected from the group consisting of recess, blind hole, defined surface roughness, diffractive structure, spherical protrusion, spherical recess and surface curvature. The modification, which is described in more detail below in connection with Fig. 13, advantageously is used to guide e.g. IR radiation to heat the optical element locally.

5

An alternative embodiment to the first lens is a **second projection lens** for an EUV lithographic exposure system which is described below. The inventors' realized that the usage of a heater 300 will have a significant influence to the lens design, especially to the material selection requirements for the mirror material.

10

A first embodiment of the second projection lens 20 in accordance with this invention comprises at least two reflective optical elements M_i like mirrors as shown in Fig. 1 and Fig. 6, designated as 21, 22, 23, 24, 25 and 26. Each such element comprises a body MB_i and a reflective surface MS_i for projecting an object field OP on a reticle onto an image field IP on a substrate if the projection lens 20 is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. Preferably a wavelength of 13 nm is used. The EUV light is reflected from the reticle after illumination by an illumination system of an EUV-lithographic projection exposure system. The bodies MB_m , MB_n of at least two reflective optical elements of the lens 20 comprise a material with a temperature dependent coefficient of thermal expansion which is zero at respective zero cross temperatures T_{0m} , T_{0n} , as e.g. shown in Fig. 2a and Fig. 2b. As an example such materials are Zerodur® or ULE®, but also Superinvar. In addition the second lens comprises a support structure for passively or actively supporting the reflective optical elements M_i . Such a support structure was described in detail in connection with Fig. 4 and Fig. 5. The temperature of at least a part of the support structure is at a reference temperature T_{Ref} , for example at 22°C as it is in the embodiments of Fig. 3 and Fig. 6. This temperature is close to the temperature of the clean-room. Usually the mirrors or reflective optical elements of the EUV projection lens are specified regarding their surfaces and surface figures also at this reference temperature. Further, the second projection lens comprises a heater 300 for heating at least one of the bodies MB_n , MB_m of the reflective optical elements with the zero cross temperatures. Also

the second lens comprises a temperature control system 200 for controlling the temperature of the at least one heated body MB_n , MB_m to a temperature T_{km} , T_{kn} . Further, if in the second lens the bodies MB_n , MB_m are not heated with the heater, then the exposure of the reflective surfaces MS_m and MS_n with EUV light, which is reflected by the illuminated reticle, results in temperature distributions $\Delta T_n(x,y,z) = (T_n(x,y,z) - T_{Ref})$, $\Delta T_m(x,y,z) = (T_m(x,y,z) - T_{Ref})$ of the bodies MB_n , MB_m relative to the reference temperature T_{Ref} with respective average and maximum temperatures ΔT_{nav} , ΔT_{mav} and ΔT_{nmax} and ΔT_{mmax} . The EUV-light usually comprises a determined spatial distribution of intensity, angular and polarization parameters which is defined by an illumination setting.

Further, in the second lens at least one zero cross temperatures T_{0m} , T_{0n} is selected higher than the maximum of the highest reference temperature T_{Ref} and the respective absolute average or maximum temperature $\Delta T_{mav} + T_{Ref}$ or $\Delta T_{mmax} + T_{Ref}$, $\Delta T_{nav} + T_{Ref}$ or $\Delta T_{nmax} + T_{Ref}$, based on the respective spatial temperature distribution $\Delta T_m(x,y,z)$, $\Delta T_n(x,y,z)$, expressed as

$T_{0m} > \max(T_{Ref}, \Delta T_{mav} + T_{Ref})$, $T_{0m} > \max(T_{Ref}, \Delta T_{mmax} + T_{Ref})$ or $T_{0n} > \max(T_{Ref}, \Delta T_{nav} + T_{Ref})$, $T_{0n} > \max(T_{Ref}, \Delta T_{nmax} + T_{Ref})$. If the absolute maximum temperature instead of the absolute average temperature is considered in the selection process then the system is more robust, e.g. regarding changes in exposure powers to higher values. The second projection lens according to this invention selects the material for the mirrors or reflective optical elements on the basis of the average or maximum temperature which a mirror may achieve if it is illuminated by the projection beam. Due to the application of a heater, the zero cross temperature can be reached independent of whether the projection lens is operating with low or high EUV light power of the projection beam. Preferably the maximum or average temperatures on the heatable mirror bodies are determined for the maximum power to which the projection lens may be subjected. For the embodiments of the second projection lens according to this invention, for the reference temperature the same can be applied as described in connection with the first projection lens and the description in connection with Fig. 4 and Fig. 5.

To consider the manufacturing tolerance of the zero cross temperatures a 2nd embodiment of the second projection lens considers that the materials with the zero cross temperatures T_{0m} , T_{0n} may vary regarding the values of the zero cross temperatures due to manufacturing. Usually this results in manufacturing tolerances ΔT_{0m} , ΔT_{0n} such that the respective real values of the zero cross temperatures are within the intervals $T_{0m} \pm \Delta T_{0m}$ and $T_{0n} \pm \Delta T_{0n}$. If so, it is advantageous to select at least one zero cross temperatures T_{0m} , T_{0n} in the second lens higher than the maximum of the highest reference temperature T_{Ref} and the respective average or maximum temperature increased by the reference temperature, resulting in $\Delta T_{mav} + T_{Ref}$ or $\Delta T_{mmax} + T_{Ref}$, $\Delta T_{nav} + T_{Ref}$ or $\Delta T_{nmax} + T_{Ref}$, based on the respective spatial temperature distribution $\Delta T_m(x,y,z)$, $\Delta T_n(x,y,z)$. This maximum is further increased by the absolute value of the respective manufacturing tolerances ΔT_{0m} , ΔT_{0n} , expressed as $T_{0m} > \max(T_{Ref}, \Delta T_{mav} + T_{Ref}) + |\Delta T_{0m}|$, $T_{0m} > \max(T_{Ref}, \Delta T_{mmax} + T_{Ref}) + |\Delta T_{0m}|$ or $T_{0n} > \max(T_{Ref}, \Delta T_{nav} + T_{Ref}) + |\Delta T_{0n}|$, $T_{0n} > \max(T_{Ref}, \Delta T_{nmax} + T_{Ref}) + |\Delta T_{0n}|$. Similar like in the first embodiment of the second lens, instead of the absolute maximum temperatures also the absolute average temperature may be sufficient, but in this case the second lens will be less robust against a raise of temperature of the mirrors which may result from higher exposure power.

In a 3rd embodiment of the second projection lens the absolute value of the difference between the zero cross temperatures T_{0m} , T_{0n} is more than 6K, expresses as $\text{abs}(T_{0m} - T_{0n}) > 6K$. Preferably in this case the second projection lens is designed to be exposed with an exposure power of more than 8W of EUV light with a wavelength in a wavelength range of less than 50 nm. As already described in connection with the description of the first projection lens of this invention the same advantages are also valid. Preferably the wavelength is in a wavelength interval selected from the group consisting of [12 nm, 14 nm], [12.5 nm, 13.5 nm], [5 nm, 15 nm], [15 nm, 25 nm] and [25 nm, 50 nm]. Such a selection of the wavelength also could be done for the other embodiments of the lenses of the EUV lithographic projection exposure systems which are described in the present specification.

In a 4th embodiment of the second projection lens at least four or six reflective optical elements M_i are used. Further the projection lens is designed to be exposed with an

exposure power of more than 10W of EUV light with a wavelength in a wavelength range of less than 50 nm. With higher power of the EUV light usually also the number of mirrors increase. For a power of 16W usually 6 mirrors are used as shown in Fig. 6. The absolute value of the difference between the zero cross temperatures T_{0m} , T_{0n} is more than 8 K in this
5 embodiment, expresses as $\text{abs}(T_{0m} - T_{0n}) > 8\text{K}$.

A 5th embodiment of the second lens in accordance to this invention controls the temperature T_k of the at least one heated body MB_n , MB_m within an interval of $\pm 5\text{K}$, better $\pm 2\text{K}$ centered around the respective zero cross temperature T_{0m} , T_{0n} to minimize any
10 thermal induced optical aberration.

In a 6th embodiment of the second projection lens at a time before the projection lens is subjected to the exposure power of the EUV light the temperature T_k of the at least one heated body MB_n , MB_m is controlled to its value by heating the heater 300 with a first
15 heating power. This is similar to the 7th embodiment of the first projection lens and reduces the warm-up phase of the EUV-projection system. Further, in an 7th embodiment of the second projection lens the heating power of the 6th embodiment is less than the first heating power when the projection lens is exposed to the exposure power of the EUV light. In a more advanced 8th embodiment of the second projection lens the temperature control
20 system 200 controls the temperature T_k such that the heating power of the heater 300, which heats the at least one body MB_n , MB_m , and the exposure power of the EUV light which is absorbed by the at least one heated body is constant in time. This is similar to the respective embodiment of the first projection lens. Constant in time in this context (and also for the other lens embodiments described herein) means that the total power of heat to
25 which the mirror is subjected (e.g. the sum of the heating power of any heater and the absorbed light like EUV light) is only varying within an interval of the total power selected from the group consisting of [0%. 20%], [0%. 10%], [0%. 5%] and [0%. 2%]. This is the case if the EUV source provides EUV light continuously in time, like a synchrotron radiation source. For pulsed EUV sources like plasma EUV light sources, the total power as mentioned above is
30 determined by an average over a number of pulses. The number of pulses is selected such

that it is within an interval selected from the group of intervals consisting of [1, 5], [1, 10], [1, 20], [1, 50] and [1, 100] pulses.

In a 9th embodiment of the second projection lens the bodies MB_n and MB_m with the
5 respective zero cross temperatures T_{0m} , T_{0n} are made of the same material. Further, in a 10th
embodiment of the second lens the lens comprises 4 or 6 reflective optical elements in form
of mirrors. As already mentioned, the number of mirrors also of the second lens may vary in
accordance to the requirements and the principles of the teaching in connection with the
first and second projection lens may be applied to each mirror or each reflective optical
10 element, especially if used in an EUV lithographic projection exposure apparatus.

Further, to minimize the optical aberration especially in projection lenses 20 according to
the second lens of this invention in which at least one mirror or optical element M_k is heated
by a heater 300, it is advantageous to connect the at least one heated optical element M_k to
an actuator for its translational movement. This allows to shift the mirror M_k to compensate
15 a homogeneous heating of the mirror M_k as it was described in connection with Fig. 3a.
Further, the heater 300 for heating the mirror or optical element M_k advantageously
comprises heating elements selected from the group consisting of IR light emitting diodes,
Peltier elements, optical fibers, light guide rods and IR lasers, as will be described in more
detail below with the description of Fig. 13. Further, such heating elements are optionally
20 arranged in one dimension or in two dimensions at predefined spatial coordinates, forming a
grid structure. Advantageously in the embodiments in which the heating elements are
emitting or guiding IR radiation, these embodiments comprise an optical arrangement to
configure the IR radiation, the optical arrangement comprises arrangement elements
selected from the group consisting of collimator, focusing lens, adjustable lens, mirror and
25 diffractive optical element, wherein the arrangement elements may be tiltable around at
least on axis. Examples of such optical arrangements are shown in Fig. 13.

Further, in an alternative embodiment of the above described second projection lenses the
at least one optical element M_k comprises a modification in or on the mirror body MB_k . The

modification is selected from the group consisting of recess, blind hole, defined surface roughness, diffractive structure, spherical protrusion, spherical recess and surface curvature. The modification, which is described in more detail below in connection with Fig. 13, advantageously is used to guide e.g. IR radiation to heat the optical element locally.

5

In the following a **third projection lens** is described as a part of this invention. This third projection lens makes use of the knowledge from Fig. 9 which show that the zero cross temperatures of different mirrors become more different with increasing power of EUV light, if the lens is designed such that the optical aberration is reduced to a minimum. For the lens of Fig. 6, as an example, the mirrors M_4 and M_6 should have a zero cross temperature with at least about 1K above the reference temperature if the lens is subjected to about 16W of EUV light. In contrary mirror M_5 should have a zero cross temperature T_{05} of about 34°C, or even higher, which is about 12K or more above the reference temperature of 22°C. According to embodiments of the first and the second projection lens in accordance with this invention it is preferred to have a zero cross temperature which is above the ones shown in Fig. 9. In such cases the heaters of these embodiments can heat the mirror, e.g. homogeneously to the respective zero cross temperatures to minimize the optical aberration. So if the EUV light power will still increase, which is always aspired, then the difference in the zero cross temperatures will also increase and become more than the 11K as it is for the lens which is described in Fig. 6 with the values of Fig. 9. Probably this difference will even double, especially if higher EUV light power is used in future lenses, so that the difference for the coldest and the hottest mirror will be about 20K, or even more. In such cases advantageously a glass ceramic like Zerodur® may be used such that for the coldest and the hottest mirror the same material is used. The colder mirror of the both is used or operated at or close to a first zero cross temperature T^1_0 . The hotter mirror is used or operated at or close to the second zero cross temperature T^2_0 which is higher than the first one. This means that e.g. mirror M_m and mirror M_n is made of the same material with the two mentioned zero cross temperatures, designated as T^1_{0mn} and T^2_{0mn} . As shown in US 2003/0125184 A1 glass ceramic materials with two zero cross temperatures in a temperature range of about 0°C to about 100°C exist which have a difference in its zero cross temperatures $T^2_0 - T^1_0$ of

30

about 20K. The usage of only one material for two mirrors will also reduce the costs of the projection lens.

Due to the above advantages, the third projection lens according to this invention comprises again at least two reflective optical elements M_i , each with a body MB_i and a reflective surface MS_i for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. As described above the EUV light is reflected from the reticle when it is illuminated by an illumination system of an EUV-lithographic projection exposure system. The bodies MB_m , MB_n of at least two reflective optical elements comprise a material with a temperature dependent coefficient of thermal expansion which is zero at at least two zero cross temperatures T_{0mn}^1 and T_{0mn}^2 . The third lens additionally comprises a support structure for passively or actively supporting the reflective optical elements M_i , whereas the temperature of at least a part of the support structure is at a reference temperature T_{Ref} as described above in connection with e.g. Fig. 4, Fig. 5 and Fig. 3. Further, the third lens comprises at least two tempering means, preferably heaters, for independently heating or cooling the at least two bodies MB_n , MB_m of the two reflective optical elements. Further, the third projection lens comprises a temperature control system for independently controlling the temperature of the at least two heated or cooled bodies MB_n , MB_m to respective temperatures T_{kn} and T_{km} . As an option at least one of the two zero cross temperatures T_{0mn}^1 and T_{0mn}^2 is higher than the reference temperature T_{Ref} , since the reference temperature is usually in the range of 22°C. This optional embodiment simplifies the material selection to get a suitable material with the two zero cross temperatures. Further, during the exposure of the lens with the exposure power of the EUV light the temperatures T_{kn} of the body MB_n preferably is within an interval of $\pm 5K$, better $\pm 2K$ centered around the first zero cross temperatures T_{0mn}^1 , and the temperatures T_{km} of the body MB_m preferably is within an interval of $\pm 5K$, better $\pm 2K$ centered around the second zero cross temperatures T_{0mn}^2 . In a further embodiment of the third lens the temperatures T_{kn} and T_{km} of the bodies of the reflective optical elements are controlled as close to the respective zero cross temperatures T_{0mn}^1 and T_{0mn}^2 as possible.

It is mentioned here that in general the reference temperature T_{Ref} may be set individual for each mirror. This depends also on the used support structure which holds the mirror. In today's systems the reference temperature is the same for all mirrors. However, this may
 5 change in future. For this reason in accordance with the present invention the meaning of the reference temperature T_{Ref} is such that always the reference temperature to the related mirror or reflective optical element is to be understood.

Further, the third projection lens according to this invention may also have a cooler for the
 10 cooling of the mirror with the lowest zero cross temperature T_{0nm}^1 and a heater for the heating of the mirror with the higher zero cross temperature T_{0mn}^2 . This has the advantage that the lowest zero cross temperature not necessarily must be above the reference temperature of 22°C. By applying a cooler a material can be used in which T_{0nm}^1 is at about 15°C, which is used e.g. for mirror M_4 or M_6 , if referred to Fig. 6, and in which T_{0mn}^2 is at
 15 about 35°C, which is used e.g. for the mirrors M_3 or M_5 . This selection of the mirrors results essentially from Fig. 9. Such a material is e.g. disclosed in US 2003/0125184 A1. Of course, if a material can be manufactured in such a way that both zero cross temperatures are in a temperature range of about 22°C to about 40°C, meaning above the reference temperature T_{Ref} of the respective mirror or optical element, then the preferred embodiment of the third
 20 lens is that both mirrors M_m and M_n are heated with a heater.

In a 2nd embodiment of the third lens the temperature of the bodies MB_n , MB_m , without a heating with the heaters, result in a temperature distributions $\Delta T_n(x,y,z) = (T_n(x,y,z) - T_{\text{Ref}})$, $\Delta T_m(x,y,z) = (T_m(x,y,z) - T_{\text{Ref}})$ of the bodies MB_n , MB_m relative to the reference temperature T_{Ref}
 25 with respective average and maximum temperatures ΔT_{nav} , ΔT_{mav} and ΔT_{nmax} and ΔT_{mmax} . This is caused by the exposure of the reflective surfaces MS_m and MS_n with the EUV light which is reflected by the illuminated reticle and which comprises a spatial distribution of angular, polarization and intensity parameters in accordance with an illumination setting. Further, at least one of the two zero cross temperatures T_{0nm}^1 and T_{0mn}^2 is higher than the

maximum of the highest reference temperature T_{Ref} and the respective absolute average or maximum temperature $\Delta T_{mav} + T_{Ref}$ or $\Delta T_{mmax} + T_{Ref}$, $\Delta T_{nav} + T_{Ref}$ or $\Delta T_{nmax} + T_{Ref}$, based on the respective spatial temperature distribution $\Delta T_m(x,y,z)$, $\Delta T_n(x,y,z)$, expressed as $T_{0mn}^1 > \max(T_{Ref}, \Delta T_{mav} + T_{Ref})$, $T_{0mn}^1 > \max(T_{Ref}, \Delta T_{mmax} + T_{Ref})$ or $T_{0mn}^2 > \max(T_{Ref}, \Delta T_{nav} + T_{Ref})$, $T_{0mn}^2 > \max(T_{Ref}, \Delta T_{nmax} + T_{Ref})$. Selecting the zero cross temperature in this way has similar advantages as already described in connection with the first and the second lens of this invention.

In a 3rd embodiment of the third projection lens comprising a material in which the zero cross temperatures T_{0mn}^1 and T_{0mn}^2 vary regarding their real values due to manufacturing which results in manufacturing tolerances ΔT_{0mn}^1 , ΔT_{0mn}^2 such that the respective real values are within the intervals $T_{0mn}^1 \pm \Delta T_{0mn}^1$ and $T_{0mn}^2 \pm \Delta T_{0mn}^2$. Due to this tolerances advantageously at least one zero cross temperatures T_{0mn}^1 and T_{0mn}^2 is higher than the maximum of the highest reference temperature T_{Ref} and the respective absolute average or maximum temperature $\Delta T_{mav} + T_{Ref}$ or $\Delta T_{mmax} + T_{Ref}$, $\Delta T_{nav} + T_{Ref}$ or $\Delta T_{nmax} + T_{Ref}$, based on the respective spatial temperature distribution $\Delta T_m(x,y,z)$, $\Delta T_n(x,y,z)$, which is additionally increased by the absolute value of the respective manufacturing tolerances ΔT_{0mn}^1 , ΔT_{0mn}^2 , expressed as $T_{0mn}^1 > \max(T_{Ref}, \Delta T_{mav} + T_{Ref}) + |\Delta T_{0mn}^1|$ or $T_{0mn}^1 > \max(T_{Ref}, \Delta T_{mmax} + T_{Ref}) + |\Delta T_{0mn}^1|$ or $T_{0mn}^2 > \max(T_{Ref}, \Delta T_{nav} + T_{Ref}) + |\Delta T_{0mn}^2|$ or $T_{0mn}^2 > \max(T_{Ref}, \Delta T_{nmax} + T_{Ref}) + |\Delta T_{0mn}^2|$.

As already mentioned above in the description of the second projection lens also for the third projection lens as an alternative the selection of the zero cross temperature can done by $T_{0n} > \max(T_{Ref}, T_{av n} + T_{Ref})$ or $T_{0m} > \max(T_{Ref}, T_{av m} + T_{Ref})$, whereby $T_{av m}$ and $T_{av n}$ are the respective average temperatures of mirrors M_m and M_n as described above e.g. in connection with Fig. 7 or Fig. 3. However, if the maximum temperature instead of the average temperature is considered in the selection process also the third lens then is more also robust, e.g. regarding changes in exposure powers to higher values. Like the previous embodiments of the lenses in accordance with this invention, instead of the absolute maximum temperatures also the absolute average temperature may be sufficient, but in this

case the third lens will be less robust against a raise of temperature of the mirrors which may result from higher exposure power.

Similar as the first and the second projection lens of this invention also the third projection lens in a 4th embodiment is controlled such that at a time before the projection lens is subjected to the exposure power of the EUV light the temperature T_{kn} or T_{km} of the at least one heated body MB_n , MB_m is controlled to its value by heating the heater with a first heating power. In a 5th embodiment the control is such that during the time of the exposure of the third projection lens with the exposure power of the EUV light the heating power of the heater with the initial first heating power is less than the first heating power. Alternative to the 4th and the 5th embodiments of the third projection lens in a 6th embodiment of the third lens the temperature control system controls at least one of the temperatures T_{km} and T_{kn} such that the heating power of the respective heater and the exposure power of the EUV light absorbed by the at least one temperature controlled body MB_m or MB_n is constant in time. The advantages of the 4th to the 6th embodiments of the third lens are already mentioned in connection with the first and the second projection lens.

In a 7th embodiment of the third projection lens of this invention the lens is designed to be exposed with an exposure power of more than 8 W of EUV light with a wavelength in a wavelength range of less than 50 nm. Especially Fig. 9 shows that for higher EUV light power to which the lens is exposed, the third embodiment can be used due materials which is available today, as are already mentioned.

In an 8th embodiment of the third projection lens the absolute value of the difference between the zero cross temperatures T_{0mn}^1 , T_{0mn}^2 is chosen more than 6K, expresses as $abs(T_{0mn}^1 - T_{0mn}^2) > 6K$. In this case the projection lens is designed to be exposed with an exposure power of more than 8 W of EUV light with a wavelength in a wavelength range of less than 50 nm. Figure 9 shows an example of such a lens. Further, in a 9th embodiment of the third projection lens 4 or 6 reflective optical elements are mirrors. Alternative or in addition the embodiments of the third projection lens, as described above, may be operated such that, e.g. at a time before the projection lens is subjected to the exposure power of the

EUV light, at least one of the temperature controlled bodies MB_n , MB_m is controlled to its value by cooling with the respective tempering means with a first cooling power. Further, the first cooling power can be increased by the tempering means at a time when the projection lens is subjected to the EUV exposure light. The cooling power describes the heat transfer per time from the temperature controlled body to the tempering means. Again the number of mirrors for the third projection lens may vary in accordance to the requirements. The principles used in third projection lens may be applied to each mirror or each reflective optical element, especially if used in an EUV lithographic projection exposure apparatus.

Further, to minimize the optical aberration especially in projection lenses 20 according to the third lens of this invention in which at least one mirror or optical element M_k is heated or cooled by a heater 300 or tempering means, it is advantageous to connect the at least one heated and/or cooled optical element M_k to an actuator for its translational movement. This allows to shift the mirror M_k to compensate a homogeneous heating or cooling of the mirror M_k as it was described in connection with Fig. 3a. Further, tempering means, as e.g. the heater 300 for heating the mirror or optical element M_k , advantageously comprises heating elements selected from the group consisting of IR light emitting diodes, Peltier elements, optical fibers, light guide rods and IR lasers, as will be described in more detail below with the description of Fig. 13. Further, such heating elements are optionally arranged in one dimension or in two dimensions at predefined spatial coordinates, forming a grid structure. Advantageously in the embodiments in which the heating elements are emitting or guiding IR radiation, these embodiments comprise an optical arrangement to configure the IR radiation, the optical arrangement comprises arrangement elements selected from the group consisting of collimator, focusing lens, adjustable lens, mirror and diffractive optical element, wherein the arrangement elements may be tiltable around at least on axis. Examples of such optical arrangements are shown in Fig. 13.

Further, in an alternative embodiment of the above described third projection lenses the at least one optical element M_k comprises a modification in or on the mirror body MB_k . The modification is selected from the group consisting of recess, blind hole, defined surface

roughness, diffractive structure, spherical protrusion, spherical recess and surface curvature. The modification, which is described in more detail below in connection with Fig. 13, advantageously is used to guide e.g. IR radiation to heat the optical element locally.

Further the present invention is also related to a method to configure a projection lens of an EUV lithographic projection exposure system. The following method is based on the teaching of the previous embodiments of the invention. The configuration method comprises the following steps:

- In a first step the number of reflective optical elements M_i of a EUV projection lens is determined. Some requirements are that the projection lens projects an object field of a give size which is on a reticle onto an image field of a given size on a substrate. For the projection an EUV projection light beam with a wavelength of less than 50 nm is used. The projection requirement is e.g. a predetermined spatial resolution with a predetermined quality.
- In a second step the surface figure and surface shape of each reflective optical element M_i is determined based on the geometric data of the object field and the image field and the predetermined spatial resolution.
- In a third step the substrate material for each reflective optical element M_i with its shape and size is selected, wherein the material is selected by consideration of thermal expansion.
- In a fourth step at least on substrate material is selected from a group of materials which have a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0m} . This material is preferably used for mirrors with a high thermal load.
- In a fifth step the maximum thermal load for each reflective optical element M_i is determined which is expected during the projection of the object field onto the image field under various conditions of the EUV projection exposure system, like EUV light power, transmission or reflection of the reticle, various illuminations settings and various pattern structures on the reticle.

- In a sixth step the spatial temperature $T(x,y,z)$ for each reflective optical element M_i based on the 5th step, considering its thermal load, is determined together with its maximum and its average temperature values $T_{i\max}$ and $T_{i\text{av}}$,
- In a seventh step the at least one material with the zero cross temperature T_{0m} is selected based on the zero cross temperature T_{0m} . The selection is done such that the maximum temperature or the average temperature $T_{m\max}$ and $T_{m\text{av}}$ of the temperature $T(x,y,z)$ of the optical element M_m related to the at least one substrate material is lower than the zero cross temperature T_{0m} , expressed as $T_{m\max} < T_{0m}$ or $T_{m\text{av}} < T_{0m}$.
- In the eighth step the mirrors and the lens are formed with the selected materials.

In a preferred method the configuration method comprises the additional steps in which the at least one material is selected such that the zero cross temperatures T_{0m} is higher than the maximum temperature or the average temperature $T_{m\max}$ and $T_{m\text{av}}$ increased by an absolute value of respective manufacturing tolerances ΔT_{0m} , to manufacture a material with the zero cross temperature T_{0m} , expressed as $T_{0m} > T_{m\max} + |\Delta T_{0m}|$ or $T_{0m} > \max(T_{\text{Ref}}, T_{m\max}) + |\Delta T_{0m}|$. With this material selection also variations of the zero cross temperatures T_{0m} are considered, since they vary regarding its real value due to manufacturing process parameters, as e.g. described in US 2003/0125184 A1. The real values of the zero cross temperatures T_{0m} are within the intervals $T_{0m} \pm \Delta T_{0m}$.

The configuration method may comprise that the one material with the zero cross temperature T_{0m} is selected such that it comprises a second zero cross temperature T_{0m}^2 such that the absolute value of the difference between the zero cross temperature and the second zero cross temperature is less than 40 K, expressed as $\text{abs}(T_{0m} - T_{0m}^2) < 40 \text{ K}$. This has the advantage that such a material is applicable for two mirrors of the EUV projection lens, whereas the two mirrors have different thermal load which result in very different zero cross temperatures to minimize optical aberration, as described in connection with Fig. 9.

Further, the configuration method may comprise that the material with the second zero cross temperature is used as substrate material for at least one additional reflective optical element, as it was just explained.

- 5 The configuration method may comprise a step in which a heater 300 and a temperature control system 200 is selected such that the at least one material with the zero cross temperature is heatable to its zero cross temperature.

10 In the following various embodiments of the heater 300 are described. Further, also heating methods and special bodies for the reflective optical element M_k are shown, which allow the heating of the reflective element or mirror in such a way that the thermal induced optical aberrations become minimal. These further aspects are also treated a parts of the present invention.

- 15 Fig. 10 schematically shows a side view a reflective optical element M_k like a mirror 421 of an EUV projection lens, as e.g. shown in Fig. 4 and Fig. 5. The optical element comprises a reflective surface MS_k which could be a mirror surface 450 or also a diffractive surface. In general, also on all the reflective optical elements, in accordance to this invention, the reflective surface can comprise diffractive structures to form a diffractive optical element for the incident radiation. The incident radiation 1000 can be a EUV light projection beam 4 (see
20 Fig. 1), or it can be light of another wavelength like e.g. infrared light. In Fig. 10 in addition, support means are schematically shown like such ones which are described in connection with Fig. 4 and Fig. 5 why the same reference numerals are used. These support means are e.g. linking points 451, linking elements 471 or a bipod structure 461 as described in Fig. 4.
- 25 Also a support element 480 and a part of the housing structure 481 is shown. Further, a heater or in general a first tempering element 300 is shown. Parts and some embodiments of such a heater or first tempering element 300 are already described together with Fig. 5. The difference between a heater and a tempering element is that the heater only can heat in a controlled way, whereas the tempering element is able to heat and cool in a controlled

way. Heating in this context means that thermal energy is transferred from the heater or tempering element to its surrounding. Cooling means that thermal energy is transferred from the surrounding of the heater or tempering element to the heater or tempering element, and the heater or the tempering element is controllable in such a way that its temperature is lower than the temperature of the surrounding. Further, the embodiment as shown in Fig. 10 comprises a cooler or second tempering element 350. The cooler 350 or second tempering element is preferably arranged between the heater or first tempering element 300 and the support element 480 and/or the housing structure 481 (not shown) and /or the support means 451, 461, 471 (not shown, see Fig. 5). If the heater or first tempering element 300 is used to influence the temperature distribution of the reflective optical element M_k then there is a risk that also the temperature of other elements in the surrounding of the reflective element M_k is changed. Such an element can be e.g. the support element 480, the housing structure 481 or the support means 451, 461, 471. However, some of these elements have to be at a well controlled constant temperature to keep the reflective optical element or the mirror M_k , 421 in its position. As mentioned above, this position has to be constant within a nanometer or even sub-nanometer range. For this reason these elements are designated as temperature sensitive elements. Any heating and/or cooling of the surrounding of the reflective optical element or the mirror M_k , 421 to influence its temperature or temperature distribution, e.g. with the heater or first tempering element 300, may change this position. For this reason the cooler or second tempering element 350 is made such that it absorbs any thermal effects which are caused by the heater or first tempering element 300. This means that on the side 351 of the cooler 350 or of the second tempering element, which is oriented to the direction of the temperature sensitive elements like the support element 480 and/or the housing structure 481 and/or the support means 451, 461, 471, the temperature of the cooler or second tempering element is kept constant, resulting in a constant temperature of the temperature sensitive element such that the position of the respective optical element M_k is constant on the nanometer or even sub-nanometer level. With this measure the temperature variation of these temperature sensitive elements can be reduced even if e.g. the heater or first tempering element changes its temperature to influence the temperature or the temperature distribution of the reflective optical element or mirror M_k , 421, to achieve the

advantages as described in connection with the above described projection lenses of the present invention.

Due to the advantages of the embodiment shown in Fig. 10 the present invention also relates to a fourth projection lens of an EUV-lithographic projection exposure system which comprises a plurality of reflective optical elements M_i . Each reflective element M_i comprises a body MB_i and a reflective surface MS_i to project an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm which is reflected from the reticle while the reticle is illuminated by an illumination system of the EUV-lithographic projection exposure system. The lens further comprises support means which comprises a temperature sensitive element selected from the group consisting of linking points 451, bipod structures 461, linking elements 471, a support element 480 and a housing structure 481, for passively or actively supporting at least one optical element M_k . Further, the temperature sensitive element is controlled to a constant temperature or to a predefined temperature. The lens further comprises a first tempering element 300 for heating and/or cooling the at least one optical element M_k to a temperature T_k , and a second tempering element 350 for tempering the temperature sensitive element to the constant temperature or to the predefined temperature. Further, the second tempering element 350 is spatially arranged between the temperature sensitive element and the first tempering element 300.

In a further second embodiment of the fourth projection lens the heated or cooled reflective optical element M_k comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0k} which is different from the constant or predefined temperature of the temperature sensitive element. Preferably in a further third embodiment of the fourth projection lens the temperature of the temperature sensitive element in the fourth projection lens is at a reference temperature T_{Ref} . The reference temperature T_{Ref} has the same meaning as for the other projection lenses of this invention or as are described herein. Preferably but not necessarily the reference

temperature $T_{\text{Ref}} = 22^\circ\text{C}$, or at the temperature of the clean room in which the lithographic projection exposure apparatus is operated for mass production.

A further fourth embodiment of the fourth projection lens comprising the features of the above second and third embodiments, and in addition the feature that without tempering the body MB_k with the first tempering element 300, the exposure of the reflective surface MS_k with EUV light, being reflected by the illuminated reticle and comprising a spatial distribution of angular, polarization and intensity in accordance with an illumination setting, results in a temperature distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{\text{Ref}})$ of the body MB_k relative to the reference temperature T_{Ref} with an average and maximum temperature ΔT_{kav} and ΔT_{kmax} . Further, the zero cross temperatures T_{0k} in this embodiment is higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature added by the reference temperature, resulting in $\Delta T_{\text{kav}} + T_{\text{Ref}}$ or $\Delta T_{\text{kmax}} + T_{\text{Ref}}$ based on the spatial temperature distribution $\Delta T_k(x,y,z)$, which is expressed as $T_{0k} > \max(T_{\text{Ref}}, \Delta T_{\text{kav}} + T_{\text{Ref}})$ or $T_{0k} > \max(T_{\text{Ref}}, \Delta T_{\text{kmax}} + T_{\text{Ref}})$.

In a further fifth embodiment of the fourth projection lens the material with the zero cross temperature T_{0k} varies regarding its real value of the zero cross temperature due to manufacturing processes. This results in a manufacturing tolerance ΔT_{0k} such that the real value is within the interval $T_{0k} \pm \Delta T_{0k}$. In this embodiment the zero cross temperatures T_{0k} is selected higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature (based on the spatial temperature distribution $\Delta T_k(x,y,z)$) added by the reference temperature, resulting in $\Delta T_{\text{kav}} + T_{\text{Ref}}$ or $\Delta T_{\text{kmax}} + T_{\text{Ref}}$, the maximum is increased by the absolute value of the manufacturing tolerance ΔT_{0k} , expressed as $T_{0k} > \max(T_{\text{Ref}}, \Delta T_{\text{kav}} + T_{\text{Ref}}) + |\Delta T_{0k}|$, $T_{0k} > \max(T_{\text{Ref}}, \Delta T_{\text{kmax}} + T_{\text{Ref}}) + |\Delta T_{0k}|$.

In a further sixth embodiment of the fourth projection lens (and its embodiments) the zero cross temperature T_{0k} of the reflective optical element M_k is lower than the reference

temperature T_{Ref} , or is at least 6 K higher than the reference temperature. In the case that the zero cross temperature is lower than the reference temperature the reflective optical element M_k is cooled by the first tempering means to a temperature close to this zero cross temperature. This feature of the fourth projection lens can be used in the third projection lens of the present invention for the cooling of the mirror with the lowest zero cross temperature as it was described above. If the zero cross temperature T_{0k} is at least 6 K above the mentioned reference temperature this feature of the fourth projection lens can be used in a projection lens in accordance with the first projection lens in which the zero cross temperatures of two reflective elements differ at least by 6 K and one of the two reflective elements has a zero cross temperature close to or at the reference temperature. As mentioned in the description of the first projection lens of the present invention such a projection lens is designed for an EUV exposure power of more than 8 W (see also Fig. 9 with description).

In an additional seventh embodiment of the fourth projection lens (and its embodiments) the reflective optical element M_k is (in at least one spatial dimension) homogeneously subjected to a heat transfer caused by the first tempering element 300. Such a homogeneous heat transfer homogeneously heats or cools the optical element M_k which results in a constant temperature distribution of the reflective optical element M_k along the at least one dimension, if only the influence of the first tempering element 300 is considered. This variant of the fourth projection lens can be used in the first, second and third projection lens to e.g. homogeneously heat up the reflective optical element to or close to its zero cross temperature, as it was described in connection with these projection lenses, and as it was schematically described with Fig. 3a to 3l and Fig. 5. Advantageously, in a further embodiment of the fourth projection lens and its various embodiments the optical element M_k is connected to an actuator for its translational movement. This is to minimize optical aberration of the projection lens or the optical element M_k for the case that the optical element is homogeneously heated or cooled to a temperature different from the reference temperature T_{Ref} , as is was described e.g. in connection with Fig. 3a and Fig. 3b.

As shown in Fig. 10 in a preferred eighth embodiment of the fourth projection lens and its embodiments the first tempering element 300 is located on a side of the body MB_k of the at least one optical element M_k which is opposite to its reflective surface MS_k . This is a similar arrangement of the first tempering element 300 as it is described in Fig. 5 for the heater 300.

- 5 In the fourth projection lens and its embodiments preferably the first tempering element 300 comprises a Peltier element or a radiation source, emitting a radiation comprising a wavelength to which the body MB_k of the at least one optical element M_k is semitransparent. As shown in Fig. 10, in a further embodiment of the fourth projection lens the second tempering element 350 is located on a side of the first tempering element 300
- 10 which is opposite to the body MB_k of the at least one optical element M_k .

In one embodiment in accordance with Fig. 10 the tempering element 300 may be a Peltier element or may comprise a Peltier element as already mentioned. The Peltier element may heat or cool the surrounding around its surface side 362 which is oriented into the direction

15 of the reflective element or mirror M_k , 421. Preferably the Peltier element extends parallel or approximately parallel to the surface of the reflective element M_k , 421 which is opposite of the reflective surface MS_k , 450. If the Peltier element has at least such a size so that the reflective surface or even the reflective element can be covered from one side then a homogenous heating and/or cooling of the reflective element can be done which results in

20 all the advantages as described herein (e.g. in connection with Fig. 3a). To make the Peltier element more efficient it is preferably coupled to the cooler 350, or in general to the second tempering element by e.g. coupling one of its surfaces 361 to one of the surfaces 352 of the cooler 350 or the second tempering element. The cooler 350 or in general the second tempering element may have a kind of a sandwich structure such that the surface 352 which

25 is in contact with the first tempering or Peltier element 300 is separated from the surface 351 which is oriented into the direction of the temperature sensitive elements, like the support element 480, the housing structure 481 or the support means 451, 461, 471. In a further embodiment the first tempering element 300 may comprise several Peltier elements. Preferably the Peltier elements are arranged side by side in at least one dimension, to form

30 an array-like arrangement. Arrangements of the Peltier elements in two or even three dimensions are also of advantage. Preferably each Peltier element of such an arrangement is

controllable by a control system like e.g. the temperature control system as described in Fig. 5. In this case a controllable temperature profile on the side which is directed to the reflective element or mirror can be adjusted. This will influence the temperature distribution within the reflective element or mirror M_k , 421 in a controlled way. Such a heater or
5 tempering element can be used for the temperature control of the reflective element or mirror M_k , 421 in accordance to the teaching of this invention in such a way that the thermal induced optical aberration or the imaging errors are minimized. The usage of the described Peltier element 300 or an arrangement of Peltier elements as a tempering means in the third projection lens according to this invention will have the advantage that the mirror with the
10 low zero cross temperature T_{0mn}^1 (according to the third projection lens of this invention) can be cooled down to this temperature or even lower, which is important if the zero cross temperature is below the reference temperature T_{Ref} . Further, the mirror with the high zero cross temperature T_{0mn}^2 (or a zero cross temperature higher than the reference temperature T_{Ref}) can be heated up to this or the respective operation temperatures as described above
15 in connection with one of the projection lenses according to this invention.

In a further embodiment of the fourth projection lens and its embodiments described above, the projection lens comprises a pressure control system for the control of the pressure Δp within a surrounding of the at least one reflective optical element M_k . Such a pressure
20 control system will be described below in connection with Fig. 11. The pressure control is based on a parameter selected from the group consisting of: The temperature of the reflective optical element M_k , the time, a parameter which directly or indirectly influences the temperature of the optical element M_k , an illumination setting, a change of the reticle, thermally or mechanically induced optical aberration data of the optical element M_k or the
25 projection lens and an output parameter from a model. The model input comprises data selected from the group consisting of: The temperature of the reflective optical element M_k , the time, a parameter which directly or indirectly influences the temperature of the optical element M_k , an illumination setting, thermally or mechanically induced optical aberration data of the optical element M_k or the projection lens and a change of the reticle. Further, the
30 pressure control system preferably comprises a gas inlet and/or a gas outlet nearby the at least one optical element M_k .

The fourth projection lens according to this invention preferably is operated such that the temperature T_k of the optical element M_k is controlled to its value by heating the first tempering element with a first heating power at a time before the projection lens is subjected to the exposure power of the EUV light. Then, during the time when the projection lens is subjected to the exposure power of the EUV light, the heating power of the first tempering element is less than the first heating power. Further, in a preferred embodiment of the fourth projection lens and its various embodiments the temperature T_k of the at least one optical element M_k which is heated and/or cooled by the first tempering element 300 is the zero cross temperature T_{0k} .

Fig. 11 schematically shows a further embodiment of the present invention similar as shown in Fig. 10 why like elements are designated with the same reference numerals. In the following the description focuses only to the differences to the embodiment of Fig. 10. The elements not described and its functions are as the ones described in Fig. 10. In the embodiment of Fig. 11 there is no heater or tempering means. The temperature of the reflective optical element or mirror M_k , 421 is controlled by pressure control of the pressure within the surrounding of the reflective element or mirror M_k , 421, designated as Δp . In this case the pressure can be controlled e.g. as a function of the temperature of the reflective element or mirror M_k , 421, as a function of time or a function of other parameters which directly or indirectly influence the temperature of the reflective element or mirror M_k , 421. Further, the control system which controls the pressure may comprise a model which uses input data like the mentioned function variables to optionally adjust the model and to provide output parameters like the pressure or any parameter which directly or indirectly influence the pressure in the mentioned surrounding. From the above, the present invention also relates to a **fifth projection lens**. The fifth projection lens is a projection lens of an EUV-lithographic projection exposure system. The lens comprises a plurality of reflective optical elements M_i , each comprises a body MB_i and a reflective surface MS_i for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than

50 nm, when the light is reflected from the reticle while illuminated by an illumination system of the EUV-lithographic projection exposure system. The lens further comprises support means for passively or actively supporting at least one optical element M_k , a pressure control system (as described in connection with the embodiment of Fig. 11) for the control of the pressure Δp within a surrounding of the at least one reflective optical element M_k , wherein the control is based on a parameter selected from the group consisting of: The temperature of the reflective optical element M_k , the time, a parameter which directly or indirectly influence the temperature of the optical element M_k , an illumination setting, a change of the reticle, thermally or mechanically induced optical aberration data of the optical element M_k or the projection lens and an output parameter from a model. Further, the model is using input data selected from the group consisting : The temperature of the reflective optical element M_k , the time, a parameter which directly or indirectly influence the temperature of the optical element M_k , an illumination setting, thermally or mechanically induced optical aberration data of the optical element M_k or the projection lens and a change of the reticle.

The following describes the fifth projection lens in more detail with various modified embodiments also referring to Fig. 11.

In a second embodiment of the fifth projection lens the support means comprising a temperature sensitive element, (as described in connection with Fig. 10) selected from the group consisting of linking points 451, bipod structures 461, linking elements 471, support element 480 and housing structure 481, for passively or actively supporting the at least one optical element M_k , wherein the temperature sensitive element is controlled to a constant or predefined temperature by a cooler 350. Preferably the cooler 350 is spatially arranged between the temperature sensitive element and the at least one optical element M_k . In the fifth projection lens and its various embodiments the pressure Δp within the surrounding of the at least one optical element M_k is in the range of 0.1 Pa to 10 Pa, more preferably in the range between 1 Pa and 5 Pa. The distance between the at least one optical element M_k and

the cooler 350 preferably is in the range of 1 mm to 10 mm, more preferably in the range between 3 mm and 5 mm. Further, the pressure control system comprises a gas inlet and/or a gas outlet nearby the at least one reflective optical element M_k . With the gas inlet and/or gas outlet (not shown in Fig. 11) the pressure within the surrounding of the at least one optical element M_k can be adjusted. In a further preferred embodiment of the fifth projection lens the distance of the cooler 350 between the at least one reflective optical element M_k and the cooler 350 is adjustable to control a heat transfer between these elements.

- 10 Further, similar as for the fourth projection lens and its embodiments as described with Fig. 10, in the fifth projection lens the at least one reflective optical element M_k also comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0k} . Generally this zero cross temperature is different from the constant or predefined temperature of the temperature sensitive element, whose
15 temperature is preferably but not necessarily at a reference temperature T_{Ref} , as it was already mentioned in connection with the fourth projection lens of this invention which was described in connection with Fig. 10.

The fifth projection lens advantageously offers the possibility that the pressure Δp (which is
20 controlled by the control system) is such that the temperature of the at least one reflective optical element M_k is at its zero cross temperature.

Usually the surrounding of the reflective element or mirror M_k , 421 comprise a gas with a pressure in the range of about 1 to 5 Pa (Pascal), preferably about 3.5 Pa. The cooler 350 is
25 usually shielding the temperature sensitive element such that any temperature change of the mirror 421 will have no influence on them, as already described with Fig. 10. For this preferably the cooler 350 is spatially arranged between the temperature sensitive element and the at least one optical element M_k .

The distance between the at least one optical element supported by the support means or the mirror 421 and the cooler 350 is about 3 to 5 mm. Within this space there is the gas pressure as mentioned. As a gas usually hydrogen is used. If, in the case of a hydrogen gas, the pressure is changes by about ± 1 Pa then the thermal resistance of the gas will change by about $\pm 25\%$. By the usage of a pressure control system to control the pressure in the direct surrounding of the mirror 421, the mirror can be controlled regarding its absolute temperature and regarding its temperature distribution as a function of time. As an example, at the start of the EUV projection process the mirror 421 is at a lower temperature as it is in a steady state. In this case the pressure is reduced so that the mirror heats up faster to its steady state temperature. As another example, if the illumination setting and/or the reticle is changed, most probable also the power will change to which the EUV projection lens is subjected as it was described above. In such a case the mirror 421 will heat up to a higher or to a lower steady state temperature. In the first case the pressure is increased to reduce the thermal resistance between the cooler 350 and the mirror 421. In the second case the pressure will be reduced to increase the thermal resistance of the gas surrounding to bring the mirror to its best steady state temperature which is closest to the zero cross temperature (this was explained with Fig. 7). Applying the regulation of the gas pressure in the surrounding of the mirror 421 will influence the steady stated temperature. Ideally the steady state temperature should be the zero cross temperature to minimize the optical aberration. As a further application, also small variations in the zero cross temperature of a certain mirror M_k , e.g. due to manufacturing tolerances, may be compensated in a way that the pressure in the direct surrounding of this mirror is adjusted such that in the steady state the average temperature T_{avk} of this mirror fits best to the zero cross temperature. Such a pressure control requires that the pressure in the direct surrounding of the individual mirrors or reflective optical elements of an EUV lens can be changed independently. Practically this is done by gas inlets and gas outlets nearby the mirrors. From this in a further embodiment of the fifth projection lens the pressure control system comprises a gas inlet and a gas outlet nearby the at least one reflective optical element M_k which is supported by the support means.

In further embodiments of the fifth projection lens also the distance of the cooler surface 352, or in general the distance between the cooler 350 and the mirror 421 or the reflective optical element M_k may be adjusted to control the heat transfer between these elements.

5 Fig. 12a shows the transmission of Zerodur® for a transmission path of 5 mm and 25 mm. It shows that Zerodur® has an about constant absorption coefficient for light with a wavelength in the range of 700 nm up to about $2\mu\text{m}$ (herein further designated as infrared or IR radiation or IR light). The attenuation length in Zerodur® for IR light with a wavelength in this range is about 50 mm to about 100 mm. This results from Fig. 12a. Fig. 3d and Fig. 3h
10 also show typical mirror sizes of mirrors used in an EUV projection lens. The diameters are typically in the range of 200 mm to 600 mm, and the thickness is up to 100 mm. This means that if IR light passes a distance of 50 mm to about 100 mm in Zerodur® material then 63% of its energy is absorbed along its path. So the attenuation length fits well to the size of the mirrors of an EUV lens such that the mirror, if made of Zerodur® or if comprising Zerodur®,
15 can be heated by the mentioned IR light. This is because the IR light deposits its energy over a distance of about 50 mm up to even 100 mm and more. Such a distance can be warmed up simultaneously in a more or less homogenous way. This means that a mirror body MB_k of a mirror M_k , as e.g. shown in Fig. 5, Fig. 10 or Fig. 11, is semitransparent for a radiation which comprises a wavelength in the infrared range, as shown in Fig. 12a. To make use of this
20 effect Fig. 12b schematically shows a further embodiment of the present invention in which a reflective optical element or a mirror M_k , 421 is coated with a coating C on or on almost its entire surface to make the mirror heatable with IR radiation. The coating C differs from the reflective surface MS_k , 450 which may comprise also a coating in the form of a multilayer to reflect the EUV light.

25

The coating C is selected such that the infrared radiation IR is reflected. As a coating material a very thin metal layer can be used. Other coatings which reflect IR radiation can also be used. Further, the coating and the wavelength of the IR radiation can be adapted such that its reflection is optimized. The coating C has the function that the IR radiation cannot leave
30 the mirror body MB_k and that mirror is heated more homogenous due to the various

reflections which are shown in Fig. 12b as 1002. With this method the IR radiation almost instantaneously and totally deposits its energy within the mirror body MB_k . To get the IR radiation into the mirror body MB_k at least one surface area of it is not coated or the coating is partly transparent for the IR radiation. Such surface areas are designated by 1004 and 1006 and are called IR windows. The IR window or a plurality of IR windows 1004, 1006 are positioned on a suitable position on the mirror which considers the attenuation length of the IR radiation within the mirror body material, the geometrical form and the size of the mirror. Also any limitations regarding construction space is considered. However, since the attenuation length is comparatively large, or in other words in the range of the size of the mirror, the position of the IR window is not so critical. Especially, the position can be on the side of the mirror body MB_k on which the reflective surface MS_k , 450 of the reflective element or mirror is arranged, as shown in the example of Fig. 12b. This has the advantage that also the construction space in front of the mirror can be used to couple the IR radiation into the reflective element or mirror. Most other heater or tempering means cannot be used in this space since they will block or shadow the EUV projection beam 1000. Preferably the IR window surrounds the reflective surface MS_k , 450, as schematically shown in Fig. 12b. As a further option the IR window comprises a certain surface roughness or a diffractive structure to scatter or distribute the IR radiation within the mirror body. Further, the IR radiation may at least partly share the same construction space as the EUV projection beam 1000, as is shown in Fig. 12b for the right IR beam. As IR radiation source any source like Lasers, IR-diodes, filaments or lamps etc. can be used. Depending on the IR source a suitable optical arrangement can be used to configure the IR radiation such that it can be coupled into the reflective element or into the mirror M_k , 421 through the IR windows. Such an optical arrangement may comprise lenses and mirrors or in general refractive, diffractive and/or reflective optical elements. In addition or alternative, such an optical arrangement may also comprise quartz fibers or optical fibers (in general light guides) e.g. to transport the IR radiation from the IR source to the IR windows 1004, 1006. In this case then the IR source can be positioned even outside the EUV projection lens or outside the EUV lithographic projection system. A reflective optical element or a mirror M_k , 421 as described with Fig. 12b has the advantage that there is no mechanical contact of the heater or tempering element or tempering means (which comprises the IR source and an optional optical arrangement to configure the IR light) with the reflective element or the mirror M_k .

In further embodiments of the present invention the reflective element or mirror of Fig. 12b can be used together with the tempering elements or tempering means e.g. the heater 300 of the embodiment of Fig. 10 and/or with the cooler 350 as described there, or as described in the embodiment of Fig. 11. In addition, or as an alternative, also the pressure control as described in Fig. 11 can be used together with the embodiments of Fig. 12b. All these embodiments can advantageously be used in an EUV projection lens, especially in one as described above in accordance to this invention, preferably in the first, second and third projection lens according to this invention, having the advantage that the thermal induced optical aberration is minimized.

The above discussion of Fig. 12a and Fig. 12b result in a **sixth projection lens** according to this invention, and which is illustrated in Fig. 12b. The first embodiment of the sixth projection lens for an EUV-lithographic projection exposure system comprises a plurality of reflective optical elements M_i . Each reflective optical element M_k comprises a body MB_i and a reflective surface MS_i for projecting an object field on a reticle onto an image field on a substrate, if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm, which is reflected from the reticle while the reticle is illuminated by an illumination system of the EUV-lithographic projection exposure system. Further, the at least one reflective optical element M_k comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0k} . In addition, the body MB_k of the optical element M_k is semitransparent to an IR radiation, and the at least one reflective optical element M_k with its body MB_k comprises a coating C on or on almost its entire surface of the body MB_k . The coating C reflects IR radiation inside the body MB_k .

A second embodiment of the sixth projection lens comprises an IR light source or comprises an optical arrangement to form an IR light path. The IR light source or the IR light path couples IR radiation into the body MB_k which comprises the coating C. In a preferred

embodiment the IR light source or the optical arrangement comprises an element selected from the group consisting of: Laser, IR-diode, filament, lens, mirror, refractive element, diffractive element, reflective element, light guide and optical fiber. Further, the body MB_k preferably comprises a surface area 1004, 1006 not coated with the coating C, or comprises
5 a surface area 1004, 1006 with a coating being semitransparent to the IR radiation, for coupling in the IR radiation into the body MB_k . Preferably the coating C comprises a metal.

In a further embodiment of the sixth projection lens the surface area 1004, 1006 is arranged on the side of the body MB_k which comprises the reflective surface MS_k . Alternative or in
10 addition, the surface area 1004, 1006 surrounds the reflective surface MS_k . Further, the surface area 1004, 1006 may comprise a surface roughness to scatter the IR radiation into the body, or the surface area may comprise a diffractive structure to distribute the IR radiation within the body MB_k by diffraction.

15 In a further embodiment of the sixth projection lens the construction space nearby the reflective surface MS_k is illuminated by the IR radiation and the EUV light. Preferably the IR source is arranged outside the projection lens or outside the EUV-lithographic projection exposure system.

20 Further, as in the first to fifth projection lenses described above, also in the sixth projection lens the optical element M_k optionally is connected to an actuator for its translational movement.

Similar as the first to fifth projection lens also the sixth projection lens may comprise
25 embodiments which comprises a cooler 350 located on a side of the body MB_k of the at least one optical element M_k which is opposite to its reflective surface MS_k . Further, the distance of the cooler 350 to the at least one reflective optical element M_k preferably is adjustable for the control of the heat transfer between these elements. Alternative or in addition, the sixth

projection lens (and its embodiments) comprises a pressure control system for the control of the pressure Δp within a surrounding of the at least one reflective optical element M_k . Further, the mentioned pressure control system may comprise a gas inlet and/or a gas outlet nearby the at least one optical element M_k .

5

Without radiating the body MB_k of the sixth projection lens with IR radiation, the exposure of the reflective surface MS_k with EUV light (which is reflected by the illuminated reticle, and which comprises a spatial distribution of angular, polarization and intensity in accordance with an illumination setting) results in a temperature distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{Ref})$ of the body MB_k with the temperature $T_k(x,y,z)$ relative to a reference temperature T_{Ref} . The temperature distribution comprises an average and maximum temperature ΔT_{kav} and ΔT_{kmax} . Preferably the zero cross temperature T_{Ok} is higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature $\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$, expressed as $T_{Ok} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref})$ or $T_{Ok} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref})$. Further, if the material with the zero cross temperature T_{Ok} varies regarding its real value of the zero cross temperature due to manufacturing, resulting in a manufacturing tolerance ΔT_{Ok} such that the real value of the zero cross temperature T_{Ok} is within the interval $T_{Ok} \pm \Delta T_{Ok}$, then the zero cross temperatures T_{Ok} is selected higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature $\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$, wherein the maximum is increased by the absolute value of the manufacturing tolerance ΔT_{Ok} , expressed as $T_{Ok} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref}) + |\Delta T_{Ok}|$, $T_{Ok} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref}) + |\Delta T_{Ok}|$.

25

In a further embodiment of the sixth projection lens (and its various embodiments) the temperature T_k of the optical element M_k is controlled to its value by irradiating the optical element MB_k with a first IR radiation power at a time before the projection lens is subjected to the exposure power of the EUV light. Optionally the IR radiation power is less than the

first IR radiation power during the time when the projection lens is subjected to the exposure power of the EUV light.

Further, the present invention relates to a mirror (as shown in Fig. 12) which comprises a body MB_k and a reflective surface MS_k , and material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0k} . Further, the body MB_k of the optical element M_k is semitransparent to an IR radiation, and the body MB_k comprises a coating C on or on almost its entire surface of the body MB_k , wherein the coating C reflects IR radiation inside the body MB_k , and wherein the mirror is adapted for a projection lens of an EUV-lithographic projection exposure system for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. Optionally the mirror body MB_k comprises a surface area 1004, 1006 which is not coated with the coating C, or it comprises a surface area 1004, 1006 with a coating which is semitransparent to the IR radiation, both for coupling in an IR radiation into the body MB_k . Preferably the coating comprises a metal. In a further embodiment of the mirror the surface area 1004, 1006 is arranged on the side of the mirror body MB_k on which the reflective surface MS_k is arranged. Alternative or in addition the surface area 1004, 1006 surrounds the reflective surface MS_k . In a further embodiment of the mirror according to the invention the surface area 1004, 1006 comprises a surface roughness to scatter an IR radiation into the body, or the surface area comprises a diffractive structure to distribute an IR radiation within the body MB_k by diffraction.

Fig. 12c schematically shows a further embodiment of the present invention in which a reflective optical element or a mirror M_k , 421 is at least partly coated with a coating C2 on its surface to make the mirror heatable. In accordance with this embodiment the coating C2 differ from the reflective surface MS_k , 450 which may comprise also a coating in the form of a multilayer coating to reflect the EUV light 1000. The coating C2 is selected such that it will have a certain electrical resistance why it is called resistive coating C2. If in the resistive coating C2 an electrical current is generated then energy is produced which is transferred as

a thermal energy to the reflective element or mirror M_k which heats up. In this way the temperature of the reflective element or mirror M_k , 421 can be controlled. In this embodiment the heater or tempering means 300 comprises the resistive coating C2 and a voltage source VS which is connected to the coating C2. According to this embodiment of the invention the resistive coating C2 may cover the surface of the body M_k . Preferably there is no resistive coating C2 between the reflective surface MS_k , 450 and the body MB_k . Alternative, only a part or several parts of the surface of the body are coated with the resistive coating C2. These parts are selected such that a homogenous temperature distribution in the body and/or on the reflective surface can be achieved. This will minimize the aberration of the reflective element or of the mirror as in the embodiments described above. The electrical current in the resistive coating C2 can be generated by an electrical voltage. For this reason a voltage source VS is connected to the resistive coating C2 of the optical element M_k , 421. This can be done by cable 1008. Alternative or in addition the voltage source VS is mounted on the body as shown by numeral 1010. If the voltage source is mounted on the body MB_k there is also no mechanical connection of the heater or tempering means 300, which is formed by the coating C2, to a support structure as it is if a cable or wires 1008 are used. Advantageously then there will be no forces or moments transferred from the cable or the wires to the mirror or reflective optical element M_k , 421.

In further embodiments of the present invention in accordance to an embodiment as described in Fig. 12c the reflective element or mirror of Fig. 12c can be used together with the tempering means or heater 300 of the embodiment of Fig. 10 and/or with the cooler 350 as described. In addition or as an alternative, also the pressure control as described in connection with Fig. 11 can be used together with the embodiments of Fig. 12c. In addition the embodiments of Fig. 12b and 12c may be combined, e.g. by using the coating C for the reflection of IR light and as a resistive coating C2. As an alternative the IR reflection coating C (of Fig. 12b) may be covered with a resistive coating C2 which is heated by a voltage source VR as described in Fig. 12c. Again, all these embodiments advantageously can be used in an EUV projection lens, especially in one as described above in accordance to this invention, preferably in the first, second and third to sixth projection lens according to this invention to reduce thermal induced optical aberration.

Due to the advantages which are described in connection with the embodiments of a projection lens with a mirror or reflective optical element as described in connection with Fig. 12c, the present invention also relates to a **seventh projection lens** and to a mirror used
5 therein.

The mirror according to the present invention in connection with Fig. 12c comprises a body MB_k and a reflective surface MS_k . Further, the mirror comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross
10 temperature T_{0k} , and the body MB_k is at least partly coated with a resistive coating C2, wherein the resistive coating C2 has an electrical resistance suitable to heat the body by electrical resistive heating. Further, the mirror is adapted for a projection lens of an EUV-lithographic projection exposure system for projecting an object field on a reticle onto an
15 image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. Preferably the resistive heating is between 0,01 W and 1 W. Further, the coating C2 is connected to a voltage source VS. The voltage source preferably is attached to the mirror body MB_k , or the voltage source is electrically connected to the mirror body MB_k by a wire 1008.

20 In a further embodiment of the mirror as described in connection with Fig. 12c the coating C2 of the mirror covers the mirror body MB_k except in the area of the reflective surface MS_k . Further, advantageously the body MB_k of the optical element M_k is semitransparent to an IR radiation and the resistive coating C2 is coated on a reflective coating C coated on or on almost the entire surface of the body MB_k . Thus a mirror with the features as described in
25 connection with Fig. 12b can be achieved. For this reason, preferably the reflective coating C reflects IR radiation inside the body MB_k . In a further preferred embodiment of the mirror the mirror body MB_k comprises a surface area 1004, 1006 which is not coated with the coatings C and C2, or it comprises a surface area 1004, 1006 with a coating which is semitransparent to the IR radiation. These embodiments of the mirror have the advantage

that an IR radiation can be coupled into the mirror body MB_k at these surface areas 1004, 1006. The surface area 1004, 1006 is preferably arranged on the side of the body MB_k with the reflective surface MS_k . and optionally the surface area 1004, 1006 surrounds the reflective surface MS_k .

5

In a further preferred embodiment of the mirror as described in connection with Fig. 12c the surface area 1004, 1006 comprises a surface roughness to scatter an IR radiation into the body, or the surface area comprises a diffractive structure to distribute an IR radiation within the body MB_k by diffraction. Further, the resistive coating C2 preferably comprises a metal
10 and also preferably the reflective and the resistive coating C, C2 comprise the same metal.

As mentioned above the present invention also relates to a seventh projection lens to make use of the advantages as described in connection with Fig. 12c. The seventh projection lens of an EUV-lithographic projection exposure system comprises a plurality of reflective optical
15 elements M_i which comprises a body MB_i and a reflective surface MS_i for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. The EUV light is reflected from the reticle while the reticle is illuminated by an illumination system of the EUV-lithographic projection exposure system. In addition at least
20 one reflective optical element M_k comprises the features of the above described embodiments of the mirror of the present invention in connection with Fig. 12c. Further, the optical element M_k is optionally connected to an actuator for its translational movement. In a further embodiment the seventh projection lens comprises a cooler 350 which is located on a side of the body MB_k of the at least one optical element M_k , wherein the side is
25 opposite to its reflective surface MS_k . Optionally a distance of the cooler 350 to the at least one reflective optical element M_k is adjustable for the control of the heat transfer between these elements.

A further embodiment of the seventh projection lens according to this invention comprises a
30 pressure control system for the control of the pressure Δp within a surrounding of the at

least one reflective optical element M_k , which comprises the features of the above described embodiments of the mirror of the present invention in connection with Fig. 12c. Further, the pressure control system optionally comprises a gas inlet and/or a gas outlet nearby the at least one optical element M_k .

5

In a further embodiment of the seventh projection lens, the projection lens heats up without heating the resistive coating C2 which is on the body MB_k , if the reflective surface MS_k is exposed with EUV light. The EUV light is reflected by the illuminated reticle and comprises a spatial distribution of angular, polarization and intensity in accordance with an illumination setting, resulting in a temperature distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{Ref})$ of the body MB_k relative to a reference temperature T_{Ref} . The temperature distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{Ref})$ comprises an average and maximum temperature ΔT_{kav} and ΔT_{kmax} . Further, the zero cross temperature T_{Ok} of the mirror body MB_k is selected higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature $\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$, expressed as $T_{Ok} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref})$ or $T_{Ok} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref})$. Further also in the seventh projection lens any manufacturing tolerances of the zero cross temperature may be considered. In such an embodiment of the seventh projection lens the material with the zero cross temperature T_{Ok} varies regarding its real value of the zero cross temperature due to manufacturing, which results in a manufacturing tolerance ΔT_{Ok} such that the real value is within the interval $T_{Ok} \pm \Delta T_{Ok}$. In such a case the zero cross temperatures T_{Ok} is selected higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature ($\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$). This maximum is additionally increased by the absolute value of the manufacturing tolerance ΔT_{Ok} , expressed as $T_{Ok} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref}) + |\Delta T_{Ok}|$, $T_{Ok} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref}) + |\Delta T_{Ok}|$.

25

20

30

In a preferred embodiment of the seventh projection lens (and its various embodiments) the temperature T_k of the optical element M_k is controlled to its value by heating the resistive coating C2 with a first electrical power of the voltage source at a time before the projection

lens is subjected to the exposure power of the EUV light. Further, during the time when subjecting the projection lens to the exposure power of the EUV light the electrical power for heating the resistive coating C2 preferably is less than the first electrical power.

Fig. 12d schematically shows a further embodiment of the present invention in which a reflective optical element or a mirror M_k , 421 is at least partly heated by a multi-zone wire grid 1050 which is arranged nearby the reflective surface MS_k . Such a reflective element or mirror can be manufactured with a process which comprises the following essential steps:

1. Preferably as a body material MB_k a material with a high zero cross temperature T_{0k} is chosen as used e.g. in at least one of the embodiments described in this description. As an example, at least one zero cross temperature of the body material is 30°C or above.

2. The wire grid 1050 is produced on the body material, e.g. by forming a thin resistive coating on the surface of the body material MB_k by an electro-plating process. The resistive coating may be or may comprise Invar.

3. Various pattern structures 1051 are etched into the resistive coating which forms the structure of the multi-zone wire grid 1050. This is done by application of known lithographic methods.

4. The various pattern structures 1051 are electrically connected to form a multiplexable integrated circuit.

5. The pattern structures 1051 which forms the electrical circuit are covered by an insulating layer 1052 with a low CTE, like quartz, such that the integrated circuit is fully covered.

6. The surface of the insulating layer 1052 is polished to the surface figure accuracy which is required for the reflective element or mirror M_k .

7. The polished insulating layer 1052 is covered with a multi-layer reflective coating 1054, whereby an optional compaction layer 1053 can be between the insulating layer 1052 and the reflective coating 1054 which forms the reflective surface MS_k .

In a preferred embodiment of the reflective element or mirror the area which is covered by of the multi-zone wire grid is about 50%, even up to 95% of the area of the reflective surface

MS_k , as schematically shown in Fig. 12d. Even a higher coverage is preferred. This has the advantage that the heat which is generated along the wires of the wire grid is deposited on a large area of the body material.

The reflective optical element with the wire grid has the advantage that it can be heated
5 without any additional heater 300 as mentioned in the various embodiments above. For example, during the start up of the EUV-lithographic projection exposure system the optical element can be heated up to its zero cross temperature before the EUV projection lens is exposed with the EUV projection beam. This results in the advantages as described in connection with the above second projection lens. The main advantage of the wire grid is
10 that it can control the temperature very close at the reflective surface MS_k . If the EUV projection beam has a non-uniform intensity distribution on the reflective surface and as a consequence is heating this surface in a non-uniform way than the wire grid will be controlled e.g. by the control system 200 such to reduce the heating power at locations with large EUV intensity or large EUV absorption, and it will increase the heating power at
15 locations with low or zero EUV absorption. With such a regulation an almost constant temperature profile across the reflective surface of the mirror or reflective optical element can be achieved which results in almost no thermal induced aberration.

Further, the wire grid can also be used to measure the temperature with a spatial resolution
20 which is defined by the grid structure. For the temperature measurement the electrical resistance of the wires is measured which is related to the temperature.

Further, the optical element with the wire grid can be used with other heating and tempering concepts as described herein. For example, the optical element with the wire grid
25 can be combined with a heater and cooler as described with Fig. 10. In this case the wire grid can be used to just control very small temperature variations nearby the reflective surface MS_k . Further, the heater 300 of the embodiment as shown in Fig. 10 may be controlled or partially controlled by the wire grid resistance values.

An additional advantage of such a combined system is that the temperature control system can be simpler, because no feed-forward control is necessary. This is because the surface temperature of the reflective surface can be adjusted very quick with the wire grid heater if this heater just controls a small temperature range around the zero cross temperature of the mirror material and if other heaters or heating concepts heat the mirror close to this zero cross temperature.

Due to the advantages which are described in connection with the embodiments of a projection lens with a mirror or reflective optical element as described in connection with Fig. 12d, the present invention also relates to a **eight projection lens** and to a mirror with the described wire grid 1050 used therein.

As mentioned, the present invention relates to a mirror with a wire grid, the mirror comprises a body MB_k and a reflective surface MS_k . Further, the body MB_k comprises a material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0k} , wherein at least a part of the surface of the body MB_k comprises a wire grid 1050 for electrically resistive heating of the body MB_k . In addition the mirror is preferably adapted for usage in a projection lens of an EUV-lithographic projection exposure system for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. Further, the wire grid 1050 of the mirror is formed by a resistive coating with a coating material and the coating material is selected from the group consisting of: metal, semiconductor material, a material comprising carbon and invar.

Preferably the wire grid 1050 of the mirror comprises a pattern structure 1051 with at least $N > 1$ electrical circuits. Preferably the pattern structure 1051 comprises at least $N+1$ electrical connectors to connect the N electrical circuits to an electrical power source to subject the N electrical circuits with an electrical power. Preferably the N electrical circuits can be independently controlled from each other regarding its electrical power to which they are subjected. Further, the heating power of the wire grid 1050 is between 0,01 W and 5 W, preferably between 0,01 W and 1 W. The mirror with the wire grid 1050 is connected to

at least one electrical power source. The electrical power source may be attached to the mirror body MB_k or the electrical power source is electrically connecting the mirror body MB_k e.g. by a wire or by wires. Further the electrical power source comprises at least two voltage and/or current sources. In addition the electrical power source may comprise a

5 multiplexer circuit. With the multiplexer circuit the N electrical circuits of the wire grid are sequentially subjected with electrical power from the power source. Further, the mirror with the wire grid in accordance with the present invention comprises an insulating layer 1052, wherein the pattern structure 1051 of the wire grid 1050 is covered by the insulating layer 1052. The insulating layer 1052 comprises a low CTE material. Further, the insulating layer

10 1052 is polished such to having surface figure data within an accuracy of ± 3 nm RMS as required for the reflective surface MS_k of the mirror. To improve the reflectivity of the mirror for EUV light, the reflective surface MS_k of the mirror with the wire grid 1050 comprises a multilayer stack 1054 which is arranged above the insulating layer 1052, or which is arranged above a compaction layer 1053. The compaction layer 1053 is arranged above the insulating

15 layer 1052. Preferably the wire grid 1050 of the mirror covers more than 50% of the area of the reflective surface MS_k .

Further, the above described mirror with the wire grid 1050 can be modified such that the mirror comprises also features of the mirrors as described in connection with Fig. 12b and

20 Fig. 12c. As an example, the body MB_k of the mirror is at least partly coated with a resistive coating C2 except in the area of the reflective surface MS_k . The resistive coating C2 has an electrical resistance suitable to heat the mirror body MB_k by electrical resistive heating. Alternative or in addition the body MB_k of the optical element M_k is semitransparent to an IR radiation. If so, advantageously the body MB_k of the mirror comprising a reflective coating C

25 coated on or on almost the entire surface of the body MB_k , wherein the reflective coating C reflects IR radiation inside the body MB_k . In a further embodiment of the mirror with the wire grid in accordance to this invention a resistive coating C2 is on the reflective coating C. In this case the mirror can be heated by IR radiation (due to the coating C) and/or by resistive heating due to the coating C2, wherein the area close to the reflective surface MS_k

30 is headed with the wire grid 1051. For the heating of the mirror with IR radiation the mirror

advantageously comprises a surface area 1004, 1006 which is not coated with the reflective coating C and the resistive coating C2, or it comprises a surface area 1004, 1006 with a coating which is semitransparent to the IR radiation. This surface area 1004, 1006 advantageously can be used for the coupling in of an IR radiation into the body MB_k , wherein the IR radiation contributes to the heating of the mirror. Preferably the mirror with the reflective coating C or the resistive coating C2 comprises a metal in the coating layer, preferably the metal is the same for the reflective and the resistive coating C, C2, if both coatings are applied. Further, the surface area 1004, 1006, for coupling in an IR radiation into the body MB_k , is arranged on the side of the body MB_k with the reflective surface MS_k , or on a the surface area 1004, 1006 which surrounds the reflective surface MS_k . Such a surface area 1004, 1006 advantageously may comprise a surface roughness to scatter the IR radiation into the body, or the surface area 1004, 1006 may comprises a diffractive structure to distribute the IR radiation within the body MB_k by diffraction.

- 15 As mentioned above the present invention also relates to a eighth projection lens to make use of the advantages as described in connection with Fig. 12d and the advantages of the mirror which comprises a wire grid 1050 and its various embodiments as discussed above.

In a first embodiment of the eighth projection lens of an EUV-lithographic projection exposure system, comprises a plurality of reflective optical elements M_i . Each reflective optical elements M_i comprises a body MB_i and a reflective surface MS_i for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm. The EUV light is reflected from the reticle while the reticle is illuminated by an illumination system of the EUV-lithographic projection exposure system. Further, the eighth projection lens comprises at least one reflective optical element M_k which comprises the features of the mirror comprising the wire grid 1050 in accordance to one of the above described embodiments of this mirror. Further, since one reflective optical element M_k with the features of the mirror with the wire grid 1050 is heatable, it is advantageous to connect

the optical element M_k to an actuator for its translational movement. Further, in an embodiment of the eighth projection lens the lens comprises a cooler 350 or a first tempering element 300 which is located on a side of the body MB_k of the at least one optical element M_k which is opposite to its reflective surface MS_k . Optionally a distance of the cooler 350 or the first tempering element 300 to the at least one reflective optical element M_k is adjustable for the control of the heat transfer between these elements. In a further embodiment of the eighth projection lens the lens comprises a pressure control system for the control of the pressure Δp within a surrounding of the at least one reflective optical element M_k . Preferably the pressure control system comprises a gas inlet and/or a gas outlet nearby the at least one optical element M_k .

In a further embodiment the eighth projection lens comprises a material selection such that without heating the wire grid 1050 on the body MB_k , the exposure of the reflective surface MS_k with EUV light, which is reflected by the illuminated reticle and which comprises a spatial distribution of angular, polarization and intensity in accordance with an illumination setting, results in a temperature distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{Ref})$ of the body MB_k with the temperature $T_k(x,y,z)$ relative to a reference temperature T_{Ref} . The temperature distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{Ref})$ comprises an average and maximum temperature ΔT_{kav} and ΔT_{kmax} . Further the zero cross temperature T_{Ok} of the body MB_k is selected higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature ($\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$), expressed as $T_{Ok} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref})$ or $T_{Ok} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref})$.

Usually the material with the zero cross temperature T_{Ok} varies regarding its real value of the zero cross temperature due to manufacturing issues. For this reason a further preferred embodiment of the eighth projection lens considers that the material with the zero cross temperature T_{Ok} varies regarding its real value of the zero cross temperature due to manufacturing, which result in a manufacturing tolerance ΔT_{Ok} such that the real value is within the interval $T_{Ok} \pm \Delta T_{Ok}$. In this embodiment the zero cross temperatures T_{Ok} is selected higher than the maximum of the reference temperature T_{Ref} and the respective average or

maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature ($\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$), and the maximum is further increased by the absolute value of the manufacturing tolerance ΔT_{Ok} , expressed as $T_{Ok} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref}) + |\Delta T_{Ok}|$, $T_{Ok} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref}) + |\Delta T_{Ok}|$.

5

In a further embodiment of the eighth projection lens the temperature T_k of the optical element M_k is controlled to its value by heating the wire grid 1050 with a first electrical power of the electrical power source at a time before the projection lens is subjected to the exposure power of the EUV light. Optionally, during the time when subjecting the projection

10 lens to the exposure power of the EUV light, the electrical power for heating the wire grid 1050 is selected less than the first electrical power. Further, the eighth projection lens may comprise a controller for controlling the electrical power to which the wire grid 1050 is subjected, or for determining a resistance value of the wire grid 1050, or a resistance value of at least one of the electrical circuits of the pattern structure 1051. Further, optionally the

15 controller controls the temperature of the first tempering element 300 or the cooler 350. Further optionally the controller controls a distance of the first tempering element 350 or the cooler 300 to the at least one reflective optical element M_k , or the controller controls the pressure Δp within the surrounding of the optical element M_k . In general the control is based on a parameter selected from the group consisting of: temperature, resistance value

20 of the wire grid 1050 or the resistance value of at least one electrical circuit of the pattern structure 1051 of the wire grid 1050, time, a parameter which directly or indirectly influence the temperature of the optical element M_k , an illumination setting, a change of the exposure power of the EUV light, a change of the reticle, thermally or mechanically induced optical aberration data of the optical element M_k or the projection lens and an output parameter

25 from a model. Further, the controller preferably controls the temperature of the reflective surface MS_k , or the body MB_k of the mirror M_k to the zero cross temperature T_{Ok} . In a further embodiment of the eighth projection lens the zero cross temperature T_{Ok} is selected lower than a reference temperature T_{Ref} , or it is selected such that it is at least 6 K higher than a reference temperature T_{Ref} .

Fig. 13 schematically shows several further embodiments of heaters or tempering means 300 in relation with a reflective element or mirror M_k , 421 in accordance with the present invention. Also with these embodiments the temperature of the reflective element or mirror M_k , 421 can be controlled to an operation temperature, averaged temperature or zero cross temperature T_{avk} , T_{0k} according to the above teachings, especially to reduce any optical aberration caused by thermal effects. The various embodiments of the heater or tempering means 300 which will be described below can be used alone or in any combination to control the mentioned temperatures or the aberration of the reflective optical element or mirror.

The mirror e.g. 421 (like the ones shown in Fig. 4 and Fig. 5) or a reflective element M_k is mounted to a support element 480 which is connected to a housing structure 481. The mounting elements and support means which support or suspend the mirror or the reflective optical element are not shown. These can be made as e.g. described in Fig. 4 with the reference numerals 451, 461, 471. Further, as described in the embodiment of Fig. 10 and Fig. 11 a cooler 350 can be used as an option to protect the support element 480 and/or the housing structure 481 (which can be temperature sensitive elements). As a further option also the pressure Δp of the surrounding of the mirror 421 or the reflective optical element may be controlled to adjust the thermal resistance of the gas, as described with Fig. 11. If the body MB_k of the reflective element or mirror M_k , 421 comprises a material with a temperature dependent CTE(T) which comprises at least one zero cross temperature T_0 , like e.g. Zerodur® or ULE®, and if this material is transparent to light of a certain wavelength like IR light, then the body may be heated with such light as it was described in connection with Fig. 12a and Fig. 12b. This kind of heating has the advantage that the heat is not only deposited on the surface of the body MB_k but it is also deposited inside the body.

As sources for IR light, e.g. light emitting diodes (LEDs) 1302 may be used. The usage of LEDs have the advantage that they easily can be arranged about side by side in at least one dimension, to form an array-like arrangement as it was already mention in the context of the Peltier elements of Fig. 10. Further, a suitable optical arrangement can be used to configure

the IR radiation which is emitted from the LEDs in such a way that it can be coupled into the reflective element or the mirror M_k , 421 under various conditions. As an example the optical arrangement 1304 is such that the IR light from LED is collected and made about parallel. This has the advantage that a defined area of the surface of the body MB_k is illuminated with

5 IR light. Optionally this surface area can be adjusted in diameter, depending on the number of LEDs which are in operation. If such LEDs with such an optical arrangement are forming a grid to illuminate the body MB_k in a grid- or matrix-like form. The grid-like form has the advantage that IR energy is deposited as a function of the grid-coordinates which result in a much defined spatial temperature distribution $T(x,y)$ as a function of x and y . As a further

10 option, the optical arrangement 1306 of the IR source, e.g. the lenses in front of the LEDs, may be adjustable to generate a focus length and/or vary the focus length 1307. With a focused IR light the body can be heated at a very local point inside. With this feature the spatial temperature distribution inside the body can be adjusted in x -, y - and z -direction. If the direction of the IR light can be also adjusted by tilting the IR beam around at least one

15 axis, preferably around the x - and the y -axis, then IR light of several IR beams can be focused in a narrow region within the body MB_k . This advantageously can be used to homogenize a temperature distribution $T(x,y,z)$ of the body which results from e.g. a certain reticle or illumination setting. In a preferred embodiment the focus length 1309 is adjusted by the optical arrangement 1308 in such a way that it is very close to the reflective surface MS_k . In

20 addition an absorption layer (not shown) may be arranged below the reflective surface which absorbs the IR light. In this case the energy of the IR light is deposited very close to the reflective surface MS_k .

As an alternative to the above described optical arrangement arrangements optical fibers

25 1310 may be used to transfer the IR light from the source (e.g. IR LEDs or an IR Laser) to close to the surface of the body MB_k . By the usage of the fibers the IR light of one IR source can be distributed also in a grid-like manner. A further alternative is to use a light guiding rod 1314 to transfer the IR light from the IR source to the body.

As a further alternative an IR light source 1312 (e.g. IR LEDs, IR-Laser) is used with a mirror 1313 which reflects the IR light onto the surface of the body MB_k . Preferably the mirror can be tilted around at least one axis, better about two axes like the x- and the y-axis. With such an embodiment the IR light can be distributed over the body. This can be done e.g. by a scanning or by a raster process.

In addition the body MB_k of the reflective element or the mirror itself may comprise recesses 1315 in which the IR light is coupled in. In general the surfaces or surface areas in which the IR light is coupled into the body may be or may comprise prepared surface areas with e.g. a defined surface roughness or a diffractive structure on it. Further, the recesses may comprise surface forms like spheres to improve the incidence of the IR radiation into the body. Instead of recesses also protrusions or projections of the body material can be chosen, which all may comprise a surface curvature, to achieve a determined spatial distribution of the IR radiation within the body M_k .

15

For the embodiments of Fig. 13 also a reflective coating on the mirror body may be used to increase the absorbed IR power. For this reason also the features of the embodiment of Fig. 12b can be applied. Further, the heater 300 of the embodiments in accordance of Fig. 13 can be integrated into the cooler 350. In addition, the wavelength of the IR radiation can be controlled to control the amount of absorption within a defined thickness of the body material. For Zerodur® the wavelength may vary from about 400 nm to about 800 nm. As it can be seen from Fig. 12a, in this wavelength range the absorption strongly depends on the used wavelength.

Due to the instantaneous deposition of the IR power inside the body of the reflective element or mirror in a spatially controlled manner, the heater or tempering means 300, as described in connection with Fig. 13, are suitable to control the operation temperature of the reflective element or mirror inside a projection lens in such a way that the thermal

induced aberration is minimized in the steady state of the lens and during the warm-up time of the mirror. This time can be significantly reduced due to the instantaneous heating effect of the IR heating.

- 5 Further, with the IR heating of the body MB_k of the k-th reflective optical element or the mirror M_k of an EUV projection lens, as shown in connection with Fig. 12b and Fig. 13 as an example, it is possible to heat this body to the at least one of its zero cross temperatures very fast. Further, with such a heating the spatial temperature distribution within the body and such along its reflective surface MS_k can be controlled in at least two dimensions,
- 10 preferably in all three spatial dimensions. This means that the temperature is controllable as a function of the x-, y- and z-coordinate of the body MB_k . Regarding the control now reference is made again to Fig. 6. With such heaters as designated with 630 in Fig. 6 an EUV projection lens 20 can comprise at least one reflective element or mirror M_k , like mirror 26, which comprises a body MB_k with comprises a material with a temperature dependent
- 15 CTE(T) which has at least one zero cross temperature T_{0k} . This zero cross temperature T_{0k} is selected such that it is higher than the expected average temperature $\Delta T_{avk} + T_{Ref}$ of the element or mirror M_k if the projection lens 20 is exposed with the maximum EUV exposure power, coming from the reticle M. The zero cross temperature is even selected higher than the respective maximum temperature of all the expected temperature distributions $T(x,y,z)$
- 20 which may occur during the exposure with the EUV exposure power (see for example Fig. 7). These average and maximum temperatures ΔT_{avk} , ΔT_{kmax} also consider potential variations regarding the reticle and regarding the illumination setting. Further, also any variations of the zero cross temperatures, caused by the manufacturing like manufacturing tolerances ΔT_{0k} , may be considered in a way that such tolerances are added to the these average or
- 25 maximum temperatures ΔT_{avk} , ΔT_{kmax} before the material selection. Then a material is selected such that its zero cross temperature is even higher than this temperature, expressed as $T_{0k} > \Delta T_{kmax} + T_{Ref} + |\Delta T_{0k}|$ or $T_{0k} > \Delta T_{avk} + T_{Ref} + |\Delta T_{0k}|$. With the application of the mentioned IR heaters (or the other heaters described in this specification) it is always possible to heat the element or mirror M_k to the real zero cross temperature. A control unit
- 30 620 (Fig. 6) controls the temperature of this element M_k (like mirror 26) preferably such that

the thermal induced aberration or imaging errors 622 of the projection lens (or the element or mirror M_k) becomes to a minimum during the exposure of the lens 20 with the EUV exposure beam 4 which propagates from the reticle M to the wafer W. As an alternative the control unit 620 controls the temperature such that the spatial temperature distribution 621 on the reflective element or mirror M_k , 26 becomes homogenous, preferably that this temperature achieves the zero cross temperature T_{0k} .

Further, if the zero cross temperature is selected as described above like $T_{0k} > \Delta T_{kmax} + T_{Ref} + |\Delta T_{0k}|$ or $T_{0k} > \Delta T_{avk} + T_{Ref} + |\Delta T_{0k}|$ then preferably the body MB_k and the reflective surface for the EUV light MS_k is manufactured such that the surface shape or figure achieves the specified accuracy at the zero cross temperature T_{0k} . In this case the reflective element or mirror M_k is heated with the mentioned IR heaters 630, or other heaters as already have been described herein, to the zero cross temperature. Preferably this heating is done before the projection lens 20 is subjected to the EUV exposure power. During the exposure of the projection lens 20 with EUV light then the reflective optical element or mirror M_k is heated in addition by the absorbed EUV light. The heater 630 then is controlled by the control unit 620 such that the spatial temperature distribution of the reflective element or mirror M_k remains almost in the same condition as before the EUV light is switched on. Preferably this condition is a constant temperature of the element or mirror M_k , 26. As already mentioned, it is not necessary to control the temperature distribution 621 of the element M_k , 26 itself, alternative or in addition the aberration 622 can be used as a control parameter, and then the heater 630 is controlled such that the aberration 622 is minimized. To measure the temperature of the element M_k or mirror 26, especially the spatial temperature distribution, or a parameter or parameters which are representative for it, an infrared camera can be used, since the temperature differences due to the absorption of EUV light are in the range of about 1 K up to about 20 K, depending on the mirror 21, 22, 23, 24, 25, 26 of the lens 20 (see. e.g. Fig. 3), the used reticle or mask, the power of the EUV light and the illumination setting. Due to this relatively high temperature difference the sensitivity requirements of the IR camera are not too high.

Alternative or in addition to the measurement of the temperature or the temperature distribution of the optical element M_k or mirror 26, or its aberration 622, as a control parameter also the deformation of the optical element M_k or the mirror 26 (anyone of the mirrors 21, 22, 23, 24, 25, 26 within the lens 20) or a parameter related to the deformation
5 may be used, to control the heater 630, especially a heater 630, 300 as described herein. For a deformation measurement, as an example, an interferometer and/or an encoder system can be used to determine any deformation of the optical element or mirror.

In a further embodiment of the invention, the temperature data (especially the temperature
10 distribution data) and/or the deformation data which result from measurements as described above are used for the calculation of an expected aberration of the optical element or mirror or the lens 20. Then the lens 20 and/or the optical element M_k or the mirror 21, 22, 23, 24, 25, 26 is controlled by at least one heater 630, 300 in such a way that the aberration will be reduced. For such calculations a model is applied why the aberration
15 of the lens 20 is minimized by model based control. The model for the control of the lens 20 may use additional input parameters which are measured in addition to the temperature and/or deformation data of a given preselected mirror or optical element. Such input parameters are e.g. the used reticle or mask, the power of the EUV light, the illumination setting, a gas pressure nearby the optical element or mirror or inside the lens 20, the time
20 for which the lens 20 is exposed by EUV light or any change in position (like e.g. z-position) of a reflective optical element like a mirror 21, 22, 23, 24, 25, or 26 of lens 20. As an output parameter the model may control any heater 630, 300, any position of a reflective optical element like a mirror 21, 22, 23, 24, 25, or 26, the power of the EUV projection light, the illumination setting with which the reticle is illuminated, the gas pressure nearby the optical
25 element or mirror or the gas pressure inside the lens 20 or any actuator which deforms the reflective surface of a mirror 21, 22, 23, 24, 25 or 26 of the lens 20 in a controlled way to reduce the optical aberration. The output parameter or the output parameters are correlated to the input parameter or the input parameters by the model transfer-function. Further, the input parameters of the model may be used for model calibration such that the

model is adjusted regarding its transfer-function, meaning that the transfer-function itself depend on the values of the input parameters and/or the output parameters.

Further, in an embodiment of the present invention the temperature data of at least one
5 optical element M_k , like a mirror 21, 22, 23, 24, 25, 26 of the lens 20 are accumulated in
time. This results in a parameter which represents a measure of the thermal load of the
optical element or mirror, which could be even with spatial resolution. Such a thermal load
parameter can be used for maintenance control of the lens 20 or the EUV lithographic
exposure system. As an example, any degradation of the mirror due to EUV light, like a
10 degradation of the reflective multilayer stack or any compaction effects of the used
substrate material, forming the mirror body, may be estimated. Further, the illuminated
masks or the used illumination settings may be selected such that the spatially resolved
thermal load of the mirror 21, 22, 23, 24, 25, 26 results in a long life time of the projection
lens 20, to reduce maintenance costs.

What is claimed is:

1. A mirror comprising
 - a body MB_k and a reflective surface MS_k ,
 - the body MB_k comprising a material with a temperature dependent coefficient of thermal expansion which is zero at a zero cross temperature T_{0k} , wherein
 - at least a part of the surface of the body MB_k comprises a wire grid 1050 for electrically resistive heating of the body MB_k and
 - the mirror is adapted for a projection lens of an EUV-lithographic projection exposure system for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm.
2. The mirror of claim 1, wherein the wire grid 1050 is formed by a resistive coating with a coating material, the coating material is selected from the group consisting of metal, semiconductor material, a material comprising carbon and invar.
3. The mirror according to claim 1 or 2, wherein the wire grid 1050 comprises a pattern structure 1051 with at least $N > 1$ electrical circuits, and the pattern structure 1051 comprises at least $N+1$ electrical connectors to connect the N electrical circuits to an electrical power source to subject the N electrical circuits with an electrical power, being independently controlled from each other.
4. The mirror according to one of the claims 1 to 3, wherein the heating power of the wire grid 1050 is between 0,01 W and 1 W.
5. The mirror according to one of the claims 1 to 4, wherein the wire grid 1050 is connected to an electrical power source selected from the group consisting of an electrical power source attached to the mirror body MB_k and an electrical power

source electrically connecting the mirror body MB_k by a wire.

6. The mirror according to claim 5, wherein the electrical power source comprises at least two voltage and/or current sources or a multiplexer circuit.

5

7. The mirror in accordance to one of the claims 3 to 6, wherein the pattern structure 1051 of the wire grid 1050 is covered by an insulating layer 1052, comprising a low CTE material.

- 10 8. The mirror in accordance to claim 7, wherein the insulating layer 1052 is polished, having surface figure data within an accuracy of ± 3 nm RMS as required for the reflective surface MS_k of the mirror.

- 15 9. The mirror according to claim 8, wherein the reflective surface MS_k comprises a multilayer stack 1054 being arranged above the insulating layer 1052, or being arranged above a compaction layer 1053 arranged above the insulating layer 1052.

- 10 10. The mirror in accordance to one of the claims 1 to 9, wherein the wire grid 1050 covers more than 50% of the area of the reflective surface MS_k .

20

11. The mirror according to one of the claims 1 to 10, wherein the body MB_k is at least partly coated with a resistive coating C2 except in the area of the reflective surface MS_k , wherein the resistive coating C2 has an electrical resistance suitable to heat the body MB_k by electrical resistive heating.

25

12. The mirror according to one of the claims 1 to 11, wherein the body MB_k of the optical element M_k is semitransparent to an IR radiation, the body MB_k comprising a reflective coating C coated on or on almost the entire surface of the body MB_k , wherein the reflective coating C reflects IR radiation inside the body MB_k .

30

13. The mirror according to claim 11 and claim 12, wherein the resistive coating C2 is on the reflective coating C.
14. The mirror according to claim 12 or 13, wherein the body MB_k comprises a surface area 1004, 1006 being not coated with the reflective coating C and the resistive coating C2, or comprises a surface area 1004, 1006 with a coating being semitransparent to the IR radiation, for coupling in an IR radiation into the body MB_k .
15. The mirror according to one of the claims 12 to 14, wherein the reflective coating C or the resistive coating C2 comprises a metal.
16. The mirror according to one of the claims 13 to 15, wherein the reflective and the resistive coating C, C2 comprise the same metal.
17. The mirror according to claim 14 to 16, wherein the surface area 1004, 1006 is arranged on the side of the body MB_k with the reflective surface MS_k , or wherein the surface area 1004, 1006 surrounds the reflective surface MS_k .
18. The mirror according to one of the claims 14 to 17, wherein the surface area 1004, 1006 comprises a surface roughness to scatter an IR radiation into the body, or the surface area 1004, 1006 comprises a diffractive structure to distribute an IR radiation within the body MB_k by diffraction.
19. A projection lens of an EUV-lithographic projection exposure system, comprising
- a plurality of reflective optical elements M_i , each comprising
 - a body MB_i and a reflective surface MS_i for projecting an object field on a reticle onto an image field on a substrate if the projection lens is exposed with an exposure power of EUV light with a wavelength in a wavelength range of less than 50 nm, being reflected from the reticle while illuminated by an illumination system of the EUV-lithographic projection exposure system, wherein

- at least one reflective optical element M_k comprises the features of the mirror in accordance to one of the claims 1 to 18.

20. The projection lens according to claim 19, wherein the optical element M_k is connected
5 to an actuator for its translational movement.

21. The projection lens according to one of the claims 19 to 20, comprising a cooler 350 or
a first tempering element 300 located on a side of the body MB_k of the at least one
optical element M_k which is opposite to its reflective surface MS_k .

22. The projection lens according to claim 21, wherein a distance of the cooler 350 or the
first tempering element 300 to the at least one reflective optical element M_k is
adjustable for the control of the heat transfer between these elements.

23. The projection lens according to one of the claims 19 to 22, comprising a pressure
control system for the control of the pressure Δp within a surrounding of the at least
one reflective optical element M_k ,

24. The projection lens according to claim 23, wherein the pressure control system
comprises a gas inlet and/or a gas outlet nearby the at least one optical element M_k .

25. The projection lens according to one of the claims 19 and 24, wherein

- without heating the wire grid 1050 on the body MB_k , the exposure of the
reflective surface MS_k with EUV light, being reflected by the illuminated reticle
and comprising a spatial distribution of angular, polarisation and intensity in
accordance with an illumination setting, resulting in a temperature
distribution $\Delta T_k(x,y,z) = (T_k(x,y,z) - T_{Ref})$ of the body MB_k with the temperature
 $T_k(x,y,z)$ relative to a reference temperature T_{Ref} with an average and
maximum temperature ΔT_{kav} and ΔT_{kmax} , and wherein
- the zero cross temperature T_{Ok} is higher than the maximum of the reference
temperature T_{Ref} and the respective average or maximum temperature based

on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature ($\Delta T_{kav} + T_{ref}$ or $\Delta T_{kmax} + T_{ref}$), expressed as $T_{0k} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref})$ or $T_{0k} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref})$.

5 26. The projection lens according to claim 25, wherein

- the material with the zero cross temperature T_{0k} varies regarding its real value of the zero cross temperature due to manufacturing, resulting in a manufacturing tolerance ΔT_{0k} such that the real value is within the interval $T_{0k} \pm \Delta T_{0k}$, and wherein

- 10 the zero cross temperatures T_{0k} is higher than the maximum of the reference temperature T_{Ref} and the respective average or maximum temperature based on the spatial temperature distribution $\Delta T_k(x,y,z)$ added by the reference temperature ($\Delta T_{kav} + T_{Ref}$ or $\Delta T_{kmax} + T_{Ref}$), the maximum is increased by the absolute value of the manufacturing tolerance ΔT_{0k} , expressed as $T_{0k} > \max(T_{Ref}, \Delta T_{kav} + T_{Ref}) + |\Delta T_{0k}|$, $T_{0k} > \max(T_{Ref}, \Delta T_{kmax} + T_{Ref}) + |\Delta T_{0k}|$.

27. The projection lens according to one of the claims 19 to 26, wherein the temperature T_k of the optical element M_k is controlled to its value by heating the wire grid 1050 with a first electrical power of the electrical power source at a time before the projection lens is subjected to the exposure power of the EUV light.

28. The projection lens according to claim 27, wherein during the time when subjecting the projection lens to the exposure power of the EUV light the electrical power for heating the wire grid 1050 is less than the first electrical power.

25

29. The projection lens according to one of the claims 19 to 28, comprising a controller for controlling the electrical power to which the wire grid 1050 is subjected, or for determining a resistance value of the wire grid 1050, or a resistance value of at least one of the electrical circuits of the pattern structure 1051.

30

30. The projection lens according to claim 29 and one of the claims 21 to 28, wherein the controller controls the temperature of the first tempering element 300 or the cooler 350, or


wherein the controller controls a distance of the first tempering element 350 or the cooler 300 to the at least one reflective optical element M_k , or wherein the controller controls the pressure Δp within the surrounding of the optical element M_k , wherein the control is based on a parameter selected from the group consisting of

- temperature,
- resistance value of the wire grid 1050 or the resistance value of at least one electrical circuit of the pattern structure 1051 of the wire grid 1050,
- time,
- a parameter which directly or indirectly influence the temperature of the optical element M_k ,
- an illumination setting,
- a change of the exposure power of the EUV light
- a change of the reticle,
- thermally or mechanically induced optical aberration data of the optical element M_k or the projection lens
- and an output parameter from a model.



31. The projection lens according to claim 29 or 30, wherein the controller controls the temperature of the reflective surface MS_k , or the body MB_k of the mirror M_k to the zero cross temperature T_{0k} .

32. The projection lens according to claim 31, wherein the zero cross temperature T_{0k} is lower than a reference temperature T_{Ref} , or is at least 6 K higher than a reference temperature T_{Ref} .

1/19

FIG.1

2/19

**FIG. 2a****FIG. 2b**




Fig. 3c




Fig. 3a






Fig. 3b


4/19

**Fig. 3d**

5/19

**Fig. 3e**

6/19

**Fig. 3f**






Fig. 3g


8/19

**Fig. 3h**

9/19

**Fig. 3i**

10/19

**Fig. 3k**

11/19






Fig. 31

12/19

FIG.4

13/19

FIG.5








Fig. 6



15/19

FIG.7**FIG.8**

16/19

FIG.9**FIG.10**

17/19

FIG.11**FIG.12a**

18/19



FIG.12b**FIG.12c**

FIG.12d





FIG.13



INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2011/062995

A. CLASSIFICATION OF SUBJECT MATTER

INV. G03F7/20 G21K1/06 G02B5/08
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

G03F G21K G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EP0-Internal, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 1 569 036 A2 (CANON KK [JP]) 31 August 2005 (2005-08-31) paragraphs [0051] - [0060]; figures 1, 6 -----	1-17, 19-32
Y	EP 1 372 009 A1 (ASMLHOLDING N V [NL] ASML HOLDING NV [NL]) 17 December 2003 (2003-12-17) paragraphs [0009], [0011] - [0019], [0063], [0064], [0068] - [0073]; figures 1, 7c -----	1-17, 19-32
Y	US 2004/165161 A1 (HARA SHINICHI [JP]) 26 August 2004 (2004-08-26) claim 23; figure 9 -----	23,24



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

10 November 2011

Date of mailing of the international search report

21/11/2011

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Eisner, Klaus

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2011/062995

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1569036	A2	31-08-2005	EP 1569036 A2	31-08-2005
			US 2005190347 A1	01-09-2005

EP 1372009	A1	17-12-2003	CN 1495529 A	12-05-2004
			DE 60308758 T2	16-08-2007
			EP 1372009 A1	17-12-2003
			JP 3786652 B2	14-06-2006
			JP 2004031952 A	29-01-2004
			SG 107662 A1	29-12-2004
			TW I273344 B	11-02-2007
			US 2003231415 A1	18-12-2003
			US 2005254154 A1	17-11-2005

US 2004165161	A1	26-08-2004	JP 4311711 B2	12-08-2009
			JP 2004259778 A	16-09-2004
			US 2004165161 A1	26-08-2004
