



(22) Date de dépôt/Filing Date: 1992/06/26

(41) Mise à la disp. pub./Open to Public Insp.: 1992/12/28

(45) Date de délivrance/Issue Date: 2002/09/03

(30) Priorités/Priorities: 1991/06/27 (3-183272) JP;
1991/09/27 (3-276673) JP

(51) Cl.Int.⁵/Int.Cl.⁵ C08F 4/649, C08F 10/00

(72) Inventeurs/Inventors:

Tajima, Yoshio, JP;
Kataoka, Naoki, JP;
Numao, Yosuke, JP;
Seki, Takashi, JP;
Matsuura, Kazuo, JP

(73) Propriétaire/Owner:

NIPPON MITSUBISHI OIL CORPORATION, JP


(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : CONSTITUANTS DE CATALYSEURS POUR LA POLYMERISATION D'OLEFINES

(54) Title: CATALYSTS COMPONENTS FOR POLYMERIZATION OF OLEFINS

(57) Abrégé/Abstract:

A catalyst component is disclosed for use in the homo- or copolymerization of olefinic hydrocarbons. The catalyst component is comprised of a first compound of the formula $\text{Me}^1(\text{OR}^1)_p \text{R}^2 \text{X}^1_{4-p-q}$, a second compound of the formula $\text{Me}^2(\text{OR}^3)_m \text{R}^4 \text{X}^2_{z-m-n}$ and a third compound which is an organocyclic compound having two or more conjugated double bonds. A process is also disclosed for the production of hydrocarbon polymers in which the above catalyst component is combined with a modified organoaluminum compound to form a catalyst composition capable of providing controlled molecular weight, wide distribution thereof and other desirable qualities in the polymer product.



2072476

ABSTRACT OF THE DISCLOSURE

A catalyst component is disclosed for use in the homo- or copolymerization of olefinic hydrocarbons. The catalyst component is comprised of a first compound of the formula $\text{Me}^1(\text{OR}^1)_p\text{R}^2_q\text{X}^1_{4-p-q}$, a second compound of the formula $\text{Me}^2(\text{OR}^3)_m\text{R}^4_n\text{X}^2_{z-m-n}$ and a third compound which is an organocyclic compound having two or more conjugated double bonds. A process is also disclosed for the production of hydrocarbon polymers in which the above catalyst component is combined with a modified organoaluminum compound to form a catalyst composition capable of providing controlled molecular weight, wide distribution thereof and other desirable qualities in the polymer product.

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to catalyst components for use in the polymerization of olefinic hydrocarbons. The invention is also directed to a process for the manufacture of olefinic polymers in which the aforesaid catalyst components are employed.

Prior Art

Catalyst compositions comprising zirconium compounds, typically metallocene, and almoxane are known for use in the homopolymerization of olefins such as ethylene or the copolymerization of ethylene/alpha-olefins as disclosed for example in Japanese Laid-Open Patent Publication No. 58-19309. While the disclosed prior art process is advantageous so far as concerns the availability of polymerized products at increased rate of yield, it has a drawback in that the polymers obtained have a relatively low molecular weight and further that they, if homopolymeric, have a relatively narrow molecular weight distribution. When taking into account the molecular weight alone, it would be possible to increase the molecular weight of a polymer to some extent by making a proper selection of transition metals from among the group of metallocene. It has been proposed to use dicyclopentadienyl hafnium as disclosed for example in Japanese Laid-Open Patent Publication No. 63-251405. However, hafnium compounds are not only difficult to synthesize but also less active


compared to dicyclopentadienyl zirconium. The use of dicyclopentadienyl hafnium would not provide any appreciable increase in the breadth of molecular weight distribution of the polymer produced, or would not help in providing sufficiently narrow composition distribution of the polymer when the latter is a copolymer.

SUMMARY OF THE INVENTION

With the foregoing drawbacks of the prior art in view, the present invention seeks to provide novel catalyst components which, when combined with a promoter such as an organoaluminum compound, will greatly contribute to the production of polyolefins having a controlled level of molecular weight distribution and a relatively narrow composition distribution where the polyolefin is a copolymer.


The invention also seeks to provide a process for the homopolymerization or copolymerization of olefinic hydrocarbons in which there is used a catalyst composition comprising a novel catalyst component and a promoter which has enhanced catalytic activity per given transition metal and is capable of providing olefinic polymers having a relatively high molecular weight.

According to the invention, there is provided a catalyst component comprising a compound (A) of the formula




where R^1 and R^2 each are hydrocarbon moieties of 1 - 24 carbon atoms; X^1 is a halogen atom; Me^1 is Ti, Zr or Hf;

p is $0 \leq p \leq 4$; q is $0 \leq p < 4$; and p+q is $0 \leq p+q \leq 4$, a compound (B) of the formula




where R^3 and R^4 each are hydrocarbon moieties of 1 - 24 carbon atoms; X^2 is a halogen atom; Me^2 is an element included in Groups I - III of the Periodic Table; z is a valence of Me^2 ; m is $0 \leq m \leq 3$; n is $0 \leq n < 3$; and m+n is $1 \leq n+m \leq 3$, and an organocyclic compound (C) having two or more conjugated double bonds.

A polymerization process according to the invention comprises homopolymerizing or copolymerizing olefinic hydrocarbons in the presence of a catalyst composition comprising a catalyst component comprising a compound (A) of the formula



where R^1 and R^2 each are hydrocarbon moieties of 1 - 24 carbon atoms; X^1 is a halogen atom; Me^1 is Ti, Zr or Hf; p is $0 \leq p \leq 4$; q is $0 \leq p < 4$; and p+q is $0 \leq p+q \leq 4$, a compound (B) of the formula



where R^3 and R^4 each are hydrocarbon moieties of 1 - 24 carbon atoms; X^2 is a halogen atom; Me^2 is an element included in Groups I - III of the Periodic Table; z is a valence of Me^2 ; m is $0 \leq m \leq 3$; n is $0 \leq n < 3$; and m+n is $1 \leq n+m \leq 3$, and an organocyclic compound (C) having two or more conjugated double bonds, and a modified organoaluminum compound having Al-O-Al bonds.


It has now been found that in addition to the above mentioned features, the use of the inventive catalyst

component provides a copolymer, typically an ethylene/alpha-olefin copolymer, which may be formed into sheets or films that are free from sticking with each other.

DETAILED DESCRIPTION OF THE INVENTION

The catalyst component of the invention is, as above described, comprised of Compound (A) and Compound (B) which are contacted together.

Compound (A) is represented by the general formula



R^1 and R^2 respectively designate separate hydrocarbon moieties each having a carbon number 1 - 24, preferably 1 - 12, more preferably 1 - 8, which include alkyl groups such as methyl, propyl, butyl, pentyl, hexyl and octyl, alkonyl groups such as vinyl and allyl, aryl groups such as phenyl, tryl and xylyl and aralkyl groups such as benzyl, phenetyl styryl and neophyl. If there are more than two members R^1 and R^2 , they may be the same or different.

X^1 is a halogen atom such as fluorine, iodine, chlorine and bromine. Me^1 designates zirconium Zr, titanium Ti and hafnium Hf, of which Zr is preferred. n is $0 \leq n \leq 4$, preferably $0 < n \leq 4$.

Specific examples of Compound (A) include tetramethyl zirconium, tetraethyl zirconium, tetrapropyl zirconium, tetra-n-butyl zirconium, tetrapentyl zirconium, tetraphenyl zirconium, tetraatolyl zirconium, tetrabenzyl zirconium, tetramethoxy zirconium, tetraethoxy zirconium, tetrapropoxy

zirconium, tetrabutoxy zirconium, tetraphenoxy zirconium,
tetratolyoxy zirconium, tetrapentyloxy zirconium,
tetrabenzoyloxy zirconium, tetraallyl zirconium, tetraneophyl
zirconium, trimethylmonochlorozirconium,
triethylmonochlorozirconium, tripropylmonochlorozirconium,
tri-n-butylmonochlorozirconium, tribenzylmonochlorozirconium,
dimethyldichlorozirconium, diethyldichlorozirconium,
di-n-butyldichlorozirconium, dibenzoyldichlorozirconium,
monomethyltrichlorozirconium, monoethyltrichlorozirconium,
mono-n-butyltrichlorozirconium, monobenzyltrichlorozirconium,
tetrachlorozirconium, tetramethoxyzirconium,
trimethoxymonochlorozirconium, dimethoxydichlorozirconium,
monomethoxytrichlorozirconium, tetraethoxyzirconium,
triethoxymonochlorozirconium, diethoxydichlorozirconium,
monoethoxytrichlorozirconium, tetraisopropoxyzirconium,
triisopropoxymonochlorozirconium,
diisopropoxydichlorozirconium,
monoisopropoxytrichlorozirconium, tetra-n-butoxyzirconium,
tri-ni-butoxymonochlorozirconium, di-n-butoxydichlorozirconium,
mono-n-butoxytrichlorozirconium, tetrapentoxyzirconium,
tripentoxymonochlorozirconium, dipentoxydichlorozirconium,
monopentoxytrichlorozirconium, tetraphenoxyzirconium,
triphenoxymonochlorozirconium, diphenoxydichlorozirconium,
monophenoxytrichlorozirconium, tetratolyoxyzirconium,
tritolyoxymonochlorozirconium, ditolyoxydichlorozirconium,
monotolyoxytrichlorozirconium, tetrabenzoyloxyzirconium,
tribenzoyloxymonochlorozirconium, dibenzoyloxydichlorozirconium,

monobenzyloxytrichlorozirconium, trimethylmonobromozirconium,
triethylmonobromozirconium, tripropylmonobromozirconium,
tri-n-butylmonobromozirconium, tribenzylmonobromozirconium,
dimethyldibromozirconium, diethyldibromozirconium,
di-n-butyldibromozirconium, dibenzyldibromozirconium,
monomethyltribromozirconium, monoethyltribromozirconium,
mono-n-butyltribromozirconium, monobenzyldibromozirconium,
tetrobromozirconium, trimethoxymonobromozirconium,
dimethoxydibromozirconium, monomethoxytribromozirconium,
triethoxymonobromozirconium, diethoxydibromozirconium,
monoethoxytribromozirconium, triisopropoxymonobromozirconium,
diisopropoxydibromozirconium, monoisopropoxytribromozirconium,
tri-n-butoxymonobromozirconium, di-n-butoxydibromozirconium,
mono-n-butoxytribromozirconium, tripentoxymonobromozirconium,
dipentoxydibromozirconium, monopentoxytribromozirconium,
triphenoxymonobromozirconium, diphenoxydibromozirconium,
monophenoxytribromozirconium, tritolyloxymonobromozirconium,
ditolyloxydibromozirconium, monotolyloxytribromozirconium,
tribenzloxymonobromozirconium, dibenzloxydibromozirconium,
monobenzloxytribromozirconium, trimethylmonoiodozirconium,
triethylmonoiodozirconium, tripropylmonoiodozirconium,
tri-n-butylmonoiodozirconium, tribenzylmonoiodozirconium,
dimethyldiioxozirconium, diethyldiioxozirconium,
dipropyldiioxozirconium, di-n-butyldiioxozirconium,
dibenzyldiioxozirconium, monomethyltriiiodozirconium,
monoethyltriiiodozirconium, monopropyltriiiodozirconium,
mono-n-butyltriiiodozirconium, monobenzyltriiiodozirconium,

tetraiodozirconium, trimethoxymonoiodozirconium,
 dimethoxydiiodozirconium, monomethoxytriiodozirconium,
 triethoxymonoiodozirconium, diethoxydiiodozirconium,
 monoethoxytriiodozirconium, triisopropoxymonoiodozirconium,
 diisopropoxydiiodozirconium, monoisopropoxytriiodozirconium,
 tri-n-butoxymonoiodozirconium, di-n-butoxydiiodozirconium,
 mono-n-butoxytriiodozirconium, tripentoxymonoiodozirconium,
 dipentoxydiiodozirconium, monopentoxytriiodozirconium,
 triphenoxymonoiodozirconium, diphenoxydiiodozirconium,
 monophenoxytriiodozirconium, tritolyoxymonoiodoiodozirconium,
 ditolyoxydiiodozirconium, monotolyoxytriiodozirconium,
 tribenzyloxymonoiodozirconium, dibenzyloxydiiodozirconium,
 monobenzyloxytriiodozirconium, tribenzylmonomethoxyzirconium,
 tribenzylmonoethoxyzirconium, tribenzylmonopropoxyzirconium,
 tribenzylmonobutoxyzirconium, tribenzylmonophenoxyzirconium,
 dibenzylldimethoxyzirconium, dibenzylldiethoxyzirconium,
 dibenzylldipropoxyzirconium, dibenzylldibutoxyzirconium,
 dibenzylldiphenoxyzirconium, monobenzyltrimethoxyzirconium,
 monobenzyltriethoxyzirconium, monobenzyltripropoxyzirconium,
 monobenzyltributoxyzirconium, monobenzyltriphenoxyzirconium,
 trineophylmonomethoxyzirconium, trineophylmonoethoxyzirconium,
 trineophylmonopropoxyzirconium, trineophylmonobutoxyzirconium,
 trineophylmonophenoxyzirconium, dineophyldimethoxyzirconium,
 dineophyldiethoxyzirconium, dineophyldipropoxyzirconium,
 dineophyldibutoxyzirconium, dineophyldiphenoxyzirconium,
 mononeophyltrimethoxyzirconium, mononeophyltriethoxyzirconium,
 mononeophyltripropoxyzirconium, mononeophyltributoxyzirconium,

mononeophyltriphenoxyzirconium, tetramethyl titanium,
tetraethyl titanium, tetrapropyl titanium, tetra-n-butyl
titanium, tetrapentyl titanium, tetraphenyl titanium,
tetraatolyl titanium, tetrabenzyl titanium, tetramethoxy
titanium, tetraethoxy titanium, tetrapropoxy titanium,
tetrabutoxy titanium, tetraphenoxy titanium, tetratolyoxy
titanium, tetrapentyloxy titanium, tetrabenzylloxy titanium,
tetraallyl titanium, tetraneophyl titanium,
trimethylmonochlorotitanium, triethylmonochlorotitanium,
tripropylmonochlorotitanium, tri-n-butylmonochlorotitanium,
tribenzylmonochlorotitanium, dimethyldichlorotitanium,
diethyldichlorotitanium, di-n-butylldichlorotitanium,
dibenzylldichlorotitanium, monomethyltrichlorotitanium,
monoethyltrichlorotitanium, mono-n-butyltrichlorotitanium,
monobenzyltrichlorotitanium, tetrachlorotitanium,
tetramethoxytitanium, trimethoxymonochlorotitanium,
dimethoxydichlorotitanium, monomethoxytrichlorotitanium,
tetraethoxytitanium, triethoxymonochlorotitanium,
diethoxydichlorotitanium, monoethoxytrichlorotitanium,
tetraisopropoxytitanium, triisopropoxymonochlorotitanium,
diisopropoxydichlorotitanium, monoisopropoxytrichlorotitanium,
tetra-n-butoxytitanium, tri-ni-butoxymonochlorotitanium,
di-n-butoxydichlorotitanium, mono-n-butoxytrichlorotitanium,
tetrapentoxytitanium, tripentoxymonochlorotitanium,
dipentoxydichlorotitanium, monopentoxytrichlorotitanium,
tetraphenoxytitanium, triphenoxymonochlorotitanium,
diphenoxydichlorotitanium, monophenoxytrichlorotitanium,

tetratolyoxytitanium, tritolyoxymonochlorotitanium,
ditolyoxydichlorotitanium, monotolyoxytrichlorotitanium,
tetrabenzylloxytitanium, tribenzylloxymonochlorotitanium,
dibenzyloxydichlorotitanium, monobenzyloxytrichlorotitanium,
trimethylmonobromotitanium, triethylmonobromotitanium,
tripropylmonobromotitanium, tri-n-butylmonobromotitanium,
tribenzylmonobromotitanium, dimethyldibromotitanium,
diethyldibromotitanium, di-n-butyldibromotitanium,
dibenzyltribromotitanium, monomethyltribromotitanium,
monoethyltribromotitanium, mono-n-butyltribromotitanium,
monobenzyltribromotitanium, tetrobromotitanium,
trimethoxymonobromotitanium, dimethoxydibromotitanium,
monomethoxytribromotitanium, triethoxymonobromotitanium,
diethoxydibromotitanium, monoethoxytribromotitanium,
triisopropoxymonobromotitanium, diisopropoxydibromotitanium,
monoisopropoxytribromotitanium, tri-n-butoxymonobromotitanium,
di-n-butoxydibromotitanium, mono-n-butoxytribromotitanium,
tripentoxymonobromotitanium, dipentoxydibromotitanium,
monopentoxytribromotitanium, triphenoxymonobromotitanium,
diphenoxydibromotitanium, monophenoxytribromotitanium,
tritolyloxymonobromotitanium, ditolyloxydibromotitanium,
monotolyloxytribromotitanium, tribenzloxymonobromotitanium,
dibenzloxydibromotitanium, monobenzloxytribromotitanium,
trimethylmonoiodotitanium, triethylmonoiodotitanium,
tripropylmonoiodotitanium, tri-n-butylmonoiodotitanium,
tribenzylmonoiodotitanium, dimethyldiioxotitanium,
diethyldiioxotitanium, dipropyldiioxotitanium,

di-n-butyldiioxotitanium, dibenzylldiioxotitanium,
 monomethyltriiodotitanium, monoethyltriiodotitanium,
 monopropyltriiodotitanium, mono-n-butyltriiodotitanium,
 monobenzyltriiodotitanium, tetraiodotitanium,
 trimethoxymonoiodotitanium, dimethoxydiiodotitanium,
 monomethoxytriiodotitanium, triethoxymonoiodotitanium,
 diethoxydiiodotitanium, monoethoxytriiodotitanium,
 triisopropoxymonoiodotitanium, diisopropoxydiiodotitanium,
 monoisopropoxytriiodotitanium, tri-n-butoxymonoiodotitanium,
 di-n-butoxydiiodotitanium, mono-n-butoxytriiodotitanium,
 tripentoxymonoiodotitanium, dipentoxydiiodotitanium,
 monopentoxytriiodotitanium, triphenoxymonoiodotitanium,
 diphenoxydiiodotitanium, monophenoxytriiodotitanium,
 tritolyoxymonoiodoiodotitanium, ditolyoxydiiodotitanium,
 monotolyoxytriiodotitanium, tribenzyloxy monoiodotitanium,
 dibenzyloxydiiodotitanium, monobenzyloxytriiodotitanium,
 tribenzylmonomethoxytitanium, tribenzylmonoethoxytitanium,
 tribenzylmonopropoxytitanium, tribenzylmonobutoxytitanium,
 tribenzylmonophenoxytitanium, dibenzyl dimethoxytitanium,
 dibenzyl diethoxytitanium, dibenzyl dipropoxytitanium,
 dibenzyl dibutoxytitanium, dibenzyl diphenoxytitanium,
 monobenzyltrimethoxytitanium, monobenzyltrietoxytitanium,
 monobenzyltripropoxytitanium, monobenzyltributoxytitanium,
 monobenzyltriphenoxytitanium, trineophylmonomethoxytitanium,
 trineophylmonoethoxytitanium, trineophylmonopropoxytitanium,
 trineophylmonobutoxytitanium, trineophylmonophenoxytitanium,
 dineophyldimethoxytitanium, dineophyldiethoxytitanium,


dineophyldipropoxytitanium, dineophyldibutoxytitanium,
dineophyldiphenoxytitanium, mononeophyltrimethoxytitanium,
mononeophyltriethoxytitanium, mononeophyltripropoxytitanium,
mononeophyltributoxytitanium, mononeophyltriphenoxytitanium,
tetramethyl hafnium, tetraethyl hafnium, tetrapropyl hafnium,
tetra-n-butyl hafnium, tetrapentyl hafnium, tetraphenyl
hafnium, tetraatolyl hafnium, tetrabenzyl hafnium, tetramethoxy
hafnium, tetraethoxy hafnium, tetrapropoxy hafnium, tetrabutoxy
hafnium, tetraphenoxo hafnium, tetratolyoxy hafnium,
tetrapentyloxy hafnium, tetrabenzilyloxy hafnium, tetraallyl
hafnium, tetraneophyl hafnium, trimethylmonochlorohafnium,
triethylmonochlorohafnium, tripropylmonochlorohafnium,
tri-n-butylmonochlorohafnium, tribenzylmonochlorohafnium,
dimethyldichlorohafnium, diethyldichlorohafnium,
di-n-butylldichlorohafnium, dibenzylldichlorohafnium,
monomethyltrichlorohafnium, monoethyltrichlorohafnium,
mono-n-butyltrichlorohafnium, monobenzyltrichlorohafnium,
tetrachlorohafnium, tetramethoxyhafnium,
trimethoxymonochlorohafnium, dimethoxydichlorohafnium,
monomethoxytrichlorohafnium, tetraethoxyhafnium,
triethoxymonochlorohafnium, diethoxydichlorohafnium,
monoethoxytrichlorohafnium, tetraisopropoxyhafnium,
triisopropoxymonochlorohafnium, diisopropoxydichlorohafnium,
monoisopropoxytrichlorohafnium, tetra-n-butoxyhafnium,
tri-ni-butoxymonochlorohafnium, di-n-butoxydichlorohafnium,
mono-n-butoxytrichlorohafnium, tetrapentoxo hafnium,
tripentoxymonochlorohafnium, dipentoxydichlorohafnium,

monopentoxytrichlorohafnium, tetraphenoxyhafnium,
triphenoxymonochlorohafnium, diphenoxydichlorohafnium,
monophenoxytrichlorohafnium, tetratolyoxyhafnium,
tritolyoxymonochlorohafnium, ditolyoxydichlorohafnium,
monotolyoxytrichlorohafnium, tetrabenzoyloxyhafnium,
tribenzoyloxymonochlorohafnium, dibenzoyloxydichlorohafnium,
monobenzoyloxytrichlorohafnium, trimethylmonobromohafnium,
triethylmonobromohafnium, tripropylmonobromohafnium,
tri-n-butylmonobromohafnium, tribenzylmonobromohafnium,
dimethyldibromohafnium, diethyldibromohafnium,
di-n-butylldibromohafnium, dibenzylldibromohafnium,
monomethyltribromohafnium, monoethyltribromohafnium,
mono-n-butyltribromohafnium, monobenzyltribromohafnium,
tetrobromohafnium, trimethoxymonobromohafnium,
dimethoxydibromohafnium, monomethoxytribromohafnium,
triethoxymonobromohafnium, diethoxydibromohafnium,
monoethoxytribromohafnium, triisopropoxymonobromohafnium,
diisopropoxydibromohafnium, monoisopropoxytribromohafnium,
tri-n-butoxymonobromohafnium, di-n-butoxydibromohafnium,
mono-n-butoxytribromohafnium, tripentoxymonobromohafnium,
dipentoxydibromohafnium, monopentoxytribromohafnium,
triphenoxymonobromohafnium, diphenoxydibromohafnium,
monophenoxytribromohafnium, tritolyloxymonobromohafnium,
ditolyloxydibromohafnium, monotolyloxytribromohafnium,
tribenzloxymonobromohafnium, dibenzloxydibromohafnium,
monobenzloxytribromohafnium, trimethylmonoiodohafnium,
triethylmonoiodohafnium, tripropylmonoiodohafnium,

tri-n-butylmonoiodohafnium, tribenzylmonoiodohafnium,
dimethyldiioxohafnium, diethyldiioxohafnium,
dipropyldiioxohafnium, di-n-butylldiioxohafnium,
dibenzylldiioxohafnium, monomethyltriiiodohafnium,
monoethyltriiiodohafnium, monopropyltriiiodohafnium,
mono-n-butyltriiiodohafnium, monobenzyltriiiodohafnium,
tetraiodohafnium, trimethoxymonoiodohafnium,
dimethoxydiiodohafnium, monomethoxytriiiodohafnium,
triethoxymonoiodohafnium, diethoxydiiodohafnium,
monoethoxytriiiodohafnium, triisopropoxymonoiodohafnium,
diisopropoxydiiodohafnium, monoisopropoxytriiiodohafnium,
tri-n-butoxymonoiodohafnium, di-n-butoxydiiodohafnium,
mono-n-butoxytriiiodohafnium, tripentoxymonoiodohafnium,
dipentoxydiiodohafnium, monopentoxytriiiodohafnium,
triphenoxymonoiodohafnium, diphenoxydiiodohafnium,
monophenoxytriiiodohafnium, tritolyoxymonoiodoiodohafnium,
ditolyoxydiiodohafnium, monotolyoxytriiiodohafnium,
tribenzyloxymonoiodohafnium, dibenzyloxydiiodohafnium,
monobenzylxytriiiodohafnium, tribenzylmonomethoxyhafnium,
tribenzylmonoethoxyhafnium, tribenzylmonopropoxyhafnium,
tribenzylmonobutoxyhafnium, tribenzylmonophenoxyhafnium,
dibenzylldimethoxyhafnium, dibenzylldiethoxyhafnium,
dibenzylldipropoxyhafnium, dibenzylldibutoxyhafnium,
dibenzylldiphenoxyhafnium, monobenzyltrimethoxyhafnium,
monobenzyltriethoxyhafnium, monobenzyltripropoxyhafnium,
monobenzyltributoxyhafnium, monobenzyltriphenoxyhafnium,
trineophylmonomethoxyhafnium, trineophylmonoethoxyhafnium,

trineophylmonopropoxyhafnium, trineophylmonobutoxyhafnium, trineophylmonophenoxyhafnium, dineophyldimethoxyhafnium, dineophyldiethoxyhafnium, dineophyldipropoxyhafnium, dineophyldibutoxyhafnium, dineophyldiphenoxyhafnium, mononeophyltrimethoxyhafnium, mononeophyltriethoxyhafnium, mononeophyltripropoxyhafnium, mononeophyltributoxyhafnium, mononeophyltriphenoxyhafnium and the like.

Compound (B) in the inventive catalyst component is represented by the formula



In the above formula, R^3 and R^4 respectively designate separate hydrocarbon moieties each having a carbon number 1 - 24, preferably 1 - 12, more preferably 1 - 8, which include alkyl groups such as methyl, ethyl, propyl, isopropyl, butyl, pentyl, hexyl, octyl, decyl and dedecyl, alkenyl groups such as vinyl and allyl, aryl groups such as phenyl, tryl and xylyl and aralkyl groups such as benzyl, phenetyl and styryl. If there are more than two members R^3 and R^4 , they may be the same or different. X^2 is a halogen atom such as fluorine, iodine, chlorine and bromine. Me^2 is a Group I - III element of the Periodic Table including lithium, sodium, potassium, magnesium, calcium, zinc, boron and aluminum. z is a valence of Me^2 . m is $0 \leq m \leq 3$; n is $0 \leq n < 3$; and $m+n$ is $1 \leq m+n \leq 3$.

Specific examples of Compound (B) include methyllithium, ethyllithium, n-propyllithium, isopropyllithium, n-butyllithium, t-butyllithium,

2072476

pentyllithium, octyllithium, phenyllithium, benzyllithium,
dimethylmagnesium, diethylmagnesium, di-n-propylmagnesium,
diisopropylmagnesium, di-n-butylmagnesium,
di-t-butylmagnesium, dipentylmagnesium, dioctylmagnesium,
diphenylmagnesium, dibenzylmagnesium, methylmagnesium
chloride, ethylmagnesium chloride, n-propylmagnesium
chloride, isopropylmagnesium chloride, n-butylmagnesium
chloride, t-butylmagnesium chloride, pentylmagnesium
chloride, octylmagnesium chloride, phenylmagnesium chloride,
benzylmagnesium chloride, methylmagnesium bromide,
methylmagnesium iodide, ethylmagnesium bromide,
ethylmagnesium iodide, n-propylmagnesium bromide,
n-propylmagnesium iodide, isopropylmagnesium bromide,
isopropylmagnesium iodide, n-butylmagnesium bromide,
n-butylmagnesium iodide, t-butylmagnesium bromide,
t-butylmagnesium iodide, pentylmagnesium bromide,
pentylmagnesium iodide, octylmagnesium bromide,
octylmagnesium iodide, phenylmagnesium bromide,
phenylmagnesium iodide, benzylmagnesium bromide,
benzylmagnesium iodide, dimethylzinc, diethylzinc,
di-n-propylzinc, diisopropylzinc, di-n-butylzinc,
di-t-butylzinc, dipentylzinc, dioctylzinc, diphenylzinc,
dibenzylzinc, trimethylbron, triethylbron, tri-n-propylbron,
triisopropylbron, tri-n-butylbron, tri-t-butylbron,
tripentylbron, trioctylbron, triphenylbron, tribenzylbron,
trimethylaluminum, triethylaluminum, diethylaluminum
chloride, diethylaluminum bromide, diethylaluminum fluoride


diethylaluminum iodide, ethylaluminum dichloride,
ethylaluminum dibromide, ethylaluminum difluoride
ethylaluminum diiodide, tripropylaluminum, dipropylaluminum
chloride, dipropylaluminum bromide, dipropylaluminum
fluoride dipropylaluminum iodide, propylaluminum dichloride,
propylaluminum dibromide, propylaluminum difluoride
propylaluminum diiodide, triisopropylaluminum,
diisopropylaluminum chloride, diisopropylaluminum bromide,
diisopropylaluminum fluoride diisopropylaluminum iodide,
ethylaluminum sesquichloride, ethylaluminum sesquibromide,
propylaluminum sesquichloride, propylaluminum sesquibromide,
n-buthylaluminum sesquichloride, n-buthylaluminum
sesquibromide, isopropylaluminum dichloride,
isopropylaluminum dibromide, isopropylaluminum difluoride,
isopropylaluminum diiodide, tributylaluminum,
dibutylaluminum chloride, dibutylaluminum bromide,
dibutylaluminum fluoride, dibutylaluminum iodide,
butylaluminum dichloride, butylaluminum dibromide,
butylaluminum difluoride, butylaluminum diiodide,
tri-sec-butylaluminum, di-sec-butylaluminum chloride,
di-sec-butylaluminum bromide, di-sec-butylaluminum fluoride,
di-sec-butylaluminum iodide, sec-butylaluminum dichloride,
sec-butylaluminum dibromide, sec-butylaluminum difluoride,
sec-butylaluminum diiodide, tri-tert-butylaluminum,
di-tert-butylaluminum chloride, di-tert-butylaluminum
bromide, di-tert-butylaluminum fluoride,
di-tert-butylaluminum iodide, tert-butylaluminum dichloride,

tert-butylaluminum dibromide, tert-butylaluminum difluoride,
tert-butylaluminum diiodide, triisobutylaluminum,
diisobutylaluminum chloride, diisobutylaluminum bromide,
diisobutylaluminum fluoride, diisobutylaluminum iodide,
isobutylaluminum dichloride, isobutylaluminum dibromide,
isobutylaluminum difluoride, isobutylaluminum diiodide,
triethylaluminum, diethylaluminum chloride, diethylaluminum
bromide, diethylaluminum fluoride, diethylaluminum iodide,
ethylaluminum dichloride, ethylaluminum dibromide,
ethylaluminum difluoride, ethylaluminum diiodide,
tripentylaluminum, dipentylaluminum chloride,
dipentylaluminum bromide, dipentylaluminum fluoride,
dipentylaluminum iodide, pentylaluminum dichloride,
pentylaluminum dibromide, pentylaluminum difluoride,
pentylaluminum diiodide, methylaluminum methoxide,
methylaluminum ethoxide, methylaluminum propoxide,
methylaluminum butoxide, dimethylaluminum methoxide,
dimethylaluminum ethoxide, dimethylaluminum propoxide,
dimethylaluminum butoxide, ethylaluminum methoxide,
ethylaluminum ethoxide, ethylaluminum propoxide,
ethylaluminum butoxide, diethylaluminum methoxide,
diethylaluminum ethoxide, diethylaluminum propoxide,
diethylaluminum butoxide, propylaluminum methoxide,
propylaluminum ethoxide, propylaluminum propoxide,
propylaluminum butoxide, dipropylaluminum methoxide,
dipropylaluminum ethoxide, dipropylaluminum propoxide,
dipropylaluminum butoxide, butylaluminum methoxide,

butylaluminum ethoxide, butylaluminum propoxide, butylaluminum butoxide, butylaluminum dibutylaluminum methoxide, dibutylaluminum ethoxide, dibutylaluminum propoxide, dibutylaluminum butoxide and the like.

Compound (C) is an organocyclic compound having two or more conjugated double bonds, examples of which include a cyclic hydrocarbon compound having two or more, preferably 2 - 4, more preferably 2 - 3 conjugated double bonds and a total carbon number of 4 - 24, preferably 4 - 12; said cyclic hydrocarbon compound partially substituted with 1 - 6 hydrocarbon moieties, typically alkyl or aralkyl groups of 1 - 12 carbon atoms; an organosilicon compound having two or more, preferably 2 - 4, more preferably 2 - 3 conjugated double bonds and cyclic hydrocarbon groups having a total carbon number of 4 - 24, preferably 4 - 12; and an organosilicon compound having said cyclic hydrocarbon groups partially substituted with 1 - 6 hydrocarbon moieties.

The organosilicon compound referred to above may be represented by the general formula



where Cp is a cyclic hydrocarbon group such as cyclopentadienyl, substituted cyclopentadienyl, indenyl and substituted indenyl groups; R is a hydrocarbon moiety of 1 - 24, preferably 1 - 12 carbon atoms exemplified by an alkyl group such as methyl, ethyl, propyl, isopropyl, butyl, t-butyl, hexyl and octyl, an alcoxy group such as methoxy, ethoxy, propoxy and butoxy, an aryl group such as phenyl,

an aryloxy group such as phenoxy, and an aralkyl group such as benzyl, or hydrogen; and L is $1 \leq L \leq 4$, preferably $1 \leq L \leq 3$.

Specific examples of Compound (B) include cyclopolyenes or substituted cyclopolyenes having 7 - 24 carbon atoms such as cyclopentadiene, methylcyclopentadiene, ethylcyclopentadiene, t-butylcyclopentadiene, hexylcyclopentadiene, octylcyclopentadiene, 1,2-dimethylcyclopentadiene, 1,3-dimethylcyclopentadiene, 1,2,4-trimethylcyclopentadiene, 1,2,3,4-tetramethylcyclopentadiene, pentamethylcyclopentadiene, indene, 4-methyl-1-indene, 4,7-dimethylindene, 4,5,6,7-tetrahydroindene, cycloheptatriene, methylcycloheptatriene, cyclooctatetraene, methylcyclooctatetraene, azurene, ethylazurene, fluorene, methylfluorene; monocyclopentadienylsilane, dicyclopentadienylsilane, tricyclopentadienylsilane, tetracyclopentadienylsilane, monocyclopentadienylmonomethylsilane, monocyclopentadienylmonoethylsilane, monocyclopentadienyldimethylsilane, monocyclopentadienyldiethylsilane, monocyclopentadienyltrimethylsilane, monocyclopentadienyltriethylsilane, monocyclopentadienylmonomethoxysilane, monocyclopentadienylmonoethoxysilane, monocyclopentadienylmonophenoxysilane,

dicyclopentadienylmonomethylsilane,
dicyclopentadienylmonoethylsilane,
dicyclopentadienyldimethylsilane,
dicyclopentadienylmethylethylsilane,
dicyclopentadienylpropylsilane,
dicyclopentadienylethylpropylsilane,
dicyclopentadienylphenylsilane,
dicyclopentadienylphenylmethylsilane,
dicyclopentadienylmonomethoxysilane,
dicyclopentadienylmonoethoxysilane,
tricyclopentadienylmonomethylsilane,
tricyclopentadienylmonoethylsilane,
tricyclopentadienylmonomethoxysilane,
tricyclopentadienylmonoethoxysilane,
3-methylcyclopentadienylsilane,
bis-3-methylcyclopentadienylsilane,
3-methylcyclopentadienylmethylsilane,
1,2-dimethylcyclopentadienylsilane,
1,3-dimethylcyclopentadienylsilane,
1,2,4-trimethylcyclopentadienylsilane,
1,2,3,4-tetramethylcyclopentadienylsilane,
pentamethylcyclopentadienylsilane, monoindenylsilane,
diindenylsilane, triindenylsilane, tetraindenylsilane,
monoindenylmonomethylsilane, monoindenylmonoethylsilane,
monoindenyldimethylsilane, monoindenyldiethylsilane,
monoindenyltrimethylsilane, monoindenyltriethylsilane,
monoindenylmonomethoxysilane, monoindenylmonoethoxysilane,

monoindenylmonophenoxysilane, diindenylmonomethylsilane, diindenylmonoethylsilane, diindenyldimethylsilane, diindenyl-diethylsilane, diindenylmethylethylsilane, diindenyl-dipropylsilane, diindenylethylpropylsilane, diindenyl-diphenylsilane, diindenylphenylmethylsilane, diindenylmonomethoxysilane, diindenylmonoethoxysilane, triindenylmonomethylsilane, triindenylmonoethylsilane, triindenylmonomethoxysilane, triindenylmonoethoxysilane, 3-methylindenylsilane, bis-3-methylindenylsilane, 3-methylindenylmethylsilane, 1,2-dimethylindenylsilane, 1,3-dimethylindenylsilane, 1,2,4-trimethylindenylsilane, 1,2,3,4-tetramethylindenylsilane, pentamethylindenylsilane and the like.

There may also be used certain compounds of the above which are bonded through alkylene groups having typically 2 - 8, preferably 2 - 3 carbon atoms, examples of which include bisindenylethane, bis(4,5,6,7-tetrahydro-1-indenyl)-ethane, 1,3-propandynyl-bis-indene, 1,3-propandynyl bisindene, 1,3-propandynyl bis(4,5,6,7-tetrahydro)indene, propylene bis(1-indene), isopropyl(1-indenyl)cyclopentadiene, diphenylmethylen(9-fluorenyl)cyclopentadiene, isopropylcyclopentadienyl-1-fluorene and the like.


The catalyst component of the invention is derived by mutual contact of Compounds (A), (B) and (C) in a molar ratio (A):(B) of 1:0.01-100, preferably 1:0.1-10, and in a molar ratio (A):(C) of 1:0.01 - 100, preferably 1:0.1 - 10, respectively. The sequence in which the three compounds are

contacted with one another is optional. However, it has been found preferable to bring Compound (A) and (C) into contact with each other in advance, followed by contact with Compound (B). There is no particular restriction upon the manner in which the three compounds are contacted. They may be contacted in an atmosphere of inert gas such as nitrogen or argon in the presence of a solvent of inert hydrocarbon such as heptane, hexane, benzene, toluene or xylene, at a temperature of about -100° - 200°C , preferably -50° - 100°C for a duration of 30 minutes to 50 hours, preferably 2 - 24 hours. The resulting catalyst component can be readily put to use in the form of a solution, or can alternatively be used after it is solidified by suitable means and removed from the solution.

The inventive catalyst component is usually combined with a suitable promoter to form a catalyst composition for use in the homo- or co-polymerization of olefins. Such a promoter may be typically a modified organoaluminum compound or other commercially available promoter compounds which do not adversely affect the performance of the inventive catalyst component.

The term modified organoaluminum compound is used herein to designate a reaction product of an organoaluminum compound and water which has 1 - 100, preferably 1 - 50 Al-O-Al bonds in the molecule. This reaction is usually conducted in the presence of an inert hydrocarbon such as pentane, hexane, heptane, cyclohexane, methylcyclohexane,

benzene, toluene and xylene, of which aliphatic and aromatic hydrocarbons are preferred. The starting organoaluminum compound may be represented by the formula



where R is an alkyl, alkenyl, aryl or aralkyl group having a carbon number of 1 - 18, preferably 1 - 12; X is a hydrogen or halogen atom; and n is an integer of $1 \leq n \leq 3$.

The above compound is typically exemplified by trialkylaluminum having an alkyl group optionally such as methyl, ethyl, propyl, isopropyl, butyl, isobutyl, pentyl, hexyl, octyl, decyl and dodecyl groups, of which methyl group is particularly preferred.

The water/organoaluminum reaction takes place in a molar ratio of water:Al in the range of 0.25:1-1.2/1, preferably 0.5:1-1/1 at a temperature of usually -70° - 100°C , preferably -20° - 20°C for a period of 5 - 24 hours, preferably 5 - 10 hours. As water for reaction with the organoaluminum compound, there may be used crystal water contained in hydrates of copper sulfate or aluminum sulfate.

The catalyst component and the modified organoaluminum compound may be supplied separately or as an admixture to the polymerization reaction system. They are used in a ratio such that the atomic ratio of aluminum in the organoaluminum compound to transition metal in the catalyst component remain in the range of 1 - 100,000, preferably 5 - 1,000.

The term olefins as used herein designates alpha-


olefins, cyclic olefins, dienes, trienes and styrene analogs. Alpha-olefins have a carbon number of 2 - 12, preferably 2 - 8 and typically include ethylene, propylene, butene-1, hexene-1 and 4-methylpentene-1. According to the invention, these olefins may be homopolymerized or copolymerized such as by alternating, random or block copolymerization process.

The copolymerization of alpha-olefins is carried out in any of the combinations of ethylene and alpha-olefins of 3 - 12, preferably 3 - 8 carbon atoms such as ethylene/propylene, ethylene/butene-1, ethylene/hexene-1 and ethylene/4-methylpentene-1, and propylene and alpha-olefins of 3 - 12, preferably 3 - 8 carbon atoms such as propylene/butene-1, propylene/4-methylpentene-1, propylene/4-methylbutene-1, propylene/hexene-1 and propylene/octene-1. Alpha-olefins to be combined with ethylene and propylene respectively are used in an amount not exceeding 90 mol% of total monomers, e.g. less than 40 mol%, preferably less than 30 mol%, more preferably less than 20 mol% with ethylene copolymers, and 1 - 90 mol%, preferably 5 - 90 mol%, more preferably 10 - 70 mol% with propylene copolymers.

The cyclic olefins to be used in the invention are those having a carbon number of 3 - 24, preferably 3 - 18 such as for example cyclopentene, cyclobutene, cyclohexene, 3-methylcyclohexene, cyclooctene, cyclodecene, cyclododecene, tetracyclodecene, octacyclodecene,

dicyclopentadiene, norbornene, 5-methyl-2-norbornene, 5-ethyl-2-norbornene, 5-isobutyl-2-norbornene, 5,6-dimethyl-2-norbornene, 5,5,6-trimethyl-2-norbornene and ethyldenenorbornene. These cyclic olefins are usually copolymerized with alpha-olefins, in which instance the cyclic olefin is present in an amount of less than 50 mol%, preferably 1 - 50 mol%, more preferably 2 - 50 mol%, obtained.

The term dienes and trienes as used herein designates a chain polyene of the formula



where m is 1 or 2; n is 0 - 20, preferably 2 - 20.

Specific examples of the above polyene include butadiene, 1,4-hexadiene, 1,5-hexadiene, 1,9-decadiene, 1,13-tetradecadiene, 2,6-dimethyl-1,5-heptadiene, 2-methyl-2,7-octadiene, 2,7-dimethyl-2,6-octadiene and 1,5,9-decatriene. These polyenes are usually copolymerized with the above-listed alpha-olefins, and their contents in the resultant copolymers remain in the range of 0.1 - 50 mol%, preferably 0.2 - 10 mol%.

The term styrene analogs as referred to herein designates styrene and derivatives thereof including t-butylstyrene, alpha-methylstyrene, p-methylstyrene, divinylbenzene, 1,1-diphenylethylene, N,N-dimethyl-p-aminoethylstyrene and N,N-diethyl-p-aminoethylstyrene.

The catalyst composition provided in accordance with the invention is suitably used for the homo- or

co-polymerization of olefins and further for reforming the homopolymers or copolymers with use of certain polar monomers. Such polar monomers may be unsaturated carboxylic acid esters exemplified by methylacrylate, methylethacrylate, butylethacrylate, dimethylmaleate, diethylmaleate, monomethylmaleate, diethylfumarate and dimethylitaconate. The polar monomer contents in the reformed copolymer obtained are usually in the range of 0.1 - 10 mol%, preferably 0.2 - 2 mol%.

The polymerization reaction according to the invention is conducted in a slurry, solution or gase phase in the presence or absence of an inert hydrocarbon solvent such as an aliphatic hydrocarbon including hexane and heptane, an aromatic hydrocarbon including benzene, toluene and xylene, and an alicyclic hydrocarbon including cyclohexane, and methylcyclohexane, substantially without the presence of oxygen and water, at a temperature of 20° - 200°C, preferably 50° - 100°C under a pressure of atmospheric -70 kg/cm²G, preferably atmospheric -20 kg/cm²G, for a time length of 5 minutes to 10 hours, preferably 5 minutes to 5 hours.

Whilst the molecular weight of the polymer product obtained may be adjusted to some extent by varying the polymerization temperature, the molar ratio of the catalyst and other polymerization parameters, it can be more effectively adjusted by introducing water into the reaction system.

Preparation of Modified Organoaluminum Compound
(Methylalumoxane)

In a 300-ml three-necked flask equipped with an electromagnetic stirrer were placed 13 grams of copper sulfate and 50 ml of toluene. The mixture after being suspended was incorporated dropwise at 0°C and over 2 hours with 150 ml of a 1 mmol/ml triethylaluminum solution. The reaction was effected at 25°C for 24 hours. Filtration of the reaction mixture and subsequent evaporation of excess toluene gave 4 grams of methylalmoxane (MAO) in the form of a white crystal.

Each of the polymers obtained in the respective Inventive and Comparative Examples given below was tested for the following items of property.

Melt Index (MI)

The procedure of ASTM D1238-57T was followed.

Density (D)

The procedure of ASTM D1505-68 was followed.

Melting Point by Calorimetry (DSC)

5 mg of the polymer sample was disposed at 180°C for 3 minutes, cooled to 0°C over 10°C/min and allowed to stand at 0°C for 10 minutes, followed by heating with a temperature rise of 10°C/min with use of a melting point tester (Seiko Electronics DSC-20).

Molecular Weight Distribution (Mw/Mn)

This was measured by a gel permeation chromatography (Model 150-C manufactured by Waters Co.) at 135°C with use of ortho-dichlorobenzene as solvent.

The invention will now be further described by way of

the following examples.

Inventive Example 1

Preparation of Catalyst Component A01

Into a 300-ml three-necked flask were introduced 100 ml of toluene, followed by addition of 11 grams of triethylaluminum (AlEt_3) and 2.6 grams of cyclopentadiene. The admixture was cooled to -60°C . 50 ml of toluene were fed into a separate 100-ml flask, followed by addition of 4.2 grams of tetrapropoxyzirconium ($\text{Zr}(\text{OPr})_4$) and 1.0 gram of cyclopentadiene. The resulting solution was admixed with the previously obtained admixture, and the whole was stirred at -60°C for one hour and slowly heated with stirring until there was produced a black solution of Catalyst Component A01. The operation was conducted thoroughly in nitrogen atmosphere.

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 300 ml of toluene, 3.6 ml of 1,5-hexadiene, 2 ml of 1 mmol/ml methylaloxane solution and 0.2 mg of Catalyst Component A01 in terms of the Zr element. Ethylene was charged to bring the autoclave internal pressure up to 9 $\text{kg/cm}^2\text{G}$, whereupon the polymerization reaction was initiated at 30°C and continued for 6 hours with continued charge of ethylene to maintain the reaction system at 9 $\text{kg/cm}^2\text{G}$.

Upon completion of the reaction, all excess gases were removed from the reactor which was then cooled to obtain an

ethylene/1,5-hexadiene copolymer in an amount of 30 grams. The resulting copolymer had an ethylene content of 98.2 mol%, a density of 0.9236 g/cm³ and a melting point of 138°C. Catalytic activity was represented by 150,000 grams copolymer/gram Zr.

Inventive Example 2

Preparation of Catalyst Component A02

Into a 300-ml three-necked flask were introduced 100 ml of toluene, followed by addition of 11 grams of triethylaluminum (AlEt₃) and 4.8 grams of bis-indenylethane. The admixture was cooled to -60°C. 50 ml of toluene were fed into a separate 100-ml flask, followed by addition of 4.5 grams of tetrabutoxyzirconium (Zr(Obu)₄) and 1.2 grams of bis-indenylethane. The resulting solution was admixed with the previously obtained admixture, and the whole was stirred at -60°C for one hour and slowly heated with stirring until there was produced a black solution of Catalyst Component A02. The operation was conducted thoroughly in nitrogen atmosphere.

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 300 ml of toluene, 5.5 ml of 1 mmol/ml methylaloxane solution and 0.5 mg of Catalyst Component A02 in terms of the Zr element. Ethylene was charged to bring the autoclave internal pressure up to 9 kg/cm²G, whereupon the polymerization reaction was initiated at 30°C and continued

for 15 minutes with continued charge of ethylene to maintain the reaction system at 9 kg/cm²G. Into the reaction product were thereafter fed 54 ml of methyl methacrylate, and the whole was further polymerized at 30°C for 3 hours with ethylene continuously charged to maintain the reaction system at 9 kg/cm²G.

Upon completion of the reaction, excess gas was removed from the reactor which was then cooled to yield 30 grams of a polymer. After being dissolved in toluene, the resulting polymer was precipitated with addition of acetone and then dried. The polymer thus treated was press-molded into a 25-micron thick sheet (190°C x 5 min). Infrared spectrometry of the sheet showed at 1740 cm⁻¹ an absorption spectrum peculiar to a carbonyl group. The polymer produced in this example was determined to have a molecular weight distribution (Mw/Mn) of 4.7 (GPC) and an intrinsic viscosity of 1.9 dl/g (135°C tetralin). Catalytic activity was represented by 20,000 grams polymer/gram Zr.

Inventive Example 3

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 300 ml of toluene, 10.0 ml of 1 mmol/ml methylaloxane solution and 1.0 mg of Catalyst Component A02 in terms of the Zr element. The admixture was heated at 50°C with stirring. The polymerization was initiated with a charge of a gas mixture propylene/butene-1 (propylene 85 mol%/butene-1

15 mol%) to bring the reactor pressure up to 5 kg/cm²G and continued for 2 hours with continued charge of the gas mixture to maintain that pressure.

Upon completion of the reaction, all excess gases were removed, followed by addition of methanol to cause the reaction product to precipitate. The precipitate was washed with methanol and dried to yield 60 grams of a copolymer. The resulting copolymer had a butene-1 content of 10.5 mol% (¹³C-MNR), a molecular weight distribution (Mw/Mn) of 4.0 (GPC) and an intrinsic viscosity of 0.83 dl/g (135°C tetralin). Catalytic activity was represented by 60,000 grams copolymer/gram Zr.

Inventive Example 4

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 300 ml of toluene, 5.0 ml of cyclopentene, 50.0 ml of 1 mmol/ml methylaloxane solution and 1.0 mg of Catalyst Component A02 in terms of the Zr element. The admixture was reacted at 30°C for 24 hours. Ethylene was charged to bring the autoclave internal pressure up to 3.5 kg/cm²G, whereupon the polymerization reaction was initiated at 30°C and continued for one hour with continued charge of ethylene to maintain the reaction system at 3.5 kg/cm²G.

Upon completion of the reaction, all excess gases were removed, followed by addition of methanol to cause the reaction product to precipitate. The precipitate was washed

with methanol and dried to yield 36 grams of a copolymer. The resulting copolymer had an ethylene content of 98.0 mol% (^{13}C -MNR), a molecular weight distribution (M_w/M_n) of 4.4 (GPC) and an intrinsic viscosity of 1.3 dl/g (135°C tetralin). Catalytic activity was represented by 12,000 grams copolymer/gram Zr.

Inventive Example 5

Preparation of Catalyst Component A03

Into a 300-ml three-necked flask were introduced 100 ml of toluene, followed by addition of 12.5 grams of triethylaluminum (AlEt_3) and 4.6 grams of indene. The admixture was cooled to -60°C . 50 ml of toluene were fed into a separate 100-ml flask, followed by addition of 4.5 grams of tetrapropoxyzirconium ($\text{Zr}(\text{OPr})_4$) and 1.8 grams of indene. The resulting solution was admixed with the previously obtained admixture, and the whole was stirred at -60°C for one hour and slowly heated with stirring up to 20°C over 2 hours. The reaction was continued with stirring at 45°C for 3 hours until there was obtained a black solution.

Into a 300-ml three-necked flask were 50 ml of 2 mmol/g toluene solution of methylaluminoxane and 2.7 ml of the black solution prepared above. The resulting solution was stirred, followed by gradual addition of 150 ml of n-hexane to cause precipitation. Subsequent filtration and in vacuo drying of the precipitate gave Catalyst Component A03 in solid form.

Prepolymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and then incorporated with 100 ml of n-hexane and 2 grams of Catalyst Component A03. Ethylene was charged into the admixture, whereupon the whole was prepolymerized at 0.5 kg/cm²G and at normal temperature for 30 minutes.

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 200 grams of sodium chloride anhydride, 5.5 ml of 1 mmol/ml isobutylaloxane solution derived by reacting isobutylaluminum and water (Al:H₂O = 1:0.5) and 0.14 gram of the above prepolymer. The admixture was heated at 60°C with stirring. The polymerization was initiated with a charge of ethylene to bring the reactor pressure up to 9 kg/cm²G and continued for one hour with continued charge of the gas to maintain that pressure.

Upon completion of the reaction, excess gas was removed from the reactor which was then cooled to obtain 25 grams of a white polymer. The resulting polymer had a melt index (MI) of 2.3 g/10 min and a molecular weight distribution (Mw/Mn) of 4.3.

Inventive Example 6

Preparation of Catalyst Component A04

Into a 300-ml three-necked flask were introduced 100 ml of toluene, followed by addition of 12.5 grams of

triethylaluminum (AlEt_3) and 5.4 grams of monocycloindenyltrimethylsilane. The admixture was cooled to -60°C . 50 ml of toluene were fed into a separate 100-ml flask, followed by addition of 4.2 grams of tetrabutoxyzirconium ($\text{Zr}(\text{OBu})_4$) and 2.1 grams of monocycloindenyltrimethylsilane. The resulting solution was admixed with the above cold admixture, and the whole was stirred at -60°C for one hour and heated slowly with stirring until there was produced a black solution of Catalyst Component A04. The resultant solution had a Zr content of 0.1 mmol/ml. The operation was conducted in nitrogen atmosphere.

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 200 grams of sodium chloride anhydride, 0.2 ml of Catalyst Component A04 and 20 ml of 1 mmol/ml methylalcoxane solution. The admixture was heated at 60°C with stirring. The polymerization was initiated with a charge of a gas mixture ethylene/butene-1 (butene-1/ethylene mol ratio = 0.25) to bring the reactor pressure up to 9 kg/cm²G and continued for one hour with continued charge of the gas mixture (butene-1/ethylene mol ratio = 0.05) to maintain that pressure.

Upon completion of the reaction, all excess gases were removed from the reactor which was then cooled to obtain 129 grams of a white copolymer. The resulting copolymer had a

melt index (MI) of 2.3 g/10 min, a molecular weight distribution (Mw/Mn) of 5.2 and a density of 0.9238. Catalytic activity was represented by 72,000 grams copolymer/gram Zr.

Inventive Example 7

Preparation of Catalyst Component A05

Into a 300-ml three-necked flask were introduced 100 ml of toluene, followed by addition of 9.7 grams of ethylmagnesium chloride (EtMgCl) in tetrahydrofuran and 4.6 grams of indene. The admixture was cooled to -60°C . 50 ml of toluene were fed into a separate 100-ml flask, followed by addition of 4.2 grams of tetrapropoxyzirconium ($\text{Zr}(\text{OPr})_4$) and 1.8 grams of indene. The resulting solution was poured over 20 minutes into the above cold admixture, and the whole was stirred at -60°C for one hour and heated slowly with stirring up to 20°C over 2 hours. By subsequent reaction with stirring at 45°C for 3 hours, there was produced a solution of Catalyst Component A05 in which Zr was contained in a concentration of 5.4 mg/ml. The operation was conducted in nitrogen atmosphere.

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied with 200 grams of sodium chloride anhydride, 0.28 ml of Catalyst Component A05 and 16 ml of 1 mmol/l methylaloxane solution. The admixture was heated at 60°C with stirring. The polymerization was initiated with a charge of a gas

mixture ethylene/butene-1 (butene-1/ethylene mol ratio = 0.25) to bring the reactor pressure up to 9 kg/cm²G and continued for one hour with continued charge of the gas mixture (butene-1/ethylene mol ratio = 0.05) to maintain that pressure.

Upon completion of the reaction, all excess gases were removed from the reactor which was then cooled to yield 100 grams of a white copolymer.

Inventive Examples 8 - 25

Preparation of Catalyst Components A06 to A22

Catalyst Components A06 to A22 were obtained, as was done in A05, with the varied compositions shown in Table 1.

Tetrabenzylzirconium (ZrBz₄) employed for A14 and A22 was prepared by the following mode of synthesis.

Into an 1-liter three-necked flask equipped with magnetic stirrer were fed, at 0°C and in nitrogen atmosphere, 500 ml of diethyl ether solution containing 70 grams of benzylmagnesium chloride, followed by addition of 30 grams of zirconium tetrachloride over 30 minutes in nitrogen atmosphere. The admixture was heated with stirring for 2 hours up to room temperature, followed by addition of 300 ml of decalin and by subsequent stirring for one hour at room temperature. Magnesium chloride having been formed was isolated from the reaction product. The resulting decalin solution was heated at 50°C to remove ether with continued blowing of nitrogen, thereby obtaining 32 grams of ZrBz₄.

Polymerization

The method of Inventive Example 7 was followed except that A06 to A22 were used respectively in place of A05. Ethylene and propylene were homopolymerized respectively in Inventive Examples 23 and 24.

Table 2 shows the details of the catalyst components of Inventive Examples 8 to 25 and the physical properties of the resultant polymers.

Comparative Examples 1 - 10

Preparation of Catalyst Component B01

Into a 300-ml three-necked flask were fed 100 ml of toluene, followed by addition of 4.2 grams of tetrapropoxyzirconium ($\text{Zr}(\text{OPr})_4$). The admixture was stirred at room temperature to obtain Catalyst Component B01.

Preparation of Catalyst Components B02 to B04

The method for B01 was followed except that tetrabenzylzirconium (ZrBz_4), tetrachlorozirconium (ZrCl_4) and dicyclopentadienyl dichlorozirconium (Cp_2ZrCl_2) were substituted respectively for $\text{Zr}(\text{OPr})_4$. There were thus obtained Catalyst Components B02 to B04.

Preparation of Catalyst Components B05 to B07

The method for A05 was followed except that without use of the tetrahydrofuran solution of ethylmagnesium chloride, zirconium compounds and indene were reacted with varying mol ratios as shown in Table 3. There were thus obtained Catalyst Components B05 to B07.

Preparation of Catalyst Components B08 to B10

The method for A05 was followed except that with

indene omitted, zirconium compounds and ethylmagnesium chloride were reacted varying mol ratios as shown in Table 3. There were thus obtained Catalyst Components B08 to B10.

Polymerization

The method of Inventive Example 7 was followed except that B01 to B10 were used respectively in place of A05.

Table 4 shows the details of the catalyst components of Comparative Examples 1 to 10 and the physical properties of the resultant polymers.

Inventive Example 26

Preparation of Catalyst Component A23

Into a 300-ml three-necked flask were introduced 100 ml of toluene, followed by addition of 12.5 grams of AlEt_3 and 4.6 grams of indene. The admixture was cooled to -60°C . 50 ml of toluene were fed into a separate 100-ml flask, followed by addition of 4.2 grams of $\text{Zr}(\text{OPr})_4$ and 1.8 grams of indene. The resulting solution was admixed over 20 minutes with the previously obtained admixture, and the whole was stirred at -60°C for one hour and heated slowly with stirring up to 20°C over 2 hours. By subsequent reaction with stirring at 45°C for 3 hours, there was produced a black solution of Catalyst Component A23. Its Zr content was 0.075 mmol/ml.

Polymerization

A 3-liter stainless steel autoclave equipped with stirrer was purged with nitrogen and thereafter supplied

with 200 grams of sodium chloride anhydride, 0.2 ml of Catalyst Component A23 and 15 ml of 1 mmol/ml methylalcoxane solution. The admixture was heated at 60°C with stirring. The polymerization was initiated with a charge of a gas mixture ethylene/butene-1 (butene-1/ethylene mol ratio = 0.25) to bring the reactor pressure up to 9 kg/cm²G and continued for one hour with continued charge of the gas mixture (butene-1/ethylene mol ratio = 0.05) to maintain that pressure.

Inventive Example 27

Preparation of Catalyst Component A24

The method for A23 was followed except that the amount of Zr(OPr)₄ was doubled. A black solution of Catalyst Component A24 was obtained with a Zr content of 0.15 mmol/ml.

Polymerization

The method of Inventive Example 26 was followed except that 0.1 mol of A24 was used in place of A23.

Inventive Example 28

Polymerization

The method of Inventive Example 26 was followed except that the amount of methylalcoxane was halved.

Inventive Example 29

Preparation of Catalyst Component A25

The method for A23 was followed except that 4.4 grams of tetrabutoxytitanium (Ti(Obu)₄) were used in place of Zr(OPr)₄. A solution of Catalyst Component A25 was obtained with a Ti content of 0.075 mmol/ml.

Polymerization

The method of Inventive Example 26 was followed except that A25 was substituted for A23.

Inventive Examples 30 - 36Preparation of Catalyst Component A26

The method for A23 was followed except that 5 grams of $\text{Zr}(\text{O}i\text{Bu})_4$ were used in place of $\text{Zr}(\text{OPr})_4$. A solution of Catalyst Component A26 was obtained with a Zr content of 0.075 mmol/ml.

Preparation of Catalyst Component A27

The method for A23 was followed except that 13.1 gramss of AlEt_2Cl were used in place of AlEt_3 .

Preparation of Catalyst Component A28

The method for A23 was followed except that 9.1 grams of fluorene were used in place of indene.

Preparation of Catalyst Component A29

The method for A23 was followed except that 5.7 grams of cyclooctatetraene were used in place of indene.

Preparation of Catalyst Component A30

The method for A23 was followed except that $\text{Zr}(\text{OPr})_4$ was replaced with 10.8 grams of tetrapropoxyhafnium ($\text{Hf}(\text{OPr})_4$).

Preparation of Catalyst Component A31

The method for A23 was followed except that $\text{Zr}(\text{OPr})_4$ was replaced with 3.9 grams of tripropoxyzirconium chloride ($\text{Zr}(\text{OPr})_3\text{Cl}$).

Preparation of Catalyst Component A32

Into a 300-ml three-necked flask were introduced 150 ml of toluene, 4.2 grams of $\text{Zr}(\text{OPr})_4$ and 6.4 grams of indene. The admixture was stirred at room temperature for one hour, followed by addition of 12.5 grams of AlEt_3 over 20 minutes, and the whole was reacted at 45°C for 3 hours. There was produced a solution of Catalyst Component A32.

Polymerization

The method of Inventive Example 26 was followed except that A26 to A32 were substituted respectively for A23.

Inventive Example 37

Polymerization

The method of Inventive Example 26 was followed except that ethylene was homopolymerized.

Comparative Examples 11 - 14

Preparation of Catalyst Component B11

As Catalyst component B11, toluene solution of $\text{Zr}(\text{OPr})_4$ was prepared to have a Zr content of 0.08 mmol/ml.

Preparation of Catalyst Component B12

The method for A23 was followed except that indene was omitted.

Preparation of Catalyst Component B13

The method for A23 was followed except that AlEt_3 was omitted. A solution of Catalyst Component B13 was obtained with a Zr content of 0.08 mmol/ml.

Preparation of Catalyst Component B14

As Catalyst component B14, toluene solution of Cp_2ZrCl_2 was prepared to have a Zr content of 0.07 mmol/ml.

Polymerization

The method of Inventive Example 26 was followed except that B11 to B14 were substituted respectively for A23.

Table 5 shows the compositions of Catalyst Components A23 to A32 and B11 to B14. Listed in Table 6 are the polymerization conditions used in Inventive Examples 26 to 37 and Comparative Examples 11 to 14 together with the physical properties of the resultant polymers.

Table 1

catalyst component	catalyst composition			mol ratio (A) : (B) : (C)
	(A)	(C)	(B)	
A05	Zr(OPr) ₄	indene	EtMgCl	1 : 4 : 8
A06	Zr(OPr) ₄	indene	Et ₂ Zn	1 : 4 : 8
A07	Zr(OPr) ₄	indene	Et ₃ B	1 : 4 : 8
A08	Zr(OPr) ₄	indene	EtMgCl	1 : 2 : 4
A09	Ti(OBu) ₄	indene	EtMgCl	1 : 2 : 4
A10	Hf(OPr) ₄	indene	PhMgCl	1 : 3 : 10
A11	Zr(OPr) ₃ Cl	fluorene	EtMgCl	1 : 1 : 2
A12	Zr(OPr) ₄	cycloocta- tetraene	EtMgCl	1 : 4 : 10
A13	ZrAy ₄	indene	AlEt ₂ Cl	1 : 4 : 8
A14	ZrBz ₄	indene	AlEt ₂ (OEt)	1 : 4 : 8
A15	ZrNp ₄	indene	EtMgCl	1 : 4 : 8
A16	ZrCl ₄	indene	EtLi	1 : 3 : 6
A17	ZrCl ₄	indene	EtMgCl	1 : 4 : 8
A18	TiCl ₄	indene	EtMgCl	1 : 4 : 8
A19	ZrCl ₄	fluorene	EtMgCl	1 : 4 : 8
A20	Zr(OPr) ₄	indene	BuMgCl	1 : 2 : 8
A21	Zr(OPr) ₄	bis-indenyl- ethane	BuMgCl	1 : 2 : 8
A22	ZrBz ₄	indene	Al(OEt) ₂ Cl	1 : 2 : 10

Notes: Et = ethyl Bu = n-butyl Bz = benzyl
 Pr = n-propyl Ay = allyl Ph = phenyl
 Np = neophil

Table 2

Inventive Example	catalyst component	Me (mg)	yield (g)	CA (g/gMe)	Mw/Mn	MI (g/10min)	density (g/cm ³)	mp (°C)
7	A05	1.5	100	67,000	5.9	0.8	0.9231	114.7
8	A06	1.6	101	53,000	5.3	0.7	0.9250	115.4
9	A07	1.4	83	59,000	5.5	1.0	0.9244	115.1
10	A08	1.7	117	69,000	6.0	0.6	0.9241	115.1
11	A09	2.0	78	39,000	4.8	0.4	0.9220	114.3
12	A10	2.3	67	29,000	4.9	0.1	0.9215	113.8
13	A11	1.4	67	48,000	5.4	0.8	0.9233	114.8
14	A12	1.5	76.5	51,000	4.4	0.7	0.9211	113.8
15	A13	1.5	102	68,000	7.2	0.6	0.9235	114.8
16	A14	1.6	110	69,000	6.2	0.5	0.9274	115.7
17	A15	1.7	107	63,000	3.4	0.7	0.9218	113.9
18	A16	1.3	87	67,000	3.3	0.8	0.9222	113.9
19	A17	1.5	97.5	65,000	3.3	0.9	0.9233	114.8
20	A18	2.1	71	34,000	3.1	0.3	0.9210	113.7
21	A19	1.8	72	40,000	5.9	0.4	0.9265	115.5
22	A20	1.5	73.5	49,000	15.0	3.0	0.9239	115.0
23	A20	1.4	88	63,000	5.8	0.08	0.9510	135.3
24	A21	3.0	117	39,000	3.9	1.3	0.9038	141.1
25	A22	1.8	86	48,000	4.7	1.0	0.9213	113.9

Notes: Me = transition metal CA = catalytic activity

Table 3

catalyst component	catalyst composition			mol ratio (A) : (C) : (B)
	(A)	(C)	(B)	
B01	Zr(OPr) ₄	-	-	1 : 0 : 0
B02	ZrBz ₄	-	-	1 : 0 : 0
B03	ZrCl ₄	-	-	1 : 0 : 0
B04	Cp ₂ ZrCl ₂	-	-	1 : 0 : 0
B05	Zr(OPr) ₄	indene	-	1 : 4 : 0
B06	ZrBz ₄	indene	-	1 : 4 : 0
B07	ZrCl ₄	indene	-	1 : 4 : 0
B08	Zr(OPr) ₄	-	EtMgCl	1 : 0 : 8
B09	ZrBz ₄	-	EtMgCl	1 : 0 : 8
B10	ZrCl ₄	-	EtMgCl	1 : 0 : 8

Notes: Py = n-propyl
 Bz = benzyl
 Cp = cyclopentadienyl

Table 4

Comparative Example	catalyst component	Me (mg)	yield (g)	CA (g/gMe)	Mw/Mn	MI (g/10min)	density (g/cm ³)	mp (°C)
1	B01	1.3	-	-	-	-	-	-
2	B02	1.5	trace	-	-	-	-	-
3	B03	1.4	-	-	-	-	-	-
4	B04	1.5	63	45,000	2.6	23	0.9198	106.7
5	B05	1.6	21	13,000	5.1	1.45	0.9281	115.3
6	B06	1.5	45	30,000	7.8	0.95	0.9224	114.3
7	B07	1.4	-	-	-	-	-	-
8	B08	1.6	-	-	-	-	-	-
9	B09	1.7	33	21,000	9.8	1.0	0.6264	115.0
10	B10	1.4	-	-	-	-	-	-

Notes: Me = transition metal CA = catalytic activity

Table 5

catalyst component	catalyst composition			mol ratio (A) : (C) : (B)
	(A)	(C)	(B)	
A23	Zr(OPr) ₄	indene	AlEt ₃	1 : 4 : 8
A24	Zr(OPr) ₄	indene	AlEt ₃	1 : 2 : 4
A25	Ti(OBu) ₄	indene	AlEt ₃	1 : 4 : 8
A26	Zr(OBu) ₄	indene	AlEt ₃	1 : 4 : 8
A27	Zr(OPr) ₄	indene	AlEt ₂ Cl	1 : 4 : 8
A28	Zr(OPr) ₄	fluorene	AlEt ₃	1 : 4 : 8
A29	Zr(OPr) ₄	cycloocta- tetraene	AlEt ₃	1 : 2 : 4
A30	Hf(OPr) ₄	indene	AlEt ₃	1 : 2 : 4
A31	Zr(OPr) ₄	indene	AlEt ₃	1 : 4 : 8
A32	Zr(OPr) ₃ Cl	indene	AlEt ₃	1 : 4 : 8
B11	Zr(OPr) ₄	-	-	-
B12	Zr(OPr) ₄	-	AlEt ₃	1 : 0 : 8
B13	Zr(OPr) ₄	indene	-	1 : 4 : 0
B14	Cp ₂ ZrCl ₂	-	-	-

Notes: Et = ethyl Bu = n-butyl Bz = benzyl
 Pr = n-propyl Ay = allyl Ph = phenyl
 Np = neophil

Table 6

Example	catalyst component solution, ml	MAO Me mol ratio	yield (g)	catalytic activity (g/gMe)	MI (g/10min)	density (g/cm ³)	DSC mp (°C)	Mw/Mn
Inventive 26	A23 0.2	1,000	82	60,000	0.2	0.9210	114.0	5.1
27	A24 0.1	1,000	89	65,000	0.5	0.9220	116.3	4.6
28	A24 0.1	500	48	35,000	0.08	0.9196	113.0	4.5
29	A25 0.35	1,000	73	15,000	0.02	0.9242	118.3	4.2
30	A26 0.2	1,000	97	71,000	0.8	0.9202	113.5	4.3
31	A27 0.2	1,000	64	47,000	0.3	0.9284	117.1	7.1
32	A28 0.2	1,000	25	18,000	0.6	0.9216	114.3	8.2
33	A29 0.1	1,000	19	14,000	3.6	0.9203	104.5	4.1
34	A30 0.1	1,000	29	21,000	0.03	0.9208	112.3	4.6
35	A31 0.2	1,000	93	68,000	0.6	0.9209	113.1	4.6
36	A32 0.2	1,000	103	75,000	0.7	0.9211	114.2	6.2
37	A33 0.2	1,000	110	80,000	0.1	0.955	131.9	4.3
Comparative 11	B11 0.2	1,000	0	-	-	-	-	-
12	B12 0.2	1,000	0	-	-	-	-	-
13	B13 0.2	1,000	19	13,000	1.45	0.9281	116.3	5.1
14	B14 0.2	1,000	57	25,000	23	0.9198	106.7	2.6


Notes: MAO = methylalumoxane Me = transition metal

As appears clear from the data shown in the above tables, the catalyst components provided by the invention can afford significantly high catalytic activity per transition metal used. The inventive catalyst components when combined with suitable promoters provide a catalyst composition useful in the homo- or co-polymerization of alpha-olefins, resulting in polymer products having increased molecular weight and broad molecular weight distribution, with a relatively narrow composition distribution for the copolymers obtained. Such copolymers typically of ethylene or propylene with other alpha-olefins which are produced with the use of the inventive catalyst components can be formed into sheets or films of high transparency without encountering objectionable mutual adhesion. The catalyst composition comprising the inventive components provides copolymers for example of ethylene and dienes which have a relatively high melting point despite their relatively low density and further provides block copolymers of olefins and polar monomers which have a relatively broad molecular weight distribution.

What is claimed is:


1. A catalyst component for use in the polymerization of olefinic hydrocarbons, said catalyst comprising:

- i) a compound (A) of the formula



where R^1 and R^2 each are hydrocarbon moieties of 1-24 carbon atoms; X^1 is a halogen atom; Me^1 is Ti, Zr or Hf; each of p and q independently is an integer of 0-4, provided that $p+q$ is 0-4;

- ii) a compound (B) of the formula



where R^1 and R^4 each are hydrocarbon moieties of 1-24 carbon atoms; X^2 is a halogen atom; Me^2 is an element included in Groups II and III of the Periodic Table; z is a valence of Me^2 ; each of m and n independently is an integer of 0-3, provided that $m+n$ is 1-3, and


- iii) an organocyclic compound (C) having two or more conjugated double bonds and a modified organoaluminum compound derived from the reaction of an organoaluminum compound with water and having 1-100 Al-0-Al bonds in the molecule.

2. A catalyst component as claimed in claim 1 wherein said R^1 and R^2 each are selected from the group of alkyl, alkenyl, aryl and aralkyl groups.

3. A catalyst component as claimed in claim 1 or claim 2 wherein said compound (A) is one selected from the group of tetramethylzirconium, tetraethylzirconium, tetrabenzylzirconium, tetraethoxyzirconium, tetraisopropoxyzirconium and tetra-n-butoxyzirconium.


4. A catalyst component as claimed in claim 1 wherein said compound (B) is one selected from the group of ethyllithium, methylmagnesium chloride, ethylmagnesium chloride, n-butylmagnesium chloride, phenylmagnesium chloride, diethylzinc, trimethylboron, diethoxyaluminum chloride, diethylaluminum chloride and diethylaluminum ethoxide.
5. A catalyst component as claimed in claim 1 wherein said compound (C) is a cyclic hydrocarbon compound having two or more conjugated double bonds and a total carbon number of 4-24.
6. A catalyst component as claimed in claim 1 wherein said compound (C) is an organosilicon compound having two or more conjugated double bonds and cyclic hydrocarbon groups having a total carbon number of 4-24.
7. A catalyst component as claimed in claim 1 wherein said compounds (A), (B) and (C) are blended in molar ratio of (A):(B) of 1:0.1 -100, and in a molar ratio (A):(C) of 1:0.1-100, respectively.
8. A process for the polymerization of olefinic hydrocarbons which comprises polymerizing an olefinic hydrocarbon in the presence of a catalyst composition comprising a catalyst component comprised of

- i) a compound (A) of the formula



where R^1 and R^2 each are hydrocarbon moieties of 1-24 carbon atoms; X^1 is a halogen atom; Me^1 is Ti, Zr or Hf; each of p and q independently is an integer of 0-4, provided that $p+q$ is 0-4;

- ii) a compound (B) of the formula



where R^3 and R^4 each are hydrocarbon moieties of 1-24 carbon atoms; X^2 is a halogen atom; Me^2 is an element included in Groups II and III of the Periodic Table; z is a valence of Me^2 ; each of m and n independently is an integer of 0-3, provided that $m+n$ is 1-3;

- iii) an organocyclic compound (C) having two or more conjugated double bonds, and
- iv) a modified organoaluminum compound derived from the reaction of an organoaluminum compound with water and having 1-100, Al-O-Al bonds in the molecule.