



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2167890 C 2006/06/06

(11)(21) **2 167 890**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1996/01/23

(41) Mise à la disp. pub./Open to Public Insp.: 1996/07/25

(45) Date de délivrance/Issue Date: 2006/06/06

(30) Priorité/Priority: 1995/01/24 (SE9500264-8)

(51) Cl.Int./Int.Cl. *C01F 7/00* (2006.01),
C01F 7/16 (2006.01), *C01F 7/74* (2006.01),
C01F 7/56 (2006.01)

(72) Inventeurs/Inventors:
KVANT, MAGNUS, FR;
BARSTROM, ROGER, SE

(73) Propriétaire/Owner:
KEMIRA KEMI AKTIEBOLAG, SE

(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : METHODE DE PREPARATION DE SOLUTIONS DE SEL D'ALUMINIUM

(54) Title: PROCESS FOR THE PREPARATION OF ALUMINUM SALT SOLUTIONS

(57) **Abrégé/Abstract:**

The present invention relates to a process for the preparation of solutions of aluminum salts, characterized in that an aluminate of an alkali metal and/or alkaline earth metal is dissolved in an acid solution to the formation of a solution which is used as such or is diluted to a suitable concentration.



ABSTRACT

The present invention relates to a process for the preparation of solutions of aluminum salts, characterized in that an aluminate of an alkali metal and/or alkaline earth metal is dissolved in an acid solution to the formation of a solution which is
5 used as such or is diluted to a suitable concentration.

10

15

20

25

PROCESS FOR THE PREPARATION OF ALUMINUM SALT SOLUTIONSDESCRIPTIONTechnical field

- 5 The present invention relates to a process for the manufacture of aluminum salt solutions.

The object of the present invention is to obtain a rational and cost efficient process for the manufacture of solutions of aluminum salts, such as of aluminum chloride,
10 aluminum sulphate and mixed salts.

Background of the invention

At purification of water different types of aqueous solutions of metal salts, such as aluminum sulphate, aluminum chloride, ferri chloride, and the similar are used. The
15 basic polysalts of aluminum chloride and aluminum sulphate or mixed aluminum-ferri chloride are in this case particularly effective and of interest. Common to all processes for the manufacture of such solutions are that they all require high temperatures and concentrated acids in order to have the dissolution and reaction with the minerals, which are the source of the metal salts, to run with a reasonable
20 speed. Due to these process parameters all equipment has to be made of corrosion resistant materials, as well as the equipment materials shall all be able to resist high pressures in those cases an elevated pressure is used to speed up the process.

- 25 Further the process capacity of the plants is limited due to the fact that the reaction time is long, two hours being the shortest time, and is hereby due for the more simple products, such as aluminum sulphate and aluminum chloride. More advanced products, such as the basic salt solutions require a longer time and e.g.,

22055-145

polyaluminum chloride-sulphate requires 6 hrs at 160°C to be produced.

There is thus a well grounded demand for obtaining better processes which can increase and cost-reduce the production of such aluminum and ferri salt solutions, in particular since the world community today requires increased water purification of economically weak nations and communities as well.

Description of the present invention

It has now surprisingly been shown possible to meet this demand by means of the present invention which is characterized in that an aluminate of an alkali metal and/or alkaline earth metal is dissolved in an acid solution to the formation of a solution which is used as such or is diluted to a suitable concentration.

By means of the present invention it is obtained that the demand for concentrated acids, high temperatures and sophisticated process equipment is eliminated.

In one aspect, the present invention provides a process for the preparation of solutions of aluminum salts, wherein a solid calcium or magnesium aluminate is dissolved at atmospheric pressure in an acid solution to the formation of a solution which is for use as such for water purification or is diluted to a suitable concentration.

As starting material for the present process solid alkali aluminates, such as portland cement like minerals of the type CIMENT FONDU, calcium-aluminum-iron-titanium-silicate cement, can be used. These cement types having high aluminum contents are commercially available and the

22055-145

production thereof is well known. See for example The
Chemistry of Cement and Concrete by F.M. Lea, E. Arnold
(Publishers) Ltd. 3rd ed. pp 490-527. These cements contain
typically 30 to 75% of Al_2O_3 . They are produced by heating
5 aluminum containing minerals, such as bauxite and aluminum
hydroxide with calcium carbonate, whereby carbon dioxide is
released and the cement is formed. This is then ground to a
fine powder for further use. These types of cement are
usually used for applications which shall resist high
10 temperatures.

It has now turned out that these cements dissolve immediately in diluted acids, such as 10-15 % hydrochloric acid in an extremely short time, and that the compounds obtained have the same properties as those prepared in a conventional way. Thus a cement fondu comprising 40 % Al_2O_3 dissolves in 15 % hydrochloric acid within 5 minutes without any addition of heat and at atmospheric pressure, whereby a mixed polyaluminum chloride, a so called PAX, having 75 % basicity is obtained. Furthermore, the product showed improved properties in flocculating tests, which properties were superior to the properties of conventionally produced products of polyaluminum chloride having the same basicity.

10

Solid aluminates, such as cement fondu or sintered aluminates can be produced using different starting alkali metals or alkaline earth metals, such as calcium, magnesium, and sodium. The aluminates can be produced by sintering or melting a mixture of aluminum hydroxide and suitable salts of calcium, magnesium and sodium. Hereby the oxides or carbonates are preferably used. Other methods for the production of alkali aluminates are known, as well.

15

The present invention is not restricted to the use of cement fondu, but other solid aluminates produced in a different way can be used in the same way.

20

Example 1

A calcium aluminate cement obtained from LaFarge Fondu International, 157, Av. Charles de Gaulle, F-92521 Neuilly-sur-Seine, France was used for dissolution.

The cement had a typical composition as follows:

25

Al_2O_3	50 %
CaO	40 %
Fe_3O_4	17 %

25 grammes of this cement was mixed with 100 g of 16 % hydrochloric acid having a temperature of 10°C. After about 5 min. the reaction had ceased. The solution now contained a polyaluminum-ferri chloride having

- 5 4.95 % Al
1.7 % Fe
Basicity 65 %.

Example 2

- 10 For the preparation of a calcium aluminate, alumium hydroxide was mixed with calcium oxide or calcium carbonate in a molar ratio of 0.30 to 2.0:1 of calcium:aluminum, whereupon sintering was carried out at 1000 to 1400°C for 0.5 to 2.5 hrs. Sintering can be carried out at a temperature of 700 to 1900°C, whereby the time for completing the sintering is changed correspondingly.

15

Dissolution of sintered aluminate

10 g of calcium aluminate having a mol ratio Ca:Al of 1.0:1 were mixed with 37 g of 37 % hydrochloric acid whereby a complete dissolution was obtained within 5 min.

The dissolution provided a polyaluminum solution having an Al content of 5.5 %

- 20 and a molar ratio $\text{OH/Al} = 1.5$, i.e. a basicity of 50%.

10 g of calcium aluminate having the molar ratio Ca:Al 0.5:1 were mixed with 38 g of 37 % hydrochloric acid, which provided a polyaluminum solution having an Al content of 6.3 and a molar ratio $\text{OH/Al} = 1.19$, i.e. a basicity of 40%.

25

Example 3

Calcium and magnesium aluminates, respectively can be produced in different ways. Thereby one can add aluminum hydroxide and a salt of calcium or magne-

sium to sodium hydroxide, whereupon the mixture is boiled for 1 to 6 hrs. The aluminate formed precipitates and is filtered off. Alternatively, a calcium salt or magnesium salt can be added to a hot or cold sodium aluminate solution whereby an aluminate of calcium or magnesium precipitates which can be filtered off. In both cases there is an excess of aluminum present in the solution.

Dissolution of aluminate produced according to a wet method
10 g of calcium aluminate having a molar ratio $\text{Ca:Al} = 1.5$ were dissolved in 25 g of 37 % hydrochloric acid which provided a polyaluminum solution having an aluminum content of 4.4 % and a molar ratio $\text{OH/Al} = 1.6$, i.e. a basicity of 53%.

For the dissolution of solid aluminates different inorganic acids can be used, such as HCl , HNO_3 , H_2SO_4 , in order to provide different coagulants, i.e. flocculating agents for the purification of e.g. sewage water. But also an aluminum chloride solution, which is acidic, can be used for the preparation of the aluminum solutions from the aluminate, whereby it is obtained that the aluminum content and the basicity can be further increased. The efficiency of a coagulant is dependent of the basicity of the solution. The desire to reach high contents of aluminum is mostly dependent on transport economical reasons.

By means of the present invention acids having lower concentrations than usual can be used, which is of importance as such acids are considerably more safer to handle, produce considerably smaller impact on the environment at the dissolution and furthermore they have a much lower price. Thus residual acids from the pickling of metal objects can be used. Hereby such acids very often contains iron and aluminum which means that these residual products can be reclaimed. Today such acids are commercially completely unprofitable and be obtained for a small cost as no use for these acids is at hand and as they are a waste problem for the

industry.

At the precipitation of impurities at the purification of water solutions having a concentration of 1 to 2 % of Al are used.

5

10

15

20

25

22055-145

CLAIMS:

1. A process for the preparation of solutions of aluminum salts, wherein a solid calcium or magnesium aluminate is dissolved at atmospheric pressure in an acid solution to the formation of a solution which is for use as such for water purification or is diluted to a suitable concentration.
2. The process according to claim 1, wherein the solid aluminate has a Ca/AL or Mg/AL molar ratio greater than 0.3.
3. The process according to claim 1, wherein the aluminate used has been prepared according to a wet process.
4. The process according to any one of claims 1-3, wherein the acid solution comprises an inorganic acid.
5. The process according to claim 4, wherein the acid solution comprises a residual acid.
6. The process according to claim 5, wherein the residual acid contains aluminum or ferri-chloride.
7. The process according to claim 5 or 6, wherein the acid solution comprises acid having a content of at least 10 weight % of HCl.
8. The process according to claim 1, wherein the acid solution is an acidic solution of aluminum salt.
9. The process according to claim 1, wherein the dissolution is carried out without the addition of heat.