

SPRUSON & FERGUSON

AUSTRALIA

PATENTS ACT 1990

PATENT REQUEST: STANDARD PATENT

I/We, the Applicant(s)/Nominated Person(s) specified below, request I/We be granted a patent for the invention disclosed in the accompanying standard complete specification.

[70,71] Applicant(s)/Nominated Person(s):

The Goodyear Tire & Rubber Company, incorporated in Ohio, of 1144 East Market Street, Akron, Ohio, 44316-0001, UNITED STATES OF AMERICA

[54] Invention Title:

Tires with Dyed Indicia

[72] Inventor(s):

Ramendra Nath Majumdar and John Richard White

[74] Address for service in Australia:

Spruson & Ferguson, Patent Attorneys
Level 33 St Martins Tower
31 Market Street
Sydney New South Wales Australia (Code SF)

Details of Basic Application(s):

[31] Appl'n No(s):

448,635

[33] Country:

US

[32] Application Date:

23 May 1995

DATED this TWENTY SECOND day of MAY 1996

The Goodyear Tire & Rubber Company

By:



Registered Patent Attorney

IRN: 336386

INSTR CODE: 54815

066141 220596

SPRUSON & FERGUSON

AUSTRALIA

Patent Act 1990

NOTICE OF ENTITLEMENT

I, Kathleen Michele Easterling, of THE GOODYEAR TIRE & RUBBER COMPANY of 1144 East Market Street, Akron, Ohio 44316-0001, United States of America, being authorized by the Applicant(s)/Nominated Person(s) in respect of an application entitled:

TIRES WITH DYED INDICIA

state the following:

The Applicant/Nominated Person has, for the following reasons, gained entitlement from the actual inventor(s):

The Applicant/Nominated Person is the assignee of the basic applicant(s)/
inventors.

The Applicant/Nominated Person is entitled to rely on the basic application listed on the Patent Request as follows:

The Applicant/Nominated Person is the assignee of the basic applicants.

The basic application(s) listed on the Patent Request is the application first made in a Convention Country in respect of the invention.

Dated this 20th day of March, 1996.

THE GOODYEAR TIRE & RUBBER COMPANY

By Kathleen Michele Easterling
Kathleen Michele Easterling, Administrator
International Patents

IRN:

INSTR. CODE:



AU9652448

(12) PATENT ABRIDGMENT (11) Document No. AU-B-52448/96
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 698488

- (54) Title
TIRES WITH DYED INDICIA
- International Patent Classification(s)
(51)⁶ C09D 011/02 B60C 001/00 B60C 019/00
- (21) Application No. : 52448/96 (22) Application Date : 22.05.96
- (30) Priority Data
- (31) Number (32) Date (33) Country
448635 23.05.95 US UNITED STATES OF AMERICA
- (43) Publication Date : 05.12.96
- (44) Publication Date of Accepted Application : 29.10.98
- (71) Applicant(s)
THE GOODYEAR TIRE & RUBBER COMPANY
- (72) Inventor(s)
RAMENDRA NATH MAJUMDAR; JOHN RICHARD WHITE
- (74) Attorney or Agent
SPRUSON & FERGUSON , GPO Box 3898, SYDNEY NSW 2001
- (56) Prior Art Documents
US 3577261
US 3729041
- (57) Claim

1. A pneumatic tire, comprising:

a toroidal shaped carbon black filled vulcanized rubber composition having integral therewith, a crosslinked non-black rubber composition comprising at least one hydrocarbon rubber having less than 10 weight percent of polar groups therein, a white pigment, and a hydrocarbon soluble dye solution comprised of a dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ absorbed into at least a portion of said crosslinked non-black rubber composition, said non-black rubber composition having an exposed surface with a CIE 1976 L* value of at least 40.

9. A process for dyeing a pneumatic tire, comprising the steps of:

applying a dye solution to at least one selective external surface of a crosslinked non-black rubber composition integral with said pneumatic tire, said dye solution being comprised of a dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$, said solvent containing less than 10 percent by weight of polar atoms other than halogens based upon the total weight of said solvent, said dye being soluble in said hydrocarbon solvent;

forming a dye penetration layer in said non-black rubber composition at said selective surface; and

evaporating said hydrocarbon solvent.

14. A rubber article, comprising:

a crosslinked substrate and an adhered crosslinked non-black rubber composition layer thereon having a swelling capacity in a hydrocarbon solvent of at

(11) AU-B-52448/96

-2-

(10) 698488

least 75 percent, a penetration layer located in the exterior portion of said non-black rubber composition layer up to the thickness thereof, and said penetration layer containing a dye solution comprised of a dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ therein.

18. An apparatus for dyeing a crosslinked swellable non-black rubber composition, comprising:

a dispenser having a receptacle containing a dye solution comprising a hydrocarbon soluble dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$, and having less than 10 percent by weight of polar atoms based upon the weight of said solvent, and an applicator in fluid communication with said receptacle.

22. A dye elastomer, comprising:

a crosslinked, non-black, swellable hydrocarbon rubber having less than 10 weight percent of polar groups, a white pigment; and

a hydrocarbon soluble dye dissolved in a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ absorbed into at least one surface of said swellable, non-black hydrocarbon rubber, and wherein said swellable hydrocarbon rubber has less than 2 PHR of carbon black.

AUSTRALIA
PATENTS ACT 1990

COMPLETE SPECIFICATION

FOR A STANDARD PATENT

ORIGINAL

Name and Address
of Applicant:

The Goodyear Tire & Rubber Company
1144 East Market Street
Akron Ohio 44316-0001
UNITED STATES OF AMERICA

Actual Inventor(s): Ramendra Nath Majumdar and John Richard White

Address for Service: Spruson & Ferguson, Patent Attorneys
Level 33 St Martins Tower, 31 Market Street
Sydney, New South Wales, 2000, Australia

Invention Title: Tires with Dyed Indicia

The following statement is a full description of this invention, including the best method of performing it known to me/us:-

TIRES WITH DYED INDICIA

Field of Invention

5 The present invention relates to dyeing non-black solvent swellable elastomeric articles or products. More specifically, the present invention relates to a dye solution which is generally a hydrocarbon soluble dye dissolved in a hydrocarbon solvent, the dye solution being utilized to penetrate and dye a non-black swellable-hydrocarbon rubber. The non-black rubber may in general be integral or adhered to an elastomeric or thermoset substrate. An apparatus for applying the dye solution is provided as a dispenser comprised of a reservoir and an applicator such as a felt tip. The present invention is particularly directed to dyeing white sidewall portions or white lettering or indicia of pneumatic tires.

Background

20 Heretofore, colored vulcanized elastomers have often been prepared by mixing finely divided pigments with uncured rubber followed by vulcanizing the rubber composition. Such elastomers generally have a very uniform color which is resistant to abrasion in the sense that a pigment is dispersed throughout the rubber composition.

25 U.S. Patent 3,577,261 provides a quick method for identifying uncured rubber stocks and rubber cements by the effect of a dye therein on an adherent layer applied thereto. The adherent layer includes particulate pigments and a solvent. The solvent picks up dye from the substrate of rubber stock or rubber cement and imparts the color of the dye to the adherent layer. It is implied that the color of the dye within the rubber stock or rubber cement is hard to visually perceive because of colored pigments (such as carbon black) in

the substrate.

White sidewalls and raised white letters on pneumatic tires are often composed of stain resistant elastomers, particularly elastomers having large amounts of isobutylene repeat units such as butyl rubber and halobutyl rubber, as well as EPDMs so that common contaminants on the roadways such as motor oils, salt, cinders, tars and also staining oils and vulcanization accelerators within the adjoining black elastomer portions of the tire do not readily stain or discolor the white regions.

Summary of the Invention

In accordance with this invention, a sulfur vulcanized rubber composition is provided comprised of a white colored rubber composition which contains titanium dioxide pigment as a white colorant in the absence of carbon black, wherein at least one surface of said white rubber composition is subsequently colored by applying an organic solvent solution of an oil soluble dye to said vulcanized rubber composition surface. Said solution of dye penetrates and swells said rubber surface and colors at least one rubber surface with the dye. Said solvent subsequently evaporates.

In the practice of this invention, the hydrocarbon solvent of the said dye solution swells the vulcanized rubber composition to create a permeable rubber surface to permit a migration, or penetration of the dye into the white pigment-colored rubber. A dyed rubber penetration layer is thereby formed in the surface of the said rubber composition.

In further accordance with this invention, a hydrocarbon solvent solution is provided which is comprised of an oil soluble dye dissolved in a hydrocarbon solvent having a solubility parameter of from about 12 to about 20, $[J/m^3]^{1/2} \cdot 10^{-3}$, said solvent

desirably containing less than 10 parts by weight of polar atoms per 100 parts by weight of said solvent.

5 Another aspect of the present invention relates to a dyed elastomer comprising a crosslinked, non-black swellable hydrocarbon rubber having less than 10 weight percent of polar groups, a white pigment, and a hydrocarbon soluble dye absorbed into at least one surface of said swellable hydrocarbon rubber.

10 Yet another aspect of the present invention relates to a rubber article comprising a crosslinked or thermoset substrate and an adhered crosslinked, non-black rubber composition layer thereon having a swelling capacity of at least 75 percent, a penetration layer located in the exterior portion of said non-black rubber composition layer, said penetration layer having a thickness up to the thickness of said non-black rubber composition, and said penetration layer containing a dye therein.

20 A still further aspect of the present invention relates to a process for dyeing a pneumatic rubber tire, comprising the steps of applying a dye solution to at least one selective external surface of a crosslinked non-black rubber composition integral with said pneumatic tire, said dye solution being comprised of a dye and a hydrocarbon solvent having a solubility parameter of from about 12 to about 20 $[J/m^3]^{1/2} \cdot 10^{-3}$, said solvent containing less than 10 percent by weight of polar atoms other than halogen based upon the total weight of said solvent, said dye being soluble in said hydrocarbon solvent, forming a dye penetration layer in said crosslinked, non-black rubber composition at said selective surface, and evaporating said hydrocarbon solvent.

35 A still further aspect of the present invention relates to a pneumatic tire comprising a toroidal shaped, carbon black filled vulcanized rubber

composition having integral therewith, a crosslinked, non-black rubber composition comprising at least one hydrocarbon rubber having less than 10 weight percent of polar groups therein, a white pigment, and a hydrocarbon soluble dye absorbed into at least a portion of said crosslinked, non-black rubber composition, said non-black rubber composition having an exposed surface with a CIE 1976 L* value according to ASTM E-308-94a of at least 40.

A still further aspect of the present invention relates to an apparatus for dyeing a swellable non-black rubber composition, comprising a dispenser having a receptacle containing a dye solution comprising a hydrocarbon soluble dye and a hydrocarbon solvent having a solubility parameter of from about 12 to about 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ and having less than 10 percent by weight of polar atoms based upon the weight of said solvent, and an applicator in fluid communication with said receptacle.

Brief Description of Drawing

The drawing relates to a cross-sectional view of a dispenser containing a dye solution therein for dyeing a non-black hydrocarbon rubber.

Detailed Description of the Invention

The invention generally relates to any vulcanized rubber article, generally black because it contains carbon black therein, which has a non-black, solvent swellable, hydrocarbon rubber portion thereon or integral therewith. The present invention will be described with respect to a preferred embodiment of white tire sidewalls, the white sidewall region being a component in a toroidal-shaped pneumatic tire. It is to be understood that it can also be applied to numerous articles or products such as bumper strips, vehicle

protection or trim strips, tennis shoes and the like. The white regions on a tire sidewall are generally prepared by assembling a white colored compounded rubber with the tire forming components during the assembly of a green (uncured) tire. The white colored rubber is desirably crosslinked in the mold with the other portions of the tire. The white colored component is formulated so that it is compatible with the other components and bonds well with the crosslinked elastomers of the tire.

While a preferred embodiment of the disclosure of the invention relates to dyeing a white tire sidewall, it is to be understood that generally any non-black rubber can be dyed. By the term "non-black" it is meant any color or reflectivity which is greater than zero, on the CIE 1976 L^* scale such as rubbers which have a CIE 1976 L^* value, of at least 40, desirably at least 50, preferably at least 60, and more preferably at least 70, 80, or 85 before dyeing. A pure white color on the CIE 1976 L^* scale has a value of 100, while a black color has a value of 0. Reference to the CIE 1976 L^* scale can be readily found in ASTM E 308-94a.

A preferred method of forming the white regions of the sidewall is to extrude the white colored component to another (generally black) tire component. The extruded white colored compound has a thin skin of a compounded rubber that matches the composition and color of the tire and which covers the white rubber component. When this covered white component is cocured with the tire and thus adhered or chemically joined thereto, the entire tire sidewall appears to be one color irrespective of whether raised or depressed regions are present on the tire such as letters, or rings, logos, etc. The tire manufacturer can then expose the white component by grinding or abrading away the thin skin to remove the same and expose any desired regions of white

rubber. Typically letters spelling a trade name, tire sizes, shape designation, etc. are raised letters (protrude above the rest of the sidewall) while rings around the tire can be raised or recessed.

5 Pneumatic tires generally comprise a tread region which is designed to contact the road or path, two or more sidewalls which help contain the air and provide lateral support, and bead areas which make contact with a rim.

10 The dyeable, non-black, solvent swellable, hydrocarbon elastomers or rubber compositions of the present invention are either substantially free or completely free of polar groups other than small amounts of halogens as in butyl rubber. Desirably, the one or
15 more elastomers have an average of less than 10 weight percent, more desirably less than 5 weight percent, preferably less than 3 or 2 weight percent, and more preferably completely free (i.e., 0 percent) of polar groups. Such polar groups are carboxylic acids, sulfites, sulfates, alkali salts of carboxylic acids, esters, etc., and specifically include amine, sulfonyl, carbonyl, hydroxyl, nitrile, carboxyl, alcohol, ether linkages, and other groups. In calculating these weight
20 percents, only the polar group is considered while attached alkyl or aromatic groups are excluded. Desirably excluded (i.e., substantially free or completely free of) from this embodiment or used in such small amounts to result in an elastomer blend having less than the above specified amounts of polar groups
25 are butadiene-acrylonitrile polymers, acrylate polymers and other polar elastomers.

30 Suitable dyeable elastomers include copolymers having at least 50, desirably at least 80 and preferably at least 90 weight percent repeat units from C_4 to C_7 isomonoolefins, lightly halogenated versions thereof
35 (e.g., less than 5 percent by weight halogen), polydiene

(i.e., C_4 to C_{12}) homopolymers or copolymers; copolymers of diene (C_4 to C_{12}) and vinyl aromatic monomers (C_8 to C_{15}); natural rubber, ethylene propylene rubbers, hydrogenated polymers or copolymers of (C_4 to C_{12}) dienes, and the like. The lightly halogenated versions of the above polymers are used due to beneficial changes in cure behavior and are not considered as polar polymers.

Preferable elastomer compositions for white sidewall portions comprise from about 20 to about 80 parts by weight of a copolymer having at least 50 weight percent repeat units from C_4 to C_7 isomonoolefin monomers (e.g., butyl rubber), more desirably from about 25 to about 65 parts by weight; optionally up to 30 parts by weight of an ethylene-propylene diene monomers rubber (EPDM), more desirably up to 25 parts by weight; and up to 80 parts by weight of a homopolymer or copolymer of one or more conjugated diene monomers and optionally with vinyl substituted aromatic monomers, more desirably from about 15 to about 75 parts by weight wherein all parts by weight are per 100 parts by weight (PHR) of total rubbers in the composition.

The carbon black filled portion of a tire sidewall often contains antioxidants and other oil soluble components which tend to discolor or stain many white rubber compounds. Often the antioxidants and other oil soluble components give desirable properties to the tire which cannot be achieved with non-staining components. Therefore, tire sidewall portions which are to be white or light colored, are compounded with large amounts (e.g., greater than 30 PHR, more desirably greater than 40 PHR, and preferably greater than 50 PHR of rubbers having predominantly repeat units from one or more isomonoolefin (C_4 - C_7) monomers (e.g., butyl rubber). The non-permeable nature of polymers from isomonoolefin monomers such as isobutylene (e.g., butyl or halobutyl

rubber) is the reason why these rubbers are used nearly exclusively (instead of natural rubber or styrene-butadiene rubber) for innertubes and tire innerliners. These isobutylene based rubbers as a cured layer slow the diffusion of pressurized air from inside the tire to a negligible rate. Similarly, polymers from isomonoolefins such as isobutylene slow the diffusion of staining ingredients such as oils, thus preventing undesirable staining of white sidewalls. The effect of polymers from isomonoolefins of preventing dye migration into the rubber is minimized in this application by applying the dye with a solvent that swells the rubber and facilitates migration of dye into the rubber. Desirably, the copolymer of at least 50 weight percent isomonoolefin is a copolymer of at least 50 weight percent isobutylene or halogenated isobutylene.

Desirably, the copolymer having at least 50 weight percent of a isomonoolefin comprises butyl rubber (typically a polymer with from about 95 to about 99 weight percent isobutylene repeat units and from about 1 to about 5 weight percent of diolefin repeat units) or chlorinated or brominated butyl rubber (having from about 0.25 to about 2.5 weight percent halogen, more desirably from about 0.5 to about 1.75 weight percent halogen). Other desired copolymers having at least 50 weight percent of isomonoolefins are derived from polymerizations of C₄ to C₇ isomonoolefins with p-alkylstyrenes having from about 80 to about 99 weight percent, more desirably from 85 to 98 weight percent isomonoolefin repeat units and from about 1 to about 20 weight percent, and more desirably from about 2 to about 15 weight percent of p-alkylstyrenes. These polymers of isomonoolefins and p-alkylstyrenes are made by Exxon. A preferred copolymer is a brominated copolymer with up to 5 weight percent bromine, more desirably from about 0.2 to about 1.5 or 2.5 weight percent bromine, and from

about 85 to about 98 weight percent isobutylene repeat units and from about 2 to about 15 weight percent p-methylstyrene. The predominate site of bromination is the p-methyl group.

5 Desirably the ethylene propylene diene monomer (EPDM) copolymer comprises repeat units of from about 20 to about 90 weight percent, and more desirably from about 30 to about 85 weight percent ethylene, from about 10 to about 80 weight percent, more desirably from about 15 to about 70 weight percent of at least one alpha olefin having from 3 to 16 carbon atoms (usually mostly propylene) based on the total of ethylene and alpha olefins having from 3 to 16 carbon atoms, and from about 0.1 to about 0.8 moles of one or more nonconjugated
10 dienes having from 6 to 12 carbon atoms per kilogram of EPDM polymer.
15

Desirably the homopolymer or copolymer of a conjugated diene monomer is natural rubber or a synthetic polymer comprised of at least 50 and usually at least 70 weight percent repeat units derived from one or more conjugated diene monomers having from 4 to 8 or 12 carbon atoms. Natural rubber (comprising repeat units of isoprene) is preferred. A desirable comonomer for the residual of the copolymer is vinyl aromatic monomers of from 8 to 12 carbon atoms such as styrene. Preferred polymers include polybutadiene and polyisobutylene. Polar monomers such as acrylates, acrylics, itaconic acid, etc., if utilized at all, are only used in amounts so the total amount of polar groups do not exceed the specified percentages. Other non-
20 polar monomers can also be used in the polymers or copolymers of this elastomer.
25
30
35

The solvent swellable rubber compositions of the present invention are not dyed until they are cured (vulcanized or crosslinked). The crosslink density is generally measured by volume swelling capacity with a

good solvent. Lower crosslink density is associated with fewer crosslinking occurrences per polymer chain, and low crosslink density results in greater swelling capacity of the cured rubber in a good solvent.

5 Suitable swelling by percent volume in cyclohexane solvent is at least 50 percent, desirably at least 75 percent, 100 percent, or 125 percent, and preferably at least 150 percent or 175 percent by volume of the solvent swellable rubber after soaking overnight at room

10 temperature, i.e., 24 hours at 25°C. Only after the solvent swellable hydrocarbon rubbers such as an elastomeric tire sidewall has been shaped and crosslinked into a final article or end product is the dye applied thereto. This is in distinct contrast to

15 the occasional use of pigments in rubber compounds wherein the pigment was always dispersed in the rubber before crosslinking or vulcanization occurs.

Known crosslinking agents (also known as curatives) which can be used include sulfur, sulfur accelerators, peroxides, other non sulfur curatives, sulfur donor compounds, etc. Sulfur accelerators include guanidines, thiurams, dithiocarbamates, thioureas, thiazoles, sulfenamides and xanthates. Peroxides include dialkyl peroxides, peresters, hydroperoxides, peroxydicarbonates, etc. Crosslinking agents also include zinc oxide, etc. The use of these crosslinking agents, their effective amounts, etc., are well known to the art. Vulcanization is a subset of the crosslinking process. Crosslinking agents are also known as curatives. Crosslinking is often called curing in the art of rubber processing.

Fillers can be added to the non-black, solvent swellable rubber composition. Fillers generally are particulate material added to either reduce the total cost or to enhance the stiffness and/or chemical resistance of a composition. Reinforcing fillers tend to

enhance the strength of a composition. While carbon black can be utilized, it is not desirable in non-black articles and hence is used in low amounts such as less than 2 PHR, more desirably less than 1.5 or 1 PHR, and preferably less than 0.5 or 0.25 PHR such that the composition would not be black and would be capable of reflecting some colored light as a result of dyeing. Preferably, the dyed elastomers of the present invention are substantially free if not completely free, that is zero parts of carbon black per 100 parts of rubber. Rubber compositions with more than these amounts are generally referred to as black surfaces while those with less than these amounts are generally referred to as non-black.

Suitable and desired fillers include talc, clay, silica, calcium carbonate, etc. These may function in addition as pigments or pigment extenders but their principal function is as fillers. Pigments are desirably added to the composition. Desirably only white pigments are added since white can be dyed to any other color. Thus, any white or non-black pigments which reflect light can be used in these rubber formulations. Desirably, the pigments used have good color retention during aging and resistance to discoloring or degrading on U.V. exposure or they are formulated with age resistors or U. V. protectors to provide color integrity in the final product. The pigments desirably are insoluble in the elastomer component and are consequently dispersed in particulate form. Desirable pigments include titanium dioxide, zinc oxide, white lead and antimony oxide, as well as precipitated silica, calcium silicate, calcium carbonate, treated clays, talc, and whiting.

Other additives added to the solvent swellable hydrocarbon composition can include processing aids which generally enhance a composition's speed and ease

of processing. They may function by reducing an elastomer's molecular weight or by lubricating the elastomer's surface. Age resistors and U.V. protectors may be added to the composition. Waxes are desirably used because they tend to bloom to the surface and protect the elastomer immediately below the waxy surface. The additives may absorb or neutralize harmful materials or energy or they function to block a mechanism of aging or degradation.

While processing oils are often used in rather large amounts in tires and other molded or shaped elastomer articles, if utilized in the non-black, solvent swellable rubber, they are desirably utilized in small amounts. To enhance the compatibility of the elastomer with the dye, the oil generally has the same solubility parameter as the elastomer and/or the solvent for the dye and thus are compatible therewith. Small amounts of oils are from about 1 or to about 15 PHR and desirably from about 2 to about 10 PHR. The process oils can include non-staining oils such as naphthenic, paraffinic, and the like.

The hydrocarbon solvents which can be utilized to swell the non-black hydrocarbon rubber compositions generally have a solubility parameter of from about 12 to about 20, desirably from about 13 to about 18, and preferably from about 14 to about 17.5 $[J/m^3]^{1/2} \cdot 10^{-3}$. Such solvents can be identified in the Polymer Handbook, Second Edition, edited by J. Brandrup and E. H. Immergut, John Wiley and Sons, New York, NY (1975), pages IV-337-347, which is hereby fully incorporated by reference. If a blend of two or more different solvents is utilized, the solubility parameter of the overall blend generally lies within the above-noted ranges. Generally, but not always, solvents which have such suitable solubility parameters can be classified as terpene based solvents such as KNI Solvent-2000, and the

like; various naphtha solvents such as high flash naphthas, petroleum naphtha, mineral spirits, and the like; various fuel oils such as kerosene, fuel oil no. 2, fuel oil no. 4, and the like; various alkanes including halogenated alkanes such as cyclohexane, hexane, heptane, octene, decane, dodecane, methylene chloride, chloroform, and the like; and various aromatic solvents including halogenated aromatics such as toluene, various Tolusols generally containing C₇ hydrocarbons and significant amounts of aromatic compounds therein, xylene, dichlorobenzene, and the like. Another, but not highly desired class of solvents include the various ethers, desirably those having a high molecular weight such as diphenyl ether, and the like. A highly preferred solvent is RE-ENTRY® KNI Solvent-2000, a terpene based solvent from Envirosolv Inc., also d.b.a. Environmental Solvents Corporation of Jacksonville, Florida.

The hydrocarbon solvents with the exception of halogenated solvents are generally substantially free or completely free of polar atoms and/or groups. That is, the weight of the total number of any polar atoms and/or groups therein is generally less than 10 percent by weight, desirably less than 5 percent by weight, more desirably less than 3 or 2 percent by weight, and preferably nil, that is, zero percent by weight based upon the total weight of the solvent. Polar atoms include oxygen, nitrogen, sulfur, and the like. Polar groups are defined with respect to the hydrocarbon elastomers. Although halogenated solvents are suitable even though they are polar, they are generally not desired due to environmental reasons.

The desired non-polar solvents are generally poorly hydrogen bonded except for the ethers which are moderately hydrogen bonded. Otherwise, moderately hydrogen bonded and strongly hydrogen bonded solvents

are avoided and thus are not within the scope of the present invention inasmuch as they generally do not effectively swell non-black rubber compositions. Moderately hydrogen bonded solvents which are avoided, generally include various esters, ketones, glycol monoethers, and the like. Strongly hydrogen bonded solvents include various alcohols, amines, acids, amides, aldehydes, and the like. Numerous examples of solvents having the above noted solubility parameters as well as being characterized as poorly, moderately, or highly hydrogen bonded are set forth in the Polymer Handbook.

Another desired attribute of the hydrocarbon solvents of the present invention is that they have a flash point of at least 100°F, (38°C) more desirably at least 125°F (52°C), and preferably at least 140°F (60°C); have no health effects at the typical exposure levels; and not be hazardous to the environment (desirably biodegradable). Desirably, the solvent has low ratings such as a total rating of 5 or less, and desirably 3 or less based upon the National Fire Protection Association's classification on labelling and properties of flammable liquids (health, flammability, and reactivity ratings).

Dyes are generally defined as compounds which contain groups that confer color, generally called chromophores. More information on dyes in general is available in "The Chemistry of Synthetic Dyes," volumes I and II by K. Venkaktaraman, 1952, published by Academic Press, Inc., New York, and in "Organic Chemistry," by W. T. Caldwell, 1943, published by Houghton Mifflin Company in its chapter entitled "Synthetic Dyes," pages 702-725. The dyes desirably are soluble in the low polarity or non-polar hydrocarbon solvents and/or soluble in the poorly hydrogen bonded solvents and are generally free of pigments. Desirably

these dyes are soluble to the extent of from about 0.0001 to about 1.0, desirably from about 0.001g to about 0.9, and preferably from about 0.01 to about 0.08 grams per 1.0 gram of solvent when the solvent has a solubility parameter of from about 12 to about 20, etc., with the solvent being further characterized as being generally a non-polar and/or a poorly hydrogen bonded solvent. Suitable dyes desirably include azo, diazo, quinoline, anthraquinone, indo, ketone imine/methine dyes or derivatives thereof, as well as combinations thereof. Preferred dyes include the azo and quinoline dyes. The synthetic dyes can also be derivatives of aromatic hydrocarbons such as benzene, toluene, naphthalene, and anthracene. Preferred dyes are Akrodye™ oil violet IRS E-705 solvent violet 13 (9,10-anthracenedione)-; 1-hydroxy-4-[(4-methylphenyl)amino], Akrodye™ oil orange #3 E-7174 solvent yellow 14, and Akrodye™ oil brown E-8855 solvent red 2 available from Akrochem Corp. in Akron, Ohio. Other dyes that can be used include Morplas yellow 33, a quinoline type (2(2-quinolylmethylene) phthalide); Morplas red 46, an anthraquinone dye (9,10-anthracenedione, 1-(alkylamino)-; Automate® yellow 126, an azo dye, also known as solvent yellow (1-phenyl-3-methyl-4-(alkylphenylazo)-5-pyrazolone; Automate® red B, a diazo dye also known as solvent red 164 (2-naphthalenol[(phenylazo)phenyl]azo alkyl derivatives); Akrodye™ oil yellow #6, solvent yellow 56, a mono azo dye; Akrodye™ oil red #1, solvent red 26, a diazo dye; Akrodye™ oil green #1, solvent green, an azo anthraquinone dye; Ceres™ red; Akrodye™ E8855 brown powder; Pylakrome™ Red LX-1903 (diazo, solvent red 24, 26) (aka CAS# 85-83-6 and CAS# 447-7-79-6); Pylakrome™ Yellow LX-1913A (monoazo, solvent yellow 29 and 56) (aka CAS# 6706-82-7 and CAS# 2481-94-9); Pylam™ blue LX-7270 (anthraquinone, solvent blue 36 and 58) (aka CAS# 14233-37-5 and CAS#

2987-08-9); and Akrodyne™ oil blue #8, solvent blue 59, an anthraquinone dye.

5 The present invention relates to dyeing generally any type of the above-noted non-black, solvent swellable, rubber compositions, including those contained on a crosslinked substrate such as vehicle
10 bumpers or trim, shoes, e.g., tennis shoes, and the like. The crosslinked substrate can also be a tire, for example, e.g., pneumatic tires as used on vehicles (cars, trucks, etc.) construction equipment tires, agricultural equipment tires, cart tires, wheelbarrow tires, recreation equipment tires (all terrain vehicles, motorcycles), bicycles tires, and the like.

15 Other uses of the dyed portion of non-black rubber compositions include the identification or origin of goods, the identification of trademarks or tradenames, the selective application of the dye for identifying marks (such as lot number, batch type, customer, supplier, and part number), and the like. Goods can
20 also be customized or further colored by use of dyeing thereby enhancing their desirability and marketability.

25 The dyeing of the non-black rubber compositions can be accomplished by any means which places the organic soluble dye solution in contact with the rubber article to be dyed. The dye solution is advantageously stored in a dispenser 10 having a receptacle portion 11 which can hold any desired amount of dye solution 14 depending upon the desired end application, frequency of usage, and the like. The receptacle is made of a suitable non-porous material such as metal, glass or plastic and has
30 an applicator 16 in fluid communication, through matingly engagable nozzle 12, with the receptacle. The dye solution can be selectively applied to the non-black rubber through applicator 16 which can be a brush, a felt or fabric, a sponge, a cloth, a roller ball, or other devices or procedures used for dyeing. Desirably,
35

the applicator optionally but preferably extends into the receptacle and typically fills a majority thereof as shown in the drawing. The non-black swellable elastomer can also be dyed by dipping. Should the non-black rubber contain oil extenders or plasticizers, the same may also aid in penetration of the dye. Advantageously, the dispenser includes a cap means (not shown) which seals the dye solution from exposure to the atmosphere when not in use.

Very small quantities of the dye are usually necessary. The quantities needed to impart a desired or appealing, suitable, color is readily determined by one skilled in the art. Generally from about 0.5 to about 10 parts, desirably from about 0.75 to about 5 parts, and more desirably from about 1 to about 3 parts by weight are mixed with 100 parts by weight of the hydrocarbon solvent to form a dyeing solution. These dilute solutions are desirable as the swelling of the rubber by the solvent facilitates dye penetration.

Typically, the dye solution, that is the dye dissolved in the hydrocarbon solvent, is selectively and/or topically applied to at least one external surface of the above-noted swellable, non-black, mildly crosslinked rubber composition. The solvent containing the dye penetrates and swells the rubber composition creating a permeable layer. That is, the dye solution is absorbed into the rubber with the dye therein. Subsequently, the solvent evaporates leaving the dye within the rubber. The result is a dye penetration layer which is located in the exterior of the non-black rubber composition. The depth thereof can vary depending upon the concentration of the dye, the amount of the dye solution applied and the number of applications of the dye solution. Generally, the depth ranges up to the thickness of the non-black rubber, or up to about 80 or 100 mils and desirably from about 5,

10, or 15 to about 20, 30, or 50 mils.

Initial penetration of the dye solution into the rubber according to the present invention is very rapid and occurs within a matter of seconds. As the solvents used are compatible with the non-black crosslinked rubber, they are absorbed therein. The high concentration of solvent in the surface of the rubber is simultaneously depleted by evaporation of the solvent from the surface and migration of the solvent and dye from the surface to deeper in the rubber. Additional applications of dye solution to the surface can allow the dye solution to penetrate deeper into the rubber. With stain resistant rubber formulations such as those containing at least 20 PHR of a copolymer having at least 50 mole percent repeat units from isomonoolefins, the dye solutions penetrate significantly slower than in rubber formulations wherein repeat units from conjugated diene monomers predominate in the rubber.

Inasmuch as the dye solution migrates from the outward or external surface of the non-black rubber generally located on a black rubber, highly crosslinked composition substrate, a dye gradient is often formed wherein the amount of dye generally diminishes inwardly with distance from the surface. This results in the dye being present in higher concentrations at the exterior dyed surfaces than the average concentration in the crosslinked rubber composition. The dye will not affect the color of the black crosslinked substrate.

The selective application and formation of a penetration dye layer in a rubber according to the present invention differs from painting since the dye solution penetrates into the swellable elastomer and the remaining dye cannot be removed by abrasion of the surface, as with paints or coatings.

EXAMPLES

The following examples illustrate how the organic soluble dye can be transferred into swellable elastomeric compositions and especially white sidewalls. Table I shows a typical formulation for a white tire sidewall. A 6"x6"x0.094" cured sheet of the white sidewall compound of Table I was prepared by molding in a bladder mold for 28 minutes/300°F/100 psi bladder pressure/30 tons platen pressure. Then 1"x1"x0.094" test pieces were clicked out from a bigger sheet for dyeing experiments.

Table I	
<u>Material</u>	<u>Parts</u>
Natural Rubber	35
Chlorobutyl Rubber	60
EPDM	5
Clay	55
TiO ₂	45
Processing Aids	7.5
Fatty Acid	1
Mix well in an intensive mixer such as two roll mill, Banbury, or Brabender	
Sulfur	1.2
Sulfur Accelerators	2.0
Zinc Oxide	5
Antidegradant	1
Further Mix in an Intensive Mixer	
Total:	217.7

A 1"x1"x0.094" test piece of the white tire sidewall compounds disclosed in Table I was dipped into

a solution of a mono azo dye, i.e., Akrodye™ oil yellow #6 (E-6089) (2 g per 100 g solvent) at 40°C in a terpene based KNI Solvent-2000 for 5 minutes. The sample was then removed, dried, and a cross-section cut was made to determine the extent of penetration. The dye penetration under these conditions was total, i.e., about 47 mils (1.19mm).

The above mentioned dyeing experiments were repeated using Akrodye™ oil red #1 (E-5883) in a variety of solvents for overnight soaking. As soon as test pieces were taken out from the solvent, swollen lengths were determined using Vernier Calipers and from which the % volume swell were calculated and are reported in Table II. The solubility parameters and the hydrogen bonding capacity of different solvents were taken from the Polymer Handbook whenever available and are also reported in Table II. The dye penetration whenever needed was measured using Vernier Calipers.

Table II

Solvent	Solubility Parameter (J/m^3) ^{1/2} · 10 ⁻³	Hydrogen Bonding*	Dye Penetration (Mil)	Volume % Swell
Cyclohexane	16.8	p	Total	141.4
m-Xylene	18	p	Total	137.4
Toluene	18.2	p	Total	129.5
KNI-2000	17.2	p	Total	108.7
Decane	13.5	p	Total	102.2
Mineral Spirit			Total	97
n-Hexane	14.9	p	Total	96.7
n-Heptane	15.1	p	Total	90.4
Methylene Chloride	19.8	p	Total	81.6
Dodecane	16.2	p	Total	68.1
Diethyl Ether	15.1	m	Total	57.3
Pyridine	21.9	s	0.0625	14.3
1,4-Dioxane	20.5	m	0.09 mil	14.0
Acetone	20.3	m	0.066	0.75
Isobutyl Alcohol	21.5	s	Surface	-2.0
Methanol	29.7	s	Surface	-3.4
Isopropanol	24	s	Surface	-3.6
Perfluoro- alkane 70	12.0	p	None	-4.9

*p = poor, m = medium, and s = strong hydrogen bonding.

As apparent from Table II, the hydrocarbon solvents of the present invention having solubility parameters between 13 and 18 as well as low amounts of polar groups and generally poor hydrogen bonding resulted in good penetration of the dye as well as good volume swell of the non-black rubber. In contrast, polar containing compounds such as alcohols, ketones, nitrogen containing compounds, and the like, resulted in poor dye penetration and low volume swell.

Four samples of cured rubber having dimensions of 1"x1"x 0.1" (2.54x2.54x0.254cm) were prepared according to the formulations in Table III. Samples B, C, and D had 2, 4, and 6 times the curative concentration of Sample A. This resulted in higher crosslink densities in samples B, C, and D, which restricted their ability to swell with toluene solvent as shown in the volume percent swell test. The reduced swelling of samples B, C, and D resulted in a slower rate of dye penetration and shallower dye penetration as shown by the dye penetration values.

Table III				
Materials	A	B	C	D
Natural rubber	70.00	70.00	70.00	70.00
SBR-1502	30.00	30.00	30.00	30.00
Silane treated clay	27.5	27.5	27.5	27.5
Titanium dioxide	37.00	37.00	37.00	37.00
Naphthenic/paraffinic medium process oil	1.00	1.00	1.00	1.00
Stearic acid	1.5	1.5	1.5	1.5
Diphenyl guanidine	0.15	0.3	0.6	0.9
Benzothiazyl disulfide	1.5	3.0	6.0	9.0
Zinc oxide	20	20	20	20
Polymeric hindered phenol	1.5	3.0	6.0	9.0
Insoluble sulfur	2.75	5.5	11.0	16.5
Dye penetration	0.038"	0.037"	0.028"	0.011"
Volume percent swell	174	152	118	75

The volume percent swell test was conducted by soaking a 1"x1"x 0.1" (2.54x2.54x0.254cm) sample in toluene overnight and then measuring the increase in the largest dimension of the sample. The increase in the dimension was cubed to give volume percent swell.

The dye penetration was conducted by dipping a 1"x1"x 0.1" (2.54x2.54x0.254 cm) sample in a solution of Akrodye™ oil red #1 in KNI Solvent-2000 for 20 minutes. The dye concentration was 2 grams per 100 ml of solvent. After the sample was removed, the solvent was allowed to evaporate and the dyed sample was cut in half. The dye penetration was then measured using Vernier Calipers after drying at room temperature.

Utilizing the general white rubber formulations set forth in Table IV with the specific rubbers set forth in Table V, other non-black cured rubber (1"x1"x0.076") examples were made and dyed utilizing 2 g of Akrodye™ oil red #1 in 100 g of KNI Solvent-2000. The dye was applied by dipping the test piece for 20 minutes at room temperature. The results are set forth in Table V.

Table IV		
	Material	Parts
First Mix	Polymers (see E, F, G, & H)	100
	Clays	27.5
	TiO ₂	37
	Processing Oil	1
	Fatty Acid	1.5
Second Mix	Benzothiazyl disulfide	1.5
	Diphenylguanidine	0.15
	Antioxidant	1.5
	Sulfur (80%)	2.75
	Zinc Oxide	20
	Total:	192.9

Table V		
DYEABILITY OF WHITE COMPOUNDS BASED ON DIFFERENT RUBBERS All Compounds Exposed to Red dyeing solution for 20'@ RT Sample Thickness = 0.076"		
<u>Example</u>	<u>E</u>	<u>F</u>
Rubbers	Natural/EPDM	Natural/SBR
Natural	50 parts by weight	70 parts by weight
Cl Butyl		
EPDM	50 parts by weight	
SBR		30 parts by weight
Dyeable	Yes	Yes
Penetration Depth	>0.038"	>0.038"
<u>Example</u>	<u>G</u>	<u>H</u>
Rubbers	Natural	Natural/Chlorobutyl
Natural	100 parts by weight	50 parts by weight
Cl Butyl		50 parts by weight
EPDM		
SBR		
Dyeable	Yes	Yes
Penetration Depth	>0.038"	>0.038"

As apparent from the Table V where the dye penetrated >0.038" from both sides of the samples to dye the entire sample (0.076"), various types of cured elastomers were readily dyeable throughout the total thickness of the rubber.

The recipe set forth in Table I was modified by adding various amounts of carbon black thereto. 6"x6"x0.094" cured test panels were dyed by dipping in a solution of Akrodye™ red #1 (E-5883) in KNI Solvent-2000 (2 g dye in 100 ml solvent). Colors were compared before and after dyeing and also their L* values were measured using a Hunter Ultascan equipment and the results are reported in Table VI.

Table VI			
Effect of carbon black content in tire white sidewall compound on dyeability as measured by ASTM E 308, Commission Internationale de l'Eclairage CIE publication No. 15.2 (CIE) indices (L*)			
<u>% Carbon Black</u>	<u>Dyeing</u>	<u>L*</u>	<u>Visual Color</u>
0	Before	87.53	White
0	After	69.49	Pink
0	% Diff	20.61	High
0.5	Before	56.49	Med Gray
0.5	After	52.03	Gray-Purple
0.5	% Diff	7.90	Medium
2.0	Before	40.07	Slate Gray
2.0	After	39.69	Dark Slate
2.0	% Diff	0.95	Low

As apparent from Table VI, the amounts of carbon black within the rubber are kept very low so that L* values before are at least 40. Otherwise, the rubber is simply not defined as a non-black rubber.

Table VII relates to dyes that were in accordance with the concepts of the present invention and dyes that did not work. Approximately 2 grams of dye were dissolved/dispersed in 200 ml of KNI Solvent-2000. To this was added the 1"x1"x 0.14" of cured control white

sidewall test pieces (prepared from 35 natural/65 Cl Butyl + EPDM), i.e., Table I. It was taken out after overnight soaking and then cut into two pieces to examine dye penetration. The dye is said to have worked if it penetrated totally, otherwise it did not work. Just surface coating and penetration less than total on overnight soaking is considered as non-dyeing. Dyes that worked and that did not work are tabulated below.

Table VII

Dyes That Worked	Dyes/Pigments That Did Not Work
Akrodye™ Oil Yellow #6, E-6089	Akrodye™ Oil Black #4 (E-8540)
Akrodye™ Oil Red #1, E-5883	Ceres™ Yellow
Akrodye™ Oil Green #1	Akrochem 626 Blue Powder
Akrodye™ E-8855 Brown Powder	Akrosperser E-98 Blue Paste
Akrodye™ Oil Orange #3	Intrasperse Yellow GBA Extra
Akrodye™ Oil Violet IRS	Intralan Yellow NW 250%
Morplas™ Red 46	Aluminum Paste
Automate™ Yellow 126	2B-Extra Concentrate Blue Dye
Automate™ Red B	Precipitated Azo Pigment
Ceres™ Red	Red Iron Oxide
Morplas™ Yellow 33	
Pylakrome™ Red LX-1903	
Pylakrome™ Yellow LX-1913A	
Pylam™ Blue LX-7270	

While certain representative embodiments and details have been shown for the purpose of illustrating the invention, it will be apparent to those skilled in this art that various changes and modifications may be made therein without departing from the spirit or scope of the invention.

The claims defining the invention are as follows:

1. A pneumatic tire, comprising:
a toroidal shaped carbon black filled vulcanized rubber composition having integral therewith, a crosslinked non-black rubber composition comprising at least one hydrocarbon rubber having less than 10 weight percent of polar groups therein, a white pigment, and a hydrocarbon soluble dye solution comprised of a dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ absorbed into at least a portion of said crosslinked non-black rubber composition, said non-black rubber composition having an exposed surface with a CIE 1976 L^* value of at least 40.
2. A pneumatic tire according to claim 1, wherein said crosslinked non-black hydrocarbon rubber composition comprises from 20 to 80 parts by weight of a copolymer per 100 parts by weight of said total hydrocarbon rubber, said copolymer containing at least 50 weight percent of repeat units derived from one or more C_4 to C_7 isomonoolefin monomers, and wherein said toroidal shaped vulcanized composition has a tread region and two sidewall regions.
3. A pneumatic tire according to claim 2, wherein said white pigment comprises titanium dioxide, wherein said portion having absorbed dye of said non-black rubber composition is one or more selective exterior layers, and wherein said crosslinked non-black rubber composition has swelling capacity of at least 75 volume percent in a hydrocarbon solvent.
4. A pneumatic tire according to claim 3, wherein said non-black rubber composition comprises:



from about 25 to about 65 parts by weight of a copolymer being at least 50 weight percent repeat units from one or more C_4 to C_7 isomonoolefin monomers;

up to 30 parts by weight of EPDM rubber;

from 15 to 75 parts by weight of natural rubber or a synthetic polymer or combinations thereof, said synthetic polymer having at least 50 weight percent of repeat units derived from a C_4 to C_{12} conjugated diene monomer; and

said parts by weight based upon 100 parts by weight total rubbers of said non-black rubber composition.

5. A pneumatic tire according to claim 1, wherein said hydrocarbon soluble dye has a solubility in a hydrocarbon solvent of at least 0.001 gram per one gram of said hydrocarbon solvent, said hydrocarbon solvent having a solubility parameter of from 12 to 20, and wherein said crosslinked non-black hydrocarbon rubber has less than 3 percent by weight of polar groups therein.

6. A pneumatic tire according to claim 5, wherein said dye is an azo, diazo dye, an anthraquinone dye, a quinoline dye, an aromatic hydrocarbon dye, an indo dye, or a ketone imine/methine dye, or derivatives thereof, or combinations thereof.

7. A pneumatic tire according to claim 4, wherein said hydrocarbon soluble dye has a solubility in a hydrocarbon solvent of at least 0.001 gram per one gram of said hydrocarbon solvent having a solubility parameter of from 12 to 20, and wherein said crosslinked non-black hydrocarbon rubber has less than 2 percent by weight of polar groups therein.

8. A pneumatic tire according to claim 7, wherein said dye is an azo, diazo dye, an anthraquinone dye, a quinoline dye, an aromatic hydrocarbon dye, an



indo dye, or a ketone imine/methine dye, or derivatives thereof, or combinations thereof.

9. A process for dyeing a pneumatic tire, comprising the steps of:

5 applying a dye solution to at least one selective external surface of a crosslinked non-black rubber composition integral with said pneumatic tire, said dye solution being comprised of a dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$, said solvent containing less than 10 percent by weight of polar atoms other than halogens based upon the total weight of said solvent, said dye being soluble in said hydrocarbon solvent;


10 forming a dye penetration layer in said non-black rubber composition at said selective surface; and

evaporating said hydrocarbon solvent.

10. A process according to claim 9, wherein said crosslinked non-black surface of said pneumatic tire is one or more sidewall surfaces, wherein said dye penetration layer is up to 100 mils deep in said one or more non-black rubber composition sidewall surfaces, and wherein said hydrocarbon solvent contains less than 5 percent by weight of polar atoms.

11. A process according to claim 10, wherein said non-black sidewall surface has a CIE 1976 L* value before dyeing of at least 50 according to method ASTM E 308, and wherein said hydrocarbon solvent has a solubility parameter of from about 13 to about 18.

12. A process according to claim 11, wherein said penetration layer is from 10 to 80 mils deep, wherein said hydrocarbon solvent contains less than 2 percent by weight of polar atoms, wherein said non-black rubber composition has a swelling



capacity of at least 75 percent in a hydrocarbon solvent, and wherein said CIE 1976 L* value is at least 80.

13. A process according to claim 12, wherein said penetration layer has a dye gradient therein.


5 14. A rubber article, comprising:

a crosslinked substrate and an adhered crosslinked non-black rubber composition layer thereon having a swelling capacity in a hydrocarbon solvent of at least 75 percent, a penetration layer located in the exterior portion of said non-black rubber composition layer up to the thickness thereof, and said penetration layer
10 containing a dye solution comprised of a dye and a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ therein.

15 15. A rubber article according to claim 14, wherein said non-black rubber has a non-dyed CIE 1976 L* value of at least 40 according to method ASTM E 308, wherein said dye is a hydrocarbon soluble dye, and wherein said penetration layer extends up to 80 mils deep.

16. A rubber article according to claim 15, wherein said CIE 1976 L* value is at least 70, wherein said substrate is a crosslinked rubber substrate, wherein said swelling capacity of said non-black rubber composition is at least 100 percent, and wherein said penetration layer extends up to 70 mils.

20 17. A rubber article according to claim 16, wherein said substrate is a pneumatic tire and wherein said swellable non-black rubber layer is a white tire sidewall, and wherein said dye is an azo dye, a diazo dye, a quinoline dye, an anthraquinone dye, an aromatic hydrocarbon dye, an indo dye, or a ketone imine/methine dye, or derivatives thereof, or combinations thereof.



18. An apparatus for dyeing a crosslinked swellable non-black rubber composition, comprising:

a dispenser having a receptacle containing a dye solution comprising a hydrocarbon soluble dye and a hydrocarbon solvent having a solubility parameter of
5 from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$, and having less than 10 percent by weight of polar atoms based upon the weight of said solvent, and an applicator in fluid communication with said receptacle.

19. An apparatus as set forth in claim 18, including a nozzle, said applicator matingly engaging said nozzle.

10 20. An apparatus as set forth in claim 18, wherein said applicator is a felt, a fabric, a cloth, a sponge, or a roller.

21. An apparatus as set forth in claim 18, wherein said hydrocarbon solvent has a solubility parameter of from about 13 to about 18, and wherein the amount of polar atoms in said solvent is less than 2 percent by weight.

15 22. A dye elastomer, comprising:

a crosslinked, non-black, swellable hydrocarbon rubber having less than 10 weight percent of polar groups, a white pigment; and

a hydrocarbon soluble dye dissolved in a hydrocarbon solvent having a solubility parameter of from 12 to 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ absorbed into at least one surface of
20 said swellable, non-black hydrocarbon rubber, and wherein said swellable hydrocarbon rubber has less than 2 PHR of carbon black.

23. A dyed elastomer according to claim 22, wherein said swellable rubber has a swelling capacity of at least 50 percent, wherein the amount of said carbon black is less than 1 PHR, and wherein said swellable, non-black hydrocarbon rubber
25 has a dye penetration layer.



24. A dyed elastomer according to claim 23, wherein said white pigment comprises titanium dioxide, and wherein said non-black hydrocarbon rubber has less than 3 percent by weight of polar groups therein.

5 25. A dyed elastomer according to claim 24, wherein said penetration layer has a dye gradient, and wherein said crosslinked, non-black hydrocarbon rubber comprises from about 20 to about 80 parts by weight of a copolymer containing at least 50 weight percent of repeat units derived from one or more C_4 to C_7 isomonoolefin monomers per 100 parts by weight of copolymer.


10 26. A dyed elastomer according to claim 25, wherein said swellable, non-black hydrocarbon rubber is an integral part of a sidewall of a pneumatic tire.

27. A dyed elastomer according to claim 26, wherein said swellable, non-black hydrocarbon rubber comprises:

15 from about 25 to about 65 parts by weight of a copolymer having at least 50 weight percent repeat units from one or more C_4 to C_7 isomonoolefin monomers, up to 30 parts by weight of EPDM rubber, and from about 15 to about 75 parts by weight of natural rubber or a synthetic homopolymer or copolymer having at least 50 weight percent of repeat units derived from a C_4 to C_{12} conjugated diene monomer, said parts by weight based upon 100 parts by weight total rubbers of said swellable, non-black hydrocarbon rubber.

20 28. A pneumatic tire, substantially as hereinbefore described with reference to any one of the Examples.

29. A process for dyeing a pneumatic tire, substantially as hereinbefore described with reference to any one of the Examples.



30. A rubber article, substantially as hereinbefore described with reference to any one of the Examples.

31. An apparatus for dyeing a crosslinked swellable non-black rubber composition, substantially as hereinbefore described with reference to the
5 accompanying drawings.

32. A dye solution, substantially as hereinbefore described with reference to any one of the Examples.

33. A dyed elastomer, substantially as hereinbefore described with reference to any one of the Examples.


10

Dated 2 September, 1998

The Goodyear Tire & Rubber Company

Patent Attorneys for the Applicant/Nominated Person

SPRUSON & FERGUSON



Tires with Dyed Indicia

Abstract

This invention relates to a vulcanized rubber substrate such as, for example, a tire and a crosslinked, non-black rubber composition layer thereon such as, for example, a white sidewall. In one aspect, the invention relates to such a tire wherein said white sidewall is colored after its vulcanization with a contrasting colored dye. In another aspect, a dye solution (14) is provided which is comprised of a dye dissolved in a hydrocarbon solvent which is characterized by having a solubility parameter of from about 12 to about 20 $[J/m^3]^{1/2} \cdot 10^{-3}$ according to the Polymer Handbook. Upon application of such dye solution (14) to, for example, a crosslinked white portion of a tire sidewall, such dye solution (14) penetrates and swells at least a portion of said white tire sidewall. Upon evaporation of the solvent, a dyed penetration layer is formed.

