



(51) **International Patent Classification:**
C08L 67/02 (2006.01)

(21) **International Application Number:**
PCT/US201 1/042143

(22) **International Filing Date:**
28 June 2011 (28.06.2011)

(25) **Filing Language:** English

(26) **Publication Language:** English

(30) **Priority Data:**
12/826,087 29 June 2010 (29.06.2010) US

(71) **Applicant (for all designated States except US):** SABIC INNOVATIVE PLASTICS IP B.V. [NL/NL]; Plastic-slaan 1, NL-4612 PX Bergen op Zoom (NL).

(72) **Inventors; and**

(75) **Inventors/Applicants (for US only):** DING, Tianhua [CN/US]; 4408 Huntington Ridge Circle, Newburgh, Indiana 47630 (US). FONSECA, Rodney [US/US]; 3677 Carmona Drive, Newburgh, Indiana 47630 (US). KIM, Sung Dug [KR/US]; 2744 Meadowcrest Drive, Newburgh, Indiana 47630 (US). VAN DER WEELE, Chris [NL/NL]; Vink 3, NL-3245 TV Sommelsdijk (NL).

(81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(H))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(Hi))

Published:

- with international search report (Art. 21(3))

(54) **Title:** FLAME RESISTANT POLYESTER COMPOSITIONS, METHOD OF MANUFACTURE, AND ARTICLES THEREOF

(57) **Abstract:** A thermoplastic polyester composition comprising, based on the total weight of the composition, a chlorine- and bromine-free combination of: from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate); from 25 to 35 wt% of a reinforcing filler; from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof; from 5 to 15 wt% of a phosphinate salt flame retardant; from more than 0 to less than 5 wt% of an impact modifier component comprising a poly(ether-ester) elastomer and a (meth)acrylate impact modifier; from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; from more than 0 to 2 wt% of a stabilizer; wherein the thermoplastic polyester composition contains less than 5 wt% of a polyetherimide.



FLAME RESISTANT POLYESTER COMPOSITIONS, METHOD OF MANUFACTURE,
AND ARTICLES THEREOF

BACKGROUND

[0001] This disclosure relates to polyester compositions, method of manufacture of the compositions, and articles thereof.

[0002] Thermoplastic polyester compositions, such as poly(alkylene terephthalates), have valuable characteristics including strength, toughness, high gloss, and solvent resistance. Polyesters therefore have utility as materials for a wide range of applications, from automotive parts to electric and electronic appliances. Because of their wide use, particularly in electronic applications, it is desirable to provide flame retardancy to polyesters.


[0003] Numerous flame retardants (FR) for polyesters are known, but many contain halogens, usually chlorine and/or bromine. Halogenated flame retardant agents are less desirable because of the increasing demand for ecologically friendly ingredients. Halogen-free flame-retardants, such as phosphorus- and nitrogen- based compounds can be used as well. Unfortunately, it can be difficult to achieve excellent flame retardancy in very thin sections.

[0004] More ecologically compatible flame retardant (eco-FR) formulations based on aluminum salts of phosphinic or diphosphinic acid compounds and melamine compounds have been developed to overcome environmental issues of halogenated flame retardants. However, these eco-FR compositions can have reduced impact strength and tensile strength, as well as less desirable flow properties compared to compositions having halogenated flame retardants. The addition of small amounts of a polyetherimide (PEI), in particular ULTEM 1010 from Sabic Innovative Plastics, has boosted the mechanical properties of the eco-FR compositions. However, in some circumstances PEI lowers the comparative tracking index (CTI) compared to halogenated flame retardants, i.e., the presence of PEI can increase the tendency to form conductive leakage paths on the surface of a molded article.

[0005] Thus, there remains a need for eco-FR thermoplastic polyester compositions having good flame retardant properties and comparable or improved mechanical properties, including ductility, flexural strength, CTI, and stiffness relative to compositions comprising halogenated flame retardants and eco-FR compositions comprising PEI.

BRIEF SUMMARY OF THE INVENTION

[0006] Disclosed herein is a thermoplastic polyester composition comprising, based on the total weight of the composition, a chlorine- and bromine-free combination of: (a) from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate) that (1) is derived from a poly(ethylene terephthalate) component selected from the group consisting of a poly(ethylene terephthalate), a poly(ethylene terephthalate) copolymer, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component; (b) from 25 to 35 wt% of a reinforcing filler, (c) from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof; (d) from 5 to 15 wt% of a phosphorous flame retardant comprising: a phosphinate of formula (I)



a diphosphinate of formula (II)




and/or a polymer derived from the phosphinate of formula (I) or the diphosphinate of the formula (II), wherein R^1 and R^2 are each independently the same or different, and are H, linear or branched C_1-C_6 alkyl, or C_6-C_{10} aryl; R^3 is C_1-C_{10} , linear or branched alkylene, C_6-C_{10} arylene, C_7-C_n alkylarylene, or C_7-C_n arylalkylene; M is an alkaline earth metal, alkali metal, Al, Ti, Zn, Fe, or B; m is 1, 2, 3 or 4; n is 1, 2, or 3; and x is 1 or 2; (e) from more than 0 to less than 5 wt% of an impact modifier component comprising a poly(ether-ester) elastomer and a (meth)acrylate impact modifier, (f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; (g) from more than 0 to 2 wt% of a stabilizer, wherein the thermoplastic polyester composition contains less than 5 wt% of a polyetherimide.

[0007] Also disclosed is a thermoplastic polyester composition comprising, based on the weight of the composition, a chlorine- and bromine-free combination of: (a) from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate) that (1) is derived from a poly(ethylene terephthalate) component selected from the group consisting of a poly(ethylene terephthalate), a poly(ethylene terephthalate) copolymer, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component; (b) from 25 to 35 wt% of a glass fiber filler; (c) from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof; (d) from more than 10 to 15 wt% a phosphinate of formula (I)



a diphosphinate of formula (II)



and/or a polymer derived from the phosphinate of formula (I) or the diphosphinate of the formula (II), wherein R^1 and R^2 are identical or different and are H, linear or branched C_1-C_6 alkyl, or C_6-C_{10} aryl; R^3 is C_1-C_{10} , linear or branched alkylene, C_6-C_{10} arylene, C_7-C_n alkylarylene, or C_7-C_n arylalkylene; M is an alkaline earth metal, alkali metal, Al, Ti, Zn, Fe, or B; m is 1, 2, 3 or 4; n is 1, 2, or 3; and x is 1 or 2; (e) at least 1% to less than 5 weight % of impact modifier component comprising a combination of (i) a poly(ether-ester) elastomer and (ii) a core-shell (meth)acrylate impact modifier; wherein the poly(ether-ester) elastomer comprises long-chain ester units of formula (III):



and short-chain ester units having units of formula (IV):



wherein R' is a divalent aromatic radical remaining after removal of carboxyl groups from terephthalic acid, isophthalic acid, or a combination of terephthalic acid and isophthalic acid; G is a divalent polyalkylene oxide radical remaining after removal of terminal hydroxyl groups from a poly(alkylene oxide) glycol having a number-average molecular weight of 100 to 2500; and D is a divalent alkylene radical remaining after removal of hydroxyl groups from aliphatic diols having a molecular weight from 62 to 286; and wherein the core-shell (meth)acrylate impact modifier has a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell; (f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; and (g) from more than 0 wt% to 2 wt% of a stabilizer; wherein the halogen free composition contains less than 5 wt% of a polyetherimide; and wherein an article molded from the composition exhibits (a) a flexural modulus that is more than 9800 MPa, (b) a flexural stress that is more than 150 MPa, (c) an unnotched impact strength that is more than 470 Joules/meter, and (d) a V0 rating at 0.8 mm, measured in accordance with UL 94.

[0008] Still further disclosed is a thermoplastic polyester composition comprising, based on the weight of the composition, a halogen-free combination of: (a) from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate) that (1) is derived from a poly(ethylene terephthalate) component selected from the group consisting of a poly(ethylene terephthalate), a poly(ethylene terephthalate) copolymer, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component; (b) from 25

to 35 wt% glass fiber filler; (c) from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof; (d) from more than 10 to 15 wt% a phosphinate of formula (I)



a diphosphinate of formula (II)



and/or a polymer derived from the phosphinate of formula (I) or the diphosphinate of the formula (II), wherein R^1 and R^2 are identical or different and are H, or linear or branched C_1 - C_6 alkyl; R^3 is C_1 - C_{10} , linear or branched alkylene; M is aluminum; m is 3; n is 3; and x is 1 or 2; (e) at least 1 to less than 5 wt% of impact modifier component comprising a combination of (i) a poly(butylene terephthalate-polytetrahydrofuran) block copolymer and (ii) a core-shell (meth)acrylate impact modifier having a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell; (f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; and (g) from more than 0 wt% to 2 wt% of a stabilizer; wherein the halogen free composition contains less than 2 wt% of a polyetherimide; and wherein an article molded from the composition exhibits (a) a flexural modulus that is more than 9800 MPa, (b) a flexural stress is more than 150 MPa, (c) an unnotched impact strength that is more than 470 Joules/meter, and (d) a V0 rating at 0.8 mm, measured in accordance with UL 94.

[0009] Also disclosed are methods for the manufacture of the foregoing compositions.

[00010] Still further disclosed are articles comprising the foregoing compositions.

DETAILED DESCRIPTION OF THE INVENTION

[0010] Our invention is based on the discovery that it is possible to make a glass filled, halogen free flame retarding composition that exhibits many useful properties: namely, good flame retardancy performance (i.e., V0 at 0.80 mm), higher CTI performance, improved impact properties and improved flexural properties by the use of a specific combination of elastomers, as compared to a composition that does not use the combination of elastomers.

[0011] Described herein is a flame retardant thermoplastic polyester composition that is chlorine- and bromine-free, and that includes a polyester, a reinforcing filler, a melamine-based flame retardant synergist, a phosphinate salt flame retardant, an anti-drip agent, an impact modifier component comprising a poly(ether-ester) elastomer and an acrylate impact

modifier, a stabilizer, and only optionally a polyetherimide. Use of the specific components in the amounts disclosed herein allows manufacture of a chlorine- and bromine-free composition with excellent flame retardance and improved flow and CTI, while maintaining and the desirable mechanical properties of currently used glass-filled eco-FR formulations, even in the absence of a polyetherimide. In particular, the compositions can have very useful impact strength properties, flexural properties, heat stability, flow properties, and/or high resistance against electrical breakdown.

[0012] As used herein the singular forms "a," "an," and "the" include plural referents. The term "combination" is inclusive of blends, mixtures, alloys, reaction products, and the like. Unless defined otherwise, technical and scientific terms used herein have the same meaning as is commonly understood by one of skill. Compounds are described using standard nomenclature. The term "and a combination thereof" is inclusive of the named component and/or other components not specifically named that have essentially the same function.


[0013] Other than in the operating examples or where otherwise indicated, all numbers or expressions referring to quantities of ingredients, reaction conditions, and the like, used in the specification and claims are to be understood as modified in all instances by the term "about." Various numerical ranges are disclosed in this patent application. Because these ranges are continuous, they include every value between the minimum and maximum values. The endpoints of all ranges reciting the same characteristic or component are independently combinable and inclusive of the recited endpoint. Unless expressly indicated otherwise, the various numerical ranges specified in this application are approximations. The term "from more than 0 to" an amount means that the named component is present in some amount more than 0, and up to and including the higher named amount.

[0014] All ASTM tests and data are from the 2003 edition of the Annual Book of ASTM Standards unless otherwise indicated. All cited references are incorporated herein by reference.

[0015] For the sake of clarity, the terms "terephthalic acid group," "isophthalic acid group," "butanediol group," and "ethylene glycol group" have the following meanings. The term "terephthalic acid group" in a composition refers to a divalent 1,4-benzene radical (-1,4-(C₆H₄)-) remaining after removal of the carboxylic groups from terephthalic acid-. The term "isophthalic acid group" refers to a divalent 1,3-benzene radical (-(-1,3-C₆H₄)-) remaining after removal of the carboxylic groups from isophthalic acid. The "butanediol group" refers to a divalent butylene radical (-(-C₄H₈)-) remaining after removal of hydroxyl groups from

butanediol. The term "ethylene glycol group" refers to a divalent ethylene radical $(-\text{C}_2\text{H}_4-)$ remaining after removal of hydroxyl groups from ethylene glycol. With respect to the terms "terephthalic acid group," "isophthalic acid group," "ethylene glycol group," "butane diol group," and "diethylene glycol group" being used in other contexts, e.g., to indicate the weight % of the group in a composition, the term "isophthalic acid group(s)" means the group having the formula $(-\text{O}(\text{CO})\text{C}_6\text{H}_4(\text{CO})-)$, the term "terephthalic acid group" means the group having the formula $(-\text{O}(\text{CO})\text{C}_6\text{H}_4(\text{CO})-)$, the term diethylene glycol group means the group having the formula $(-\text{O}(\text{C}_2\text{H}_4)\text{O}(\text{C}_2\text{H}_4)-)$, the term "butanediol group" means the group having the formula $(-\text{O}(\text{C}_4\text{H}_8)-)$, and the term "ethylene glycol groups" means the group having formula $(-\text{XC}_2\text{H}_4-)$.

[0016] Polyesters for use in the present thermoplastic compositions having repeating structural units of formula (I)



wherein each T is independently the same or different divalent C_{6-10} aromatic group derived from a dicarboxylic acid or a chemical equivalent thereof, and each D is independently a divalent C_{2-4} alkylene group derived from a dihydroxy compound or a chemical equivalent thereof. Copolyesters containing a combination of different T and/or D groups can be used. Chemical equivalents of diacids include the corresponding esters, alkyl esters, e.g., C_{1-3} dialkyl esters, diaryl esters, anhydrides, salts, acid chlorides, acid bromides, and the like. Chemical equivalents of dihydroxy compounds include the corresponding esters, such as C_{1-3} dialkyl esters, diaryl esters, and the like. The polyesters can be branched or linear.

[0017] Exemplary polyesters include poly(alkylene terephthalate) ("PAT"), poly(1,4-butylene terephthalate), ("PBT"), poly(ethylene terephthalate) ("PET"), poly(ethylene naphthalate) ("PEN"), poly(butylene naphthalate), ("PBN"), poly(propylene terephthalate) ("PPT"), poly(cyclohexane dimethanol terephthalate) ("PCT"), poly(cyclohexane-1,4-dimethylene cyclohexane-1,4-dicarboxylate) also known as poly(1,4-cyclohexanedimethanol 1,4-dicarboxylate) ("PCCD"), poly(cyclohexanedimethanol terephthalate), poly(cyclohexylenedimethylene-co-ethylene terephthalate), cyclohexanedimethanol-terephthalic acid-isophthalic acid copolymers and cyclohexanedimethanol-terephthalic acid-ethylene glycol ("PCTG" or "PETG") copolymers. When the molar proportion of cyclohexanedimethanol is higher than that of ethylene glycol the polyester is termed PCTG.

When the molar proportion of ethylene glycol is higher than that of cyclohexane dimethanol the polyester is termed PETG.

[0018] The polyesters can be obtained by methods well known to those skilled in the art, including, for example, interfacial polymerization, melt-process condensation, solution phase condensation, and transesterification polymerization. Such polyester resins are typically obtained through the condensation or ester interchange polymerization of the diol or diol equivalent component with the diacid or diacid chemical equivalent component. Methods for making polyesters and the use of polyesters in thermoplastic molding compositions are known in the art. Conventional polycondensation procedures are described in the following, see, generally, U.S. Pat. Nos. 2,465,319, 5,367,011 and 5,411,999. The condensation reaction can be facilitated by the use of a catalyst, with the choice of catalyst being determined by the nature of the reactants. The various catalysts are known in the art. For example, a dialkyl ester such as dimethyl terephthalate can be transesterified with butylene glycol using acid catalysis, to generate poly(butylene terephthalate). It is possible to use a branched polyester in which a branching agent, for example, a glycol having three or more hydroxyl groups or a trifunctional or multifunctional carboxylic acid has been incorporated.

[0019] The polyester component can comprise a modified poly(butylene terephthalate), that is, a PBT derived from poly(ethylene terephthalate), for example waste PET such as soft drink bottles. The PET-derived PBT (referred to herein for convenience as "modified PBT") (1) can be derived from a poly(ethylene terephthalate) component selected from the group consisting of poly(ethylene terephthalate), poly(ethylene terephthalate) copolymers, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component. The modified PBT can further be derived from a biomass-derived 1,4-butanediol, e.g., corn derived 1,4-butanediol or a 1,4-butanediol derived from a cellulosic material. Unlike conventional molding compositions containing virgin PBT (PBT that is derived from monomers), the modified PBT contains a poly(ethylene terephthalate) residue, e.g., a material such as ethylene glycol and isophthalic acid groups (components that are not present in virgin, monomer-based PBT). Use of modified PBT can provide a valuable way to effectively use underutilized scrap PET (from post-consumer or post-industrial streams) in PBT thermoplastic molding compositions, thereby conserving non-renewable resources and reducing the formation of greenhouse gases, e.g., CO₂.

[0020] The residue derived from the poly(ethylene terephthalate) component and which is present in the modified PBT can be selected from the group consisting of ethylene

glycol groups, diethylene glycol groups, isophthalic acid groups, antimony-containing compounds, germanium-containing compounds, titanium-containing compounds, cobalt-containing compounds, tin-containing compounds, aluminum, aluminum salts, 1,3-cyclohexane dimethanol isomers, 1,4-cyclohexane dimethanol isomers, the cis isomer of 1,3-cyclohexane dimethanol, the cis isomer of 1,4-cyclohexane dimethanol, the trans isomer of 1,3-cyclohexane dimethanol, the trans isomer of 1,4-cyclohexane dimethanol, alkali salts, alkaline earth metal salts, including calcium, magnesium, sodium and potassium salts, phosphorous-containing compounds and anions, sulfur-containing compounds and anions, naphthalene dicarboxylic acids, 1,3-propanediol groups, and combinations thereof.

[0021] Depending on factors such as the type and relative amounts of poly(ethylene terephthalate) and poly(ethylene terephthalate) copolymers, the residue can include various combinations. For example, the residue can include mixtures of ethylene glycol groups and diethylene glycol groups. The residue can also include mixtures of ethylene glycol groups, diethylene glycol groups, and isophthalic acid groups. The residue derived from poly(ethylene terephthalate) can include the cis isomer of 1,3-cyclohexane dimethanol groups, the cis isomer of 1,4-cyclohexane dimethanol groups, the trans isomer of 1,3-cyclohexane dimethanol groups, the trans isomer of 1,4-cyclohexane dimethanol groups, or combinations thereof. The residue can also be a mixture of ethylene glycol groups, diethylene glycol groups, isophthalic acid groups, cis isomer of cyclohexane dimethanol groups, trans isomer of cyclohexane dimethanol groups, or combinations thereof. The residue derived from poly(ethylene terephthalate) can also include mixtures of ethylene glycol groups, diethylene glycol groups, and cobalt-containing compounds. Such cobalt-containing compound mixture can also contain isophthalic acid groups.

[0022] The amount of the ethylene glycol groups, diethylene glycol groups, and isophthalic groups in the polymeric backbone of the modified PBT component can vary. The modified PBT ordinarily contains isophthalic acid groups in an amount that is at least 0.1 mole % and can range from 0 or 0.1 to 10 mole % (0 or 0.07 to 7 weight percent (wt%)). The modified PBT component ordinarily contains ethylene glycol in an amount that is at least 0.1 mole % and can range from 0.1 to 10 mole % (0.02 to 2 wt%). In an embodiment, the modified PBT component has an ethylene glycol content that is more than 0.85 wt%. In another embodiment, compositions can contain ethylene glycol in an amount from 0.1 to 2 wt%. The modified PBT component can also contain diethylene glycol in an amount from 0.1 to 10 mole % (0.04 to 4 wt%). The amount of the butanediol groups is generally about 98 mole % and can vary from 95 to 99.8 mole % in some embodiments. The amount of the

terephthalic acid groups is generally about 98 mole % and can vary from 90 to 99.9 mole % in some embodiments. Unless otherwise specified, all molar amounts of the isophthalic acid groups and/or terephthalic acid groups are based on the total moles of diacids/diesters in the composition. Unless otherwise specified, all molar amounts of the butanediol, ethylene glycol, and diethylene glycol groups are based on the total moles of diol in the composition. These weight percent measurements are based on the above definitions of terephthalic acid groups, isophthalic acid groups, ethylene glycol groups, and diethylene glycol groups.

[0023] The total amount of the poly(ethylene terephthalate) component residue in the modified PBT can vary in amounts from 1.8 to 2.5 wt%, or from 0.5 to 2 wt%, or from 1 to 4 wt%, based on the total weight of the modified PBT. The ethylene glycol, diethylene glycol, and cyclohexane dimethanol groups can be present, individually or in combination, in an amount from 0.1 to 10 mole %, based on 100 mole % of glycol in the molding composition. The isophthalic acid groups can be present in an amount from 0.1 to 10 mole %, based on 100 mole % of diacid/diester in the molding composition.

[0024] It has been discovered that when it is desirable to make a poly(butylene terephthalate) copolymer having a melting temperature T_m that is at least 200°C, the total amount of diethylene glycol, ethylene glycol, and isophthalic acid groups should be within a certain range. As such, the total amount of the diethylene glycol, ethylene glycol, and isophthalic acid groups in the modified poly(butylene terephthalate) component can be more than 0 and less than or equal to 23 equivalents, relative to the total of 100 equivalents of diol and 100 equivalents of diacid groups in the modified PBT. The total amount of the isophthalic acid groups, ethylene glycol groups, and diethylene glycol groups can be from 3 to less than or equal to 23 equivalents, relative to the total of 100 equivalents of diol and 100 equivalents of diacid groups in the PET-derived PBT. Alternatively, the total amount of the isophthalic acid groups, ethylene glycol groups, and diethylene glycol groups can be from 3 to less than or equal to 10 equivalents, relative to the total of 100 equivalents of diol and 100 equivalents of diacid groups in the modified PBT. Still further, the total amount of the isophthalic acid groups, ethylene glycol groups, and diethylene glycol groups can be from 10 to less than or equal to 23 equivalents, relative to the total of 100 equivalents of diol and 100 equivalents of diacid groups in the modified PBT. The diethylene glycol, ethylene glycol, and/or isophthalic acid can be added during the process.

[0025] The total ethylene glycol groups, isophthalic acid groups, and diethylene glycol groups can vary, depending on the application needs. The composition can have total monomer content selected from the group consisting of ethylene glycol, isophthalic acid

groups, and diethylene glycol groups in an amount from more than 0 and less than or equal to 17 equivalents relative to the total of 100 equivalents of diol and 100 equivalents of diacid groups in the modified PBT. Advantageously, such compositions can maintain useful properties, such as heat deflection temperatures that are more than 80°C.

[0026] It has also been discovered that the total amount of inorganic residues derived from the poly(ethylene terephthalate) can be present from more than 0 ppm and up to 1000 ppm. Examples of such inorganic residues include those selected from the group consisting of antimony-containing compounds, germanium-containing compounds, titanium-containing compounds, cobalt-containing compounds, tin containing compounds, aluminum, aluminum salts, alkaline earth metal salts, alkali salts, including calcium, magnesium, sodium and potassium salts, phosphorous-containing compounds and anions, sulfur-containing compounds and anions, and combinations thereof. The amounts of inorganic residues can be from 250 to 1000 ppm, and more specifically from 500 to 1000 ppm.

[0027] The PET component from which the modified PBT is made can have a variety of forms. Generally, the PET component includes recycle (scrap) PET in flake, powder/chip, film, or pellet form. Before use, the PET is generally processed to remove impurities such as paper, adhesives, polyolefin, e.g., polypropylene, polyvinyl chloride (PVC), nylon, polylactic acid, and other contaminants. Also, the PET component can include PET that is not waste in flake, chip, or pellet form. As such, PET that would ordinarily be deposited in landfills can now be used productively and effectively. The PET component can also include other polyesters and/or polyester copolymers. Examples of such materials include poly(alkylene terephthalates) selected from the group consisting of poly(ethylene terephthalate), poly(cyclohexane dimethanol terephthalate), copolyesters of terephthalate esters with comonomers containing cyclohexanedimethanol and ethylene glycol, copolyesters of terephthalic acid with comonomers containing cyclohexane dimethanol and ethylene glycol, poly(butylene terephthalate), poly(xylylene terephthalate), poly(butylene terephthalate), poly(trimethylene terephthalate), polyester naphthalates, and combinations thereof.

[0028] Commercial examples of a modified PBT include those available under the trade name VALOX iQ PBT, manufactured by SABIC Innovative Plastics Company. The modified PBT can be derived from the poly(ethylene terephthalate) component by any method that involves depolymerization of the poly(ethylene terephthalate) component and polymerization of the depolymerized poly(ethylene terephthalate) component with 1,4-butanediol to provide the modified PBT. For example, the modified poly(butylene terephthalate) component can be made by a process that involves depolymerizing a

poly(ethylene terephthalate) component selected from the group consisting of poly(ethylene terephthalate) and poly(ethylene terephthalate) copolymers, with a 1,4-butanediol component at a temperature from 180°C to 230°C, under agitation, at a pressure that is at least atmospheric pressure in the presence of a catalyst component, at an elevated temperature, under an inert atmosphere, to produce a molten mixture containing a component selected from the group consisting of oligomers containing ethylene terephthalate moieties, oligomers containing ethylene isophthalate moieties, oligomers containing diethylene terephthalate moieties, oligomers containing diethylene isophthalate moieties, oligomers containing butylene terephthalate moieties, oligomers containing butylene isophthalate moieties, covalently bonded oligomeric moieties containing at least two of the foregoing moieties, 1,4-butanediol, ethylene glycol, and combinations thereof; and agitating the molten mixture at sub-atmospheric pressure and increasing the temperature of the molten mixture to an elevated temperature under conditions sufficient to form a modified PBT containing at least one residue derived from the poly(ethylene terephthalate) component.

[0029] Polyester moieties and the 1,4-butanediol are combined in the liquid phase under agitation and the 1,4-butanediol can be continuously refluxed back into the reactor during step (a). The tetrahydrofuran (THF) and water formed in the stage can be removed by distillation or partial condensation.

[0030] The poly(ethylene terephthalate) component and the 1,4-butanediol component are generally combined under atmospheric pressure. In another embodiment, however, it is possible to use pressures that are higher than atmospheric pressures. For instance, in an embodiment, the pressure at which the poly(ethylene terephthalate) component and the 1,4-butanediol are subjected to is 2 atmospheres or higher. For higher pressures, the reaction mixtures can be depolymerized at temperatures higher than 230°C.

[0031] The temperature at which the poly(ethylene terephthalate) component and the 1,4-butanediol component are combined and reacted is sufficient to promote depolymerization of the poly(ethylene terephthalate) component into a mixture of oligomers containing ethylene terephthalate moieties, oligomers containing ethylene isophthalate moieties, oligomers containing diethylene terephthalate moieties, oligomers containing diethylene isophthalate moieties, oligomers containing butylene terephthalate moieties, oligomers containing butylene isophthalate moieties, covalently bonded oligomeric moieties containing at least two of the foregoing moieties, 1,4-butanediol, ethylene glycol, and combinations thereof. The temperature at which the poly(ethylene terephthalate) component and the 1,4-butanediol component are combined generally ranges from 180 to 230°C. 1,4-

Butanediol is generally used in excess amount relative to the poly(ethylene terephthalate) component. In an embodiment, 1,4-butanediol is used in a molar excess amount from 2 to 20.

[0032] During the initial stage of the process when the poly(ethylene terephthalate) component and the 1,4-butanediol are combined and react ("step (a)"), the poly(ethylene terephthalate) component and the 1,4-butanediol depolymerize into a molten mixture at a pressure that is at least atmospheric pressure suitable conditions. 1,4-Butanediol and ethylene glycol are generally recirculated, and tetrahydrofuran is distilled during "step (a)" of the process. The molten mixture contains oligomers containing ethylene terephthalate moieties, oligomers containing ethylene isophthalate moieties, oligomers containing diethylene terephthalate moieties, oligomers containing diethylene isophthalate moieties, oligomers containing butylene terephthalate moieties, oligomers containing butylene isophthalate moieties, covalently bonded oligomeric moieties containing at least two of the foregoing moieties, 1,4-butanediol, ethylene glycol, and combinations thereof.

[0033] The duration of the step in which poly(ethylene terephthalate) component reacts with 1,4-butanediol can vary, depending on factors, such as available equipment, production needs, desired final properties, and the like. In an embodiment, this step is carried out in at least 2 hours. In another embodiment, the step is carried out from 2 to 5 hours.

[0034] The process further includes the step of subjecting the molten mixture to sub-atmospheric pressure and increasing the temperature of the molten mixture to a temperature from 240 to 260°C, and thereby forming the modified poly(butylene terephthalate) component derived from the poly(ethylene terephthalate) component.

[0035] Excess butanediol, ethylene glycol, and THF are preferably removed and step (b) is carried out under agitation. The molten mixture, when placed in sub-atmospheric pressure conditions at a suitable temperature for a sufficiently long time period, polymerizes into a modified poly(butylene terephthalate) component derived from the poly(ethylene terephthalate) component copolymer. Generally, the molten mixture pressure is subjected to a pressure from sub-atmospheric to less than 1 Torr (0.133 MPa). In an embodiment, the pressure is reduced to a pressure from 100 to 0.05 Torr (13.3 to 0.0066 MPa) in a continuous manner. In another embodiment, the pressure is reduced to a pressure from 10 to 0.1 Torr (1.33 to 0.0133 MPa) in a continuous fashion. Advantageously, the molten mixture can be placed under sub-atmospheric conditions without isolation and dissolution of any material from the molten mixture. The avoidance of this step greatly enhances the utility of the process.

[0036] During the step when the molten mixture is placed under sub-atmospheric conditions and the temperature is increased, excess butanediol, ethylene glycol, and THF are removed from the reactor and oligomers are allowed to build in molecular weight. Agitation can be continuously provided to facilitate the removal of the low boiling components and allow the molecular weight buildup of the polymer. After sufficient molecular weight is obtained, the resulting molten PBT polymer is cast from the reactor through a diehead, cooled with water, stranded and chopped into pellets.

[0037] The duration of the step (step (b) discussed above) in which the molten mixture polymerizes from poly(ethylene terephthalate) and poly(butylene terephthalate) oligomers, 1,4-butanediol, and ethylene glycol can vary, depending on factors, such as equipment available, production needs, desired final properties, and the like. In an embodiment, this step is carried out in at least two hours. In another embodiment, the step is carried out from 2 to 5 hours.

[0038] The temperature at which the molten mixture is placed under sub-atmospheric conditions is sufficiently high to promote polymerization of the poly(ethylene terephthalate) and poly(butylene terephthalate) oligomers, 1,4-butanediol, and ethylene glycol to the modified poly(butylene terephthalate) component derived from the poly(ethylene terephthalate) component. Generally, the temperature is at least 230°C. In an embodiment, the temperature is from 250°C to 275°C.

[0039] Both steps of the process can be carried out in the same reactor. In an embodiment, however, the process is carried out in two separate reactors, where step (a) is carried out in a first reactor and when the molten mixture has formed, the molten mixture is placed in a second reactor and step (b) is carried out. In another embodiment, the process can be carried out in more than two reactors. In another embodiment, the process can be carried out in a continuous series of reactors.

[0040] The catalyst component that facilitates the reaction can be selected from antimony compounds, tin compounds, titanium compounds, combinations thereof as well as many other metal catalysts and combinations of metal catalysts that have been disclosed in the literature. The amount of the catalyst will vary depending on the specific need at hand. Suitable amounts of the catalyst range from 1 to 5000 ppm, or more. The catalyst component is generally added during the step when the poly(ethylene terephthalate) component initially combines with the 1,4-butanediol component. In another embodiment, however, the catalyst component can be added to the molten mixture that forms after the poly(ethylene terephthalate) component and the 1,4-butanediol component are combined.

[0041] The process for making the modified PBT is preferably carried out under agitative conditions. The term "agitative conditions" or "agitation" refers to subjecting the poly(ethylene terephthalate) component and the 1,4-butanediol or the molten mixture to conditions that involve physically mixing the poly(ethylene terephthalate) component 1,4-butanediol or molten mixture under conditions that promote the depolymerization of the PET when the agitative conditions are applied to poly(ethylene terephthalate) component 1,4-butanediol, i.e., step (a), or the polymerization of the PBT from poly(ethylene terephthalate) oligomers, 1,4-butanediol, and ethylene glycol, i.e., step (b). The physical mixing can be accomplished by any suitable way. In an embodiment, a mixer containing rotating shaft and blades that are perpendicular to the shaft can be used.

[0042] In another embodiment, a process involves the steps of: (a) reacting (i) a poly(ethylene terephthalate) component selected from the group consisting of poly(ethylene terephthalate) and poly(ethylene terephthalate) copolymers with a diol component selected from the group consisting of ethylene glycol, propylene glycol, and combinations thereof, in a reactor at a pressure that is at least atmospheric pressure in the presence of a catalyst component at a temperature from 190°C to 250°C, under an inert atmosphere, under conditions sufficient to depolymerize the poly(ethylene terephthalate) component into a first molten mixture containing components selected from the group consisting of oligomers containing ethylene terephthalate moieties, oligomers containing ethylene isophthalate moieties, oligomers containing diethylene terephthalate moieties, oligomers containing diethylene isophthalate moieties, oligomers containing trimethylene terephthalate moieties, oligomers containing trimethylene isophthalate moieties, covalently bonded oligomeric moieties containing at least two of the foregoing moieties, ethylene glycol, propylene glycol and combinations thereof; wherein the poly(ethylene terephthalate) component and the diol component are combined under agitation; (b) adding 1,4-butanediol to the first molten mixture in a reactor in the presence of a catalyst component at a temperature from 190 to 240°C, under conditions that are sufficient to form a second molten mixture containing a component selected from the group consisting of oligomers containing ethylene terephthalate moieties, oligomers containing ethylene isophthalate moieties, oligomers containing diethylene terephthalate moieties, oligomers containing diethylene isophthalate moieties, oligomers containing trimethylene terephthalate moieties, oligomers containing trimethylene isophthalate moieties, oligomers containing butylene terephthalate moieties, oligomers containing butylene isophthalate moieties, covalently bonded oligomeric moieties containing at least two of the foregoing moieties, 1,4-butanediol, propylene glycol, ethylene glycol, and

combinations thereof; and (c) increasing the temperature of the second molten mixture under sub-atmospheric conditions and agitation to a temperature from 240 to 260°C, thereby forming a modified PBT containing at least one residue derived from the poly(ethylene terephthalate) component.

[0043] This three-step embodiment provides an additional advantageous way for producing modified PBT copolymers from PET. The diol component used in step (a) of the three-step embodiment can be selected from ethylene glycol, propylene glycol, and combinations thereof. The diol component can be present in step (a) at a molar amount that is at least half the amount of the ethylene glycol moieties present in the poly(ethylene terephthalate) component. The depolymerization of the poly(ethylene terephthalate) component can be carried out for various times. In an embodiment, the depolymerization is carried out for at least 25 minutes. The 1,4-butanediol used during step (b) of the three step embodiment can be added at a molar amount that is in excess relative to the molar amount of butanediol moieties incorporated into the modified PBT component obtained in step (c). During the process the compounds used in the process can be reused and/or collected. In an embodiment, the diol component selected from the group consisting of ethylene glycol, propylene glycol, and combinations thereof and (2) 1,4-butanediol are removed and collected in a vessel in step (b). In another embodiment, in step (b), 1,4-butanediol is refluxed back into the reactor and a component selected from the group of excess butanediol, ethylene glycol, propylene glycol, tetrahydrofuran, and combinations thereof is removed. Step (b) is practiced for a sufficient period of time to reduce at least 65 % of ethylene glycol from the second molten mixture. The duration of step (b) can also vary. In an embodiment, step (b) lasts at least 45 minutes. The pressure at which step (b) is carried out can vary. In an embodiment, step (b) is carried out in atmospheric conditions. In another embodiment, step (b) is carried out in sub-atmospheric conditions. Different combinations are possible. In an embodiment, step (b) is carried out with excess 1, 4-butanediol and at a pressure from 300 to 1500 mbar absolute (30 to 150 MPa). In another embodiment, 1,4-butanediol is used in a molar excess amount from 1.1 to 5. Step (c) of the three-step embodiment can also be carried out with modifications, depending on the application. In an embodiment, for example, a component selected from the group of excess butanediol, ethylene glycol, propylene glycol, tetrahydrofuran, and combinations thereof is removed during step (c). The pressure at which step (c) is carried out can also vary. In an embodiment, step (c) is carried out at a pressure that is less than 10 mbar (1 MPa). The three-step process can be carried out in the same reactor. Alternatively, the three-step process can be carried out in at least two reactors.

[0044] In another embodiment, the three-step process can include the step of adding a basic compound during step (a), step (b), step (c), and combinations thereof, and thereby further reduce THF production. The basic compound, as in the two-step embodiment, can contain those compounds mentioned above. Alternatively, difunctional epoxy compounds can be added during step (b) in the amounts indicated above.

[0045] The process for making the modified PBT copolymer can contain an additional step in which the PBT formed from the molten mixture is subjected to solid-state polymerization. Solid-state polymerization generally involves subjecting the PBT formed from the molten mixture to an inert atmosphere or sub-atmospheric pressure and heating to a temperature for a sufficient period of time to build the molecular weight of the PBT. Generally, the temperature to which the PBT is heated is below the melting temperature of the PBT, e.g., from 5°C to 60°C below the melting temperature of the PBT. In an embodiment, such a temperature can range from 150°C to 210°C. Suitable periods of time during which the solid-state polymerization occurs can range from 2 to 20 hours, depending on the conditions and equipment. The solid-state polymerization is generally carried out under tumultuous conditions sufficient to promote further polymerization of the PBT to a suitable molecular weight. Such tumultuous conditions can be created by subjecting the PBT to tumbling, the pumping of inert gas into the system to promote fluidization of polymer particle, e.g., pellets, chips, flakes, powder, and the like. The solid-state polymerization can be carried out at atmospheric pressure and/or under reduced pressure, e.g. from 1 atmosphere to 1 mbar (101 to 0.1 MPa).

[0046] A combination of polyesters can be used, for example a combination of virgin polyesters (polyesters derived from monomers rather than recycled polymer, including virgin poly(1,4-butylene terephthalate) and modified PBT. Also contemplated herein are second polyesters comprising minor amounts, e.g., 0.5 to 30 wt%, of units derived from aliphatic acids and/or aliphatic polyols to form copolyesters. The aliphatic polyols include glycols, such as poly(ethylene glycol). Such polyesters can be made following the teachings of, for example, U.S. Pat. Nos. 2,465,319 to Whinfield et al., and 3,047,539 to Pengilly. Second polyesters comprising block copolyester resin components are also contemplated, and can be prepared by the transesterification of (a) straight or branched chain poly(alkylene terephthalate) and (b) a copolyester of a linear aliphatic dicarboxylic acid and, optionally, an aromatic dibasic acid such as terephthalic or isophthalic acid with one or more straight or branched chain dihydric aliphatic glycols. Especially useful when high melt strength is

important are branched high melt viscosity resins, which include a small amount of, e.g., up to 5 mole percent based on the acid units of a branching component containing at least three ester forming groups. The branching component can be one that provides branching in the acid unit portion of the polyester, in the glycol unit portion, or it can be a hybrid branching agent that includes both acid and alcohol functionality. Illustrative of such branching components are tricarboxylic acids, such as trimesic acid, and lower alkyl esters thereof, and the like; tetracarboxylic acids, such as pyromellitic acid, and lower alkyl esters thereof, and the like; or preferably, polyols, and especially preferably, tetrols, such as pentaerythritol; triols, such as trimethylolpropane; dihydroxy carboxylic acids; and hydroxydicarboxylic acids and derivatives, such as dimethyl hydroxyterephthalate, and the like. Branched poly(alkylene terephthalate) resins and their preparation are described, for example, in U.S. Pat. No. 3,953,404 to Borman. In addition to terephthalic acid units, small amounts, e.g., from 0.5 to 15 mole percent of other aromatic dicarboxylic acids, such as isophthalic acid or naphthalene dicarboxylic acid, or aliphatic dicarboxylic acids, such as adipic acid, can also be present, as well as a minor amount of diol component other than that derived from 1,4-butanediol, such as ethylene glycol or cyclohexane dimethanol, etc., as well as minor amounts of trifunctional, or higher, branching components, e.g., pentaerythritol, trimethyl trimesate, and the like.

[0047] In an embodiment, a PBT (for example a PET-derived PBT) is used in combination with a poly(ethylene terephthalate), poly(1,4-butylene terephthalate), poly(ethylene naphthalate), poly(1,4-butylene naphthalate), poly(trimethylene terephthalate), poly(1,4-cyclohexanedimethylene 1,4-cyclohexanedicarboxylate), poly(1,4-cyclohexanedimethylene terephthalate), poly(1,4-butylene-co-1,4-but-2-ene diol terephthalate), poly(cyclohexanedimethylene-co-ethylene terephthalate), or a combination thereof. The weight ratio of PBT:other polyester can vary from 50:50 to 99:1, specifically from 80:20 to 99:1.

[0048] Any of the foregoing first and optional second polyesters can have an intrinsic viscosity of 0.4 to 2.0 deciliters per gram (dLVg), measured in a 60:40 by weight phenol/1,1,2,2-tetrachloroethane mixture at 23°C. The PBT can have a weight average molecular weight of 10,000 to 200,000 Daltons, specifically 50,000 to 150,000 Daltons as measured by gel permeation chromatography (GPC). The polyester component can also comprise a mixture of different batches of PBT prepared under different process conditions in order to achieve different intrinsic viscosities and/or weight average molecular weights. In an embodiment, a combination of polyesters having different viscosities is used, for example a



combination comprising a first polyester having a viscosity from 0.5 to 1.0 dL/g and a second polyester having an intrinsic viscosity ranging from 1.1 to 1.4 dL/g. One or both of the polyesters can be a PBT, in particular a PET-derived PBT. The weight ratio of the two polyesters of different viscosity can be adjusted to achieve the desired properties, and is generally within the range of 20:80 to 80:20, more specifically from 40:60 to 60:40.

[0049] The amount of the polyester in the compositions can be adjusted to provide the desired properties within the limits described herein, which varies with the specific application. The composition can accordingly comprise from 40 to 60 wt%, specifically from 45 to 55 wt%, of the polyester, wherein each of the foregoing is based on the total weight of the composition.

[0050] The composition includes a melamine flame retardant synergist and a phosphinate flame retardant. It has been found that this combination provides excellent flame retardance, in combination with advantageous physical properties in the absence of PEL. The flame retardant synergist is melamine pyrophosphate, melamine polyphosphate, melamine phosphate, or melamine cyanurate. Combinations comprising the foregoing can be used.

[0051] The flame retardant synergist is present in the composition in an amount from 2 to 8 wt%, specifically from 3 to 7 wt%, still more specifically from 4 to 6 wt%, each based on the total weight of the composition.

[0052] The flame retardant synergist is used in combination with one or more phosphinic acid salts. The phosphinates and diphosphinates include those set forth in U.S. Pat. No. 6,255,371 to Schosser et al. The specification of this patent, column 1, line 46 to column 3 line 4 is incorporated by reference into the present specification. Specific phosphinates mentioned include aluminum diethylphosphinate (DEPAL), and zinc diethylphosphinate (DEPZN). The phosphinates have the formulas



and include polymers comprising such formula I or II, wherein R^1 and R^2 are the same or different and are H, Ci-C₆ alkyl, linear or branched, or C₆-C₁₀ aryl; and R^3 is C₁-C₁₀, alkylene, linear or branched, C₆-C₁₀ arylene, C₇-C_n alkylarylene, or C₇-C_n arylalkylene; M is an alkaline earth metal, alkali metal, Al, Ti, Zn, Fe, or boron; m is 1, 2, 3 or 4; n is 1, 2, or 3; and x is 1 or 2. In an embodiment R^1 and R^2 are the same and are Ci-C₆-alkyl, linear or branched, or phenyl; R^3 is Ci-C₁₀-alkylene, linear or branched, C₆-C₁₀-arylene, -alkylarylene or -arylalkylene; M is magnesium, calcium, aluminum, zinc, or a combination thereof; m is 1, 2 or 3; n is 1, 2 or 3; and x is 1 or 2. R^1 and R^2 can be H, in addition to the substituents

referred to set forth in the patent. This results in a hypophosphite, a subset of phosphinate, such as calcium hypophosphite, aluminum hypophosphite, and the like.

[0053] In a specific embodiment M is aluminum, and R^1 and R^2 are the same and are H, C_1-C_6 alkyl, linear or branched; and R^3 is C_1-C_{10} alkylene, linear or branched. A commercial example of a phosphinic acid salt includes aluminum diethyl phosphinic acid (Al-DPA), commercially available from Clariant Corp.

[0054] The composition comprises from 5 to 15 wt%, specifically from 8 to 14 wt%, even more specifically from 10 to 12.5 wt% of a flame retardant phosphinate salt, based on the total weight of the composition.

[0055] The thermoplastic polyester composition also comprises a reinforcing filler, for example rigid fibers such as glass fibers, carbon fibers, metal fibers, ceramic fibers or whiskers, and the like. Glass fibers typically have a modulus of greater than or equal to about 6,800 megaPascals, and can be chopped or continuous. The glass fiber can have various cross-sections, for example, round, trapezoidal, rectangular, square, crescent, bilobal, trilobal, and hexagonal. Glass fibers can be in the form of chopped strands having an average length of from 0.1 mm to 10 mm, and having an average aspect ratio of 2 to 5. In articles molded from the compositions, shorter lengths will typically be encountered because during compounding considerable fragmentation can occur.

[0056] In some applications it can be desirable to treat the surface of the fiber, in particular a glass fiber, with a chemical coupling agent to improve adhesion to a thermoplastic resin in the composition. Examples of useful coupling agents are alkoxy silanes and alkoxy zirconates. Amino, epoxy, amide, or thio functional alkoxy silanes are especially useful. Fiber coatings with high thermal stability are preferred to prevent decomposition of the coating, which could result in foaming or gas generation during processing at the high melt temperatures required to form the compositions into molded parts.

[0057] The reinforcing filler, for example a glass fiber, is present in the composition in an amount from 25 to 35 wt%, specifically from 20 to 40% by weight, and most preferably, from 25 to 35% by weight.

[0058] In still other embodiments, the compositions can optionally additionally comprise a particulate (non-fibrous) organic filler, which can impart additional beneficial properties to the compositions such as thermal stability, increased density, stiffness, and/or texture. Exemplary particulate fillers are inorganic fillers such as alumina, amorphous silica, alumino silicates, mica, clay, talc, glass flake, glass microspheres, metal oxides such as titanium dioxide, zinc sulfide, ground quartz, and the like.

[0059] In some embodiments, the reinforcing filler, for example glass fibers, is used in combination with a flat, plate-like filler, for example talc, mica or flaked glass. Typically, the flat, plate-like filler has a length and width at least ten times greater than its thickness, where the thickness is from 1 to about 1000 microns. Combinations of rigid fibrous fillers with flat, plate-like fillers can reduce warp of the molded article. A specific particulate filler is talc, in particular a talc filler having an average largest dimension of less than 0.9 micrometers. In addition, or in the alternative, the filler can have a median particle size of less than 0.9 micrometers. In an embodiment, the equivalent spherical diameter of the particle is used to determine particle size. Use of these types of filler provides molded articles having both low shrinkage and a smooth surface finish. Use of these types of filler can also aid the crystallization of the polyester, and increase heat resistance of the composition. Such talcs are commercially available from Barretts Minerals Inc. under the trade name ULTRATALC® 609.

[0060] When present, the particulate filler is used in an amount from more than zero to 3 wt%, specifically more than 0 to 2 wt%, more specifically from 0.1 to 1 wt%.

[0061] The composition further comprises a specific amount of a specific combination of two types impact modifiers, a poly(ether-ester) elastomer and a (meth)acrylate impact modifier. It has surprising been found that use of only a single impact modifier, or a combination of impact modifiers outside of the specified range, adversely affects the desired combination of properties. In a specific embodiment, no other impact modifiers are present in the composition.

[0062] Poly(ester-ether) elastomers are copolymers that contain "hard blocks" (derived from the polyester units) and "soft blocks" (derived from the polyether units) that provide the polymer with elastomeric properties. The copolymers can be characterized by the melting temperature (T_m) of the hard block and the glass transition temperature (T_g) of the soft block and. In general, the T_m of the hard block can be 120 to 200°C, specifically 150 to 195°C, and the T_g of the soft block can be -25 to -85 °C, specifically -45 to -65 °C.

[0063] The poly(ester-ether) elastomers accordingly comprise units derived from the reaction of a dicarboxylic acid component (or chemical equivalent thereof) with two types of diols (or chemical equivalent thereof), a short chain C1-10 diol, and a long-chain poly(oxyalkylene) diol.


[0064] The dicarboxylic acid component can be one or more of the dicarboxylic acids described above in connection with the polyesters. In one embodiment, the dicarboxylic acid is aromatic, for example terephthalic acid, isophthalic acid, or a combination comprising at

least one of the foregoing acids. In a specific embodiment, the dicarboxylic acid is terephthalic acid. In another embodiment, the dicarboxylic acid is a combination of terephthalic acid and isophthalic acid.


[0065] Suitable short chain diols include C1-8 diols as described above in connection with the polyester. Specific diols are ethylene glycol and butane diol, even more specifically butane diol.

[0066] The poly(oxyalkylene) diol is derived from the polymerization of a C1-6 diol or a combination comprising one or more C1-6 diols, in particular C2-4 diols, or the chemical equivalents thereof. Poly(oxytetramethylene) glycol is preferred, and can be prepared by well known techniques. The poly(oxyalkylene) diol, in particular the poly(oxytetramethylene) glycol, has a weight average molecular weight (Mw) of 100 to 5,000, or more specifically, 150 to 4,000, or even more specifically, 200 to 3,000.

[0067] The poly(ether-ester) elastomers can accordingly comprise long-chain ester units of formula (III):



and short-chain ester units having units of formula (IV):



wherein R' is a divalent aromatic radical remaining after removal of carboxyl groups from terephthalic acid, isophthalic acid, or a combination of terephthalic acid and isophthalic acid; G is a divalent polyalkylene oxide radical remaining after removal of terminal hydroxyl groups from a poly(alkylene oxide) glycol having a number-average molecular weight of 100 to 2500 Daltons; and D is the divalent alkylene radical remaining after removal of hydroxyl groups from an aliphatic diol having a molecular weight from 62 to 286.

[0068] A specific poly(ester-ether) elastomer is a poly(butylene terephthalate/isophthalate-oxytetramethylene) copolymer, i.e., a poly(butylene terephthalate-polytetrahydrofuran) block copolymer. The copolymer comprises 25 to 65 wt%, more specifically 30 to 60 wt%, even more specifically 25 to 55 wt% of units derived from poly(oxytetramethylene) glycol or chemical equivalents thereof, based on the weight of the copolymer.

[0069] The poly(butylene terephthalate-oxytetramethylene) copolymer can further comprise isophthalic acid in addition to terephthalic acid. In one embodiment, the poly(butylene terephthalate/isophthalate-oxytetramethylene) copolymer comprises 0 to 40 mole% of units derived from isophthalic acid or a chemical equivalent thereof, based on the total number of isophthalate and terephthalate units. For example, the poly(butylene

terephthalate/isophthalate-oxytetramethylene) copolymer can comprise less than 5 mole % of isophthalate units, specifically 0 to 5 mole% of isophthalate units, based on the total number of isophthalate and terephthalate units in the copolymer. In another embodiment, the poly(butylene terephthalate/isophthalate-oxytetramethylene) copolymer comprises greater than 5 mole % of isophthalate units, specifically 5 to 40 mole %, based on the total number of isophthalate and terephthalate units in the copolymer.

[0070] A variety of poly(ether-ester) copolymers are commercially available, for example under the trademarks ARNITEL EM400 and ARNITEL EL630 poly(ether-ester) copolymers from DSM; HYTREL 3078, HYTREL 4056, HYTREL 4556, and HYTREL 6356 poly(ether-ester) copolymers from DuPont; and ECDEL 9966 poly(ether-ester) copolymer from Eastman Chemical. In all cases, the soft block is derived from tetrahydrofuran. In the HYTREL 4556, HYTREL 6356, ARNITEL EM400, and ARNITEL EL630 poly(ether-ester) copolymers, the hard block is based on poly(butylene terephthalate) (PBT). In the HYTREL 4056 poly(ether-ester) copolymer, the hard block contains isophthalate units in addition to terephthalate units. In the ECDEL 9966 poly(ether-ester) copolymer, the hard block is based on poly(1,4-cyclohexane-dimethanol-1,4-cyclohexane dicarboxylate) (PCCD) units. In another embodiment, the poly(ether-ester) elastomer can include a thermoplastic copolyetherester elastomer derived from polyethylene terephthalate, in particular, post-consumer polyethylene terephthalate. The random copolyetherester contains a modified, random polybutylene terephthalate copolymer block that is derived from a polyethylene terephthalate component selected from the group consisting of polyethylene terephthalate and polyethylene terephthalate copolymers, or a combination thereof; and contains at least one residue derived from the polyethylene terephthalate component; and a polyalkylene oxide copolymer block that is derived from a polyethylene terephthalate component and polyalkylene oxide glycol, and contains polyalkylene oxide and at least one residue derived from the polyethylene terephthalate component. Such random copolyetheresters are disclosed in U.S. Publ. 2008/0027167, and is commercially available under the trademark VALOX iQ elastomer, which can be available from SABIC Innovative Plastics.

[0071] The impact modifier component also comprises a (meth)acrylate impact modifier. A (meth)acrylate impact modifier includes graft and/or core shell structures having a rubbery component with a T_g below 0°C , preferably between about -40°C to about -80°C , and which include a poly(alkyl (meth)acrylate) or polyolefin grafted with a poly(methyl methacrylate) or styrene-acrylonitrile copolymer.

[0072] Typical core materials in core-shell impact modifiers consist substantially of a (meth)acrylate rubber, for example a (meth)acrylate rubber of derived from a C4-12 acrylate. Typically, one or more shells are grafted on the core. Usually these shells are built up from a vinyl aromatic compound, a vinyl cyanide, an alkyl (meth)acrylate, (meth)acrylic acid, or a combination thereof. The shell can be derived from an alkyl (meth)acrylate, more specifically a methyl (meth)acrylate. The core and/or the shell(s) often comprise multi-functional compounds that can act as a cross-linking agent and/or as a grafting agent. In one embodiment, the (meth)acrylate impact modifier has a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell.

[0073] Core-shell acrylic rubbers can be of various particle sizes, for example from 300-800 nm, although larger particles, or mixtures of small and large particles, can also be used. In some instances, (meth)acrylate impact modifier with a particle size of 350-450 nm is used. In other applications where higher impact is desired, particle sizes of 450-550 nm or 650-750 nm can be used.

[0074] Specific (meth)acrylate impact modifiers include the core-shell polymers available from Rohm & Haas (now Dow Advanced Materials) under the trade name PARALOID®, including, for example, PARALOID® EXL3691 and PARALOID® EXL3330, EXL3300 and EXL2300.

[0075] Other (meth)acrylate impact modifiers include ethylene-acrylic acid copolymers (EEA), sold by Dupont under the trade name ELVALOY; ethylene-methacrylate-glycidyl methacrylate copolymers (E-GMA-MA), sold by Arkema under the trade name LOTADER®; and polyethylene-g-glycidyl methacrylate (10%), sold by Sumitomo Chemical Co. under the trade name IGETABOND E.

[0076] The impact modifier component is present in the composition in an amount from more than 0 to less than 5 wt%, specifically from 2 to 2.5 wt%.

[0077] In a specific embodiment, the impact modifier component comprises from more than 0 to 5 wt%, specifically from 2 to 4 wt%, of a combination of (i) a poly(butylene terephthalate-polytetrahydrofuran) block copolymer and (ii) a core-shell impact modifier having a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell.

[0078] The polyester compositions further comprise from more than 0 to 5 wt%, specifically from 0.5 to 5 wt% of an encapsulated particulate fluoropolymer, in particular poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer.). Small amounts of other fluoropolymers can be used, for example those comprising units derived from fluorinated monomers such as 3,3,3-trifluoropropene, 3,3,3,4,4-pentafluoro-1-butene,

hexafluoropropylene, vinyl fluoride; vinylidene fluoride, 1,2-difluoroethylene, and the like, or a mixture comprising at least one of the foregoing monomers

[0079] The fluoropolymer is encapsulated styrene-acrylonitrile (SAN). PTFE encapsulated in styrene-acrylonitrile is also known as TSAN.

[0080] Encapsulated fluoropolymers can be made by polymerizing the encapsulating polymer in the presence of the fluoropolymer, for example an aqueous dispersion of the fluoropolymer. Alternatively, the fluoropolymer can be pre-blended with a second polymer, such as for, example, an aromatic polycarbonate or SAN to form an agglomerated material. Either method can be used to produce an encapsulated fluoropolymer. The relative ratio of monovinyl aromatic monomer and monovinyl comonomer in the rigid graft phase can vary widely depending on the type of fluoropolymer, type of monovinylaromatic monomer(s), type of comonomer(s), and the desired properties of the composition. The rigid phase can comprise 10 to 95 wt% of monovinyl aromatic monomer, specifically about 30 to about 90 wt%, more specifically 50 to 80 wt% monovinylaromatic monomer, with the balance of the rigid phase being comonomer(s). The SAN can comprise, for example, about 75 wt% styrene and about 25 wt% acrylonitrile based on the total weight of the copolymer. An exemplary TSAN comprises about 50 wt% PTFE and about 50 wt% SAN, based on the total weight of the encapsulated fluoropolymer.

[0081] The molding composition can optionally comprise a small amount of a charring polymer, in particular a polyetherimide (PEI). A commercially available polyetherimide is available from SABIC Innovative Plastics Co. under the trade name ULTEM® 1010. Other charring polymers include, poly(phenylene ether), poly(phenylenesulfide), polysulphones, polyethersulphones, poly(phenylenesulphide oxide) (PPSO), and polyphenolics (e.g., novolacs). Use of a polyetherimide in compositions comprising aluminum phosphinate salts can improve the mechanical properties of the compositions, in particular tensile strength and impact properties. High temperature molding stability can also be further improved, as well as melt stability.

[0082] The charring polymer, in particular PEI, can accordingly be present in an amount from 0 to less than 5 wt% of the composition, more specifically from more than 0 to less than 3 wt%, by even more specifically from more than 0 to less than 1 wt%, based on the total weight of the composition.

[0083] However, in a unique advantage of the current compositions, improvement in flexural modulus, notched and unnotched Izod impact strength, tensile stress at break and/or elastic modulus, and high CTI is observed when the composition comprises no

polyetherimide. Thus, in one embodiment, no polyetherimide is present. In another embodiment, no charring polymer is present. In an embodiment wherein the composition contains no polyetherimide, an article molded from the composition exhibits a CTI (Comparative Tracking Index) of 600 volts.

[0084] A stabilizer component is further present in the composition, in an amount from more than 0 to 2 wt%, specifically 0.01 to 1 wt%, even more specifically 0.05 to 0.5 wt%. As used herein, a "stabilizer" is inclusive of an antioxidant, thermal stabilizer, radiation stabilizer, ultraviolet light absorbing additive, and the like, and combinations thereof. In one embodiment the stabilizer component comprises an antioxidant.

[0085] Exemplary antioxidants include organophosphites such as tris(nonyl phenyl)phosphite, tris(2,4-di-*t*-butylphenyl)phosphite, bis(2,4-di-*t*-butylphenyl)pentaerythritol diphosphite, distearyl pentaerythritol diphosphite; alkylated monophenols or polyphenols; alkylated reaction products of polyphenols with dienes, such as tetrakis[methylene(3,5-di-*tert*-butyl-4-hydroxyhydrocinnamate)] methane; butylated reaction products of para-cresol or dicyclopentadiene; alkylated hydroquinones; hydroxylated thiodiphenyl ethers; alkylidene-bisphenols; benzyl compounds; esters of beta-(3,5-di-*tert*-butyl-4-hydroxyphenyl)-propionic acid with monohydric or polyhydric alcohols; esters of beta-(5-*tert*-butyl-4-hydroxy-3-methylphenyl)-propionic acid with monohydric or polyhydric alcohols; esters of thioalkyl or thioaryl compounds such as distearylthiopropionate, dilaurylthiopropionate, ditridecylthiodipropionate, octadecyl-3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)propionate, pentaerythrityl-tetrakis[3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)propionate; amides of beta-(3,5-di-*tert*-butyl-4-hydroxyphenyl)-propionic acid, or combinations comprising at least one of the foregoing antioxidants. A specific antioxidant is a hindered phenol stabilizer, pentaerythritol tetrakis(3,5-di-*tert*-butyl-4-hydroxyhydrocinnamate), sold under the trade name IRGANOX® 1010 from Ciba Specialty Chemicals.

[0086] Exemplary heat stabilizer additives include organophosphites such as triphenyl phosphite, tris-(2,6-dimethylphenyl)phosphite, tris-(mixed mono-and di-nonylphenyl)phosphite; phosphonates such as dimethylbenzene phosphonate, phosphates such as trimethyl phosphate, or combinations comprising at least one of the foregoing heat stabilizers. Heat stabilizers are used in amounts of 0.01 to 0.1 parts by weight, based on 100 parts by weight of the total composition, excluding any filler.

[0087] Light stabilizers and/or ultraviolet light (UV) absorbing additives can also be used. Exemplary light stabilizer additives include benzotriazoles such as 2-(2-hydroxy-5-

methylphenyl)benzotriazole, 2-(2-hydroxy-5-tert-octylphenyl)-benzotriazole and 2-hydroxy-4-n-octoxy benzophenone, or combinations comprising at least one of the foregoing light stabilizers. Light stabilizers are used in amounts of 0.01 to 5 parts by weight, based on 100 parts by weight of the total composition, excluding any filler.

[0088] Exemplary UV absorbing additives include hydroxybenzophenones; hydroxybenzotriazoles; hydroxybenzotriazines; cyanoacrylates; oxanilides; benzoxazinones; 2-(2H-benzotriazol-2-yl)-4-(1,1,3,3-tetramethylbutyl)-phenol (CYASORB® 5411); 2-hydroxy-4-n-octyloxybenzophenone (CYASORB® 531); 2-[4,6-bis(2,4-dimethylphenyl)-1,3,5-triazin-2-yl]-5-(octyloxy)-phenol (CYASORB® 1164); 2,2'-(1,4-phenylene)bis(4H-3,1-benzoxazin-4-one) (CYASORB® UV-3638); 1,3-bis[(2-cyano-3,3-diphenylacryloyl)oxy]-2,2-bis[[[(2-cyano-3,3-diphenylacryloyl)oxy]methyl]propane (UVINUL® 3030); 2,2'-(1,4-phenylene)bis(4H-3,1-benzoxazin-4-one); 1,3-bis[(2-cyano-3,3-diphenylacryloyl)oxy]-2,2-bis[[[(2-cyano-3,3-diphenylacryloyl)oxy]methyl]propane; nano-size inorganic materials such as titanium oxide, cerium oxide, and zinc oxide, all with particle size less than or equal to 100 nanometers; or combinations comprising at least one of the foregoing UV absorbers. UV absorbers are used in amounts of 0.01 to 5 parts by weight, based on 100 parts by weight of the total composition, excluding any filler.

[0089] With the proviso that flame retardance properties and mechanical properties such as impact strength and flexural modulus are not significantly adversely affected, the compositions can further comprise other conventional additives used in polyester polymer compositions such as mold release agents, plasticizers, quenchers, lubricants, antistatic agents, processing aids, dyes, pigments, laser marking additives, and the like. A combination comprising one or more of the foregoing or other additives can be used. Plasticizers, lubricants, and/or mold release agents can be specifically mentioned. There is considerable overlap among these types of materials, which include phthalic acid esters such as dioctyl-4,5-epoxy-hexahydrophthalate; tris-(octoxycarbonyl)isocyanurate; tristearin; di- or polyfunctional aromatic phosphates such as resorcinol tetraphenyl diphosphate (RDP), the bis(diphenyl) phosphate of hydroquinone and the bis(diphenyl) phosphate of bisphenol A; poly- α -olefins; epoxidized soybean oil; silicones, including silicone oils; esters, for example, fatty acid esters such as alkyl stearyl esters, e.g., methyl stearate, stearyl stearate, pentaerythritol tetrastearate, and the like; combinations of methyl stearate and hydrophilic and hydrophobic nonionic surfactants comprising polyethylene glycol polymers, polypropylene glycol polymers, poly(ethylene glycol-co-propylene glycol) copolymers, or a combination comprising at least one of the foregoing glycol polymers, e.g., methyl stearate

and polyethylene-polypropylene glycol copolymer in a solvent; waxes such as beeswax, montan wax, and paraffin wax. Such materials are used in amounts of 0.1 to 1 parts by weight, based on 100 parts by weight of the total composition, excluding any filler. An exemplary mold release agent is pentaerythritol tetrastearate, available from Faci SpA.

[0090] The compositions can be prepared by blending the components of the composition, employing a number of procedures. In an exemplary process, the polyester component, reinforcing filler, melamine flame retardant synergist, phosphinate salt flame retardant, impact modifier component, poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer, stabilizer, and optionally polyetherimide are placed into an extrusion compounder to produce molding pellets. The components are dispersed in a matrix in the process. In another procedure, the components and reinforcing filler are mixed by dry blending, and then fluxed on a mill and comminuted, or extruded and chopped. The composition and any optional components can also be mixed and directly molded, e.g., by injection or transfer molding techniques. Preferably, all of the components are freed from as much water as possible. In addition, compounding is carried out to ensure that the residence time in the machine is short; the temperature is carefully controlled; the friction heat is utilized; and an intimate blend between the components is obtained.

[0091] The components can be pre-compounded, pelletized, and then molded. Pre-compounding can be carried out in conventional equipment. For example, after pre-drying the polyester composition (e.g., for four hours at 120°C), a single screw extruder can be fed with a dry blend of the ingredients, the screw employed having a long transition section to ensure proper melting. Alternatively, a twin screw extruder with intermeshing co-rotating screws can be fed with resin and additives at the feed port and reinforcing additives (and other additives) can be fed downstream. In either case, a generally suitable melt temperature will be 230°C to 300°C. The pre-compounded composition can be extruded and cut up into molding compounds such as conventional granules, pellets, and the like by standard techniques. The composition can then be molded in any equipment conventionally used for thermoplastic compositions, such as a Newbury or van Dorn type injection molding machine with conventional cylinder temperatures, at 230°C to 280°C, and conventional mold temperatures at 55°C to 95°C. The molded compositions provide an excellent balance of impact strength and flame retardancy.

[0092] In particular, the compositions provide excellent flame retardancy when molded into either thick or thin components. One set of test conditions commonly accepted and used as a standard for flame retardancy is set forth in Underwriters Laboratories, Inc.

Bulletin 94, which prescribes certain conditions by which materials are rated for self-extinguishing characteristics. Another set of conditions commonly accepted and used (especially in Europe) as a standard for flame retardancy is the Glow Wire Ignition Test (GWIT), performed according to the International standard IEC 695-2-1/2. A 0.8 mm thick molded sample comprising the composition can have a UL-94 flammability rating of V0.

[0093] An article can be molded from the thermoplastic polyester composition as described above. The article can include computer fans, electrical connectors, automotive battery housings, and lighting sockets.

[0094] A molded article comprising the composition can have a flexural modulus of from 3000 MPa to 20000 MPa, more specifically more than 9800 MPa to 20000 MPa, measured in accordance with ASTM 790, and the flexural stress at break can be from 120 to 200 MPa, more specifically 130 to 190 MPa, even more specifically more than 150 MPa to 190 MPa, measured in accordance with ASTM 790.

[0095] A molded article comprising the composition can have good impact properties, for example, an unnotched Izod impact strength from 300 to 700 J/m, more specifically, more than 470 J/m to 700 J/m, as measured at 23°C in accordance with ASTM D256.

[0096] In a specific embodiment, the glass-filled, chlorine- and bromine-free poly(alkylene ester) flame retardant composition containing a combination of impact modifiers can have a combination of highly useful physical properties, namely, good flame retardance performance (e.g., a rating of V0 at 0.80 mm), higher CTI performance, improved impact properties and improved flexural properties, as compared to a glass-filled, chlorine and bromine-free poly(alkylene ester) flame retardant composition that contains polyimide but no elastomers. More specifically, the compositions containing a combination of elastomers can meet targeted performance properties, namely: (a) a flexural modulus greater than 9800 MPa, (b) a flexural stress greater than 150 MPa, (c) an unnotched impact strength greater than 470 Joules/meter, and (d) a rating of V0 at a thickness of 0.8 mm, measured in accordance with the UL 94 protocol.

[0097] For example, an article molded from the following thermoplastic polyester composition exhibits (a) a flexural modulus that is more than 9800 MPa, (b) a flexural stress is more than 150 MPa, (c) an unnotched impact strength that is more than 470 Joules/meter, and (d) a V0 rating at 0.8 mm, measured in accordance with UL 94, when the composition comprises, based on the weight of the composition, a combination of: (a) from 40 to 60 wt% of polybutylene terephthalate; (b) from 25 to 35 wt% glass fiber filler; (c) from 2 to 8 wt% of

a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof; (d) from more than 10 to 15 wt% a phosphinate of formula (I) described herein a diphosphinate of formula (II) described herein, and/or a polymer derived from the phosphinate of formula (I) or the diphosphinate of the formula (II), (e) at least 1 to less than 5 wt% of impact modifier component comprising a combination of (i) a poly(butylene terephthalate-polytetrahydrofuran) block copolymer and (ii) a core-shell (meth)acrylate impact modifier having a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell; (f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; and (g) from more than 0 wt% to 2 wt% of a stabilizer; wherein the halogen free composition contains less than 2 wt% of a polyetherimide.

[0098] Advantageously, it is now possible to make gas filled halogen free flame retarding compositions that exhibit good flame retardancy performance (i.e., V0 at 0.80 mm), higher CTI performance, improved impact properties and improved flexural properties. Our invention provides an eco-FR thermoplastic polyester composition having good flame retardant properties and comparable or improved mechanical properties, including ductility, flexural strength, CTI, and stiffness relative to compositions comprising halogenated flame retardants and eco-FR compositions comprising PEL

[0099] It should be clear that the compositions and articles disclosed herein can include reaction products of the above described components used in forming the compositions and articles.

[00100] The invention is further illustrated by the following non-limiting examples, in which all parts are by weight unless otherwise stated.

EXAMPLES

[00101] The following materials were used in Examples 1 to 8 (i.e., E1 to E8) and Comparative Examples 1 to 25 (i.e., CE1 to CE25). Table 1 shows the nomenclature used as well as a description. All amounts in the following Tables are weight percent, unless indicated otherwise.

Table 1. Abbreviation, Description and Sources of Materials used in Examples

Abbreviation	Description	Source
VALOX iQ* PBT-1	Intrinsic viscosity = 1.19 dl/g, Mn = 110,000 g/mol	SABIC Innovative Plastics Company
VALOX iQ*-PBT-2	Intrinsic viscosity = 0.66 dl/g, Mn = 53400 g/mol	SABIC Innovative Plastics Company
Glass Fiber	13-micron diameter	PPG Industries
MPP	Melamine polyphosphate	Ciba Specialty
Al-DPA	Aluminum diethyl phosphinic acid	Clariant
PEI	Polyetherimide (ULTEM 1010)	SABIC Innovative Plastics Company
TSAN	SAN encapsulated PTFE	SABIC Innovative Plastics Company
AO	Hindered phenol stabilizer	Ciba Specialty
PETS	Pentaerythritol tetrastearate	Faci SpA
ULTRATALC	Talc (avg particle size < 0.90 micrometer)	Barretts
ELVALOY 2615 AC	Ethylene-ethyl acrylate copolymer	Dupont
IGETABOND E	Polyethylene-g-glycidyl methacrylate (10%)	Sumitomo
LOTADER	E-GMA-MA	Arkema
HYTREL	Poly(butylene tere/iso phthalate-co-polyoxybutylene)	Dupont
PARALOID EXL	Acrylic polymer impact modifier	Rohm & Haas
VALOX iQ* Elastomer**	Thermoplastic poly(ether-ester) elastomer	SABIC Innovative Plastics Company

* Trademark of SABIC Innovative Plastics IP B.V.

** The VALOX iQ thermoplastic poly(ether-ester) elastomer used was a polybutylene terephthalate -based poly(ester-ether) derived from post-consumer polyethylene terephthalate, as disclosed in US Publ. 2008/0027167. The poly(ester-ether) copolymer comprises units derived from terephthalic or a chemical equivalent thereof, units derived from butane diol or a chemical equivalent thereof, and 23 to 70 weight percent of units derived from poly(oxytetramethylene) glycol or a chemical equivalent thereof, based on the weight of the copolymer.

Techniques and Procedures

[00102] Extrusion/Molding Procedures. The components as shown in Table 1 were tumble blended and then extruded on a 27-mm twin-screw extruder with a vacuum vented mixing screw, at a barrel and die head temperature of 240°C - 265 °C and a screw speed of 300 rpm. The extrudate was cooled through a water bath before pelletizing. ASTM Izod and flexural bars were injection molded on a van Dorn molding machine with a set temperature of approximately 240°C to 265°C. The pellets were dried for 3 to 4 hours at 120 °C in a forced air-circulating oven before injection molding.

[00103] Un-notched Izod Testing/Flexural Testing/Flame Testing. Un-notched Izod testing was performed on 75 mm x 12.5 mm x 3.2 mm bars in accordance with ASTM D256. Flexural properties were measured in accordance with ASTM 790 on molded samples having a thickness of 3.2 mm. Flame testing per UL 94 protocol was conducted on flame bars with 0.80 mm thickness after both 23°C/48 hr and 70°C/168 hr aging conditions.

[00104] CTI Testing Procedures. CTI was used to measure the electrical breakdown (tracking) properties of the test material. In order to test for CTI, a specimen (2.54 cm diameter disk or larger) was molded from the pellets and placed on a support. Two electrodes, 4 mm apart, touched the specimen surface. A solution of 0.1% ammonium chloride electrolyte solution was introduced via a syringe. One drop fell every 30 seconds on the surface between the electrodes. The test proceeded by setting the electrodes to a fixed applied voltage between 100 volts to 600 volts, and turning the syringe pump on. The voltage that caused failure at 50 drops of electrolytes was selected as a measure of susceptibility of a material to tracking. Interpolation was used if necessary to obtain this voltage. Performance Level Categories (PLC) were used to avoid excessive implied precision and bias. The relationship between tracking index voltage and PLC is shown in Table 2.

Table 2. Relationship between tracking index and PLC

Tracking Index (V)	PLC Rating
600 and Greater	0
400 through 599	1
250 through 399	2
175 through 249	3
100 through 174	4
< 100	5

EXAMPLES 1-8; COMPARATIVE EXAMPLES 1-2

[00104] The purpose of Examples 1-8 was to make a glass-filled, chlorine and bromine-free poly(alkylene) ester composition containing a combination of elastomers and evaluate their performance with regard to the following properties: (i) flame retardance performance (i.e., V0 at 0.80 mm), (ii) CTI performance, (iii) impact properties and (iv) flexural properties. These compositions were evaluated to determine whether they certain minimum targeted performance properties, namely: (a) a flexural modulus greater than 9800 MPa, (b) a flexural stress greater than 150 MPa, (c) an unnotched impact strength greater than 470 Joules/meter, and (d) a rating of V0 at a thickness of 0.8 mm, measured in accordance with the UL 94 protocol.

[00105] The purpose of Comparative Examples 1-2 was compare the performance properties of the compositions of Examples 1-8 with (i) a glass-filled, chlorine and bromine-free poly(alkylene ester) flame retardant composition that contained polyimide but no elastomers (Comparative Example 1) and (ii) a glass-filled, chlorine and bromine-free poly(alkylene ester) flame retardant composition that contained no polyimide and no elastomers (Comparative Example 2).

[00106] Examples were prepared and tested as described above. The results for Examples 1-8 are summarized in Table 3 and the results for Comparative Examples 1-2 are summarized in Table 4.

Table 3. Formulation and physical properties of 30% glass-filled, chlorine- and bromine-free, flame retardant poly(alkylene ester) compositions (Examples 1 to 8)

Component	Unit	Targeted Performance	E1	E2	E3	E4	E5	E6	E7	E8
VALOX iQ PBT-1	%		24.83	24.83	24.83	24.58	24.58	24.58	25.58	25.33
VALOX iQ PBT-2	%		24.83	24.83	24.83	24.58	24.58	24.58	25.58	25.33
Glass Fiber	%		30.00	30.00	30.00	30.00	30.00	30.00	30.00	30.00
MPP	%		5.00	5.00	5.00	5.00	5.00	5.00	5.00	5.00
Al-DPA	%		12.50	12.50	12.50	12.50	12.50	12.50	11.00	11.00
TSAN	%		0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50
AO	%		0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.15
PETS	%		0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20
ULTRATALC	%									0.50
PEI (ULTEM 1010)	%									
VALOX iQ Elastomer Resin	%				1.50		1.25	1.88	1.50	1.50
HYTREL	%		1.00	1.50		1.88				
PARALOID EXL	%		1.00	0.50	0.50	0.63	1.25	0.63	0.50	0.50
EEA	%									
IGETABOND E	%									
LOTADER	%									
			100	100	100	100	100	100	100	100
Test Description	Unit		E1	E2	E3	E4	E5	E6	E7	E8
Flexural Modulus	MPa	>9800	9935	9955	10030	10300	10500	10400	9990	9820
Flexural Stress at Break	MPa	>150	157	158	154	157	160	154	158	157
Izod Impact strength, Un-Notched	J/m	>470	493	505	486	518	499	474	476	568
Flame Rating - UL 94, 23°C/48 hr	0.80 mm	V0	V0	V0	V0	V0	V0	V0	V0	V0
Flame Rating - UL 94, 70°C/168 hr	0.80 mm	V0	V0	V0	V0	V0	V0	V0	V0	V0
CTI (100)	V		600	600	600	-	-	-	600	600
CTI PLC Rating			0	0	0	-	-	-	0	0

Table 4. Formulation and physical properties of glass-filled, chlorine- and bromine-free, flame retardant poly(alkylene ester) compositions (Comparative Examples 1 to 2)

Component	Unit	Targeted Performance	CE1	CE2
VALOX iQ PBT-1	%		25.83	25.83
VALOX iQ PBT-2	%		25.83	25.83
Glass Fiber	%		25.00	30.00
MPP	%		5.00	5.00
AI-DPA	%		12.50	12.50
TSAN	%		0.50	0.50
AO	%		0.15	0.15
PETS	%		0.20	0.20
ULTRATALC	%			
PEI (ULTEM 1010)	%		5.00	
VALOX iQ Elastomer Resin	%			
HYTREL	%			
PARALOID EXL	%			
EEA	%			
IGETABOND E	%			
LOTADER	%			
			100	100
Test Description	Unit		CE1	CE2
Flexural Modulus	MPa	>9800	9670	10100
Flexural Stress at Break	MPa	>150	160	150
Izod Impact strength, Un-Notched	J/m	>470	432	410
Flame Rating - UL 94, 23°C/48 hr	0.80 mm	V0	V0	V0
Flame Rating - UL 94, 70°C/168 hr	0.80 mm	V0	V0	V0
CTI (100)	V		250	-
CTI PLC Rating			2	-

[00107] The results shown in Tables 3 and 4 indicate that it is possible to make a glass-filled, chlorine- and bromine-free poly(alkylene ester) flame retardant composition containing a combination of elastomers with useful properties, namely, good flame retardance performance (i.e., a rating of V0 at 0.80 mm), higher CTI performance, improved impact properties and improved flexural properties, as compared to a glass-filled, chlorine and bromine-free poly(alkylene ester) flame retardant composition that contains polyimide but no elastomers. More particularly, the results of Examples 1-8 showed that the inventive compositions meet the minimum targeted performance properties, namely: (a) a flexural modulus greater than 9800 MPa, (b) a flexural stress greater than 150 MPa, (c) an unnotched impact strength greater than 470 Joules/meter, and (d) a rating of V0 at a thickness of 0.8 mm, measured in accordance with the UL 94 protocol. The compositions of Comparative Examples 1-2 did not meet these properties.

[00108] It can be seen that in Examples E1 to E8 in Table 3, when no ULTEM 1010 was present in the formulations and glass fiber content was 30%, the addition of combinations of elastomers (HYTREL/VALOX iQ Elastomer and PARALOID EXL) at a 2 wt% level (E1 (1% HYTREL and 1% PARALOID EXL), E2 (1.5% HYTREL and 0.5% PARALOID EXL) and E3, E7, and E8 (1.5% VALOX iQ Elastomer and 0.5% PARALOID EXL)) and 2.5 wt% level (E4 (1.88% HYTREL and 0.63% PARALOID EXL), E5 (1.25% VALOX iQ Elastomer and 1.25% PARALOID EXL), and E6 (1.88% VALOX iQ Elastomer and 0.63% PARALOID EXL)) can improve mechanical properties such as unnotched Izod impact strength by at least 8.8%, while maintaining flame retardance performance (V0 at 0.8 mm) per UL 94, compared with CE1. Furthermore, the CTIs of E1, E2, E3, E7, and E8 are also in much higher voltages than CE1: 600 V for E1, E2, E3, E7, and E8 as compared to 250 V for CE1. This is equivalent to a 2 PLC rating increase. Furthermore, when less Al-DPA was used in E7 and E8 (11%) as compared with in CE1 (12.5%), a UL 94 V0 rating at 0.80 mm was still achieved. Especially in E8, where 0.5% ULTRATALC is present in the formulation, the unnotched impact strength (568 J/m) was largely improved from the 438 J/m observed for CE1, as well as the 476 J/m of E7.

[00109] As shown in the comparative examples (Table 4), CE1 was a 25 wt% glass and 5 wt% polyimide (ULTEM 1010)-filled, chlorine- and bromine-free poly(alkylene ester) flame retardant composition. CE2 was a 30 wt% glass-filled, chlorine- and bromine-free poly(alkylene ester) flame retardant composition with no polyimide (ULTEM 1010). When the 5 wt% ULTEM 1010 in CE1 was replaced with 5 wt% glass in CE2, the unnotched Izod impact strength of the formulation dropped by 5% (from 432 to 410 J/m), even though the same V0 rating was achieved. The low impact strength of CE2 limits its use in applications such as electrical connectors and computer fans.

COMPARATIVE EXAMPLES 3-25

[00110] The purpose of Comparative Examples 3-25 was to compare the performance of compositions containing a single elastomer with compositions having a combination of elastomers, as well as the performance of compositions containing a combination of elastomers in amounts outside the inventive ranges.

[00111] Examples were prepared and tested as described above. The results for Comparative Examples CE3-CE25 are shown in Tables 5, 6, and 7.

Table 5. Formulation and physical properties of glass-filled, chlorine- and bromine-free, flame retardant poly(alkylene ester) compositions (Comparative Example 3 to 12)

Component	Unit	Targeted Properties	CE3	CE4	CE5	CE6	CE7	CE8	CE9	CE10	CE11	CE12
VALOX iQ PBT-1	%		23.33	23.33	23.33	23.33	23.33	23.33	23.33	23.33	23.33	23.83
VALOX iQ PBT-2	%		23.33	23.33	23.33	23.33	23.33	23.33	23.33	23.33	23.33	23.83
Glass Fiber	%		30.00	30.00	30.00	30.00	30.00	30.00	30.00	30.00	30.00	30.00
MPP	%		5.00	5.00	5.00	5.00	5.00	5.00	5.00	5.00	5.00	5.00
Al-DPA	%		12.50	12.50	12.50	12.50	12.50	12.50	12.50	12.50	12.50	11.00
TSAN	%		0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50
AO	%		0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.15
PETS	%		0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20
ULTRATALC	%		-	-	-	-	-	-	-	-	-	0.50
PEI (ULTEM 1010)	%		-	-	-	-	-	-	-	-	-	-
VALOX iQ Elastomer Resin	%		-	-	-	-	-	-	-	2.50	3.75	3.75
HYTREL	%		5.00	-	-	-	-	2.50	3.75	-	-	-
PARALOID EXL	%		-	5.00	-	-	-	2.50	1.25	2.50	1.25	1.25
EEA	%		-	-	5.00	-	-	-	-	-	-	-
IGETABOND E	%		-	-	-	5.00	-	-	-	-	-	-
LOTADER	%		-	-	-	-	5.00	-	-	-	-	-
			100	100	100	100	100	100	100	100	100	100
Test Description	Unit		CE3	CE4	CE5	CE6	CE7	CE8	CE9	CE10	CE11	CE12
Flexural Modulus	MPa	>9800	8570	9420	8820	8610	8370	9840	9700	9810	9420	9410
Flexural Stress at Break	MPa	>150	119	137	126	143	138	147	144	146	142	147
Izod Impact strength, Un-Notched	J/m	>470	442	398	412	461	452	464	482	529	557	494
Flame Rating - UL 94, 23°C/48 hr	0.80 mm	V0	V0	V0	V0	V0	V0	V0	V0	V0	V0	V0
Flame Rating - UL 94, 70°C/168 hr	0.80 mm	V0	V0	V0	V0	V1	V1	V0	V0	V0	V0	V2
CTI (100)	V		-	-	-	-	-	-	-	-	-	-
CTI PLC Rating			-	-	-	-	-	-	-	-	-	-

Table 6. Formulation and physical properties of glass-filled, chlorine- and bromine-free, flame retardant poly(alkylene ester) compositions (Comparative Example 13 to 19)

Component	Unit	Targeted Properties	CE13	CE14	CE15	CE16	CE17	CE18	CE19
VALOX iQ PBT-1	%		24.58	24.58	24.58	24.58	24.58	24.58	25.08
VALOX iQ PBT-2	%		24.58	24.58	24.58	24.58	24.58	24.58	25.08
Glass Fiber	%		30.00	30.00	30.00	30.00	30.00	30.00	30.00
MPP	%		5.00	5.00	5.00	5.00	5.00	5.00	5.00
AI-DPA	%		12.50	12.50	12.50	12.50	12.50	12.50	11.00
TSAN	%		0.50	0.50	0.50	0.50	0.50	0.50	0.50
AO	%		0.15	0.15	0.15	0.15	0.15	0.15	0.15
PETS	%		0.20	0.20	0.20	0.20	0.20	0.20	0.20
ULTRATALC	%								0.50
PEI (ULTEM 1010)	%								
VALOX iQ Elastomer Resin	%								1.88
HYTREL	%		2.50					1.25	
PARALOID EXL	%			2.50				1.25	0.63
EEA	%				2.50				
IGETABOND E	%					2.50			
LOTADER	%						2.50		
			100	100	100	100	100	100	100
Test Description	Unit		CE13	CE14	CE15	CE16	CE17	CE18	CE19
Flexural Modulus	MPa	>9800	6460	9600	9250	9370	9190	10600	9860
Flexural Stress at Break	MPa	>150	110	141	133	148	147	150	155
Izod Impact strength, Un-Notched, 23°C	J/m	>470	420	442	371	471	470	447	506
Flame Rating - UL 94, 23°C/48 hr	0.80 mm	V0	V0	V0	V0	V0	V1	V0	V0
Flame Rating - UL 94, 70°C/168 hr	0.80 mm	V0	V0	V0	V0	V1	V1	V0	V2
CTI (100)	V		-	-	-	-	-	-	-
CTI PLC Rating			-	-	-	-	-	-	-

Table 7. Formulation and physical properties of glass-filled, chlorine- and bromine-free, flame retardant poly(alkylene ester) compositions (Comparative Example 20 to 25)

Component	Unit	Targeted Properties	CE20	CE21	CE22	CE23	CE24	CE25
VALOX iQ PBT-1	%		24.83	24.83	25.83	25.58	25.20	25.20
VALOX iQ PBT-2	%		24.83	24.83	25.83	25.58	25.20	25.20
Glass Fiber	%		30.00	30.00	30.00	30.00	30.00	30.00
MPP	%		5.00	5.00	5.00	5.00	5.00	5.00
Al-DPA	%		12.50	12.50	10.50	10.50	12.50	12.50
TSAN	%		0.50	0.50	0.50	0.50	0.50	0.50
AO	%		0.15	0.15	0.15	0.15	0.15	0.15
PETS	%		0.20	0.20	0.20	0.20	0.20	0.20
ULTRATALC	%					0.50		
PEI (ULTEM 1010)	%							
VALOX iQ Elastomer Resin	%				1.50	1.50		
HYTREL	%		2.00				1.25	
PARALOID EXL	%			2.00	0.50	0.50		1.25
EEA	%							
IGETABOND E	%							
LOTADER	%							
			100	100	100	100	100	100
Test Description	Unit		CE20	CE21	CE22	CE23	CE24	CE25
Flexural Modulus	MPa	>9800	9530	9760	10100	10200	8950	10200
Flexural Stress at Break	MPa	>150	153	156	161	164	143	154
Izod impact strength, Unnotched, 23°C	J/m	>470	531	417	508	561	429	466
Flame Rating, UL 94, 23°C/48 hr	0.80 mm	V0	V0	V0	V0	V0	V0	V0
Flame Rating, UL 94, 70°C/168 hr	0.80 mm	V0	V2	V1	V1	V0	V0	V0
CTI (100)	V		-	-	600	550	-	-
CTI PLC Rating			-	-	0	1	-	-

[001 12] The results shown in Tables 5, 6, and 7 (Comparative Examples 3-25) illustrate that use of a single elastomer, or two elastomers outside of a relatively narrow range did not meet the minimum targeted performance properties; namely these compositions did not exhibit the following combination of properties: (a) a flexural modulus greater than 9800 MPa, (b) a flexural stress greater than 150 MPa, (c) an unnotched impact strength greater than 470 Joules/meter, and (d) a rating of V0 at a thickness of 0.8 mm, measured in accordance with the UL 94 protocol. The compositions of Comparative Examples 1-2 did not meet these properties.

[001 13] As shown in Table 5, when impact modifiers including ELVALOY, IGETABOND, LOTADER, HYTREL, and PARALOID EXL were used individually at a level of 5 wt%, the 30 wt% glass-filled, chlorine- and bromine-free poly(alkylene ester)

flame retardant formulations (CE3 to CE7) showed some disadvantages such as in low flexural modulus, low flexural stress at break, and low unnotched Izod impact strength. In CE6 and CE7, flame retardance performance was rated as VI. In CE8 to CE12, where the addition of combinations of elastomers (HYTREL VALOX iQ Elastomer and PARALOID EXL) at a level of 5 wt% was used, flexural stress at break was still less desirable, i.e., less than 150 MPa. In CE12, where 11% Al-DPA was used, the UL 94 rating at 0.80 mm was VI.

[001 14] As shown in Table 6, when impact modifiers including ELVALOY, IGETABOND, LOTADER, HYTREL and PARALOID EXL were used individually at a level of 2.5 wt%, the 30% glass-filled, chlorine- and bromine-free poly(alkylene ester) formulations (CE13 to CE17) showed some disadvantages such as in low flexural modulus, low flexural stress at break, and in some cases, low un-notched Izod impact strength. In CE16 and CE17, flame retardance performance was rated as VI. In CE18, where the addition of combinations of elastomers (1.25% HYTREL and 1.25% PARALOID EXL) at a level of 2.5 wt% was used, flexural stress at break is still less desirable, i.e., less than 150 MPa. In CE19, where 11% Al-DPA was used, the UL 94 rating at 0.80 mm was V2.

[001 15] As shown in Table 7, when impact modifiers including HYTREL and PARALOID EXL were used individually at a level of 2.0 wt%, the 30% glass-filled, chlorine- and bromine-free poly(alkylene ester) formulations (CE20 and CE21) showed some disadvantages such as in low flexural modulus and failure to meet V0 flame retardance at 0.80 mm. When impact modifiers including HYTREL and PARALOID EXL were used individually at a level of 1.25 wt%, the 30% glass-filled, chlorine- and bromine-free poly(alkylene ester) flame retardant formulations (CE24 and CE25) showed some disadvantages such as low flexural modulus (CE24) and low unnotched Izod impact strength, i.e., less than 470 J/m. In CE22 to CE23, containing 2 wt% of a combination of elastomers (1.50% VALOX iQ Elastomer and 0.5% PARALOID EXL) and 10.5 wt% of Al-DPA, the formulations showed either insufficient UL 94 rating (CE22) or less desirable CTI voltage, i.e., less than 600V (CE23).

[001 16] All references cited herein are incorporated by reference in their entirety. While the invention has been described with reference to a preferred embodiment, it will be understood by those skilled in the art that various changes can be made and equivalents can be substituted for elements thereof without departing from the scope of the invention. In addition, many modifications can be made to adapt a particular situation or material to the teachings of the invention without departing from essential scope thereof. Therefore, it is

intended that the invention not be limited to the particular embodiment disclosed as the best mode contemplated for carrying out this invention, but that the invention will include all embodiments falling within the scope of the appended claims.

CLAIMS

1. A thermoplastic polyester composition comprising, based on the total weight of the composition, a chlorine- and bromine-free combination of:


(a) from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate) that (1) is derived from a poly(ethylene terephthalate) component selected from the group consisting of a poly(ethylene terephthalate), a poly(ethylene terephthalate) copolymer, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component;

(b) from 25 to 35 wt% of a reinforcing filler;

(c) from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof;

(d) from 5 to 15 wt% of a phosphorous flame retardant comprising:

a phosphinate of formula (I)



a diphosphate of formula (II)



a polymer derived from the phosphinate of formula (I) or the diphosphate of the formula (II),

wherein R^1 and R^2 are each independently the same or different, and are H, linear or branched C_1 - C_6 alkyl, or C_6 - C_{10} aryl; R^3 is C_1 - C_{10} , linear or branched alkylene, C_6 - C_{10} arylene, C_7 - C_n alkylarylene, or C_7 - C_n arylalkylene; M is an alkaline earth metal, alkali metal, Al, Ti, Zn, Fe, or B; m is 1, 2, 3 or 4; n is 1, 2, or 3; and x is 1 or 2;


(e) from more than 0 to less than 5 wt% of an impact modifier component comprising a poly(ether-ester) elastomer and a (meth)acrylate impact modifier;

(f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; and


(g) from more than 0 to 2 wt% of a stabilizer;

wherein the thermoplastic polyester composition contains less than 5 wt% of a polyetherimide.

2. The thermoplastic polyester composition of Claim 1, wherein the poly(ether-ester) elastomer comprises long-chain ester units of formula (III):



and short-chain ester units having units of formula (IV):



wherein R' is a divalent aromatic radical remaining after removal of carboxyl groups from terephthalic acid, isophthalic acid, or a combination of terephthalic acid and isophthalic acid; G is a divalent polyalkylene oxide radical remaining after removal of terminal hydroxyl groups from a poly(alkylene oxide) glycol having a number-average molecular weight of 100 to 2500 Daltons; and D is the divalent alkylene radical remaining after removal of hydroxyl groups from an aliphatic diol having a molecular weight from 62 to 286.

3. The thermoplastic polyester composition of any of Claims 1-2, wherein the poly(ether-ester) elastomer is a poly(butylene terephthalate-polytetrahydrofuran) block copolymer.

4. The thermoplastic polyester composition of any of Claims 1-3, wherein the (meth)acrylate impact modifier is a core-shell (meth)acrylate impact modifier having a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell.

5. The thermoplastic polyester composition of any of Claims 1-4, wherein the phosphorus flame retardant is present in an amount ranging from 11 to 12.5 wt%.

6. The thermoplastic polyester composition of any of Claims 1-5, wherein the impact modifier is present in an amount ranging from 2 to 2.5 wt%.

7. The thermoplastic polyester composition of any of Claims 1-6, wherein the composition contains no polyetherimide, and an article extruded from the composition exhibits a CTI (Comparative Tracking Index) of 600 volts.

8. The thermoplastic polyester composition of **any of Claims 1-7**, wherein the flame retardant comprises the phosphinate of formula (I).

9. The thermoplastic polyester composition of **any of Claims 1-8**, wherein the phosphinate of formula (I), the diphosphinate of formula (II), and/or a polymer thereof is present in an amount from more than 10 to 15 wt%, based on the total weight of the composition.

10. An article comprising the thermoplastic polyester composition of any of Claims 1-9.

11. The article of Claim 10, wherein the article is selected from the group consisting of computer fans, electrical connectors, automotive battery housings, and lighting sockets.

12. A thermoplastic polyester composition comprising, based on the weight of the composition, a chlorine- and bromine-free combination of:

(a) from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate) that (1) is derived from a poly(ethylene terephthalate) component selected from the group consisting of a poly(ethylene terephthalate), a poly(ethylene terephthalate) copolymer, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component;

(b) from 25 to 35 wt% of a glass fiber filler;

(c) from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof;

(d) from more than 10 to 15 wt% a phosphinate of formula (I)



a diphosphate of formula (II)




a polymer derived from the phosphinate of formula (I) or the diphosphate of the formula (II),


wherein R^1 and R^2 are identical or different and are H, linear or branched C_1 - C_6 alkyl, or C_6 - C_{10} aryl; R^3 is C_1 - C_{10} , linear or branched alkylene, C_6 - C_{10} arylene, C_7 - C_{11} alkylarylene, or C_7 - C_n arylalkylene; M is an alkaline earth metal, alkali metal, Al, Ti, Zn, Fe, or B; m is 1, 2, 3 or 4; n is 1, 2, or 3; and x is 1 or 2;

(e) at least 1 % to less than 5 weight % of impact modifier component comprising a combination of (i) a poly(ether-ester) elastomer and (ii) a core-shell (meth)acrylate impact modifier;

wherein the poly(ether-ester) elastomer comprises long-chain ester units of formula (HI):



and short-chain ester units having units of formula (IV):



wherein R' is a divalent aromatic radical remaining after removal of carboxyl groups from terephthalic acid, isophthalic acid, or a combination of terephthalic acid and isophthalic acid; G is a divalent polyalkylene oxide radical remaining after removal of terminal hydroxyl groups from a poly(alkylene oxide) glycol having a number-average molecular weight of 100 to 2500; and D is a divalent alkylene radical remaining after removal of hydroxyl groups from aliphatic diols having a molecular weight from 62 to 286; and

wherein the core-shell meth(acrylate) impact modifier has a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell;

(f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; and

(g) from more than 0 wt% to 2 wt% of a stabilizer;

wherein the halogen free composition contains less than 5 wt% of a polyetherimide; and

wherein an article molded from the composition exhibits

(a) a flexural modulus that is more than 9800 MPa,

(b) a flexural stress that is more than 150 MPa,

(c) an unnotched impact strength that is more than 470 Joules/meter, and

(d) a V0 rating at 0.8 mm, measured in accordance with UL 94.

13. An article comprising the thermoplastic polyester composition of Claim 12.

14. The article of Claim 13, wherein the article is selected from the group consisting of computer fans, electrical connectors, automotive battery housings, and lighting sockets.


15. A thermoplastic polyester composition comprising, based on the weight of the composition, a halogen-free combination of:

(a) from 40 to 60 wt% of a modified poly(1,4-butylene terephthalate) that (1) is derived from a poly(ethylene terephthalate) component selected from the group consisting of a poly(ethylene terephthalate), a poly(ethylene terephthalate) copolymer, and a combination thereof, and (2) has at least one residue derived from the poly(ethylene terephthalate) component;

(b) from 25 to 35 wt% glass fiber filler;

(c) from 2 to 8 wt% of a flame retardant synergist selected from the group consisting of melamine polyphosphate, melamine cyanurate, melamine pyrophosphate, melamine phosphate, and combinations thereof;

(d) from more than 10 to 15 wt% a phosphinate of formula (I)



a diphosphinate of formula (II)



a polymer derived from the phosphinate of formula (I) or the diphosphinate of the formula (II),

wherein R^1 and R^2 are identical or different and are H, or linear or branched $Ci-C_6$ alkyl; R^3 is $Ci-C_{10}$, linear or branched alkylene; M is aluminum; m is 3; n is 3; and x is 1 or 2;

(e) at least 1 to less than 5 wt% of impact modifier component comprising a combination of (i) a poly(butylene terephthalate-polytetrahydrofuran) block copolymer and (ii) a core-shell (meth)acrylate impact modifier having a crosslinked poly(butyl acrylate) core with a grafted poly(methyl methacrylate) shell;

(f) from more than 0 to 5 wt% poly(tetrafluoroethylene) encapsulated by a styrene-acrylonitrile copolymer; and

(g) from more than 0 wt% to 2 wt% of a stabilizer;

wherein the halogen free composition contains less than 2 wt% of a polyetherimide; and

wherein an article molded from the composition exhibits

- (a) a flexural modulus that is more than 9800 MPa,
- (b) a flexural stress is more than 150 MPa,
- (c) an unnotched impact strength that is more than 470 Joules/meter, and
- (d) a V0 rating at 0.8 mm, measured in accordance with UL 94.

16. An article comprising the composition of Claim 15.

17. The article of Claim 16, wherein the article is selected from the group consisting of computer fans, electrical connectors, automotive battery housings, and lighting sockets.

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2011/042143

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08L67/02

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal , WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	wo 2008/154600 A2 (SABIC INNOVATIVE PLASTICS I P [NL] ; BORADE PRAVIN KAMLAKAR [IN] ; GALLUC) 18 December 2008 (2008-12-18) claims example 20; tabl e 7 -----	1-17



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 September 2011

Date of mailing of the international search report

21/09/2011

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Schl i cke, Benedi kt

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2011/042143

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2008154600 A2	18-12-2008	US 2008139711 A1	12-06-2008